

AD No. 16 276
ASTIA FILE COPY

OFFICE OF NAVAL RESEARCH

Contract N7onr-35801

T. O. I.

NR-041-032

Technical Report No. 95

THREE-DIMENSIONAL PLASTIC FLOW UNDER UNIFORM STRESS

by

William Prager

GRADUATE DIVISION OF APPLIED MATHEMATICS

BROWN UNIVERSITY

PROVIDENCE, R. I.

August 1953

THREE-DIMENSIONAL PLASTIC FLOW UNDER UNIFORM STRESS*

by

William Prager
Brown University, Providence, R. I., U.S.A.

Abstract. In view of the role that regions of uniform stress play in the theory of plane plastic flow, the most general velocity field is investigated that is possible under a uniform state of stress at the yield limit. Two cases are distinguished according to whether all principal components of the stress deviation are different from zero ("regular case") or not ("degenerate case"). The analytical description of the velocity field involves two arbitrary functions in the degenerate case but no such functions in the regular case.

1. Introduction. The theory of the slip line field in plane plastic flow is one of the best developed branches of the mathematical theory of perfectly plastic solids. Among the problems that have been solved in this field, those involving rectilinear boundaries are predominant. In many of these problems, the slip line field contains finite regions of uniform stress. The most general velocity field possible in such a region is obtained by the superposition of two arbitrary shear flows in the directions of the maximum shearing stresses. The analytical description of this velocity field involves two arbitrary functions of one variable each.

Whereas fields of plane plastic flow have been studied systematically (see, for instance, Ref. 1, Chaps. 6-9, or Ref. 2, Chaps. 5-7), three-dimensional plastic flow is practically unexplored. Finzi (Ref. 3) and Thomas (Ref. 4) obtained some general

*The results presented in this paper were obtained in the course of research conducted under Contract N7onr-35801 between the Office of Naval Research and Brown University.

results, but did not construct examples of three-dimensional flows. De Simoni (Ref. 5) attempted to construct a three-dimensional plastic flow field, but closer inspection of his example reveals this to be a field of plane flow referred to coordinate axes that are oblique to the plane of flow. A non-trivial and genuinely three-dimensional field of plastic flow is found in a paper by Hill (Ref. 6). This flow field describes the incipient plastic flow in a prismatic bar made of a plastic rigid material and subjected to combined tension, torsion, and bending. The equations for the velocity components (Ref. 6, Eqs. 17) contain an unknown function, however, and the non-linear differential equation for this function has not yet been solved. When this function is set equal to zero and the necessary adjustment of constants is made, Hill's flow field reduces to a special case of the "regular" field discussed in the present paper.

In view of the role that regions of uniform stress play in the theory of plane plastic flow, it seems worthwhile to investigate the most general three-dimensional flow field that is possible under a uniform state of stress at the yield limit. It will be seen that, contrary to what is the case for plane flow, the analytical description of the most general three-dimensional flow field possible under uniform stress does not, in general, involve any arbitrary functions.

2. Fundamental equations. Choose the rectangular axes X , Y , and Z , in the principal directions of the uniform stress field and denote the given principal components of the stress deviation by K , L , and M , and the unknown velocity components by

U, V, and W. According to Mises' theory of plasticity (Ref. 7), the components of the velocity strain at a generic point are proportional to the components of the stress deviation at this point, the non-negative factor of proportionality being a function of position. Applied to the present case, this flow rule leads to the following equations in which subscripts denote differentiation with respect to the coordinates:

$$U_X = \lambda K, \quad V_Y = \lambda L, \quad W_Z = \lambda M; \quad (1)$$

$$U_Y + V_X = 0, \quad V_Z + W_Y = 0, \quad W_X + U_Z = 0. \quad (2)$$

In these equations, λ denotes the non-negative factor of proportionality.

Since K, L, and M, are constants, elimination of the velocity components between Eqs. (1) and (2) leads to the following differential equations for the unknown function λ :

$$K\lambda_{YY} + L\lambda_{XX} = 0, \quad L\lambda_{ZZ} + M\lambda_{YY} = 0, \quad M\lambda_{XX} + K\lambda_{ZZ} = 0; \quad (3)$$

$$K\lambda_{YZ} = 0, \quad L\lambda_{ZX} = 0, \quad M\lambda_{XY} = 0. \quad (4)$$

These are the equations of compatibility (see, for instance, Ref. 8, p. 27, Eqs. 10,10) for the components of the velocity strain when these are expressed in terms of the components of the stress deviation and the factor λ .

In discussing Eqs. (3) and (4), we must keep in mind that K, L, and M, are the principal components of the stress deviation. Accordingly,

$$K + L + M = 0. \quad (5)$$

The following two cases must be discussed separately.

- 1) None of the quantities K , L , and M , vanishes. Equations (3) then yield

$$\lambda_{XX} = \lambda_{YY} = \lambda_{ZZ} = 0. \quad (6)$$

This will be called the regular case.

- 2) One of the quantities K , L , and M , vanishes. If, for instance, $M = 0$, we have $L = -K$, by (5), and Eqs. (3) and (4) furnish

$$\lambda_{XX} - \lambda_{YY} = 0, \quad \lambda_{ZZ} = 0; \quad (7)$$

$$\lambda_{YZ} = 0, \quad \lambda_{ZX} = 0. \quad (8)$$

This will be called the degenerate case.

For the regular case, Eqs. (4) and (5) yield

$$\lambda = AX + BY + CZ + D, \quad (9)$$

where A , B , C , and D , are arbitrary constants. For the singular case, it follows from Eqs. (7) and (8) that λ has the form

$$\lambda = f(X + Y) + g(X - Y) + CZ, \quad (10)$$

where C again denotes an arbitrary constant.

3. Regular velocity fields. With λ as given by Eq. (9), integration of Eqs. (1) and (2) will yield a velocity field that is compatible with the considered uniform stress field. Since λ is non-negative, however, such a velocity field can be constructed only in the half-space in which the right-hand side of (9) is

non-negative. The following analysis is simplified by the introduction of new rectangular coordinates x , y , and z , that are chosen so that this half-space corresponds to $z \geq 0$.

Let k , l , and m , and p , q , and r , be the normal and shear components of the stress deviation with respect to the new coordinate axes, and u , v , and w , the components of the velocity. Equations (1) and (2) must now be replaced by

$$u_x = \lambda k, \quad v_y = \lambda l, \quad w_z = \lambda m; \quad (11)$$

$$u_y + v_x = 2\lambda p, \quad v_z + w_y = 2\lambda q, \quad w_x + u_z = 2\lambda r, \quad (12)$$

where

$$\lambda = cz, \quad (c > 0). \quad (13)$$

To within a velocity field that corresponds to a rigid body motion, the most general velocity field compatible with these equations is given by

$$\left. \begin{aligned} u &= c(kxz + pyz + rz^2), \\ v &= c(pxz + lyz + qz^2) \\ w &= -\frac{1}{2} c(kx^2 + ly^2 + 2pxy - mz^2). \end{aligned} \right\} (z > 0) \quad (14)$$

This velocity field involves no arbitrary functions, in fact no arbitrary constants other than c .

For given values of the components of the stress deviation, the velocity field (14) is valid only in $z \geq 0$. Under certain conditions, it is possible, however, to continue this field into $z < 0$ by admitting different uniform states of stress on the two sides of the plane $z = 0$. We use the prime to distinguish

quantities in $z < 0$ from the corresponding quantities in $z > 0$. Since λ cannot be negative, the constant c' must be negative. If the velocity field (14) is to be valid throughout space, we must therefore set $k' = -k$, $l' = -l$, ... , $r' = -r$. Equilibrium between the tractions transmitted across $z = 0$ requires, however, that $q' = q$, $r' = r$. There is no such condition for m and m' because the normal stresses in the z direction are obtained by adding, to m and m' , the respective mean normal stresses which do not appear elsewhere in our analysis. It follows from the preceding discussion that

$$q = q' = r = r' = 0. \quad (15)$$

With this restriction, the velocity field (14) can be continued into $z < 0$. The plane $z = 0$ is then a discontinuity surface of the stress field (for a discussion of such discontinuity surfaces see Ref. 9). The application of this type of stress and velocity fields to a plastic plate under uniform bending and twisting moments is obvious.

4. Degenerate velocity fields. With λ as given by Eq. (10), integration of Eqs. (1) and (2) yields the following result: to within a velocity field that corresponds to a rigid body motion, the most general velocity field possible in the degenerate case is given by

$$\begin{aligned} U &= K [F(X + Y) + G(X - Y) + CXZ], \\ V &= -K[F(X + Y) - G(X - Y) + CYZ], \\ W &= -\frac{1}{2} CK(X^2 - Y^2), \end{aligned} \quad (16)$$

where the functions F and G have as derivatives the functions f and g appearing in (10). This velocity field is, of course, restricted to the region in which λ as given by Eq. (10) is non-negative.

The known results for plane plastic flow under constant stress are obtained from (16) by setting $C = 0$. The general degenerate field (16) results from the superposition of the field of plane plastic flow represented by the functions F and G , and the field represented by the terms with C in Eqs. (16). The velocities of the latter field tend to tilt the planes $X = \text{const.}$ or $Y = \text{const.}$ about their intersections with the plane $Z = 0$ and to transform the planes $Z = \text{const.}$ into congruent hyperbolic paraboloids.

REFERENCES

1. R. Hill, The mathematical theory of plasticity, Clarendon Press, Oxford, 1950.
2. W. Prager and P. G. Hodge, Jr., Theory of perfectly plastic solids, Wiley, New York, 1951.
3. B. Finzi, Atti Acc. Sc. Torino 76, 222-238 (1941).
4. T. Y. Thomas, J. Rat. Mech. Analysis 1, 343-357 (1952), and 2, 339-381 (1953).
5. F. De Simoni, Ist. Lombardo Sci. Lett., Rendiconti Cl. Sci. Mat. Nat. (3) 15, 623-634 (1951).
6. R. Hill, Quart. J. Mech. Appl. Math. 1, 18-28 (1948).
7. R. v. Mises, Goettinger Nachr., math. phys. Kl. 1913, 582-592 (1913).
8. I. S. Sokolnikoff, Mathematical theory of elasticity, McGraw-Hill, New York, 1946.
9. W. Prager, Courant Anniversary Volume, Interscience Publishers, New York, 1948, pp. 289-299.

APPROVED DISTRIBUTION LIST FOR UNCLASSIFIED TECHNICAL REPORTS

Issued by

BROWN UNIVERSITY
Contract N7onr-358, T. O. 1
NR O+1 032

Office of Naval Research
Washington 25, D. C.

M-2 Attn: Mathematics Branch (Code 432)
M-1 Mechanics Branch (Code 438)
M-1 Physical Branch (Code 421)
M-1 Metallurgy Branch (Code 423)

M-2 Commanding Officer
Office of Naval Research Branch Office
150 Causeway Street
Boston 14, Massachusetts

M-1 Commanding Officer
Office of Naval Research Branch Office
346 Broadway
New York, New York

M-1 Commanding Officer
Office of Naval Research Branch Office
844 North Rush Street
Chicago 11, Illinois

M-1 Commanding Officer
Office of Naval Research Branch Office
1000 Geary Street
San Francisco 9, California

M-1 Commanding Officer
Office of Naval Research Branch Office
1030 East Green Street
Pasadena 1, California

M-17 Officer-in-Charge
Office of Naval Research
Navy #100
Fleet Post Office
New York, New York

M-9 Director
Naval Research Laboratory
Washington 20, D. C.

Attn: Scientific Information Division
M-2 Library (Code 2021)
M-1 Applied Mathematics Branch (Code 3830)
M-1 Shock and Vibrations Section (Code 3850)
M-1 Structures Branch (Code 3860)

Bureau of Ships
Department of the Navy
Washington 25, D. C.

M-2 Attn: Code 364 (Technical Library)
R-1 Code 423 (Underwater Explosion Research)
M-1 Code 442 (Scientific Section, Design)

David Taylor Model Basin
Carderock, Maryland

M-2 Attn: Library
M-1 Structural Mechanics Division

Naval Ordnance Laboratory
White Oak, Silver Spring 19, Maryland
M-2 Attn: Library

Bureau of Aeronautics
Department of the Navy
Washington 25, D. C.

M-1 Attn: AER-TD-414
R-1 Materials Branch
R-1 Design Elements Division

Bureau of Yards and Docks
Department of the Navy
Washington 25, D. C.

R-2 Attn: Director, Research Division

Commander
Norfolk Naval Shipyard
Norfolk, Virginia

M-1 Attn: Technical Library (Code 243A)
M-1 UERD (Code 290)

Superintendent
Aeronautical Structures Laboratory
Building 600, Naval Air Experimental Station
Philadelphia 12, Pennsylvania

R-1 Attn: Experimental Structures Section

Office, Assistant Chief of Staff, G4
The Pentagon
Washington, D. C.

M-1 Attn: Research and Development Division

M-1 The Chief, Armed Forces Special Weapons Project
Department of Defense
P. O. Box 2610
Washington, D. C.

U. S. Army Arsenal
Watertown 72, Massachusetts
M-1 Attn: Dr. R. Beeuwkes

Frankford Arsenal
Pitman-Dunn Laboratory
Philadelphia 37,
M-1 Attn: Dr. Herbert L. Fusfeld

M-1 Picatinny Arsenal
Dover, New Jersey
Attn: Mr. L. Gilman

M-1 Commanding General
R-1 Air Materiel Command
Wright-Patterson Air Force Base
Dayton, Ohio
Attn: Chief, Materials Division (DCRTS)
Head, Structures Lab (MCREX-B)

M-1 Department of Commerce
Office of Technical Service
Washington 25, D. C.
Attn: Library Section

M-1 National Advisory Committee for Aeronautics
1724 F. Street NW
Washington 25, D. C.
Attn: Chief of Aeronautical Intelligence

M-1 National Advisory Committee for Aeronautics
Langley Aeronautical Laboratory
Langley Field, Virginia
Attn: Library

M-1 National Advisory Committee for Aeronautics
Lewis Flight Propulsion Laboratory
Cleveland Airport
Cleveland 11, Ohio
Attn: Library

M-1 National Bureau of Standards
Washington, D. C.
Attn: Dr. W. H. Ramberg

M-1 Director of Research
Sandia Corporation
Albuquerque, New Mexico
Attn: Dr. R. P. Peterson

R-1 Brooklyn Polytechnic Institute
R-1 85 Livingston Street
M-1 Brooklyn, New York
Attn: Dr. N. J. Hoff
Dr. H. Reissner
Dr. F. S. Shaw (Dept. Aero. Engrg. & Appl. Mech.)

M-1 Brown University
Providence 12, Rhode Island
Attn: Chairman, Graduate Division of Applied Mathematics

R-1 California Institute of Technology
R-1 Pasadena, California
Attn: Dr. J. G. Kirkwood
Dr. Pol Duwez

University of California
Berkeley, California

M-1 Attn: Dr. J. E. Dorn
R-1 Dr. H. Hultgren
R-1 Dr. G. C. Evans
M-1 Dr. C. F. Garland

University of California
Los Angeles, California

R-1 Attn: Dr. I. S. Sokolnikoff
R-1 Dr. D. Rosenthal

Carnegie Institute of Technology
Pittsburgh, Pennsylvania

R-1 Attn: Dr. J. S. Koehler
R-1 Dr. G. H. Handelman
M-1 Dr. E. Saibel
R-1 Dr. H. J. Greenberg
R-1 Dr. E. D'Appolonia

Case Institute of Technology
Cleveland, Ohio

M-1 Attn: Dr. W. M. Baldwin, Jr., Metals Research Laboratory
R-1 Dr. O. Hoffman

Catholic University of America
Washington, D. C.

M-1 Attn: Dr. F. A. Biberstein
R-1 Dr. K. Hertzfeld

University of Chicago
Chicago, Illinois

R-1 Attn: Dr. T. S. Ke
R-1 Dr. C. S. Barrett

Columbia University
New York, New York

M-1 Attn: Dr. R. D. Mindlin
M-1 Dr. H. Bleich

Cornell University
Ithaca, New York

R-1 Attn: Dr. H. S. Sack
R-1 Dr. A. Kantrowitz

University of Florida
Gainesville, Florida

M-1 Attn: Dr. C. G. Smith

Harvard University
Cambridge 38, Massachusetts

R-1 Attn: Dr. R. von Mises
R-1 Dr. F. Birch, Dunbar Laboratory
R-1 Dr. H. M. Westergaard

Illinois Institute of Technology
Chicago, Illinois

R-1 Attn: Dr. L. H. Donnell
R-1 Dr. L. van Griffis
M-1 Dr. E. Sternberg
R-1 Dr. W. Osgood
M-1 Dr. C. A. Eringen

University of Illinois
Urbana, Illinois

M-1 Attn: Dr. N. M. Newmark
R-1 Engineering
R-1 T. J. Dolan
R-1 Dr. F. Seitz, Department of Physics
M-1 Department of Theoretical and Applied Mathematics

Indiana University
Bloomington, Indiana

M-1 Attn: Dr. T. Y. Thomas

Institute for Advanced Study
Princeton, New Jersey

R-1 Attn: Dr. J. von Neumann

Iowa State College
Ames, Iowa

R-1 Attn: Dr. G. Murphy
R-1 Dr. D. L. Hall

Johns Hopkins University
Baltimore, Maryland

M-1 Attn: Dr. W. H. Hoppman, II

M-1 Director, Applied Physics Laboratory
Johns Hopkins University
8621 Georgia Avenue
Silver Spring, Maryland

Lehigh University
Bethlehem, Pennsylvania

R-1 Attn: Mr. Lynn S. Beedle

Massachusetts Institute of Technology
Cambridge 39, Massachusetts

R-1 Attn: Dr. F. B. Hildebrand
R-1 Dr. C. W. MacGregor
R-1 Dr. J. M. Lessels
R-1 Dr. W. M. Murray
R-1 Dr. E. Reissner
R-1 Dr. H. S. Tsien
R-1 Dr. M. Cohen, Rm. 8-413, Department of Metallurgy
R-1 Dr. B. L. Averbach, Department of Metallurgy
R-1 Dr. J. T. Norton
R-1 Dr. E. Orowan
M-1 Dr. R. Bisplinghoff, Dept. Aero. Engr.

University of Michigan
Ann Arbor, Michigan

M-1 Attn: Dr. Bruce G. Johnston
M-1 Dr. Paul Nagdhi
R-1 Dr. N. Coburn
R-1 Dr. W. Kaplan

New York University
Institute for Mathematics & Mechanics
45 Fourth Avenue
New York 3, New York

R-1 Attn: Professor R. Courant
R-1 Dr. G. Hudson

New York University
New York 53, New York

R-1 Attn: Dr. C. T. Wang, Department of Aeronautics

Northwestern University
Evanston, Illinois

R-1 Attn: Dr. M. M. Hetenyi

University of Notre Dame
Notre Dame, Indiana

R-1 Attn: Dr. P. A. Beck

Ohio State University
Columbus, Ohio

M-1 Attn: Dr. B. A. Boley

Pennsylvania State College
State College, Pennsylvania

R-1 Attn: Dr. M. Gensamer
R-1 Dr. J. A. Sauer
R-1 Dr. Joseph Marin
R-1 Dr. J. W. Fredrickson

Princeton University
Princeton, New Jersey

R-1 Attn: Dr. S. Lefschetz
R-1 Dr. L. Lees
R-1 Dr. J. V. Charyk

Rensselaer Polytechnic Institute
Troy, New York

R-1 Attn: Library
R-1 Dr. Paul Leiber

Santa Clara University
Santa Clara, California

M-1 Attn: Dr. R. M. Hermes

Stanford University
Stanford, California

R-1 Attn: Dr. L. Jacobsen
M-1 Dr. A. Phillips, Department of Mechanical Engineering
R-1 Dr. J. N. Goodier

Stevens Institute of Technology
 Hoboken, New Jersey
 R-1 Attn: Dr. E. G. Schneider

Swarthmore College
 Swarthmore, Pennsylvania
 M-1 Attn: Capt. W. P. Roop

University of Texas
 Austin 12, Texas
 R-1 Attn: Dr. A. A. Topractsoglou

University of Utah
 Salt Lake City, Utah
 M-1 Attn: Dr. H. Eyring

Washington State College
 Pullman, Washington
 R-1 Attn: Dr. B. Fried

Wheaton College
 Norton, Massachusetts
 R-1 Attn: Dr. H. Geiringer

Aerojet, Inc.
 Azusa, California
 R-1 Attn: F. Zwicky

Aluminum Company of America
 New Kensington, Pennsylvania
 M-1 Attn: R. L. Templin

Armstrong Cork Company
 Lancaster, Pennsylvania
 R-1 Attn: J. W. Scott

Bell Telephone Laboratories
 Murray Hill, New Jersey
 R-1 Attn: C. Herring
 R-1 J. M. Richardson
 R-1 D. P. Ling
 R-1 W. P. Mason

Corning Glass Company
 Corning, New York
 R-1 Attn: J. T. Littleton

E. I. Dupont de Nemours & Co., Inc.
 Wilmington 98, Delaware
 R-1 Attn: J. H. Faupel, Materials of Construction Section

General Electric Company
 Schenectady, New York
 R-1 Attn: H. Fehr
 R-1 H. Poritsky
 R-1 J. H. Hollomon

R-1 General Motors
Detroit, Michigan
Attn: J. O. Almen

R-1 Lockheed Aircraft Company
Department 72-25, Factory A-1, Building 66
Burbank, California
Attn: Engineering Library

R-1 Midwest Research Institute
Kansas City, Missouri
Attn: C. O. Dohrenwend
R-1 M. Golan

R-1 Pratt & Whitney Aircraft Corporation
East Hartford, Connecticut
Attn: R. Morrison

R-1 U. S. Rubber Company
Passaic, New Jersey
Attn: H. Smallwood

M-1 Welding Research Council
Engineering Foundation
29 West 39th Street
New York 18, New York
Attn: W. Spraragen, Director

M-1 Westinghouse Research Laboratories
East Pittsburgh, Pennsylvania
Attn: Dr. A. Nadai
R-1 Dr. E. A. Davis

R-1 Westinghouse Electric Corporation
Lester Branch P. O.
Philadelphia, Pennsylvania
Attn: R. P. Kroon, Mgr. of Engineering, AGT Division