

AD NO. 18 365

ASTIA FILE COPY

Navy Contract Number N6ori-17, T.O. IV
ONR Project Number NR 058 059

Tech. Report No. 10 Project RF-280

**THE OHIO STATE UNIVERSITY
RESEARCH FOUNDATION**

FORMATION, STABILITY AND CRYSTAL STRUCTURE
OF THE SOLID ALUMINUM SUBOXIDES:
 Al_2O AND AlO

by

Michael Hoch and Herrick L. Johnston

TR 280-10

August 1, 1953

Technical Report

Cryogenic Laboratory
Department of Chemistry
The Ohio State University
Columbus 10, Ohio

FOREWORD

This work was carried out at The Ohio State University Cryogenic Laboratory under contract with U.S. Navy, Office of Naval Research Contract Number M6ori-17, Task Order IV, ONR Project Number NR 358 039, with The Ohio State University Research Foundation. This report covers information obtained during the study entitled: "Formation, Stability and Crystal Structure of the Solid Aluminum Suboxides: Al_2O and AlO ." It represents the 10th Technical Report of this series.

Director - H. L. Johnston

Editor - E. R. Fultz

TABLE OF CONTENTS

FOREWORD	ii
ABSTRACT	1
INTRODUCTION	2
MATERIALS AND EXPERIMENTAL PROCEDURE . . .	2
EXPERIMENTAL RESULTS	3
DISCUSSION OF RESULTS	5
REFERENCES	6

ABSTRACT

The study of the reactions (1) $4\text{Al}_{(l)} + \text{Al}_2\text{O}_{3(s)} \longrightarrow 3\text{Al}_2\text{O}_{(s)}$ and (2) $\text{Al}_{(l)} + \text{Al}_2\text{O}_{3(s)} \longrightarrow 3\text{AlO}_{(s)}$ between 1000° and 2000°C , by means of a high temperature x-ray technique, indicated the formation of solid Al_2O and AlO above certain temperatures.

At 1000°C no reaction occurs. Between 1100° and 1500°C , $\text{Al}_2\text{O}_{(s)}$ is formed according to reaction (1). Between 1500° and 1600°C , both reactions, (1) and (2), occur simultaneously, whereas above 1600°C the latter reaction occurs. On cooling or rapid quenching both compounds disproportionate into Al and Al_2O_3 .

From the x-ray diffraction patterns the crystal structure and lattice constants of Al_2O and AlO were determined. Both are cubic, the lattice constants being 4.98 Å. for Al_2O at 1110°C , and 5.67 Å for AlO at 1700°C .

INTRODUCTION

The existence of gaseous AlO has been known from spectroscopic investigations.¹ From their investigation on the gaseous species of the Al-Al₂O₃ system, Brewer and Searcy,² concluded that two suboxides of aluminum must exist in the gas phase; these they identified as Al₂O and AlO. A phase diagram study of Al-Al₂O₃, made by Baur and Brunner³, revealed the presence of a compound, Al₈O₉, melting at 2323° C with a eutectic between Al₈O₉ and Al₂O₃. Beletskii and Rapoport⁴ reported the formation of hexagonal Al₂O by heating Al and Al₂O₃ in vacuum in the presence of SiO₂ and C and condensing the volatile products.

In the present investigation the formation, in the solid state, of the lower oxides of aluminum, which are not stable at room temperature, was studied by taking x-ray diffraction patterns at high temperatures. The presence of a new compound is shown by the appearance of a new set of diffraction lines. By varying the temperature, the stability of the compound with respect to disproportionation into Al and Al₂O₃ can be determined. From the position of the diffraction patterns, lattice constants and crystal structure can be determined, and from the relative intensity of the pattern the approximate composition of the compound can be estimated.

MATERIALS AND EXPERIMENTAL PROCEDURE

The x-ray diffraction patterns were taken in our high temperature camera which has been described elsewhere.⁵ Besides the changes already made,⁶ a new collimator was designed, which lowered the exposure time to 1 hour. This was necessary, due to the high evaporation rate of aluminum, even in the presence of 1 atm. of helium. The temperature was measured with a Leeds and Northrup disappearing filament optical pyrometer which had been calibrated against a standard lamp obtained from the National Bureau of Standards. The temperature calibration of the camera was carried out by placing a "black body" made from a piece of tantalum tube, in place of the x-ray specimen. By taking account of the various calibration and correction factors, the uncertainty in the reading of the pyrometer, and the slight temperature variations during the runs, the temperature may be considered accurate to within 20°. Ni-filtered Cu K_{1α} radiation, obtained from a Machlett Tube operated at 50 Kv. and 20 Ma., was used.

The Al and Al_2O_3 were obtained from the I. T. Baker Chemical Co., and were of "Purified" and "Analyzed" grades, respectively. Rods of $\frac{1}{32}$ " diameter and $\frac{1}{4}$ " length were pressed from Al_2O_3 and $\text{Al}_2\text{O}_3 + \text{Al}$ and placed into the camera. After filling with helium, the camera was heated and the x-ray diffraction patterns were taken. For every x-ray determination a new sample was employed.

EXPERIMENTAL RESULTS

The $\alpha\text{-Al}_2\text{O}_3$ was found to have the same crystal structure at 2000°C as at room temperature. Since aluminum is a liquid above 660°C , it does not contribute any lines to the x-ray diffraction patterns.

Two sets, or series, of experiments were carried out: Set No. 1 corresponded to the composition ratio 4:1 for Al : Al_2O_3 , while Set No. 2 corresponded to the ratio 1:1.

The x-ray diffraction patterns obtained from Set No. 1 indicated that at 1000°C no reaction occurred, while at 1100°C a new set of lines (corresponding, as we will see later, to Al_2O), besides those for Al_2O_3 , appeared. The diffraction pattern from Al_2O is consistent with a cubic structure having a lattice constant of 4.98 Å. The interplanar distances are given in Table I.

Diffraction patterns obtained from Set No. 2 (Al : $\text{Al}_2\text{O}_3 = 1:1$) show that the Al lines, at room temperature, are much weaker than those from Set No. 1. This is to be expected since the ratio of Al to Al_2O_3 is now 1:1 instead of 4:1. At 1100°C the same new lines (those for Al_2O) appear as before, but they are much weaker. At 1500°C another set of lines, belonging, as we will see later, to AlO , appear together with the Al_2O lines. At 1700°C , only the AlO lines appear. The AlO diffraction pattern leads to a cubic structure with a lattice constant of 5.67 Å. Interplanar distances are given in Table II.

At 1900°C the whole sample (15 mg) vaporized within one hour, indicating that AlO has a high vapor pressure at that temperature.

On every pattern Al_2O_3 lines are present. This can be expected to be due to the fact that some Al evaporates during the

TABLE I

X-RAY DIFFRACTION LINES OF Al_2O_3 AT 1100°C

<u>Intensity</u>	<u>$\sin^2 \Theta$</u>	<u>$d(\text{in } \text{\AA})$</u>	<u>Indices h, k, l</u>
Strong	0.0729	2.85	1, 1, 1
Medium	0.1157	2.26	2, 1, 0
Medium	0.2107	1.67	3, 0, 0 2, 2, 1
Weak	0.3438	1.31	3, 2, 1

TABLE II

X-RAY DIFFRACTION LINES OF AlO AT 1700°C

<u>Intensity</u>	<u>$\sin^2 \Theta$</u>	<u>$d(\text{in } \text{\AA})$</u>	<u>Indices h, k, l</u>
Strong	0.0548	3.28	1, 1, 1
Medium	0.0923	2.52	2, 1, 0
Medium	0.1091	2.33	2, 1, 1
Weak	0.1502	1.98	2, 2, 0
Medium	0.2012	1.71	3, 1, 1

exposures thereby shifting the equilibrium in the two reactions $4\text{Al} + \text{Al}_2\text{O}_3 \rightleftharpoons 3\text{Al}_2\text{O}$ and $\text{Al} + \text{Al}_2\text{O}_3 \rightleftharpoons 3\text{AlO}$ to the left. Because of the rapid disproportionation into Al and Al_2O_3 , every attempt to obtain diffraction patterns for the two compounds at room temperature by rapidly quenching the samples was unsuccessful.

DISCUSSION OF RESULTS

The investigation showed the existence of two lower aluminum oxides in the solid phase, each having a cubic structure, the lattice constants being 4.98 and 5.67 Å. The problem now is to decide which is Al_2O and which is AlO. Let us call the compound formed at 1100°C "Compound 1" and the one at 1700°C, "Compound 2."

All diffraction pictures were obtained using the same x-ray intensity and exposure time. The Al_2O_3 pattern is present on every picture with about the same intensity. Thus the relative intensity of the new diffraction patterns gives information as to how much Al is needed (compared to Al_2O_3) in the formation of the compounds. The ratio Al: Al_2O_3 was 4:1 in the first set, and 1:1 in the second set. A visual comparison of the intensities of the different diffraction patterns shows that the intensity of the new diffraction pattern in Set No. 2 at 1700°C is much stronger than that for the new diffraction pattern in this same set at 1100°C, and that the intensity of the new pattern in this set at 1700°C is about equal to that in Set No. 1 at 1100°C. For the same amount of Al, less of Compound 1 is formed than of Compound 2. Similarly, to form the same amount of material, more Al is needed for Compound 1 than for Compound 2. It therefore follows that Compound 1 (at 1100°C) is richer in Al than is Compound 2. Thus Compound 1 is Al_2O while Compound 2 is AlO, as was assumed during the description of the patterns.

From the diffraction patterns obtained, the stability against disproportionation into Al and Al_2O_3 of the lower oxides in solid form can be deduced. Below 1000°C only liquid Al and Al_2O_3 are stable. Al_2O is stable between 1050° and 1600°C, and AlO is stable above 1500°C.

REFERENCES

1. G. Herzberg, "Molecular Spectra and Molecular Structure. I. Spectra of Diatomic Molecules," D. Van Nostrand Co., Inc., New York (1950).
2. L. Brewer and A.W. Searcy, J. Am. Chem. Soc. 73, 5308 (1951).
3. E. Baur and R. Brunner, Z. Elektrochem. 40, 155 (1934).
4. M.S. Beletskii and M.B. Rapoport, Doklady Akad. Nauk SSSR 80, 751 (1951).
5. J.W. Edwards, R. Speiser and H.L. Johnston, Rev. Sci. Inst. 20, 343-7 (1949).
6. M. Hoch and H.L. Johnston (unpublished results).

List Revised 6/25/51

RF Project 280

DISTRIBUTION LIST FOR TECHNICAL REPORTS
N6onr-17 Task Order IV
Office of Naval Research
NR 058 039

<u>Addressee</u>	<u>No. of Copies</u>
Commanding Officer U. S. Navy Office of Naval Research Branch Office 495 Summer Street Boston 10, Mass.	1
Commanding Officer U. S. Navy Office of Naval Research Branch Office 844 N. Rush Street Chicago 11, Ill.	2
Commanding Officer U. S. Navy Office of Naval Research Branch Office Van Nuys Bldg. , Suite 507 Los Angeles 14, Calif.	1
Commanding Officer U. S. Navy Office of Naval Research Branch Office 1030 N. Green Street Pasadena 1, Calif.	1
Commanding Officer U. S. Navy Office Branch Office 801 Donahue Street San Francisco 24, Calif.	1
Commanding Officer U. S. Naval Ordnance Test Station Inyokern, China Lake, Calif.	1
Commanding Officer Naval Powder Factory Indian Head, Maryland	1

List Revised 6/25/51

RF Project 280

<u>Addressee</u>	<u>No. of Copies</u>
Office of Naval Research 346 Broadway New York 13, N. Y.	1
Office of Naval Research Navy Department Washington 25, D. C. Attn: Project Status, Code N482	2
Officer-in-Charge Office of Naval Research, Branch Office Navy No. 100 Fleet Post Office New York, N. Y.	2
Chief of Naval Research Office of Naval Research Washington 25, D. C. Attn: Chemistry Branch	4
Chief of the Bureau of Aeronautics Navy Department Washington 25, D. C. Attn: Code TD-4	2
Chief of the Bureau of Ordnance Navy Department Washington 25, D. C. Attn: Code Rexd	2
Chief of the Bureau of Ships Navy Department Washington 25, D. C. Attn: Code 330	2
Director, Naval Research Laboratory Washington 25, D. C. Attn: Tech. Info. Officer	9

List Revised 6/25/51

RF Project 280

<u>Addressee</u>	<u>No. of Copies</u>
Director, Naval Research Laboratory Washington 20, D. C. Attn: Chemistry Division	2
Office of the Quartermaster General, USA Research and Development Branch Chemistry and Plastics Section Washington, D. C. Attn: Mr. Wm. McC. Lee, Chief	1
Joint Research and Development Board 1712 G Street, N. W. Washington, D. C. Attn: Mr. R. L. Clark, Program Division	1
Research and Development Group Logistics Division, General Staff Department of the Army Washington 25, D. C. Attn: Dr. W. T. Read, Scientific Advisor	1
Research and Development Board Pentagon, Room 3E123 Washington 25, D. C. Attn: Technical Reference Section	1
Commanding General Army Air Forces Pentagon Bldg. Washington 25, D. C.	1
Commanding General Air Materiel Command Wright-Patterson Air Force Base Dayton, Ohio Attn: Office of Air Research (MCRRXS) Power Plant Laboratory (MCREXP-3) Central Air Document Office (1'CLDSD)	3

List Revised 6/25/51

RF Project 280

<u>Addressee</u>	<u>No. of Copies</u>
National Bureau of Standards Thermochemistry Laboratory Washington 25, D. C. Attn: Dr. F. W. Brickwedde	1
Library of Congress Navy Research Section Washington 25, D. C. Attn: Mr. J. H. Heald	6
Aerojet Engineering Corporation Azusa, California Attn: Dr. F. Zwicky	1
Battelle Memorial Institute 505 King Avenue Columbus 1, Ohio Attn: Mr. J. B. Holding	1
Los Alamos Scientific Laboratory P. O. Box 1663 Los Alamos, New Mexico Attn: Dr. J. F. Lemons	1
California Institute of Technology Jet Propulsion Laboratory GALCIT Pasadena 4, California	1
Carnegie Institute of Technology Department of Chemistry Metals Research Laboratory Pittsburgh, Pennsylvania Attn: Dr. E. Birchenall	1
Carnegie Institute of Technology Department of Chemistry Pittsburgh 13, Pennsylvania Attn: Dr. F. D. Rossini	1

List Revised 6/25/51

RF Project 280

<u>Addressee</u>	<u>No. of Copies</u>
John Hopkins University Applied Physics Laboratory 9621 Georgia Avenue Silver Springs, Maryland Attn: Dr. L. R. Hofstad	1
Princeton University Princeton, New Jersey Attn: Project SQUID	1
Ohio State University Research Foundation 310 Administration Building Columbus 10, Ohio	1
Ohio State University Department of Chemistry Columbus 10, Ohio Attn: Prof. H. L. Johnston	1