

UNCLASSIFIED

|                                                                                                                                                                                                                                             |                     |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------|
| <b>AD NUMBER</b>                                                                                                                                                                                                                            |                     |
| <b>AD018516</b>                                                                                                                                                                                                                             |                     |
| <b>CLASSIFICATION CHANGES</b>                                                                                                                                                                                                               |                     |
| <b>TO:</b>                                                                                                                                                                                                                                  | <b>unclassified</b> |
| <b>FROM:</b>                                                                                                                                                                                                                                | <b>confidential</b> |
| <b>LIMITATION CHANGES</b>                                                                                                                                                                                                                   |                     |
| <b>TO:</b><br><b>Approved for public release; distribution is unlimited.</b>                                                                                                                                                                |                     |
| <b>FROM:</b><br><b>Distribution authorized to U.S. Gov't. agencies and their contractors;</b><br><b>Administrative/Operational Use; JUN 1953. Other requests shall be referred to Material Lab., New York Naval Shipyard, Brooklyn, NY.</b> |                     |
| <b>AUTHORITY</b>                                                                                                                                                                                                                            |                     |
| <b>DNA ltr, 15 Mar 1977; DNA ltr, 15 Mar 1977</b>                                                                                                                                                                                           |                     |

THIS PAGE IS UNCLASSIFIED

**CONFIDENTIAL**

**SECURITY INFORMATION**

Lab. Project 5046-3, Part 31  
Final Report  
NS 081-001

AW-7

**MATERIAL LABORATORY  
NEW YORK NAVAL SHIPYARD  
BROOKLYN 1, N. Y.**

**TECHNICAL REPORT**



**CONFIDENTIAL**

S E C U R I T Y    I N F O R M A T I O N

CRITICAL THERMAL ENERGIES

of

DOPED FABRICS

Submitted by  
THE WRIGHT AIR DEVELOPMENT CENTER  
Dept. of the Air Force

L. Banet  
J. Bfacciaventi

Lab. Project 5046-3, Part 31  
Final Report  
NS 081-001  
Technical Objective AW-7  
AFSWP-389

24 June 1953

Optics and Nucleonics Branch  
J. M. McGreevy

Superintending Engineer  
G. J. DASHEFSKY

The Director  
CAPT. H. T. KOONCE, USN

MATERIAL LABORATORY  
New York Naval Shipyard  
Brooklyn 1, New York

S E C U R I T Y    I N F O R M A T I O N

Lab. Project 5046-3 Part 31  
Final Report

CONTENTS

|                                   | Page |
|-----------------------------------|------|
| Abstract                          | 2    |
| Authority                         | 3    |
| Introduction                      | 3    |
| Equipment and Methods of Exposure | 3    |
| Results                           | 3    |
| Summary                           | 4    |
| Bibliography                      | 5    |

CONFIDENTIAL

Lab. Project 5046-3 Part 31  
Final Report

#### ABSTRACT

For the purpose of evaluating the resistance of doped fabrics to the thermal radiation of atomic explosions, the critical thermal energies of several doped fabric assemblies submitted by the Wright Air Development Center, Department of the Air Force, were determined by exposing the materials to the Laboratory carbon-arc source of thermal radiation and examining the consequent damage.

The carbon arc source furnishes a maximum irradiance of 85 cal/cm<sup>2</sup>/sec in the central area of the specimens if no absorbing screens were employed. However, for a better approximation of the Laboratory exposure time to that obtained in the field, absorbing screens were employed, giving effective exposure times between 0.3 and 0.6 seconds. The methods of exposure and evaluation of the effective damage are indicated. It was found that the assemblies suffered complete destruction at radiant exposures ranging from 4.9 to 213 cal/cm<sup>2</sup>, depending on the assembly exposed. Assemblies employing metal foils had considerably higher critical energies of destruction (55 to 213 cal/cm<sup>2</sup>) than the other experimental assemblies investigated, (4.9 to 20 cal/cm<sup>2</sup>).

CONFIDENTIAL

CONFIDENTIAL

Lab. Project 5046-3 Part 31  
Final Report

Ref: (a) COMNAVSHIPYD ltr C-999/L5, Ser C-960-92 of 14 Mar 1950  
(b) BUSHIPS restr spdltr 599-(0)(348) Ser 348-75 of 6 Apr 1950

Encl: (1) Critical Thermal Energies of Doped Fabrics

AUTHORITY

1. This investigation is part of the program proposed by reference (a) and formally authorized by reference (b). The general Thermal Radiation Program is under the supervision of the Armed Forces Special Weapons Project.

INTRODUCTION

2. As part of its general program on the effects of the thermal radiation of atomic explosions on materials, the Naval Material Laboratory is evaluating the characteristics, under exposure to thermal radiation, of the various materials of particular interest to the several agencies of the Department of Defense. As data become available, these findings are published. In this report, the critical thermal energies of doped fabrics, submitted by the Wright Air Development Center, Department of the Air Force, are indicated.

EQUIPMENT AND METHODS OF EXPOSURE

3. The critical thermal energies of the doped fabrics were determined, employing the Material Laboratory carbon-arc source of thermal radiation (Bibliography 1,2,3,4). The source consists of an 11-mm carbon arc, mounted at the focus of a mirror which collimates the emitted energy. A second mirror, which is mounted coaxially at a distance of 12 feet from the collimator, condenses the radiation to the mirror's focus. Gradations of thermal damage are obtained by varying the effective exposure time by accelerating a sample, 1 x 8 inches in surface dimensions, moving transversely through the focus. Except for the last two of the specimens, the exposure of the materials was made by fastening them to glass melamine blocks provided with cut-outs in the central area to furnish an air background. In order to reduce propagation of flame during exposure and in order to secure the specimens to the glass melamine block serving as a base, a glass silicone mask with several stops was used over the fabrics.

RESULTS

4. The critical thermal energies of the doped fabrics, submitted by the Wright Air Development Center, were defined as those which produce certain characteristic, reproducible effects on the materials, such as

CONFIDENTIAL

CONFIDENTIAL.

Lab. Project 5046-3 Part 31  
Final Report

destruction, blistering or ignition. These exposures were obtained with a carbon-arc source which furnished a maximum irradiance of  $85 \text{ cal/cm}^2/\text{sec}$  in the central area of the specimens, if no absorbing screens were employed. However, for a better approximation of the laboratory exposure time to that obtained in the field, absorbing screens were employed, giving effective exposure times of 300 to 600 milliseconds. The critical energies are given on enclosure (1).

5. It may be noted that the laboratory exposures have been produced under highly controlled conditions and, as a rule, give results which can be reproduced very well. However, for several reasons, one must use the data of enclosure (1) with caution. The effects to be observed on material samples frequently remain unchanged over a considerable range of exposures. Since the surface effects are not gradated sufficiently for refired evaluations, only the initial stages have been recorded. The effects on material surfaces are influenced by such factors as mounting, uniformity of material, atmospheric conditions and moisture content. Differences in density, absorption coefficient, chemical composition and particle size are responsible for the variations in effects which may be observed from area to area on the same material. Liquids and gases form during exposure to thermal radiation, even in a period of less than one second, thereby affecting the amount of thermal radiation incident on and absorbed by the surface.

#### SUMMARY

6. The results of this investigation indicate that upon irradiation by the Material Laboratory carbon-arc source of thermal radiation for exposure times of 300-600 milliseconds, the doped fabric assemblies, submitted by the Wright Air Development Center, suffered destruction at radiant exposures ranging from 4.9 to  $146 \text{ cal/cm}^2$ , depending upon the assembly exposed; the metallic, vinyl coated specimen was destroyed at  $213 \text{ cal/cm}^2$ . However, there was a marked difference between the fabric assemblies with and without metal foils. Assemblies without metal foils were destroyed at exposures ranging from 4.9 to  $20 \text{ cal/cm}^2$ , but doped fabrics with metal foils suffered destruction at radiant exposures as high as 55 to  $146 \text{ cal/cm}^2$ , depending on the specific assembly employed.

CONFIDENTIAL

CONFIDENTIAL

Lab. Project 5046-3 Part 31  
Final Report

BIBLIOGRAPHY

1. Material Laboratory, New York Naval Shipyard. Determination of Intensity Distribution at the Focus of a Parabolic Mirror and the Energy Density on a Moving Surface, using a Tungsten Lamp Source.  
Report No. 5046, Part 5 (July 1949).
2. Material Laboratory, New York Naval Shipyard. Evaluation of Thermal Effects on Specimens Exposed at Bikini.  
Report No. 5046, Part 7 (March 1950).
3. Material Laboratory, New York Naval Shipyard. A Method of Measuring High Intensities at the Focus of a Parabolic Reflector with Large Relative Aperture.  
Report No. 5046, Part 3 (November 1948.)
4. Material Laboratory, New York Naval Shipyard. Critical Thermal Energies of Clothing Materials, Submitted by the U.S. Marine Corps.  
Report No. 5046-3, Part 3 (July 1951).

Approved:

  
H. T. KOONCE, CAPTAIN, USN  
The Director

CONFIDENTIAL

CONFIDENTIAL

Material Laboratory

Lab. Project 5046-3 Part 31

Final Report

Enclosure (1)

Page 1 of 3

Critical Thermal Energies  
of Experimental Dope Systems  
Submitted by  
The Wright Air Development Center  
(Exposures of 300 to 600 Milliseconds)

| WADC<br>Designation | Materials and<br>Treatment                                                                                                                                                 | Description of Effect                                                                                                                                                    | C. E.<br>cal./cm <sup>2</sup> |
|---------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------|
| A                   | 2 Spray coats MIL-D-5552 Dope (Aluminum pigment 6 oz/gal) on Standard Doped Fabric Finish, consisting of 2 brush coats and 2 spray coats MIL-D-5553 Cellulose Nitrate Dope | Destruction by propagating flame and afterglow                                                                                                                           | 4.9                           |
| B                   | 1 Spray coat (1 mil) Silicone coating on Standard Doped Fabric Finish (as in "A")                                                                                          | Dulling of Surface<br>Surface blisters, fabric chars through<br>Destruction by propagating flame and afterglow                                                           | 4.9-6.2<br>11<br>13           |
| C                   | 2 Spray coats (1 1/2 mil) vinyl coating on Standard Doped Fabric Finish                                                                                                    | Paint carbonized by slowly propagating flame, leaving tumescent but flimsy ash, fabric chars through, but not completely destroyed<br>Destruction of fabric by afterglow | 4.9<br>12                     |
| D                   | 1 Spray coat (1 mil) MIL-V-6893 varnish on Standard Doped Fabric Finish                                                                                                    | Surface blisters<br>Surface coat destroyed by slowly propagating flame, fabric chars through, but not completely destroyed<br>Destruction of fabric by afterglow         | 7.3-8.0<br>9.1<br>15          |
| E                   | Aluminum foil (0.0015") on 1 Spray coat MIL-C-4003 (1 mil) on Standard Doped Fabric Finish                                                                                 | Flames sporadically, foil melts sporadically, fabric backing chars through                                                                                               | 56-63                         |

CONFIDENTIAL

CONFIDENTIAL

Material Laboratory

Lab. Project 5046-3 Part 31

Final Report

Enclosure (1)

Page 2 of 3

Critical Thermal Energies  
of Experimental Dope Systems

Submitted By

The Wright Air Development Center  
(Exposures of 300-to 600 Milliseconds)

| WADC<br>Designation | Materials and<br>Treatment                                                                                                                                   | Description of Effect                                                                                         | C.E.<br>cal/cm <sup>2</sup> |
|---------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------|-----------------------------|
| F                   | Aluminum foil (0.0025")<br>on 1 Spray coat MIL-C-<br>4003 (1 mil) on Stan-<br>dard Doped Fabric<br>Finish                                                    | Flames sporadically,<br>foil melts sporadi-<br>cally, fabric backing<br>chars through                         | 146                         |
| G                   | Aluminum foil (0.0025")<br>on 1 Spray coat MIL-C-<br>4003 Cement (1/4 mil)<br>on Standard Doped<br>Fabric Finish                                             | Flames sporadically,<br>foil melts sporadi-<br>cally, fabric backing<br>chars through                         | 56                          |
| H                   | 2 Spray coats MIL-D-<br>5552 Dope (Aluminum<br>pigment 6.0 oz/gal) on<br>2 brush coats and 2<br>spray coats MIL-D-5549<br>Cellulose Acetate<br>Butynate Dope | Dulling of surface                                                                                            | 3.7                         |
|                     |                                                                                                                                                              | Fabric chars<br>Destruction of fabric<br>by slowly propagating<br>flame                                       | 6.6<br>18-20                |
| I                   | Aluminum foil (0.0015")<br>on 1 spray coat MIL-C-<br>4003 cement (1 mil) on<br>CAB Doped Fabric                                                              | Flames sporadically,<br>foil melts sporadi-<br>cally, fabric backing<br>chars through, dense<br>smoke evolved | 112                         |
| J                   | Vinyl coating (as in<br>C) on 1 dip coat and<br>1 spray coat MIL-P-<br>6889 Zinc Chromate<br>Primer on 0.016" ano-<br>dized magnesium (CVAC #1)              | Surface chars                                                                                                 | 18                          |
|                     |                                                                                                                                                              | Flames during exposure                                                                                        | 31                          |
|                     |                                                                                                                                                              | Paint completely car-<br>bonized, base metal<br>exposed on slight<br>scraping                                 | 49                          |
| K                   | 1 Spray coat of white<br>gloss enamel (Specif.<br>MIL-E-7729) over<br>assembly of "A"                                                                        | Metal completely de-<br>stroyed by violent<br>reaction, leaving<br>powdery ash                                | 213                         |
|                     |                                                                                                                                                              | Paint forms soft<br>blisters and chars                                                                        | 7.5                         |
|                     |                                                                                                                                                              | Fabric chars through<br>Destruction of fabric<br>by slowly propagating<br>flame                               | 16<br>19                    |

CONFIDENTIAL

CONFIDENTIAL

Material Laboratory

Lab. Project 5045-3 Part 31

Final Report

Enclosure (1)

Page 3 of 3

Critical Thermal Energies  
of Experimental Dope Systems  
Submitted By  
The Wright Air Development Center  
(Exposures of 300 to 600 Milliseconds)

| WADC<br>Designation | Materials and<br>Treatment                                                                        | Description of Effect                                       | C.E.<br>cal/cm <sup>2</sup> |
|---------------------|---------------------------------------------------------------------------------------------------|-------------------------------------------------------------|-----------------------------|
| (None)<br>NML #1    | Aluminum (3 mil, painted)<br>over doped fabric,<br>mounted on 4" metal<br>shell (5 walls)         | Charring and blister-<br>ing of paint                       | 14                          |
|                     |                                                                                                   | Paint destroyed                                             | 24-27                       |
|                     |                                                                                                   | Surface flames during<br>exposure                           | 34                          |
|                     |                                                                                                   | Charring and destruc-<br>tion of fabric under<br>metal foil | 37-54                       |
|                     |                                                                                                   | Melting of metal foil                                       | 55-62                       |
| (None)<br>NML #2    | Aluminum (3 mil, un-<br>painted) over doped<br>fabric, mounted on<br>4" metal shells<br>(5 walls) | Charring of fabric<br>under metal foil                      | 40-64                       |
|                     |                                                                                                   | Destruction of fabric<br>under metal foil                   | 66-108                      |
|                     |                                                                                                   | Flame development<br>during exposure                        | 108                         |
|                     |                                                                                                   | Sporadic melting of<br>metal foil                           | 94-123                      |
|                     |                                                                                                   |                                                             |                             |

CONFIDENTIAL

DISTRIBUTION LIST NO. 100  
Thermal Radiation Reports  
(Research)

20 May 1953

| <u>ADDRESSEE</u>                                                                                               | <u>AFMY</u> | <u>No. of Cys</u> |
|----------------------------------------------------------------------------------------------------------------|-------------|-------------------|
| Asst Chief of Staff, G-2, D/A, Washington 25, D. C.                                                            |             | 1                 |
| Asst Chief of Staff, G-3, D/A, Washington 25, D.C, ATTN: DSC,G-3(RR&SW)                                        |             | 1                 |
| Asst Chief of Staff, G-4, D/A, Washington 25, D. C.                                                            |             | 1                 |
| Chief of Ordnance, D/A, Washington 25, D. C., ATTN: ORDTX-AR                                                   |             | 1                 |
| Chief Signal Officer, D/A, P&O Div, Washington 25, DC, ATTN: SIGOP                                             |             | 3                 |
| The Surgeon General, D/A, Washington 25, DC, ATTN: Chairman, Med R&D Bd                                        |             | 3                 |
| Chief Chemical Officer, D/A, Washington 25, D.C.                                                               |             | 2                 |
| Chief of Engineers, D/A, Military Construction Div, Protective Construction Br, Washington 25, DC, ATTN: ENGEB |             | 1                 |
| Chief of Engineers, D/A, Civil Works Div, Washington 25, DC, ATTN: Engineering Div, Structural Br              |             | 1                 |
| The Quartermaster General, CBR, Liaison Office, R&D Div, D/A, Washington 25, D. C.                             |             | 2                 |
| Chief of Transportation, Mil Planning & Intelligence Division, Bldg T-7, Washington 25, D. C.                  |             | 1                 |
| Chief, Army Field Forces, Fort Monroe, Virginia                                                                |             | 4                 |
| Army Field Forces Board #1, Ft. Bragg, North Carolina                                                          |             | 1                 |
| Army Field Forces Board #4, Ft. Bliss, Texas                                                                   |             | 1                 |
| Commanding General, First Army, Governor's Island, New York 4, NY,<br>ATTN: G-1                                |             | 1                 |
| G-2                                                                                                            |             | 1                 |
| G-3                                                                                                            |             | 1                 |
| G-4                                                                                                            |             | 1                 |
| Commanding General, Second Army, Ft. George G Meade, Md, ATTN: AIAEB                                           |             | 1                 |
| AIAED                                                                                                          |             | 1                 |
| Commanding General, Third Army, Ft. McPherson, Ga, ATTN: ACoFS, G-3                                            |             | 2                 |

DISTRIBUTION LIST NO. 100 (Cont'd)

|                                                                                                                                   |   |
|-----------------------------------------------------------------------------------------------------------------------------------|---|
| Commanding General, Fourth Army, Ft. Sam Houston, Tex, ATTN: G-3                                                                  | 1 |
| Commanding General, Fifth Army, 1660 E. Hyde Park Blvd, Chicago 15,<br>Ill. ATTN: ALFEN                                           | 1 |
| ALFOR                                                                                                                             | 1 |
| Commanding General, Sixth Army, Presidio of San Francisco, Calif,<br>ATTN: AMGCT-4                                                | 1 |
| Commander-in-Chief, Far East Command, APO 500, c/o PM, San Francisco,<br>Calif, ATTN: ACofS, J-3                                  | 2 |
| Commanding General, U.S. Army Forces Far East (Main) APO 343, c/o PM;<br>San Francisco, Calif, ATTN: ACofS, G-3                   | 3 |
| Commanding General, USAR Alaska, APO 942, c/o PM, Seattle, Washington                                                             | 1 |
| Commanding General, USARCARIB, APO 834, c/o PM, New Orleans, La.,<br>ATTN: CG, USARCARIB                                          | 1 |
| CG, USARPANT                                                                                                                      | 1 |
| Cml Off, USARCARIB                                                                                                                | 1 |
| Surgeon, USARCARIB                                                                                                                | 1 |
| Commanding General, USARPACIFIC, APO 958, c/o PM, San Francisco, Calif,<br>ATTN: Cml Off                                          | 2 |
| Commandant, Command & General Staff College, Ft. Leavenworth, Kan,<br>ATTN: ALLIS(AS)                                             | 1 |
| Commandant, The Infantry School, Ft. Benning, Ga., ATTN: C.D.S.                                                                   | 2 |
| Commandant, The Artillery School, Ft. Sill, Oklahoma                                                                              | 1 |
| Commandant, The AAA&GM Branch, The Artillery School, Ft. Bliss, Texas                                                             | 1 |
| Commandant, The Armored School, Ft. Knox, Ky, ATTN: Class Doc Sect,<br>Eval & Res Div.                                            | 2 |
| Commanding General, Medical Field Service School, Brooke Army Medical<br>Center, Ft. Sam Houston, Texas                           | 1 |
| Surgical Research Unit, Brooke Army Hospital, San Antonio, Tex                                                                    | 1 |
| Commandant, Army Medical Service Graduate School, Walter Reed Army<br>Medical Center, Washington 25, DC, ATTN: Dept of Biophysics | 1 |
| The Superintendent, USMA, West Point, NY, ATTN: Prof of Ordnance                                                                  | 1 |