

UNCLASSIFIED

AD NUMBER

AD025048

CLASSIFICATION CHANGES

TO: unclassified

FROM: confidential

LIMITATION CHANGES

TO:
Approved for public release, distribution unlimited

FROM:
Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; DEC 1953. Other requests shall be referred to Naval Proving Ground, Dahlgren, VA.

AUTHORITY

USNSWC ltr, 21 Jun 1976; USNSWC ltr, 21 Jun 1976

THIS PAGE IS UNCLASSIFIED

Armed Services Technical Information Agency ^{III}

PLEASE RETURN THIS COPY TO:

AD

ARMED SERVICES TECHNICAL INFORMATION AGENCY
DOCUMENT SERVICE CENTER
Knott Building, Dayton 2, Ohio

Because of our limited supply you are requested to return this copy as soon as it has served your purposes so that it may be made available to others for reference use. Your cooperation will be appreciated.

25048

NOTICE: WHEN GOVERNMENT OR OTHER DRAWINGS, SPECIFICATIONS OR OTHER DATA ARE USED FOR ANY PURPOSE OTHER THAN IN CONNECTION WITH A DEFINITELY RELATED GOVERNMENT PROCUREMENT OPERATION, THE U. S. GOVERNMENT THEREBY INCURS NO RESPONSIBILITY, NOR ANY OBLIGATION WHATSOEVER; AND THE FACT THAT THE GOVERNMENT MAY HAVE FORMULATED, FURNISHED, OR IN ANY WAY SUPPLIED THE SAID DRAWINGS, SPECIFICATIONS, OR OTHER DATA IS NOT TO BE REGARDED BY IMPLICATION OR OTHERWISE AS IN ANY MANNER LICENSING THE HOLDER OR ANY OTHER PERSON OR CORPORATION, OR CONVEYING ANY RIGHTS OR PERMISSION TO MANUFACTURE, USE OR SELL ANY PATENTED INVENTION THAT MAY IN ANY WAY BE RELATED THERETO.

Reproduced by
DOCUMENT SERVICE CENTER
KNOTT BUILDING, DAYTON, 2, OHIO

CONFIDENTIAL

11

NOTICE: THIS DOCUMENT CONTAINS INFORMATION AFFECTING THE NATIONAL DEFENSE OF THE UNITED STATES WITHIN THE MEANING OF THE ESPIONAGE LAWS, TITLE 18, U.S.C., SECTIONS 793 and 794. THE TRANSMISSION OR THE REVELATION OF ITS CONTENTS IN ANY MANNER TO AN UNAUTHORIZED PERSON IS PROHIBITED BY LAW.

CONFIDENTIAL

NPG REPORT NO. 1194

U. S. NAVAL PROVING GROUND
DAHLGREN, VIRGINIA

Twelfth Partial Report

on

Development of a Cool Propellant
for the 5"/54 Caliber Gun

Final Report

on

Ballistic Test of Cool Propellants
EX-7084 to EX-7089 inclusive

Project No.: NPG-Re2d-61-1-53
Copy No.: 9
No. of Pages: 10

Date:

DEC 4 1953

CONFIDENTIAL
SECURITY INFORMATION

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

PART A

SYNOPSIS

1. From the results of the subject tests, it is concluded that:

a. EX-7085 was ballistically satisfactory for use in the 5"/54 caliber gun with the 60 lb. projectile at a velocity of 3000 f/s.

b. EX-7088 was ballistically satisfactory at a velocity of 3000 f/s at a PPD (Production Packing Depth) of 3#1 but unsatisfactory at the proposed PPD of 3#5.

c. Satisfactory ballistics were obtained at 3000 f/s velocity at a PPD of 2#5 for EX-7085, EX-7087, and EX-7088.

d. The pressure-time curves obtained with the subject propellants had pronounced steps occurring in the pressure-rise region and were inferior to those obtained with either EX-6822 or EX-6883.

2. From the results of the subject tests, the following recommendations for a powder granulation, as requested in reference (b), are as follows:

<u>Velocity</u> <u>(f/s)</u>	<u>Pressure</u> <u>(t.s.i.)</u>	<u>Approx.</u> <u>PPD</u>	<u>Flame Temp.</u> <u>°K</u>	<u>Av. Web</u> <u>(in.)</u>	<u>L/D</u>
3000 (a)	22-24	3#5	2200	0.0410	2.3
3000 (b)	22-24	3#1	2250	0.0430	2.3

(a) Similar to EX-7085

(b) Similar to EX-7088

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABLE OF CONTENTS

	<u>Page</u>
SYNOPSIS.	1
TABLE OF CONTENTS	2
AUTHORITY	3
REFERENCES.	3
BACKGROUND.	3
OBJECT OF TEST.	4
PERIOD OF TEST.	4
DESCRIPTION OF ITEMS UNDER TEST	4
PROCEDURE	5
RESULTS AND DISCUSSION.	5
CONCLUSIONS	8
RECOMMENDATIONS	9
APPENDIX A - TABULATION OF FIRING DATA.	1-13 (Incl)
APPENDIX B - GRAPHICAL REPRESENTATION OF FIRING DATA.	1-6 (Incl)
APPENDIX C - PRESSURE-TIME CURVES	1-4 (Incl)
APPENDIX D - DISTRIBUTION	1-5 (Incl)

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive
-----PART BINTRODUCTION

1. AUTHORITY:

The tests conducted herein were authorized by reference (b) under Task Assignment NPG-Re2d-61-1-53 as established by reference (a).

2. REFERENCES:

- a. BUORD Conf ltr NP9 Re2d-CNB:aph Ser 42692 of 29 July 1952
- b. BUORD Conf ltr Re2d-CNB:dad NP9 Ser 55117 of 13 Apr 1953
- c. BUORD Conf ltr Re2d-CNB:jd NOrd 9691 Ser 55201 of 14 Apr 1953 to E. I. du Pont Co., Inc.
- d. NPG Conf Report No. 984 of 18 Aug 1952
- e. BUORD Conf ltr Re2d-CNB:dad S78-1(54) Ser 59809 of 10 July 1953
- f. Description Sheets of Manufacture and Closed Bomb Data

3. BACKGROUND:

Reference (a) set up the general task for development of a cool propellant for the 5"/54 caliber gun. Reference (b) requested EX-7084 through EX-7089 be fired for ballistic assessment in the 5"/54 caliber gun, Mk 18 with the 60 lb. projectile in the 22-24 tsi pressure range at a velocity of 3000 f/s. Reference (b) described these propellants as cool picrite powders with nominal flame temperatures around 2180 to 2250 °K prepared in accordance with reference (c). Reference (b) further requested the Naval Proving Ground to recommend an optimum granulation (based on the results of the subject powders) for manufacture of a large lot of cool picrite powder for the continuation of erosion trials in the 5"/54 caliber gun presently being fired with EX-6883, as reported in reference (d). Reference (e) stated that the near-term objective in the 5"/54 caliber gun with the 60 lb. projectile is now being reduced from the original goal of velocities in the 3000 - 3100 f/s range to 2800 f/s because of projectile band failure at the higher velocities.

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

4. OBJECT OF TEST:

a. To determine whether the subject propellants are ballistically satisfactory in the 5"/54 caliber gun, Mk 18, at 3000 f/s velocity in the 22-24 tsi pressure range with the 60 lb. projectile.

b. To obtain data incident to the manufacture of a large lot of cool picrite powder for continuation of erosion trials in the 5"/54 caliber gun.

5. PERIOD OF TEST:

a. Dates Project Letters:	29 Jul 1953
	13 Apr 1953
b. Date Material Received:	8 Apr 1953
c. Date Commenced Test:	22 Apr 1953
d. Date Test Completed:	26 May 1953

PART CDETAILS OF TEST

6. DESCRIPTION OF ITEMS UNDER TEST:

Reference (f) described the subject propellants as follows:

a. Chemical Composition:

	<u>EX-7084</u>	<u>EX-7085</u>	<u>EX-7086</u>
Nitrocellulose (13.20%N)	19.84%	20.09%	19.41%
Nitroglycerin #3	11.88	11.99	11.95
Picrite	60.01	59.77	60.13
Centralite	1.96	1.91	1.89
Dibutylphthalate	6.31	6.24	6.62
Lead Carbonate (added)	0.97	0.95	0.92
Flame Temp. (°K)	2211	2202	2169
	<u>EX-7087</u>	<u>EX-7088</u>	<u>EX-7089</u>
Nitrocellulose (12.20%N)	20.30%	20.62%	20.45%
Nitroglycerin	13.86	12.47	12.30
Picrite	58.17	59.03	58.22
Centralite	1.85	1.90	1.77
Dibutylphthalate	5.82	5.98	5.82
Lead Carbonate (added)	0.93	0.93	0.94
Flame Temp. (°K)	2321	2244	2260

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

b. Grain Geometry and Closed Bomb Data:

<u>Sample</u>	<u>Length (in)</u>	<u>Diameter (in)</u>	<u>Av. Web (in)</u>	<u>No. of Perfs.</u>	<u>RQ (%)</u>	<u>RF (%)</u>
EX-7084	0.5193	0.2157	0.0369	7	107.8(a) 96.8(b) 119.1(c)	105.3(a) 93.0(b) 95.5(c)
EX-7085	0.5258	0.2301	0.0405	7	98.2(a) 88.2(b) 108.5(c)	104.5(a) 92.3(b) 94.8(c)
EX-7086	0.5479	0.2420	0.0424	7	86.7(a) 77.8(b) 95.7(c)	104.2(a) 92.0(b) 94.5(c)
EX-7087	0.5267	0.2303	0.0404	7	113.3(a) 99.9(b) 123.0(c)	110.3(a) 96.5(b) 99.8(c)
EX-7088	0.5514	0.2428	0.0433	7	98.1(a) 86.6(b) 106.6(c)	107.5(a) 94.0(b) 97.3(c)
EX-7089	0.5809	0.2542	0.0462	7	95.0(a) 83.8(b) 103.3(c)	107.2(a) 93.8(b) 97.1(c)

(a) Based on EX-6586 as 100% at 90°F

(b) Based on EX-6883 as 100% at 90°F

(c) Based on EX-7001 as 100% at 90°F

7. PROCEDURE:

The subject propellants were fired in the 5"/54 caliber gun Mk 18-0 for charge determination. Muzzle velocities, maximum pressures (copper crusher), and ejection times were recorded. Pressure time records on the subject powders were obtained in both the Mk 16-0, and Mk 18-0 gun. All charges were assembled at PPD (Production Packing Depth).

8. RESULTS AND DISCUSSION:

The results of the subject tests are given in detail in the Appendices and are summarized below:

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

a. Uniformity:

Date 1953	Powder	PPD (in)	Charge (lb)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	No. of Rounds
4-22	EX-7084	10.5	16.00	2539±2	16.6±0.1	18±0	2
"	"	5.7	19.50	2877±3	23.5±0.5	16±1	5
"	EX-7085	8.1	18.00	2673±5	17.0±0.1	18±2	2
"	"	3.3	21.60	3000±4	23.6±0.6	16±1	5
"	EX-7086	6.7	19.00	2649±4	15.3±0.1	19±2	2
"	"	1.4	22.90	2992±5	21.1±0.5	16±1	5
4-23	EX-7087	9.1	17.00	2711±2	18.8±0.4	18±2	2
"	"	6.3	19.00	2901±3	22.7±0.2	16±1	5
"	EX-7088	7.9	18.00	2668±7	16.4±0.2	19±1	2
"	"	3.8	21.00	2937±4	20.7±0.5	17±1	5
"	EX-7089	6.6	19.00	2706±1	15.4±0.1	20±1	2
"	"	2.0	22.30	3001±4	21.0±0.5	16±1	5
4-29	EX-7084	5.6	19.50	2876±5	24.4±0.2	18±1	2
"	EX-7085	3.2	21.60	2993±8	25.2±0.2	19±2	2
"	EX-7086	1.2	22.99	2990±7	23.1±1.4	19±2	2
"	EX-7087	5.7	19.30	2908±2	25.1±0.1	18±2	2
"	EX-7088	2.7	21.70	2996±11	24.0±0.5	20±0	2
"	EX-7089	1.9	22.29	2977±1	21.0±0.3	21±0	2
5-12	EX-6883	7.3	18.50	2827±3	18.0±0.1	19(a)	2
"	"	4.8	20.28	2994±1	20.9±0.2	20±1	5
"	"(b)	4.8	20.28	2997±3	21.2±0.1	19±1	5
"	EX-7085	7.3	18.50	2719±2	18.2±0.1	17±0	2
"	"	3.1	21.60	2995±2	23.7±0.5	17±1	5
"	EX-7086	6.5	19.00	2649±2	15.4±0.1	19±1	2
"	"	1.1	22.99	3004±5	22.2±0.5	17±1	5
5-15	EX-7087	8.9	17.00	2708±3	19.6±0.4	20±1	2
"	"	4.6	20.04	2994±3	25.2±0.3	17±1	5
"	EX-7088	7.7	18.00	2669±1	16.6±0.0	18±0	2
"	"	2.6	21.70	3006±9	22.8±0.6	17±1	5
"	EX-7089	6.4	19.00	2697±5	15.5±0.6	19±0	2
"	"	1.8	22.29	2997±7	21.5±0.3	17±0	5
5-21	EX-7085	2.5	21.70	2989±5	22.5±0.1	19±0	3
"	"	4.1	20.50	2881±2	20.5±0.1	18±2	2
"	EX-7088	2.5	21.60	2991±8	22.3±1.0	18±2	3
"	"	7.5	18.00	2664±1	16.2±0.1	18±0	2
"	EX-7087	2.5	20.10	2986±4	22.6±0.5	17±1	3
"	"	6.4	17.50	2732±3	18.2±0.1	18±0	2
"	EX-7084	2.5	20.80	2979±10	24.2±1.1	18±2	4
"	"	6.6	18.00	2726±5	18.8±0.5	18±0	2
5-26	EX-7084	2.5	21.03	3005±6	25.3±0.4	16±1	2
"	EX-7087	2.5	20.24	2991±4	23.1±0.2	17±2	2
"	EX-6822	2.5	20.60	2998±1	20.8±0.2	19±0	2
"	EX-6882	2.5	20.42	2996±5	20.6±0.2	19±0	2

(a) Based on 1 round

(b) XC-M5B primer

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

b. Charge determination:

Gun: 5"/54 caliber, Mk 18 Mod 0, No. 16077

<u>Powder</u>	<u>Charge (lb)</u>	<u>PPD (in)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Results</u>
EX-7084	20.77	4.2	3000	26.0	Too quick
EX-7084	21.03	2.5	3000	24.6	Too quick
EX-7085	21.60	3.5	3000	23.6	
EX-7085	<u>21.66</u>	<u>3.5</u>	<u>3000</u>	<u>23.9</u>	
EX-7085(a)	21.63	3.5	3000	23.8	Satisfactory
EX-7085	21.82	2.5	3000	22.7	Satisfactory
EX-7086	22.99	1.5	3000	21.3	
EX-7086	<u>22.94</u>	<u>1.5</u>	<u>3000</u>	<u>22.1</u>	
EX-7086(a)	22.97	1.5	3000	21.7	Too slow
EX-7087	20.04	5.0	3000	24.7	
EX-7087	<u>20.10</u>	<u>4.9</u>	<u>3000</u>	<u>25.3</u>	
EX-7087(a)	20.07	5.0	3000	25.0	Too quick
EX-7087	20.24	2.5	3000	22.8	Satisfactory
EX-7088	21.70	3.0	3000	23.3	
EX-7088	<u>21.63</u>	<u>3.1</u>	<u>3000</u>	<u>22.7</u>	
EX-7088(a)	21.67	3.1	3000	23.0	(b)
EX-7088	21.70	2.5	3000	22.4	Satisfactory
EX-7089	22.29	2.2	3000	21.0	
EX-7089	<u>22.32</u>	<u>2.2</u>	<u>3000</u>	<u>21.6</u>	
EX-7089(a)	22.31	2.2	3000	21.3	Too slow
EX-6883	20.34	2.5	3000	21.0	(c)

(a) Average of 2 gun firings

(b) Ballistically satisfactory at PPD (Production Packing Depth) of 3#1 but unsatisfactory at proposed 3#5 PPD.

(c) Reported in reference (d).

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

c. EX-7085 was satisfactory ballistically in that a velocity of 3000 f/s was obtained within the prescribed pressure range of 22-24 tsi and proposed PPD of 3#5.

EX-7088 was ballistically satisfactory at a PPD of 3#1 but unsatisfactory at the 3#5 level.

EX-7084 and EX-7087 were too quick for the 5"/54 caliber gun under standard powder packing conditions.

EX-7086 and EX-7089 were too slow for the 5"/54 caliber gun at 3000 f/s velocity in that only 21.7 and 21.3 tsi pressure was obtained at 1#5 and 2#2 PPD respectively.

d. EX-7084, EX-7085, EX-7087, and EX-7088 were fired for ballistic assessment at 3000 f/s with loose packing of 2#5. All of the propellants tested gave satisfactory ballistics and uniformities except EX-7084 which was too fast.

e. The pressure-time curves obtained with the subject powders had pronounced steps occurring in the pressure rise region and were inferior to those obtained with either EX-6822 or EX-6883.

PART D

CONCLUSIONS

9. From the results of the subject tests, it is concluded that:

a. EX-7085 was ballistically satisfactory for use in the 5"/54 caliber gun with the 60 lb. projectile at a velocity of 3000 f/s.

b. EX-7088 was ballistically satisfactory at a velocity of 3000 f/s at a PPD of 3#1 but unsatisfactory at the proposed PPD of 3#5.

c. Satisfactory ballistics were obtained at 3000 f/s velocity at a PPD of 2#5 for EX-7085, EX-7087, and EX-7088.

d. The pressure-time curves obtained with the subject propellants had pronounced steps occurring in the pressure-rise region and were inferior to those obtained with either EX-6822 or EX-6883.

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

PART ERECOMMENDATIONS

10. From the results of the subject tests, the following recommendations for a powder granulation as requested in reference (b) are as follows:

<u>Velocity</u> (f/s)	<u>Pressure</u> (t.s.i.)	<u>Approx.</u> PPD	<u>Flame Temp.</u> °K	<u>Av. Web</u> (in)	<u>L/D</u>
3000(a)	22-24	3#5	2200	0.0410	2.3
3000(b)	22-24	3#1	2250	0.0430	2.3

(a) Similar to EX-7085

(b) Similar to EX-7088

CONFIDENTIAL

NPG REPORT NO. 1194

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

The tests upon which this report is based were conducted by:

J. A. KRYSZTOFIK, Head of Test Branch
Interior Ballistics Division
Armament Department

This report was prepared by:

J. A. KRYSZTOFIK, Head of Test Branch
Interior Ballistics Division
Armament Department

This report was reviewed by:

D. C. CAIN, Head of the Interior Ballistics Division
Armament Department
L. C. KLINGAMAN, Commander, USN
Armament Officer
Armament Department
C. C. BRAMBLE, Director of Research, Ordnance Group

APPROVED: J. F. BYRNE
Captain, USN
Commander, Naval Proving Ground



E. A. RUCKNER
Captain, USN
Ordnance Officer
By direction

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive
-----TABULATION OF FIRING DATA

Gun: 5"/54 Caliber,
Mk 18-0, No. 16077 ESR = 214.5 D₀ = 5.009
Mk 16-0, No. 15453 ESR = 114.8 D₀ = 5.018

Projectile: Mk 41-0 (60.00 lb) Empty

Cartridge Case: Mk 7-0 (NGF) Brass

Primer: Mk 45

Lead Foil: None

Plug: Cork

Wad and Spacer: Cardboard, NGF Dwg. No. 132664 Pc. Nos. 18 and 15

Powder Temp: 90°F

Note: Velocity and pressure corrected for variation of projectile weight to 60.00 lb nominal

CONFIDENTIAL

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 22 April 1953 (Continued)

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
20	EX-7085	2.8	22.00	3058	25.7	14	25	125
21	EX-7086	6.7	19.00	2652	15.3	17	0	150
22	"	"	"	2645	15.2	20	"	"
	Mean of 2 rounds		19.00	2649±4	15.3±0.1	18±2		
23	EX-7086	3.3	21.50	2865	18.5	18	0	150
24	"	1.4	22.90	3003	21.9	17	100	100
25	"	"	"	2994	21.2	"	"	"
26	"	"	"	2992	21.3	18	75	125
27	"	"	"	2983	20.2	14	"	"
28	"	"	"	2987	20.7	15	Tr	150
	Mean of 5 rounds		22.90	2992±5	21.1±0.5	16±1		
29	EX-7087	10.5	16.00	2608	16.6	17	0	150
30	"	9.1	17.00	2711	18.9	19	"	"
31	"	7.0	18.50	2863	22.6	14	Tr	"
32	EX-7088	9.3	17.00	2575	14.5	26	0	"
33	"	7.9	18.00	2667	15.8	28	0	"
34	"	5.9	19.50	2809	18.3	-	"	"
35	EX-7089	6.6	19.00	2714	15.8	-	"	"
36	"	3.8	21.00	2889	18.7	16	"	"

(a) Conditioning round - not used

CONFIDENTIAL
SECURITY INFORMATION

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 23 April 1953

Gun: Mk 18-0, No. 16077

Rd. No.	Powder	PPD (in.)	Charge (lbs.)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	Flesh (%)	Smoke (%)
1 (a)	EX-7087	9.1	17.00	2705	18.4	16	0	150
2	"	"	"	2712	18.4	"	"	"
3	"	"	"	2709	19.2	19	"	"
	Mean of 2 rounds		17.00	2711±2	18.8±0.4	18±2		
4	EX-7087	7.0	18.50	2861	22.5	18	0	150
5	"	6.3	19.00	2904	22.7	15	"	"
6	"	"	"	2902	22.9	16	"	"
7	"	"	"	2901	22.5	17	"	"
8	"	"	"	2892	22.5	18	"	"
9	"	"	"	2905	23.0	15	"	"
	Mean of 5 rounds		19.00	2901±3	22.7±0.2	16±1		
10	EX-7087	5.8	19.30	2918	22.7	15	0	150
11	EX-7088	7.9	18.00	2674	16.5	18	"	"
12	"	"	"	2661	16.2	19	"	"
	Mean of 2 rounds		18.00	2668±7	16.4±0.2	19±1		
13	EX-7088	5.9	19.50	2797	18.1	17	0	150
14	"	3.8	21.00	2930	19.9	19	"	"
15	"	"	"	2942	21.1	17	"	"
16	"	"	"	2936	20.3	"	"	"
17	"	"	"	2934	20.7	15	"	"
18	"	"	"	2942	21.7	17	"	"
	Mean of 5 rounds		21.00	2937±4	20.7±0.5	17±1		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 23 April 1953 (Continued)

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
19	EX-7088	3.0	21.60	3008	23.3	17	100	100
20	EX-7089	6.6	19.00	2705	15.4	19	"	"
21	"	"	"	2706	15.4	20	0	150
	Mean of 2 rounds		19.00	2706±1	15.4±0.1	20±1		
22	EX-7089	3.8	21.00	2881	17.9	19	0	150
23	"	2.0	22.30	3002	21.1	15	"	"
24	"	"	"	2999	21.4	"	Tr	"
25	"	"	"	3005	20.6	18	"	"
26	"	"	"	3006	21.8	16	"	"
27	"	"	"	2991	20.3	17	0	"
	Mean of 5 rounds		22.30	3001±4	21.0±0.5	16±1		
28	EX-7089	1.5	23.00	3061	22.9	16	100	100

(a) Conditioning round - not used

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 29 April 1953

Gun: Mk 16-0, No. 15453

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
1 - 10	REPORTED SEPARATELY							
11	EX-7084	5.6	19.50	2871	24.2	17	0	125
12	"	"	"	2881	24.6	19	"	"
	Mean of 2 rounds		19.50	2876±5	24.4±0.2	18±1		
13	EX-7085	3.2	21.60	3000	25.3	17	Tr	125
14	"	"	"	2985	25.0	20	100	100
	Mean of 2 rounds		21.60	2993±8	25.2±0.2	19±2		
15	EX-7086	1.2	22.99	2997	24.5	17	75	100
16	"	"	"	2983	21.7	21	"	"
	Mean of 2 rounds		22.99	2990±7	23.1±1.4	19±2		
17	EX-7087	5.7	19.30	2906	25.0	19	75	100
18	"	"	"	2909	25.2	16	"	"
	Mean of 2 rounds		19.30	2908±2	25.1±0.1	18±2		
19	EX-7088	2.7	21.70	3007	24.4	20	75	100
20	"	"	"	2985	23.5	"	"	"
	Mean of 2 rounds		21.70	2996±11	24.0±0.5	20±0		
21	EX-7089	1.9	22.29	2976	21.3	21	75	100
22	"	"	"	2978	20.7	"	100	"
	Mean of 2 rounds		22.29	2977±1	21.0±0.3	21±0		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 12 May 1953

Gun: Mk 18-0, No. 16077

Rd. No.	Powder	PPD (in.)	Charge (lbs.)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	Flash (%)	Smoke (%)
1 (a)	EX-6883	7.3	18.50	2814	17.4	21	50	125
2	"	"	"	2824	17.9	-	0	"
3	"	"	"	2820	18.1	19	"	"
	Mean of 2 rounds		18.50	2827±3	18.0±0.1	19 (b)		
4	EX-6883	4.8	20.28	2992	20.8	19	80	125
5	"	"	"	2995	21.4	20	50	"
6	"	"	"	2995	20.7	21	80	"
7	"	"	"	2995	20.9	19	0	"
8	"	"	"	2994	20.9	"	80	"
	Mean of 5 rounds		20.28	2994±1	20.9±0.2	20±1		
9 (c)	EX-6883	4.8	20.28	2997	21.2	19	80	125
10 (c)	"	"	"	2995	21.2	"	"	"
11 (c)	"	"	"	3004	21.3	"	"	"
12 (c)	"	"	"	2997	20.9	21	"	"
13 (c)	"	"	"	2992	21.2	18	"	"
	Mean of 5 rounds		20.28	2997±3	21.2±0.1	19±1		
14	EX-6883	3.4	21.31	3089	22.6	18	80	125
15	EX-7085	7.3	18.50	2717	18.3	17	0	"
16	"	"	"	2720	18.1	"	"	"
	Mean of 2 rounds		18.50	2719±2	18.2±0.1	17±0		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 12 May 1953 (Continued)

Rd. No.	Powder	PPD (in.)	Charge (lbs.)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	Flash (%)	Smoke (%)
17	EX-7085	3.1	21.60	2994	23.1	16	50	125
18	"	"	"	2991	23.1	19	"	"
19	"	"	"	2977	24.4	16	Tr	"
20	"	"	"	2998	23.7	17	50	"
21	"	"	"	2996	24.3	16	0	"
	Mean of 5 rounds		21.60	2995±2	23.7±0.5	17±1		
22	EX-7085	2.6	22.00	3026	25.1	-	Tr	125
23	EX-7086	6.5	19.00	2647	15.3	19	0	"
24	"	"	"	2651	15.4	18	"	"
	Mean of 2 rounds		19.00	2649±2	15.4±0.1	19±1		
25	EX-7086	1.1	22.99	2994	21.6	18	50	125
26	"	"	"	3006	22.2	17	"	"
27	"	"	"	3006	22.5	16	0	"
28	"	"	"	3012	23.0	19	Tr	"
29	"	"	"	3001	21.6	17	50	"
	Mean of 5 rounds		22.99	3004±5	22.2±0.5	17±1		
30	EX-7086	0.6	23.40	3039	23.5	19	50	125

- (a) Conditioning round - not used
- (b) Based on one round
- (c) XC-M5B Primer

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 15 May 1953

Gun: Mk 18-O, No. 16077

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
1 (a)	EX-7087	8.9	17.00	2706	19.0	19	0	150
2	"	"	"	2705	19.2	"	"	"
3	"	"	"	2710	19.9	20	"	"
	Mean of 2 rounds		17.00	2708±3	19.6±0.4	20±1		
4	EX-7087	4.6	20.04	2996	25.6	19	Tr	150
5	"	"	"	2995	25.0	18	25	125
6	"	"	"	2988	25.1	15	Tr	150
7	"	"	"	2997	25.5	18	"	"
8	"	"	"	2992	24.6	16	"	"
	Mean of 5 rounds		20.04	2994±3	25.2±0.3	17±1		
9	EX-7087	4.4	20.14	3005	25.1	16	Tr	150
10	EX-7088	7.7	18.00	2668	16.6	18	0	"
11	"	"	"	2670	16.6	"	"	"
	Mean of 2 rounds		18.00	2669±1	16.6±0.0	18±0		
12	EX-7088	2.6	21.70	2995	22.3	16	Tr	150
13	"	"	"	3014	23.3	19	0	"
14	"	"	"	3009	23.1	16	Tr	"
15	"	"	"	3016	23.4	"	"	"
16	"	"	"	2995	21.8	18	25	125
	Mean of 5 rounds		21.70	3006±9	22.8±0.6	17±1		
17	EX-7088	2.1	22.10	3029	22.8	16	Tr	150
18	EX-7089	6.4	19.00	2702	16.0	19	0	"
19	"	"	"	2692	14.9	"	"	"
	Mean of 2 rounds		19.00	2697±5	15.5±0.6	19±0		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 15 May 1953 (Continued)

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
20	EX-7089	1.8	22.29	2997	21.6	17	100	100
21	"	"	"	3002	21.5	"	80	"
22	"	"	"	3011	22.0	"	"	"
23	"	"	"	2994	21.1	"	50	125
24	"	"	"	2983	21.1	19	0	150
	Mean of 5 rounds		22.29	2997±7	21.5±0.3	17±0		
25	EX-7089	1.3	22.70	3020	21.8	18	20	150

(a) Conditioning round - not used

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Rd. No.	Powder	PPD (in.)	Charge (lbs.)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	Flash (%)	Smoke (%)
	Gun: Mk 18-0, No. 16077							
1	EX-7085	6.9	18.50	2687	16.8	22	0	150
2	"	4.1	20.50	2882	20.5	19	"	"
3	"	2.5	21.70	2996	22.6	18	10	"
4	"	"	"	2984	22.3	19	0	"
5	"	"	"	2987	22.5	"	"	"
	Mean of 2 rounds		21.70	2989±5	22.5±0.1	19±0		
6	EX-7085	4.1	20.50	2879	20.4	16	0	150
	Mean of rounds 2 and 6		20.50	2881±2	20.5±0.1	18±2		
7	EX-7088	7.5	18.00	2665	16.1	18	0	150
8	"	4.7	20.00	2852	19.2	17	"	"
9	"	2.5	21.60	2995	22.8	16	10	"
10	"	"	"	2999	23.3	17	Tr	"
11	"	"	"	2979	20.9	20	10	"
	Mean of 3 rounds		21.60	2991±8	22.3±1.0	18±2		
12	EX-7088	7.5	18.00	2663	16.2	18	0	150
	Mean of rounds 7 and 12		18.00	2664±1	16.2±0.1	18±0		
13	EX-7087	6.4	17.50	2729	18.3	18	0	150
14	"	3.4	19.50	2925	21.6	"	"	"
15	"	2.5	20.10	2982	21.9	16	"	"
16	"	"	"	2993	23.2	18	"	"
17	"	"	"	2984	22.7	16	25	"
	Mean of 3 rounds		20.10	2986±4	22.6±0.5	17±1		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 21 May 1953 (Continued)

<u>Rd. No.</u>	<u>Powder</u>	<u>PPD (in.)</u>	<u>Charge (lbs.)</u>	<u>Velocity (f/s)</u>	<u>Pressure (t.s.i.)</u>	<u>Ejec. Time (millisec)</u>	<u>Flash (%)</u>	<u>Smoke (%)</u>
18	EX-7087	6.4	17.50	2734	18.1	18	0	150
	Mean of rounds 13 and 18		17.50	2732±3	18.2±0.1	18±0		
19	EX-7084	6.6	18.00	2731	19.2	18	0	150
20	"	3.6	20.00	2902	22.2	16	"	"
21	"	2.5	20.80	2975	23.3	19	10	"
22	"	"	"	2973	23.1	16	0	"
23	"	"	"	2998	26.4	"	25	"
24	"	"	"	2970	24.0	20	0	"
	Mean of 4 rounds		20.80	2979±10	24.2±1.1	18±2		
	Mean of rounds 21, 22 and 24		20.80	2073±2	23.5±0.4	18±2		
25	EX-7084	6.6	18.00	2721	18.3	18	0	150
	Mean of rounds 19 and 25		18.00	2726±5	18.8±0.5	18±0		

Ballistic Test of Cool Propellants EX-7084 to EX-7089 inclusive

TABULATION OF FIRING DATA (Continued)

Date: 26 May 1953


Gun: Mk 18-O, No. 16077

Rd. No.	Powder	PPD (in.)	Charge (lbs.)	Velocity (f/s)	Pressure (t.s.i.)	Ejec. Time (millisec)	Flash (%)	Smoke (%)
1 (a)	EX-7084	2.5	21.03	3006	26.1	16	0	150
2	"	"	"	2999	24.9	17	"	"
3	"	"	"	3010	25.6	15	Tr	"
	Mean of 2 rounds		21.03	3005±6	25.3±0.4	16±1		
4	EX-7087	2.5	20.24	2987	23.3	15	0	150
5	"	"	"	2995	22.9	19	"	"
	Mean of 2 rounds		20.24	2991±4	23.1±0.2	17±2		
6	EX-7088	2.5	21.70	3002	22.1	19	50	100
7	EX-7085	2.5	21.82	3011	24.3	18	0	150
8	EX-6822	2.5	20.60	2997	20.6	"	100	100
9	"	"	"	2998	20.9	19	"	"
	Mean of 2 rounds		20.60	2998±1	20.8±0.2	19±0		
10	EX-6883	2.5	20.42	2991	20.4	19	75	125
11	"	"	"	3001	20.8	19	"	"
	Mean of 2 rounds		20.42	2996±5	20.6±0.2	19±0		

(a) Conditioning round - not used

Ballistic Test of Cool Propellants

VELOCITY AND PRESSURE VS CHARGE




○ EX-7084 (Standard powder packing)

● EX-7084 (Loose powder packing)

Ballistic Test of Cool Propellants

VELOCITY AND PRESSURE VS CHARGE




CONFIDENTIAL

NPG REPORT NO 1194

Ballistic Test of Cool Propellants

VELOCITY AND PRESSURE VS CHARGE




○ EX-7086 (Standard powder packing)

● EX-7086 (" " ")

CONFIDENTIAL
SECURITY INFORMATION

Ballistic Test of Cool Propellants


VELOCITY AND PRESSURE VS CHARGE



- EI-7087 (Standard powder packing)
- EI-7087 (n n n)
- ⊕ EI-7087 (Loose powder packing)


Ballistic Test of Cool Propellants

VELOCITY AND PRESSURE VS CHARGE



Ballistic Test of Cool Propellants


VELOCITY AND PRESSURE VS CHARGE



○ EK-7089 (Standard powder packing)
● EK-7089 (" " ")


Ballistic Test of Cool Propellants EX-7084 to EX-7089 Inclusive

PRESSURE-TIME CURVES




Ballistic Test of Cool Propellants EX-7084 to EX-7089 Inclusive

PRESSURE-TIME CURVES



Ballistic Test of Cool Propellants EX-7084 to EX-7089 Inclusive

PRESSURE-TIME CURVES



Ballistic Test of Cool Propellants EX-7084 to EX-7089 Inclusive

PRESSURE-TIME CURVES

