

UNCLASSIFIED

AD 137831

Armed Services Technical Information Agency

Reproduced by

DOCUMENT SERVICE CENTER

KNOTT BUILDING, DAYTON, 2, OHIO

This document is the property of the United States Government. It is furnished for the duration of the contract and shall be returned when no longer required, or upon recall by ASTIA to the following address: Armed Services Technical Information Agency, Document Service Center, Knott Building, Dayton 2, Ohio.

NOTICE: WHEN GOVERNMENT OR OTHER DRAWINGS, SPECIFICATIONS OR OTHER DATA ARE USED FOR ANY PURPOSE OTHER THAN IN CONNECTION WITH A DEFINITELY RELATED GOVERNMENT PROCUREMENT OPERATION, THE U. S. GOVERNMENT THEREBY INCURS NO RESPONSIBILITY, NOR ANY OBLIGATION WHATSOEVER; AND THE FACT THAT THE GOVERNMENT MAY HAVE FORMULATED, FURNISHED, OR IN ANY WAY SUPPLIED THE SAID DRAWINGS, SPECIFICATIONS, OR OTHER DATA IS NOT TO BE REGARDED BY IMPLICATION OR OTHERWISE AS IN ANY MANNER LICENSING THE HOLDER OR ANY OTHER PERSON OR CORPORATION, OR CONVEYING ANY RIGHTS OR PERMISSION TO MANUFACTURE, USE OR SELL ANY PATENTED INVENTION THAT MAY IN ANY WAY BE RELATED THERETO.

UNCLASSIFIED

137831

597772

1, 1

THE OHIO STATE UNIVERSITY
RESEARCH FOUNDATION

REPORT

By

THE OHIO STATE UNIVERSITY
RESEARCH FOUNDATION
COLUMBUS 10, OHIO

NAVY RESEARCH SECTION
SCIENCE DIVISION
REFERENCE DEPARTMENT
LIBRARY OF CONGRESS

SEP 28 1949

Cooperator U.S. NAVY, OFFICE OF NAVAL RESEARCH

Contract Number N6onr-225, T.O. I

ONR Project Number NR 038 031

Investigation of VAPOR PRESSURE OF METALS AND METAL OXIDES.

Subject of Report Twelfth Quarterly Progress Report

Submitted by H.L. Johnston

Date July 1, 1949

FILE COPY
NAVY RESEARCH SECTION
SCIENCE DIVISION
LIBRARY OF CONGRESS
TO BE RETURNED

C7613

Xg

PROGRESS REPORT ON PROJECT RE-281

INVESTIGATION OF VAPOR PRESSURE OF METALS AND METAL OXIDES

Navy Contract Number N6onr-225, T.O.I
ONR Project Number NR 058 031

1. Personnel.

No change in personnel on this project during the last report period.

2. Vapor Pressure of Columbium.

The experimental work in columbium is nearly completed and the data is being processed for a technical report.

3. Vapor Pressure of Al_2O_3 .

About 15 runs were made with Al_2O_3 in a molybdenum Knudsen cell. Flat targets and hollow spherical quartz targets (with a 2 cm. hole for the vapor to enter) have been employed to determine whether or not Al_2O_3 dissociates in neighborhood of 1700 to 1900°C. The spherical quartz target was used to ascertain if the failure of the mass of the vapor evaporating from the cell to balance the mass intercepted by the target was due to thermal dissociation of the Al_2O_3 into non-condensable products or whether it was due to the fact that the accommodation coefficient for the condensation of Al_2O_3 on the target was not unity. The data indicates that Al_2O_3 dissociates into an oxygen deficient product. Vapor pressure measurements by these methods will be abandoned for the time being. A technical report on the data so far obtained will be prepared as this material may be of use to research workers employing Al_2O_3 in high temperature research.

4. Vapor Pressure of Zirconium.

A zirconium Langmuir ring was prepared by first fusing some pure zirconium in a low pressure argon arc furnace and then machining the resultant ingot into a ring. This method of fusion yields almost completely uncontaminated ingots since a water cooled copper crucible is employed and the molten metal does not wet the crucible. Utilization of a tungsten rod as an anode eliminates the possibility of contamination with the anode material.

A number of runs have been made with zirconium and the work is progressing well.

5. Vapor Pressure of Boron.

A boron carbide liner inside a graphite Knudsen cell has been made by heating boron and graphite to 2100°C.

Successful measurements of the boron vapor pressure have been made but the work is slow and tedious. A new Knudsen cell has to be made about every third run and many hours are consumed in preparing the Knudsen

cells. However, these measurements although laborious are very promising.

6. The Vapor Pressure of Chromium.

A chromium Langmuir ring has been prepared by the same method employed in the preparation of the zirconium ring. Preliminary vacuum treatment of the sample will be started.

7. The Vapor Pressure of Aluminum and Tantalum.

Work on these two materials have been deferred for the time being.

8. Technical Reports.

Technical reports are being prepared for gallium and B_2O_3 . Their titles will be,

Tech. Report No. 4, "The Vapor Pressure of Inorganic Substances. II B_2O_3 ".

Tech. Report No. 5, "The Vapor Pressure of Inorganic Substances. III Gallium".

NOTE: In submitting this report it is understood that all provisions of the contract between The Foundation and the Cooperator and pertaining to publicity of subject matter will be rigidly observed.

Investigator Rudolph Speiser Date JUL 1 1949

Supervisor Herivel L Johnston Date JUL 1 1949

For The Ohio State University Research Foundation

Executive Director James S. Ames Date 9/16/49
W.R.B.