

UNCLASSIFIED

AD 260 957

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

260957

2-4-19
XEROX

150

Technical Report

PROTECTION OF EXPOSED PARTS OF
SHELTERS AGAINST THERMAL RADIATION
FROM MEGATON WEAPONS

28 July 1961

CATALOGED BY ASTIA
AS AD No. _____



U. S. NAVAL CIVIL ENGINEERING LABORATORY
Port Hueneme, California

PROTECTION OF EXPOSED PARTS OF SHELTERS AGAINST THERMAL RADIATION FROM MEGATON WEAPONS

Y-F011-05-401(c)

Type C Final Report

by

F. W. Brown, III, A. Y. Eliason

OBJECT OF TASK

To determine the effects of high-intensity thermal radiation resulting from the explosion of nuclear weapons on the exposed portions of certain defensive structures, and to propose protective measures.

ABSTRACT

In a theoretical study of the thermal radiation effects on underground shelters that are designed to withstand 100 psi, it has been found that for surface bursts of one megaton or greater the 100-psi contour is within the fireball. A 10-megaton weapon has been taken as an example and calculations have been made for the thermal flux received by a structure at a distance corresponding to the 100-psi overpressure. The total heat flux is of the order of 60,000 cal per cm². Possible measures for the protection of entrance coverings and ventilation valves are examined. Conventional heat-shielding materials seem to be impractical for these immense thermal radiation levels. The degree of protection necessary makes all but the most sophisticated materials impractical.

Simple carbon and graphite shields are discussed and more complicated shielding systems are proposed for future experimental studies.

Qualified requesters may obtain
copies of this report from ASTIA

STATEMENT OF THE PROBLEM

Nuclear weapons explosions described in the publication "The Effects of Nuclear Weapons"¹ indicate that the damage due to thermal radiation can be reduced manyfold by appropriate shielding. Also, sufficient shielding can be provided for survival against the ionizing radiation.^{1,2} It is now apparent that survival in shelters is possible at a distance from the center of the explosion of megaton weapons that is even less than the maximum radius of the fireball, if protection of the exposed portions is provided against thermal radiation.

Figure 1 shows the time, temperature, and distance values expected from a 10-megaton surface burst. If one considers the comparable effects of nuclear weapons, he can calculate the radius of the fireball and the position of the 100-psi contour.^{3,4} This is given in Figure 2 for weapons of various sizes. It can be seen that for bombs greater than 0.5 megaton, the pressure contour of 100 psi or more is within the fireball.

Shelters for the protection of people from blast damage and radioactive fallout are now being designed, with an overpressure criterion of 100 psi. The shelters are usually buried under six feet or more of earth for nuclear radiation protection. This depth of cover is more than adequate for the protection of the occupants from nuclear, thermal, and blast radiation, but the problem exists of protecting the exposed ventilation valves and entrance coverings so that they may operate as designed when subjected to very high thermal radiation levels.

APPROACH TO THE PROBLEM

Aluminum and steel are the proposed materials of construction for the valves and entrance coverings. These must be preserved from melting or other failure, and the mechanical functioning of the blast closure valves must be maintained.

Experiments in laboratories as well as at nuclear weapons test sites indicate that damage of exposed shelter appurtenances by thermal radiation can be minimized by the application of highly reflective coatings,⁵ by the use of refractory materials to reduce heat conduction, and by use of coatings of materials with high latent heats of fusion and vaporization to serve as heat sinks.⁶

maximum diameter of fireball at
about 30-40 sec

8,000 C 3.2 sec

4,100 C 1 sec

R at second
temperature
maximum

Figure 1. Distances, times, and temperatures for a 10-megaton
weapon burst.




Figure 2. Thermal and pressure characteristics of nuclear weapons.

Much experimental work has been done on the thermal properties of materials for the nose cones of missiles and re-entry vehicles.^{6,7,8,9,10,11} The specifications for these are different from the problem under investigation, because in addition to the high thermal fluxes, the nose cones are subject to supersonic wind velocities during their entire time of re-entry. H. A. King⁸ has suggested six basic techniques that can be applied to the control of large heat fluxes such as those produced in the nose cones of missiles. They are:

<u>Technique</u>	<u>Commonly Used Name</u>
Conduction	1. Heat sink 2. Tubular
Convection	1. Transpiration cooling 2. Film cooling
Radiation	1. Radiation and/or reflection
Combination	1. Insulation 2. Ablation
Change of State	1. Physical 2. Chemical (endothermic reaction)
Electrical-Magnetic	1. Magnetohydrodynamic 2. Thermoelectric

The technique most suitable for heat shielding within the fireball of a nuclear weapon appears to be a combination of ablation and insulation.⁶ By ablation, we mean the removal of the insulating or protective material by melting and vaporizing, by sublimation and removal by a high gas velocity.

Heat shielding for industrial high-temperature processes can be provided by many different refractory materials, such as the carbides, nitrides, oxides, and sulfides of many elements. However, for high temperatures, such as are found in the fireball of nuclear weapons, these materials and all others quickly decompose into gaseous constituents. Ablation can absorb most of the heat received at the surface of the underlying structures and hence permit only a small portion of the incident energy to be stored in or pass to the solid of the structures.

The ablation rate depends on the rate of heat transfer to the surface and is influenced by the presence of products of ablation, their absorption of thermal radiation, the surface reflectivity of the protective coating, and the gas velocity across the surface. If the protective material is a chemical compound, it may dissociate after or during sublimation or evaporation and hence dissipate most of the heat transferred to the front face of the protective coating.⁹ On the other hand, if the protective coating is a refractory metal such as tungsten, heat is produced in its oxidation. Experiments by Bloxsom¹¹ have shown that the heat of oxidation of the gaseous metal is not transferred to the solid surface, because the oxidation does not occur in the immediate vicinity of the surface.

Our study indicates that the exposed valves and entrance coverings can be protected from thermal destruction by means of heat shielding only by excessive thicknesses of single materials that utilize the process of ablation in combination with insulation.

THEORETICAL CONSIDERATIONS

Shielding by ablation is most effective if the shielding material has a relatively low sublimation temperature, a large heat of sublimation, and a sufficiently low thermal diffusivity, so that only a relatively small amount of the total heat is transferred to the shielding material and thus to the solid itself during a short exposure. It is desirable that the protective material have a low vaporization temperature to absorb the maximum amount of heat by ablation so that the temperature of the protected aluminum or steel may be kept below the melting point with a minimum thickness of shielding.

Georgiev, Hildago, and Adams¹⁰ have shown that for satellite re-entry, the energy blocked by mass injection, i.e., the energy absorbed by the vapor as it diffuses across the boundary layer, is large in comparison with the latent heat of vaporization or the heat of sublimation. Teflon, for example, is found by these authors to have a heat of ablation five times greater than the heat of sublimation at the stagnation point heat-transfer rate for a typical satellite trajectory.

Shielding by sublimation at the surface of a solid, instead of melting and subsequent vaporization, is not only much simpler in analysis, but also avoids the instability of a liquid film. The simple theory used in the calculations for this study assumes a quasi-steady state; i.e., the rate of energy transfer across the surface is equal to the rate of energy absorption by ablation. After the temperature

of the surface reaches the sublimation point, it remains approximately constant and provides a temperature gradient across the solid heat shield. If the sublimation temperature is high, the shield must have a coefficient of conductivity sufficiently low to keep the aluminum or steel well below its melting point.

The energy liberated in the explosion of a 10-megaton nuclear weapon (the size assumed for this study) is 10^{16} calories, of which approximately one third is thermal.¹² At a distance of 7,000 feet from the center of a surface burst the over-pressure is about 100 psi; however, the maximum radius of the fireball is 11,200 feet. Calculations show that for a surface at this point, the Q received by any surface at a distance d with the fireball subtending an angle ϕ is:

$$Q = Q_0 \frac{\pi}{2} \sin^2 \phi$$

Where: Q = Energy received per cm^2

Q_0 = Energy emitted per cm^2 for unit solid angle summed over all wavelengths at the surface of the fireball

This only holds for $\phi \leq 90^\circ$. After that, $Q = 2\pi Q_0$ because the object is engulfed by and is at the temperature of the fireball. The energy received has been calculated in cal per cm^2 sec. These calculations assume that the energy received per unit area near the edge of the fireball is the same as the energy emitted per unit area at its surface. The temperature at this location certainly is as high but may be higher than at the surface of the fireball. Also shielding may occur by energy-absorbing dust clouds. Consequently, these calculations represent an approximate value of the energy received per unit area. To our knowledge no measurements of Q_0 have been made in this region of the fireball on any nuclear tests.

The Q received at a distance of 7,000 feet is plotted in Figure 3. Integration of this curve to 45 seconds shows that on a surface at a distance of 7,000 feet, the total Q received is about 60,500 cal per cm^2 . Integration to 30 seconds, temperature = 3,680 C, yields 59,700 cal per cm^2 .

If the weight of the shielding material per unit area is to be kept to a minimum it must have a large heat of ablation. A survey of the literature shows that carbon, carbides, and fluorocarbon resins can be adapted to the high-temperature shielding of aluminum and steel.¹¹ The calculations that follow illustrate the shielding properties of carbon and Teflon.




Figure 3. Thermal energy as a function of time for a 10-megaton surface burst.

CALCULATIONS — CARBON

Symbols and numerical values used in the equations:

C_p - Specific heat of carbon, 0.4 cal per gram*

d - Thickness in cm of carbon ablated

k - Coefficient of thermal conductivity, 0.25 cal per cm sec deg C*

m - Mass per cm^2 of carbon evaporated

Q_s - Heat of sublimation of carbon, 14,300 cal per gram*

T - Temperature in deg C at x cm from hot carbon surface after time, θ

T_0 - Initial temperature of carbon, 20 C

T_s - Temperature at which sublimation of carbon occurs, 3,680 C

x - Thickness of carbon needed for insulation

α - Thermal diffusivity constant $= k/C_p\rho = 0.25 \text{ cm}^2 \text{ per sec}^*$

θ - Time in seconds for application of T_s to carbon surface

ρ - Specific gravity of carbon, 2.2 grams per cm^3 *

In order to protect the blast closure valve, the temperature of the back of the aluminum cover (thickness, 7mm) should not exceed 700 F or 375 C. Graphite is ablated until the temperature of the fireball drops to 3,680 C, in about 30 seconds. The thickness of graphite ablated until $\theta = 30$ seconds would be:

$$Q = m C_p (T_s - T_0) + m Q_s$$

$$59,700 = 0.4 (3,680) m + 14,300 m$$

* Data given by Bloxson¹¹ and Litz¹³ show that the thermal properties of carbon and graphite are affected greatly by the raw materials and fabrication procedures used in its production. Within limits the manufacturers of these products can and will adjust the properties of the finished product to specifications.

$$m = \frac{59,700}{15,800} = 3.78 \text{ grams}$$

$$d = \frac{3.78}{2.2} = 1.72 \text{ cm}$$

The temperature of the surface of the carbon is approximately constant during the ablation process (3,680 C). The back surface of the aluminum cover must not exceed 375 C during the 30-second exposure; accordingly, the front surface must not reach 446 C. The thickness of graphite to provide this insulation can be calculated by the following formula:¹⁴

$$T = T_s \operatorname{erfc} \frac{x}{2 \sqrt{\alpha \theta}}$$

$$446 = 3,680 \operatorname{erfc} \frac{x}{2 \sqrt{0.25 (30)}} = 3,680 \operatorname{erfc} \frac{x}{5.5}$$

$$\text{Therefore: } \operatorname{erfc} \frac{x}{5.5} = \frac{446}{3,680} = 0.121$$

$$\text{But: } \operatorname{erfc} (1.09) = 0.121$$

$$\text{Therefore: } \frac{x}{5.5} = 1.09$$

$$x = 6 \text{ cm}$$

$$\text{Hence: } \text{Total thickness needed} = d + x = 1.72 + 6.0 = 7.7 \text{ cm}$$

In these calculations, $\theta = 30$ seconds was assumed to be the time for the temperature of the fireball to drop below 3,625 C. Any shielding due to mass injection was neglected, so the thickness of 7.7 cm of graphite carbon represents an upper limit. However, what will happen to the graphite due to thermal shock with possible spalling and erosion at high temperatures is still unknown. The values of thermal flux at the maximum rate of delivery are 10 times those in any laboratory tests that have been performed.

Experimental checks on the efficiency of carbon as a heat shielding agent should be made. Other factors to be investigated are:

1. Oxidation of graphite
2. Resistance to thermal shock
3. Thermal expansion coefficient and mechanical strength
4. The use of pyrolytic graphite,¹⁵ which has values of thermal conductivity differing by a factor of one to about 1,000 in different directions

CALCULATIONS — TEFLON (Polytetrafluoroethylene Resin)

Symbols and numerical values used in the equations:

C_p - Specific heat at constant pressure at 0 C, 0.223 cal per gram

d - Thickness in cm of Teflon ablated

k - Coefficient of thermal conductivity, 0.7×10^{-3} cal per cm sec deg C

m - Mass per cm^2 of Teflon evaporated

Q_{eff} - Effective heat of ablation, 2,200 cal per gram

T_0 - Initial temperature of Teflon, 20 C

T_s - Maximum surface temperature, 640 C

x - Thickness of Teflon needed for insulation

α - Thermal diffusivity, $k/C_p\rho = 1.4 \times 10^{-3} \text{ cm}^2 \text{ sec}$

θ - Time in seconds for application of T_s to Teflon surface

ρ - Specific gravity of Teflon, 2.1-2.2 grams per cm^3

The thickness of Teflon ablated would be:

$$Q = m C_p (T_s - T_o) + m Q_{\text{eff}}$$

$$60,500 = 0.223 (640) m + 2,200 m = (142 + 2,200) m$$

$$2,340 m = 60,500$$

$$d = \frac{m}{\rho} = \frac{60,500}{(2.2) (2,340)} = 11.7 \text{ cm}$$

The temperature of the aluminum valve surface should not be greater than 446 C; therefore, an additional thickness of Teflon is needed, given by the following:

$$T = T_s \operatorname{erfc} \frac{x}{2 \sqrt{\alpha \theta}}$$

$$446 = 640 \operatorname{erfc} \frac{x}{2 \sqrt{(0.0014) (30)}} = 640 \operatorname{erfc} \frac{x}{0.41}$$

$$\text{Therefore: } \frac{446}{640} = 0.69 = \operatorname{erfc} (2.44 x)$$

$$\text{But: } \operatorname{erfc} (0.28) = 0.69$$

Therefore: $2.44x = 0.28$

$$x = 0.12 \text{ cm}$$

Hence: Total thickness needed = $d + x = 11.7 + 0.12 = 11.8 \text{ cm}$

Neither of these calculations take into account the reflectivity of the carbon and Teflon or the possible cutting off of thermal radiation by gas escaping from the subliming surfaces.

DISCUSSION

Since nothing has ever been subjected to the environmental conditions calculated in this report except at full-scale weapons tests, it is difficult to know how materials will behave under these conditions. It appears from the simple calculations made that impractical thicknesses of single materials such as ordinary graphite or Teflon would be needed for protection. Built-up layers of anisotropic graphite, zirconium oxide, and aluminum oxide are being used in nose cones and rocket motors and appear to be much more attractive materials for thermal protection.^{16, 17} However, little or no data exists for such systems and each one is hand-tailored for the use of the system.

CONCLUSIONS

1. The exposed portions of underground 100-psi shelters must be protected against the thermal radiation from the explosion of megaton weapons.
2. This protection may be achieved by relatively thick coatings of carbon or Teflon.
3. Built-up systems of more sophisticated materials appear to offer a better solution to the problem.
4. A much more thorough analysis of such composite coatings is necessary and experimental tests of such coatings are needed before recommendations can be made for the optimum protection systems.

RECOMMENDATIONS

1. That suitable thermal-resistant protective devices be incorporated in the test plan if future megaton weapon tests are performed.
2. That laboratory tests of heat-shielding materials be made to develop the most suitable protective systems.

ACKNOWLEDGMENT

The authors wish to acknowledge the help of Mr. W. L. Wilcoxson in calculating the thermal fluxes received as a function of the solid angle. Mr. E. J. Beck has helped in numerous discussions with the authors.

REFERENCES

1. Glasstone, Samuel, ed. Effects of Nuclear Weapons. Atomic Energy Commission, Washington, D. C., 1957. P. 290.
2. Ibid., pp. 518-519
3. Anderson, Fred E. Blast from a Nuclear Burst. ASCE Discussion, Figure 1, 16 Oct 1957.
4. Glasstone, op. cit., p. 67.
5. Ibid., p. 292.
6. Adams, Scala. "Interaction of Higher Temperature Air with Materials During Re-Entry." Proceedings of International Symposium on High Temperature Technology. McGraw-Hill Book Co., New York, 6 Oct 1959. P. 54.
7. Wright Air Development Center. WADC-TR-59-87, Determination of Factors Governing Selection and Application of Materials for Ablation Cooling of Hypervelocity Vehicles, by J. H. Bonin, C. F. Drice, and Henry Halle. Chicago, Illinois, Feb 1960.
8. King, H. A. "Materials and Techniques for Thermal Transfer and Accommodation." Proceedings of International Symposium on High Temperature Technology. McGraw-Hill Book Co., New York, 6 Oct 1959. P. 129.

9. National Aeronautics and Space Administration. NASA R-10, Stagnation, Point Shielding by Melting and Vaporization, by Leonard Roberts. Washington, D. C., 1959. P. 14.
10. Georgiev, S., H. Hildago, and M. C. Adams. On ablation for the Recovery of Satellites. Heat Transfer and Fluid Mechanics Institute, Stanford University Press, 1959. P. 171.
11. Bloxsom, D. E. Cooling of Solid Surfaces with Heat Power Inputs Over 10^5 watts/cm². Heat Transfer and Fluid Mechanics Institute, Stanford University Press, 1957.
12. Glasstone, op. cit., pp. 331 and 324.
13. Litz, L. M. "Graphite, Carbide, Nitride, and Sulfide Refractories." Proceedings of International Symposium on High Temperature Technology. McGraw-Hill Book Co., New York, 6 Oct 1959. P. 90.
14. Carslow, H. S., and J. C. Jaejer. Conduction of Heat in Solids, 2nd ed. Oxford University Press, Oxford, Oct 1959. P. 63.
15. Judge, John. "High Temperatures Spur Novel Graphite Development." Missiles and Rockets, Vol. 7, No. 19 (7 Nov 60), pp. 21-22.
16. Levy, Alan V. Lecture at U. C. L. A., "Extreme High Temperature," 9 Jan 1961, under the series, "Materials for Missiles and Spacecraft."
17. Steurer, Wolfgang H. Lecture at U. C. L. A., "Materials for Thermal Protection," 16 Jan 1961, under the series, "Materials for Missiles and Spacecraft."

DISTRIBUTION LIST

No. of Copies	SNDL Code	
10		Chief, Bureau of Yards and Docks
		<u>BuDocks Standard Distribution</u>
1	23A	Naval Forces Commanders (Taiwan Only)
2	39B	Construction Battalions
9	39D	Mobile Construction Battalions
3	39E	Amphibious Construction Battalions
2	39F	Construction Battalion Base Units
1	A2A	Chief of Naval Research - Only
2	A3	Chief of Naval Operations (Op-07, Op-04)
5	A5	Bureaus
3	B3	Colleges
2	F4	Laboratory ONR (Washington, D. C. Only)
1	E16	Training Device Center
8	F9	Station - CNO (Boston; Key West; New Orleans; San Juan; Long Beach; San Diego; Treasure Island; and Rodman, C. Z. Only)
5	F17	Communication Station (San Juan; San Francisco; Pearl Harbor; Adak, Alaska; and Guam only)
1	F21	Administration Command and Unit CNO (Saipan only)
1	F40	Communication Facility (Pt. Lyautey and Japan only)
1	F41	Security Station
2	F42	Radio Station (Oso and Cheltenham only)
2	F48	Security Group Activities (Winter Harbor only)
8	H3	Hospital (Chelsea; St. Albans; Portsmouth, Va; Beaufort; Great Lakes; San Diego; Oakland; and Camp Pendleton only)
1	H6	Medical Center
2	J1	Administration Command and Unit-BuPers (Great Lakes and San Diego only)
1	J3	U. S. Fleet Anti-Air Warfare Training Center (Virginia Beach only)
2	J4	Amphibious Bases
1	J19	Receiving Station (Brooklyn only)
1	J34	Station - BuPers (Washington, D. C. only)
1	J37	Training Center (Bainbridge only)
1	J46	Personnel Center
1	J48	Construction Training Unit
1	J60	School Academy

Distribution List (Cont'd)

No. of copies	SNDL Code	
1	J65	School CEC Officers
1	J84	School Postgraduate
1	J90	School Supply Corps
1	J95	School War College
1	J99	Communication Training Center
11	L1	Shipyards
4	L7	Laboratory - BuShips (New London; Panama City; Carderock; and Annapolis only)
5	L26	Naval Facilities - BuShips (Antigua; Turks Island; Barbados; San Salvador; and Eleuthera only)
1	L30	Submarine Base (Groton, Conn. only)
2	L32	Naval Support Activities (London & Naples only)
2	L42	Fleet Activities - BuShips
4	M27	Supply Center
7	M28	Supply Depot (Except Guantanamo Bay; Subic Bay; and Yokosuka)
2	M61	Aviation Supply Office
12	N1	BuDocks Director, Overseas Division
30	N2	Public Works Offices
7	N5	Construction Battalion Center
5	N6	Construction Officer-in-Charge
1	N7	Construction Resident-Officer-in-Charge
12	N9	Public Works Center
1	N14	Housing Activity
2	R9	Recruit Depots
2	R10	Supply Installations (Albany and Barstow only)
1	R20	Marine Corps Schools, Quantico
3	R64	Marine Corps Base
1	R66	Marine Corps Camp Detachment (Tongan only)
7	W1A1	Air Station
35	W1A2	Air Station
9	W1B	Air Station Auxiliary
4	W1C	Air Facility (Phoenix; Monterey; Oppama; Naha; and Naples only)
3	W1E	Marine Corps Air Station (Except Quantico)
1	W1F	Marine Corps Auxiliary Air Station
8	W1H	Station - BuWeps (Except Rota)

Distribution List (Cont'd)

No. of
copies

1	Chief of Staff, U. S. Army, Chief of Research and Development, Department of the Army, Washington 25, D. C.
1	Office of the Chief of Engineers, Asst. Chief of Engineering for Civil Works, Department of the Army, Washington 25, D. C.
1	Chief of Engineers, Department of the Army, Attn: Engineering R & D Division, Washington 25, D. C.
1	Commanding Officer, Engineering R & D Laboratories, Attn: Technical Intelligence Branch, Fort Belvoir, Virginia
1	Commanding General, Wright Air Development Center, Air Research and Development Command, Wright-Patterson Air Force Base, Ohio
1	Deputy Chief of Staff, Development, Director of Research and Development, Department of the Air Force, Washington
1	President, Marine Corps Equipment Board, Marine Corps Schools, Quantico, Virginia
1	Director, National Bureau of Standards, Department of Commerce, Connecticut Avenue, Washington, D. C.
10	Armed Services Technical Information Agency, Arlington Hall Station, Arlington 12, Virginia
1	Deputy Chief of Staff, Research and Development Headquarters, U. S. Marine Corps
3	Headquarters, USAF, Directorate of Civil Engineering, Attn: AFOCE-ES, Washington 25, D. C.
2	Commander, Headquarters, Air Research and Development Command, Andrews Air Force Base, Washington 25, D. C.
2	Office of the Director, U. S. Coast and Geodetic Survey, Washington 25, D. C.
2	Library of Congress, Washington 25, D. C.
2	Director, Office of Technical Services, Department of Commerce, Washington 25, D. C.
	<u>NCEL Standard Distribution</u>
2	Director of Defense Research and Engineering, Department of Defense, Washington 25, D. C.
2	Director, Division of Plans and Policies, Headquarters, U. S. Marine Corps, Washington 25, D. C.
2	Director, Bureau of Reclamation, Washington 25, D. C.
2	Commanding Officer, U. S. Naval Construction Battalion Center, Attn: Technical Division, Code 141, Port Hueneme, California
2	Commanding Officer, U. S. Naval Construction Battalion Center, Attn: Materiel Department, Code 142, Port Hueneme, California
1	Commanding Officer (Patent Dept.), Office of Naval Research Branch Office, 1030 E. Green Street, Pasadena, California
1	Commanding Officer, Yards and Docks Supply Office, U. S. Naval Construction Battalion Center, Port Hueneme, Calif.

Distribution List (Cont'd)

No. of
copies

NCEL Supplemental Distribution

1	Commandant, Industrial College of the Armed Forces, Washington, D. C.
1	Chief, Bureau of Ships, Attn: Chief of Research and Development Division, Navy Department, Washington, D. C.
1	Officer in Charge, U. S. Navy Unit, Rensselaer Polytechnic Institute, Troy, N. Y.
1	Officer in Charge, U. S. Naval Supply Research and Development Facility, Naval Supply Center, Attn: Library, Bayonne, N. J.
1	Commander, Norfolk Naval Shipyard, Portsmouth, Va.
1	Commander, U. S. Naval Shipyard, Boston
1	Commander, U. S. Naval Shipyard, Brooklyn
1	Commandant, U. S. Armed Forces Staff College, U. S. Naval Base, Norfolk, Va.
1	Officer in Charge, U. S. Naval Biological Laboratory, Naval Supply Center, Oakland, Calif.
1	Chief, Bureau of Medicine and Surgery, Attn: Research Division, Navy Department, Washington, D. C.
1	Chief, Bureau of Naval Weapons, Attn: Research Division, Navy Department, Washington, D. C.
1	Commander, Pacific Missile Range, Attn: Technical Director, Point Mugu, Calif.
1	Commander, Amphibious Force, U. S. Pacific Fleet, San Diego
1	Commander, Amphibious Force, U. S. Atlantic Fleet, U. S. Naval Base, Norfolk, Va.
1	Officer in Charge, U. S. Naval Supply Research and Development Facility, Naval Supply Center, Bayonne, N. J.
1	Commander, U. S. Naval Shipyard, Mare Island, Vallejo, Calif.
1	Navy Liaison Officer, Detroit Arsenal, Centerline, Mich.
1	Commanding Officer, Field Research Laboratory, Bureau of Medicine and Surgery, Camp LeJeune, N. C.
1	Deputy Chief of Staff, Research and Development Headquarters, U. S. Marine Corps, Washington, D. C.
1	Paint Laboratory, U. S. Engineers Office, Clock Tower Building, Rock Island, Ill.
1	U. S. Army, Attn: Director of Research and Development Group, Washington, D. C.
1	Commanding Officer, Signal Corps Engineering Labs, Fort Monmouth, N. J.
1	Commanding Officer, Fleet Training Center, Navy No. 128, c/o FPO, San Francisco
1	Office of Naval Research, Branch Office, Navy No. 100, Box 39, FPO, New York
1	Commanding Officer, Naval Electronics Laboratory, Attn: Technical Director, San Diego
1	Commanding Officer, U. S. Naval Unit, U. S. Army Chemical Corps School, Fort McClellan, Ala.
1	U. S. Naval Research Laboratory, Washington, D. C.
1	Deputy Chemical Liaison Officer for Scientific Activities, Washington, D. C.
1	Chief of Ordnance, U. S. Army, Attn: Research and Development Laboratory, Washington, D. C.
1	President, Chemical Warfare Board, Army Chemical Center, Md.

Distribution List (Cont'd)

No. of copies	
1	U. S. Army Corps of Engineers, Office of the District Engineer, St. Paul District, 1217 U. S. P. O. and Customs House, St. Paul, Minn.
1	Directorate of Research, Air Force Special Weapons Center, Kirtland Air Force Base, N. M.
1	Chief, Physical Research Branch, Research Division, U. S. Department of Commerce, Bureau of Public Roads, Washington, D. C.
1	Operation Civil, University of California, Richmond Field Station, Berkeley, Calif.
1	Library, Harvard University, Graduate School of Engineering, Cambridge, Mass.
1	Director, Engineering Research Institute, University of Michigan, Ann Arbor, Mich.
1	Library, University of Southern California, University Park, Los Angeles
1	Library, California Institute of Technology, Pasadena, Calif.
1	Commander, Air Research & Development Command, Attn: Library, Andrews Air Force Base, Washington, D. C.
1	Air Force Cambridge Research Cen., Hanscom Field, Bedford, Mass.
1	Sandia Corporation, Attn: Classified Document Division, Box 5800, Albuquerque, N. M.
1	Library, Engineering Department, Stanford University, Stanford, Calif.
1	Library, Battelle Institute, Columbus, Ohio
1	Library, Engineering Department, University of California, 405 Hilgard Avenue, Los Angeles
1	Director, The Technological Institution, Northwestern University, Evanston, Ill.
1	Library, Institute of Technology, University of Minnesota, Minneapolis, Minn.
1	Dr. N. M. Newmark, Civil Engineering Hall, University of Illinois, Urbana, Ill.
1	Dr. Harold Brode, RAND Corporation, 1700 Main Street, Santa Monica, Calif.
1	Dr. Robert V. Whitman, Massachusetts Institute of Tech., Cambridge, Mass.
1	Mr. William J. Taylor, Terminal Ballistics Laboratory, Aberdeen Proving Ground, Aberdeen Proving Ground, Md.
1	Commander, Air Force Ballistic Missile Division, Air Research & Development Command, Attn: Dr. George Young, Post Office Box 262, Inglewood, Calif.
1	Prof. J. Nells Thompson, Civil Engineering Laboratory, University of Texas, Austin, Tex.
1	Mr. G. L. Arbuthnot, Waterways Experiment Station, P.O. Box 631, Vicksburg, Miss.
1	Mr. W. R. Parret 5112, Sandia Corporation, Sandia Base, Albuquerque, N. M.
1	Mr. Fred Sauer, Physics Department, Stanford Research Institute, Menlo Park, Calif.
1	Mr. Kenneth Kaplan, Broadview Research Corporation, 1811 Trousdale Drive, Burlingame, Calif.
1	Chief of Engineers, Department of the Army, Washington, D. C.
1	Dr. T. H. Schiffman, Armour Research Foundation, Technology Center, Chicago
1	Mr. J. O'Sullivan, The Mitre Corporation, P.O. Box 208, Lexington, Mass.
1	Dr. James O. Buchanan, Office of Civil and Defense Mobilization, Battle Creek, Mich.
1	Mr. Charles M. Eisenhower, Radiation Physics Laboratory, High Voltage Laboratory, National Bureau of Standards, Washington, D. C.

Distribution List (Cont'd)

No. of
copies

- 1 Mr. L. Neal FitzSimons, OCDM, Winder Building, Washington, D. C.
- 1 CAPT A. B. Chilton, CEC, USN, U. S. Naval Civil Engineering Laboratory, Port Hueneme, Calif.
- 1 CDR C. A. Grubb, CEC, USN, District Public Works Office, 11th Naval District, 1220 Pacific Highway, San Diego
- 1 CAPT W. M. McLellan, CEC, USN, Public Works Office, U. S. Naval Base, Charleston, S. C.
- 1 CDR W. J. Christensen, CEC, USN, Bureau of Yards and Docks, Code D-400, Washington, D. C.
- 1 LCDR C. Curione, CEC, USN, District Public Works Officer, 14th Naval District, Navy No. 128, FPO, San Francisco
- 1 Mr. Jack C. Greene, Office of Civil and Defense Mobil., Battle Creek, Mich.
- 1 Dr. Ronald Shephard, University of California, Engineering Field Station, 1301 South 46th Street, Richmond, Calif.
- 1 Mr. Richard Park, National Academy of Sciences, 2101 Constitution Avenue, Washington, D. C.
- 1 Mr. E. E. Shalowitz, Protective Construction GSA Building, 19th and F Street, N. W., Washington, D. C.
- 1 LTCOL Russel J. Hutchinson, 052921, Office of Area Engineer, Saudi Arabia, USA Engineer District, APO 616, New York
- 1 CDR J. F. Clarke, CEC, USN, Area Public Works Office, Chesapeake, U. S. Naval Weapons Plants, Washington, D. C.
- 1 LCDR J. D. Andrews, CEC, USN, Defense Atomic Support Agency, Washington, D. C.
- 1 LCDR W. A. Walls, CEC, USN, U. S. Naval Reserve Officers, Training Corps Unit, University of Illinois, Urbana, Ill.
- 1 LCDR W. J. Francy, CEC, USN, Bureau of Yards and Docks, Code D-500, Washington, D. C.
- 1 LCDR E. M. Saunders, CEC, USN, NROTC Unit, Stanford University, Palo Alto, Calif.
- 1 LCDR J. C. LeDoux, CEC, USN, Executive Officer, U. S. Naval School, CEC Officers, Port Hueneme, California
- 1 Commanding Officer, U. S. Army Chemical Corps, Research & Development Command, Washington, D. C.
- 1 Commander, Air Force Special Weapons Center, Kirtland Air Force Base, Albuquerque, N. M.
- 1 Commander, Field Command, Defense Atomic Support Agency, Box 5100, Albuquerque, N. M.
- 1 Commanding Officer, Chemical Warfare Laboratories, Army Chemical Center, Md.
- 1 U. S. Atomic Energy Commission, Technical Information Service, P.O. Box 62, Oak Ridge, Tenn.
- 1 LCDR R. C. Vance, CEC, USN, U. S. Naval School, CEC Officers, Port Hueneme, Calif.
- 1 Officer in Charge, CECOS (ATTN: ADCE Course), Port Hueneme, Calif.
- 1 Officer of the Chief of Engineers, Department of the Army, Washington, D. C. Attn: ENGMC-ED
- 1 Hdq. U. S. Air Force, Director of Research & Development, DCS/D (Attn: Combat Components Div.) Washington, D. C.
- 1 Chief, Defense Atomic Support Agency, Washington, D. C.
- 1 Office of Civil and Defense Mobil., Attn: Mr. Ben Taylor, Battle Creek, Mich.
- 1 Director, Civil Effects Test Group, Atomic Energy Commission, ATTN: Mr. R. L. Corsbie, Washington, D. C.

U. S. Naval Civil Engineering Laboratory.

Technical Report R-150.

PROTECTION OF EXPOSED PARTS OF SHELTERS
AGAINST THERMAL RADIATION FROM MEGATON
WEAPONS, by F. W. Brown, III and A. Y. Eliason.

19 p. illus. 28 July 1961 UNCLASSIFIED

A theoretical study is made to determine the effects on the exposed parts of underground shelters of thermal radiation from the explosion of nuclear weapons. Simple carbon and graphite shields are discussed, and more sophisticated shielding systems are proposed for future experimental studies.

I. Shielding - Thermal
Radiation

I. Brown, F. W., III

II. Eliason, A. Y.

III. Y-F011-05-401 (c)

U. S. Naval Civil Engineering Laboratory.

Technical Report R-150.

PROTECTION OF EXPOSED PARTS OF SHELTERS
AGAINST THERMAL RADIATION FROM MEGATON
WEAPONS, by F. W. Brown, III and A. Y. Eliason.

19 p. illus. 28 July 1961 UNCLASSIFIED

A theoretical study is made to determine the effects on the exposed parts of underground shelters of thermal radiation from the explosion of nuclear weapons. Simple carbon and graphite shields are discussed, and more sophisticated shielding systems are proposed for future experimental studies.

I. Shielding - Thermal
Radiation

I. Brown, F. W., III

II. Eliason, A. Y.

III. Y-F011-05-401 (c)

U. S. Naval Civil Engineering Laboratory.

Technical Report R-150.

PROTECTION OF EXPOSED PARTS OF SHELTERS
AGAINST THERMAL RADIATION FROM MEGATON
WEAPONS, by F. W. Brown, III and A. Y. Eliason.

19 p. illus. 28 July 1961 UNCLASSIFIED

A theoretical study is made to determine the effects on the exposed parts of underground shelters of thermal radiation from the explosion of nuclear weapons. Simple carbon and graphite shields are discussed, and more sophisticated shielding systems are proposed for future experimental studies.

I. Shielding - Thermal
Radiation

I. Brown, F. W., III

II. Eliason, A. Y.

III. Y-F011-05-401 (c)

U. S. Naval Civil Engineering Laboratory.

Technical Report R-150.

PROTECTION OF EXPOSED PARTS OF SHELTERS
AGAINST THERMAL RADIATION FROM MEGATON
WEAPONS, by F. W. Brown, III and A. Y. Eliason.

19 p. illus. 28 July 1961 UNCLASSIFIED

A theoretical study is made to determine the effects on the exposed parts of underground shelters of thermal radiation from the explosion of nuclear weapons. Simple carbon and graphite shields are discussed, and more sophisticated shielding systems are proposed for future experimental studies.

I. Shielding - Thermal
Radiation

I. Brown, F. W., III

II. Eliason, A. Y.

III. Y-F011-05-401 (c)