

UNCLASSIFIED

AD 262 205

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

262205

CATALOGED BY ASTIA
AS AD NO

THE CRYSTAL STRUCTURE OF Cr_3B_4

Mats Elfström

Institute of Chemistry, University of Uppsala, Uppsala, Sweden

Technical Note No. 25

Contract No. AF 61(052)-40

June 21, 1961

61-4-3
XEROX

ASTIA
JUN 23 1961
DELIVERED TO
TIPDR A

The research reported in this document has been sponsored by the

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH

of the AIR RESEARCH AND DEVELOPMENT COMMAND, UNITED STATES AIR
FORCE, through its European Office.

The Crystal Structure of Cr_3B_4

By Mats Elfström

Institute of Chemistry, University of Uppsala, Uppsala, Sweden

A number of borides isostructural with Ta_3B_4 have already been investigated by Andersson and Kiessling^{1,2,3}. From his data on Mn_3B_4 Kiessling⁴ concluded that there are boron-boron distances as short as 1.50 Å in this phase and he believed these short boron-boron distances to be present also in the other Me_3B_4 phases³. The value 1.5 Å is considerably shorter than any boron-boron distance previously reported. However, the atomic parameters are very uncertain. A reinvestigation of these compounds is therefore being undertaken in order to achieve greater accuracy. The present communication deals with the results obtained for the alloy Cr_3B_4 .

Experimental: The alloys were prepared by arc-melting mixtures of boron (99.0 %) and chromium (99.9 %) in an atmosphere of purified argon. X-ray photographs were taken in a Guinier camera with Si as internal standard ($a_{\text{Si}} = 5.4306$ Å) and with $\text{CrK}\alpha$ -radiation. The atomic parameters were determined from single crystal data, obtained in a Weissenberg camera with $\text{MoK}\alpha$ -radiation. The relative intensities were estimated visually using the multiple film technique and a calibrated intensity scale. The electron density projection $\rho(xy)$, the structure factors and the scale- and temperature factors were computed and refined on the digital electronic

computer BESK with programs available at BESK. The scattering factors according to Watson and Freeman ⁵ for chromium and Ibers ⁶ for boron were used.

Results: Within the limits of the experimental errors (estimated to be ± 0.04 %) no lattice parameter variations were observed. The lattice parameters of Cr_3B_4 obtained in this investigation ($a = 2.986$ Å, $b = 13.02$ Å, $c = 2.952$ Å) are in excellent agreement with Anderson's and Kiessling's ¹ values ($a = 2.984$ Å, $b = 13.02$ Å, $c = 2.953$ Å).

The space group Immm derived by Kiessling in his study of Ta_3B_4 was confirmed. The atomic parameters obtained in this investigation for Cr_3B_4 are given in Table 1. with standard deviations calculated from Cruickshank's formula ⁷. The final R-value for the 94 independent h_k0 reflexions was 7.6 %.

Interatomic distances are given in Table 2. Of particular interest are the shortest boron-boron distances, which have a standard deviation of 0.02 Å. The difference between the two shortest non-equivalent boron-boron distances is not significant. Thus it has been shown that in Cr_3B_4 there exists no such abnormally short boron-boron distances as suggested by Kiessling ³.

Acknowledgements: The author wishes to thank Professor G. Hägg for the facilities put at his disposal. This work has been supported by the Air Force Office of Scientific Research of the Air Research and Development Command, US Air Force, through its European Office under contract No. AF 61(052)-40. Facilities for use of the digital computer BESK were granted by the Swedish Board for Computing Machinery.

References:

1. Andersson, L.-H. and Kiessling, R. Acta Chem. Scand. 4 (1950) 160.
2. Kiessling, R. ibid. 3 (1949) 90.
3. Kiessling, R. ibid. 4 (1950) 209.
4. Kiessling, R. ibid. 4 (1950) 146.
5. Watson, R.E. and Freeman, A.J. Acta Cryst. 14 (1961) 27.
6. Ibers, J.A. ibid. 10 (1957) 86.
7. Cruickshank, D.W.J. ibid. 2 (1949) 65.

Table 1. Atomic parameters in Cr_3B_4

Cr_I in 2(c)

Cr_II in 4(g) with $y = 0.1861 \pm 0.0000_6$

B_I in 4(g) with $y = 0.3607 \pm 0.0003$

B_II in 4(h) with $y = 0.4351 \pm 0.0003$

Table 2. Interatomic distances in Cr_3B_4 shorter than 3 Å

$\text{Cr}_\text{I} - \text{Cr}_\text{I}$	2.952 (2), 2.986 (2)
$\text{Cr}_\text{I} - \text{Cr}_\text{II}$	2.83 ₇ (4)
$\text{Cr}_\text{I} - \text{B}_\text{I}$	2.35 (4)
$\text{Cr}_\text{I} - \text{B}_\text{II}$	2.26 (8)
$\text{Cr}_\text{II} - \text{Cr}_\text{I}$	2.83 ₇ (2)
$\text{Cr}_\text{II} - \text{Cr}_\text{II}$	2.67 ₉ (4), 2.952 (2), 2.986 (2)
$\text{Cr}_\text{II} - \text{B}_\text{I}$	2.19 (4), 2.27 (1)
$\text{Cr}_\text{II} - \text{B}_\text{II}$	2.17 (2)
$\text{B}_\text{I} - \text{Cr}_\text{I}$	2.35 (2)
$\text{B}_\text{I} - \text{Cr}_\text{II}$	2.19 (4), 2.27 (1)
$\text{B}_\text{I} - \text{B}_\text{I}$	2.952 (2), 2.986 (2)
$\text{B}_\text{I} - \text{B}_\text{II}$	1.77 (2)
$\text{B}_\text{II} - \text{Cr}_\text{I}$	2.26 (4)
$\text{B}_\text{II} - \text{Cr}_\text{II}$	2.17 (2)
$\text{B}_\text{II} - \text{B}_\text{I}$	1.77 (2)
$\text{B}_\text{II} - \text{B}_\text{II}$	1.69 (1), 2.952 (2), 2.986 (2)