

UNCLASSIFIED

AD 276 838

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA



UNCLASSIFIED


NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOG OF ASTIA 276838
AS AD NO.

276 838


HEADQUARTERS
QUARTERMASTER RESEARCH & ENGINEERING COMMAND
U S ARMY

TECHNICAL REPORT
EP-159



APPARENT THERMAL DIFFUSIVITY OF
COMPOSITE FABRIC LAYERS

Astia Availability Notice: "QUALIFIED
REQUESTORS MAY OBTAIN COPIES OF THIS
REPORT FROM ASTIA."



QUARTERMASTER RESEARCH & ENGINEERING CENTER
ENVIRONMENTAL PROTECTION RESEARCH DIVISION

JULY 1961

NATICK, MASSACHUSETTS

<p>AD- Div. 14, 25, 29 Accession No.</p> <p>Quartermaster Research & Engineering Center, Natick, Mass. APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS by James J. Powers, Francis W. Botach and Michael J. Sacco, 19 pp, illus. (Technical Report EP-159) July 1961</p> <p>A mathematical derivation of an apparent thermal diffusivity for a generalized composite fabric system consisting of different cloth layers is presented in order to provide a parameter for analysis of unidimensional heat flow in a clothing system. An experimental method is described for obtaining the apparent thermal diffusivity as a general solution to Fourier's Conduction Equation, using a boundary step change on a semi-infinite solid composed of dissimilar fabric layers.</p> <p>Also presented are several specific examples of transient heat flow in dual layer systems. The apparent diffusivities of each system are obtained both theoretically and experimentally, and the results compared graphically.</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Thermal diffusion 2. Mathematical analysis 3. Textiles 4. Clothing 5. Climatic factors 6. Conductivity 7. Heat transfer 8. Title 9. Series <p>III. Powers, James J. IV. Botach, Francis W. V. Sacco, Michael J.</p>	<p>AD- Div. 14, 25, 29 Accession No.</p> <p>Quartermaster Research & Engineering Center, Natick, Mass. APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS by James J. Powers, Francis W. Botach and Michael J. Sacco, 19 pp, illus. (Technical Report EP-159) July 1961</p> <p>A mathematical derivation of an apparent thermal diffusivity for a generalized composite fabric system consisting of different cloth layers is presented in order to provide a parameter for analysis of unidimensional heat flow in a clothing system. An experimental method is described for obtaining the apparent thermal diffusivity as a general solution to Fourier's Conduction Equation, using a boundary step change on a semi-infinite solid composed of dissimilar fabric layers.</p> <p>Also presented are several specific examples of transient heat flow in dual layer systems. The apparent diffusivities of each system are obtained both theoretically and experimentally, and the results compared graphically.</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Thermal diffusion 2. Mathematical analysis 3. Textiles 4. Clothing 5. Climatic factors 6. Conductivity 7. Heat transfer 8. Title 9. Series <p>III. Powers, James J. IV. Botach, Francis W. V. Sacco, Michael J.</p>
<p>AD- Div. 14, 25, 29 Accession No.</p> <p>Quartermaster Research & Engineering Center, Natick, Mass. APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS by James J. Powers, Francis W. Botach and Michael J. Sacco, 19 pp, illus. (Technical Report EP-159) July 1961</p> <p>A mathematical derivation of an apparent thermal diffusivity for a generalized composite fabric system consisting of different cloth layers is presented in order to provide a parameter for analysis of unidimensional heat flow in a clothing system. An experimental method is described for obtaining the apparent thermal diffusivity as a general solution to Fourier's Conduction Equation, using a boundary step change on a semi-infinite solid composed of dissimilar fabric layers.</p> <p>Also presented are several specific examples of transient heat flow in dual layer systems. The apparent diffusivities of each system are obtained both theoretically and experimentally, and the results compared graphically.</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Thermal diffusion 2. Mathematical analysis 3. Textiles 4. Clothing 5. Climatic factors 6. Conductivity 7. Heat transfer 8. Title 9. Series <p>III. Powers, James J. IV. Botach, Francis W. V. Sacco, Michael J.</p>	<p>AD- Div. 14, 25, 29 Accession No.</p> <p>Quartermaster Research & Engineering Center, Natick, Mass. APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS by James J. Powers, Francis W. Botach and Michael J. Sacco, 19 pp, illus. (Technical Report EP-159) July 1961</p> <p>A mathematical derivation of an apparent thermal diffusivity for a generalized composite fabric system consisting of different cloth layers is presented in order to provide a parameter for analysis of unidimensional heat flow in a clothing system. An experimental method is described for obtaining the apparent thermal diffusivity as a general solution to Fourier's Conduction Equation, using a boundary step change on a semi-infinite solid composed of dissimilar fabric layers.</p> <p>Also presented are several specific examples of transient heat flow in dual layer systems. The apparent diffusivities of each system are obtained both theoretically and experimentally, and the results compared graphically.</p>	<p>UNCLASSIFIED</p> <ol style="list-style-type: none"> 1. Thermal diffusion 2. Mathematical analysis 3. Textiles 4. Clothing 5. Climatic factors 6. Conductivity 7. Heat transfer 8. Title 9. Series <p>III. Powers, James J. IV. Botach, Francis W. V. Sacco, Michael J.</p>

HEADQUARTERS
QUARTERMASTER RESEARCH & ENGINEERING COMMAND, US ARMY
Quartermaster Research & Engineering Center
Natick, Massachusetts

ENVIRONMENTAL PROTECTION RESEARCH DIVISION

Technical Report
EP-159

APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS

James J. Powers

Francis W. Botsch Michael J. Sacco

BIOPHYSICS BRANCH

Project Reference:
7x83-01-009

July 1961

FOREWORD

This report is the second in a series on the mathematical analysis of transient thermal variation in clothing. Thermal diffusivity is the physical parameter associated with transient heat conduction and is a constant for any homogeneous material. However, a uniform during field use rarely consists of a single material, and a method is needed for determining the heat conduction across a composite system of non-homogeneous layers under non-equilibrium conditions.

This report presents a mathematical derivation of apparent thermal diffusivity for composite fabric systems consisting of different cloth layers, and demonstrates a method for experimentally determining the composite thermal diffusivity based upon the general equation of conductive heat transfer in the unsteady state.

AUSTIN HENSCHEL, Ph.D.
Chief
Environmental Protection Research
Division

Approved:

DALE H. SIELING, Ph.D.
Scientific Director
QM Research & Engineering Command

MERRILL L. TRIBE
Brig. Gen., USA
Commanding
QM Research & Engineering Command

CONTENTS

	<u>Page</u>
Abstract	iv
1. Introduction	1
2. Theory	1
a. Thermal conductivity of the composite layer	2
b. Heat capacity of the composite layer	4
c. Thermal diffusivity of the composite layer	6
3. Apparatus and procedure	7
4. Results	9
5. Discussion	13
6. References	14

ABSTRACT

A mathematical derivation of an apparent thermal diffusivity for a generalized composite fabric system consisting of different cloth layers is presented in order to provide a parameter for analysis of unidimensional heat flow in a clothing system. An experimental method is described for obtaining the apparent thermal diffusivity as a general solution to Fourier's Conduction Equation, using a boundary step change on a semi-infinite solid composed of dissimilar fabric layers.

Also presented are several specific examples of transient heat flow in dual layer systems. The apparent diffusivities of each system are obtained both theoretically and experimentally, and the results compared graphically.

APPARENT THERMAL DIFFUSIVITY OF COMPOSITE FABRIC LAYERS

1. Introduction

In a previous report (7) the concept of thermal diffusivity was applied to fabrics in order to provide a parameter for the mathematical analysis of the thermal response of cloth to non-uniform boundary conditions. However, a uniform worn during field activities rarely consists of a single type of material, and clothing for arctic use is composed of several dissimilar clothing layers. As a result, the transient response of the clothing to thermal changes at the boundary is a function not only of time and temperature but the thermal properties of the individual layers as well. Therefore, a method is needed for combining parameters of the individual layer into similar parameters for the composite layer in order to mathematically analyze transient heat transfer by conduction through the material.

Very little can be found in the literature concerning solutions to transient heat transfer problems by conduction involving composite layers. In one of his later books, Jakob (4) included a small section on composite layers; however, he was concerned with interface temperatures between two dissimilar layers, and used the methods of finite difference to approximate his solution. Capey and McKenzie (1) worked with transient heat flow in an aircraft wing, but this was a finite composite slab which was heated on one side and cooled on the other side by convection. Chen and Jensen (2) reported on transient heat by radiation in composite material. However, no one has reported a method of combining parameters to measure unsteady-state heat conduction through a dissimilar layer system.

The purpose of this report is to show that a single parameter - the thermal diffusivity - is applicable to a series of layers. The application of this complex thermal diffusivity is needed to permit a mathematical analysis of a clothing system under transient thermal conditions.

2. Theory

The general equation which describes thermal conduction through a thick slab of material which is heated at one boundary and cooled at the other is

$$\frac{\partial T}{\partial t} = \alpha \frac{\partial^2 T}{\partial x^2} \quad (1)$$

where

T = temperature

t = time

x = distance into cloth from heat source

and is generally known as the Fourier Conduction Equation in One Dimension

(3). The thermal diffusivity α is directly proportional to the thermal conductivity and inversely proportional to the density and specific heat of the conducting material. In cloth, α is defined as apparent thermal diffusivity and was shown to be a reproducible characteristic of the cloth; thus the apparent thermal diffusivity serves as a parameter for adequately expressing the material's transient heat conduction properties.


In a composite layer of material, the apparent thermal diffusivity of the resultant will depend on the thermal conductivity k , and the heat capacity ρc of the combined materials. These in turn must be determined from the individual conductivities and heat capacities of the various materials and then combined into an α for the composite layers.

If the composite cloth consists of n layers of dissimilar materials, the heat flow will be assumed unidirectional, perpendicular to the layers, as shown by arrows in Figure 1. The cross-sectional area is the same for all the materials and equal to A .

Assuming the following parameters for the various layers are:

thickness	$x_1, x_2, x_3 \dots x_n$
thermal conductivities	$k_1, k_2, k_3 \dots k_n$
densities	$\rho_1, \rho_2, \rho_3 \dots \rho_n$
specific heats	$c_1, c_2, c_3 \dots c_n$

respectively for the individual layers numbered from top to bottom.



a. Thermal conductivity of the composite layer

If the temperature at the upper edge of the first material is T_0 , at the interface between the first and second material it is T_1 , at second interface T_2 , at third interface T_3 , and so on until the lower boundary which is T_n , the heat flow may be considered the same for each layer and may be represented by q . Then for material 1

$$q = \frac{k_1 A (T_0 - T_1)}{x_1} \quad (2)$$

for material 2,

$$q = \frac{k_2 A (T_1 - T_2)}{x_2} \quad (3)$$

Figure 1. Cross sectional diagram of 'n' different fabric layers where arrows show direction of heat flow, T 's are interface temperatures and x 's are thickness of layers.

for material 3,

$$q = \frac{k_3 A(T_2 - T_3)}{x_2} \quad (4)$$

and so forth until material n, where

$$q = \frac{k_n A(T_{n-1} - T_n)}{x_n} \quad (5)$$

For all the material

$$q = \frac{k A(T_0 - T_n)}{x_1 + x_2 + x_3 + \dots + x_n} \quad (6)$$

where k is the thermal conductivity of the composite layer. Solving equations 2 through 5 for the temperature differences

$$T_0 - T_1 = \frac{q x_1}{k_1 A} \quad (7)$$

$$T_1 - T_2 = \frac{q x_2}{k_2 A} \quad (8)$$

$$T_2 - T_3 = \frac{q x_3}{k_3 A} \quad (9)$$

and so forth until $T_{n-1} - T_n = \frac{q x_n}{k_n A} \quad (10)$

Summing the n temperature differences inclusive in equation 7 through 10

$$T_0 - T_n = \frac{q}{A} \left(\frac{x_1}{k_1} + \frac{x_2}{k_2} + \frac{x_3}{k_3} + \dots + \frac{x_n}{k_n} \right) \quad (11)$$

Solving equation 6 for the temperature difference

$$T_0 - T_n = \frac{q}{kA} (x_1 + x_2 + x_3 + \dots + x_n) \quad (12)$$

Equating equations 11 and 12

$$\frac{q}{kA} (x_1 + x_2 + x_3 + \dots + x_n) = \frac{q}{A} \left(\frac{x_1}{k_1} + \frac{x_2}{k_2} + \frac{x_3}{k_3} + \dots + \frac{x_n}{k_n} \right) \quad (13)$$

Dividing both sides by $\frac{q}{A}$

$$\frac{\sum x}{k} = \frac{x_1}{k_1} + \frac{x_2}{k_2} + \frac{x_3}{k_3} + \dots + \frac{x_n}{k_n} \quad (14)$$

where

$$\sum x = x_1 + x_2 + x_3 + \dots + x_n$$

In order to simplify equation 14, both sides can be divided by $\sum x$, and making the substitutions:

$$\begin{aligned}
 K_1 &= \frac{k_1}{x_1/\sum x} \\
 K_2 &= \frac{k_2}{x_2/\sum x} \\
 K_3 &= \frac{k_3}{x_3/\sum x} \\
 &\dots \dots \dots \\
 K_n &= \frac{k_n}{x_n/\sum x}
 \end{aligned}
 \tag{15}$$

where K_1, K_2 and so forth are the proportional part conductance of the individual layers.

Substituting 15 in 14

$$\frac{1}{k} = \frac{1}{K_1} + \frac{1}{K_2} + \frac{1}{K_3} + \dots + \frac{1}{K_n}
 \tag{16}$$

and

$$k = \frac{1}{\frac{1}{K_1} + \frac{1}{K_2} + \frac{1}{K_3} + \dots + \frac{1}{K_n}}
 \tag{17}$$

Simplifying equation 17

$$k = \frac{1}{\sum_{a=1}^n \frac{1}{K_a}}
 \tag{18}$$

Equation 18 gives the thermal conductivity of the composite system as a summation of the reciprocals of the proportional thermal conductances of the individual layers.

b. The heat capacity of composite layers

In a similar manner the heat capacity of the composite layer system may be obtained from the heat capacities of the individual layers.

Multiplying the volume ($A x_1$) by the density ρ_1 , gives the mass of the

first layer, and multiplying the mass by the specific heat c_1 , gives the heat stored in the layer if its temperature is increased by 1 degree. So if the temperature is increased dT in the time dt , the heat stored is

$$Q_1 = A x_1 \rho_1 c_1 \frac{dT}{dt} \quad (19)$$

For material 2, the heat stored when the temperature is increased dT in the time dt is

$$Q_2 = A x_2 \rho_2 c_2 \frac{dT}{dt} \quad (20)$$

For material 3

$$Q_3 = A x_3 \rho_3 c_3 \frac{dT}{dt} \quad (21)$$

and so forth until material n

$$Q_n = A x_n \rho_n c_n \frac{dT}{dt} \quad (22)$$

Then the total amount of heat stored Q in the composite layer is the sum of the heat stored in the individual layers. Then

$$Q = \sum_{a=1}^n Q_a = A(x_1 \rho_1 c_1 + x_2 \rho_2 c_2 + x_3 \rho_3 c_3 + \dots + x_n \rho_n c_n) \frac{dT}{dt} \quad (23)$$

The total heat stored Q in the composite layer may also be expressed as a function of the composite heat capacity for an increase of temperature dT in the time dt and

$$Q = A(x_1 + x_2 + x_3 + \dots + x_n) \rho c \frac{dT}{dt} \quad (24)$$

where

ρ = density of the composite layer

and

c = specific heat of the composite layer

Equating equations 23 and 24

$$A(x_1 + x_2 + \dots + x_n) \rho c \frac{dT}{dt} = A(x_1 \rho_1 c_1 + x_2 \rho_2 c_2 + \dots + x_n \rho_n c_n) \frac{dT}{dt} \quad (25)$$

reducing

$$(x_1 + x_2 + \dots + x_n) \rho c = x_1 \rho_1 c_1 + x_2 \rho_2 c_2 + \dots + x_n \rho_n c_n$$

and dividing through by $\sum x$

$$\rho c = \frac{x_1 \rho_1 c_1 + x_2 \rho_2 c_2 + \dots + x_n \rho_n c_n}{\sum x}$$

Introducing a new series of constants $S_1, S_2, S_3 \dots S_n$

such that

$$\begin{aligned} S_1 &= \frac{x_1 \rho_1 c_1}{\sum x} \\ S_2 &= \frac{x_2 \rho_2 c_2}{\sum x} \\ S_3 &= \frac{x_3 \rho_3 c_3}{\sum x} \\ &\dots \dots \dots \\ S_n &= \frac{x_n \rho_n c_n}{\sum x} \end{aligned} \tag{26}$$

Where S_1 may be defined as the proportional part of the total heat capacity of the composite system contained in the first layer.

Substituting 26 in 25

$$\rho c = S_1 + S_2 + S_3 + \dots + S_n$$

and

$$\rho c = \sum_{a=1}^n S_a \tag{27}$$

Equation 27 gives the heat capacity of the composite system as a function of the proportional heat capacities of the individual layers.

c. Thermal diffusivity of the composite layer

The thermal parameter required as a measure of transient temperature variation by conduction is α as shown in equation 1. In cloth,

α is defined as "the apparent thermal diffusivity" and is directly proportional to the thermal conductivity and inversely proportional to the heat capacity of the conducting material. In the previous two sections, the heat capacity ρc and the thermal conductivity k were derived for a composite layer. These two parameters may now be combined into an α for a composite system and

$$\alpha = \frac{k}{\rho c} = \frac{1}{\sum_{a=1}^n \frac{1}{k_a} \sum_{a=1}^n S_a} \quad (28)$$

Equation 28 expresses the thermal diffusivity of the composite layer system as a function of the proportional thermal conductivities and specific heats of the individual layers.

In this report only two different cloths will be used in each experiment so that $n = 2$ in equation 28 and

$$\alpha = \frac{K_1 K_2}{(K_1 + K_2)(S_1 + S_2)} \quad (29)$$

3. Apparatus and procedure

The semi-infinite solid method, as explained in a previous report (7), was used to experimentally determine the apparent thermal diffusivity of a composite layer system. The materials comprising the semi-infinite solid were placed in a constant-temperature chamber and allowed to equilibrate. A step change in temperature was introduced at the upper plane bounding face at time $t = 0$ and heat began to flow into the cloth.

The step change is accomplished by bringing the upper face of the cloth into contact with the surface of a heat source which is thermostatically regulated at a higher temperature. This heat source must be capable of storing a large amount of heat and delivering it, subsequent to contact with the cloth, to the interface as required to maintain it at a constant temperature.

A large cylindrical mass of iron with heater wire wound around the circumference was used as a basic heat source. The temperature of this drum heater core temperature is sensed by thermistor T_3 (Fig. 2) imbedded near the geometric center of the steel drum. The core temperature is controlled by the regulator D by adjusting the duty cycle of the circumferential heater.




Figure 2. Wiring diagram for thermal regulation of the block and face heaters.

The drum heater is supplemented by an additional heater placed near the interface and separated from it by a thin copper plate. The copper conducts heat rapidly, thus minimizing the time lag in supplying heat to the interface (a time lag occasioned by the low thermal conductivity of the steel) and also minimizes the possibility of hot spots which could occur if the heater were placed at the surface. The use of this second heater, however, necessitates the inclusion of another heating system with associated regulatory mechanism.

The thermistor T_1 for the face is set in a hole in the copper plate close to the exposed side. A second thermistor T_2 is positioned at the junction of the steel block and copper plate. These two thermistors T_1 and T_2 are wired in series and together they maintain the face heater labeled HF in the diagram. When the cold cloth is brought in contact with the copper plate, it causes the plate to lose heat, resulting in a temperature difference between T_1 and T_2 . This activates regulator F which sends heat to the heater. The influx of heat at T_2 tends to negate the transient effect at T_1 , thus reducing the possibility of

overshoot of the interface temperature due to the finite time required for the diffusion of heat to the surface. Power is supplied to the face heater through variac V.

The heater and control wires L_1 and L_2 are brought up through the cylinder and attached to a terminal strip mounted on the top of the block. The top surface and the entire circumference of the block are covered by an insulating jacket of wood.

The thermocouple used for measuring the interface or boundary temperature is imbedded into but insulated from the exposed side of the copper plate. In this manner, the thermocouple makes thermal contact with the copper as well as the material to be measured.

Once the step change is realized at the cloth's upper surface, the temperature distribution within the material at some time after $t = 0$ is dependent upon the thermal properties, the initial temperature conditions and the new boundary temperature. This relationship is expressed mathematically by the particular solution of equation 1 for a semi-infinite solid (3) which is

$$T = T_s - (T_s - T_o) \left[\frac{2}{\sqrt{\pi}} \int_0^{\frac{x}{2\sqrt{\alpha t}}} e^{-\beta^2} d\beta \right] \quad (30)$$

where

- α = apparent thermal diffusivity of composite layers
- t = time
- T_o = temperature of cloth at $t = 0$
- T_s = temperature of the face
- T = temperature at distance x and time t
- β = Gaussian error integral function of x and t
- x = thickness of 1,2,3 . . . composite layers

4. Results

The first semi-infinite solid used experimentally consisted of 40 layers of cloth: 20 layers of nylon 66 alternated with 20 layers of blanket cloth. These two materials were used because all the necessary parameters were available from a previous report (7).

Thermocouples were placed in the semi-infinite solid down one composite layer (1 layer nylon plus 1 layer of blanket cloth) and two composite layers from the top, giving x 's of .172 and .344 inches (that is, .437 and .874 centimeters to keep the units consistent with those

in Table 1). The cloth and chamber came into equilibrium at $T_0 = 47.7^\circ\text{F}$, and when brought into contact with the heated cylinder resulted in a boundary temperature T_s of 110.4°F . The resultant temperature-time curves are plotted as the circled points of Figure 3.




Figure 3. Transient temperature by composite layers in a semi-infinite solid of nylon and blanket cloth.

The solid curves of Figure 3 were computed using equation 30 and T_0 , T_s and x 's as listed above. The value of apparent thermal diffusivity used was calculated from equation 29 using the parameters of both fabrics listed in Table 1.

The computed parameters for the composite layer are also presented in Table 1 to make comparison easy. The apparent thermal diffusivity of the composite layer when converted to English units is $.0120 \text{ in}^2/\text{min}$ as compared to $.0225 \text{ in}^2/\text{min}$ for blanket cloth and $.0030 \text{ in}^2/\text{min}$ for nylon 66.

Figure 4 is a plot of the complementary semi-infinite solid. The order of the fabrics has been reversed with a layer of blanket cloth adjacent to the step change. The purpose of this was to find if any variations in the transient heat flow occur because of varying the

relative positions of the cloths. Again the circled dots are the experimental data and the solid lines are computed for an apparent thermal diffusivity of .0120 square inches per minute and with an initial temperature $T_0 = 45.3$, a boundary temperature of $T_S = 102.5$, and x again equal to .172 and .344 inches.




Figure 4. Transient temperature by composite layers in a semi-infinite solid of blanket cloth and nylon.

The experiment was next tried with a more practical relationship: two adjacent components of the standard arctic uniform, underwear fabric (50% wool-50% cotton, tubular knit, natural finish, 12 oz/yd²) and shirting (85% wool-15% nylon, OG 108). The properties of these two materials and their composite layer are listed in Table II. The values of apparent thermal diffusivity in English units are: shirting .0123 in²/min; underwear .0155 in²/min; and the composite layer .0136 in²/min.

The temperature-time curves for one and two composite layers are plotted in Figure 5. The solid curve was computed using equation 30 and an apparent thermal diffusivity of .0136 in²/min with $T_0 = 45^\circ\text{F}$, $T_S = 103^\circ\text{F}$ and $x = .145$ and $.290$ inches. The circled points are the experimental temperatures obtained with T_0 , T_S and x 's as stated above.

TABLE I
NECESSARY CONSTANTS FOR COMPUTING THE APPARENT THERMAL
DIFFUSIVITY OF A COMPOSITE LAYER OF BLANKET CLOTH AND NYLON 66

Constants	CLOTH		
	Nylon 66	Blanket Cloth	Composite
x (cm)	.069	.368	.437
Proportional part	.158	.842	1.000
K $\left(\frac{\text{cal}}{\text{cm}^2/\text{sec}/\text{OC}}\right)$	47.85×10^{-5}	11.08×10^{-5}	9.00×10^{-5}
S $\left(\frac{\text{cal}}{\text{cm}^3/\text{OC}}\right)$	3.70×10^{-2}	3.25×10^{-2}	6.95×10^{-2}
α (cm ² /sec)	3.23×10^{-4}	24.19×10^{-4}	12.95×10^{-4}
α (in ² /min)	.0030	.0225	.0120

TABLE II
NECESSARY CONSTANTS FOR COMPUTING THE APPARENT THERMAL
DIFFUSIVITY OF A COMPOSITE LAYER OF UNDERWEAR FABRIC AND NYLON-WOOL SHIRTING

Constants	CLOTH		
	Nylon-Wool Shirting	Underwear Fabric	Composite
x (cm)	.204	.165	.369
Proportional part	.553	.447	1.000
K $\left(\frac{\text{cal}}{\text{cm}^2/\text{sec}/\text{OC}}\right)$	26.58×10^{-5}	33.78×10^{-5}	14.88×10^{-5}
S $\left(\frac{\text{cal}}{\text{cm}^3/\text{OC}}\right)$	6.14×10^{-2}	4.05×10^{-2}	10.19×10^{-2}
α (cm ² /sec)	1.33×10^{-3}	1.67×10^{-3}	1.46×10^{-3}
α (in ² /min)	.0123	.0155	.0136




Figure 5. Transient temperature by composite layers in a semi-infinite solid of underwear cloth and nylon-wool shirting.

5. Discussion

The close agreement between the theoretical and experimental data of Figure 3, 4 and 5 shows that there is an apparent thermal diffusivity associated with a composite layer of dissimilar materials. Furthermore, this apparent thermal diffusivity can be computed for the composite layer of cloth if the thermal conductivities, thermal diffusivities and thicknesses of the individual layers are known.

The apparent thermal diffusivity of the composite system must be known in order to compute the transient heat losses through a multi-layered uniform, and it can also provide valuable insight into thermal problems in clothing design. As an example, consider the two components of the arctic uniform discussed above, the shirting and underwear fabric. The upper curve of Figure 5 is for one composite layer and shows the thermal response with time for an x of .145 inches (1 layer shirting + 1 layer underwear) and a composite apparent thermal diffusivity of .0135 in^2/min . These two constants are combined to form the upper limit to the

integral of equation 30. Inserting this upper limit into the equation as the exponent of e, it can be seen that the rate of transient response is determined by

$$-\left(\frac{x}{2\sqrt{\alpha t}}\right)^2$$

For one composite layer of shirting and underwear fabric,

$$-\left(\frac{x}{2\sqrt{\alpha t}}\right)^2 = -\left(\frac{.145}{2\sqrt{.0136}}\right)^2 = -(.620)^2$$

An equivalent transient response offered by shirting alone would have an upper limit equal to $-(.620)^2$ or

$$\frac{x}{2\sqrt{\alpha t}} = .620$$

With an α equal to $.0123 \text{ in}^2/\text{min}$, the thickness of shirting required to give an equal transient response can be obtained by solving for x, and $x = .138$ inches. Thus a layer of shirting .138 inches thick would have an equivalent transient thermal response to a composite layer .145 inches thick. Since a comparison of insulation values under steady state conditions shows that identical insulation to .145 inches of composite layer, could be equivocated by .143 inches of shirting alone, the major portion of the transient difference could not result from differences in "clo value". Although the underwear cloth may have features which make its inclusion in an arctic uniform quite desirable (such as the feel of contact with the skin and its moisture-absorbitive properties) a 5% saving in bulk and more important, a 13.7% savings in weight could be realized by using two modified layers of shirting rather than a composite layer of shirting and underwear cloth.

The example given, although not completely practical, does show that mathematical analysis of transient thermal components could lead to increased environmental protection from clothing. By properly combining materials, uniforms can be designed which have lighter weight, less bulk and greater tolerance time.

6. References

1. Capey, E.C. and K.I. McKenzie, Theoretical analysis of the heating of a composite slab, with application to the kinetic heating of an aircraft wing. Royal Aircraft Est., Farnborough, England, Tech. Note No. 243, Jun 1958.
2. Chen, N.Y. and W.P. Jensen, Skin simulant with depth magnification. Tech. Rpt. No. 5, Fuels Res. Lab., M.I.T., Cambridge, Mass., Mar 1957.

3. Ingersoll, L.R., O.J. Zobel and A.C. Ingersoll, Heat Conduction. McGraw-Hill, Inc., N.Y. 1948.
4. Jakob, M., Heat Transfer, Vol. I. John Wiley & Sons, N.Y. 1949.
5. Jakob, M. and G.A. Hawkins, Heat Transfer and Insulation. John Wiley & Sons, N.Y. 1942.
6. McAdams, W.H., Heat Transmission. McGraw-Hill, Inc., N.Y. 1942.
7. Powers, J.J. and F.W. Botsch, Apparent thermal diffusivity of fabrics. QM R&E Center, Natick, Mass., Env Prot Res Div Rpt EP-126, Feb 1960.

DISTRIBUTION LIST

GENERAL STAFF

- 1 Deputy Chief of Staff for Logistics
Department of the Army
Washington 25, D. C.
- 1 Deputy Chief of Staff for Personnel
Department of the Army
Washington 25, D. C.
- 1 Deputy Chief of Staff for Military
Operations, Department of the Army
Washington 25, D. C.
- 1 Chief of Research & Development
Department of the Army
Washington 25, D. C.

ARMY

- 5 The Quartermaster General
Department of the Army
Washington 25, D. C.
- 2 Commanding General
Philadelphia QM Depot, U.S. Army
2800 South 20th Street
Philadelphia, Pa.
- 4 Commandant
Q4 Food & Container Institute for the
Armed Forces, U. S. Army
1819 W. Pershing Rd.
Chicago, Illinois
- 3 Commanding Officer
QM R&E Field Evaluation Agency, U.S. Army
Ft. Lee, Virginia
Attn: Chief, TSO
- 2 QM Liaison Officer, WCOL-8
Wright Air Development Center
Wright-Patterson AF Base
Dayton, Ohio
- 1 Commandant
The QM School
Ft. Lee, Virginia
Attn: Library
- 1 Commanding General
Frankford Arsenal, Phila 37, Pa.
Attn: Engr. Psychology Div. (L2)
- 3 Hqs., Army Electronic Proving Ground
Ft. Huachuca, Arizona
Attn: Aviation & Meteorological Dept.
Tech. Information Br.
Deputy Chief for Meteorology
- 2 Commanding General
The Engineer Center
Ft. Belvoir, Va.
- 1 Commanding Officer
Diamond Ordnance Fuze Labs.
Washington 25, D. C.
Attn: Tech Reference Section
(ORDTL-012)
- 2 Commanding General
Aberdeen Proving Ground
Aberdeen, Maryland
- 2 Chief Signal Officer
Department of the Army
Washington 25, D. C.
Attn: Res. & Dev. Div.

ARMY (Cont)

- 1 Commanding Officer
Signal Corps Engr. Lab.
Ft. Monmouth, N. J.
- 1 Office of Chief of Engineers
Department of the Army
Temp. Bldg. T-7, Gravelly Point
Washington 25, D. C.
Attn: Research & Dev. Div.
- 4 CO, Chemical Warfare Laboratories
Army Chemical Center, Maryland
Attn: Technical (AS 13) Library
- 1 Chief Chemical Officer
Department of the Army
Bldg. T-7, Gravelly Point
Washington 25, D. C.
Attn: Res. & Dev. Div.
- 2 CO, Hq., Medical Nutrition Lab.
Fitzsimons Army Hospital
Denver, Colorado
(1-Dr. Friedmann)
- 1 Armed Forces Institute of Pathology
Washington 25, D. C.
- 1 Chief, Armed Services Medical
Procurement Agency
84 Sands St., Brooklyn 1, N. Y.
Attn: Property Officer
Marked: Req. DUED #151
- 1 Chief of Transportation
Department of the Army
Temp Bldg. T-7, Gravelly Point
Washington 25, D. C.
- 2 Commanding Officer
Transportation Res & Eng Command
U. S. Army
Ft. Eustis, Virginia
Attn: Tech Services Dir.
- 1 The Army Library
Pentagon Bldg.,
Washington 25, D. C.
- 1 Commandant, Command & General Staff
College
Ft. Leavenworth, Kansas
- 1 Commandant, U. S. Military Academy
West Point, New York
- 1 Commanding Officer, Detroit Arsenal
2825 Van Dyke St., Centerline, Mich.
Attn: Res & Engr. Div.
- 1 Commanding General
Hqs., U. S. Army Medical R&D Command
Main Navy Bldg.
Washington 25, D. C.
Attn: NP&PP Research Branch
- 2 Commander
QM Intelligence Agency, U.S. Army
Washington 25, D. C.
- 2 Executive Director
Military Clothing and Textile Supply Agency
2800 S. 20th St., Phila. 45, Pa.
- 1 Commanding Officer
QM R&E Field Evaluation Agency, U.S. Army
Airborne Systems Test Div.
Yuma Test Station
Yuma, Arizona

ARMY (Cont)

- 1 Commanding Officer
Cold Weather & Mountain Indoctrination
School
Fort Greeley, Alaska
- 1 Commanding Officer
Fort Greeley, Alaska
AIR FORCE Post Library
- 2 Department of Air Force
Hqs., USAF, Wash 25, D. C.
(1 DC/S Material, 1 DC/S Dev.)
- 1 Director
Air University Library, Attn: 7876
Maxwell AFB, Alabama
- 2 Commandant
USAF School of Aviation Medicine
Randolph AF Base
Randolph Field, Texas
- 1 Commander, Arctic Aeromedical Lab
APO 731, Seattle, Washington
- 1 Commander
Air Res & Dev Command
Attn: RDBETL (Hqs., Tech Lib. Br.)
Andrews AF Base, Washington 25, D. C.
- 1 Commander
Wright Air Development Center
Wright Patterson AF Base, Ohio
Attn: Tech Library
- 1 Commander
Strategic Air Command
Offutt AF Base, Nebraska
- 1 Chief, Nutrition Div.
Air Development Center
Asso-Medical Lab.
Wright Patterson AFB, Ohio
Attn: Dr. Harry C. Dyme
- 1 Commander
AF Cambridge Research Center
Air Research & Development Cmd.
Laurence G. Hanscom Field
Bedford, Mass.
Attn: CRTOTT-2

NAVY (Cont)

- 1 Commander, U. S. Naval Ord. Test
Station, China Lake, Calif.
Attn: Code 763
- 1 Chief, Bureau of Aeronautics
Dept. of the Navy, Wash 25, D. C.
Attn: Code AE 52
- 1 Chief, Bureau of Supplies & Accounts
Department of the Navy
Washington 25, D. C.

CONARC

- 1 C. G., U.S. Continental Army Command
Ft. Monroe, Va.
- 1 President
U. S. Army Artillery Bd.
Ft. Sill, Okla.
Attn: ATBA
- 1 President
US Army Armor Board
Ft. Knox, Ky.
Attn: ATBB
- 1 President
U. S. Army Infantry Bd.
Ft. Benning, Ga.
Attn: ATBC
- 1 President
U. S. Army Air Defense Bd.
Ft. Bliss, Texas
Attn: ATBD
- 1 President
U. S. Army Airborne and Electronics Bd.
Ft. Bragg, N. C.
Attn: ATBE
- 1 President
U. S. Army Aviation Bd.
Ft. Rucker, Ala.
Attn: ATBG
- 1 Commanding Officer
U. S. Army Arctic Test Board
Ft. Greely, Alaska
Attn: ATBE

NAVY

- 1 Director
Naval Research Laboratory
4th & Chesapeake St., S. W.
Washington 25, D. C.
- 1 Chief, Bureau of Ordnance
Department of the Navy
Washington 25, D. C.
Attn: R&D Div.
- 1 Naval Medical Research Institute
National Naval Med. Res. Center
Bethesda, Md.
- 2 Chief of Naval Research
Washington 25, D. C.
Attn: Code 402S
- 1 Chief, Bureau of Ships
Department of the Navy
Washington 25, D. C.
Attn: Code 331
- 1 Chief, Bureau of Med. & Surgery
Dept. of the Navy, Wash 25, D. C.
Attn: Code 33

BOARDS & COMMITTEES

- 1 Army Committee on Environment
Chief, Research & Development
Pentagon, Washington, D. C.
- 1 Armed Forces Pest Control Bd.
Walter Reed Army Med. Center
Forest Glen Annex
Main Bldg.
Forest Glen, Maryland
- 1 Army Research Committee
Chief, Research & Development
Pentagon, Washington, D. C.

MISCELLANEOUS

- 1 National Research Council
12 Constitution Ave., Washington, D. C.
Attn: Advisory Bd. on QM R&D
- 10 Armed Services Technical Information Agency
Arlington Hall Station
Arlington 12, Va.
Attn: TTI-DR
- 2 Gift and Exchange Division
Library of Congress
Washington 25, D. C.
- 1 U. S. Department of Commerce
Weather Bureau Library, Washington, D. C.
- 1 Central Intelligence Agency
Collection & Dissemination
Washington 25, D. C.
- 1 National Library of Medicine
Washington 25, D. C.
- 1 Generalintendanten
Standardiseringskontoret
Festningen
Oslo, Norway
- 1 Marine Corps Equipment Board
Marine Development Center
Marine Corps School
Quantico, Va.
- 1 Office of Technical Services
U. S. Department of Commerce
Washington 25, D. C.
Attn: Tech Rpt's Sec (THRU OQMG)
- 1 U. S. Department of Agriculture Library
Washington 25, D. C.
- 1 Commandant
Industrial College of the Armed Forces
Ft. McNair, Washington 25, D. C.
- 1 QM Representative
Army Command and General Staff College
Department of the Infantry Div.
Ft. Leavenworth, Kansas

UNCLASSIFIED

UNCLASSIFIED