

63-1-1

U. S. NAVAL AMMUNITION DEPOT
Crane, Indiana

RDTR No. 31
7 August 1962

284 794
CATERGOGED BY ASTIA
AS AD NO. 284794

INVESTIGATION OF VISIBILITY AND
FORMULATION OF "ASHLESS BLUE FLARE"

OCT 2 1962

PREPARED BY James McGriffin
James McGriffin, Chemist

William Ripley
William Ripley, Chemist

REVIEWED BY Carl Armour
Carl Armour, Head Chemical Laboratory

REVIEWED BY Antonio Trenta
Antonio Trenta, Head Facilities Division

The information contained in this document represents the opinions of the Research and Development Department and should not be construed to represent the official policy of the U. S. Naval Ammunition Depot, Crane, Indiana. This document is authorized for external distribution.

SIGNED R. M. Janig
Director, Research & Development Dept.

ABSTRACT

The object of this study is to conduct investigations leading to the development of a feasible blue flare formula with the remaining ash residue being as small as possible. After trying numerous formulae a very promising formula was developed containing copper dust, as the molecular emitter, ammonium perchlorate, stearic acid, and paraffin. This report covers all of the physical and chemical tests performed in estimating the feasibility of using the proposed formula in an operational signal.

TABLE OF CONTENTS

	<u>Page</u>
Abstract	1
Introduction	1
Formula	2
Test Results	2
(a) Test body description	2
(b) Test body burn time.	2
(c) Oxygen balance	2
(d) Particle size investigation.	2
(e) Electrostatic Sensitivity	2
(f) Impact Sensitivity	2
(g) DTA Analysis	3
(h) TGA Analysis	3
(i) Chromaticity & candle power.	3
Conclusions	3

INTRODUCTION

The optimum formula, in reference to visual observation, and sensitivity tests contains 74.2% ammonium perchlorate. This amount was necessary to obtain a brilliant blue flame, and any reduction resulted in undesirable flame characteristics. Paraffin was added to desensitize and also serve as a binder. Visual observation of the flame purity was very good when observed in darkness and semi-darkness. However, daylight tests have not been conducted.

FORMULA

Ammonium Perchlorate (oxidizer)	74.2%
Stearic Acid (Reducing Agent)	11.1%
Paraffin (desensitizer & binder)	3.7%
Copper Dust (molecular emitter)	11.1%

TEST RESULTS

- (a) Test bodies of 3/4" diameter & length 1 1/8" were used, and a pressure of 8,000 psi was used to press bodies.
- (b) Test bodies burned at a rate of 20 seconds/inch.
- (c) Fuel-oxidizer investigation indicated 74.2% oxidizer and 11.1% reducer to be the optimum ratio.
- (d) Increasing particle size of oxidizer, to increase burning time, reduced the intensity greatly.
- (e) Electrostatic Sensitivity (0.2 mfd Capacitance)
- | | |
|---------|----------------------|
| Voltage | 4250 Volts - No fire |
| | 2000 Volts - No fire |
| | 1000 Volts - No fire |
| | 500 Volts - No fire |
| | 250 Volts - No fire |
| | 220 Volts - No fire |
| | 200 Volts - No fire |
- (f) Impact Sensitivity (ran on impact sensitivity machine)
- | | |
|-----------------|-----------------|
| 16 cm - No fire | 40 cm - No fire |
| 20 cm - No fire | 50 cm - No fire |
| 25 cm - No fire | 70 cm - No fire |
| 30 cm - No fire | |

By dropping block directly on sample the following results were obtained:

30 cm - No fire

40 cm - No fire

41 cm - Fire

42.5 cm - Fire

51 cm - Fire

(g) DTA Analysis:

A severe exotherm occurred at 250°C which was apparently ignition of the sample.

(h) TGA Analysis:

No weight loss was obtained until the temperature of 250°C was reached. Ignition then occurred.

(i) Chromaticity Test:

Flare body 1 5/8" diameter and length 5" composition weight 250 gm, using TNC first fire. Distance 5.75 ft. Burn time 64.6 seconds.

	<u>Test 1</u>	<u>Test 2</u>
Candlepower	- 671	784
DWL	- 567 mu	567 mu
Purity	- 76%	76%

CONCLUSIONS

It appears this formula is very good, in reference to color and residue left after ignition. However, tests should be made in daylight to determine visibility and color. Sensitivity tests indicate that the material should be safe to handle and press.

DISTRIBUTION

Addressee	Copies
Chief, Bureau of Naval Weapons Department of the Navy Washington 25, D.C. Attention: Code DIS-3 (One copy) Code RMMO-32 (One copy)	2
Director ASTIA Document Center Arlington Hall Station Arlington, Virginia	10
Commander U. S. Naval Ordnance Test Station China Lake, California Attention: Code 4543 (One copy) Library (One copy)	2
Commander U. S. Naval Ordnance Laboratory White Oak, Silver Spring, Md. Attention: Code WE (One copy) Library (One copy)	2
Wright-Patterson AFB Aeronautical Systems Division Dayton, Ohio Attention: ASRNGC-3	1
Commanding General U. S. Ordnance Corps Picatinny Arsenal Dover, New Jersey Attention: Pyrotechnic Laboratory	1