

UNCLASSIFIED

AD 296 283

*Reproduced
by the*

**ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA**



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

65-2-7


CATALOGED BY ASTIA
AS AD ~~NO~~ 6283

USAEIRD Technical Report 2310

**TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS
ON GERMANIUM PNP ALLOY TRANSISTORS**

Edwin T. Hunter

Harry E. Wannemacher



October 1962

296 283

**UNITED STATES ARMY
ELECTRONICS RESEARCH AND DEVELOPMENT LABORATORY
FORT MONMOUTH, N.J.**

U. S. ARMY ELECTRONICS RESEARCH AND DEVELOPMENT LABORATORY
FORT MONMOUTH, NEW JERSEY

October 1962

USAKIRD Technical Report 2310 has been prepared under the supervision of the Director, Electronic Components Department, and is published for the information and guidance of all concerned. Suggestions or criticisms relative to the form, contents, purpose, or use of this publication should be referred to the Commanding Officer, U. S. Army Electronics Research and Development Laboratory, Fort Monmouth, New Jersey, Attn: Chief, Semiconductor and Microelectronics Branch, Solid State and Frequency Control Division.

J. M. KIMBROUGH, JR.
Colonel, Signal Corps
Commanding

OFFICIAL:

HOWARD W. KILLAM
Major, SigC
Adjutant

DISTRIBUTION:

Special

QUALIFIED REQUESTERS MAY OBTAIN COPIES
OF THIS REPORT FROM ASTIA.

THIS REPORT HAS BEEN RELEASED TO THE OFFICE OF
TECHNICAL SERVICES, U. S. DEPARTMENT OF COMMERCE,
WASHINGTON 25, D. C., FOR SALE TO THE GENERAL PUBLIC.

TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS
ON GERMANIUM PNP ALLOY TRANSISTORS

Edwin T. Hunter

Harry E. Wannemacher

TASK NR. OST-74-00-005-26 (DASA)

TASK NR. 3A99-21-001-01 (DA)

ABSTRACT

Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Penn. State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of $f\alpha$.

U. S. ARMY ELECTRONICS RESEARCH AND DEVELOPMENT LABORATORY

FORT MONMOUTH, NEW JERSEY

CONTENTS	Page
ABSTRACT	
INTRODUCTION	1
EXPERIMENTAL PROCEDURE	1
RESULTS	3
CONCLUSIONS	6
ACKNOWLEDGEMENTS	6
REFERENCES	7

FIGURES

1. Common Base Forward Current Transfer Ratio, α vs. Total Neutron Dose of $E > 0.1$ Mev, Φ	8
2. Leakage Current, I_{CBO} vs. Φ ($E > 0.1$ Mev)	9
3. Maximum Transient Change in I_{CBO} vs. V_{CB}	10
4. Degradation in α vs. Φ_f	11
5. Damage Constant, K , vs. Φ_f	12
6. Damage Constant vs. Φ_f	13

TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS

INTRODUCTION

Many groups of experimenters and theoreticians have, during the past several years, contributed much data and many theories concerning the effects of nuclear radiation on semiconductor devices, such as transistors or diodes. At first, most of these contributions concerned nuclear radiation in general, with no regard for the rate of delivery of the radiation to the devices under consideration. As time passed and more was learned about mechanisms of radiation damage, two separate types of studies began to develop; namely, exposures of devices to relatively low rate sources for lengthy periods of time, and exposures to very brief bursts of radiation with very high peak rates. The former types of studies were conducted, and still are being conducted, to observe at a leisurely pace what happens to create the so-called permanent damage effects. The latter variety of work being carried out is an effort to simulate what one might expect in the way of nuclear radiation from the detonation of a nuclear or thermonuclear type weapon.

Studies of this kind have resulted in a fair library of data and ideas. It has been our purpose during the past twelve months to plan experiments and acquire data to enable comparison of the effects observed on a given variety of transistors when exposed to the nuclear radiation environment extant in a power reactor (in this case the Pennsylvania State University 200 Kw facility) and to that found near a pulsed reactor (in this case the Sandia Pulsed Reactor Facility (SPRF)).

EXPERIMENTAL PROCEDURE

The Pennsylvania State University Reactor Experiments

The reactor facility available at Penn. State is of the swimming pool variety, capable of operation at a maximum power level of 200 Kw. At this level of operation, a target located underwater, and immediately adjacent to the reactor core, will be bombarded by a neutron flux of $2 \times 10^{12} N_f v$ (neutrons/cm²-sec) with energies between 0.1 Mev and 10 Mev. In this report, N_f will refer to neutrons with energy > 0.1 Mev. The total dose received can be obtained either by calculating it from the power level of the reactor and the time of exposure, or by using some selected threshold detector and the measured spectrum of the reactor. In our experiments, the former system was employed with an occasional check being made with sulfur threshold dosimeters.

The actual experimental arrangements used in the two experiments at Penn. State discussed in this report, if examined carefully, will show a great improvement from the first to the second. In general, the system

consists of a waterproof container, which houses the items under test, placed near the reactor core; a plastic tube containing the electrical connections from the submerged housing; the test circuitry, and a means of recording the information. In the first of these two experiments, the underwater container proved extremely awkward in that it was oriented horizontally and, being buoyant, quite difficult to lower on the instrument bridge. The plastic tubing used was heavy wall polyethylene, which became cracked during transit and tended to allow water to penetrate the system. These items did their job, but the system designed for the second experiment was much more efficient. For example, the container was oriented vertically and weighted with lead poured into the bottom. There was no problem whatever in lowering this tank to the bottom of the reactor pool. Also, the tubing used was lighter weight Tygon rather than polyethylene. Tygon will withstand the bending and rolling encountered in the laboratory and in transit.

The test circuits were basically the same in the two experiments; except that in the second one all devices not in the actual test circuit were switched to a common standby circuit which maintained d.c. bias on all such devices. During the first experiment, the devices were removed from the test circuit and left with no bias. In both experiments, the data was fed to a digital voltmeter with printout and recorded on printed tape. The devices under test were Ge alloy units arranged in a common base configuration, and the forward current transfer ratio α , was monitored consecutively on all devices. Upon completion of a set of α measurements, the emitter of the device under test was opened, and the collector-base leakage current I_{CBO} was monitored. Before and after measurements were also made on the effective minority carrier lifetime by the current injection technique described by Lederhandler and Giacoletto.¹ The nature of the data taken may be seen in Figure 1 showing α vs. Φ_F for the extremes of f_Q , the cutoff frequency, under investigation, and in Figure 2, which shows the variation in I_{CBO} with Φ_F , again for the extremes in f_Q .

The Sandia Pulsed Reactor Facility

The Sandia reactor is a bare critical assembly providing a mixed neutron and gamma pulse of about 50 microseconds width at half maximum. At the screen, which is as near to the core as it is possible to locate, a target will be exposed to approximately 10^{13} nvt (neutrons/cm²) with energies greater than 0.1 Mev, and about 2500 rads (H₂O) from gamma rays. The neutron doses are measured by threshold dosimeters, mainly sulfur ($E > 2.0$ Mev), with an occasional set of fission foils to keep a check on the spectrum. The gamma ray dose is measured by the Bausch & Lomb glass microdosimeter system. All of this dosimetry is provided by The Sandia Corporation. A more complete description of the Facility may be found in a Sandia Corp. monograph.²

The circuitry and recording equipment were set up in a trailer outside of the reactor building with the components being tested

mounted on a small chassis next to the reactor screen and connected to the trailer with approximately 150' lengths of RG-58 cable. Since the reactor pulse is very short, it is required to have a recording "channel" for each piece of information desired, and, as a result, the four oscilloscope traces can be utilized to record only three pieces of parametric data and one trace from a MgORAD to provide the pulse shape. For this reason, a much smaller quantity of data is available from the Sandia experiments than from Penn. State; however, some of this data is on the transient effects, about which there is currently great interest.

The devices under test were again germanium alloy units arranged in a common base configuration. In some of the tests, I_{CBO} was monitored with data being taken with different applied V_{CB} . In other tests, the output current, I_C , was monitored; however, circuit problems resulted in some rather unenlightening information in this area. The information was fed into oscilloscopes (Tektronix 555) and the resulting traces were photographed during the reactor burst. The transient I_{CBO} data is the most interesting transient information obtained in these experiments, and a plot of the peak change in I_{CBO} vs. the applied V_{CB} is shown in Figure 3. If one examines this data carefully and notes that the original values of I_{CBO} are much smaller than the transient values, a judicious application of Ohm's law reveals that there is a shunt resistance of approximately 200 K being dropped across the collector-base junction during the reactor burst. Pending closer study of other experimenters' data, it appears that this may possibly be an indicator that we are observing air ionization between leads inside the can, since 200 K is approximately the resistance of ionized air near the screen of the SPRF.

In an effort to compare SPRF produced effects with Penn. State produced effects, a set of transistors was placed on a plank which was laid radially outward from the reactor and left there for 16 pulses. In this manner a large dose was obtained, but with a much higher rate than at Penn. State. On these devices h_{FE} and τ_e were measured for permanent change.

RESULTS

The combined results of these previously described experiments can be presented in various forms. One form that is used rather prevalently is the relationship between $\Delta\alpha$ and Φ_f . Figure 4 shows data obtained from all of the experiments, broken into three separate categories according to f_α of the devices. From these curves, it can be seen that there is greater damage, represented by greater changes in α , at higher dose levels, and at lower values of f_α . This is understandable when one considers the relation derived in the literature;³

$$f_\alpha = \frac{1.22}{\pi} \left(\frac{D_p}{W^2} \right) \quad (1)$$

where D_p is the diffusion constant for holes in the base of a pnp device

and W is the base width. If f_α is high, then W must be narrower, thereby providing less volume in which lattice displacements can affect the passage of minority carriers, and, at the frequencies in question, the reduction in the minority carrier lifetime is the major cause of electrical degradation, manifested in the lowering of α .

Now, let us consider the damage constants involved in these experiments. According to Webster⁴

$$\frac{1}{\beta} = \frac{SWA_s}{D_p A_e} + \frac{\sigma_b W}{\sigma_e L_{ne}} + \frac{W^2}{2L_{pb}^2} \quad (2)$$

where: β = common emitter forward current transfer ratio

σ = conductivity

A_e = area of the emitter junction

A_s = effective surface recombination area around emitter

L = diffusion length

W = base width

S = surface recombination velocity.

From equation (1) and the fact that

$$L_{pb}^2 = D_p \tau_p \quad (3)$$

we arrive at the equation:

$$\frac{W^2}{2L_{pb}^2} = \frac{1.22}{2\pi} \left(\frac{1}{f_\alpha} \right) \left(\frac{1}{\tau_p} \right) \quad (4)$$

which can be substituted into equation (2) to give:

$$\frac{1}{\beta} = \frac{SWA_s}{D_p A_e} + \frac{\sigma_b W}{\sigma_e L_{ne}} + \frac{1.22}{2\pi f_\alpha} \left(\frac{1}{\tau_p} \right). \quad (5)$$

Now, according to Loferski,⁵ the surface recombination term and the emitter efficiency term are unchanging with radiation, at least relative to the bulk term, at the frequencies of interest. Therefore, we can examine the difference between Webster's equation before irradiation and after irradiation:

$$\frac{1}{\beta_f} - \frac{1}{\beta_i} = \frac{1.22}{2\pi f_\alpha} \left(\frac{1}{\tau_{pf}} - \frac{1}{\tau_{pi}} \right) \quad (6)$$

where the subscript i indicates initial conditions, and the subscript f indicates conditions after irradiation.

Relating τ_{pf} to τ_{pi} by the following:⁶

$$\frac{1}{\tau_{pf}} = \frac{1}{\tau_{pi}} + \frac{\Phi_f}{K} \quad (7)$$

where Φ_f = total integrated neutron dose in neutrons/cm², with energy greater than 0.1 Mev

and K = the damage constant.

Combining equations (6) and (7),

$$\frac{1}{\beta_f} - \frac{1}{\beta_i} = \frac{1.22}{2\pi f\alpha} \left(\frac{\Phi_f}{K} \right). \quad (8)$$

Lifetime changes are available on only some of the devices; however, on these, it is of interest to compare the values of K calculated directly from equation (7), which values will be referred to as K_r , and those calculated from equation (8), which values will be referred to as K_β . If the ratio, r_K , of K_β is computed for each of the fifteen devices

$\frac{K_\beta}{K_r}$ exposed at Sandia on which both lifetime and gain changes were recorded, and the results averaged, a value of r_K is obtained of 3.2 ± 1.7 . On six devices exposed at Penn. State, the computed ratio is 1.7 ± 0.5 . The constant that is generally referred to as the damage constant is K_r . Reference 6 gives a K for n-type Ge of $5.0 \pm 2.0 \times 10^7$ Nvt-sec. The fact that the above difference exists between K_r and K_β may be explained by the fact that the injected carrier transport mechanism is not solely diffusion.

Some experimenters have indicated possible differences in amount of damage for the same radiation dose administered in different spectral distributions.⁷ This problem arises because the dose is given in terms of all neutrons having $E >$ some value which is not the damage threshold. Data taken during these experiments yield the following values of K_β averaged over the number of devices shown:

Penn. State Ept.	#1	8 Units	$(1.05 \pm 0.19) \times 10^8$	Nvt-sec.
Penn. State Ept.	#2	20 Units	$(2.1 \pm 0.8) \times 10^8$	Nvt-sec.
Sandia Ept.	#1	20 Units	$(5.2 \pm 2.2) \times 10^7$	Nvt-sec.
Sandia Ept.	#2	66 Units	$(3.5 \pm 1.3) \times 10^7$	Nvt-sec.

It is readily apparent that there is a significant difference in the K_β 's obtained in the two different environments. The two values obtained in one environment may be averaged, as can the other two, and then a ratio, r_{Env} , can be obtained. The data above yield a value of $r_{Env} = 3.6 \pm 2.5$ by statistical error treatment. This factor is

attributed to the different dose rates of the two environments used. If one expressed the dose in terms of all neutrons with energy greater than 400 e.v., the factor would be even larger due to the spectral differences in the two environments.

The values of K calculated so far have been made on the basis of an actual constant existing. No further calculations will be made, but it may be of interest to note that, as shown in Figure 5, the values of K_T as calculated from Sandia data have somewhat of a dependence on the total neutron flux. Figure 6, showing data on K_T taken at two different total exposures at Penn. State show an opposite dependence on total dose. An attempt to explain the significance of these observations will not be made at this time.

CONCLUSIONS

The conclusions reached are applicable to the particular family of devices on which these data were collected, i.e., germanium alloy, PNP devices with a range of τ_Q from 3.3 mc. to 13.2 mc. The conclusions are as follows:

1. Permanent gain degradation is inversely proportional to f_Q .
2. Permanent increase in I_{CBO} is directly proportional to f_Q .
3. Transient increases in I_{CBO} are directly proportional to the applied voltage, V_{CB} , indicating a shunt resistance of 200 K.
4. The damage constants calculated from changes in minority carrier lifetimes are approximately one-third the value of the constants calculated from changes in β . This indicates that in the units under study, the injected carrier transport mechanism is not solely diffusion.
5. The damage constants obtained on devices exposed at Penn. State were about three times as large as those obtained on devices exposed at Sandia. This indicates that three times as much permanent damage was done by the high-rate pulsed radiation received at Sandia as was done by the same dose of low-rate radiation received at Penn. State. If the total dose is expressed as all neutrons having energy greater than 400 ev., rather than 100 Kev., this factor would be still larger, since the PSU spectrum is richer in low energy neutrons than is the SPRF spectrum.

ACKNOWLEDGEMENTS

The authors wish to note contributions made in the planning and conducting of these experiments by Sp/4 Gary D. Thomas and PFC William C. Bush. The personnel of the Sandia Corp. and of the Pennsylvania State University Reactor Facility also contributed by their cooperation in the

use of their facilities. Some of the original suggestions leading to this set of experiments were made by Mr. Frederick Gordon, Jr., Deputy Chief, S & M Branch.

REFERENCES

1. Lederhandler, S. R. & Giacoletto, L. J., "Measurement of Minority Carrier Lifetime and Surface Effects in Junction Devices," Proc. IRE, Vol. 43, pp. 477-483, April 1955.
2. Colp, J. L. & O'Brien, P. D., "The Sandia Pulsed Reactor Facility," Sandia Corp. Monograph SCR-229, August 1960.
3. Hunter, L.P., Handbook of Semiconductor Electronics, McGraw-Hill, 1956, Chapter 4, p.23.
4. Webster, W.M., "On the Variation of Junction Transistor Current Amplification Factor with Emitter Current," Proc. IRE, Vol. 42, pp. 914-920, June 1954.
5. Loferski, J.J., "Analysis of the Effect of Nuclear Radiation on Transistors," J. Applied Physics 29, 35 (Jan. 1958).
6. Messenger, G.C. & Spratt, V.P., "The Effect of Neutron Irradiation on Germanium and Silicon," Proc. IRE, Vol. 46, Nr. 6, June 1958, pp. 1038-1044.
7. Contract Report ASD TR 61-511 from Litton Systems, Inc., under Contract AF 33 (600)-41452.






FIG. 2
LEAKAGE CURRENT, I_{CB0}
vs. Φ ($E > 0.1 \text{ MeV}$)








FIG. 4. DEGRADATION IN α VS. Φ_f





FIG. 6
DAMAGE CONSTANT VS. Φ_f



DISTRIBUTION

	<u>COPIES</u>
Office of the Assistant Secretary of Defense (Research and Engineering) ATTN: Technical Library Room 3E1065, The Pentagon Washington 25, D.C.	1
Commanding General U. S. Army Electronics Command ATTN: AMSEL-AD Fort Monmouth, New Jersey	3
Chief of Research and Development Department of the Army Washington 25, D.C.	2
Chief, United States Army Security Agency ATTN: ACofS, G4 (Technical Library) Arlington Hall Station Arlington 12, Virginia	1
Commanding Officer U. S. Army Electronics Research & Development Activity ATTN: Technical Library Fort Huachuca, Arizona	1
Commanding Officer U. S. Army Electronics Research & Development Activity ATTN: SELMS-AJ White Sands, New Mexico	1
Commanding Officer U. S. Army Electronics Research Unit P.O. Box 205 Mountain View, California	1
Commanding Officer U. S. Army Electronics Materiel Support Agency ATTN: SELMS-ADC Fort Monmouth, New Jersey	1
Headquarters, United States Air Force ATTN: AFCIN Washington 25, D.C.	2

DISTRIBUTION (Cont)

COPIES

Rome Air Development Center ATTN: RAALD Griffiss Air Force Base, New York	1
Ground Electronics Engineering Installation Agency ATTN: ROZMEL Griffiss Air Force Base, New York	1
Aeronautical Systems Division ATTN: ASAPRL Wright-Patterson Air Force Base, Ohio	1
U. S. Air Force Security Service ATTN: ESD San Antonio, Texas	1
Strategic Air Command ATTN: DOCE Offutt Air Force Base Nebraska	1
Air Proving Ground Center ATTN: PGAPI Eglin Air Force Base, Florida	1
Air Force Cambridge Research Laboratories ATTN: CRXL-R Laurence G. Hanscom Field Bedford, Massachusetts	2
AFSC SCIENTIFIC/TECHNICAL LIAISON OFFICE U. S. Naval Air Development Center Johnsville, Pa.	1
Chief of Naval Research ATTN: Code 427 Department of the Navy Washington 25, D.C.	1
Bureau of Ships Technical Library ATTN: Code 312 Main Navy Building, Room 1528 Washington 25, D.C.	1
Chief, Bureau of Ships ATTN: Code 454 Department of the Navy Washington 25, D.C.	1

DISTRIBUTION (Cont)

	<u>COPIES</u>
Hq, Electronic Systems Division ATTN: ESAT Laurence G. Hanscom Field Bedford, Massachusetts	1
Chief, Bureau of Ships ATTN: Code 686B Department of the Navy Washington 25, D.C.	1
Director U. S. Naval Research Laboratory ATTN: Code 2027 Washington 25, D.C.	1
Commanding Officer & Director U. S. Navy Electronics Laboratory ATTN: Library San Diego 52, California	1
Commander U. S. Naval Ordnance Laboratory White Oak Silver Spring 19, Maryland	1
Director U.S. Army Engineer Research & Development Laboratories ATTN: Technical Documents Center Fort Belvoir, Virginia	1
Commanding Officer U. S. Army Chemical Warfare Laboratories ATTN: Technical Library, Building 330 Army Chemical Center, Maryland	1
Commander Armed Services Technical Information Agency ATTN: TISIA Arlington Hall Station Arlington 12, Virginia	20
USAEIRDL Liaison Officer Ordnance Tank Automotive Command U. S. Army Ordnance Arsenal Detroit, Center Line, Michigan	1

DISTRIBUTION (Cont)

	COPIES
Commanding Officer Harry Diamond Laboratories ATTN: Library, Bldg. 92, Room 211 Washington 25, D.C.	1
USAEIRDL Liaison Officer Naval Research Laboratory ATTN: Code 1071 Washington 25, D.C.	1
USAEIRDL Liaison Officer Massachusetts Institute of Technology Building 26, Room 131 77 Massachusetts Avenue Cambridge 39, Massachusetts	1
USAEIRDL Liaison Office Aeronautical Systems Division ATTN: ASDL-9 Wright-Patterson Air Force Base Ohio	1
U. S. Army Research Liaison Office Lincoln Laboratory P. O. Box 73 Lexington, Massachusetts	1
USAEIRDL Liaison Officer Rome Air Development Center ATTN: RAOL Griffiss Air Force Base New York	1
Chief, West Coast Office U. S. Army Electronics Research & Development Laboratory 75 South Grand Avenue, Building 13 Pasadena, California	1
USAEIRDL Liaison Engineer USASCAJ A.P.O. 343 San Francisco, California	1
Chief Scientist, SELRA/CS Hq. USAEIRDL	1
USAEIRDLA--White Sands Liaison Office, SELRA/LNW, USAEIRDL	1
Corps of Engineers Liaison Officer, SELRA/LNE, USAEIRDL	1
Marine Corps Liaison Officer, SELRA/LNR, USAEIRDL	1

DISTRIBUTION (cont)

COPIES

U.S. Army Combat Developments Command Liaison Office, SELRA/ LNF, USAEIRDL	3
Commanding Officer, U.S. Army Signal Research Activity, Evans Area	1
Chief, Technical Information Division, Hq, USAEIRDL	6
USAEIRDL Technical Documents Center, Evans Area	1
Commanding General Army Materiel Command ATTN: R&D Directorate Washington 25, D. C.	2
Director, Electronic Components Dept., USAEIRDL	1
Director, Solid State & Frequency Control Div., EC Dept	1
Deputy Director, Solid State & Frequency Control Div., EC Dept	1
Chief, Technical Staff, Solid State & Frequency Control Div	5
Chief, Piezoelectric Crystal & Circuitry Br, Solid State & Frequency Control Div.	5
Chief, Semiconductor & Microelectronics Br, Solid State & Frequency Control Div.	25
Chief, Microwave & Quantum Electronics Br, Solid State & Frequency Control Div.	5
File Unit Nr. 1, Rm 3C-133, Hexagon	1
USAEIRDL Liaison Officer, USA Combat Developments Command, ATTN: CDC-LNEL, Fort Belvoir, Virginia	1
Air Force Systems Command Scientific/Technical Liaison Office, SELRA/LNA, USAEIRDL	1
Hq, Research and Technology Division ATTN: RTH Bolling AF Base Washington 25, D.C.	1

DISTRIBUTION (Cont)

	COPIES
Advisory Group on Electron Devices 346 Broadway New York 13, New York	2
Commanding Officer Frankford Arsenal Philadelphia 37, Pennsylvania Attn: ORDBAZFEL	1
Commanding General U.S. Army Rocket & Guided Missile Agency Redstone Arsenal Attn: Technical Library Huntsville, Alabama	1
Commanding Officer Watertown Arsenal Attn: CMRO Watertown, Massachusetts	1
V.A.J. Van Lint General Atomic (Div. of General Dynamic Corp.) P.O. Box 608 San Diego 12, California	1
President, Sandia Corporation Attn: Carter Broyles (5113) Sandia Base Albuquerque, New Mexico	1
Headquarters, AFSWC Attn: Capt. Glenn (SWRPA) Kirtland Air Force Base, New Mexico	1
Applied Physics Laboratory The Johns Hopkins University (For BuWeps RMLA-4) 8621 Georgia Avenue Silver Springs, Maryland Attn: Robert Freiberg	1
Hughes Aircraft Company Ground Systems Group Fullertown, California Attn: T. D. Hanscome, MS393/BL22	1

DISTRIBUTION (Cont)

COPIES

U. S. Army Air Defense School Ft. Bliss, Texas Attn: AKBAAS-CD-R	1
Chief of Research and Development OCS, Department of the Army (Atomics Division) Washington 25, D.C.	1
Deputy President U. S. Army Security Agency Board Arlington Hall Station Arlington 12, Virginia	1
Radiation Effects Information Center Battelle Memorial Institute 505 King Avenue Columbus 1, Ohio Attn: R. E. Bowman	1
Chief, Field Command Defense Atomic Support Agency Sandia Base, New Mexico Attn: PCWT	1
Defense Atomic Support Agency Washington 25, D.C. Attn: DASA RA-4 (Major R. I. LaRock)	1
D. A. Hicks Northrop Corporation - Radioplane Division 80000 Woodley Avenue Van Nuys, California	1
Commanding Officer Harry Diamond Laboratories Attn: Chief, Nuclear Vulnerability Br (230) Washington 25, D. C.	1

AD	Div.	UNCLASSIFIED	AD	Div.	UNCLASSIFIED
Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.			Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.		
1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26		
AD	Div.	UNCLASSIFIED	AD	Div.	UNCLASSIFIED
Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.			Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.		
1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26		
AD	Div.	UNCLASSIFIED	AD	Div.	UNCLASSIFIED
Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.			Amy Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannemacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-26) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of I_{CBO} changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_a.		
1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannemacher, Harry E.. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DASA Task 3A99-21-001-01 DASA Task OST-74-00-005-26		

AD	Div.	UNCLASSIFIED	AD	Div.	UNCLASSIFIED
Army Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannenmacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-98) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of ICBO changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_C.		1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98
		UNCLASSIFIED			UNCLASSIFIED
Army Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannenmacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-98) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of ICBO changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_C.		1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98
		UNCLASSIFIED			UNCLASSIFIED
Army Electronics Research and Development Laboratory, Fort Monmouth, New Jersey TRANSIENT AND STEADY-STATE NUCLEAR RADIATION EFFECTS ON GERMANIUM PNP ALLOY TRANSISTORS by Edwin T. Hunter and Harry E. Wannenmacher October 1962, 13 p. incl. illus., 7 refs. (USAEIRD L Technical Report 2310) (DA Task 3A99-21-001-01) (DASA Task OST-74-00-005-98) Unclassified report Procedures and results of nuclear irradiations made on germanium alloy transistors are reported. The facilities used were the Pennsylvania State University Reactor and the Sandia Pulsed Reactor. Transient results of ICBO changes indicate dependence on applied voltage, with a resultant effective shunt resistance of 200 K. Changes in gain and in minority carrier lifetime were used to compute damage constants from data taken at both facilities. A factor of three is observed between the constants. Leakage current measurements and gain measurements are reported as functions of I_C.		1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98			1. Nuclear Radiation Effects 2. Transistors I. Hunter, Edwin T. Wannenmacher, Harry E. II. Army Electronics Research and Development Laboratory, Fort Monmouth, N. J. III. DA Task 3A99-21-001-01 DASA Task OST-74-00-005-98
		UNCLASSIFIED			UNCLASSIFIED