

UNCLASSIFIED

AD 297 330

*Reproduced
by the*

**ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA**



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

63-2-5

GHIIIID

GENERAL DYNAMICS | CONVAIR

CATALOGED BY ASTIA
AS AD No. 297330

Report No. 8926-102

Material - Titanium - Ti 2.5Al 5Sn

Mechanical Properties of Hot Formed Sheet

P. W. Bergstedt, H. C. Turner, W. M. Sutherland

297 330

19 March 1959

ASTIA
MAR 6 1963
TISIA

Published and Distributed
under
Contract AF 33(600)-8926

Report No. 8926-102

Material - Titanium - Ti 2.5Al 5Sn

Mechanical Properties of Hot Formed Sheet

Abstract ↓ Laboratory test to determine the effect of hot forming upon the mechanical properties of Ti-2.5Al-5Sn alloy. Ti 2.5Al 5Sn sheet, 0.050 inch thick, was stretch wrapped at various rates and held for various times after wrapping against a stretch forming die which was heated to 1150°F. This treatment resulted in tensile losses of from zero to 3 per cent; ultimate strength losses of from zero to 6 per cent; elongation losses averaging about 2.5 per cent of the original elongation; and compression yield strength losses ranging upwards to 7 per cent. In general, the property losses were very slight.

References: Bergstedt, P. W., Turner, H. C., Sutherland, W. M.,
"Mechanical Properties of Hot Formed 5Al-2.5 Sn
Titanium Alloy*," General Dynamics/Convair Report
MP 59-103, San Diego, California, 19 March 1959.
(Reference attached).

*Alloy improperly designated, should be Ti 2.5Al 5Sn
titanium alloy.

i

INTRODUCTION:

Considerable difficulty has been experienced recently in Plant II in the cold-forming of 5Al-2.5 Sn titanium alloy. Some of this material has proved hyper-sensitive to stress-corrosion cracking; finger-prints upon formed parts have caused cracks to develop before or during the stress-relief operation.

In an attempt to circumvent this problem, the Engineering Productivity Group hot-stretch-wrapped several of the parts. This report describes the evaluation of six (6) of these parts by the Materials and Processes Laboratory.

OBJECT:

To determine the effect of hot-forming plus short-term soak upon the mechanical properties of Ti-5Al-2.5 Sn alloy.)

CONCLUSIONS:

Based upon control-specimen average properties, the following hot-forming effects were noted:

1. Ultimate tensile strength was raised. Strength increases ranged from 0 to 6%.
2. Tensile yield strength was reduced; maximum loss incurred was 3%.
3. Elongation losses were quite uniform; maximum loss was 2.5% (16.7% of the as-received elongation).
4. Compression yield strength was lowered. The maximum loss was 7%.

PROCEDURE:

All material, including flat control sheet, was 0.050" nominal Ti-5Al-2.5 Sn alloy from Heat No. 8419 of Titanium Metals Corporation of America.

The configuration of the hot-formed parts, the processing notes, and the sampling plan are included with the attached tabulation of results.

All specimens were tested in a Tinius-Olsen Universal Testing Machine. Both tension-yield and compression-yield were taken at 0.2% offset.

ANALYSIS
PREPARED BY Bergstedt
CHECKED BY Turner/Sutherland
REVISED BY


C O N V A I R
CORPORATION
SAN DIEGO

PAGE 2
REPORT NO NP 59-103
MODEL F-106
DATE 3-19-59

RESULTS AND DISCUSSION:

The results of the mechanical tests are listed on the attached form which was submitted by the Producibility Group. The changes in properties (reported under "Conclusions") suggest that this hot-forming procedure is relatively harmless when applied to the Ti-5Al-2.5 Sn alloy. The most significant reduction occurred in the compression yield strength; however, only one specimen was reduced as much as 7%. In general, the property losses were very slight.

NOTE: The data from which this report was prepared are recorded in Materials and Processes Laboratory Notebook No. 910.



Part No.	Wrap Time	Soak Time	Sample No.	UTS	TYS	%Elong.	CYS
K	As-received, control material		K-T-1	122,420	117,450	15.5	—
			K-T-2	123,200	117,200	15.0	—
			K-T-3	121,790	116,390	14.5	—
			K-C-1	—	—	—	124,270
			K-C-2	—	—	—	125,120
			K-C-3	—	—	—	123,460
			1	3 min.	2 min.	1-T-1	124,000
1-T-2	124,570	114,790				13.0	—
1-C-1	—	—				—	120,140
1-C-2	—	—				—	119,330
2	3 min.	2 min.	2-T-1	124,730	115,150	12.5	—
			2-T-2	123,070	114,280	13.0	—
			2-C-1	—	—	—	121,870
			2-C-2	—	—	—	120,950
3	3 min.	5 min.	3-T-1	122,240	113,890	13.5	—
			3-T-2	123,230	113,450	13.0	—
			3-C-1	—	—	—	119,290
			3-C-2	—	—	—	118,970
4	3 min.	5 min.	4-T-1	124,390	114,190	13.0	—
			4-T-2	125,470	113,800	12.5	—
			4-C-1	—	—	—	119,340
			4-C-2	—	—	—	119,460
5	3 min.	10 min.	5-T-1	124,310	114,550	13.0	—
			5-T-2	125,360	114,970	13.0	—
			5-C-1	—	—	—	115,590
			5-C-2	—	—	—	120,780
6	3 min.	10 min.	6-T-1	129,740	118,150	12.5	—
			6-T-2	123,700	113,490	12.5	—
			6-C-1	—	—	—	119,250
			6-C-2	—	—	—	119,860

NOTES: All material was SA1-2.5 Sn from TMCA Heat No. 8419.
 All parts stretched to 10% elongation.
 All parts formed at 1100°F.
 TYS & CYS taken at 0.2% offset.