

UNCLASSIFIED

AD NUMBER	
AD379338	
CLASSIFICATION CHANGES	
TO:	unclassified
FROM:	confidential
LIMITATION CHANGES	
TO:	Approved for public release, distribution unlimited
FROM:	Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; JAN 1967. Other requests shall be referred to U.S. Army Missile Command, Redstone Arsenal, AL 35809.
AUTHORITY	
USAMC ltr, 14 Mar 1967; USAMC ltr, 23 Aug 1971	

THIS PAGE IS UNCLASSIFIED

UNCLASSIFIED

AD

REPORT NO. RS-TR-67-1

STRESS-CORROSION CRACKING IN THE HAWK MOTOR CASE

by

William T. McClane

JANUARY 1967

DISTRIBUTION LIMITED

See Notices Page

CLASSIFICATION UNCLASSIFIED
CHANGED TO
AUTH. CITED IN ASTIA R/B # 67-12
DATED 5/15/67
By *Bohmer* 4/20/67
(Signature & Date)

U.S. ARMY MISSILE COMMAND

Redstone Arsenal, Alabama

UNCLASSIFIED
EXEMPTED FROM AUTOMATIC
DECLASSIFICATION
EXEMPTED FROM GDS, E.O. 11652

DDC
RECEIVED
MAR 21 1967

BDC
RECEIVED
MAR 9 1967

UNCLASSIFIED

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed. Do not return it to the originator.

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position.

DISTRIBUTION LIMITATION

This document may be further distributed by any holder only with specific prior approval of HAWK Project Manager's Office, AMCPM-HAE, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809.

UNCLASSIFIED

DO NOT FILL IN

18 January 1967

REPORT NO. RS-TR-67-1

STRESS-CORROSION CRACKING

IN THE HAWK MOTOR CASE

This document contains information affecting the National Defense of the United States within the meaning of the Espionage Laws, Title 18, U. S. C., Section 793 and 794. Its transmission by the revelation of its contents in any manner to an unauthorized person is prohibited by law.

William T. McClane

DA Project No. 11B10011

AMC Management Structure Code No. 4210.18.0450.1.12

DISTRIBUTION LIMITED

See Notices Page

Materials Engineering and Development Branch
Structures and Mechanics Laboratory
Research and Development Directorate
U.S. Army Missile Command
Redstone Arsenal, Alabama 35809

UNCLASSIFIED

UNCLASSIFIED

ABSTRACT

Samples from the girth weld in the forward motor case of the HAWK missile were evaluated for susceptibility to stress-corrosion. Eight motor cases were fabricated from AISI-4132 steel using two different resistance weld cycles and four heat treatments. Welding in the heat treated condition gave the greatest resistance to stress-corrosion; however, the strength of the case was lowered in the heat affected zone. Samples that were normalized prior to quench and tempering had the poorest resistance to stress-corrosion. Welding, heat treating in salt, and sealing the crevice between the dome and the shell with a potting compound is the most effective method of preventing stress-corrosion in the HAWK motor case.

UNCLASSIFIED

UNCLASSIFIED

CONTENTS

	Page
Section I. INTRODUCTION	1
Section II. DESCRIPTION OF TEST SPECIMENS	2
Section III. TEST PROCEDURE	6
Section IV. RESULTS	7
Section V. DISCUSSION	11
Section VI. CONCLUSIONS	14

ILLUSTRATIONS

Table		Page
I	Results of Stressed Specimens in Salt Spray Cabinet	7
Figure		
1	Dome Welded to Shell by Resistance Seam Weld	4
2	Stress-Corrosion Sample	5
3	Section of Weld Before Testing	8
4	Failed Specimen	9
5	Microstructure of a Failed Sample	10
6	Dendritic Weld Area	12
7	Effect of Homogenizing Treatment on Microstructure	13

UNCLASSIFIED

UNCLASSIFIED

Section I. INTRODUCTION

During a routine inspection of some HAWK missiles that had been in the field, a small crack was observed in one of the motor cases. The crack was in the girth weld that joins the forward closure dome to the motor case shell. Further inspection of other missiles revealed similar cracks in the same weld area. An ultrasonic test inspection indicated that a large number of motors were cracked in various degrees. A program was then initiated to develop a field fix for those missiles already produced.

A laboratory evaluation of several of the cracked cases pointed to stress-corrosion as the probable cause. The approach that was taken to prevent stress-corrosion on those cases that were not cracked was to seal the crevice between the shell and the dome with a potting compound. This involved selecting a suitable compound and devising a process for obtaining a satisfactory bond.

The compound that was finally chosen was Dow Corning 92-018 Aerospace Sealant. A sequence of cleaning operations was developed that produced a satisfactory bond and was adaptable for use in the field. Laboratory stress-corrosion tests substantiated both the material and the process as preventing stress-corrosion from starting and arresting it in those cases where it had already begun.

Teams were trained in the use of ultrasonic inspection and the application of the potting compound. These teams inspected all of the missiles deployed throughout the world. Those cases that were cracked were replaced with new motor cases. Those cases that were not cracked were cleaned and potted. A requirement that all new cases be potted was added to the motor case drawings.

As an additional protection against the recurrence of stress-corrosion in future motor cases, another program was established and will be described in this report. It involved an evaluation of various welding and heat treat cycles regarding their resistance to stress-corrosion.

UNCLASSIFIED

Section II. DESCRIPTION OF TEST SPECIMENS

The motor case is fabricated from a low alloy high strength steel, AISI-4132, that is resistance seam-welded. Two different cycles have been certified and used in production. However, all of the welds were made with the same welding machine.

There were also two different methods of heat treating--one in salt and one in air. The initial cases were heat treated in air in accordance with the following schedule:

- a. Heat to 1600°F for 1 hour.
- b. Quench in oil at 130°F.
- c. Temper at 825°F for 3 hours.

The present practice is to heat treat in salt in the following manner:

- a. Heat to 1625°F for one-half hour in neutral salt.
- b. Quench in salt at 400°F. Hold for 15 minutes.
- c. Air cool.
- d. Temper in salt at 800°F for 1 hour.

Eight welded cases were made for this study. They were designated:

- A-1 Welded per cycle "A." Heat treated in salt.
- A-2 Welded per cycle "A." Heat treated in air.
- A-3 Welded per cycle "A." Normalized and then heat treated in salt.
- A-4 Heat treated in salt then welded per cycle "A."
- B-1 Welded per cycle "B." Heat treated in salt.
- B-2 Welded per cycle "B." Heat treated in air.
- B-3 Welded per cycle "B." Normalized and then heat treated in salt.
- B-4 Heat treated in salt then welded per cycle "B."

CONFIDENTIAL

All of the above cases were welded and heat treated at the manufacturer's plant, with two exceptions--A-3 and B-3, which were normalized and heat treated in the laboratory.

Upon receipt, the welded and heat treated sections were cut into specimens one-inch wide at the weld. A hole was then drilled in the end of the specimen to provide a means for applying a tensile stress on the weld. A welded dome is shown in Figure 1. A loaded stress-corrosion specimen is shown in Figure 2.



Figure 1. Dome Welded to Shell by Resistance Seam Weld.




Figure 2. Stress-Corrosion Sample.

Section III. TEST PROCEDURE

One stress-corrosion specimen from each of the eight groups was torn apart in tension to determine the yield strength and the tear strength at the weld. Specimens were then loaded to 75 percent of the yield and 75 percent of the ultimate and placed in the salt spray cabinet. They remained in the cabinet exposed to a 5 percent NaCl fog until they failed or had withstood at least 360 hours exposure.

Section IV. RESULTS

The results of the stressed specimens in the salt spray cabinet are shown in Table I.

Table I

Case	Hours at 75% Elastic Stress	Hours at 75% Ultimate Stress
A-1	99, 99, 360+, 360+	327, 384+, 384+, 384+, 384+
A-2	99, 99, 99, 99, 99	15, 15, 135, 40, 15
A-3	20, 20, 53	20, 53, 53, 20
A-4	360+, 360+, 360+, 360+, 360+	384+, 384+, 384+, 384+
B-1	384+, 384+, 384+	384+, 112, 384+, 216
B-2	92, 384+, 15	384+, 15, 384+, 384+
B-3	92, 72, 40	15, 72, 15, 21
B-4	360+, 360+, 360+, 360+, 360+	40, 92, 384+, 72, 40

A cross-section of a typical weld before testing is shown in Figure 3. A similar section of a failed specimen is shown in Figure 4. Figure 5 shows the microstructure of a failed sample.




Figure 3. Section of Weld Before Testing.




Figure 4. Failed Specimen.




Figure 5. Microstructure of a Failed Sample.
500X Magnification.

Section V. DISCUSSION

A dendritic microstructure was typical of all the welded and heat treated specimens, as shown in Figure 6. There was no noticeable difference in any of them. The attendant segregation in such a microstructure suggests a mechanism whereby the stress-corrosion can proceed in accordance with one of the more widely held theories of stress-corrosion.

The composition gradient would be responsible for establishing local galvanic cells that electrochemically corrode the metal. Although stress is a necessary requisite, its exact role in the crack propagation has not yet been established. If the dendritic microstructure promotes stress-corrosion, then a normalizing heat treatment that would homogenize the structure should eliminate or greatly reduce its susceptibility.

A normalizing treatment consisting of heating to 1650°F, holding for one hour, and air cooling was performed on specimens A-3 and B-3. Following the normalizing treatment they were quenched and tempered in neutral salt per the standard heat treat cycle. The effect of this homogenizing treatment on the microstructure is shown in Figure 7. However, as Table I shows, the normalized specimens failed in considerably shorter times than any other group of samples.

The specimens that were heat treated and then welded, A-4 and B-4, had outstanding resistance to stress-corrosion. The only failures were those that were welded in accordance with cycle "B" and loaded beyond the yield point. Such a procedure, though, lowers the strength of the case because of the heat-affected zone on each side of the weld.

The susceptibility to stress-corrosion is lowered by the salt heat treating procedure as compared to specimens heat treated in air. This is contrary to the results of service life in the field. There have been no reports of motor case cracking in any of the cases that were heat treated in air, in spite of the fact that they were older cases and had been in service longer. This is undoubtedly the result of potting the crevice between the dome and the shell on all of the cases that were heat treated in air. This potting requirement was removed shortly after the salt bath heat treating process was initiated.

UNCLASSIFIED




Figure 6. Dendritic Weld Area.
50X Magnification.




Figure 7. Effect of Homogenizing Treatment on Microstructure.
50X Magnification.

UNCLASSIFIED

UNCLASSIFIED

Section VI. CONCLUSIONS

A normalizing treatment prior to quenching and tempering has a detrimental effect on resistance to stress-corrosion cracking of AISI-4132.

The type of weld cycle had very little effect on the susceptibility to stress-corrosion.

Welding followed by heat treating in salt and sealing the crevice between the dome and the shell with a potting compound is the most effective method of preventing stress-corrosion in the HAWK motor case.

UNCLASSIFIED

UNCLASSIFIED

Security Classification

UNCLASSIFIED

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Materials Engineering & Development Branch Structures & Mechanics Laboratory U.S. Army Missile Command, Redstone Arsenal, Ala.		2a. REPORT SECURITY CLASSIFICATION Unclassified 2b. GROUP
3. REPORT TITLE Stress-Corrosion Cracking in the HAWK Motor Case		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)		
5. AUTHOR(S) (Last name, first name, initial) McClane, William T.		
6. REPORT DATE 18 January 1967	7a. TOTAL NO. OF PAGES 18	7b. NO. OF REFS
8a. CONTRACT OR GRANT NO. a. PROJECT NO. 11B10011 c. AMC Management Structure Code No. 4210.18.0450.1.12 d.	9a. ORIGINATOR'S REPORT NUMBER(S) RS-TR-67-1 9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. AVAILABILITY/LIMITATION NOTICES This document may be further distributed by any holder only with specific prior approval of HAWK Project Manager's Office, AMCPM-HAE, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY HAWK Project Manager's Office, AMCPM-HAE U.S. Army Missile Command Redstone Arsenal, Alabama 35809	
13. ABSTRACT Samples from the girth weld in the forward motor case of the HAWK missile were evaluated for susceptibility to stress-corrosion. Eight motor cases were fabricated from AISI-4132 steel using two different resistance weld cycles and four heat treatments. Welding in the heat treated condition gave the greatest resistance to stress-corrosion; however, the strength of the case was lowered in the heat affected zone. Samples that were normalized prior to quench and tempering had the poorest resistance to stress-corrosion. Welding, heat treating in salt, and sealing the crevice between the dome and the shell with a potting compound is the most effective method of preventing stress-corrosion in the HAWK motor case.		

DD FORM 1473

UNCLASSIFIED

Security Classification

13

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED
Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Stress-Corrosion Normalizing Motor Cases Low Alloy Steels						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.

UNCLASSIFIED
Security Classification

UNCLASSIFIED