

UNCLASSIFIED

AD 400 245

*Reproduced
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY
ARLINGTON HALL STATION
ARLINGTON 12, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOGED BY ASTIA

AS AD NO. 400245

400 245

Rock Island Arsenal Laboratory



TECHNICAL REPORT

IMPROVING THE RUST PREVENTIVE PROPERTIES
OF MULTIPURPOSE GREASES

By

R. L. Young

APR 5 1963

A

Dept. of the Army Project No. 1-A-0-24401-A-107AMC Code No. 5026.11.801RIA Report No. 63-313

Copy No. _____

IEL 1-8-107-2Date 31 January 1963

DISTRIBUTED BY THE
OFFICE OF TECHNICAL SERVICES
U. S. DEPARTMENT OF COMMERCE
WASHINGTON 25, D. C.

THIS REPORT MAY BE DESTROYED WHEN
NO LONGER REQUIRED FOR REFERENCE

The findings in this report are not to be construed
as an official Department of the Army position.

"Copies Available at Office of Technical Services \$.50".

Report No. 63-313

Copy No. _____

IMPROVING THE RUST PREVENTIVE PROPERTIES
OF MULTIPURPOSE GREASES

By

R. L. Young
R. L. Young

Approved by:

A. C. Hanson
A. C. HANSON
Laboratory Director

31 January 1963

DA Project No. 1-A-0-24401-A-107

AMC Code No. 5026.11.801

Rock Island Arsenal
Rock Island, Illinois

ASTIA Availability Notice:

Qualified requesters may obtain
copies of this report from ASTIA.

ABSTRACT

Eighteen compounds or mixtures were selected for testing as rust preventive additives for greases. They were intimately mixed into a selected base grease in predetermined percentages. A screening test was developed and those additives showing up well on it were further tested by Method 4012 of Federal Standard No. 791. The greases containing the best performing additives were checked to determine if any of the requirements of MIL-G-10924B, Grease, Automotive and Artillery, had been seriously altered. The minimum effective percentages of the additive displaying the best protection was determined. The most effective additives were incorporated in minimum concentration in commercial greases which had failed to meet the rust preventive test to see if improvements could be made.

**IMPROVING THE RUST PREVENTIVE PROPERTIES
OF MULTIPURPOSE GREASES**

CONTENTS

	<u>Page No.</u>
Object	1
Introduction	1
Procedure	2
Results and Discussion	5
Literature References	15
Distribution	16

IMPROVING THE RUST PREVENTIVE PROPERTIES OF MULTIPURPOSE GREASES

OBJECT

To improve the rust and corrosion preventive abilities of multipurpose greases by the use of additives.

INTRODUCTION

While the primary function of a grease is to lubricate and reduce friction, an equally important function is to protect the bearing surface from rusting and other forms of corrosion. Practically all current military, Federal and Industrial grease specifications contain some requirement concerning rust and corrosion prevention. Specification MIL-G-10924⁽¹⁾ Grease, Automotive and Artillery, is no exception and has always had some form of a corrosion and rust preventive test in all its revisions. MIL-G-10924A, the revision in use since 1956, contained two such tests. They were a copper corrosion test, Federal Standard No. 5309⁽²⁾, and a synthetic sea water test based upon the Federal Standard salt spray test, No. 4001. Greases secured under the specification have successfully met these test requirements for a number of years.

Recently the Coordinating Research Council completed work on a rust preventive test method involving a Timken roller bearing cone and cup. Federal Standard Test Method No. 4012⁽²⁾ was based on the CRC technique which was known as L-41. Since it was felt that this test more nearly approached actual use conditions, it was incorporated into the revision of the Specification MIL-G-10924B⁽¹⁾.

Suppliers of the MIL-G-10924 greases were somewhat concerned since the new test was admittedly more severe than those in use. Consequently this Laboratory was deluged with requests to suggest some additives which would enable a grease to meet the new requirements. Fortunately, enough preliminary work had been done so that two or three compounds could be suggested. It was deemed advisable to conduct a more exhaustive investigation to enlarge upon the list of possible additives and to determine what effect the successful ones would have upon other properties of the grease.

The various high molecular weight organic sulfonates and their metallic salts, lead soaps, amines, amine salts, naphthenates and non-ionic surfactants have been long regarded as rust preventives for oils and greases^(3,4).

Baker, et.al.(5) have shown that of all the sulfonates, basic barium dinonyl naphthalene sulfonate in concentrations of 0.05% in petroleum oils and 0.5% in synthetic fluids gave the best corrosion inhibiting and acid deactivating properties.

Pines and Spivack(6) found that nonylphenoxy acetic acid protected ferrous metal surfaces from corrosion by adsorbing on the surfaces to form a close packed protective film. It is convenient to use for several reasons: (a) It is readily soluble in petroleum and synthetic fluids over a wide temperature range, (b) it is insoluble in water thus minimizing the tendency for the protective film to be desorbed by leaching into the aqueous phase, (c) its rust preventive properties persist in the presence of other additives and it appears to be compatible with most of them, (d) since it is a liquid, it can readily be adapted to a variety of blending technique, (e) it is organic in nature and consequently leaves little or no ash on combustion.

Preston(7) claims that compounds having the formula $R \cdot O \cdot CH_2 \cdot COOH$ where R is alkyl or alkaryl, and the alkyl groups preferably contain from 7 to 20 carbon atoms, are effective inhibitors of rusting when used in petroleum fluids. He found para nonyl phenoxy acetic acid to be the most effective of the compounds corresponding to the above formula. Concentrations of 0.02% enabled isooctane to pass the corrosion tests of MIL-I-25017A(8). It was assumed that greater concentrations would be necessary for oils or greases.

The Armour Research Foundation working under contract with Wright Air Development Center screened several hundred compounds for their corrosion or rust preventive ability(9,10,11). They also synthesized a number of compounds having potential corrosion inhibiting ability. Their work was with oils only and no greases were tested. The compounds evaluated in this investigation were chosen from those listed in these reports and from technical bulletins of various companies or from stocks available in this laboratory which were judged to be potentially successful.

PROCEDURE

One-hundred pounds of a multipurpose grease conforming to Specification MIL-G-10924A(1) was obtained to serve as the base grease. Eighteen likely additives were selected from those mentioned in the literature or which were considered as likely to be effective. They are listed in Table I. The additive was mixed into the base grease by means of a spatula. The percentages used varied somewhat and are listed in the pertinent tables. For preliminary evaluation a screening

TABLE I

ADDITIVES USED IN INVESTIGATION

1. Basic Barium Dinonyl Naphthalene Sulfonate
2. Sorbitan Monoleate
3. Para-Nonylphenoxyacetic Acid 90%
4. Stearoyl Sarcosine and Heptadecenyl Imidazoline
5. Undecyl Imidazoline and Oleic Acid
6. Morpholine
7. Lauroyl Iminodiacetic Acid
8. Dioctyldiphenylamine
9. Organic Sulfonates (commercial product)
10. Cadmium Diamyldithiocarbamate
11. Lead Dinonylnaphthalene Sulfonate
12. Lead Diamyldithiocarbamate
13. Commercial Lead-Sulfur E.P. Additive
14. Barium Dinonyl Naphthalene Sulfonate
15. Ethylene Diamine Dinonyl Naphthalene Sulfonate
16. Ammonium Dinonyl Naphthalene Sulfonate
17. Fatty Amido Phosphate
18. Anhydrous Lanolin

test was employed. This test took considerably less time and was more economical of materials than the specification test. It was conducted as follows:

Discs of #52100 bearing steel 1-3/8" in diameter, 5/16" thick and weighing 56.45 ± 0.05 grams were prepared. One surface of each disc was ground and finished with a diamond polishing wheel to obtain a finish equivalent to that of a bearing race. This surface was cleaned with xylene and air dried. As soon as the surface was dry, the additive-containing grease was spread over the surface with a stainless steel spatula. The excess grease was scraped off with the spatula and the disk placed grease side down upon a clean Kleenex tissue paper laid on a flat surface. The disc was then slid from one end of the tissue to the other with no downward force upon it except its own weight. The disc was then picked up and rotated approximately 90° horizontally, placed on a clean surface, and again pushed the full length of the tissue. The previously numbered discs were placed grease side up in a desiccator containing, in place of the desiccant, deionized distilled water. Upon each disc was placed six drops of deionized distilled water in a circular arrangement. The cover was placed on the desiccator which was then placed in a dark cabinet. The discs were checked at fifteen minute intervals for the first hour and then at hourly intervals thereafter. The time for appearance of rust was noted and when a very slight rust was noticeable on the last disc the test was discontinued. The discs were then given a numerical rating from 1 to 6 according to the severity of rusting.

The preliminary screening tests resulted in the elimination of additives No. 2, 4, 5, 6, 7, 8, 9, 10, 12, 13 and 14 from further consideration. Those additives which were most effective in the screening test were then added to the base grease and tested according to Federal Standard Test Method No. 4012. The base grease was also tested. Different concentrations of the additives were used in an attempt to determine the minimum concentrations which would provide sufficient protection. The additive-containing greases were also checked against the requirements of MIL-G-10924B to see if other properties of the grease had been altered.

Several of the most successful additions were also added to samples of commercial greases, including molybdenum disulfide containing greases, to further test their rust preventing abilities.

RESULTS AND DISCUSSION

One of the problems confronting the grease maker is the effect of any additive upon the over-all character of the grease. Some additives will affect other properties of a grease in addition to the one they were expected to enhance. Table II contains the results of several pertinent tests of Specification MIL-G-10924B upon the base grease and the base grease with two of the successful additives incorporated in it.

TABLE II
EFFECTS OF ADDITIVES UPON BASE GREASE

Property	Base Grease	+ Additive #1(1)	+ Additive #3(2)
Worked Penetration	266	286	271
Work Stability	+15	+28	+27
Water Stability	+38	+44	+12
Water Washout, %	4.57	3.9	5.2
Apparent Viscosity, Poises			
@ 25 sec. ⁻¹	15,600	17,300	20,200
@ 100 sec. ⁻¹	9,700	9,900	10,000
Copper Corrosion	Pass	Pass	Some darkening of grease

(1) Additive #1: 3% Basic Barium Dinonyl Naphthalene Sulfonate.

(2) Additive #3: 1% Para Nonyl Phenoxyacetic Acid.

Examination of Table II discloses that both additives did affect other properties of the grease. Additive #1, basic barium dinonylnaphthalene sulfonate, had an effect upon the worked penetration, work stability and apparent viscosity. Additive #3, para-nonylphenoxyacetic acid, affected the work and water stability and the apparent viscosity.


The results of the screening test made on a few of the compounds tested are shown in Figures 1 and 2 and in Table III. The ratings are based on the number of rust spots at the end of 72 hours or if less than 72 hours, were required the number of rust spots at the time all discs showed at least one rust spot.

Figure 1 shows the discs in the desiccator at the conclusion of 72 hours. In Figure 2 the discs are lined up in order for better comparison. Table III lists the disc No., the number of the chosen additive taken from Table I, the additive percent, the number of rust spots at hourly intervals and the results of Federal Standard No. 4012 tests on the same grease-additive mixture.


Examination of the data in Table III reveals that the results on the screening test are evident after a 4-6 hour period and are not significantly changed afterwards. Also, the screening test results are not very well correlated with the results of the Federal Standard No. 4012 test, as illustrated with Additives #1, 11 and 16. Since the 4012 technique has been standardized, and found to give reproducible results, it is considered to be the final answer in this investigation. The 4012 tests shown in Table III were made on two instead of three bearings for economy reasons. They are also shown pictorially in Figures 3 and 4.

To further test the effectiveness of these additives, two of them were tested in commercial greases as follows. The selected two additives were incorporated in a lithium soap W.P. grease designed for automotive use. Figure 5 shows the results of the Federal Standard 4012 test on the base grease and on the same grease containing the indicated amount of each additive. The additive containing greases successfully resisted rusting.

Figure 6 shows the results when 1% of nonylphenoxyacetic acid was added to a commercial molybdenum disulfide grease. The additive successfully controlled the rusting evident in the base grease.



SCREENING TEST FOR ADDITIVES IN GREASE




SCREENING TEST FOR ADDITIVES IN GREASE


TABLE III

SCREENING TESTS ON ANTIRUST ADDITIVES


Disc No.	Additive No. From Table I	Additive Percent	Rust Spots on Disc at Time Indicated						Results Fed.Std. No. 4012 Test	
			1 hr.	2 hr.	3 hr.	4 hr.	5 hr.	6 hr.		72 hr.
1	3	1	0	0	0	0	0	0+	1	1,1
2	11	1	0	3	4	4	4	4	4	1,1
3	16	1	0	0	4	6	6	6	6	1,1
4	15	1	0	0	2	3	3	3	3	1,1
5	1	1	0	4	4	5	5	5	5	1,3
6	17	2	0	2	2	3	3	3	3	1,1
7	18	2	0	3	3	3	3	4-5	5	3,3
8	Base Grease		0	2	5	5	5	5	5	3,3




FEDERAL STANDARD 4012 TEST METHOD ON VARIOUS
ADDITIVES IN A MIL-G-10924A BASE GREASE



FEDERAL STANDARD 4012 TEST METHOD ON VARIOUS
ADDITIVES IN A MIL-G-10924A BASE GREASE



1 1/2% NONYL PHENOXY ACETIC ACID IN E.P. LITHIUM GREASE




3% BASIC BARIUM DINONYL NAPHTHALENE SULFONATE IN E.P. LITHIUM GREASE



E.P. LITHIUM GREASE

FEDERAL STANDARD 4012 TEST; RUST PREVENTIVE PROPERTIES OF GREASES



RESULTS OF FED. STD. 4012 ON MoS₂ GREASE.

RESULTS ON SAME GREASE + 1% NPA.

SUMMARY

1. The rust preventive properties of multipurpose greases can be improved by the addition of relatively small amounts of several different compounds.
2. These compounds are also effective in other types of commercial greases.
3. Other important properties of the greases were also affected by the additives and care must be taken to allow for this in the final formulations.

LITERATURE REFERENCES

1. Specification MIL-G-10924, Grease, Automotive and Artillery. "A" Revision, 10 April 1956. "B" Revision, 14 July 1961.
2. Federal Test Method Standard No. 791A, 31 Dec. 1961.
3. Kaufman, Gus, Lubricating Eng., 3, 55-61 (1947).
4. McDonald, R.T., and Dreker, J.L., Inst. Spokesman 17, No. 1 (1953).
5. Baker, H.R., Singleterry, C.R., and Soloman, E.M., "Neutral and Basic Sulfonates", Ind. and Eng. Chem., Vol. 46, p. 1035, May 1954.
6. Pines, R.M., and Spivack, J.D., "Rust Preventive Properties of Nonylphenoxycetic Acid in Some Petroleum Products". Geigy Research Division Bulletin Technica 1, June 1960.
7. British Patent No. 812,938, 6 May 1959.
8. Specification MIL-I-25017A, Inhibitor, Corrosion, Fuel Soluble, 23 September 1959.
9. "Corrosion Preventive Additives", Project 90-806C, Final Report, March 1951 to March 1952.
10. "Corrosion Preventive Additives", Project C-012-2, Final Report, March 1952 to March 1953.
11. "Corrosion Preventive Additives", WADC Technical Report No. 53-12, Feb. 1953.

DISTRIBUTION

	<u>No. of Copies</u>
Commanding General U.S. Army Materiel Command ATTN: AMCRD-RS-CM Room 2502, Bldg. T-7 Washington 25, D. C.	2
Commanding General U.S. Army Weapons Command ATTN: AMSWE-RD AMSWE-SM AMSWE-PP AMXOA-EA	1 1 1 1
Rock Island Arsenal Rock Island, Illinois	
Commanding General U.S. Army Tank & Automotive Center ATTN: SMOTA-REM.2 SMOTA-REM.3	1 1
Detroit Arsenal Center Line, Michigan	
Commanding Officer U.S. Army Research Office (Durham) Box CM, Duke Station Durham, North Carolina	1
Office of the Assistant Secretary of Defense ATTN: Technical Advisory Panel on Fuels and Lubricants Washington 25, D. C.	1
Commanding Officer ATTN: U.S. Army Coating & Chemical Laboratory Technical Library	1 2
Aberdeen Proving Ground, Maryland	
Commanding General U.S. Army Missile Command ATTN: E. J. Wheelahan, AMSMI-RSM R. Fink, AMSMI-RKX R. E. Ely, AMSMI-RRS W. H. Thomas, AMSMI	1 1 1 1
Redstone Arsenal, Alabama	

DISTRIBUTION

	<u>No. of Copies</u>
Commanding Officer Detroit Arsenal ATTN: SMOTA-B Center Line, Michigan	1
Commanding Officer Frankford Arsenal ATTN: SMUFA-1300 SMUFA-LS Library-0270 Philadelphia 37, Pa.	1 1 1
Commanding Officer Picatinny Arsenal ATTN: Plastics & Packaging Laboratory Dover, New Jersey	1
Commanding General U.S. Army Munitions Command Dover, New Jersey	1
Director PLASTECH Picatinny Arsenal Dover, New Jersey	1
Commanding Officer Springfield Armory ATTN: Mr. J. Szanto Springfield 1, Mass.	1
Commanding Officer Watertown Arsenal ATTN: Technical Information Section Watertown 72, Mass.	1
Commanding Officer Watervliet Arsenal Watervliet, New York	1
Commanding Officer Anniston Ordnance Depot ATTN: Chemical Laboratory Anniston, Alabama	1

DISTRIBUTION

No. of Copies

Commander
Wright Air Development Division
ATTN: WWRCO
Wright-Patterson Air Force Base, Ohio 1

Director
Aeronautical Materials Laboratory
Naval Air Material Center
Philadelphia 12, Pa. 1

Commanding Officer
U.S. Naval Air Station
Overhaul and Repair Department
San Diego, California 1

Chief
Bureau of Supplies and Accounts
Department of the Navy
Code H62, Arlington Annex
Washington 25, D. C. 1

Chief
Dept. of the Navy
Bureau of Ordnance
Code Maf-1-g
Washington 25, D. C. 1

Commander
Armed Services Technical Information Agency
Arlington Hall Station
ATTN: TIPDR
Arlington 12, Virginia 20

Commanding Officer
Harry Diamond Laboratory
ATTN: Technical Library
Washington 25, D. C. 1

National Aeronautics and Space Administration
1520 H Street Northwest
Washington 25, D. C. 1

Prevention of Deterioration Center
National Academy of Science
National Research Council
2101 Constitution Avenue
Washington 25, D. C. 1

DISTRIBUTION

No. of Copies

Commanding General
U.S. Army Weapons Command
ATTN: AMSWE-RD 3
Rock Island Arsenal
Rock Island, Illinois
for
release to

Commander
British Army Staff
ATTN: Reports Officer
3100 Massachusetts Avenue, N. W.
Washington 8, D. C.

Commanding General
U.S. Army Weapons Command
ATTN: AMSWE-RD 3
Rock Island Arsenal
Rock Island, Illinois
for
release to

Canadian Army Staff, Washington
ATTN: GSO-1, A & R Section
2450 Massachusetts Avenue, N. W.
Washington 8, D. C.

Commanding General
ATTN: ORDBS-OM- Electro-Mechanical Labs 1
ORDBS-OM- Systems Test Division 1
ORDBS-OM 1
White Sands Missile Range, New Mexico

Office of Technical Services Stock
1200 South Eads Street
Arlington, Virginia 200

AD Rock Island Arsenal Laboratory, Rock Island, Illinois IMPROVING THE RUST PREVENTIVE PROPERTIES OF MULTIPURPOSE GREASES, by R. L. Young RIA Lab. Rep. 63-313, 31 Jan 63, 19 p. incl. illus. tables, (DA Project No. 1-A-0-24401- A-107, AMC Code No. 5026.11.801) Unclassified report.	UNCLASSIFIED 1. Greases 2. Rust Prevention 3. Lubricant- Additives 4. Lubrication
Eighteen compounds or mixtures were selected for testing as rust preventive additives for greases. They were intimately mixed into a selected base grease in predetermined percentages. A screening test was developed and those additives showing up well on it were further tested by Method 4012 of Federal Standard No. 791. The greases containing the best performing additives were checked to determine if any of the requirements of MIL-G-10924B, Grease, Automotive and Artillery, had been seriously altered. The minimum effective percentages of the additive (Cont.) over	DISTRIBUTION: Copies obtainable from ASTIA
AD Rock Island Arsenal Laboratory, Rock Island, Illinois IMPROVING THE RUST PREVENTIVE PROPERTIES OF MULTIPURPOSE GREASES, by R. L. Young RIA Lab. Rep. 63-313, 31 Jan 63, 19 p. incl. illus. tables, (DA Project No. 1-A-0-24401- A-107, AMC Code No. 5026.11.801) Unclassified report.	UNCLASSIFIED 1. Greases 2. Rust Prevention 3. Lubricant- Additives 4. Lubrication
Eighteen compounds or mixtures were selected for testing as rust preventive additives for greases. They were intimately mixed into a selected base grease in predetermined percentages. A screening test was developed and those additives showing up well on it were further tested by Method 4012 of Federal Standard No. 791. The greases containing the best performing additives were checked to determine if any of the requirements of MIL-G-10924B, Grease, Automotive and Artillery, had been seriously altered. The minimum effective percentages of the additive (Cont.) over	DISTRIBUTION: Copies obtainable from ASTIA
AD Rock Island Arsenal Laboratory, Rock Island, Illinois IMPROVING THE RUST PREVENTIVE PROPERTIES OF MULTIPURPOSE GREASES, by R. L. Young RIA Lab. Rep. 63-313, 31 Jan 63, 19 p. incl. illus. tables, (DA Project No. 1-A-0-24401- A-107, AMC Code No. 5026.11.801) Unclassified report.	UNCLASSIFIED 1. Greases 2. Rust Prevention 3. Lubricant- Additives 4. Lubrication
Eighteen compounds or mixtures were selected for testing as rust preventive additives for greases. They were intimately mixed into a selected base grease in predetermined percentages. A screening test was developed and those additives showing up well on it were further tested by Method 4012 of Federal Standard No. 791. The greases containing the best performing additives were checked to determine if any of the requirements of MIL-G-10924B, Grease, Automotive and Artillery, had been seriously altered. The minimum effective percentages of the additive (Cont.) over	DISTRIBUTION: Copies obtainable from ASTIA

displaying the best protection was determined. The most effective additives were incorporated in minimum concentration in commercial greases which had failed to meet the rust preventive test to see if improvements could be made.

displaying the best protection was determined. The most effective additives were incorporated in minimum concentration in commercial greases which had failed to meet the rust preventive test to see if improvements could be made.

(P)

displaying the best protection was determined. The most effective additives were incorporated in minimum concentration in commercial greases which had failed to meet the rust preventive test to see if improvements could be made.

displaying the best protection was determined. The most effective additives were incorporated in minimum concentration in commercial greases which had failed to meet the rust preventive test to see if improvements could be made.