

UNCLASSIFIED

---

---

AD 400 503

*Reproduced  
by the*

ARMED SERVICES TECHNICAL INFORMATION AGENCY  
ARLINGTON HALL STATION  
ARLINGTON 12, VIRGINIA



---

---

UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

63-3-1

FTD-TT- 62-1761

CATALOGED BY ASTIA  
AS AD NO. 400 503

# TRANSLATION

STRUCTURAL DIAGRAM OF VANADIUM-CERIUM SYSTEM

By

Ye. M. Savitskiy, V. V. Baron  
and Yu. V. Yefimov

## FOREIGN TECHNOLOGY DIVISION

AIR FORCE SYSTEMS COMMAND

WRIGHT-PATTERSON AIR FORCE BASE

OHIO



ASTIA  
RECEIVED  
APR 10 1963  
ASTIA

## UNEDITED ROUGH DRAFT TRANSLATION

### STRUCTURAL DIAGRAM OF VANADIUM-CERIUM SYSTEM

BY: Ye. M. Savitskiy, V. V. Baron and  
Yu. V. Yefimov

English Pages: 4

SOURCE: Russian Periodical, Zhurnal Neorganicheskoy  
Khimii, Vol. 7, Nr. 3, 1962, pp. 701-703

S/78-62-7-3

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION SERVICES BRANCH  
FOREIGN TECHNOLOGY DIVISION  
WP-AFB, OHIO.

## Structural Diagram of Vanadium-Cerium System

by

Ye.M.Savitskiy; V.V.Baron; Yu.V.Yefimov

The structural diagram of the Vanadium-Cerium system has not been formulated to this day. Literature data [1] about the reaction of vanadium with cerium are limited to information, that this system is similar to other V - p.z.e. systems.

Employing methods of macro- and microstructural, thermal and x-ray analyses, as well as the microhardness method was investigated the structural diagram of the vanadium-cerium system up to 50 weight percentages of cerium. As basic materials served: carbothermal vanadium (99.766%) and metallic cerium (98.8%). The fusions were prepared in an arc furnace with nonconsumable tungsten electrode on a copper water-cooled bottom in an atmosphere of purified titanium getterated helium under a pressure of 0.9 atm. To attain uniformity in composition along the ingot, the alloys were subjected to fourfold remelting. The annealing of alloys, containing up to 1 weight percentage of cerium, was done at 1100° for a period of 100 hrs, and alloys with greater cerium content - at 750° for a period of 200-250 hrs in quartz evacuated ampoules.

During macro- and microstructural analysis (fig.1a) of the alloys was revealed the appearance of a second layer, rich in cerium, beginning with 0.2 - 0.3% of Ce. The vanadium rich layers, were monophasic (fig.1b). Solubility of cerium in solid vanadium is very low and remains almost unchanged at a change in temperature. Maximum solubility of cerium in vanadium equals 0.1%.

Fig.1. Microstructure of vanadium-cerium alloys: a-separation boundary of two layers of vanadium alloy with 50% Ce; b-vanadium layer of very same alloy.

Data about maximum solubility of Ce have been confirmed by the microhardness method. When measuring microhardness on the PMT-3 instrument at a load of 100 g it was found that microhardness of pure vanadium upon the addition of 0.05 - 0.1% of Ce rises from 150 to 165 - 170 kg/mm<sup>2</sup>. Upon a further increase in the Ce content in the batch the microhardness of vanadium changes little.

Fig.2. Structural Diagram of vanadium-cerium system

No intermediate phases are formed in the system. On the powder roentgenogram of the vanadium alloy with 50% Ce (VK<sub>α</sub> - radiation) were visible only vanadium lines and cerium lines. The parameter of the vanadium lattice (  $a = 3.029 \text{ \AA}$  ) does not change during fusion with cerium.

By measuring the melting point by the drop method, which is described in report [2] it was established, that the temperature of a monotectic equilibrium is very close to the melting point of vanadium (1885±15°). By a differential thermal microanalysis, described in report [3] it was established that vanadium raises the melting point of Ce very little (by 5-7°), forming with it, apparently, a peritectic, and reduces by 20-25° the temperature of polymorphous transformation of gamma-Ce into δ - Ce.

Smelting of technical vanadium, contaminated with oxygen and nitrogen, with cerium leads to a reduction in its hardness and rise in plasticity in cold state, as it has been observed also in other rare metals [4]. Molten Ce affects each vanadium

bath as a deoxidizing flux as result of formation of  $CeO_2$  and  $CeN$ . Cerium reduces the content of oxygen and nitrogen in vanadium to a level, at which these admixtures produce no negative effect on its plasticity.

Vanadium, refined with cerium, is cold rolled without intermediate annealings to a high degree of deformation (95%).

By the results of these investigations was plotted a structural diagram of the vanadium-cerium system, as shown in fig.2.

#### Literature

1. S. A. Kompathy, R. H. Read, W. Rostoker. Phase Relationships in Selected binary and ternary Vanadium - base alloys Systems. Armour Research Foundation of Illinois Institute of Technology. Waco Technical Report 59-483, p 6-15 Jan.
2. V.V. Baron; Yu.V. Yefimov; Ye.M. Savitskiy, Izvestiya Akademii Nauk SSSR, Otdel Tekhn. Nauk, No.4, 36, (1958).
3. Ye.M. Savitskiy; Ch.V. Kopetskiy, Zhurnal Neorganicheskoy Khimii 5, 2422, 1960
4. Ye.M. Savitskiy, Izvest. Akad. Nauk SSSR, Otdel. Tekhn. Nauk, Metallurgiya i Toplivo No.5, 52 (1960).

Submitted Sept. 16, 1961

DISTRIBUTION LIST

DEPARTMENT OF DEFENSE	Nr. Copies	MAJOR AIR COMMAND	Nr. Copies
		AFSC	
		SCFDD	1
		ASTIA	25
HEADQUARTERS USAF		TDBTL	5
		TDBDP	5
AFCIN-3D2	1		
ARL (ARB)	1	AEDC (AEY)	1
OTHER AGENCIES			
CIA	1		
NSA	6		
DIA	9		
AID	2		
OTS	2		
AEC	2		
PWS	1		
NASA	1		
ARMY	3		
NAVY	3		
RAND	1		