

UNCLASSIFIED

AD 400 786

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

400 786

42236

S/019/62/000/014/050/054
I007/I207

15.3200

STEP

AUTHORS: D'yachkov, P.N., Bol'shakov, I.P. and Purgin, A.K.

TITLE: Method for obtaining refractory concrete

PERIODICAL: Byulleten' izobreteniy, no.14, 1962, 60 (Soviet patent, class 80b, 8₁₈, no.149052, 672368/29, July 4, 1960)

TEXT: A method is described for obtaining refractory concrete from a mixture of soluble glass, sodium silicon-fluoride and suitable fillers. To eliminate setting (contraction) of concrete and to increase its resistance to high-temperatures, the fillers used are made of waste obtained during burning (firing) Dinas brick, or from broken, used Dinas bricks.

[Abstracter's note: Complete translation.]

Card 1/1