

**UNCLASSIFIED**

**AD 406 769** \_\_\_\_\_

**DEFENSE DOCUMENTATION CENTER**

FOR

**SCIENTIFIC AND TECHNICAL INFORMATION**

**CAMERON STATION, ALEXANDRIA, VIRGINIA**



**UNCLASSIFIED**

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

63-3-6

# AZUSA PLANT

STRUCTURAL MATERIALS DIVISION

INVESTIGATION OF STRESS-CORROSION CRACKING  
OF HIGH-STRENGTH ALLOYS

A Report To

FRANKFORD ARSENAL

Contract DA-04-495-ORD-3069

Report No. L0414-01-24 / June 1963 / Copy No.

8

CATALOGED BY DDC

AS AD No.

406769

406 769

DDC  
RECEIVED  
JUN 25 1963  
TISIA B




AEROJET-GENERAL CORPORATION  
AZUSA, CALIFORNIA

This is the twenty-fourth in a series of informal monthly progress reports submitted in partial fulfillment of Contract DA-04-495-ORD-3069. It constitutes the eighth monthly progress report for the one-year continuation of the original two-year program.

This report covers the period 1 May through 31 May 1963. It was written by R. B. Setterlund, who was supervised by A. Rubin.

AEROJET-GENERAL CORPORATION



P. L. Jordan, Head  
Metallics and Refractories Department  
Structural Materials Division

NOTE: The information contained herein is regarded as preliminary and subject to further checking, verification, and analysis.

I. OBJECTIVES

The objectives of this program are outlined below:

A. Investigation of the stress-corrosion cracking characteristics of at least three new high-strength alloys of interest for rocket motor-case applications. These alloys are 6Al-4V titanium, 18%-nickel maraging steel, and 20%-nickel maraging steel, in addition to limited testing of vacuum-melted 9Ni-4Co steel.

B. Study of the environmental parameters that could affect the rate and extent of stress-corrosion cracking.

C. Determination of the effect of material parameters (composition, strength level, welding, and microstructure) on stress-corrosion susceptibility.

D. Continuation of the evaluation of protective coatings and other techniques for preventing stress-corrosion cracking.

II. SUMMARY

Testing has been started on the final remaining alloy of the program - a vacuum-cast 9%-nickel 4%-cobalt steel with approximately 0.30% carbon. This alloy has shown some failures in the 140<sup>o</sup>F water-saturated air environment.

III. WORK PROGRESS

A. INTRODUCTION

Since the initiation of the original test program two years ago to investigate the stress-corrosion cracking characteristics of high-strength alloys, a number of new high-strength steels have been receiving increased attention for use in constructing rocket-motor cases. The third-year test program is directed to the study of three of these new alloys, as well as of one titanium alloy presently being used for the same application.

The test environments, substantially the same as those evaluated in the original two-year investigation, are as follows: (1) distilled water; (2) tap water; (3) salt water; (4) sodium-dichromate-inhibited water; (5) soluble oil-inhibited water; (6) air; (7) high-humidity atmosphere; (8) trichloroethylene; and (9) cosmoline. These are considered to be environments representative of those to which the cases would normally be exposed during fabrication, processing, and storage. One additional environment is included in the new program, that of sea-coast atmospheric exposure.

The test methods being used in this investigation employ bent-beam, U-bend, and center-notched specimens. Evaluation of results included micro-structural studies, using both standard metallographic and electron microscopic techniques, to attempt to associate the failure mechanism with specific micro-structural characteristics of the materials.

An evaluation of protective coatings and surface treatments to prevent stress-corrosion cracking is also being conducted.

The scope of the program is shown in Table 1.

#### B. WORK PROGRESS

During the period covered by this report, four groups of specimens of vacuum-cast 9%-nickel 4%-cobalt steel were placed in test. The material was tested at three strength levels attained by double-tempering at 400, 600 and 800°F. Material at each strength level was exposed to four environments: aerated distilled water, aerated tap water, aerated salt water, and 140°F water-saturated air. The chemical and physical properties of the material is shown in Table 2. Results to date, Table 3, show that the only failures have occurred in the 140°F water-saturated air environment.

#### IV. FUTURE WORK

Work is continuing along the guidelines of the master plan (Table 1). Both bent-beam and center-notched specimens are being tested to fulfill as much as possible of this schedule.

Metallographic sections of selected cracked samples have been photographed and presented in the last quarterly report. In addition, photomicrographs will be made of welded 18 and 20%-nickel steel samples which have failed in test.

Three samples were studied by means of the electron microscope, utilizing fracture replicas. Selected fractographs were presented in the last quarterly report. For the final report an additional set of fractographs is being prepared, using a failed sample of annealed and aged 18%-nickel maraging steel.

V. BUDGET

The expenditure rate for the month of May was 46 hours, leaving a balance of 160 hours for the remainder of the contract period.

Alloy	Processing Condition (Titanium Content of Welding Steel Shown)	Strength Level, 0.2% Offset Yield (psi)	Specimen Code	Number of Test Environments											Sea Coast Atmosphere	Total	
				Distilled Water	Tap Water	3% NaCl Solution	0.2% Sodium Dichromate Solution	1% Soluble Oil	High Humidity	Trichloro- ethylene	Comoline	Solid Propellant	Ambient Air				
6Al-4v titanium	Annealed	138,000	G-1	3	3	3	3	3	3	3	3	3	3	3	3	3	30
	Quenched and Aged	163,000	G-2	2	2	2	2	2	2	2	2	2	2	2	2	2	20
	Welded	157,000	G-4	8	8	8	8	8	8	8	8	8	8	8	8	8	80
	Total			13	13	13	13	13	13	13	13	13	13	13	13	13	132
20% Nickel Maraging Steel	Annealed and Aged	291,000	H-1	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	50% CW and Aged	321,000	H-2	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	75% CW and Aged	298,300	H-3	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	Welded and Aged	To be tested	H-4	2	2	2	2	2	2	2	2	2	2	2	2	2	22
Total			12	12	12	12	12	12	12	12	12	12	12	12	12	12	132
10% Nickel Maraging Steel	Annealed & Aged (0.62% Ti)	283,000	I-1	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	50% CW & Aged (0.50% Ti)	302,400	I-2	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	50% CW & Aged (0.62% Ti)	283,000	I-3	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	Annealed & Aged (0.50% Ti)	249,900	I-4	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	50% CW & Aged (0.40% Ti)	278,000	I-5	3	3	2	2	2	2	2	2	2	2	2	2	2	22
	Annealed & Aged (0.50% Ti)	275,400	I-6	3	3	2	2	2	2	2	2	2	2	2	2	2	22
	50% CW & Aged (0.50% Ti)	332,000	I-7	3	3	2	2	2	2	2	2	2	2	2	2	2	22
	Annealed & Aged (1.00% Ti)	283,200	I-8	3	3	2	2	2	2	2	2	2	2	2	2	2	22
	50% CW & Aged (1.00% Ti)	354,400	I-9	2	2	2	2	2	2	2	2	2	2	2	2	2	22
	Welded & Aged (0.50% Ti)	To be tested	I-W	2	2	2	2	2	2	2	2	2	2	2	2	2	22
	Total			30	30	23	15	15	15	15	15	15	15	15	15	15	15
9 Ni-4 Co Vacuum- Cast Alloy	Aged (0.25-0.30% C)	To be tested	J-1	3	3	3	3	3	3	3	3	3	3	3	3	3	33
	Aged (0.40-0.45% C)	To be tested	J-2	2	2	2	2	2	2	2	2	2	2	2	2	2	22
	Total			6	6	6	6	6	6	6	6	6	6	6	6	6	66
E-11 Steel (Coating Tests)	Application of Various Protective Coatings			36	41	21	41	41	41	22	85	41	41	41	41	41	286
	Total			36	41	86	41	41	41	85	41	41	41	41	41	41	595

Number of replicate tests conducted.

Table 1

TABLE 2

CHEMICAL ANALYSIS AND MECHANICAL PROPERTIES OF  
9Ni-4Co VACUUM CAST ALLOY

Mill Certified Chemical Analysis*									
C	Mn	P	S	Si	Co	Ni	Cr	Mo	V
0.30	0.23	0.006	0.007	0.02	4.10	8.65	0.43	0.35	0.10

Mechanical Properties (Transverse) Aerojet Tests					
Condition	Yield Strength (0.2% Offset) ksi	Ultimate Tensile Strength ksi	Elongation %	% Reduction of Area	Rc Hardness
(Austenitized 1550°F in argon - oil quenched 2 hours double temper at temperatures shown)					
400°F	190.3	230.3	8	52	48
600°F	184.6	203.0	7	54	43
800°F	172.4	186.7	9	59	41
1000°F	176.7	187.1	11	60	40.5

\* Republic Heat 3950924.

TABLE 3

## BENT-BEAM TESTS, STRESS CORROSION OF 9Ni-4Co STEEL\*

<u>Environment</u>	<u>Tempering Temperature (°F)</u>	<u>Failure Ratio**</u>	<u>Failure Time (hr)</u>	
			<u>Mean</u>	<u>Range</u>
140°F Saturated Air	400	3/3	187	115-260
	600	1/3	428	428-NF500
	800	0/2	-	NF 170**
Aerated Distilled Water	400	0/3	-	NF 500
	600	0/3	-	NF 500
	800	0/2	-	NF 170
Aerated Tap Water	400	0/3	-	NF 500
	600	0/3	-	NF 500
	800	0/2	-	NF 170
Aerated Salt Water	400	0/3	-	NF 500
	600	0/3	-	NF 500
	800	0/2	-	NF 170

\* All samples austenitized at 1550°F, oil-quenched and double-tempered at indicated temperatures for 2 hours. All samples were stressed to give a maximum outer-fiber stress of 75% of the 0.2% offset yield strength.

\*\* Failure ratio is the number of specimens failed over the number of specimens tested. NF indicates no failures were obtained.