

UNCLASSIFIED

AD 410282

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOGED BY DDC
AS AD No. 410282

410282

NOTES ON LARGE-SIZE FURNACES
FOR HEAT TREATING METAL ASSEMBLIES
(A Revision of DMIC Memo 63)

DEFENSE METALS INFORMATION CENTER
BATTELLE MEMORIAL INSTITUTE
COLUMBUS 1, OHIO

The Defense Metals Information Center was established at Battelle Memorial Institute at the request of the Office of the Director of Defense Research and Engineering to provide Government contractors and their suppliers technical assistance and information on titanium, beryllium, magnesium, refractory metals, high-strength alloys for high-temperature service, corrosion- and oxidation-resistant coatings, and thermal-protection systems. Its functions, under the direction of the Office of the Secretary of Defense, are as follows:

1. To collect, store, and disseminate technical information on the current status of research and development of the above materials.
2. To supplement established Service activities in providing technical advisory services to producers, melters, and fabricators of the above materials, and to designers and fabricators of military equipment containing these materials.
3. To assist the Government agencies and their contractors in developing technical data required for preparation of specifications for the above materials.
4. On assignment, to conduct surveys, or laboratory research investigations, mainly of a short-range nature, as required, to ascertain causes of troubles encountered by fabricators, or to fill minor gaps in established research programs.

Contract No. AF 33(616)-7747
Project No. 2(8-8975)

"The information in this report came from many sources, and the original language may have been extensively quoted. Quotations should credit the original authors and the originating agency. Where patent questions appear to be involved, the usual preliminary search is advised before making use of the material, and where copyrighted material is used, permission should be obtained for its further publication."

COPIES AVAILABLE FROM DTIC \$

NOTES ON LARGE-SIZE FURNACES
FOR HEAT TREATING METAL ASSEMBLIES

H. J. Hucek, A. R. Elsea, A. M. Hall*

INTRODUCTION

This memorandum is a revision of DMIC Memorandum 63, dated August 25, 1960. The revision was initiated as a result of recent inquiries by defense contractors. Most of these inquiries concerned the availability of heat-treating facilities of larger size than those listed in the original memorandum.

The information given in this memorandum was obtained from telephone conversations with company representatives, company literature, the Defense Metals Information Center files, and published information.(1,2,3)** The names of the companies contacted are listed in the Appendix.

The technology of rockets and missiles has placed great emphasis on the heat treatment of the high-strength steels used in the manufacture of high-speed aircraft and missiles. For example, a rocket body, consisting of a thin-wall cylindrical tank, must be heat treated after fabrication so as to maintain very close dimensional tolerances and at the same time meet stringent specifications for mechanical properties. Decarburization must be held to a minimum, and in some cases no decarburization can be tolerated.

Surface reactions (such as decarburization) that occur during heat treatment are usually prevented, or at least minimized, by filling the heating chamber with a protective atmosphere or by heating in a neutral molten salt. The most familiar types of protective atmospheres are exothermic, endothermic, nitrogen, inert gases (chiefly argon), dry hydrogen, and vacuum. No one atmosphere is suitable for all heat treatments. The most common protective atmospheres, endothermic and exothermic, are obtained from the products of combustion of hydrocarbon fuel gases.

Exothermic gas is obtained from air-gas mixtures that will support combustion. These exothermic gases are saturated at about 10 F above the cooling-water temperature, and auxiliary drying equipment is needed to vary the water-vapor content (dew point) after the mixture leaves the generator.

The gas-air mixture used to produce endothermic gas is too rich to support combustion, and the reaction takes place in an externally heated retort. Within practical limits, the moisture content can be varied by adjusting the air-to-gas ratio without the use of auxiliary drying equipment. It has been established that the dew point of an endothermic atmosphere is a theoretical and practical measure of its carbon potential.

*Ferrous and High-Alloy Metallurgy Division, Battelle Memorial Institute.

**References are listed at the end of this memorandum.

AVAILABILITY OF LARGE FURNACES

The availability and location of extra-large-capacity furnaces is summarized in Table 1. Most of the companies listed as having furnaces also have metallurgical test facilities available which include Magnaflux, X-ray, tensile, and hardness testing. Many have additional facilities such as Magnaglo, ultrasonic inspection, spectrograph, chemical analysis, and metallographic laboratories.

As shown in Table 1, most of the furnaces are bottom-open gantry furnaces using an endothermic protective atmosphere. This type of furnace allows loading from or quenching into a pit below the furnace without losing the protective atmosphere or exposing the part to the air. Also, holding the parts to be heat treated in a vertical position assists in reducing distortion during heat treatment.

The endothermic protective atmosphere is the most popular because it is easy to control the carbon potential with this gas by regulating the dew point.⁽⁴⁾ The dew point in the furnace can be readily varied by regulating the mixture in the generator and the flow of atmosphere through the furnace. The regulation of the carbon potential of the furnace atmosphere is extremely important in heat treating parts which require close control or elimination of decarburization. An atmosphere which would be neutral to a 0.30 carbon steel could very readily decarburize a 0.40 carbon steel.

Table 1 is not intended to be a complete listing of all heat-treating facilities in the country. It is intended as a guide to the location of unusually large furnaces. Also, the information listed does not cover all available facilities at the various companies. Some of the facilities have a considerable flexibility which cannot be indicated in a brief table. For example, in some instances the same quench tanks and tempering units are available for more than one heating furnace. Other companies have furnaces and facilities which can be readily adapted for a wide range of work. Information as to the availability and uses of the facilities at any given time can best be obtained by contacting the company listed.

In contacting furnace manufacturers and heat treaters in order to bring up to date the list of furnaces in Table 1, most companies indicated they are waiting for definite sizes and material commitments from potential customers before installing any new large furnaces. Large gantry-type furnace installations are a major capital investment, and most companies are reluctant to spend such sums on the basis of speculation.

The largest heat-treating furnaces now available were built specifically to heat treat cases with diameters up to 120 inches. The only larger furnace presently available (204 inches in diameter; Item 11 in Table 1, Eastern Section) is stationary and is presently being used in manufacture of large glass-lined steel tanks. This furnace does not now have a protective atmosphere available. Engineering work has been completed on the design modifications to provide hoists which operate through the furnace arch. Also, shrouds with seals to enclose the work piece, a salt-quench bath, and a separate

preheating and tempering furnace have been designed. When a definite need develops for incorporating these features into the furnace, it could be done in a few months' time.

REFERENCES

- (1) DMIC Report 119, "Heat Treatment of High-Strength Steels for Airframe Applications", R. J. Fiorentino, D. B. Roach, and A. M. Hall, OTS PB 151076.
- (2) "Survey of Special Furnaces for Rocket, Missile and Aircraft Components", Metal Treating, September-October, 1959, and April-May, 1960.
- (3) DMIC Memorandum 63, "Notes on Large-Size Furnaces for Heat Treating Metal Assemblies", H. J. Hucek, A. R. Elsea, and A. M. Hall (August 25, 1960).
- (4) Round Table on Atmosphere Generation, Metal Progress, 66, N5, pp 81-123 (November, 1954)

TABLE 1. DESCRIPTIONS OF SOME EXTRA-LARGE-CAPACITY

Company	Description of Furnace		Size of Heating Chamber		Types of Protective Atmospheres
	Type of Furnace	Method of Heating	Furnace	Length, feet	
			Opening, inches		
Central Section					
1. General Electric, Rocket Engine Section, Cincinnati, Ohio	Bottom-open, Gantry	Electric	120 dia	30	Endothermic
2. Army Ballistic Missile Agency, Redstone Arsenal, Alabama	Bottom-opening	Electric	96 dia	10	None (air)
3. Lindberg Steel Treating Co., Melrose Park, Illinois	Bottom-open, Gantry	Electric	80 dia	24	Endothermic, nitrogen, argon
4. Thompson-Ramo-Wooldridge, Inc., Cleveland, Ohio	Bottom-open, Gantry	Electric	72 dia	22	High nitrogen, argon, endothermic
5. Commercial Steel Treating Corp. Detroit, Michigan	Bottom-open, Gantry	Radiant tube-gas	70 dia	28	Endothermic
	Ditto	Ditto	70 dia	14	"
6. Goodyear Aircraft Corp., Akron, Ohio	Bottom-open, Gantry	Electric	68 dia	21	Nitrogen
7. Metallurgical Inc., Minneapolis, Minnesota	Bottom-open	Electric	72 dia	24	Any atmosphere required
8. Wall Colmonoy Corp., Detroit, Michigan	Vertical		72 dia	10	Dry hydrogen, argon, nitrogen, carbon dioxide, exothermic
9. Ingersoll Kalamazoo Division, Borg-Warner Corp., Kalamazoo, Michigan	Bottom-drop	Electric	42 dia	13	Endothermic
10. A O. Smith, Milwaukee, Wis.	Top-open pit	Electric	60 dia	10	Inert or recarb.
	Ditto	"	54 dia	12	Ditto
11. The National Acme Co., Cleveland, Ohio	Top-open pit	Electric	30 dia	7.5	Endothermic
	Ditto	"	30 dia	6.5	"
12. Allison Division, General Motors Corp., Indianapolis, Ind.	Bottom-open	For more information contact Allison			

FURNACE EQUIPMENT AVAILABLE IN THE UNITED STATES

Maximum Temperature, F	Quenching Media	Tempering Facilities		Remarks
		Size ^(a) Diam, inches; Length, ft.	Maximum Temperature, F	
<u>Central Section</u>				
1. 2000	Salt, water, air, oil (available)	120" dia x 30' (two)	1400	Salt quench can be heated 300 F to 1000 F; water quench can be heated to 180 F
2. 1200		96" dia x 10'	1200	
3. 2050	Salt, nitrogen (gas), water	80" dia x 24' (two)	1400	
4. 2050	Salt, oil, water	72" dia x 22'	1400	
5. 1850 1850	Oil Oil	70" dia x 22'	1250	
6. 1950	Salt, water	72" dia x 22' (two)	1400	Plan to add facilities to Gantry; add endothermic
7. 2150	Salt, oil, water	84" dia x 24'	1250	
8.				Furnace used for brazing and heat treating
9. 1800	Oil	72" dia x 14'	1400	
10. 1750 1750		54" dia x 12' (two)	1350	
11. 1900 1900		30" dia x 7'-8" 30" dia x 6'-8"	800 800	
12.		For more information contact Allison.		

TABLE 1.

Company	Description of Furnace		Size of Heating Chamber		Types of Protective Atmosphere	
	Type of Furnace	Method of Heating	Furnace	Length, feet		
			Opening, inches			
Eastern Section						
1. J. W. Rex Company, Lansdale, Pennsylvania	On same track {	Bottom-open, Gantry	Electric	71 dia	22	Endothermic
		Bottom-open, Gantry	Electric	60 dia	15	Endothermic
		Bottom-open, vertical	--	144 dia	32	Endothermic
2. H. K. Porter Company, Inc. Ambridge, Pennsylvania	Bottom-open, Gantry Ditto	Gas	48 dia	13	Endothermic	
		Gas	36 dia	18	"	
3. Alco Products Manufacturing Company, Dunkirk, N. Y.	Bottom-opening	Electric	44 dia	13.5	Endothermic	
4. Pittsburgh Commercial Heat Treating Co., Pittsburgh, Pennsylvania	Bottom-opening	Electric	44 dia	10	Endothermic	
5. Metlab Company, Philadelphia, Pennsylvania	Bottom-opening	Propane gas	36 dia	14	Endothermic or exothermic	
6. Parish Pressed Steel, Reading, Pennsylvania	Top-open pit		30 dia	12'-11"	Products of combustion	
7. S. D. Hicks, Ashville, North Carolina	Salt pot	Gas	72 sq	20	Neutral salt	
8. The Hicks Corporation, Boston, Massachusetts	Salt pot		48 sq	15	Neutral salt	
	Salt pot ^(b)	Electric and gas	33 dia	16	Ditto	
9. M. W. Kellogg Company, Jersey City, N. J.	Salt pot		48 sq	15	Neutral salt	
	Salt pot ^(b)	Electric	30 dia	10	Ditto	
	Salt pot ^(b)	Electric	30 dia	10	"	
10. Pratt-Whitney, East Hartford, Connecticut	Gantry-type	Electric	90 dia	12	Endothermic and nitrogen	
11. The Pfaudler Co. Division of Pfaudler Permutit, Inc. Rochester, New York	Vertical, Bottom-open	Natural gas	204 dia	33	Can be made available	

(Continued)

		Tempering Facilities			
Maximum Temperature, F	Quenching Media	Size ^(a) Diam, inches; Length, ft.	Maximum Temperature, F	Remarks	
<u>Eastern Section</u>					
1. 1950	Caustic, oil	71" x 22' (two)	1500	}	On same track
	salt, water	71" x 15' (two)	1500		
1950	Oil, caustic	71" x 8'	1500		
1950		60" x 13'	1500		
1850	Salt	157" x 44'	1250		20 tons
2. 1700		60" x 57" x 12'-6"	850		
		36" x 13'	1700		
1700		48" x 18'	1700		
3. 1950	Oil or water	72" x 48" x 20' (horiz.)	1250		
		44" x 13'-8" (vert.)	1250		
4. 1900		40" x 10'	1850		
5. 1850		Available according to requirements			
6. 1650		36" x 68" x 23'-4 (horiz.)	1300		
7.	Oil				
8. 1700		72" sq x 20' (horiz.)	1300		
9. 1700		36" sq x 12'	1300		
1300		36" sq x 6'	1300		
10. 2000	Tempering facilities will be available			Proposed future construction	
11. 2500	Will be made available as needed			50 ton max. work load	

TABLE 1.

Company	Description of Furnace		Size of Heating Chamber		Types of Protective Atmospheres
	Type of Furnace	Method of Heating	Furnace	Length, feet	
			Opening, inches		
Western Section					
1. Aerojet-General Corp., Azusa, California	Bottom-open, Gantry	Electric	100 dia	21	Endothermic
Sacramento, California	Bottom-open, Gantry	Electric	96 dia	20	Endothermic
2. North American Aviation, Los Angeles, California	Bottom-open, Gantry	Electric	84 dia	29	Exothermic nitrogen base
3. Menasco Manufacturing Co., Fort Worth, Texas	Bottom-open, Gantry		80 dia	24	Endothermic
4. Lindberg Steel Treating Co., Los Angeles, California	Bottom-open, Gantry	Electric	80 dia	16	Exothermic, argon, nitrogen
5. The Marquardt Corp., Ogden, Utah	Bottom-opening	Electric	80 dia	10	Endothermic and exothermic
6. Marquardt Aircraft Co., Van Nuys, California	Bottom-open, Gantry	Electric	72 dia	10	Endothermic
7. Norris-Thermador, Los Angeles, California	Bottom-open, Gantry Ditto	Gas "	60 dia 96 dia	11 20	Endothermic "
8. Douglas Aircraft Company, Inc., Torrance, California	Bottom-open, Gantry (two) Bottom-opening	Electric Electric	74 dia 48 dia	18 10	Endothermic and exothermic Exothermic
9. Menasco Manufacturing Co., Burbank, California	Vertical	Electric	72 dia	13	Endothermic
10. California-Doran Heat Treating Co., Los Angeles, California	Bottom-open, Gantry Top-open pit Bottom-open, Gantry	Radiant tube-gas Gas Gas	60 dia 60 dia 154 dia	16 6 14	Exothermic, nitrogen Endothermic, or argon Endothermic and exothermic
11. Boeing Airplane Company, Seattle, Washington	Gantry	Electric	60 dia	14	Endothermic
12. Lockheed Aircraft Corp., Burbank, California	Bottom-open, Gantry	Electric	60 dia	15	Endothermic
13. E and J Heat Treating Inc.	Bottom-open, Gantry Top-open pit	Radiant tube-gas Electric	84 dia 48 dia	10 16	Endothermic Endothermic
14. Solar, A Subdivision of International Harvester, San Diego, California	Top-open pit	Electric	108 dia	30	Endothermic, nitrogen hydrogen, argon
15. North American Aviation, Downey, California	Horizontal		78 dia	40	Vacuum or inert gas
16. Convair, Astronautics San Diego, California	Vacuum	Electric	72 dia	10	Vacuum

(a) Vertical unless noted.

(Continued)

Maximum Temperature, F	Quenching Media	Tempering Facilities		Maximum Temperature, F	Remarks
		Size ^(a) Diam, inches; Length, ft			
<u>Western Section</u>					
1. 2050		100" dia x 21'		1450	
	Salt, oil				
2. 2050	Nitrogen-base atmosphere water,	84" dia x 29'		1450	Subzero cooling chamber 84" x 29' cools to -110 F
3. 2050	Salt, water	80" dia x 24'		1250	
4. 2050	Salt, water			1400	
5. 2000		80" dia x 10'		1000	
6. 2000		72" dia x 10'		1000	
7. 1800	Salt	60" dia x 16'		1300	
8. 2000	Oil, water, salt atmosph.	74" dia x 18'		1450 F	11 pit stations
1800	Oil			1250	
9. 2000	Water, oil, salt	72" dia x 13'			
10. 1900 1800	Water	60" dia x 16'		1150	
11. 1900 2050		42" dia x 16' 60" dia x 14'		1700 1450	
12. 2050		60" dia x 15'		1450	
13. 1950 1900	Oil, water Oil, water	48" x 16' 72" x 20'		1250 Quench pits for both furnaces	Can temper in Gantry (has circulating fan) also, a 48" x 16' pit is available for subzero treatment to -110 F
14. 1950	Air	108" dia x 30'		1950	
15. 2250	Cooled inside fur- nace by inert atmosphere				Furnace used for degassing, heat treatment and brazing
16.					

(b) Two salt pots of this size.

APPENDIX

APPENDIX

Companies and individuals contacted in the survey of extra-large-capacity furnace equipment available in the United States.

General Electric Corporation
Rocket Engine Section
Cincinnati, Ohio
Mr. N. C. White

Lindberg Steel Treating Co.
Melrose Park, Illinois
Mr. G. H. Bodeen
Mr. J. Boerema

J. W. Rex Company
Lansdale, Pennsylvania
Mr. John E. King

Commercial Steel Treating Company
Detroit, Michigan
Mr. Patterson

Thompson-Ramo-Wooldridge, Inc.
Cleveland, Ohio
Mr. Jim Long

Metallurgical, Inc.
Minneapolis, Minnesota
Mr. Paul Wallace

Pacific Scientific Company
Los Angeles 22, California
Mr. Bob Grossman

Surface Combustion Division of
Midland-Ross Corporation
Toledo, Ohio
Mr. Koch

Allison Division of General Motors
Corporation
Indianapolis, Indiana
Mr. Roger Fleming

Sunbeam Equipment Corporation
162 Mercer Street
Meadville, Pennsylvania
Mr. Dain

Excelco Developments, Inc.
Silver Creek, New York
Mr. W. D. Abbott

Goodyear Aircraft Corporation
Akron, Ohio
Mr. Ed Saneoska
Mr. Bob Barch

Rheem Manufacturing
Downey, California
Mr. Sykes

E and J Heat Treating, Inc.
Los Angeles 58, California
Mr. D. Leach

General Electric Corporation
Industrial Heating Department
Shelbyville, Indiana
Mr. Richardson

Lindberg Engineering Company
Chicago, Illinois
Mr. Norbert K. Koebel

Pfautler Company
Rochester, New York
Mr. William Galloway
Mr. J. W. Glenn

LIST OF DMIC MEMORANDA ISSUED
(Continued)

A list of DMIC Memoranda 1-164 may be obtained from DMIC, or see previously issued memoranda.

DMIC Memorandum Number	Title
165	Review of Uses for Depleted Uranium and Nonenergy Uses for Natural Uranium, February 1, 1963
166	Literature Survey on the Effect of Sonic and Ultrasonic Vibrations in Controlling Grain Size During Solidification of Steel Ingots and Weldments, May 15, 1963