

UNCLASSIFIED

AD 414693

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOGUED BY DDC

AS AD No. 414693


414693

BRL

MEMORANDUM REPORT NO. 1485
JUNE 1963

PREPARATION OF POROUS NITROCELLULOSE
FOR A TRAVELING CHARGE GUN

James E. Cole
Carl R. Ruth



RDT & E Project No. 1M010501A004
BALLISTIC RESEARCH LABORATORIES

ABERDEEN PROVING GROUND, MARYLAND

DDC AVAILABILITY NOTICE

Qualified requestors may obtain copies of this report from DDC.

The findings in this report are not to be construed
as an official Department of the Army position.

BALLISTIC RESEARCH LABORATORIES

MEMORANDUM REPORT NO. 1485.

JUNE 1963

PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING CHARGE GUN

James E. Cole
Carl R. Ruth

Interior Ballistics Laboratory

RDT & E Project No. 1M010501A004

ABERDEEN PROVING GROUND, MARYLAND

B A L L I S T I C R E S E A R C H L A B O R A T O R I E S

MEMORANDUM REPORT NO. 1485

JCole/CRuth/mec
Aberdeen Proving Ground, Md.
June 1963

PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING CHARGE GUN

ABSTRACT

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

TABLE OF CONTENTS

	Page
ABSTRACT	3
INTRODUCTION	7
PROPELLANT PREPARATION	7
TRAVELING CHARGE PREPARATION	7
DISCUSSION	8
CONCLUSIONS.	10
ACKNOWLEDGEMENTS	10
BIBLIOGRAPHY	11

INTRODUCTION

Various porous propellants for use in a traveling charge gun have been investigated by the Ballistic Research Laboratories.^{1,2,3} Recently Cole and Adams described a process⁴ for the preparation of porous propellants in the density range 0.8 to 1.3 g/cc. Their objective was to produce porous propellants having a narrow density gradient over the length of the round. Since then a porous nitrocellulose propellant has been formed for traveling charge rounds with a wide density gradient. These rounds have a length of four inches, an outer diameter of 0.575", and a density variation of $0.9 \pm .05$ g/cc at the one end to $1.2 \pm .05$ g/cc at the other end. For firing as a traveling charge, an inhibitor coating is applied to the porous propellant.

PROPELLANT PREPARATION

The procedures used to prepare the propellant (Military Grade Nitrocellulose 13.15N) were essentially the same as described in an earlier BRL Report.⁴ The significant differences in the preparation procedure were the loading and pressing of the nitrocellulose into the mold. The loading of the material into the mold was achieved with the aid of a specially constructed eight-inch riser fitted to the top of a six inch mold (Fig. 1). This riser enabled the nitrocellulose to be added in one large unit instead of in several increments. A torque wrench on the arbor press enabled the operator to apply and repeat any specific compressive force when preparing the propellant. A constant load was applied to a consolidating ram during curing in order to achieve the density-gradient required in the round (Fig. 2).

TRAVELING CHARGE PREPARATION

After the propellant was prepared it was glued to an aluminum projectile and inhibited to form a traveling charge projectile (projectile, propellant and inhibitor). The inhibitors examined were an organosol of a double base propellant (M-8); a liquid plastic; and an aluminum sleeve.

The initial step in inhibiting a traveling charge with the M-8 or liquid plastic was the fastening of an aluminum projectile to the propellant. Next a dip coating of a solvent solution of M-8 was used to inhibit the propellant. The M-8 inhibited round was then cured by partial room temperature evaporation of the solvent and a final cure for ten hours in a 40°C oven.

A potting process was used for propellant inhibited with liquid plastic. After potting the propellant into molds containing the liquid plastic, the assembly was placed in a 25°C oven to cure the liquid plastic by polymerization. The sample cured in two hours.

The pre-fabricated aluminum sleeve inhibitors had the correct outside diameter. It was, therefore, necessary only to use a solvent solution of M-8 and pot the porous propellant into these aluminum sleeves.

DISCUSSION

Initial studies indicated that the density-gradient, and especially the density of the top and bottom one-inch pieces of a round, was due to the compressional forces applied during both packing and curing. The table illustrates this effect on the density-gradient for a propellant round. When increment loading was used the density-gradient changed irregularly at the increment junctions. Elimination of weak, irregular density connections between successive increment pressings⁴ has been attained by using an eight-inch riser which enables the nitrocellulose to be added in one increment.

The propellant, used for the aluminum inhibited or plastic inhibited traveling charges, was 0.575 inches in diameter before it was inhibited and 0.625 inches after the inhibitor was applied. To use M-8 to inhibit rounds, it was necessary to start with 0.600 inch diameter propellant in order to obtain the required 0.625 inch diameter end product. Figure 4 illustrates the problem encountered when additional M-8 coatings were applied to previously dried coatings. A maximum of 0.025 inch thickness of M-8 inhibitor could be applied to the outside of the traveling charge projectile because of a softening effect of successive coatings of the M-8 inhibitor on the previously dried coatings. The liquid plastic (Fig. 3) fulfilled all requirements for a coating, except for the undesirable residue left in the gun after firing. It was superior to the M-8 coating because of its ease of handling, ease of application, and fast curing to a hard translucent solid. The pre-fabricated aluminum sleeve inhibitors were used as potting containers for the porous propellant.

The performance of the porous propellant and the inhibitors tested will be published as part of a report on the traveling charge gun.

EFFECT OF COMPRESSION AND CURE WEIGHT ON THE DENSITY-GRADIENT IN A FOUR-INCH PIECE OF POROUS NITROCELLULOSE


Compression lbs/in ²	Curing Weight lbs	Density g/cc for adjacent one inch sections			
		1 (bottom)	2	3	4 (top)
86	10	0.52	0.77	0.93	0.99
86	10	0.65	0.74	0.96	1.10
160	20	0.59	0.86	1.13	1.25
224	30	0.95	1.17	1.22	1.33
224	10	0.59	1.21	1.22	1.21
196	10	0.87	1.19	1.27	1.27
196	10	0.89	1.17	1.19	1.26
196	15	0.92	1.13	1.10	1.20
196	15	0.85	1.11	1.17	1.25

CONCLUSIONS

Porous nitrocellulose propellant was formed into pieces 4" x 0.575" with a density variation of 0.9 gm/cc at one end to 1.2 g/cc at the other end. Increment loading, resulting in poor segment bonds was avoided by using a long loading riser on the mold. Techniques were developed to apply effective inhibitors to traveling charge propellant.

ACKNOWLEDGEMENTS

The authors wish to thank Mr. Horace Smith for his evaluation of the porous propellant and traveling charge rounds; Mr. Ernest Adams for designing the hardware; and Mr. Paul Brown for assisting in the preparation of the propellant.


JAMES E. COLE


CARL R. RUTH

BIBLIOGRAPHY

1. Vest, D. C. An Experimental Traveling Charge Gun. BRL Report No. 773, 1951.
2. Baer, P. B. Application of Porous Propellant to the Traveling Charge Gun. BRL Technical Note No. 1219, 1958.
3. Vest, D. C., and Vinti, J. P. A Theory of Fast Burning Propellants and Applications to the Traveling Charge Gun. Bulletin of the 9th Meeting of JANAF Solid Propellant Group.
4. Cole, J. E. and Adams, E. C. A Process for the Preparation of Nitro-cellulose Propellants in the Density Range of 0.8 to 1.3 g/cc. BRL Technical Note No. 1487.




Figure 1. Mold assembly with compacting ram.




Figure 2. Mold assembly ready for curing.



Figure 3. One M-8 and two liquid plastic inhibited traveling-charge rounds



Figure 4. Effect of excess M-8 coatings

DISTRIBUTION LIST

<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>
10	Defense Documentation Center Cameron Station Alexandria, Virginia	1	Redstone Scientific Information Center ATTN: Chief, Document Section U. S. Army Missile Command Redstone Arsenal, Alabama
2	Director Advanced Research Projects Agency ATTN: Advanced Propellant Chemistry Office The Pentagon, Room 3D159 Washington 25, D. C.	2	Commanding General U. S. Army Ammunition Command ATTN: ORDLY-AREL, Engr. Library Joliet, Illinois
1	Commanding General U. S. Army Materiel Command ATTN: AMCRD-RP-Bal Research and Development Directorate Washington 25, D. C.	1	Commanding General White Sands Missile Range ATTN: ORDBS-OM-TL New Mexico
1	Commanding General U. S. Army Materiel Command ATTN: AMCRD-RC Research and Development Directorate Washington 25, D. C.	1	Commander U. S. Naval Ordnance Laboratory White Oak Silver Spring 19, Maryland
3	Commanding Officer Picatinny Arsenal ATTN: Library Dover, New Jersey	2	Commanding Officer U. S. Naval Propellant Plant ATTN: Technical Library Indian Head, Maryland
1	Commanding Officer Radford Arsenal Radford, Virginia	2	Commander U. S. Naval Ordnance Test Station ATTN: Technical Library Branch China Lake, California
1	Commanding Officer Frankford Arsenal ATTN: Propellant and Explosives Section, 1331 Philadelphia 37, Pennsylvania	1	AFMTC (MTRSS) Patrick Air Force Base Florida
1	Commanding Officer Harry Diamond Laboratories ATTN: Technical Information Office, Branch 012 Washington 25, D. C.	2	AFGC (FGAPI) Eglin Air Force Base Florida
		1	Director National Aeronautics and Space Administration ATTN: Library Langley Research Center Langley Field, Virginia

DISTRIBUTION LIST

<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>
2	6593d Test Group (DGPS, DGS) Edwards Air Force Base California	1	Jet Propulsion Laboratory ATTN: I. E. Newlan, Chief Reports Group 4800 Oak Grove Drive Pasadena 3, California
2	Scientific and Technical Information Facility ATTN: NASA Representative P. O. Box 5700 Bethesda, Maryland	1	Lockheed Propulsion Company ATTN: Librarian P. O. Box 111 Redlands, California
1	U. S. Department of Interior Bureau of Mines ATTN: Reports Librarian Explosives Research Lab. 4800 Forbes Avenue Pittsburgh 13, Pennsylvania	1	Olin Mathieson Chemical Corporation ATTN: Research Library Marion, Illinois
1	Aerojet-General Corporation ATTN: Technical Information Office P. O. Box 1947 Sacramento, California	1	Rocketdyne A Division of North American Aviation, Inc. ATTN: Library Solid Propulsion Operations P. O. Box 548 McGregor, Texas
1	Armour Research Foundation of Illinois Institute of Technology ATTN: G. K. Hersh, Chemistry Div. Technology Center Chicago 16, Illinois	1	Rocketdyne ATTN: Library, Dept. 596-306 6633 Canoga Avenue Canoga Park, California
1	Atlantic Research Corporation Shirley Highway and Edsall Road Alexandria, Virginia	1	Roim and Haas Company ATTN: Librarian Redstone Arsenal Research Division Huntsville, Alabama
1	E. I. duPont deNemours and Company ATTN: Mrs. Alice R. Steward Eastern Laboratory Gibbstown, New Jersey	2	Stanford Research Institute ATTN: Code 460 Menlo Park, California
1	Hercules Powder Company ATTN: Library Allegany Ballistics Laboratory P. O. Box 210 Cumberland, Maryland	1	Thiokol Chemical Corporation ATTN: Librarian Elkton Division Elkton, Maryland

DISTRIBUTION LIST

<u>No. of Copies</u>	<u>Organization</u>
1	United Technology Corporation ATTN: Librarian P. O. Box 358 Sunnyvale, California
10	Solid Propellant Information Agency Applied Physics Laboratory The Johns Hopkins University Silver Spring, Maryland
10	The Scientific Information Officer Defence Research Staff British Embassy 3100 Massachusetts Avenue, N. W. Washington 8, D. C.
4	Defence Research Member Canadian Joint Staff 2450 Massachusetts Avenue, N. W. Washington 8, D. C.

AD	Accession No.	UNCLASSIFIED
Ballistic Research Laboratories, AFG		
PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING		
CHARGE GUN		
James E. Cole and Carl R. Ruth		Traveling Charge - Preparation Propellants - Preparation Nitrocellulose - Processing
BRL Memorandum Report No. 1485 June 1963		
ROT & E Project No. 1M010501A004		
UNCLASSIFIED Report		

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

AD	Accession No.	UNCLASSIFIED
Ballistic Research Laboratories, AFG		
PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING		
CHARGE GUN		
James E. Cole and Carl R. Ruth		Traveling Charge - Preparation Propellants - Preparation Nitrocellulose - Processing
BRL Memorandum Report No. 1485 June 1963		
ROT & E Project No. 1M010501A004		
UNCLASSIFIED Report		

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

AD	Accession No.	UNCLASSIFIED	UNCLASSIFIED
Ballistic Research Laboratories, APC			
PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING			
CHARGE GUN			
James E. Cole and Carl R. Ruth			Traveling Charge - Preparation
			Propellants - Preparation
			Nitrocellulose - Processing
REL Memorandum Report No. 1485	June 1963		
NOT & E Project No. 1M010501A004			
UNCLASSIFIED Report			

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

AD	Accession No.	UNCLASSIFIED	UNCLASSIFIED
Ballistic Research Laboratories, APC			
PREPARATION OF POROUS NITROCELLULOSE FOR A TRAVELING			
CHARGE GUN			
James E. Cole and Carl R. Ruth			Traveling Charge - Preparation
			Propellants - Preparation
			Nitrocellulose - Processing
REL Memorandum Report No. 1485	June 1963		
NOT & E Project No. 1M010501A004			
UNCLASSIFIED Report			

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.

A method is described for the preparation of porous nitrocellulose propellant with a density-gradient of 0.9 gm/cc at one end to 1.2 gm/cc at the other end. Hardware refinements are discussed for the loading and pressing of the nitrocellulose. A table is included showing the variation of density with different compressional forces. A description is given of the assembling of the hardware and inhibiting the propellant.