

**UNCLASSIFIED**

**AD - 4 2 6 4 2 4**

**DEFENSE DOCUMENTATION CENTER**

**FOR**

**SCIENTIFIC AND TECHNICAL INFORMATION**

**CAMERON STATION, ALEXANDRIA, VIRGINIA**



**UNCLASSIFIED**

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

0426424

|    |    |    |    |    |    |    |
|----|----|----|----|----|----|----|
| 0  | 4  | 2  | 6  | 4  | 2  | 4  |
| 1  | 2  | 3  | 4  | 5  | 6  | 7  |
| 8  | 9  | 10 | 11 | 12 | 13 | 14 |
| 15 | 16 | 17 | 18 | 19 | 20 | 21 |
| 22 | 23 | 24 | 25 | 26 | 27 | 28 |
| 29 | 30 | 31 | 32 | 33 | 34 | 35 |
| 36 | 37 | 38 | 39 | 40 | 41 | 42 |
| 43 | 44 | 45 | 46 | 47 | 48 | 49 |
| 50 | 51 | 52 | 53 | 54 | 55 | 56 |
| 57 | 58 | 59 | 60 |    |    |    |

## GENERAL PURPOSE SUMMARY CARD

AF FORM 993A 1 AUG 54

[illegible]

414768

CATALOGED BY DDC

AS AD No.

426424

Final Technical Report

1 October, 1962 - 30 September, 1963

Professor Thomas Edman

Philadelphia College of Textiles and Science

Development of Prosthetic Knitted Fabrics  
Contract No. DA-49-193-MD-2359

Qualified Requestors may obtain copies of this report from ASTIA.

0426424

|    |
|----|
| 1  |
| 2  |
| 3  |
| 4  |
| 5  |
| 6  |
| 7  |
| 8  |
| 9  |
| 10 |
| 11 |
| 12 |
| 13 |
| 14 |
| 15 |
| 16 |
| 17 |
| 18 |
| 19 |
| 20 |
| 21 |
| 22 |
| 23 |
| 24 |
| 25 |
| 26 |
| 27 |
| 28 |
| 29 |
| 30 |
| 31 |
| 32 |
| 33 |
| 34 |
| 35 |
| 36 |
| 37 |
| 38 |
| 39 |
| 40 |
| 41 |
| 42 |
| 43 |
| 44 |
| 45 |
| 46 |
| 47 |
| 48 |
| 49 |
| 50 |
| 51 |
| 52 |
| 53 |
| 54 |
| 55 |
| 56 |
| 57 |
| 58 |
| 59 |
| 60 |

# GENERAL PURPOSE SUMMARY CARD

[illegible]

414-66

Textile Department

Philadelphia College of Textiles and Science

Development of Prosthetic

Knitted Fabrics

Professor Thomas Edman

27 December, 1963

Contract Number DA-49-193-MD-2359

Supported by United States Army Medical Biochemical Research Laboratory

U.S. Army Medical Research and  
Development Command  
Department of the Army  
Washington, D.C. 20025

Summary:

The purpose of this project was to develop and finish knitted fabric samples as directed by the staff of the U.S. Army Medical Biochemical Research Laboratory (formerly the U.S. Army Prosthetic Research Lab) for Cosmetic Gloves, Leg Cover Materials, Porous Laminates, Grafts, and other Surgical Fabrics. The fabric samples were used in plastic coating and evaluation experiments by MEDEC M.B.R.L.

Method: 1. There is no final determination of the ultimate Synthetic vascular grafts to be used. We supplied the following prosthesis -

20 pieces 6 mm 80 denier polyester 60 courses per inch 10/4 crimp tubes

|    |   |       |     |   |   |    |   |   |   |      |   |   |
|----|---|-------|-----|---|---|----|---|---|---|------|---|---|
| 20 | " | 8 mm  | 80  | " | " | 60 | " | " | " | 10/4 | " | " |
| 20 | " | 10 mm | 80  | " | " | 60 | " | " | " | 10/4 | " | " |
| 20 | " | 12 mm | 80  | " | " | 60 | " | " | " | 10/4 | " | " |
| 10 | " | 25 mm | 140 | " | " | 60 | " | " | " | 10/4 | " | " |
| 5  | " | 30 mm | 140 | " | " | 60 | " | " | " | 10/4 | " | " |

12 pieces 19-9.5 mm. 140 denier polyester 60 courses per inch 10/4 crimp bifurcation

|   |     |        |     |   |           |    |   |   |   |                |
|---|-----|--------|-----|---|-----------|----|---|---|---|----------------|
| 5 | "   | 2.5 mm | 100 | " | teflon    | 60 | " | " | " | bleached tubes |
| 5 | "   | 12 mm  | 100 | " | "         | 60 | " | " | " | "              |
| 1 | yds | 2 mm   | 80  | " | polyester | 60 | " | " | " | straight tubes |
| 1 | "   | 3 mm   | 80  | " | "         | 60 | " | " | " | "              |
| 1 | "   | 4 mm   | 80  | " | "         | 60 | " | " | " | "              |
| 1 | "   | 5 mm   | 80  | " | "         | 60 | " | " | " | "              |
| 1 | "   | 6 mm   | 80  | " | "         | 60 | " | " | " | "              |

The above fabrics were knitted on circular knitting machines 3/8" - 1 1/2" diameter, 30 and 34 cut - single feed and straight rib machine 18 cut, 2 feed, 20" wide.

2. The development of cosmetic gloves continued for adults and children with the following items:-

8 adults right hand

8 " left "

3 child's right "

2 " left "

The glove is knitted on Diamont hand flat rib machine, 10 cut, cam setting

$\frac{5}{10.5} \frac{10.5}{5}$  for tubular construction, using 3 ends of 40 denier "S" twist polyester Fluflon yarn. The finished gloves are mended, scoured and tumble dried.

The palm is knitted on 60 needles in each bed for 200 rounds. SNW (Single Needle Widening) 20 x 2 on both sides. Insert marker yarn for thumb on needles 5 to 40 counting from the right for right glove. SNN (Single Needle Narrowing) 10 x 5 on both sides.

|                             |    |     |     |     |
|-----------------------------|----|-----|-----|-----|
| Fingers: needle arrangement | 20 | 22  | 24  | 23  |
|                             | 0  | 20  | 41  | 62  |
|                             |    |     |     | 80  |
| Total rounds                | 80 | 110 | 120 | 110 |
| start of narrowing          | 66 | 96  | 106 | 96  |

Thumb: start on 36 needles of marker in each bed SNN 10 x 2 on left side only, 100 rounds, start of narrowing at 86.

3. The development of porous laminates included mesh flat knitted fabrics on 28 and 32 gauge 2 bar tricot machines. The size of the openings varied from 1/16" to 1/2". The final fabric was knitted with the following construction:-

FB 10/12/10/12/10/12/10/12/23/21/23/21/23/21/23/21

BB 23/21/23/21/23/21/23/21/10/12/10/12/10/12/10/12

The yarn was 40 denier polyester Flufion, 6 inch quality. Ten yards of fabric was scoured and tumble dried for further processing at MEDEC-MDRL.

4. A large number of assorted constructions were supplied for undesignated end uses as follows:-

1 lb. 1900 denier polyester twisting 4 ends 440 den.

2 yds. 807 tricot fabric

20 " 704 tube 40 DF 12 CPI

10 " 706 " 80 DF 12 CPI

10 " 708 " 80 DF 12 CPI

50 " 360 " 70 DB 13 CPI