

UNCLASSIFIED

AD 431311

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

TECHNICAL REPORT

AMRA TR 63-35

CATALOGED BY DDC

AS AD No.


431311

431311

EFFECT OF TEMPERING ON NOTCH PROPERTIES
OF D6AC ALLOY STEEL SHEET

by

ROBERT N. KATZ



MATERIALS ENGINEERING LABORATORY

U. S. ARMY MATERIALS RESEARCH AGENCY

WATERTOWN, MASSACHUSETTS 02172

DECEMBER 1963

The findings in this report are not to be construed
as an official Department of the Army position.

DDC AVAILABILITY NOTICE

Qualified requesters may obtain copies of this report from Commanding Officer,
Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314

Copies available at Office of Technical Services, U.S. Department
of Commerce, Washington 25, D.C.

Price \$0.50

DISPOSITION INSTRUCTIONS

Destroy; do not return

Rocket motor materials
Notch testing - sheet
materials
Steel, high strength

EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC ALLOY STEEL SHEET

Technical Report AMRA TR 63-35

by

Robert N. Katz

December 1963

AMCMS Code 5025.11.843

Materials for Solid Propellant Rocket Motors

D/A Project 1A024401A111


MATERIALS ENGINEERING LABORATORY
U. S. ARMY MATERIALS RESEARCH AGENCY
WATERTOWN, MASSACHUSETTS 02172

U. S. ARMY MATERIALS RESEARCH AGENCY

EFFECT OF TEMPERING ON NOTCH PROPERTIES
OF D6AC ALLOY STEEL SHEET


ABSTRACT

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher tempers. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.



ROBERT N. KATZ
Physical Metallurgist

APPROVED:



JOSEPH I. BLUHM
Chief
Materials Engineering Laboratory

CONTENTS

	Page
ABSTRACT	
INTRODUCTION	3
MATERIAL	3
EXPERIMENTAL PROCEDURE	4
RESULTS AND DISCUSSION	5
CONCLUSIONS	12
FUTURE WORK	12
APPENDIX	13
REFERENCES	14

INTRODUCTION

During October 1961, at the request of the U. S. Army Missile Command, the U. S. Army Materials Research Agency (AMRA) conducted a series of burst tests to evaluate the adequacy of the H11 steel being used in the Shillelagh missile rocket motor cases. When brittle fractures were observed in cases which were burst at -65 F, AMRA recommended a change from H11 steel to D6AC steel for this application. The recommendation was accepted and AMRA was asked to conduct burst tests on the D6AC Shillelagh rocket motor cases when they became available. While the missile case was being redesigned and fabrication procedures were being established by the prime contractor, the smooth and notch tensile properties of 0.040-inch-thick D6AC alloy sheet were studied in order to have supplementary data available for subsequent evaluation of the adequacy of the D6AC alloy for the rocket motor case application.

MATERIAL

The material used in this investigation was consumable electrode vacuum-melted D6AC steel. It was received in the hot-rolled and annealed condition and was 0.060-inch thick. The supplier's chemical analysis and that obtained by AMRA are shown in Table I.

TABLE I
CHEMICAL COMPOSITION

Analysis	Element (weight percent)								
	C	Mn	P	S	Si	Ni	Cr	Mo	V
Composition Limits	0.42-0.48	0.60-0.90	0.015 max.	0.015 max.	0.15-0.30	0.40-0.70	0.90-1.20	0.90-1.10	0.05-0.10
Manufacturer	0.44	0.77	0.009	0.009	0.24	0.52	1.08	1.06	0.09
AMRA	0.49	0.84	0.008	0.008	0.26	0.58	1.10	1.07	0.08

All material was subjected to a 20-minute normalization at 1650 F followed by air cooling. After normalizing, the material was austenitized at 1650 F for 20 minutes and air cooled. This treatment rendered the material fully martensitic. The austenitizing temperature of 1650 F was chosen to eliminate the possibility of free ferrite being present as has occurred at lower austenitizing temperatures.¹ After cooling, samples A through F were double tempered and sample G was triple tempered as indicated in Table II.

TABLE II
TEMPERING TEMPERATURE OF D6AC STEEL

Specimen Series	Temper (°F)	Time
A	800	1 + 1 hr AC
B	900	"
C	950	"
D	1000	"
E	1050	"
F	1100	"
G	400 then 600	1 hr AC 2 + 2 hr AC

The maximum observed decarburization was 0.0065 inch, which was later eliminated during Blanchard grinding to the 0.040-inch thickness.

EXPERIMENTAL PROCEDURE

All blanks were cut from the sheet in the transverse direction. After heat treatment, blanks were surface ground down to final thickness and finish machined. For each condition of heat treatment, 10 AMRA standard sheet tensile specimens and 10 AMRA standard flat tensile edge-notched specimens were prepared (for dimensions see Figure 1). These specimens were then tested at five test temperatures, encompassing the range of +70 F to -200 F. After testing the notched tensile specimens, two sheet Charpy specimens were taken from the shoulder of one of the broken halves. The Charpy specimens were cut so the crack would propagate in the same direction as in the notched tensile specimens. The Charpy specimens were precracked by fatiguing and were tested on a 16 ft-lb capacity machine at the same temperature as the tensile specimen from which they were cut.

The values of the fracture toughness, K_{IC} , were based on percent shear measurements and are thus K_{IC4} values in the standard ASTM designation.² G_C values calculated from these K_{IC4} measurements were correlated with W/A values (energy per unit area values measured in in-lb/sq in.) obtained from the precracked Charpy specimens.




Figure 1. SHEET SPECIMEN DIMENSIONS

RESULTS AND DISCUSSION

The smooth and notch tensile properties for each tempering temperature are plotted versus test temperatures in Figures 2 through 8; the transition properties are shown in Figure 9; and the fracture toughness data versus tempering temperature are presented in Figures 10 and 11. The data from which these figures were prepared are tabulated in the Appendix.

The tempering response of the smooth and notch tensile properties of D6AC sheet presented in Figures 2 through 8 are as one would have predicted. Increasing the tempering temperature decreases both ultimate and yield strengths. The ultimate strength at room temperature falls from about 275 ksi for 600 F tempers to 232 ksi for the 1100 F temper. The yield strength at room temperature falls from about 235 ksi to about 210 ksi over this same tempering range. The notch properties also follow a rather predictable pattern. As the tempering temperature increases, the notch strength increases, and the deterioration of notch strength with falling test temperatures becomes less pronounced. This is demonstrated in the plots of notch strength and notch/unnotch ratio in Figures 2 through 8.




Figure 2. 600 F Temper




Figure 3. 800 F Temper




Figure 4. 900 F Temper




Figure 5. 950 F Temper

TENSILE PROPERTIES OF D6AC AS A FUNCTION OF TEST TEMPERATURE




Figure 6. 1000 F Temper




Figure 7. 1050 F Temper




Figure 8. 1100 F Temper
TENSILE PROPERTIES OF D6AC AS A
FUNCTION OF TEST TEMPERATURE

The 50% shear lip transition temperatures, measured on edge-notched specimens, also undergo decreases as tempering temperature increases, as shown in Figure 9. When working with a notch-sensitive material, the notch strength becomes a more valid criteria of expected materials performance than the more traditional criteria of tensile or yield strength, especially when the materials may be used at a temperature below its shear transition temperature. This criteria is particularly important in a material such as the one studied in this report where, in all but one instance, the notch strength is significantly below the yield strength. For this reason, the notch strength at the shear transition temperature versus tempering temperature is also plotted in Figure 9, making it possible to obtain both the 50% shear transition temperature and the notch strength at this temperature for 0.040-inch D6AC sheet material as a function of tempering temperatures.




Figure 9. PERCENT SHEAR TRANSITION TEMPERATURE AND NOTCH STRENGTH AT THE TRANSITION TEMPERATURE OF D6AC AS A FUNCTION OF TEMPERING TEMPERATURE




Figure 10. FRACTURE TOUGHNESS OF D6AC AT ROOM TEMPERATURE AND -40 F AS A FUNCTION OF TEMPERING TEMPERATURE




Figure 11. FRACTURE TOUGHNESS OF D6AC AT -120 F AND -200 F AS A FUNCTION OF TEMPERING TEMPERATURE

The fracture toughness of D6AC 0.040-inch sheet measured by K_{IC} and G_C values as a function of tempering temperature for tests at room temperature and -40 F is shown in Figure 10. It is observed that for tempers above 800 F there is little difference in fracture toughness at a given temper between the two test temperatures. In Figure 11, however, a large falloff in fracture toughness is observed as testing temperature is decreased to -120 F and -200 F. Only the 1100 F temper exhibits adequate fracture toughness at -120 F, based on the criteria of a minimum G_C of 1000 in-lb/sq in. From the figures and the data it is obvious that for both high strength and toughness at the widest variety of test temperatures, the optimum tempering range is 1000 F to 1100 F. It is especially interesting to note that in this range the designer is provided a material with a yield strength of about 216 ksi and a G_C of over 1000 in-lb/sq in. for use at temperatures down to -40 F, or a yield strength of about 210 ksi and fracture toughness values of 1000 in-lb/sq in. at temperatures in the vicinity of -100 F. The rapid falloff in fracture toughness when tempering below 1000 F and the relatively poor low temperature properties obtained at these tempers should preclude the use of such materials when notch sensitivity is a consideration or when low temperature service is a probability.

It was observed that the notched tensile specimens exhibited four distinct types of fracture surfaces when broken. These are shown in Figure 12. If one of the specimens in a given test broke in mode 1 or 2 and one broke in mode 3 or 4, an attempt was made to see if a significant difference in the notch tensile strengths occurred. It was found that such differences that did occur were often less than the differences in the scatter obtained when both bars would break in the same mode (e.g., without the 180-degree rotation of the shear lip). Although the observation from this study is that the different fracture appearances with the same percent shear lip do not affect the notch strength*




Figure 12. OBSERVED MODES OF CRACK PROPAGATION

*It must be remembered that a correlation does exist between percent shear and fracture toughness and that the values of K_{IC} were calculated using a factor which is dependent on the percent shear (see Reference 2).

(and hence K_C), there were not enough specimens to test for each specific condition to give statistical validity to this observation. It is hoped, therefore, that in future studies of this nature investigators will note the fracture mode as well as the tensile and notch properties so that enough data for a valid statistical analysis may be accumulated.

Other investigators³ have shown that values of energy per unit area (W/A values) obtained from precracked sheet Charpy specimens can be correlated with the critical strain energy release rates (G_C) as calculated from notched sheet specimens. However, their study showed somewhat more scatter than desirable in order to have confidence in using precracked sheet Charpy specimens as a substitute for the more expensive (in both time and money) edge- or center-notched sheet tensile tests for determining fracture toughness. It was felt that taking sheet Charpy specimens from the same notched tensile specimens that were used to obtain the fracture toughness data would considerably reduce the scatter in the G_C versus W/A correlation. As can be seen from Figure 13, the scatter is equal to that in Reference 3 and is considerable. This is surprising since several different high strength steels were used in their correlation, while this study used only one. However, if the average rather than the individual values of the two Charpy specimens cut from each notched specimen is plotted, the scatter is reduced considerably (see Figure 14). Since averaging two sheet Charpy specimens reduces the scatter, further reductions in scatter might be anticipated if three or more specimens are used.

As part of another program currently being conducted by this Laboratory, Shillelagh rocket motor cases* were tested under varying conditions of testing temperature and pre-existent crack length. These motor cases were austenitized at 1650 F, quenched into salt at 400 F, and tempered at 1025 F. They had a wall thickness of 0.047 inch as compared to the 0.040-inch thickness of the sheet material tested. All the cases broke in full shear at temperatures down to -85 F. The K_C values calculated on the basis of the Boeing⁴ cylindrical pressure vessel formula for through-the-thickness cracks were consistently 10 to 20% below those obtained from the sheet material. This difference may be attributed to variations in thickness, processing history, and heat treatment. It is also interesting to note that all cases tested without pre-existent cracks burst near their ultimate strengths and that no premature failures occurred.

*"Burst Tests of DBAC Shillelagh Missile Motor Cases," unpublished research at AMRA by R.N. Katz




Figure 13. FRACTURE TOUGHNESS VALUES OBTAINED FROM EDGE-NOTCHED TENSILE SPECIMENS VERSUS W/A VALUES OBTAINED FROM PRECRACKED CHARPY SPECIMENS, USING INDIVIDUAL CHARPY VALUES.




Figure 14. FRACTURE TOUGHNESS VALUES OBTAINED FROM EDGE-NOTCHED TENSILE SPECIMENS VERSUS W/A VALUES OBTAINED FROM PRECRACKED CHARPY SPECIMENS, USING THE AVERAGE OF TWO CHARPY VALUES.

CONCLUSIONS

1. The best combination of notch and tensile properties in 0.040-inch-thick D6AC sheet are obtained by tempering between 1000 F and 1100 F, within the range of tempers studied.

2. The precracked sheet Charpy specimen provides better correlation with G_c values than previously observed, if several specimens in the same condition of heat treatment, chemistry, and test variables are averaged.

FUTURE WORK

A continuation of the study on the sheet tensile and notch properties is underway. It will entail a determination of the critical thickness of D6AC sheet for various heat treatments and testing temperatures. A fuller investigation into the reliability of the precracked sheet Charpy specimen as a means of obtaining fracture toughness and critical thickness data will be undertaken.

APPENDIX

Tensile and Notch Properties of 0.040-inch D6AC Sheet

Test Temperature (F)	Yield Strength (ksi)	Tensile Strength (ksi)	NTS (ksi)	NTS/UTS	Shear (%)	K _{C4} (ksi√in.)	G _C (in-lb/sq in.)
600 F Temper							
+200	202.5	266.5	160.0	0.60	100	137.0	625
RT	236.0	276.5	163.5	0.59	100	139.0	645
-40	231.5	270.5	115.0	0.43	78	90.0	270
-70	236.5	280.5	168.0	0.60	10	118.5	470
-120	244.0	283.5	105.5	0.37	10	71.5	170
-200	257.5	302.5	86.5	0.29	5	57.5	110
800 F Temper							
RT	226.5	256.0	170.0	0.66	100	143.0	680
-40	231.0	263.0	161.0	0.61	95	133.0	590
-70	238.5	269.5	154.0	0.57	93	126.5	535
-120	244.5	274.0	128.0	0.47	20	89.5	265
-200	251.5	287.0	110.0	0.38	10	74.5	185
900 F Temper							
RT	218.5	242.0	187.0	0.77	98	160.5	860
-40	225.5	255.5	172.0	0.67	93	142.0	670
-80	231.5	261.5	159.0	0.61	90	128.5	550
-180	232.0	254.0	139.0	0.55	35	101.5	345
-200	244.0	274.0	131.5	0.48	10	98.0	275
950 F Temper							
RT	219.0	247.0	201.0	0.82	88	181.5	1090
-40	213.5	252.0	169.5	0.67	88	158.5	840
-120	222.5	258.0	158.0	0.61	65	129.0	550
-140	225.5	263.0	139.5	0.53	45	104.0	360
-200	230.0	271.0	137.0	0.51	20	97.0	315
1000 F Temper							
RT	216.5	238.5	197.0	0.83	100	182.5	1110
-40	223.5	253.5	193.5	0.77	90	182.5	1110
-120	226.5	256.0	161.0	0.63	85	128.0	545
-160	229.0	262.5	156.0	0.60	40	114.0	435
-200	233.5	271.5	147.5	0.55	25	106.5	380
1050 F Temper							
RT	211.5	237.5	207.0	0.87	100	197.0	1295
-40	215.0	247.5	203.5	0.82	100	192.5	1235
-120	229.0	256.0	169.0	0.66	95	141.0	665
-160	224.5	265.0	154.0	0.58	63	115.5	445
-200	237.5	269.0	143.5	0.53	23	103.0	355
1100 F Temper							
RT	209.5	232.0	215.5	0.93	100	207.5	1435
-40	218.5	243.0	205.2	0.85	100	188.0	1180
-120	219.5	244.5	185.5	0.75	90	169.5	960
-160	220.0	251.0	168.0	0.67	95	143.5	685
-200	236.5	264.0	138.5	0.53	20	104.0	360

REFERENCES

1. SLINEY, J. L. Tabulation of Notch Properties of Commercial Sheet Alloys. Watertown Arsenal Laboratories, WAL TN 766.5/1, January 1963, p. 7.
2. Fracture Testing of High Strength Sheet Materials. ASTM Bulletin, January 1960, p. 29.
3. ORNER, G. M., and HARTBOWER, C. E. Sheet Fracture Toughness Evaluated by Charpy Impact and Slow Bend. Welding Journal, v. 40, no. 9, 1961, p. 405-409.
4. TIFFANY, C. F., and LORENZ, P. M. Notes for August 1962 Meeting of ASTM, FTHSM Committee.

U. S. ARMY MATERIALS RESEARCH AGENCY
WATERTOWN, MASSACHUSETTS 02172

TECHNICAL REPORT DISTRIBUTION

Report No.: AMRA TR 63-35 Title: Effect of Tempering on Notch
December 1963 Properties of D6AC Alloy Steel
Sheet

No. of Copies	TO
	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20315
1	ATTN: Mr. J. C. Barrett
1	Dr. Earl T. Hayes, Assistant Director (Materials)
20	Commanding Officer, Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314
	Director, Army Research Office, Office Chief of Research and Development, 3045 Columbia Pike, Arlington, Virginia 22204
2	ATTN: Physical Sciences Division
3	Solid Propellant Information Agency, Applied Physics Laboratory, The Johns Hopkins University, Silver Spring, Maryland
1	Defense Materials Information Center, Battelle Memorial Institute, Columbus, Ohio
	Commanding General, U. S. Army Materiel Command, Washington, D.C. 20315
1	ATTN: AMCRD-CM
	Commanding General, U. S. Army Electronics Command, Fort Monmouth, New Jersey 07703
1	ATTN: Mr. H. H. Kedesky
	Commanding General, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
2	ATTN: Documentation and Technical Information Branch
1	AMSMI-RRS, Mr. R. E. Ely
1	AMSMI-RKX, Mr. R. Fink
1	AMSMI, Mr. E. Fohrell
1	AMSMI, Mr. T. N. L. Pughe
1	AMSMI-RSM, Mr. E. J. Wheelahan
1	Commanding General, U. S. Army Munitions Command, Dover, New Jersey 07801

No. of Copies	TO
1	Commanding General, Headquarters, U. S. Army Tank-Automotive Center, Warren, Michigan 48090 ATTN: Mr. S. Sobak
1	Commanding General, U. S. Army Weapons Command, Rock Island, Illinois 61202 ATTN: AMSWE-QA, Mr. B. Gerke AMSWE-RDR, Mr. G. Reinsmith
1	Commanding Officer, Harry Diamond Laboratories, Washington, D.C. 20438 ATTN: AMXDO, Library
1	Commanding Officer, Frankford Arsenal, Bridge and Tacony Streets, Philadelphia, Pennsylvania 19137 ATTN: SMUFA-1330, Dr. H. Gisser SMUFA-1320, Mr. H. Markus SMUFA-1740, Mr. E. Roffman
3	Commanding Officer, Picatinny Arsenal, Dover, New Jersey 07801 ATTN: SMUPA, Mr. J. Matlack, Plastics and Packaging Laboratory SMUPA-DE3, Mr. D. Stein
1	Director, PLASTEC, Picatinny Arsenal, Dover, New Jersey 07801
1	Commanding Officer, Rock Island Arsenal, Rock Island, Illinois 61202 ATTN: SWERI, Laboratory
1	Commanding Officer, Springfield Armory, Springfield, Massachusetts 01101 ATTN: SWESP, Research Materials Laboratory
1	Commanding Officer, U. S. Army Coating and Chemical Laboratory, Aberdeen Proving Ground, Maryland 21005 ATTN: AMSTE, Dr. C. Pickett
1	Commanding Officer, U. S. Army Research and Development Office, Panama, P. O. Drawer 942, Fort Clayton, Canal Zone ATTN: STEDO
1	Commanding Officer, Watertown Arsenal, Watertown, Massachusetts 02172 ATTN: SMIWT-OE, Industrial Engineering Section
1	Commanding Officer, Watervliet Arsenal, Watervliet, New York 12189 ATTN: SWEWV-R, Mr. F. Dashnaw
9	Chief, Bureau of Naval Weapons, Department of the Navy, Washington, D.C. ATTN: Mr. H. Boertzel Mr. P. Goodwin RMMP, Room 2225, Munitions Building

No. of Copies	TO
1	Commander, U. S. Naval Ordnance Laboratory, White Oak, Silver Spring, Maryland ATTN: Code WM
1	Commander, U. S. Naval Ordnance Test Station, China Lake, California ATTN: Technical Library Branch
1	Commander, Naval Research Laboratory, Anacostia Station, Washington, D. C. ATTN: Mr. J. E. Srawley
1	Code 6110, Mr. E. Kohn
1	Chief, Office of Naval Research, Department of the Navy, Washington, D. C. ATTN: Code 423
1	Chief, Special Projects Office, Department of the Navy, Washington, D. C. ATTN: SP 271
1	U. S. Air Force Directorate of Research and Development, Room 4D-313, The Pentagon, Washington, D. C. 20315 ATTN: Lt. Col. J. B. Shipp, Jr.
1	Headquarters, Aeronautical Systems Division, Wright-Patterson Air Force Base, Ohio 45433 ATTN: ASRCN-11, Mr. F. J. Fecek
2	ASRCM-1, Mr. R. F. Klinger
2	ASRCT, Manufacturing and Technology Division
1	ASRCNP, Dr. Tamborski
2	ASRCEE-1-2, Mr. H. Zoeller
1	6593 Test Group (Development), Edwards Air Force Base, California 93523 ATTN: Solid Systems Division, DGSC
1	U. S. Atomic Energy Commission, Office of Technical Information Extension, P. O. Box 62, Oak Ridge, Tennessee
1	National Aeronautics and Space Administration, Washington, D. C. 20546 ATTN: Mr. B. G. Achhammer
1	Mr. G. C. Deutsch
1	Mr. R. V. Rhode
1	Director, Jet Propulsion Laboratory, California Institute of Technology, 4800 Oak Grove Drive, Pasadena, California ATTN: Dr. L. Jaffe

No. of Copies	TO
1	Director, George C. Marshall Space Flight Center, Huntsville, Alabama
1	ATTN: M-S&M-M, Dr. W. Lucas
1	M-ME-M, Mr. William A. Wilson
1	Aerojet-General Corporation, P. O. Box 296, Azusa, California
1	ATTN: Librarian
1	Aerojet-General Corporation, P. O. Box 1168, Sacramento, California
1	ATTN: Librarian
1	Aerojet-General Corporation, Building 2019, Department 4620, P. O. Box 1947, Sacramento, California
1	ATTN: Mr. C. A. Fournier
1	Allegheny Ludlum Steel Corporation, Research Center, Brackenridge, Pennsylvania
1	ATTN: Mr. R. A. Lula
1	Allison Division, General Motors Corporation, Indianapolis, Indiana
1	ATTN: Mr. D. K. Hanink
1	Alloyd Electronics Corporation, 35 Cambridge Parkway, Cambridge, Massachusetts
1	Aluminum Company of America, Alcoa Research Laboratories, Post Office Box 772, New Kensington, Pennsylvania
1	ATTN: Dr. J. L. Brandt
1	ARDE-Portland, Inc., 100 Century Road, Paramus, New Jersey
1	ATTN: Mr. R. Alper
1	Armco Steel Corporation, General Offices, Middletown, Ohio
1	ATTN: Mr. J. Barnett
1	Atlantic Research Corporation, Shirley Highway and Edsall Road, Alexandria, Virginia
1	ATTN: Mr. E. A. Olcott
1	Battelle Memorial Institute, 505 King Avenue, Columbus, Ohio
1	ATTN: Mr. R. Monroe
1	Boeing Company, Aerospace Division, P. O. Box 3707, Seattle, Washington
1	ATTN: Mr. R. R. Barber, Library Unit Chief
1	Borg-Warner Corporation, Ingersoll Kalamazoo Division, 1810 North Pitcher Street, Kalamazoo, Michigan
1	ATTN: Mr. L. E. Hershey

No. of Copies	TO
1	The Budd Company, Defense Division, Philadelphia, Pennsylvania ATTN: Mr. R. C. Dethloff
1	Climax Molybdenum Company, 1270 Avenue of the Americas, New York, N. Y. ATTN: Mr. R. R. Freeman
1	Crucible Steel Company of America, Four Gateway Center, Pittsburgh, Pennsylvania ATTN: Mr. W. L. Finlay
1	Curtiss-Wright Corporation, Wright Aeronautical Division, Wood-Ridge, New Jersey ATTN: Mr. A. M. Kettle, Technical Library
1	Douglas Aircraft Company Inc., Santa Monica Division, Santa Monica, California ATTN: Mr. J. L. Waisman
1	E. I. DuPont de Nemours and Co., Eastern Laboratories, Wilmington, Delaware ATTN: Mr. J. J. Douglass
1	Mr. C. P. Williams
1	General Electric Company, Rocket Engine Section, Flight Propulsion Laboratory Department, Cincinnati, Ohio
1	Hercules Powder Company, Allegheny Ballistics Laboratory, P. O. Box 210, Cumberland, Maryland ATTN: Dr. R. Steinberger
1	Hughes Aircraft Company, Culver City, California ATTN: Librarian
1	Kaiser Aluminum and Chemical Corporation, Spokane, Washington
1	A. D. Little, Inc., Acorn Park, Cambridge, Massachusetts ATTN: Dr. R. Davis
1	Ladish Company, Cudahy, Wisconsin ATTN: Mr. R. P. Daykin
1	Lyon, Inc., 13881 West Chicago Boulevard, Detroit, Michigan ATTN: Mr. W. Martin
1	Manufacturing Laboratories, 21-35 Erie Street, Cambridge, Massachusetts ATTN: Dr. V. Radcliffe

No. of Copies	TO
1	Minneapolis-Honeywell Regulator Co., 1230 Soldier Field Road, Brighton, Massachusetts
	Narmco Research and Development, 3540 Aero Court, San Diego, California
1	ATTN: Technical Library
	Norris-Thermador Corporation, 5215 South Boyle Avenue, Los Angeles, California
1	ATTN: Mr. L. Shiller
	The Perkin-Elmer Corporation, Main Avenue, Norwalk, Connecticut
1	ATTN: Mr. H. L. Sachs
	Pratt and Whitney Aircraft, East Hartford, Connecticut
1	ATTN: Mr. F. A. Crosby
	Reactive Metals Corporation, Niles, Ohio
1	ATTN: Mr. H. Lundstrem
	Republic Aviation Company, Missile Systems Division, 223 Jericho Turnpike, Mineola, New York
1	ATTN: Mr. R. Stegler
	Republic Steel Corporation, Research Center, 6801 Brecksville Road, Cleveland, Ohio
1	ATTN: Mr. H. P. Manger
	Rohm and Haas Company, Redstone Division, Redstone Arsenal, Alabama
1	ATTN: Library
	Space Technology Laboratories, Inc., P. O. Box 95001, Los Angeles, California
1	ATTN: Technical Information Center Document Procurement
	Tapco Group, 23555 Euclid Avenue, Cleveland, Ohio
1	ATTN: Mr. W. J. Piper
1	Thiokol Chemical Corporation, Utah Division, Brigham City, Utah
1	Thiokol Chemical Corporation, Reaction Motors Division, Denville, New Jersey
	Thiokol Chemical Corporation, Redstone Division, Redstone Arsenal, Alabama
1	ATTN: Library
1	H. I. Thompson Fiber Glass Co., 1600 West 135th Street, Gardena, California

No. of Copies	TO
1	Thompson Ramo Wooldridge, Inc., Tapco Group, 207 Hindry Avenue, Inglewood, California ATTN: Mr. G. J. Guarnieri
1	Titanium Metals Corporation, 233 Broadway, New York, N. Y. ATTN: Mr. G. Erbin
1	Universal-Cyclops Steel Corporation, Stewart Street, Bridgeville, Pennsylvania
1	U. S. Borax Research Corporation, 412 Crescent Way, Anaheim, California ATTN: Mr. R. J. Brotherton
1	United States Rubber Company, Research Center, Wayne, New Jersey ATTN: Dr. E. J. Joss
1	Wyman-Gordon Company, Grafton, Massachusetts ATTN: Mr. A. Rustay
1	Philco Corporation, Aeronutronics Division of Ford Motor Company, Ford Road, Newport Beach, California ATTN: Aeronutronics Library
1	Massachusetts Institute of Technology, Cambridge, Massachusetts ATTN: Professor W. A. Backofen
1	Professor M. C. Flemings
1	Mellon Institute, 4400 Fifth Avenue, Pittsburgh, Pennsylvania ATTN: Dr. H. L. Anthony
1	Mr. C. J. Owen
1	Michigan State University, Department of Chemistry, East Lansing, Michigan ATTN: Mr. R. N. Hammer
1	Ohio State University, Research Foundation, Columbus, Ohio ATTN: Dr. R. McMaster
5	Commanding Officer, U. S. Army Materials Research Agency, Watertown, Massachusetts 02172 ATTN: AMXMR-TICL
1	AMXMR-CS
1	AMXMR-PT
1	Author
154	TOTAL COPIES DISTRIBUTED

OTS Price \$0.50

AD Accession No.
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5025.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

NO DISTRIBUTION LIMITATIONS

UNCLASSIFIED

1. Rocket motor materials

2. Notch testing - sheet materials

3. Steel, high strength

I. Katz, Robert N.

II. AMCMS Code 5025.11.843

III. D/A Project 1A024401A111

OTS Price \$0.50

AD Accession No.
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5025.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

NO DISTRIBUTION LIMITATIONS

UNCLASSIFIED

1. Rocket motor materials

2. Notch testing - sheet materials

3. Steel, high strength

I. Katz, Robert N.

II. AMCMS Code 5025.11.843

III. D/A Project 1A024401A111

OTS Price \$0.50

AD Accession No.
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5025.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

NO DISTRIBUTION LIMITATIONS

UNCLASSIFIED

1. Rocket motor materials

2. Notch testing - sheet materials

3. Steel, high strength

I. Katz, Robert N.

II. AMCMS Code 5025.11.843

III. D/A Project 1A024401A111

OTS Price \$0.50

AD Accession No.
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5025.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

NO DISTRIBUTION LIMITATIONS

UNCLASSIFIED

1. Rocket motor materials

2. Notch testing - sheet materials

3. Steel, high strength

I. Katz, Robert N.

II. AMCMS Code 5025.11.843

III. D/A Project 1A024401A111

OTS Price \$0.50

AD
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5026.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

UNCLASSIFIED

- I. Rocket motor materials
2. Notch testing - sheet materials
3. Steel, high strength
- I. Katz, Robert N.
- II. AMCMS Code 5026.11.843
- III. D/A Project 1A024401A111

OTS Price \$0.50

AD
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5026.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

UNCLASSIFIED

- I. Rocket motor materials
2. Notch testing - sheet materials
3. Steel, high strength
- I. Katz, Robert N.
- II. AMCMS Code 5026.11.843
- III. D/A Project 1A024401A111

NO DISTRIBUTION LIMITATIONS

OTS Price \$0.50

AD
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5026.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

UNCLASSIFIED

- I. Rocket motor materials
2. Notch testing - sheet materials
3. Steel, high strength
- I. Katz, Robert N.
- II. AMCMS Code 5026.11.843
- III. D/A Project 1A024401A111

OTS Price \$0.50

AD
U.S. Army Materials Research Agency, Watertown,
Massachusetts 02172
EFFECT OF TEMPERING ON NOTCH PROPERTIES OF D6AC
ALLOY STEEL SHEET - Robert N. Katz
Technical Report AMRA TR 63-35, December 1963, 14 pp -
illus - tables, AMCMS Code 5026.11.843, D/A Project
1A024401A111, Unclassified Report

A study of the strength and notch properties of D6AC (consumable electrode, vacuum-melted Cr-Mo-V) steel sheet, 0.040 inch thick, was conducted to evaluate the effect of tempering for various test temperatures. Smooth tensile, edge-notched tensile, and precracked subsize Charpy specimens were employed. Tempering in the range of 1000 F to 1100 F provided good fracture toughness with slight loss in strength properties that would be expected at higher temperatures. The results are compared with burst tests conducted on Shillelagh motor cases made from the 0.040-inch-thick D6AC steel.

UNCLASSIFIED

- I. Rocket motor materials
2. Notch testing - sheet materials
3. Steel, high strength
- I. Katz, Robert N.
- II. AMCMS Code 5026.11.843
- III. D/A Project 1A024401A111

NO DISTRIBUTION LIMITATIONS

NO DISTRIBUTION LIMITATIONS