

UNCLASSIFIED

AD NUMBER

AD525631

CLASSIFICATION CHANGES

TO: unclassified

FROM: confidential

LIMITATION CHANGES

TO:
Approved for public release, distribution
unlimited

FROM:
No Foreign

AUTHORITY

GDS 31 Dec 79; DTRA ltr, 6 May 99

THIS PAGE IS UNCLASSIFIED

CONFIDENTIAL

DNA 3042F

JANUARY 1973

**COMPOSITE HEMISPHERE FEASIBILITY STUDY (u)
FINAL REPORT**

AD 525631

WILFORD S. STEWART

**Headquarters
Defense Nuclear Agency
Washington, D.C. 20305**

**Government Research Laboratory
Esso Research and Engineering Company
Linden, New Jersey 07036**

Contract DNA001-73-C-0021

**"NATIONAL SECURITY INFORMATION"
"Unauthorized Disclosure Subject to Criminal Sanctions"**

**CLASSIFIED BY DD Form 254 dtd 16 Aug 72
CONTRACT DNA001-73-C-0021
AND CLASSIFICATION GUIDE CG-WX-2
SUBJECT TO GENERAL DECLASSIFICATION
SCHEDULE OF EXECUTIVE ORDER 11652
AUTOMATICALLY DOWNGRADED AT
TWO YEAR INTERVALS
DECLASSIFIED ON DECEMBER 31, 1979**

CONFIDENTIAL

CONFIDENTIAL

When this report is no longer needed, Department of Defense Organizations will destroy it in accordance with appropriate procedures. Contractors will destroy the report according to the requirements of the Industrial Security Manual for safeguarding classified information.

Retention of this document by DoD Contractors is authorized in accordance with Paragraph 2, Industrial Security Letter 71L-3, dated 17 May 1971.

CONFIDENTIAL

CONFIDENTIAL

**DNA 3042F
GRX.1CR.73
JANUARY 1973**

**COMPOSITE HEMISPHERE FEASIBILITY STUDY (U)
FINAL REPORT**

This work was supported by the Defense Nuclear Agency under NWED/Subtask AC308-06

WILFORD S. STEWART

**Headquarters
Defense Nuclear Agency
Washington, D.C. 20305**

**Government Research Laboratory
Esso Research and Engineering Company
Linden, New Jersey 07036**

Contract DNA001-73-C-0021

**"NATIONAL SECURITY INFORMATION"
"Unauthorized Disclosure Subject to Criminal Sanctions"**

CLASSIFIED BY DD Form 254 dtd 16 Aug 72
CONTRACT DNA001-73-C-0021
AND CLASSIFICATION GUIDE CG-WX-2
SUBJECT TO GENERAL DECLASSIFICATION
SCHEDULE OF EXECUTIVE ORDER 11652
AUTOMATICALLY DOWNGRADED AT
TWO YEAR INTERVALS
DECLASSIFIED ON DECEMBER 31, 1979

CONFIDENTIAL

CONFIDENTIAL

This report classified **CONFIDENTIAL**
per AEC letter because it implies
hardening - Classified in accordance
with topic 5.212 in CG-WX-2.

CONFIDENTIAL

CONFIDENTIAL

- 1 -

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	1
1. PURPOSE OF STUDY	1
2. DISCUSSION AND RESULTS OF FEASIBILITY STUDY	2
3. CONCLUSIONS	4

CONFIDENTIAL

CONFIDENTIAL

- 11 -

COMPOSITE HEMISPHERE FEASIBILITY STUDY

ABSTRACT

The feasibility of applying slip casting technology to the fabrication of a complex rounded carbon matrix composite structure having a controlled metal carbide content has been investigated.

The slip casting technology is based on the use of certain controlled particle size formulations; i.e., resin, carbon/graphite powders, and reinforcing fiber to fabricate a high strength carbon matrix composite structure.

Formulations were prepared in which certain metal carbide powders, TiC, TaC and ZrC, were incorporated into the slip formulation replacing selected fractions of the carbon/graphite powders. Conditions were established for the compression molding and carbonization of Z-loaded carbon hemispheres of approximately 4" O.D. and 100 mils wall thickness. Two different Z-layered structures (50 mils each) were fabricated into a single (100 mil) hemisphere. These carbon hemispheres showed little distortion and surface cracks after heat treatment up to 1400°C.

CONFIDENTIAL

CONFIDENTIAL

- 1 -

1. PURPOSE OF STUDY

The objective of the two month research program performed at Esso Research and Engineering Company and supported by the Defense Nuclear Agency, Washington, D.C. (Contract No. DNA-001-73-C-0021) was to demonstrate the feasibility and virtues of using certain controlled particle size formulations for the compression molding of a complex, rounded, metal carbide loaded carbon matrix composite structure.

The complex shape chosen was a hemisphere of approximately 4" O.D. The target wall thickness of hemisphere was 100 mils. In addition, the hemisphere should contain two discrete layers, each layer containing about 25 weight percent loading of different metal carbide powders and should be no more than 50 mils thick to stay within the 100 mil total wall thickness requirement.

CONFIDENTIAL

CONFIDENTIAL

- 2 -

2. DISCUSSION AND RESULTS OF FEASIBILITY STUDY

A graphite fiber reinforced phenolic slip formulation was prepared which consisted of approximately 45 weight percent graphite powders, 25 weight percent metal carbide powders, 20-25 weight percent of a phenolic-epoxy novalac resin mixture (10 phr-epoxy-novalac) and 10 weight percent of Hercules HMS graphite fibers. The particle sizes of the graphite powders used ranged from less than 0.2 micron (μ) to greater than 20.0 μ . It was observed that a family of particle size distributions could be utilized to effect a 70 to 75 weight percent loaded formulation. Formulations were prepared which contained three different metal carbide powders. These metal carbides were TiC, TaC and ZrC and were obtained from Atlantic Equipment Engineers of Bergenfield, New Jersey. The particle sizes of these metal carbides were specified by the manufacturer to be between 1 and 5 microns.

The general procedure used to fabricate the phenolic precursors to the carbon composite hemispheres consisted of the following sequence of steps. The Hercules HMS continuous tow graphite fibers were chopped to aspect ratios (L/D) of between 500/1 and 100/1. The chopped fibers were mixed with the phenolic and epoxy resin in a methanol-ethanol solvent system. The graphite powders and appropriate metal carbide powders were added, and the viscosity of the formulation increased to the desired level by continuous mixing. Approximately 100 g. of the viscous slip formulation was charged into the hemisphere mold, "B" staged for 0.5 hours at 140°F and compression molded at 325°F and 15 tons platten pressure for one hour. After cooling, the loaded phenolic hemisphere was removed from the mold, post-cured for 2 hours at 450°F and then carbonized to 1400°C. The carbonization cycle required a total of 48 hours. The temperature of the sample was increased only about 20°C per hour up to 1000°C during the carbonization cycle. It was observed that the greatest weight loss of the hemispheres occurred between 760°C and 930°C.

Table 1 compares typical measurements, i.e., rim O.D. and I.D., also wall thickness of the typical phenolic precursor hemispheres and typical carbon composite hemispheres. These measurements indicate that both the precursor hemispheres and the carbon composite hemispheres are virtually distortion free.

Table 1

Hemisphere Measurements

	<u>Typical Phenolic Precursor Hemisphere - TaC and TiC Loaded</u>	<u>Typical Carbon Composite Hemisphere - TaC and TiC Loaded</u>
Rim O.D.	4.189 $\pm$ 0.014 (4)	4.143 $\pm$ 0.038 (4)
Rim I.D.	3.980 $\pm$ 0.007 (4)	3.950 $\pm$ 0.033 (4)
Wall Thickness	0.110 $\pm$ 0.005 (8)	0.100 $\pm$ 0.006 (8)

CONFIDENTIAL

CONFIDENTIAL

- 3 -

Table 2 summarizes the properties of the carbon matrix composite hemispheres. Considering the degree of porosity in the samples, and that no precautions were taken to minimize porosity since it was indicated that void content in the samples was desirable, the property data is very reasonable. The strength properties of the Z-loaded carbon composite are comparable to commercially available bulk graphite

Table 2

Property Data

<u>Carbon Composites - Sample No.</u>	<u>Specific Gravity - (g/cc)</u>	<u>Flexural Strength - (x 10³ psi)</u>	<u>Flexural Modulus (x 10⁶ psi)</u>
1	1.786	3.7	1.1
2	1.636	2.8	1.1
3	1.666	3.7	1.1
4	<u>1.604</u>	<u>2.6</u>	<u>1.1</u>
Averages	1.673	3.2	1.1

CONFIDENTIAL

CONFIDENTIAL

- 4 -

3. CONCLUSIONS

The objectives of the program were accomplished. Several complex, rounded, metal carbide loaded carbon composite structures were fabricated that contained two layers of different metal carbide powders. The carbon matrix hemispheres were subjected to temperatures up to 1400°C. The wall thickness of the layered hemispheres was maintained at about 100 mils. Also the carbon matrix composite hemispheres, by rim O.D. and I.D. measurements, showed little or no distortion and dimensional instability.

CONFIDENTIAL

This document is being sent to the below listed Contractors for the use of the individuals listed. Recipient contractors are requested to validate individual's clearances before forwarding document to same.

DEPARTMENT OF DEFENSE

Director
Defense Advanced Res. Projects Agency
ATTN: STO

Defense Documentation Center
ATTN: TC (2 copies)

Director
Defense Nuclear Agency
ATTN: APSI (Archives)
ATTN: SPAS
ATTN: DDST
ATTN: APTL, Technical Library (2 cys)

Commander
Field Command
Defense Nuclear Agency
ATTN: FCTA-A, Technical Library

Director
Weapons Systems Evaluation Group, ODDR&E
ATTN: Capt. Donald E. McCoy, USN

DEPARTMENT OF THE ARMY

Commander
Aberdeen Research and Development Center
ATTN: AMXRD-XSE For)
ATTN: Dr. Val Kucher

Department of the Army
Harry Diamond Laboratories
ATTN: AMXDO-NP
ATTN: AMXDO-RBF, Dr. Robert Oswald

Commander
Picatinny Arsenal
ATTN: SMUPA-VE, Mr. L. Avrami

Director
U.S. Army Advanced Ballistic Missile
Defense Agency

DEPARTMENT OF THE ARMY

Commander
U.S. Army Materials & Mechanics
Research Center
ATTN: AMXMR-X, Mr. John F. Dignam

Commander
U.S. Army Materiel Command
ATTN: AMCRD-BN-RE-2
Mr. John J. F. Corrigan

DEPARTMENT OF THE NAVY

Commander
Naval Ordnance Laboratory
ATTN: Code 121, Navy Nuclear
Programs Office
ATTN: Code 2302, Mr. Leo F. Gowen

Commander
Naval Ordnance Systems Command
Headquarters
ATTN: Mr. Marlin Kinna

DEPARTMENT OF THE AIR FORCE

AF Materials Laboratory, AFSC
ATTN: Dr. T. Nicholas
ATTN: LNE, Mr. Don Schmidt

AF Weapons Laboratory, AFSC
ATTN: DOGL, Technical Library

Space and Missile Systems Organization
ATTN: RNSE, Capt. Rene
ATTN: RSS

ATOMIC ENERGY COMMISSION

Los Alamos Scientific Laboratory
ATTN: DOC Control for J. W. Taylor

Sandia Laboratories
Livermore Laboratory
ATTN: DOC Control for Dr. T. Gold

This document is being sent to the below listed Contractors for the use of the individuals listed. Recipient contractors are requested to validate individual's clearances before forwarding document to same.

DEPARTMENT OF DEFENSE CONTRACTORS

Aerospace Corporation
ATTN: W. Barry

AVCO
Government Products Group
ATTN: Mr. John Gilmore
E502, Room 1263

Battelle Memorial Institute
ATTN: R. Castle

General Electric Company
Tempo-Center for Advanced Studies
ATTN: DASIAC

Lockheed Missiles & Space Co., Inc.
Division of Lockheed Aircraft Corp.
ATTN: L. Hearne (8114)

Martin Marietta Corporation
Orlando Division
ATTN: Mr. William A. Gray

McDonnell Douglas Corporation
ATTN: Dr. L. Cohen

TRW Systems Group
ATTN: Dr. Paul Nordin

CONFIDENTIAL

- 7 -

CONFIDENTIAL

Security Classification

DOCUMENT CONTROL DATA - R & D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Esso Research and Engineering Company Linden, New Jersey 07036	2a. REPORT SECURITY CLASSIFICATION CONFIDENTIAL	
	2b. GROUP Subject to GDS Declassified on 31 Dec. 79	
3. REPORT TITLE Composite Hemisphere Feasibility Study (U)		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Final Report 16 August 1972 to 16 October 1972		
5. AUTHOR(S) (First name, middle initial, last name) Wilford S. Stewart		
6. REPORT DATE January 1973	7a. TOTAL NO. OF PAGES 10	7b. NO. OF REFS --
8a. CONTRACT OR GRANT NO. DNA001-73-C-0021	8b. ORIGINATOR'S REPORT NUMBER(S) GRX.1CR.73	
b. PROJECT NO. NWE Code N99QAXA	8c. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) DNA-3042F	
c. Task and Subtask Code C308		
d. Work Unit Code 06		
10. DISTRIBUTION STATEMENT		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Defense Nuclear Agency Washington, D.C. 20305	
13. ABSTRACT The feasibility of applying slip casting technology to the fabrication of a complex rounded carbon matrix composite structure having a controlled metal carbide content has been investigated. The slip casting technology is based on the use of certain controlled particle size formulations; i.e., resin, carbon/graphite powders, and reinforcing fiber to fabricate a high strength carbon matrix composite structure. Formulations were prepared in which certain metal carbide powders, TiC, TaC and ZrC, were incorporated into the slip formulation replacing selected fractions of the carbon/graphite powders. Conditions were established for the compression molding and carbonization of Z-loaded carbon hemispheres of approximately 4" O.D. and 100 mils wall thickness. Two different Z-layered structures (50 mils each) were fabricated into a single (100 mil) hemisphere. These carbon hemispheres showed little distortion and surface cracks after heat treatment up to 1400°C.		

DD FORM 1473
1 NOV 65

REPLACES DD FORM 1473, 1 JAN 64, WHICH IS OBSOLETE FOR ARMY USE.

CONFIDENTIAL

Security Classification

CONFIDENTIAL

CONFIDENTIAL

- 8 -

CONFIDENTIAL

Security Classification

14.	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	Carbon Matrix Composites						
	Carbon Hemisphere						
	Metal Carbide Powders						
	Graphite Powders						
	Graphite Fiber						
	Carbonization						
	Slip Casting						

CONFIDENTIAL

CONFIDENTIAL



Defense Threat Reduction Agency

45045 Aviation Drive
Dulles, VA 20166-7517

CPWC/TRC

May 6, 1999

MEMORANDUM FOR DEFENSE TECHNICAL INFORMATION CENTER
ATTN: OCQ/MR WILLIAM BUSH

SUBJECT: DOCUMENT REVIEW

The Defense Threat Reduction Agency's Security Office has reviewed and declassified or assigned a new distribution statement:

- AFSWP-1069, AD-341090, STATEMENT A ✓
- ✓DASA-1151, AD-227900, STATEMENT A ✓
- DASA-1355-1, ~~AD-336443~~, STATEMENT A **OK**
- DASA-1298, AD-285252, STATEMENT A ✓
- DASA-1290, AD-444208, STATEMENT A ✓
- DASA-1271, AD-276892, STATEMENT A ✓
- DASA-1279, AD-281597, STATEMENT A ✓
- DASA-1237, AD-272653, STATEMENT A ✓
- DASA-1246, AD-279670, STATEMENT A ✓
- DASA-1245, AD-419911, STATEMENT A ✓
- DASA-1242, AD-279671, STATEMENT A ✓
- DASA-1256, AD-280809, STATEMENT A ✓
- DASA-1221, AD-243886, STATEMENT A ✓
- DASA-1390, ~~AD-340311~~, STATEMENT A ✓
- DASA-1283, AD-717097, STATEMENT A **OK**
- DASA-1285-5, AD-443589, STATEMENT A ✓
- DASA-1714, AD-473132, STATEMENT A ✓
- DASA-2214, AD-854912, STATEMENT A ✓
- DASA-2627, AD-514934, STATEMENT A ✓
- DASA-2651, AD-514615, STATEMENT A ✓
- ~~DASA-2536, AD-876697, STATEMENT A~~
- DASA-2722T-V3, AD-518506, STATEMENT A ✓
- DNA-3042F, AD-525631, STATEMENT A ✓
- DNA-2821Z-1, AD-522555, STATEMENT A ✓

AD waiting for reply

FAD

If you have any questions, please call me at 703-325-1034.

Arldith Jarrett

ARDITH JARRETT
Chief, Technical Resource Center