

AD

AD 651386

CCL REPORT NO. 228


FINAL REPORT

POLYAMIDE-DIPHENOLIC ACID
WASH PRIMER

BY

STANLEY F. KOUTEK

APRIL 1967



DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

U. S. ARMY COATING & CHEMICAL LABORATORY

Aberdeen Proving Ground
Maryland

TRIMME COPY

DDC AVAILABILITY NOTICE

Qualified requesters may obtain copies of this report from Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314

THE FINDINGS IN THIS REPORT ARE NOT TO BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSITION, UNLESS SO DESIGNATED BY OTHER AUTHORIZED DOCUMENTS.

DESTROY THIS REPORT WHEN IT IS NO LONGER NEEDED. DO NOT RETURN IT TO THE ORIGINATOR.

ACCESSION for		
CFSTI	WHITE SECTION	☒
DDC	DIFF SECTION	☐
UNCLASSIFIED		☐
DDC AVAILABILITY CODES		
DICTIONARY	A-ANL. 666/67	SPECIAL
1		

UNCLASSIFIED

CCL REPORT NO. 228

POLYAMIDE-DIPHENOLIC ACID
WASH PRIMER

FINAL REPORT

BY

STANLEY F. KOUTEK

APRIL 1967

AMCMS CODE NO. 5025.11.29500

DEPARTMENT OF THE ARMY PROJECT NO.
1C024401A329

U. S. ARMY COATING AND CHEMICAL LABORATORY
ABERDEEN PROVING GROUND
MARYLAND

Distribution of this document is unlimited.

UNCLASSIFIED

ABSTRACT

A solid polyamide resin containing diphenolic acid was formulated into one and two package wash primers and evaluated against the control pretreatment primer, MIL-C-15328, for salt spray and water immersion resistance on steel, aluminum and magnesium substrates. Differences in performance between MIL-C-15328 and the two package diphenolic acid wash primer were negligible; however, the one package wash primers were inferior to the two package ones, particularly in water immersion.

TABLE OF CONTENTS

	<u>Page No.</u>
TITLE PAGE	i
ABSTRACT	ii
INTRODUCTION	1
DETAILS OF TEST	1 - 2
DISCUSSION	2
DISTRIBUTION LIST	3 - 5
APPENDIX A	6
Tables I - VII	6 - 14
DD FORM 1473	15

I. INTRODUCTION

Proper substrate preparation is necessary for the successful painting of metal surfaces. In addition to cleaning the metal, a surface treatment, such as a phosphate pretreatment on ferrous metals and chemical or electrolytic treatments on non-ferrous materials, is often employed for maximum corrosion protection. Frequently, a two component pretreatment wash primer, covered by specification MIL-C-15328 is used on these substrates, particularly in applications where special processing equipment required for applying the electrolytic and chemical conversion coatings is not available and/or practical. Although MIL-C-15328 enhances substrate protection and adhesion properties, field experience and laboratory studies indicate the need for improvement with respect to uniformity of performance and improved corrosion resistance on both ferrous and non-ferrous metals. Also desirable would be a one component wash primer. This would result in handling and storage savings as well as minimizing the chances of error in application for those not familiar with the two component system.

II. DETAILS OF TEST

The standard two component wash primer conforming to MIL-C-15328 (Table II) contains polyvinyl butyral as the vehicle. A two component wash primer using a polyamide-diphenolic acid resin as the binder is shown in Table III. According to the manufacturer's literature, this resin possesses outstanding adhesion to a variety of substrates, good resistance properties, rapid solvent release and is readily soluble in the alcohols normally employed in wash primers. Formulas C and D (Table IV and V) are one package materials using the polyamide-diphenolic acid resin at ratios of 4 parts vehicle solids to 1 part acid by weight and 6 parts vehicle solids to 1 part acid by weight, respectively.

Salt spray and aerated water immersion tests were selected as a means of evaluating the primers. The wash primers were applied by spray to a dry film thickness between 0.00025 and 0.0003 inch on 4 by 12 inch panels of ground steel conforming to Federal Test Method Standard No. 141, Method 2011, 24S Aluminum and AZ-31 Magnesium. The panels were vapor degreased and solvent cleaned in accordance with Method 2011 of Federal Test Method Standard No. 141. MIL-C-15328 was applied to magnesium at 1/2 acid strength which is the standard practice to prevent hydrogen evolution. The experimental primers were tested using the formula acid concentration with no gassing observed on magnesium. After approximately 30 minutes air drying, the wash primers were topcoated with 0.001 inch dry film thickness of olive drab semi-gloss rust inhibiting enamel conforming to specification TT-E-485, Type II, and allowed to air dry 96 hours before testing. Panels for salt spray exposure were scored and exposed for a maximum of 500 hours to a 20 percent sodium chloride fog as in Method 6061 of Federal Test Method Standard No. 141, and rated in accordance with Table I. Unscored panels were immersed in aerated

water at $95^{\circ} \pm 2^{\circ}\text{F}$. and examined every 24 hours for a period of 120 hours. For package stability studies, the wash primers were stored at ambient temperatures in pint cans and checked periodically up to 4 months; in addition, the one package primers were stored in glass jars and viscosity determinations and flow outs on glass were made to examine for reactivity and seeding.

III. DISCUSSION

The two component polyamide-diphenolic acid resin primer (Formula B) contains a higher non-volatile content than MIL-C-15328 (Formula A) at a lower viscosity giving the advantage of a larger square foot coverage per gallon at comparable film thicknesses. Settling after 2 months storage was the same for both primers. One package wash primer (Formula C) exhibited seeding after 2 weeks and the viscosity increased steadily until a gummy state was attained in 2 months. In an attempt to improve stability, Formula D was prepared with a reduced phosphoric acid content. Viscosity determinations indicated no significant change after 4 months storage and no evidence of seeding was observed. Table VI lists the physical properties of the wash primers.

Salt spray exposure (Table VII) shows the two component polyamide-phenolic (primer B) to be comparable to MIL-C-15328 on aluminum, to provide better score protection on magnesium but to be slightly inferior in undercutting at the score on steel. One package wash primer C was equal to primer B on steel and aluminum but offered less protection on magnesium. The freshly prepared one package primer D was comparable to MIL-C-15328 on steel, and aluminum but had somewhat more corrosion along the score on magnesium. After 2 months storage the protective properties of primer D decreased.

Water immersion (Table VI) indicated the two component primer B to be inferior on aluminum to MIL-C-15328 and relatively comparable on steel. On magnesium both primers blistered. The one component wash primers were definitely inferior to the two component primers on all three substrates.

From the data, the one component polyamide-diphenolic acid wash primer does not perform satisfactorily, and further investigation appears unnecessary. The two component primer B, although superior to the one component primer and within the performance level of MIL-C-15328, offers no definite improvement over the existing specification wash primer.

DISTRIBUTION LIST FOR AMCMS CODE NO. 5025.11.29500

<u>Department of Defense</u>	<u>No. of Copies</u>
Defense Documentation Center Cameron Station Alexandria, Virginia 22314	20
<u>Department of the Army</u>	
Commanding General U.S. Army Materiel Command ATTN: AMCRD-RS-CM Washington, D. C. 20315	1
Continental Army Command Department of the Army Fort Monroe, Virginia 23351	3
Commanding General U.S. Army Tank-Automotive Command ATTN: Mr. J. Dudzinski Warren, Michigan 48090	1
Commanding Officer Frankford Arsenal ATTN: L7000-64-4 Library Philadelphia, Pa. 19137	1 1
Commanding Officer Yuma Proving Ground, Arizona 85364	1
Commanding General U.S. Army Weapons Command ATTN: AMSWE-RDR Rock Island, Illinois 61200	2
Commanding Officer U.S. Army Materials Research Agency ATTN: Technical Information Center Watertown, Massachusetts 02172	2
Commanding Officer U.S. Army Chemical Research and Development Laboratories ATTN: Librarian Edgewood Arsenal, Maryland 21040	1

DO NOT PHOTOGRAPH THIS PAGE

APPENDIX A

TABLE I

RATING SYSTEM FOR SALT SPRAY EXPOSURE

I. SCORE CONDITION

<u>RATING</u>	<u>RUSTING AND/OR BLISTERING</u>
5	None - 1/32 Inch
4	1/32 - 1/16 Inch
3	1/16 - 1/8 Inch
2	1/8 - 3/16 Inch
1	3/16 - 1/4 Inch
0	> - 1/4 Inch

II. UNDERCUTTING AT SCORE

<u>RATING</u>	
5	None - Intermittent
4	Continuous to 1/16 Inch
3	Continuous 1/16 - 1/8 Inch
2	Continuous 1/8 - 3/16 Inch
1	Continuous 3/16 - 1/4 Inch
0	Continuous > - 1/4 Inch

TABLE 1 - CONTINUED

III. SURFACE CONDITION*

<u>RATING</u>	<u>A. RUSTING ALONE (CORROSION)</u>
5	None
4	A.S.T.M. Photo No. 10 Type 1
3	A.S.T.M. Photo No. 9 Type 1
2	A.S.T.M. Photo No. 8 Type 1
1	A.S.T.M. Photo No. 7 Type 1
0	A.S.T.M. Photo No. 6 Type 1 Or Worse
<u>RATING</u>	<u>B. RUSTING ACCOMPANIED BY BLISTERING</u>
5	None
4	Trace, Less than 5 defects on 4x12 inch panel
3	A.S.T.M. Photo No. 8 Type 2
2	A.S.T.M. Photo No. 7 Type 2
1	A.S.T.M. Photo No. 6 Type 2
0	A.S.T.M. Photo No. 4 Type 2 Or Worse
<u>RATING</u>	<u>C. BLISTERING ALONE</u>
5	None
4	Trace-A.S.T.M. Blister Size 2 on 4x12 inch panel-2 Max. A.S.T.M. Blister Size 4 on 4x12 inch panel-4 Max. A.S.T.M. Blister Size 6 on 4x12 inch panel-6 Max. A.S.T.M. Blister Size 8 on 4x12 inch panel-8 Max.
3	A.S.T.M. Few - Record Blister Size
2	A.S.T.M. Medium - Record Blister Size
1	A.S.T.M. Medium-Dense - Record Blister Size
0	A.S.T.M. Dense - Record Blister Size

*Select Applicable Condition

TABLE I - CONTINUED

IV. SUBSTRATE CONDITION

<u>RATING</u>	<u>PITTING AND/OR CORROSION SPOTS</u>
5	None
4	Trace-A.S.T.M. Blister Size 2 on 4x12 inch panel-2 Max. A.S.T.M. Blister Size 4 on 4x12 inch panel-4 Max. A.S.T.M. Blister Size 6 on 4x12 inch panel-6 Max. A.S.T.M. Blister Size 8 on 4x12 inch panel-8 Max.
3	A.S.T.M. Few - Record Size
2	A.S.T.M. Medium - Record Size
1	A.S.T.M. Medium-Dense - Record Size
0	A.S.T.M. Dense - Record Size

AERATED WATER IMMERSION RATING SYSTEM

<u>SURFACE CONDITION</u>	<u>BLISTERING</u>
5	None
4	Trace - Record Blister Size-A.S.T.M. No.
3	Few - Record Blister Size-A.S.T.M. No.
2	Medium - Record Blister Size-A.S.T.M. No.
1	Medium-Dense - Record Blister Size-A.S.T.M. No.
0	Dense - Record Blister Size-A.S.T.M. No.

TABLE II

FORMULA A - CONTROL

MIL-C-15328 PRIMER, PRETREATMENT FOR METALS

COMPONENT I PIGMENTED POLYVINYL BUTYRAL

<u>INGREDIENT</u>	<u>POUNDS</u>	<u>GALLONS</u>
Polyvinyl Butyral	54.2	5.9
N-Butanol	121.0	17.9
Denatured Alcohol 190°	367.7	54.2
Basic Zinc Chromate	52.1	1.7
Lo-Micron Magnesium Silicate	7.7	0.3
Lampblack	0.6	---
	<u>603.3</u>	<u>80.0</u>

COMPONENT II ACID ACCELERATOR

85% Orthophosphoric Acid	30.8	2.0
Distilled Water	24.7	3.0
Denatured Alcohol 190°	101.6	15.0
	<u>157.1</u>	<u>20.0</u>

Mix 4 parts Component I with 1 part Component II by volume.

TABLE III:

FORMULA B

TWO PACKAGE POLYAMIDE - DIPHENOLIC ACID RESIN PRIMER

COMPONENT I PIGMENTED RESIN

<u>INGREDIENT</u>	<u>POUNDS</u>	<u>GALLONS</u>
Polyamide-Diphenolic Acid Resin	88.0	10.6
99% Isopropanol	348.0	53.0
N-Butanol	20.0	3.0
Basic Zinc Chromate	89.0	2.8
Lo-Micron Magnesium Silicate	13.0	0.6
Lampblack	<u>1.0</u>	<u>---</u>
	559.0	70.0

COMPONENT II ACID ACCELERATOR

85% Orthophosphoric Acid	70.0	5.0
99% Isopropanol	99.0	15.0
N-Butanol	68.0	10.0
Toluol	<u>144.0</u>	<u>20.0</u>
	381.0	50.0

Mix 7 parts Component I with 5 parts Component II by volume.

TABLE IV

FORMULA C

ONE PACKAGE POLYAMIDE - DIPHENOLIC ACID RESIN PRIMER
 RATIO OF 4 PARTS VEHICLE SOLIDS TO 1 PART ACID BY WEIGHT

<u>INGREDIENT</u>	<u>POUNDS</u>	<u>GALLONS</u>
Polyamide-Diphenolic Acid Resin	120.0	14.5
99% Isopropanol	480.0	73.0
N-Butanol	27.0	4.0
Basic Zinc Chromate	62.0	1.9
Strontium Chromate	62.0	1.8
Lo-Micron Magnesium Silicate	18.0	0.7
Charge into pebble mill and grind 4 hours. Premix the following and stir into mill. Continue grinding for 18 hours.		
Distilled Water	23.4	2.7
85% Orthophosphoric Acid	<u>35.0</u> 827.4	<u>2.5</u> 101.1

TABLE V

FORMULA D

ONE PACKAGE POLYAMIDE - DIPHENOLIC ACID RESIN PRIMER

RATIO 6 PARTS VEHICLE SOLIDS TO 1 PART ACID BY WEIGHT

<u>INGREDIENT</u>	<u>POUNDS</u>	<u>GALLONS</u>
Polyamide-Diphenolic Acid Resin	120.0	14.5
99% Isopropanol	480.0	73.0
N-Butanol	27.0	4.0
Basic Zinc Chromate	62.0	1.9
Strontium Chromate	62.0	2.0
Lo-Micron Magnesium Silicate	18.0	0.7
Charge into pebble mill and grind for 4 hours. Premix the following and stir into mill. Continue grinding for 18 hours.		
Distilled Water	33.4	4.0
85% Orthophosphoric Acid	<u>23.8</u>	<u>1.7</u>
	826.2	101.8

TABLE VI

PHYSICAL PROPERTIES OF THE WASH PRIMERS

A. TWO COMPONENT PRIMERS	<u>FORMULA A</u>	<u>FORMULA B</u>
Grind - Hegman Gauge	6	6 1/2
Viscosity - Krebs Units Component 1	60	51
% Non-Volatile - Admixed Primer	18.9	27.8
Pigment Volume Concentration - %	20.6	25.8
Package Condition After 2 Months Storage	Hard, Dry Sediment	Hard, Dry Sediment
B. ONE PACKAGE PRIMERS	<u>FORMULA C</u>	<u>FORMULA D</u>
Grind - Hegman Gauge	6 1/2	6
Initial Viscosity - Krebs Units	55	51
% Non Volatile	35.3	34.2
Pigment Volume Concentration - %	21.5	22.8
Viscosity After Storage - Krebs Units	<u>Can and Glass</u> <u>(same)</u>	<u>Can and Glass</u> <u>(same)</u>
24 Hours	57	51
1 Week	65	51
2 Weeks	87 - Seeding	53 - No Seeding
1 Month	95 - Seeding	53 - No Seeding
2 Months	Gummy	53 - No Seeding
4 Months	---	53 - No Seeding

TABLE VII

A. SALT SPRAY EXPOSURE TEST RESULTS

Formula	SUBSTRATE				<u>STEEL</u>		<u>ALUMINUM</u>				<u>MAGNESIUM</u>			
	A	B	C	D	D	2 Months Storage	A	B	C	D	A	B	C	D
Hours Exposed	500	500	500	500	500	500	500	500	500	500	500	500	500	336
Rating - Score	4	4	4	4	4	4	5	5	5	5	4	1	2	0
Undercutting	4	3	3	4	3	3	5	5	5	5	4	5	5	5
Surface	5	5	5	5	5	5	5	5	5	5	5	5	5	5
Substrate	5	5	5	5	5	5	5	5	5	5	5	5	5	5
B. <u>AERATED WATER IMMERSION</u>														
Hours Exposed	120	120	24	24	24	24	120	24	24	24	24	24	72	24
Surface Blistering	4	5	0	0	0	0	5	0	0	0	0	0	2	0
Size of Blister	48	-	8	8	8	8	-	8	8	8	8	8	8	8

Unclassified

Security Classification

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1 ORIGINATING ACTIVITY (Corporate author) U. S. Army Coating and Chemical Laboratory Aberdeen Proving Ground, Maryland		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3 REPORT TITLE POLYAMIDE-DIPHENOLIC ACID WASH PRIMER		
4 DESCRIPTIVE NOTES (Type of report and inclusive dates) Final		
5 AUTHOR(S) (Last name, first name, initial) Koutek, Stanley F.		
6 REPORT DATE April 1967	7a. TOTAL NO. OF PAGES 19	7b. NO. OF REFS 0
8a. CONTRACT OR GRANT NO. AMCMS Code No. 5025.11.29500	9a. ORIGINATOR'S REPORT NUMBER(S) CCL #228	
b. PROJECT NO. 1C024401A329	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
c.		
d.		
10 AVAILABILITY/LIMITATION NOTICES Qualified requesters may obtain copies of this report from Defense Documentation Center. Distribution of this document is unlimited.		
11 SUPPLEMENTARY NOTES	12 SPONSORING MILITARY ACTIVITY U. S. Army Materiel Command Washington, D. C. 20310	
13. ABSTRACT A solid polyamide resin containing diphenolic acid was formulated into one and two package wash primers and evaluated against the control pretreatment primer, MIL-C-15328, for salt spray and water immersion resistance on steel, aluminum and magnesium substrates. Differences in performance between MIL-C-15328 and the two package diphenolic acid wash primer were negligible; however, the one package wash primers were inferior to the two package ones, particularly in water immersion.		

DD FORM 1473
1 JAN 64

Security Classification

KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Organic Metal Pretreatment Corrosion Resistance						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.