

AD 651 988

DEPARTMENT OF THE NAVY
OFFICE OF NAVAL RESEARCH
WASHINGTON, D.C. 20360

RESEARCH AND DEVELOPMENT
BAUSCH & LOMB INCORPORATED
ROCHESTER, NEW YORK 14602

Contract No. Nonr-4717(00)

LASER DAMAGE STUDY OF THIN FILMS
FOURTH QUARTERLY REPORT
FOR THE PERIOD
1 JANUARY 1967 - 1 APRIL 1967

STATEMENT NO. 1

Distribution of This Document Is Unlimited



ARCHIVE COPY

Laser Damage Study of Thin Films

Contract No.	Nonr-4717(00)
Order No.	ARPA Order 306
Project Code No.	4730
Name of Contractor	Bausch & Lomb Inc. Rochester, New York
Date of Contract	1 April 1965
Amount of Contract	\$58,226.00
Contract Expiration Date	31 March 1967
Project Scientist	Dr. A.F. Turner 716-232-6000 Ext.: 296

FOURTH QUARTERLY REPORT

For the Period: 1 January 1967 - 1 April 1967
Report Prepared by: S. Reformat and A.F. Turner

ABSTRACT

A concentrated effort was made, during the fourth quarterly period, to increase the laser damage threshold, E_t , of aluminum oxide films. This objective was approached empirically. Selected vacuum deposition parameters were varied and the effect on E_t was observed. E_t for $\lambda/4$ and $3\lambda/4$ films were increased by a factor of two over previously reported values. The $\lambda/2$ threshold was increased by a factor of six over the previous value. The $\lambda/4$ threshold spontaneously fell to half its original value two days after manufacture.

TABLE OF CONTENTS

<u>Section</u>	<u>Title</u>	<u>Page</u>
1.0	Introduction	1
2.0	Experimental	2
2.1	Sample Preparation	2
2.2	Optical Thickness and Absorption Measurements	2
3.0	Results	4
3.1	General Observations	4
3.2	Threshold as a function of Pressure	5
3.3	Threshold as a function of Substrate Temperature During Deposition	7
3.4	Threshold as a function of Deposition Rate	7
3.5	Threshold as a function of Substrate Cleaning Procedure and Electron Gun Current and Voltage at Constant Power	8
3.6	Deterioration of Threshold with Time	8
4.0	Recommendations	10
5.0	Conclusion	11
	References Consulted	12

LIST OF FIGURES

<u>Figure</u>	<u>Title</u>	<u>Page</u>
1	Laser Damage Threshold versus Pressure; Substrate Temperature During Deposition: 120°F	13
2	Laser Damage Threshold versus Pressure; Substrate Temperature During Deposition: 170°F	14
3	Laser Damage Threshold versus Pressure; Substrate Temperature During Deposition: 350°F	15
4	Laser Damage Threshold versus Substrate Temperature During Deposition; Pressure: 1.8×10^{-4} torr.	16

LIST OF TABLES

<u>Table</u>	<u>Title</u>	<u>Page</u>
I	Comparison of Substrate Cleaning Procedures	17
II	Index of Refraction versus Wavelength for $\lambda/4$ Al_2O_3 Films	18
III	Results of an Empirical Study to Increase E_t of Al_2O_3 Films	19

1.0 Introduction

The primary contract objective is the measurement of ruby laser energy densities needed to damage commonly used optical materials in thin film form. Since this primary goal has been achieved, we directed our efforts towards the secondary contract objective, which is to increase the established values of thin film laser damage thresholds, E_t (joules/cm²). During the fourth quarterly period, we improved the threshold of aluminum oxide (Al₂O₃) films by varying selected deposition parameters. This report describes the results of our efforts.

2.0 Experimental

2.1 Sample Preparation and testing:

The thin film samples were produced by vacuum evaporation. The deposition was monitored using an optical system in the reflectance mode. The 99.3% pure aluminum oxide used in all the samples reported was obtained from the Norton Company, Worcester, Massachusetts. The white, granular (grain size 0.2 - 0.8mm) material was easily evaporated by the electron gun with 2 kilowatt power level.

The 2" x 2" x 3/32" glass substrates have an index of refraction at $\lambda = 5890\text{\AA}$ of 1.52. The substrate cleaning procedures used are listed in Table I.

The laser damage threshold measurements were performed using a previously reported technique.¹

2.2 Optical thickness and absorption measurements:

The wavelength at which a sample had a $\lambda/4$ optical thickness was the wavelength of minimum transmittance. The wavelength of maximum transmittance was the wavelength at which the sample had a $\lambda/2$ optical thickness. The transmittance measurements were made on the Cary 14 recording spectrophotometer. The $\lambda/4$ transmittance values were used to obtain the index of refraction of the films, using an established method.²

Absorption measurements were made at the $\lambda/2$ position. The transmittance of the film-substrate combination should equal that of the substrate alone at the $\lambda/2$ position assuming a film homogeneous in refractive index. But

absorption reduces the transmittance of the film-substrate combination.

Values of absorption as little as 0.5% can be measured using this method.

3.0 Results

3.1 General Observations:

The damaged areas observed in high threshold ($E_t > 30 \text{ joules/cm}^2$), and low threshold ($E_t < 20 \text{ joules/cm}^2$), films differ in appearance. A typical high threshold damage spot has little symmetry. Its periphery consists of sharp, jagged irregularities. The boundary between the areas of film removal and residual film are sharp and distinct. Also, near threshold, the damage spot "radius" decreases rapidly with decreasing energy density. Low threshold damage spots are generally circular in appearance. Near threshold, the core area of complete film removal is not accompanied by substrate damage. The central area is usually surrounded by an annular ring of partial film removal. The damage spot "radii" of low threshold films decrease more slowly with decreasing energy density than those of high threshold films.

The mechanical durability of selected λ/λ samples was investigated. Essentially, the test apparatus was an eraser under a constant one pound load. To measure the mechanical durability, the number of rubs needed to permanently mar the film were counted. The values generally ranged from 750-1200 rubs. The film with the highest rub resistance also had the highest threshold ($E_t = 40 \text{ joules/cm}^2$). A sample with an amount of absorption that could be detected by visual observation (film was tan colored in transmission), was tested also. It had a rub resistance of only 4 rubs.

The measured index of refraction values range from 1.59 - 1.61 $\pm$ 0.02, in the visible region of the spectrum (Table II). These values were determined from $\lambda/4$ samples produced with the following values of parameters:

Pressure; $P = 1.8 \times 10^{-4}$ torr

Substrate temperature during deposition; $T_s = 170^\circ\text{F}$

Rate of Deposition; $D = 12\text{A/second}$

Electron gun power = 2.0 kilowatts

Previously, aluminum oxide films had been evaporated in an oxygen atmosphere. Oxygen was bled into the vacuum chamber to keep the pressure constant at 1.8×10^{-4} torr during evaporation. We decided to substitute an air bleed for the oxygen and observe the effect on E_t . The values of the other parameters were held constant. The resulting samples were compared and no measurable difference in laser damage threshold or mechanical durability was found. No difference in clarity was detected visually. The values of pressure quoted in this report refer to the residual air pressure in the chamber, not the oxygen pressure.

3.2 Threshold as a function of pressure.

The variations of threshold with pressure for three substrate temperatures during deposition are illustrated in Figures 1 - 3. All the samples measured to obtain these figures were produced at a deposition rate of 12A/second.

For the films tested to obtain Figure 1, the conditions held constant during evaporation were:

Substrate temperature during evaporation; $T_s = 120^\circ\text{F}$

Electron gun power level = 2 kilowatts

Optical thickness = $\lambda/4$ at $\lambda = 5500 \pm 500\text{\AA}$

Because the $\lambda/2$ position was below the glass cut-off, any absorption in these samples was not able to be measured spectrophotometrically. However, no absorption was detected with a visual observation. The maximum uncertainty in E_t is $\pm 1\frac{1}{2}$ joules/cm².

The parameters during evaporation of the samples of Figure 2 were:

$$T_s = 170^\circ\text{F}$$

Electron gun power level = 2 kilowatts, except for the sample deposited at pressure = 2.5×10^{-4} torr. That sample was evaporated with a power level of 2.5 kilowatts to keep $D = 12\text{\AA}/\text{second}$.

Optical thickness = $\lambda/4$ at $\lambda = 6900 \pm 700\text{\AA}$

This graph has a definite maximum of $E_t = 40$ joules/cm². The $\lambda/4$ sample with the highest E_t also had the highest mechanical durability, 1200 rubs. This sample had no measurable absorption. The film evaporated at a pressure = 2.5×10^{-4} torr had 2% absorption at $\lambda = 3600\text{\AA}$. Any absorption in the other samples was unable to be measured on the spectrophotometer. Visually no absorption was detected. The maximum uncertainty in E_t is $\pm 1\frac{1}{2}$ joules/cm².

The parameter values used during production of the samples tested to obtain Figure 3 were:

$$T_s = 350^\circ\text{F}$$

Electron gun power level = 2 kilowatts

Optical thickness = $\lambda/4$ at $\lambda = 5500 \pm 500\text{\AA}$

E_t increases slowly as the pressure is increased. One sample did have, and one did not have measureable absorption. Absorption in the other eight samples was unable to be measured on the spectrophotometer. No absorption was detected by visual inspection. The largest uncertainty in E_t is $\pm 2.5 \text{ joules/cm}^2$.

3.3 Threshold as a function of substrate temperature during deposition, T_s :

The samples tested to obtain Figure 4 were deposited with the following conditions constant:

Pressure = 1.8×10^{-4} torr

D = 12A/second

Electron gun power level = 2.0 kilowatts

Optical thickness = $\lambda/4$ at $\lambda = 6900\text{\AA} \pm 600\text{\AA}$

Figure 4 has a definite maximum $E_t = 40 \text{ joules/cm}^2$. Three of the seven samples tested had no measureable absorption. The other films had no visibly detectable absorption. The maximum uncertainty in E_t is $\pm 1\frac{1}{2} \text{ joules/cm}^2$.

3.4 Threshold as a function of Deposition Rate:

The parameters held constant during production of the samples used in the investigation of deposition rate were:

P = 1.8×10^{-4} torr

$T_s = 170^\circ\text{F}$

Optical thickness = $\lambda/2$ at $\lambda = 6900\text{\AA} \pm 100\text{\AA}$

The effect of deposition rate on threshold is difficult to study, primarily because at certain rates of deposition (3, 2.4 A/second) the resulting films were either absorbing or had a graded index. The most striking result of the deposition rate investigation is the six times increase in threshold

of two $\lambda/2$ samples. At $D = 4$ A/second, $E_t = 42, 45$ were obtained. These two samples had no measureable absorption at $\lambda=6900\text{\AA}$. The maximum uncertainty in E_t was $\pm 1 \text{ joule/cm}^2$.

3.5 Substrate cleaning procedures and electron gun current and voltage at constant power:

The samples used in these investigations were produced under the following conditions:

$$P = 3 \times 10^{-5} \text{ torr}$$

$$T_s = 350^\circ\text{F}$$

$$D = 12 \text{ A/second}$$

$$\text{Electron gun power} = 1.5 \text{ kilowatts}$$

The values of threshold were not altered measurably ($E_t = 10\text{-}12 \text{ joules/cm}^2$) as the substrate cleaning procedure was changed. The variation of electron gun current and voltage at constant power did not change the threshold values, ($E_t = 10\text{-}12 \text{ joules/cm}^2$). The current, voltage and power values investigated were:

<u>Current</u> <u>(amps)</u>	<u>Voltage</u> <u>(volts)</u>	<u>Power</u> <u>(KW)</u>
280	5000	1.4
440	3400	1.5
480	3200	1.5

There was no visible absorption in any of these samples.

3.6 Deterioration of threshold with time:

The $\lambda/4$ sample yielding the highest threshold was produced under the following conditions:

$$P = 1.8 \times 10^{-4} \text{ torr}$$

$$T_s = 170^\circ\text{F}$$

$$D = 12 \text{ A/second}$$

Electron gun power = 2.0 kilowatts

The film was irradiated one day after it was produced and $E_t = 40 \text{ joules/cm}^2$

The sample was tested again two days after it was deposited and the threshold had decreased to 23 joules/cm^2 .

4.0 Recommendations

The following procedure is suggested for future study of threshold versus selected deposition parameters.

1. Establish the degree of absorption and optical thickness of each sample.
2. Establish a family of threshold versus pressure curves at various substrate temperatures during deposition.
3. From the data collected in Step 2, use a bootstrap technique to zero in on the temperature - pressure combination yielding the highest threshold.
4. At the pressure-temperature values found in Step 3, study the effect on E_t of other parameters such as:

deposition rate

evaporation rate

electron gun power level

electron beam spot size

glow discharge

angle of incidence of evaporant on substrate

electron gun current, voltage; constant power

cleaning procedures

5. As the best values of the other parameter are determined, insure that the previously determined pressure - temperature combination still yields the highest threshold value.

5.0 Conslusion

The mechanism of laser damage in thin films is not well understood, nor are the above described effects on the damage threshold of variations in the vacuum coating parameters attendant upon the preparation of aluminum oxide films. An attempt is being made to formulate a model to explain them, and this will be reported upon later.

We thank Duane Waterman and Gibb Nettles for their valuable aid in producing and evaluating the thin film samples.

This report was written by S. Refermat and A.F. Turner.

References Consulted

1. Turner, A.F., et. al., Office of Naval Research Contract Nonr 4717(00),
Final Technical Report, pages 3 - 4, (1966).
2. Chang, L., 9th Quarterly Report to Fort Belvoir, Contract DA-44-009-AMC-124
(T) Mod. 2, (1965).

LASER DAMAGE THRESHOLD vs. PRESSURE

$T_s = 120^\circ \text{ F}$

$D = 12 \text{ A/SECOND}$

OPTICAL THICKNESS = $\lambda/4$ at $\lambda = 5500 \pm 500 \text{ \AA}$

⊙ - VISUALLY ABSORPTION FREE




FIG. 1

LASER DAMAGE THRESHOLD vs. PRESSURE

$T_s = 170^\circ F$

$D = 12 A / SEC$

OPTICAL THICKNESS = $\lambda/4$ at $\lambda = 6900 \pm 700 A$

○ - VISUALLY ABSORPTION FREE

◇ - ABSORPTION $< 0.5\%$ at $\lambda = 3600 A$

□ - ABSORPTION = 2.0% at $\lambda = 3600 A$




FIG. 2

LASER DAMAGE THRESHOLD vs. PRESSURE

$T_s = 350^\circ \text{F}$

$D = 12 \text{ A/SECOND}$

OPTICAL THICKNESS $= \lambda/4$ at $\lambda = 5500 \pm 500 \text{ \AA}$

$\odot$ -VISUALLY ABSORPTION FREE

$\diamond$ -ABSORPTION $< 0.5\%$ at $\lambda = 3600 \text{ \AA}$

$\square$ ABSORPTION $> 0.5\%$ at $\lambda = 3600 \text{ \AA}$




FIG. 3




FIG. 4

TABLE I

COMPARISON OF SUBSTRATE CLEANING PROCEDURES

Ultra-Sonic Cleaning Method	Hand Cleaning Method
1. Ultra-sonic rinse in distilled water and detergent (orvious) at temperature = 150⁰ F 2. Ultra-sonic rinse in distilled water at T = 150⁰F. 3. Rinse in tap water at 120⁰F 4. Rinse in alcohol 5. Rinse in the isopropyl alcohol degreaser at 180⁰F	1. Rinse in tap water. 2. Polish with zirconium dioxide and wet cotton. 3. Rinse in tap water. 4. Dry with a soft, lint-free cloth

TABLE II
Index of Refraction versus
Wavelength*

Wave- length (μ)	Index†
0.44	1.59
0.55	1.61
0.69	1.60

*Samples used in index determinations were produced at:

Pressure = 1.8×10^{-4} torr

Substrate Temperature

During Deposition = 170°F

Deposition Rate = 12 Angstroms/second

Optical Thickness = $\lambda/4$ at wavelength indicated

†Index value uncertainty = ± 0.02

TABLE III

Results of An Empirical Study to Increase E_t

CODE	SAMPLE	E_t (joules/cm ²)	OPTICAL THICKNESS
1 2 3	12/27/65 #2 1/4/67 #1 1/11/67 #1	26 22 40	$\lambda/4$ +
1 2 3 4	2/21/66 #34 2/8/67 #1 2/15/67 #1 3/22/67 #2	7* 11 16 40-45	$\lambda/2$ +
2 3	1/4/67 #3 2/16/67 #2	15 12	$6\lambda/4$ * $6\lambda/4$
1 3	3/2/66 #21 3/17/67 #1	4.6 9.0	$36\lambda/4$ + $33\lambda/4$

*On silica substrate

+ λ = 6900A

* λ = 5100A

CODE FOR TABLE III

1. Oxygen Pressure = 1.8×10^{-4} torr.

Substrate Temperature
During Deposition $T_s = 350^\circ\text{F}$

Deposition Rate: $D = 12$ Angstroms/second

2. Residual Pressure: $P = 1.8 \times 10^{-4}$ torr.
 $T_s = 350^\circ\text{F}$

$D = 12$ A /second

3. $P = 1.8 \times 10^{-4}$ torr.
 $T_s = 170^\circ\text{F}$

$D = 12\text{A}$ /second

4. $P = 1.8 \times 10^{-4}$ torr.

$T_s = 170^\circ\text{F}$

$D = 4\text{A}$ /second

BLANK PAGE

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Bausch & Lomb Incorporated Rochester, New York 14602		2a. REPORT SECURITY CLASSIFICATION Unclassified	
		2b. GROUP	
3. REPORT TITLE Laser Damage Study of Thin Films			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Final Quarterly Report, 1 January 1967 - 1 April 1967			
5. AUTHOR(S) (Last name, first name, initial) Turner, Arthur F. and Refermat, Stanley J.			
5. REPORT DATE 1 April 1967		7a. TOTAL NO. OF PAGES 24	7b. NO. OF REFS 2
8a. CONTRACT OR GRANT NO.		8a. ORIGINATOR'S REPORT NUMBER(S) Final Quarterly Report 1 April 1967	
b. PROJECT NO.			
c.		8b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.			
10. AVAILABILITY/LIMITATION NOTICES			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Commanding Officer U.S. Navy Regional Finance Center Third Avenue and 29th Street Brooklyn, New York 11232	
13. ABSTRACT A concentrated effort was made, during the fourth quarterly period, to increase the laser damage threshold, E_t , of aluminum oxide films. This objective was approached empirically. Selected vacuum deposition parameters were varied and the effect on E_t was observed. E_t for $\lambda/4$ and $3\lambda/4$ films were increased by a factor of two over previously reported values. The $\lambda/2$ threshold was increased by a factor of six over the previous value. The $\lambda/4$ threshold spontaneously fell to half its original value two days after manufacture.			

14

KEY WORDS

LINK A

LINK B

LINK C

ROLE

WT

ROLE

WT

ROLE

WT

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., Interim, progress, summary, annual, or final. Give the inclusive date when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.