

AD 665788

PASSIVATION OF CREVICES
DURING ANODIC PROTECTION

Technical Report No. 4

Office of Naval Research
Contract Number - Nonr-591(17)

W. D. France, Jr.

M. D. Greene


Rensselaer Polytechnic Institute
Troy, New York

February, 1963

Reproduction in whole or in part
is permitted for any purpose of
the United States Government

Reproduced by the
CLEARINGHOUSE
for Federal Scientific & Technical
Information Springfield Va 22151

This document has been approved
for public release and sale; its
distribution is unlimited.



PASSIVATION OF CREVICES DURING ANODIC PROTECTION

W. D. France, Jr.*

N. D. Greene

Corrosion Research Laboratory
Materials Research Center
Rensselaer Polytechnic Institute
Troy, New York

Publication rights reserved by the National Association of Corrosion Engineers. Permission is granted to other journals to publish reviews, condensations or abstracts prior to publication of the paper by NACE, provided these reviews, condensations or abstracts do not exceed 500 words or one-third of the total contents of the original paper, whichever is shorter, and provided acknowledgment is given of the previous presentation of the paper at the 1968 Conference, National Association of Corrosion Engineers, Cleveland, Ohio, March 18-22, 1968.

* Present Address:

Chemistry Department,
Research Laboratories,
General Motors Corporation,
Warren, Michigan. 48090

ABSTRACT

The protection of crevices poses an important problem in industrial applications of anodic protection. Experimental studies with a special crevice assembly have shown that the interiors of crevices often remain active and corrode at a rapid rate. These experiments, together with theoretical analyses, demonstrate that the ability to passivate crevices during anodic protection is controlled by electrolyte characteristics, crevice geometry, and the electrochemical behavior of the protected metal. Of these, critical anodic current density, i_c , is the most important parameter.

Anodic protection, first demonstrated by Edeleanu in
(1)
1954, has been widely applied as an industrial corrosion
(2-5)
control method. Although the major advantages and limita-
tions of this technique have been discussed in considerable
(6-8)
detail, the problems associated with the protection of
crevices have been largely ignored. Crevice effects have
probably not been troublesome in the past, since anodic
protection has been generally restricted to storage tanks.
(2-5)
However, in more complex plant structures, crevices and
other narrow electrolyte paths are invariably present.
Examples include: threaded pipe sections, bolt and rivet
holes and flanges. Also, unintentional crevices associated
with porous welds and other surface defects are more likely
in large systems.

(9)
In a previous study, it was shown that a large poten-
tial gradient exists in crevices during potentiostatic anodic
polarization. This gradient, caused by the high resistance
of the narrow electrolyte path, often prevents the passivation
of the crevice interior. Thus, although the exterior is main-
tained in the passive potential region, the interior remains
active and rapidly corrodes.

The purpose of this investigation is to determine the factors influencing the anodic protection of crevices. This problem may be viewed as a special case of throwing power,^(6,7,10) or the uniformity of current distribution.

EXPERIMENTAL

Most experiments were conducted with the special plexiglas electrode assembly illustrated in Figure 1. A cylindrical metal electrode, 2.65 inches in length, was press-fitted into the upper portion of the plastic mount, and attached to the external circuit by means of a Stern-Makrides Teflon gasket.⁽¹¹⁾ The electrode was centered in the precision-bored orifice with a measuring microscope (± 0.0001 inch) to insure a uniform annular crevice opening of 0.009 inch. Geometrically, this assembly resembles a large bolted or riveted section.

The potential of the crevice exterior (bottom face of the cylindrical electrode) was measured with a glass Luggin-Haber probe, while the potentials within the crevice were determined by four internal Luggin-Haber probes at 0.5 inch intervals. Connection to these probes was achieved by a thistle tube-salt bridge sealed with a quartz wick. All potentials were measured relative to a saturated calomel electrode (S.C.E.).

Specimens of Type 304 and CF-8 stainless steel (Table I), water-quenched after 1 hour at 1095°C (2000°F), were used in these experiments. These were abraded on 2/0 emery paper, ultrasonically cleaned in detergent solution, rinsed in double-distilled water, and dried.

All tests were conducted in a multineck polarization cell containing hydrogen-saturated normal sulfuric acid at 25±°C. Solution level was maintained slightly above the uppermost probe opening. The potential of the crevice face was maintained constant within ± 1 mv. with an electronic potentiostat and the potentials of the crevice interior were determined. The polarization cell, auxiliary electrodes and related instrumentation have been described.⁽¹¹⁻¹³⁾

In addition to the above experiments, potentiostatic anodic polarization measurements were performed in a conventional manner.^(1,6,7,13) Specimens were preexposed for one hour, followed by 50 millivolt potential-step polarization at 5 minute intervals in hydrogen-saturated acid.

RESULTS

The potential distribution along CF-8 and Type 304 stainless steel crevices, 0.009 inch wide, as a function of external control potentials, are shown in Figures 2 and 3. These potential gradients are markedly different in spite of the similarities in crevice width and geometry. However, the

respective anodic polarization curves show that the principal difference between these alloys is the value of critical anodic current density which is $2000 \mu\text{a}/\text{cm}^2$ for the CF-8 and $76 \mu\text{a}/\text{cm}^2$ for Type 304. Included in these Figures are current density distributions along the crevice at a 0.20 volt control potential. Such plots are constructed from the potential gradient and anodic polarization curve data.^(7,10) Considering the 0.20 potential gradient of Figure 2, each crevice length defines a unique potential which has a corresponding current density value on the anodic polarization curve. For example, at 0.42 inch the crevice potential is -0.300 volt which corresponds to $2000 \mu\text{a}/\text{cm}^2$ on the anodic polarization curve. Other points obtained in the same way define the complete current density distribution. At more noble control potentials the current density maximum moves to longer crevice lengths (e.g., 1.03 inch at 0.60 volts) and this shift increases the passive crevice length (L_p). It is evident in Figure 3 that the entire length of the Type 304 specimen is completely passive at a control potential of 0.20 volt.

The electrochemical data in Figures 2 and 3 are consistent with the appearances of specimens after extended testing. A specimen of CF-8 tested 100 hours at a control potential of 0.6 volt vs S.C.E. is shown in Figure 4. The unattacked or passive region is visible on the left, while the position of the current

density maximum is indicated by the area of severe attack. Note that corrosion diminishes to the right of this point (slight grain faceting) as expected from the data in

Figure 2.

Crevice width also has a pronounced influence, as shown in Figure 5. In this experiment, the potential at a depth of 0.25 inch was monitored at a constant external control potential of 0.20 volt. Crevices less than 0.0015 inch wide remain active (i.e., below 0.02 volt), while crevices wider than 0.002 inch are maintained passive to a depth of 0.25 inch.

DISCUSSION

The above results demonstrate that crevice potential is not an absolute value, but depends on crevice dimensions as well as anodic polarization characteristics. It is possible to relate these terms to the crevice length which can be passivated using the Fokin and Timonin analysis of potential distribution along thin wires polarized in relatively large diameter tubes.⁽¹⁰⁾

During polarization, assuming the average current density under the polarization peak is $1/2 i_c$, the total measured current, I , is:

$$I = 1/2 i_c \pi d L_a + i_p \pi d L_p + i_p \pi d^2/4 \quad (1)$$

$$= 1/2 i_c \pi d L_a \text{ for } i_c \gg i_p \quad (1a)$$

where i_c = critical anodic current density
 d = specimen diameter
 L_a = active length
 i_p = passive current density
 L_p = passive length

From Ohm's Law and the resistivity equation these authors developed an equation for the passive length obtained by anodic protection. In terms of experimentally measurable values:

$$L_p = \frac{\Delta E_p \sqrt{D^2 - d^2}}{2 \sqrt{i_c \Delta E_a \rho d}} \quad (2)$$

where D = orifice diameter = 0.387 inch = 0.984 cm
for crevice assembly.
 d = specimen diameter = 0.369 inch = 0.936 cm
for crevice assembly
 ρ = solution resistivity = 4.7 ohm-cm for
1N(4.8%) H_2SO_4 at 25°C⁽¹⁴⁾
 i_c = critical anodic current density
 i_c (CF-8) = 2000 $\mu a/cm^2$ and
 i_c (304) = 76 $\mu a/cm^2$
 ΔE_p = passive potential range = $E_{control} - 0.02$ volt*
 ΔE_a = active potential range (defined by
polarization peak) ΔE_a (CF-8) = 0.42 volt
and ΔE_a (304) = 0.36 volt

When $D \gg d$ this equation can be simplified and reduced

* The lower limit of the passive potential range is taken arbitrarily from anodic polarization data as 0.02 volt where the corrosion rate for both stainless steel alloys is $2 \mu a/cm^2 \approx 1$ MPY.

to Edeleanu and Gibson's relation for wires polarized in tubes, which showed excellent correlation with experimental data.⁽⁷⁾ However, the present work represents the first experimental test of the unmodified Equation 2, where $D \approx d$ for very narrow electrolyte paths.

Substituting the appropriate values for each alloy into the equation yields:

$$\text{for CF-8: } L_p(\text{cm}) = 2.42 \Delta E_p \quad (3)$$

$$\text{for 304 : } L_p(\text{cm}) = 13.4 \Delta E_p \quad (4)$$

In Table II, values of L_p calculated from these equations are compared with experimental measurements (i.e., crevice lengths at 0.02 volt) from Figures 2 and 3. The analysis yields excellent correlation for all values when portions of the crevice remain active at potentials below 0.02 volt.* However, when the entire crevice length becomes completely passive (i.e., $L_p = L$ crevice) as in the case of Type 304 at control potentials above 0.10 volt, the Fokin-Timonin expression (Equation 2) is no longer applicable for analyzing the potential gradient curves, and another relationship must be developed to determine the crevice length which can be maintained passive.

* These results are also in good agreement with the long term exposure test (Figure 4). The unattached region measures approximately 0.4 inch, which compares favorably with the experimental and calculated values of 0.50 and 0.55 inch, respectively.

The reason is evident from Equation 1a which becomes equal to zero when the active length $L_a=0$. For this situation, the second two terms of Equation 1 must be considered. For the crevice assembly $dL_p \gg d^2/4$ and therefore the current for a completely passivated crevice is:

$$I = i_p \pi d L_p \quad (5)$$

Then, from Ohm's Law and the resistivity equation, the passive length maintained by anodic protection is determined:

$$L_p = 1/2 \sqrt{\frac{\Delta E_p (D^2 - d^2)}{i_p d \rho}} \quad (6)$$

where $i_p = 2 \mu a/cm^2$ for Type 304 stainless steel.

The passive crevice length calculated from this equation for Type 304 alloy controlled at 0.20 volt shows good correspondence in Table II with the extrapolation of the experimental data to 0.02 volt. Comparison of these results with other data in the table clearly illustrates the extraordinary lengths which can be maintained passive once complete passivity is obtained. Similar observations have been noted in other anodic protection studies. (6, 7)

Methods for improving the feasibility of anodically protecting structures containing crevices follow directly from Equation 2. Since localized attack is avoidable only when the passive length equals or exceeds the crevice length, variables which increase the numerator and decrease the denominator of

this equation are most advantageous. However, there are practical limitations which should be noted. The environment in industrial applications is generally fixed and therefore ρ is constant. Also, engineering designs, such as threaded sections or rivet construction, seldom can be widened to increase the $(D^2 - d^2)$ term. Obviously, any attempts to eliminate crevices with sealants or coatings must be complete, since very narrow crevices are the worst cases. In view of these restrictions, proper material selection is essential. Considering anodic polarization characteristics, the transpassive region (e.g., $E > 0.80\text{v}$ in Figure 2) where corrosion rate increases rapidly is the upper limit for control potentials. In a given environment, this potential is similar for most stainless steels, but may be considerably more noble or nonexistent for other materials such as titanium. The most important constant in Equations 3 and 4 is the critical anodic current density which can vary by orders of magnitude for different materials. In fact, other things being equal, a 10-fold decrease in i_c increases the passive length by a factor of 3.16. Thus, critical anodic current density is doubly important, since it also represents the magnitude of current necessary to achieve passivity during anodic protection. ^(1,6-8)

In determining the passive length from Equation 2 the most subtle restriction is the arbitrary definition of passivity

involved in selecting the upper limit of ΔE_a . This potential range is similar for most stainless steels and provides only a minor contribution to the constants of Equations 3 and 4, but its interrelationship with ΔE_p does influence the magnitude of L_p . Choosing a smaller ΔE_a increment increases ΔE_p , thereby making the calculated and experimental passive lengths larger, although still in agreement. For example, in the 0.20 volt controlled potential experiment with Type 304, the passive crevice length calculated from Equation 4 is 0.95 inch. However, selecting $\Delta E_a = 0.24$ volt instead of 0.36 volt defines the lower passive potential limit at -0.10 volt, rather than 0.02 volt used in these experiments, and then $L_p = 1.95$ inch. Since the requirement for the complete passivity observed during this test is $L_p = L_{\text{crevice}} = 2$ inches, this greater L_p value is more nearly the actual passive length. However, this example illustrates the preference for overestimating ΔE_a , since a safety factor is provided in predicting the crevice length which can be passivated.

SUMMARY

1. The ability to passivate narrow crevices is an important factor in practical applications of anodic protection. In long, narrow crevices, internal portions of crevices often remain

active, resulting in rapid, localized corrosion.

2. Experiments with an anodically protected crevice assembly have shown that the Fokin-Timonin equation accurately predicts the length of the passive zone in partially protected, narrow crevices.
3. In selecting materials for anodic protection applications, it is important to choose alloys possessing small critical anodic current densities. This reduces the current requirements for initial passivation and improves the crevice-passivating ability of the system.

ACKNOWLEDGMENT

The authors thank the Office of Naval Research for their support of this study. We also gratefully acknowledge partial assistance from unrestricted funds granted by Gulf Research and Development Company, and Continental Oil Company.

REFERENCES

1. C. Edeleanu, Metallurgica, 50, 113 (1954).
2. D. A. Shock, O. L. Riggs, Jr., and J. D. Sudbury, Corrosion, 16, 55t (1960).
3. A. O. Fisher and J. F. Brady, Corrosion, 19, 37t (1963).
4. J. C. Redden, Materials Protection, 5, 51 (Feb., 1966).
5. L. D. Perrigo, ibid, 73 (March, 1966).
6. J. D. Sudbury, O. L. Riggs, Jr. and D. A. Shock, Corrosion, 16, 47t (1960).
7. C. Edeleanu and J. G. Gibson, Chemistry and Industry, 30 (March 11, 1961).
8. M. G. Fontana and N. D. Greene, Corrosion Engineering, McGraw-Hill, New York, 1967, pp. 210-214, 338, 339.
9. N. D. Greene, W. D. France, Jr., and B. E. Wilde, Corrosion, 21, 275 (1965).
10. M. N. Fokin and V. A. Timonin, Doklady Akademii Nauk, SSSR, 164, 150 (1965).
11. M. Stern and A. C. Makrides, J. Electrochemical Society, 107, 782 (1960).
12. M. Stern, ibid, 102, 609 (1955).
13. N. D. Greene, Experimental Electrode Kinetics, Rensselaer Polytechnic Institute, Troy, New York, 1965.
14. A. N. Campbell, E. M. Kartzmark, D. Bisset, and M. E. Bednas, Can. J. Chem., 31, 303 (1953).

TABLE I
ALLOY COMPOSITIONS
(Weight Percent)

<u>CF-9</u>		<u>Type 304</u>	
Cr	18.08	Cr	18.34
Ni	12.20	Ni	9.28
C	0.08	C	0.08
Mn	0.74	Mn	0.83
N	0.05	S	0.014
Si	1.22	Si	0.65
Fe	Balance	P	0.020
		Mo	0.11
		Cu	0.19
		Fe	Balance

TABLE II
Comparison of Calculated and Experimental
Protected Crevice Lengths

Alloy	E_{control} (volts)	$\Delta E_p = E_{\text{control}} - 0.02$ (volts)	L_p (inches) Experimental	L_p (inches) Calculated
CF-8	0.02	0	0	0.
	0.20	0.18	0.13	0.17
	0.40	0.38	0.27	0.36
	0.60	0.58	0.50	0.55
	0.80	0.78	0.81	0.74
	1.00	0.98	0.98	0.93
304	0.02	0	0	0
	0.10	0.08	0.37	0.42
	0.20	0.18	8.0*	8.3**

* Obtained by extrapolating potential gradient data to 0.02 volt.

** Calculated from Equation 6.

FIGURES

- Figure 1 Plexiglas Electrode Assembly for Crevice Studies. Orifice dimensions: 0.387 inch X 2.50 inch. Internal Probe Openings Spaced at 0.5 inch Intervals.
- Figure 2 Crevice Potential Variation of CF-8 Stainless Steel Together with Anodic Polarization Curve and Calculated Current Distribution Hydrogen-Saturated $\bar{N}$ H₂SO₄ at 25°C. Crevice Width: 0.009 inch.
- Figure 3 Crevice Potential Variation of Type 304 Stainless Steel Together with Anodic Polarization Curve and Calculated Current Distribution, Hydrogen-Saturated $\bar{N}$ H₂SO₄ at 25°C. Crevice Width: 0.009 inch.
- Figure 4 Crevice Specimen of CF-8 Maintained at a Control Potential of 0.60 Volt (vs S.C.E.) for 75 Hours in $\bar{N}$ H₂SO₄, 25°C. Crevice Face (Bottom) on Left. Magnification 1.5X.
- Figure 5 Crevice Potential Variation at a Depth of 0.25 inch as a Function of Crevice Width. Material: CF-8; Control Potential: 0.20 Volt (vs S.C.E.) NH₂SO₄ at 25°C.




FIG. I




FIG.2






FIG. 3




FIG. 4




FIG.5

Unclassified

Security Classification

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Rensselaer Polytechnic Institute Troy, New York		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3. REPORT TITLE Passivation of Crevices During Anodic Protection		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Report #4		
5. AUTHOR(S) (Last name, first name, initial) France, W. DeWayne, Jr., Greene, Norbert D.		
6. REPORT DATE February, 1968	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS
8a. CONTRACT OR GRANT NO. Nonr-591(17)	8a. ORIGINATOR'S REPORT NUMBER(S) Research Project 438.92 Technical Report #4	
b. PROJECT NO. PR 007-08-01		
c.		
d.	8b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. AVAILABILITY/LIMITATION NOTICES Qualified requesters may obtain copies of this report from D.D.C.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Office of Naval Research, Washington, D. C. 20360	
13. ABSTRACT The protection of crevices is an important problem in the application of anodic protection. Theoretical analyses and experimental studies with a special crevice assembly show that the crevice-passivating ability of a system is controlled by electrolyte characteristics, crevice geometry, and the electrochemical behavior of the protected metal.		

DD FORM 1473
1 JAN 64

Security Classification

14

KEY WORDS

Crevice Corrosion
Anodic Protection
Potentiostatic Polarization
Stainless Steel

LINK A

ROLE

WT

LINK B

ROLE

WT

LINK C

ROLE

WT

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. The security classification cannot be selected without classification. The security classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY LIMITATION NOTICES:** Enter any limitation on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, roles, and weights is optional.