

AD 685146


FOREIGN TECHNOLOGY DIVISION



A METHOD OF INCREASING THE WEAR RESISTANCE AND
CORROSION RESISTANCE OF METALS AND ALLOYS BY
SATURATING THEIR SURFACE LAYERS WITH HALIDES

by

B. P. Grigor'yev



APR 15 1969

Distribution of this document is unlimited.
It may be released to the Clearinghouse,
Department of Commerce, for sale to the
general public.

Reproduced by the
CLEARINGHOUSE
for Federal Scientific & Technical
Information Springfield Va. 22151

EDITED TRANSLATION

A METHOD OF INCREASING THE WEAR RESISTANCE AND
CORROSION RESISTANCE OF METALS AND ALLOYS BY
SATURATING THEIR SURFACE LAYERS WITH HALIDES

By: B. P. Grigor'yev

English pages: 2

SOURCE: Patent No. 189278 (Appl. No. 837211/22-2,
May 20, 1963), 1 page.

Translated by: H. Peck/TDBRO-2

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:

TRANSLATION DIVISION
FOREIGN TECHNOLOGY DIVISION
WP-AFB, OHIO.

DATA HANDLING PAGE				
01-ACCESSION NO. TA8001410	98-DOCUMENT LOC	20-TOPIC TAGS corrosion rate, impregnation, halide, metal surface, wear resistance		
09-TITLE A METHOD OF INCREAS- ING THE WEAR RESISTANCE AND CORROSION RESITANCE OF METALS AND ALLOYS BY SATURATING THEIR SURFACE *				
47-SUBJECT AREA 11, 13				
42-AUTHOR/CO-AUTHORS GRIGOR'YEV, B. P.			10-DATE OF INFO 20MAY63	
43-SOURCE PATENT 189278 (837211/22-2) CLASS 48d ¹ , 15/00 48b, 9/04 (RUSSIAN) FTD			68-DOCUMENT NO. HT-23-373-68	
			69-PROJECT NO. 6010801	
63-SECURITY AND DOWNGRADING INFORMATION UNCL, 0			64-CONTROL MARKINGS NONE	97-HEADER CLAS UNCL
70-REEL/FRAME NO. 1886 0470	77-SUPERSEDES	76-CHANGES	40-GEOGRAPHICAL AREA UR	NO. OF PAGES 2
CONTRACT NO.	X REF ACC. NO. 65-AP7002611	PUBLISHING DATE 94-00	TYPE PRODUCT Translation	REVISION FREQ NONE
02-UR/0000/66/000/000/0001/0001			ACCESSION NO.	
ABSTRACT This Author Certificate introduces a method for improving the wear and corrosion resistance of metals and alloys by surface impregnation with halides. Zinc, lead, and aluminum or their alloys are treated in a solution of iodine in acetone, and copper alloys are treated in a solution of bromine in glycerin. *09 Title cont. - LAYERS WITH HALIDES				

A METHOD OF INCREASING THE WEAR RESISTANCE AND CORROSION
RESISTANCE OF METALS AND ALLOYS BY SATURATING THEIR
SURFACE LAYERS WITH HALIDES

B. P. Grigor'yev

The saturation of metal and alloy surfaces with sulfur, bromine, chlorine and other elements for increasing the wear resistance and improving the anticorrosion properties of friction surfaces is known. Here, the saturation is done from solid, gaseous and liquid media at a high temperature.

The essence of the described method consists in the fact that the surfaces of the metals and alloys are processed by solutions of iodine or bromine in organic solvents. The surface layers of alloys, zinc, lead or aluminum are saturated by a solution of iodine in acetone, and copper alloys are saturated by a solution of bromine in glycerine.

The technological process of the treatment of B-2 brand babbit bushings, for example, consists of the following operations. The bushings are heated up to 50-60°, moistened with a solution of iodine in acetone, dried and polished lightly with a cloth or burlap until a metallic shine is obtained. This treatment cycle is repeated twice. After the second cycle the bushings are lubricated with hot mineral oil and are aged for sometime.

Subject of Invention

A method of increasing the resistance to wear and the stability of metals and alloys by saturating the surface layers with halides,

differ in that the metals or alloys are processed by solutions of iodine or bromine in organic solvents, for example, iodine in acetone for alloys of zinc, lead and aluminum or bromine in glycerine for copper alloys.