

AD 693509

FTD-HT-23-609-68


FOREIGN TECHNOLOGY DIVISION



STABILITY OF ORTHOTROPIC VISCOELASTIC SHELLS

By

P. M. Ogibalov and M. A. Koltunov



OCT 1 1969

Distribution of this document is unlimited. It may be released to the Clearinghouse, Department of Commerce, for sale to the general public.

23-609-68

# EDITED TRANSLATION

STABILITY OF ORTHOTROPIC VISCOELASTIC SHELLS

P. M. Ogibalov and M. A. Koltunov

English pages: 11

SOURCE: Prikladnaya Mekhanika (Applied Mechanics). Vol. 3, Issue 8, 1967, pp. 1 - 10.

Translated Under: Contract P33657-68-D-0966 P002

DATA LABELING PAGE	
01-ACCESSION NO. TP0000091	02-DOCUMENT LOC. shell structure stability, glass fiber, reinforced plastic, shell buckling, elastic plate, elasticity theory
06-TITLE STABILITY OF ORTHOTROPIC VISCOELASTIC SHELLS	
07-SUBJECT AREA 20, 11	
03-AUTHOR CO-AUTHORS OGI BALOV, P. M.; KOLTUNOV, M. A.	04-DATE OF INFO -----67
05-SOURCE PRIKLADNAYA MEKhanIKA (RUSSIAN)	06-SECURITY NO. HT-23-609-68
	07-PROJECT NO. 72301-78
01-SECURITY AND DOWNGRADING INFORMATION UNCL. O	04-CENTRAL MARKING NONE UNCL
08-REEL FRAME NO. 1889 0844	09-ORIGINATOR AREA UR
09-STARTING PAGE NO. P33657-68-D-0866 P002	10-PUBLICATION DATE 04-00
11-STEP NO. 02-UR/0198/67/003/008/0001/0010	12-TRANSLATION NONE
ABSTRACT	
<p>(U) The authors review the basic principles of the closed quasilinear quadratic theory of viscoelasticity of physically nonlinear media as proposed by A. A. Il'yushin and F. M. Ogibalov. A system of nonlinear equations of bending and stability is proposed for flexible (i.e. with regard to geometric nonlinearity) shallow plates and shells made from orthotropic materials with linear properties (fiberglass-reinforced plastics). It is assumed that the hypothesis of straight normals is applicable to these plates and shells. It is also assumed that stresses normal to the middle surface are insignificantly small compared to the other components and that the shells and plates remain orthotropic throughout the entire deformation process. A method of solving the proposed equations is outlined and illustrated by analysis of the stability of a rectangular orthotropic plate of slightly curved panel of fiberglass-reinforced plastic with given stress relaxation curves. The results agree satisfactorily with experimental data on creep in a square plate hinged at the edges. Methods are also given for determining the upper and lower critical loads as related to the loading conditions and the critical time. A viscoelastic solution is found by the proposed method for the problem of stability of a compressed cylindrical shell and compared with an elastic solution found by the Ritz method. Orig. art. has: 36 formulas.</p>	

THIS TRANSLATION IS A REPRODUCTION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES APPLICATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION.

PREPARED BY:  
TRANSLATION DIVISION  
FOREIGN TECHNOLOGY DIVISION  
AFSC

FTD - HT - 23-609-68

Date 30 Jun 19 69

FORM 4 (FOR ORDINARY USE ONLY)

Some nonlinear effects of creep for a noncompressible medium can be described by the equations

$$\epsilon(t) = \psi(\sigma) + \int_0^t K(t-s)\psi(\sigma(s))ds \quad \psi(\sigma) = \sigma(t) + \int_0^t K(t-s)\sigma(s)ds \quad (3)$$

where function  $\psi(\sigma)$  is constructed from similarity of the creep curves, while function  $\psi(\sigma)$  is constructed from similarity of isochronous curves, characterizing the strain on rapid loading.

Reference [1] recommends to represent the general relationship  $\sigma \sim \epsilon - t$  between the stresses, strains and time by means of a linear tensor operator. References [2]-[4] suggest a closed quasi-linear quadratic theory of viscoelasticity of media which have a physical nonlinearity. Here are already established all the general principal one-to-one relationships between tensors  $\sigma_{ij}$ ,  $\epsilon_{ij}$  and time, and relationships are obtained between the secondary kernels of creep and relaxation, as well as between them and the corresponding kernels of the linear theory.

Let us consider the main concepts of the theory being suggested. Let  $S_{ij}(t_1, \dots, t_n)$ ,  $\dots$ ,  $S_{ij}(t_k, \dots, t_n)$  be the stresses at times  $t_1, t_2, \dots, t_k, \dots, t_n - t$  of the interval  $[t_0, t]$  ( $t$  being the time at which it is required to determine the stress in the body, acting during a short time interval  $\Delta t$ ). Let us assume that it is required to study the function of process  $Z_{ij}$  at time  $t$ , for example, the strain which is produced by the entire ensemble of stress pulses  $S_{ij}(t_k)$ . The sum of contribution of individual stress pulses with the corresponding influence function will give a representation of  $Z_{ij}$  in the form of a linear operator of  $S_{ij}$  of the type of (1), which is the first approximation. The following approximation will be the combined action of two preceding stress pulses  $S_{ij}$  at times  $t_1$  and  $t_2$ . This effect will be proportional to the product of these pulses during the applicable times, multiplied by the joint effect function of this pair. The following approximation is the effect of three stress pulses, acting during three different times, with the joint effect function of these three stresses, etc. For deviators of the stress and deformation tensors the relationship  $\sigma \sim \epsilon - t$  should be odd, since for a nonvarying value of  $3\sigma = \sigma_{ii}$ , a reversal in the direction of shear should change the sign of  $S_{ij}$ .

According to the isotropy postulate, the relationship  $\sigma \sim \epsilon - t$  should contain a triple product, which yields the quasi-linear tensor  $S_{ij}(t_k)S_{mn}(t_l)$ . As a result, for a process  $Z_{ij}$  (strains, for example) we get

$$Z_{ij}(t) = \int_0^t K(t, \tau)S_{ij}(\tau)d\tau + \int_0^t \int_0^t S_{ij}(\tau)d\tau \int_0^t K_3(t, \tau, \xi, \eta)S_{ij}(\xi, \eta)d\tau d\xi d\eta \quad (4)$$

The solution of this system of integral equations for stresses  $S_{ij}$  is

$$S_{ij}(t) = \int_0^t \Gamma_1(t-s)Z_{ij}(s)ds + \int_0^t \int_0^t \Gamma_2(t, \tau, \xi, \eta)Z_{ij}(\tau, \xi, \eta)d\tau d\xi d\eta \quad (5)$$

Equations (4) and (5) express the property of reciprocity: kernels  $K$ ,  $\Gamma_1$ ,  $K_3$  and  $\Gamma_3$  should be interrelated by integral equations which are not a function of  $Z$  and  $S$ . The

## STABILITY OF ORTHOTROPIC VISCOELASTIC SHELLS

P. M. Ogibalov and M. A. Koltunov

(Moscow)

This article presents the fundamental concepts of heredity theories. For orthotropic materials with linear properties the article presents a system of nonlinear equations of flexure and stability for plates and shells, as well as a method for constructing solutions. Methods are presented for determining the upper and lower critical loads as a function of the loading regime and of the critical time.

The ever-increasing use of plastics, fiberglass and other synthetic materials requires providing new methods for solving engineering problems which take into account the rheonomy of their properties.

The elastic aftereffect phenomenon, discovered in 1834 by L. Vicat and then by K. Weber, was subjected in the middle of the past century to the scrutiny of such major scientists as F. Kohlrausch, R. Clausius, D. Maxwell, S. Thomson, L. Boltzmann, and others. Bringing his theory in line with experimental results L. Boltzmann put forward two hypotheses: 1) the stress depends not only on the strain prevailing at the given time, but also on the preceding strains, whose effect is the weaker, the farther they are removed in time from the present; 2) the law of independent force action is applicable to elastic forces.

On the basis of these hypotheses we shall represent the relationships between stresses and strains in time suggested by L. Boltzmann in the following form:

$$\sigma(t) = \frac{\sigma(t)}{E} + \frac{1}{E} \int_0^t K(t-s)\sigma(s)ds \quad \sigma(t) = E\epsilon(t) - E \int_0^t \Gamma(t-s)\epsilon(s)ds \quad (1)$$

In the beginning of the present century W. Volterra developed a theory of integral equations from which, in particular, follows a relationship between the kernel  $K$  and the resolvent  $\Gamma$

$$K(t) - \Gamma(t) = \int_0^t \Gamma(t-s)K(s)ds \quad (2)$$

properties of resolvent  $\Gamma_3$  should be analogous to those of kernel  $K_3$ , in particular,  $\Gamma_3$  should be symmetrical with respect to arguments  $\xi$  and  $\eta$ .

The integral equation relating kernels  $K$  and  $K_3$  and resolvents  $\Gamma$  and  $\Gamma_3$  reduces to the form

$$\int_0^1 K(t, \tau) \Gamma_3(\tau, \xi, \rho, q) d\tau = - \int_0^1 \Gamma(\tau, \tau) d\tau \int_0^1 \Gamma(\xi, \rho) d\xi \int_0^1 \Gamma(\eta, q) K_3(t, \tau, \xi, \eta) d\eta. \quad (6)$$

The solution of this equation is expressed as

$$- \Gamma_3(t, \tau, \xi, \eta) = \int_{-\infty}^0 \int_{-\infty}^0 \Gamma(t, x) dx \int_0^1 \Gamma(y, \tau) dy \int_0^1 \Gamma(u, \xi) du \int_0^1 \Gamma(v, \eta) K_3(x, y, u, v) dv. \quad (7)$$

Due to symmetry of kernels  $K$  and  $\Gamma$  it is possible to write an expression for  $K_3$  in terms of  $\Gamma_3$

$$- K_3(t, \tau, \xi, \eta) = \int_{-\infty}^0 \int_{-\infty}^0 K(t, x) dx \int_0^1 K(y, \tau) dy \int_0^1 K(u, \xi) du \int_0^1 K(v, \eta) \Gamma_3(x, y, u, v) dv. \quad (8)$$

It is clear from this that, the closer times  $t_k$ ,  $\tau$ , and  $t_p$  to time  $t$ , the greater is the effect on the process at hand of the values of  $S_{ij}(t_m)$  and, consequently, this property shows that the expressions for  $K$ ,  $\Gamma$ ,  $K_3$  and  $\Gamma_3$  contain Dirac's  $\delta$ -functions

$$\bar{K}(t, x) = \delta(t - x) + K(t, x); \quad \bar{\Gamma}(t, x) = \delta(t - x) - \Gamma(t, x), \quad (9)$$

where  $K$  and  $\Gamma$  are regular kernels (for example, such as  $\Gamma(t) = me^{-mt}$ ), which is a scalar, has the form

$$\bar{R}(x) = R(x) + R_3 \delta_3(x) + R_{33} \delta_3(x) \delta_3(x) + R_{333} \delta_3(x) \delta_3(x) \delta_3(x) + \dots$$

Here

$$\delta_3 = \begin{cases} \delta(x_i) & i = 1, \\ \delta(x_j) & i = j. \end{cases}$$

The quantity  $R$  with its subscripts forms a set of three "tensors" of second, fourth and sixth-order regular kernels, which are a function of  $x$ . Expressions of  $\bar{K}_3$  and  $\bar{\Gamma}_3$  in terms of  $\delta$ -functions and regular kernels are more complex and are not presented (the reader is referred for them to [3]).

In constructing a theory of plates and shells made from material with rheonomic properties, it is first necessary to assume relationships in which the physical law is the first approximation of the general theory, given for the Boltzmann-Volterra linear processes in the form of (1) and (2). Here kernel  $K$  may be selected either with a singularity at  $t = 0$ , or as a sum of some Dirac kernel [6], which reflects the start of the process, and a regular  $K$ , in such a manner that the relationship  $\sigma \sim \epsilon - t$  will be

written in the form

$$\sigma(t) = E \left[ \epsilon(t) - \lambda \int_0^t D(t-s) \epsilon(s) ds - \int_0^t K_1(t-s) \epsilon(s) ds \right].$$

If the temperature shear function  $a_{temp}(T) = t_{loc}$ , where  $t$  is the time of observation and  $t_{loc}$  is some reduced or "local" time, for the material under study is known, then the principal relationships of the heredity theories, which are valid for any temperatures from the range of operation of temperature-time analogy, will be written by replacing time  $t$  by "time"  $t_{loc}$  [2, 5]. For example, in the linear case we will have

$$E\epsilon = \int_0^t K_{temp}(t_{loc} - s_{loc}) d\sigma(s); \quad K_{temp}(t) = \int_0^t K(x) dx.$$

Let us now pass on to construction of equations of viscoelastic shells, understanding that  $R$  and  $K$  denote either a sum in the form  $\lambda D + K$ , or kernels with a singularity in  $t = 0$ .

Since plates and shells are made quite extensively from fiberglass, whose properties in the majority of cases are orthotropic, we shall construct the equations of the theory of shells for flexible (i. e., with consideration of geometric nonlinearity) orthotropic shallow shells, whose material displays linear heredity. We assume that the hypothesis of undeformable normals is applicable to fiberglass plates and shells. It is assumed in addition that the stresses acting normal to the middle surface are negligible in comparison with other components and that orthotropy is retained during the entire deformation process.

We select a coordinate system  $(x, y, z)$  lining up axes  $ox$  and  $oy$  along the base and weft (principal system), while axis  $oz$  is directed normal to the  $(x, y)$  coordinate plane. We have the following expressions for the deformation of the middle layer of the shell and for the curvatures in terms of the displacement of the middle layer:

$$\begin{aligned} \epsilon_{11} &= \frac{\partial u_x}{\partial x} + \frac{1}{2} \left( \frac{\partial w}{\partial x} \right)^2 - k_1 w, & \kappa_x &= -\frac{\partial^2 w}{\partial x^2}; \\ \epsilon_{22} &= \frac{\partial u_y}{\partial y} + \frac{1}{2} \left( \frac{\partial w}{\partial y} \right)^2 - k_2 w, & \kappa_y &= -\frac{\partial^2 w}{\partial y^2}; \\ \epsilon_{12} &= \frac{\partial u_x}{\partial y} + \frac{\partial u_y}{\partial x} + \frac{\partial w}{\partial x} \frac{\partial w}{\partial y}, & \kappa_{xy} &= -\frac{\partial^2 w}{\partial x \partial y}. \end{aligned} \quad (10)$$

By virtue of the Kirchhoff theorem, the displacements and strains in a layer situated at distance  $z$  from the middle surface are

$$\begin{aligned} u &= u_0 - z \frac{\partial w}{\partial x}; & v &= v_0 - z \frac{\partial w}{\partial y}; \\ \epsilon_{11} &= \epsilon_{11}^0 - z \frac{\partial^2 w}{\partial x^2}; & \epsilon_{22} &= \epsilon_{22}^0 - z \frac{\partial^2 w}{\partial y^2}; & \epsilon_{12} &= \epsilon_{12}^0 - 2z \frac{\partial^2 w}{\partial x \partial y} \end{aligned} \quad (11)$$

The relationship between stresses and strains for orthotropic materials is written in the form

$$\begin{aligned} \sigma_{11} &= B_{11} \epsilon_{11} - \tau \int R_{11}(\tau) d\tau + B_{12} \epsilon_{22} - \int R_{12}(\tau - \tau) \epsilon_{22}(\tau) d\tau; \\ \sigma_{22} &= B_{22} \epsilon_{22} - \int R_{22}(\tau - \tau) \epsilon_{22}(\tau) d\tau + B_{21} \epsilon_{11} - \int R_{21}(\tau - \tau) \epsilon_{11}(\tau) d\tau; \\ \sigma_{12} &= 2B_{12} \epsilon_{12} - 2 \int R_{12}(\tau - \tau) \epsilon_{12}(\tau) d\tau. \end{aligned} \quad (12)$$

Here

$$\begin{aligned} B_{11} &= \frac{E_1}{1 - \nu_1 \nu_2}; & B_{12} &= B_{21} = \frac{\nu_1 E_2}{1 - \nu_1 \nu_2} - \frac{\nu_2 E_1}{1 - \nu_1 \nu_2}; & B_{22} &= \frac{E_2}{1 - \nu_1 \nu_2}; \\ 2B &= G = \frac{E_{22}}{2(1 + \nu_{22})}; & \nu_1 &= \nu_{21} = \frac{\epsilon_{21}}{\epsilon_{11}}; & \nu_2 &= \nu_{12} = \frac{\epsilon_{12}}{\epsilon_{22}} \end{aligned} \quad (13)$$

are the components of the tensor of the moduli of elastic anisotropy and the Poisson ratios for tension along the base and along the web;

$$R_{11} = B_{11} R_{11}(t), \quad R_{22} = B_{22} R_{22}(t), \quad R_{12} = B_{12} R_{12}(t), \quad R = BR \quad (14)$$

are the components of the tensor of the relaxation kernels.

The forces acting per unit width of shell-element cross section are

$$\begin{aligned} T_x &= \int_{-\frac{h}{2}}^{+\frac{h}{2}} \sigma_x dz; & M_x &= \int_{-\frac{h}{2}}^{+\frac{h}{2}} \sigma_x z dz; & \tilde{S} &= \tilde{S}_1 = \tilde{S}_2 = \int_{-\frac{h}{2}}^{+\frac{h}{2}} \sigma_x dz; \\ H &= H_1 = H_2 = \int_{-\frac{h}{2}}^{+\frac{h}{2}} \sigma_x dz. \end{aligned}$$

while stresses  $\sigma_{mn}$  are given by Eqs. (12). Substituting Eqs. (10), (12) and (14) into the expression for forces, we get

$$\begin{aligned} T_1 &= hB_{11}(\epsilon_{11}^0 - J_{11}\epsilon_{11}^0) + hB_{12}(\epsilon_{22}^0 - J_{22}\epsilon_{22}^0); \\ T_2 &= hB_{12}(\epsilon_{11}^0 - J_{11}\epsilon_{11}^0) + hB_{22}(\epsilon_{22}^0 - J_{22}\epsilon_{22}^0); \\ \tilde{S} &= 2hB(\epsilon_{12}^0 - J_{12}\epsilon_{12}^0), \end{aligned} \quad (15)$$

where

$$J_{ij}^0 = \int_0^t R_{ij}(\tau - \tau) \epsilon_{ij}^0(\tau) d\tau$$

After a Laplace transformation, Eqs. (15) take on the form

$$\begin{aligned} T_1 &= hB_{11}\epsilon_{11}^0 + hB_{12}\epsilon_{22}^0 - T_1^0; & T_2 &= hB_{12}\epsilon_{11}^0 + hB_{22}\epsilon_{22}^0 - T_2^0; \\ \tilde{S} &= 2hB\epsilon_{12}^0 - \tilde{S}^0 \end{aligned} \quad (16)$$

-5-

Here

$$B_{ij}^0 = B_{ij}(1 - R_{ij}^0); \quad R_{ij}^0 = \int_0^t R_{ij}(\tau) e^{-\tau} d\tau.$$

From Eqs. (16) we find

$$\begin{aligned} \epsilon_{11}^0 &= \frac{1}{h} \frac{T_1 B_{11}^0 - T_2 B_{12}^0}{B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0}; & \epsilon_{22}^0 &= \frac{1}{h} \frac{T_2 B_{22}^0 - T_1 B_{12}^0}{B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0}; & \epsilon_{12}^0 &= \frac{\tilde{S}^0}{2hB^0}; \\ \text{We set up the identity} & & & & & \\ \frac{\partial}{\partial y^2} (2B^0 (B_{22}^0 T_1 - B_{12}^0 T_2) + \frac{\partial}{\partial x^2} (2B^0 (B_{11}^0 T_2 - B_{12}^0 T_1)) - \frac{\partial}{\partial x \partial y} (B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0) \tilde{S}^0) & & & & & \\ &= 2hB^0 (B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0) \left( \frac{\partial}{\partial y^2} (\epsilon_{11}^0) + \frac{\partial}{\partial x^2} (\epsilon_{22}^0) - \frac{\partial}{\partial x \partial y} (\epsilon_{12}^0) \right). \end{aligned} \quad (17)$$

into which we substitute expressions for  $\epsilon_{ij}^0$  from the preceding expressions, we simplify and introduce the stress function  $\psi$  using the formulas

$$\frac{\partial^2 \psi}{\partial y^2} = \frac{1}{h} T_1, \quad \frac{\partial^2 \psi}{\partial x^2} = \frac{1}{h} T_2, \quad \frac{\partial^2 \psi}{\partial x \partial y} = -\frac{1}{h} \tilde{S}.$$

and also apply the Laplace transform

$$\begin{aligned} T_1 &= h \frac{\partial^2 \psi}{\partial y^2}; & T_2 &= h \frac{\partial^2 \psi}{\partial x^2}; & \tilde{S} &= -h \frac{\partial^2 \psi}{\partial x \partial y}. \end{aligned} \quad (18)$$

As a result we get a continuity equation [7] for an orthotropic elastic shell, whose material has linear heredity properties, in the operator form

$$\begin{aligned} B_{11} \frac{\partial^4 \psi}{\partial x^4} + \frac{1}{2B^0} (B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0 - 4B^0 B_{12}^0) \frac{\partial^4 \psi}{\partial x^2 \partial y^2} + B_{22}^0 \frac{\partial^4 \psi}{\partial y^4} = \\ = (B_{11}^0 B_{22}^0 - B_{12}^0 B_{21}^0) \left\{ \left( \frac{\partial^2 \psi}{\partial x \partial y} \right)^2 \right\} - \left( \frac{\partial^2 \psi}{\partial x^2} \frac{\partial^2 \psi}{\partial y^2} \right) - k_1 \frac{\partial^2 \psi}{\partial y^2} - k_2 \frac{\partial^2 \psi}{\partial x^2}. \end{aligned}$$

The right-hand side of the above expression has nonlinear terms  $\left\{ \left( \frac{\partial^2 \psi}{\partial x \partial y} \right)^2 \right\}, \dots$

It will be subsequently assumed that it is possible to represent the deflection in the form  $w(x, y, t) = w(x, y) \bar{w}_1(t)$ , where function  $w_1(t)$ , its derivatives and their squares allow the Laplace transform.

With the aid of (12), the expressions for the moments have the form

$$\begin{aligned} M_1 &= \int_{-\frac{h}{2}}^{+\frac{h}{2}} \sigma_{11} z dz = -12 \left[ B_{11} \left[ \frac{\partial^2 w}{\partial x^2} - \int_0^t R_{11}(\tau - \tau) \frac{\partial^2 w}{\partial x^2} d\tau \right] + \right. \\ &\quad \left. + B_{12} \left[ \frac{\partial^2 w}{\partial y^2} - \int_0^t R_{12}(\tau - \tau) \frac{\partial^2 w}{\partial y^2} d\tau \right] \right]; \end{aligned} \quad (19)$$

-6-

$$M_3 = -\frac{h^3}{12} \left[ B_{11} \frac{\partial^2 w}{\partial x^2} - \int_0^t R_{11}(t-\tau) \frac{\partial^2 w}{\partial x^2} d\tau + B_{22} \left[ \frac{\partial^2 w}{\partial y^2} - \int_0^t R_{22}(t-\tau) \frac{\partial^2 w}{\partial y^2} d\tau \right] \right] \quad (19)$$

$$H = -\frac{h^3}{12} B \left[ \frac{\partial^2 w}{\partial x \partial y} - \int_0^t R(t-\tau) \frac{\partial^2 w}{\partial x \partial y} d\tau \right]$$

Introducing the values of  $M_1$ ,  $M_2$ ,  $H$  and of  $T_1$ ,  $T_2$ ,  $\tilde{S}$  into the equilibrium equation of the shell

$$\frac{\partial^2 M_1}{\partial x^2} + 2 \frac{\partial H}{\partial x \partial y} + \frac{\partial^2 M_2}{\partial y^2} + T_1 \left( k_1 + \frac{\partial^2 w}{\partial x^2} \right) + T_2 \left( k_2 + \frac{\partial^2 w}{\partial y^2} \right) + 2\tilde{S} \frac{\partial^2 w}{\partial x \partial y} + q = 0$$

and applying the Laplace transform, we find the equilibrium equation for an elastic orthotropic shell from a material with linear hereditary properties

$$B_{11}' \frac{\partial^2 w}{\partial x^2} + 2(B_{12}' + 4B') \frac{\partial^2 w}{\partial x^2 \partial y^2} + B_{22}' \frac{\partial^2 w}{\partial y^2} - h^2 \left( k_2 \frac{\partial^2 w}{\partial x^2} + k_1 \frac{\partial^2 w}{\partial y^2} \right) - \frac{12}{h^2} \left[ \left( \frac{\partial^2 \varphi}{\partial x^2} \frac{\partial^2 w}{\partial y^2} \right) + \left( \frac{\partial^2 \varphi}{\partial y^2} \frac{\partial^2 w}{\partial x^2} \right) - 2 \left( \frac{\partial^2 \varphi}{\partial x \partial y} \frac{\partial^2 w}{\partial x \partial y} \right) \right] - h^2 \varphi = 0 \quad (20)$$

Here  $B_{ij}' = B_{ij}(1 - R_{ij})$  is a known function of  $p$ .

In intermediate calculations we have obtained the expressions

$$\begin{aligned} M_1' &= -\frac{h^3}{12} \left( B_{11}' \frac{\partial^2 w}{\partial x^2} + B_{12}' \frac{\partial^2 w}{\partial y^2} \right); \\ M_2' &= -\frac{h^3}{12} \left( B_{12}' \frac{\partial^2 w}{\partial x^2} + B_{22}' \frac{\partial^2 w}{\partial y^2} \right); \\ H' &= -\frac{h^3}{12} B' \frac{\partial^2 w}{\partial x \partial y}. \end{aligned} \quad (21)$$

We thus have two resolving equations (18) and (20), for the unknown stress  $(x, y)$  and deflection  $w(x, y, t)$  functions. We note that these two equations contain terms of two types: such as  $B_{ij}' \frac{\partial^2 w}{\partial x^2}$ , in which coefficients  $B_{ij}'$  are known functions of the complex parameter  $p$ , while the transform of the unknown functions is contained in the linear form, and such as  $\left( \frac{\partial^2 \varphi}{\partial x^2} \frac{\partial^2 w}{\partial y^2} \right)$ , where, by virtue of the method being presented, one of the functions (for example,  $w$ ) contained in parentheses will be considered as a known function of position and time, specified to within undetermined constants. Consequently, with respect to unknowns not specified by functions (for example,  $\varphi$ ) the above product will be linear.

To clarify this method we now present one of the possible approximate solutions of the system of equations (18) and (20). We shall consider an orthotropic plate or weakly bent panel, rectangular in the plan, from fibreglass, for which the stress relaxation curves in specimens under tension are known and are representable, for example, in the form

$$\sigma(t) = \sigma_0(1 - \gamma(1 - e^{-\alpha t})), \quad (22)$$

Obviously, the kernel of relaxation will be

$$R = \gamma e^{-\alpha t}, \quad (0 < \gamma < 1, 0 < \alpha < \infty), \quad (23)$$

where  $\alpha$  and  $\gamma$  depend on the orientation of the specimen.

The transform of the kernel has the form

$$R' = \frac{\gamma \alpha}{p + \alpha}. \quad (24)$$

We assume henceforth for simplicity that all the

$$B_{ij}' = B_{ij}(1 - R') \quad (25)$$

and that  $w$ , the deflection function is given in the form

$$w(x, y, t) = w_0(x, y) \varphi_1(t), \quad (26)$$

where  $w_0(x, y)$  is the elastic solution, while function  $w_1(t)$  is selected to within unknown parameters  $\lambda$  and  $\mu$  in the form

$$\varphi_1(t) = \lambda - \mu e^{-\alpha t}, \quad \lambda - \mu = 1. \quad (27)$$

Stress function  $\varphi$  is sought in the form

$$\varphi(x, y, t) = \varphi_0(x, y) \varphi_1(t), \quad (28)$$

here  $\varphi_0(x, y)$  is the elastic solution, while  $\varphi_1(t)$  for a given form of function  $w_1(t)$  is to be determined.

Laplace transform of  $w_1(t)$  yields

$$\varphi_1'(p) = \frac{\lambda}{p} - \frac{\mu}{p + \alpha}. \quad (29)$$

Substituting Eqs. (25), (26) and (28) into continuity equation (13), we find

$$\varphi_1' = \alpha_1 \delta(1 - R') w_1' + \alpha_2 \delta(1 - R') (w_1'')'. \quad (30)$$

Here

$$\begin{aligned} \alpha_1 &= -\frac{1}{\nabla^2 \varphi_0}, \quad \alpha_2 = -\frac{1}{\nabla^2 \varphi_0} \left( k_1 \frac{\partial^2 \varphi_0}{\partial x^2} + k_2 \frac{\partial^2 \varphi_0}{\partial y^2} \right); \\ C &= \frac{1}{2B} (\delta - 4BB_{12}), \quad \delta = B_{11}B_{22} - B_{12}^2; \\ \alpha_3 &= \frac{N_0}{\nabla^2 \varphi_0} = \frac{\left( \frac{\partial^2 \varphi_0}{\partial x \partial y} \right)^2 - \frac{\partial^2 \varphi_0}{\partial x^2} \frac{\partial^2 \varphi_0}{\partial y^2}}{\nabla^2 \varphi_0^2}. \end{aligned}$$

Substituting Eqs. (24) and (29) into Eq. (30) and having reference to the fact that

$$\frac{1}{(\rho + ka)(\rho + ma)} = \frac{1}{(m-k)a(\rho + ka)} - \frac{1}{(m-k)a(\rho + ma)},$$

we get

$$\varphi_1 = \frac{A_1}{\rho} + \frac{A_2}{\rho + a} + \frac{A_3}{\rho + 2a} + \frac{A_4}{\rho + \alpha}, \quad (31)$$

Inverting (31) we find

$$\varphi_1 = A_1 + A_2 e^{-\rho a} + A_3 e^{-2\rho a} + A_4 e^{-\rho \alpha}, \quad (32)$$

where

$$A_1 = \delta(1 - \gamma)(\lambda \alpha_1 + \lambda \alpha_2); \quad A_2 = \alpha_1 \delta(\gamma \lambda^2 - 2\lambda \mu - \gamma \mu^2) - \alpha_1 \delta(\mu - \lambda \gamma);$$

$$A_3 = \alpha_1 \delta \mu^2 (1 + \gamma); \quad A_4 = \delta \gamma \mu (\alpha_1 \mu + 2\alpha_2 \lambda \mu). \quad (33)$$

To determine the sought parameters  $\lambda$  and  $\mu$  we substitute Eqs. (26) and (28), with reference to (27) and (32), into equilibrium equation (20). Then

$$\frac{K_1}{\rho} + \frac{K_2}{\rho + a} + \frac{K_3}{\rho + 2a} + \frac{K_4}{\rho + \alpha} + \frac{K_5}{(\rho + \alpha)^2} + \frac{K_6}{(\rho + 2\alpha)^2} = 0,$$

which, after inversion, yields an equation relating the load and the deflection in the form

$$K_1 + K_2 e^{-\rho a} + K_3 e^{-2\rho a} + K_4 e^{-\rho \alpha} + K_5 e^{-2\rho \alpha} + K_6 e^{-2\rho \alpha} = 0. \quad (34)$$

Here

$$K_1 = \nabla^2 \nabla^2 \varphi_0 \lambda (1 - \gamma) - \frac{12}{h^2} \nabla^2 \varphi_0 A_1 - \frac{12}{h^2} M_0 \lambda A_1 - \frac{12}{h^2} q_1(0);$$

$$K_2 = -\nabla^2 \nabla^2 \varphi_0 (\mu - \lambda \gamma) - \frac{12}{h^2} \nabla^2 \varphi_0 A_2 - \frac{12}{h^2} M_0 (\lambda A_2 - \mu A_1);$$

$$K_3 = -\frac{12}{h^2} \nabla^2 \varphi_0 A_3 - \frac{12}{h^2} M_0 (\lambda A_3 - \mu A_1); \quad K_4 = \frac{12}{h^2} M_0 \mu A_1;$$

$$K_5 = \nabla^2 \nabla^2 \varphi_0 \gamma \mu \alpha - \frac{12}{h^2} \nabla^2 \varphi_0 A_4 - \frac{12}{h^2} \lambda A_1 M_0; \quad K_6 = \frac{12}{h^2} M_0 \mu A_1.$$

From Eq. (34) we get

$$K_1 + K_2 + K_3 + K_4 + K_5 = 0 \text{ when } t = 0, \\ K_1 = 0 \text{ when } t \rightarrow \infty. \quad (35)$$

To determine  $\lambda$  we substitute the value of  $A_1$  from Eq. (33) into (35). As a result we get, for example, for  $q = q_0$

$$\lambda^2 - (\alpha_1 - \alpha_2) \lambda^2 - \left( \frac{A^2 m_1}{12 \delta \alpha_1} + \alpha_1 \alpha_2 \right) \lambda + \frac{q_0 m}{k(1 - \gamma)} = 0. \quad (36)$$

Here

$$\alpha_1 = \frac{\nabla^2 \varphi_0}{N_0}; \quad \alpha_2 = \frac{\nabla^2 \varphi_0}{M_0}; \quad m_1 = \frac{\nabla^2 \nabla^2 \varphi_0}{M_0}; \quad n_1 = \frac{N_0}{\nabla^2 \nabla^2 \varphi_0};$$

$$m = \frac{\nabla^2 \nabla^2 \varphi_0}{8 N_0 M_0}; \quad M_0 = \frac{\partial^2 \varphi_0}{\partial x^2} \frac{\partial^2 \varphi_0}{\partial y^2} + \frac{\partial^2 \varphi_0}{\partial x^2} \frac{\partial^2 \varphi_0}{\partial x^2} - 2 \frac{\partial^2 \varphi_0}{\partial x \partial y} \frac{\partial^2 \varphi_0}{\partial x \partial y}.$$

Solution of Eq. (36) for a square hinged plate from orthotropic polyethylene fiber-glass with the following components of the tensor of elastic moduli  $B_{ij}$

$$B_{11} = 1.49 \cdot 9.81 \cdot 10^9 \text{ N/m}^2; \quad B_{22} = 1.143 \cdot 9.81 \cdot 10^9 \text{ N/m}^2;$$

$$B_{12} = B_{21} = 0.18 \cdot 9.81 \cdot 10^9 \text{ N/m}^2; \quad B = 0.13 \cdot 9.81 \cdot 10^9 \text{ N/m}^2$$

yields one real root  $\lambda = 1.21$ , which is in good agreement with experimental data on the creep of a square plate with hinged edges ( $\lambda = 1.19$ ).

In solving problems of shell stability it is useful to select function  $w_1(t)$  in the form

$$w_1(t) = \lambda - \mu e^{-\beta t} - \beta \phi(t - t_{cr})$$

here

$$\phi = \begin{cases} 0 & t < t_{cr}, \\ 1 & t = t_{cr}. \end{cases}$$

The "popping" parameter  $\beta$  will be found by equating the "jump" in the deflection of the viscoelastic problem, to the deflection "jump" in the elastic problem, since it may be assumed that creep will not develop during the popping.

We now present the results from solving the problem of stability of a compressed circular cylindrical shell from PN-1, T-1 polyester fiberglass along the axis; here the twist of the fiber is directed along the generatrix, while the base is directed along the directrix.

Creep and relaxation experiments show that it is possible to assume

$$\gamma_{11} = \gamma_{22} = \frac{1}{6}; \quad \alpha_{11} = \alpha_{22} = \alpha_{33} = 0.5; \quad \gamma_{12} = \mu \gamma_{11}; \quad \gamma = 3\gamma_{11},$$

where  $\mu_1$  is of the order of magnitude of the Poisson ratio and is to be determined (it was found from conditions at  $t \rightarrow \infty$  that  $\mu = 0.12$ ) the elastic solution of the problem was found by the Ritz method, while the viscoelastic solution was obtained by the method presented above.

It follows from the solution for a constant load that the critical loads are the same as in the elastic case, while the critical deflections increase; for a time-varying load the critical loads become smaller, while the deflections become larger as compared

DISTRIBUTION LIST

Organization	Mr. Cys.	Organization	Mr. Cys.
<u>AIR FORCE</u>			
Hq USAF		DDC	20
ACIC (ACDEL-7)	2	C072 CDC INLAND COMBAT	1
AFCEL (CERLR)	1		
ARL (AFB) AF, AFB	2	C513 Floating Arsenal	1
ETAC (MAC)	1	C523 Harry Diamond Lab	1
Hq AFSC	1	C525 Aberdeen Fp	1
AFETR (ETM)	1	C535 Aviation Mat Comd	1
AFML (WLF)	1		
ASD (ASFS)	9	C619 MID Helotere	1
FDDC (1)			
ESD (ESY/ESDT)	1	D153 Pac Mgl Range	1
SAMSO (SMFA)	1	H521 Hq USAREUR - UTIC	1
FTD			
<u>OTHER GOVERNMENT AGENCIES</u>			
TORAE	3		
ATD (2)			
PHS (1)			
TDRAS-2	10		
TDRID-2	2		
TDR	1		
IDCS	1		
TDF (PHE)	3		
PC (1)			
PE (1)			
PH (1)			
TDFMP/1	1		

DISTRIBUTION TO BE MADE BY

DIA (DIACO-3)	23
F154 DIAS-1 Data Base	
F162 DIAS-2D	
F737 DIAAF-10A	
F768 OACSI - USAITAG	
DO08 U.S. Navy (STIC)	
D220 ONR	
F055 CIA/OCR/SD (5)	
F090 NSA (CHRF/CDE) (6)	

with the elastic values. Thus,  $\hat{p}_{up,el} = 0.558$ ,  $\hat{p}_{up,v,el} = 0.483$ ,  $\hat{p}_{l,el} = 0.171$ ,  $\hat{p}_{l,v,el} = 0.137$ . We note that the values of the "upper" and "lower" critical loads for viscoelastic shells depends appreciably on the loading rate (with an increase in this rate the "upper" critical load becomes greater).

We note an important circumstance which can be successfully used, namely: if the temperature range for which the temperature-time analogy  $T \sim t$  holds is known, i.e., the temperature shear function  $a_{temp}(T) = t/a_{loc}$  for the given material has been constructed, then for any temperature  $T_k$  from this range the solutions are obtained by simple replacement of the time axis  $t$  by the "local" time  $T_{loc} = a_{temp} t$ , where  $T_k$  is the shell's "functioning" temperature.

REFERENCES

1. Il'yushin, A. A. Teoriya plastichnosti pri prostom nagruzhenshi tel, materialy i metody obracheniya [The Theory of Plasticity on Simple Loading of Bodies Made from Work-Hardenable Material]. Prikladnaya Matematika i Mekhanika, Vol. 11, issue 2, 1967.
2. Il'yushin, A. A. and P. M. Ogibalov. Nekotoryye osnovnyye voprosy mekhaniki polimerov [Certain Fundamental Problems of the Mechanics of Polymers]. Mekhanika Polimerov, No. 3, 1965.
3. Il'yushin, A. A. and P. M. Ogibalov. Kvazilineynaya teoriya vyzhkosprugosti i metod malogo parametra [The Quasi-linear Theory of Viscoelasticity and the Method of the Small Parameter]. Mekhanika Polimerov, No. 2, 1966.
4. Il'yushin, A. A. and P. M. Ogibalov. Metod malogo parametra i teoriya nelineynoy vyzhkosprugosti [The Method of the Small Parameter and the Theory of Non-linear Viscoelasticity]. Prikladnaya Matematika, Vol. 2, issue 5, 1966.
5. Il'yushin, A. A. and P. M. Ogibalov. O kriterii dlitel'noy prochnosti polimerov [On the Theory of Long-Time Strength of Polymers]. Mekhanika Polimerov, No. 6, 1966.
6. Koltzov, M. A. K voprosu vybora yader pri reshenii zadach s uchedom poizucheshi i relaksatsii [On the Problem of Selection of Kernels when Solving Problems with Allowance for Creep and Relaxation]. Mekhanika Polimerov, No. 4, 1966.
7. Koltzov, M. A. O raschete gibkikh pologikh ortotropnykh obolochek s lineynoy nasledstvennost'yu [On the Design of Elastic Shell of Orthotropic Shells with Linear Heredity]. Vestnik Moskovskogo Universiteta, No. 5, 1964.

Moscow State University

Submitted 20 August 1966