



AD 696446

AD

CCL REPORT NO. 272


FINAL REPORT

DEVELOPMENT OF A MULTI-METAL PRIMER

BY

STANLEY F. KOUTEK

OCTOBER 1969



THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED

U. S. ARMY ABERDEEN RESEARCH & DEVELOPMENT CENTER
COATING & CHEMICAL LABORATORY

Aberdeen Proving Ground
Maryland

Reproduced by the
CLEARINGHOUSE
for Federal Scientific & Technical
Information Springfield Va. 22151

48

UNCLASSIFIED

CCL REPORT NO. 272

FINAL REPORT

DEVELOPMENT OF A MULTI-METAL PRIMER

BY

STANLEY F. KOUTEK

OCTOBER 1969

AMCMS CODE NO. 502E.11.29500

DEPARTMENT OF THE ARMY PROJECT NO.
1T062105A329

U.S. ARMY ABERDEEN RESEARCH AND DEVELOPMENT CENTER
COATING AND CHEMICAL LABORATORY
ABERDEEN PROVING GROUND
MARYLAND 21005

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED

UNCLASSIFIED

ABSTRACT

Some currently employed specification epoxy primers and experimental formulations were exposed at the Panama test sites for corrosion resistance studies. Inhibiting pigments considered included strontium, zinc and basic zinc chromates up to 90% by weight of the total pigmentation at different pigment volume concentrations. Polyamide and amino-silane curing agents were used. Experimental vinyl and polyurethane primers offered no significant improvement in corrosion resistance when compared to two existing specification primers, particularly on pretreated substrates. It is recommended that MIL-P-52192, Primer Coat, Epoxy be used for ferrous substrates and MIL-P-23377, Primer Coating, Epoxy Polyamide, Chemical and Solvent Resistant, for aluminum, magnesium or bi-metallic materials.

TABLE OF CONTENTS

	<u>Page No.</u>
TITLE PAGE	i
ABSTRACT	ii
INTRODUCTION	1
DETAILS OF TEST	1
DISCUSSION	1 - 4
CONCLUSIONS	4
DISTRIBUTION LIST	5 - 7
APPENDIX A	8
Tables 1 - 11	9 - 12
APPENDIX B	13
Formulas 1 - 19	14 - 23
APPENDIX C	24
Tables 1 - 17	25 - 41
DD FORM 1473	42

I. INTRODUCTION

A study was initiated for the development of a multi-metal epoxy primer as reported in CCL Report No. 192, 24 February 1966. This work indicated that further information was needed concerning performance of epoxy primers in corrosive and humid atmospheres before a decision could be made as to which type provided the maximum desired results. With this in mind, an exterior exposure study was conducted at the Panama exposure sites. This location was selected because atmospheric and environmental conditions provided, in a reasonable length of time, a means of reliably evaluating the primers.

II. DETAILS OF TEST

A. Preparation of Coatings

All pigmented resin components were prepared by charging the vehicle, pigments and necessary solvents into a pebble mill and grinding for 24 hours. All catalyst components consisted of a blend of the curing agent with the required solvents.

B. Test Panels

Flat polished 4 by 12 inch cold-rolled automotive steel, 2024 aluminum and AZ-31 magnesium were cleaned and pretreated in accordance with methods listed under Surface Preparation, Table I (Appendix A).

C. Application of Coatings

All primers were applied by spray to a dry film thickness of 0.9 to 1.1 mils. Primers which were topcoated were allowed to air dry 2 hours before spraying a 0.9 to 1.1 mil dry film thickness topcoat of Olive Drab Semi-Gloss Enamel conforming to Specification TT-E-529, Class A.

D. Panama Exposure

Scored test panels placed at the Panama Breakwater and Rain Forest sites were evaluated approximately twice a year in accordance with the rating system of Table II (Appendix A).

III. DISCUSSION

A study on the Development of a Multi-Metal Epoxy Primer, Progress Report CCL No. 192, showed an experimental epoxy primer furnished better corrosion resistance to aluminum and magnesium substrates than specification Epoxy Primer MIL-P-52192, but was inferior on steel along the score.

Based on the data obtained from this work, it was decided to conduct further corrosion resistance studies by placing at the Panama Breakwater site some currently employed specification epoxy primers and additional

experimental formulations. The Panama Test Sites are situated on the Atlantic Sector of Panama at Fort Sherman, Panama Canal Zone. The Breakwater site is located at the junction of Limon Bay and the Caribbean Sea on a jetty separating the sea from the bay, with panel racks positioned 30° from the vertical and facing the prevailing trade winds. Thus, a severely corrosive atmosphere is present at all times and metal attack is accelerated in comparison to other environments. The Rain Forest is located approximately 4 miles inland from the Breakwater site in the Tropical Evergreen Forest that is composed of basically 3 tiers of tree growth ranging from 20 to 125 feet high. In this region high humidity conditions prevail.

The epoxy primer formulations are given in Appendix B and include MIL-P-52192, MIL-P-27316 and MIL-P-23377A, Formulas 1, 2 and 3 respectively. The previous developed experimental epoxy primer control is shown in Formula 4 and zinc and strontium chromate epoxy primers are given in Formulas 5 and 6. Primers 5 and 6 are cured with a polyamide, amino-silane coreactant to utilize the wetting and adhesion properties attributed to these reagents.

Breakwater exposure data is given in Appendix C, Tables I through VII. On zinc phosphate pretreated (TT-C-490, Type I) Steel, MIL-P-52192 offered the best score protection although heavy score rusting developed within 12 months. Primers 2, 5 and 6 were definitely inferior. MIL-P-23377A and the experimental epoxy control primer were comparable when topcoated. All primers without the TT-E-529 topcoat developed surface and substrate defects.

On solvent cleaned aluminum primed with MIL-P-23377A and topcoated with TT-E-529, excessive score undercutting developed within 6 months Breakwater exposure. Likewise, MIL-P-52192 failed along the score. Other primers were generally comparable with the experimental epoxy primer control providing the best overall protection. On aluminum chemically pretreated with MIL-C-5541, performance improved significantly. MIL-P-52192 and MIL-P-27316 without topcoats were unsatisfactory along the score; all other primers, with and without topcoats, were comparable having only slight score defects.

On solvent cleaned magnesium, primers 1, 2 and 6 were unsatisfactory after 6 months exposure. The remaining primers developed score and/or surface-substrate defects within 12 months. MIL-P-23377A was the best among the specification primers and the experimental epoxy primer control had the least score attack. MIL-P-52192 and MIL-P-27316 were inferior to MIL-P-23377 and the experimental primers on all pretreated magnesium substrates. Differences between pretreatments were not excessive, however, MIL-M-3171, Type III appeared the most effective.

From the data, it is apparent that none of these epoxy primers would function as a multi-metal primer. MIL-P-52192 would be preferred on steel, MIL-P-23377A and the experimental epoxy control appeared better

on aluminum and magnesium pretreated substrates. The experimental zinc and strontium chromate primers offered no definite improvement, nor did the curing agents.

Previous Panama exposure tests indicated that MIL-P-15930B, Vinyl Zinc Chromate Primer, performed among the better primers on steel substrates. Accordingly, a second exposure study was initiated using MIL-P-15930B as a control and formulating that pigmentation into epoxy primers at the pigment volume concentration (PVC) of MIL-P-15930B, 25.9 percent, and at the experimental epoxy primer control of 35.2 percent. Further, basic zinc chromate content was increased to 90 percent of the pigment in the same vehicle formulations. Both polyamide and amino-silane curing agents were used. Included in the study were MIL-P-52192, the experimental epoxy primer control and MIL-P-23377A, amended, which increased the strontium chromate content to 52-54 percent by weight of the pigment from 15.6 percent. A polyurethane, aliphatic diisocyanate cured two package primer, Formula 19, pigmented as MIL-P-15930B at the Specification PVC, was added to investigate the corrosion resistance properties of this type system. The primers are shown in Formulas 1, 4 and 7 to 19 inclusive.

Exposure studies were conducted at the Panama Breakwater and Rain Forest sites. The primers were tested on zinc phosphate (TT-C-490, Type I) pretreated steel, alkali cleaned and chemically (MIL-C-5541, Type II) pretreated aluminum and alkali cleaned and anodically (MIL-M-45202, Type I) pretreated magnesium. Alkali cleaning insured a more uniform substrate surface than was possible by the solvent cleaning method.

Breakwater Exposure (Tables VIII-XII)

Primers 1, 8, 14 and 19 were slightly better along the score on zinc phosphated steel than the remaining primers after 6 months exposure. Differences were negligible after 15 months with defects confined to the scored areas except for primer 18. After 21 months some surface blistering and rusting occurred on vinyl primer 8 and amino-silane epoxy primers 14, 16 and 18, all containing 90 percent basic zinc chromate. The polyurethane primer 19 likewise exhibited similar attack. Polyamide primers and MIL-P-52192 were without surface or substrate defects. None of the experimental primers offered improved corrosion resistance over MIL-P-52192 and MIL-P-23377A was only slightly inferior along the score. Differences in pigment volume concentration had little effect on performance.

On alkali cleaned aluminum, MIL-P-52192 was unsatisfactory along the score after six months and in 15 months primers 1, 7, 11, 12 and 19 had excessive score defects. Primers 10, 17 and 18 had no defects after 21 months exposure. The experimental epoxy control primer and amended MIL-P-23377A were comparable. Vinyl primers 7 and 8 had poor adhesion to the aluminum substrate in addition to score failures.

MIL-P-52192 developed score blisters within six months when applied to chemically pretreated aluminum. MIL-P-23377A, amended, and primers

11, 13, 17 and 18 were without defects after 21 months. The polyurethane primer was rated below these. All primers had minor score blistering. Pigmentation and pigment-volume concentration differences had little effect. Polyamide cured primers appeared slightly better than the corresponding amino-silane types.

Over alkali cleaned magnesium only the amino-silane cured primers 4, 12 and 16 were considered acceptable after 21 months exposure. MIL-P-23377A, amended, was overall better than MIL-P-52192. All primers on anodically pretreated magnesium, except 14 and 18, were satisfactory after 21 months exposure, developing only light score corrosion.

Rain Forest (Tables XIII-XVII)

MIL-P-52192 and the experimental epoxy control primer were without defects after 21 months on zinc phosphate pretreated steel. The remaining primers had traces of score blisters.

On both alkali cleaned and chemically pretreated aluminum, MIL-P-52192 and the polyurethane primer blistered excessively along the score. All other primers were either without defects or had only slight score blistering.

Surface blisters and some substrate pitting was evident on primers 1, 8, 9, 10, 11, 15, 16 and 19 when exposed 21 months on alkali cleaned magnesium. Primer 17 had score defects. The experimental epoxy control primer and in general lower PVC primers performed the best. On anodically pretreated magnesium, the specification primers were satisfactory.

IV. CONCLUSIONS

The experimental primers offered no significant improvement in corrosion resistance over the existing epoxy specification primers MIL-P-52192 and MIL-P-23377A on pretreated substrates. On untreated light metal substrates, the amino-silane cured epoxy primers performed somewhat better than the other types. However, for optimum corrosion resistance, surfaces to be painted should be given a pretreatment prior to coating and specification epoxy primer MIL-P-23377A was adequate under these conditions. The polyurethane primer as formulated in this report is inferior to the specification epoxy primers.

It is recommended that where resistance properties of epoxy coatings are required, MIL-P-52192 be applied to ferrous substrates and MIL-P-23377A be used on light metal substrates. In the event of multi-metal fabrication, MIL-P-23377A would be preferred.

DISTRIBUTION LIST FOR AMCMS CODE NO. 502E.11.29500

	<u>No. of Copies</u>
<u>Department of Defense</u>	
Defense Documentation Center Cameron Station Alexandria, Virginia 22314	20
<u>Department of the Army</u>	
Commanding General U. S. Army Materiel Command ATTN: AMCRD-GF Washington, D. C. 20315	1
Continental Army Command Department of the Army Fort Monroe, Virginia 23351	3
Commanding General U. S. Army Tank-Automotive Command ATTN: Mr. J. Dudzinski Warren, Michigan 48090	1
Commanding Officer Frankford Arsenal ATTN: L7000-64-4 Library Philadelphia, Pennsylvania 19137	1
Commanding Officer Yuma Proving Ground Arizona 85364	1
Commanding General U. S. Army Weapons Command ATTN: AMSWE-RDR Rock Island, Illinois 61200	2
Commanding Officer U. S. Army Materials & Mechanics Research Center ATTN: Technical Information Center Watertown, Massachusetts 02172	2

DISTRIBUTION LIST CONTINUED

	<u>No. of Copies</u>
Commanding Officer U. S. Army Chemical Research and Development Laboratories ATTN: Librarian Edgewood Arsenal, Maryland 21040	1
Commanding Officer U. S. Army Mobility Equipment Research and Development Center ATTN: Technical Documents Center Fort Belvoir, Virginia 22060	2
Commanding Officer Rock Island Arsenal ATTN: Laboratory 9320 Rock Island, Illinois 61200	1
Commanding Officer Watervliet Arsenal ATTN: Dr. R. Weigle Watervliet, New York 12189	1
Commanding Officer Picatinny Arsenal Dover, New Jersey 07801	1
Commanding Officer U. S. Army Ballistic Research Laboratories ATTN: Mr. R. Eichelberger Mr. J. Sperrazza Aberdeen Proving Ground, Maryland 21005	1 1
Technical Library Aberdeen Proving Ground, Maryland 21005	1
<u>Department of the Navy</u>	
Department of the Navy c/o Navy Liaison Aberdeen Proving Ground, Maryland 21005	1
Commanding Officer and Director (Code L31) U. S. Naval Civil Engineering Laboratory Port Hueneme, California 93041	1

DISTRIBUTION LIST CONTINUED

	<u>No. of Copies</u>
Commander Naval Air Engineering Center ATTN: M44 Aeronautical Materials Laboratory Philadelphia, Pennsylvania 19112	1
Commander U. S. Naval Weapons Laboratory Dahlgren, Virginia 22428	1
Commander Naval Air Systems Command ATTN: AIR-330 Washington, D. C. 20360	1
Department of the Navy Chief, Bureau of Naval Weapons Washington, D. C. 20360	1
<u>Department of the Air Force</u>	
Commander Air Force Materials Laboratory ATTN: MAAM Wright Patterson Air Force Base, Ohio 45433	1
Air Force Systems Command Bldg. 314 ATTN: STLO Aberdeen Proving Ground, Maryland 21005	1
<u>Other Government Agencies</u>	
NASA Scientific and Technical Information Facility P. O. Box 33 College Park, Maryland 20740	3
Federal Aviation Administration 800 Independence Avenue S. W. ATTN: Administrative Standards Division (MS-110) Washington, D. C. 20590	2

APPENDIX A - TABLES

TABLE I
SURFACE PREPARATION

Steel

TT-C-490, Type I

Zinc Phosphate Chemical Conversion
Coating

Aluminum

Solvent Cleaned

1:1 by volume aliphatic naptha
(TT-N-95) - Ethylene Glycol Monoethyl
Ether (TT-E-781)

Alkali Cleaned

Hot Trisodium Phosphate followed by
Deoxidizing in 50% Nitric Acid

MIL-C-5541

Chemical Films and Chemical Film
Materials for Aluminum and Aluminum
Alloys, Type II, Grade C, Class 2

Magnesium

Solvent Cleaned

1:1 by Volume Aliphatic Naptha (TT-N-95)-
Ethylene Glycol Monoethyl Ether (TT-E-781)

Alkali Cleaned MIL-M-3171

"Magnesium Alloy, Processes for Pretreat-
ment and Prevention of Corrosion Pro-
tection On"
Type I Chromate Pickle Treatment
Type II Dichromate Treatment

MIL-M-45202

"Magnesium Alloys, Anodic Treatment Of"
Type I, Class C, Light Green Coating

TABLE II
Rating System

I. Score Condition

<u>Rating</u>	<u>Corrosion and/or Blistering</u>
5	None - 1/32 inch
4	1/32 - 1/16 inch
3	1/16 - 1/8 inch
2	1/8 - 3/16 inch
1	3/16 - 1/4 inch
0	> 1/4 inch

II. Undercutting at Score

<u>Rating</u>	
5	None - intermittent
4	Continuous to 1/16 inch
3	Continuous to 1/16 - 1/8 inch
2	Continuous to 1/8 - 3/16 inch
1	Continuous to 3/16 - 1/4 inch
0	Continuous > 1/4 inch

TABLE II - Continued

III. Surface Condition*

<u>Rating</u>	<u>A. Corrosion Alone</u>
5	None
4	ASTM Photo No. 10, Type 1 ¹
3	ASTM Photo No. 9, Type 1
2	ASTM Photo No. 8, Type 1
1	ASTM Photo No. 7, Type 1
0	ASTM Photo No. 6, Type 1 or Worse
<u>Rating</u>	<u>B. Corrosion Accompanied by Blistering</u>
5	None
4	Trace, less than 5 defects on 4x12 inch panel
3	ASTM Photo No. 8, Type 2 ¹
2	ASTM Photo No. 7, Type 2
1	ASTM Photo No. 6, Type 2
0	ASTM Photo No. 4, Type 2 or Worse
<u>Rating</u>	<u>C. Blistering Alone</u>
5	None
4	Trace - ASTM Blister Size 2 on 4x12 inch panel - 2 max. ² ASTM Blister Size 4 on 4 12 inch panel - 4 max. ASTM Blister Size 6 on 4x12 inch panel - 6 max. ASTM Blister Size 8 on 4x12 inch panel - 8 max.
3	ASTM Few - Record Blister Size
2	ASTM Medium - Record Blister Size
1	ASTM Medium-Dense - Record Blister Size
0	ASTM Dense - Record Blister Size

*Select applicable condition.

¹Reference Standards - Federal Test Method No. 141a, Method 6451.

²Reference Standards - Federal Test Method No. 141a, Method 6461.

TABLE II - Continued

IV. Substrate Condition

<u>Rating</u>	<u>Pitting and/or Corrosion Spots</u>
5	None
4	Trace - ASTM Blister Size 2 on 4x12 inch panel - 2 max. ² ASTM Blister Size 4 on 4x12 inch panel - 4 max. ASTM Blister Size 6 on 4x12 inch panel - 6 max. ASTM Blister Size 8 on 4x12 inch panel - 8 max.
3	ASTM Few - Record Size
2	ASTM Medium - Record Size
1	ASTM Medium-Dense - Record Size
0	ASTM Dense - Record Size

²Reference Standards - Federal Test Method No. 141a, Method 6461.

APPENDIX B - FORMULAS

Specification Epoxy Primer Coatings

<u>Ingredient</u>	<u>MIL-P-52192</u>		<u>MIL-P-27316</u>	
	<u>Formula 1</u>		<u>Formula 2</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Red iron oxide	71.6	1.67	--	--
Basic Lead silico chromate	190.0	5.57	--	--
Calcium chromate	--	--	240.3	6.60
Rutile titanium dioxide	--	--	242.1	6.92
Fibrous magnesium silicate	51.8	2.18	--	--
Micronized magnesium silicate	51.8	2.29	--	--
Suspension agent	4.0	0.27	--	--
Epoxy resin, 450-550 epoxide eq.	139.2	13.85	--	--
Epoxy resin, 2000-2500 epoxide eq.	72.3	7.57	--	--
Epoxy resin, 2500-4000 epoxide eq.	--	--	204.9	20.66
Urea formaldehyde resin, 60% N.V.	13.4	1.58	--	--
Xylene	158.3	21.92	--	--
Toluene	--	--	148.4	20.56
Methyl isobutyl ketone	29.9	4.48	116.6	17.45
Butyl alcohol	96.3	14.27	--	--
Cellosolve acetate	35.8	4.42	--	--
Cellosolve	--	--	198.5	25.61
Isopropyl alcohol	--	--	14.5	2.20
	<u>914.4</u>	<u>80.07</u>	<u>1165.3</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Amine adduct	80.8	9.62	--	--
Polyamide resin	--	--	107.6	12.96
Methyl isobutyl ketone	24.9	3.73	166.1	24.86
Cellosolve	24.8	3.20	200.0	25.75
Xylene	24.9	3.45	179.5	24.86
Toluene	--	--	40.4	5.60
Isopropyl alcohol	--	--	39.3	5.97
	<u>155.4</u>	<u>20.00</u>	<u>732.9</u>	<u>100.00</u>
Pigment volume concentration		32.1%		28.6%

Specification and Experimental Control Epoxy Primer Coatings

Ingredient	MIL-P-23377A		Experimental Control	
	Formula 3		Formula 4	
	Pounds	Gallons	Pounds	Gallons
<u>Component A, Pigmented Epoxy Resin</u>				
Strontium chromate	54.2	1.61	54.2	1.61
Rutile titanium dioxide	119.0	3.40	--	--
Red iron oxide	--	--	271.1	6.46
Fibrous magnesium silicate	115.3	5.11	211.8	8.92
Diatomaceous silica	59.5	3.57	--	--
Suspension agent	--	--	5.4	0.36
Silicone resin, 60% N.V.	--	--	4.9	0.60
Epoxy resin solution, 75% N.V., 450-550 epoxide eq.	377.6	41.68	--	--
Epoxy resin, 450-550 epoxide eq.	--	--	286.6	28.52
Methyl isobutyl ketone	201.1	30.10	89.4	13.38
Butyl cellosolve	--	--	60.3	8.04
Butyl alcohol	--	--	36.0	5.34
Toluene	104.7	14.53	--	--
Xylene	--	--	193.3	26.77
	<u>1031.4</u>	<u>100.00</u>	<u>1213.0</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin solution, 70% N.V.	218.6	27.63	--	--
Amino silane	--	--	26.5	3.12
Butyl alcohol	139.9	20.73	6.3	0.94
Isopropyl alcohol	139.9	21.36	--	--
Toluene	218.6	30.28	--	--
Xylene	--	--	60.9	8.44
	<u>717.0</u>	<u>100.00</u>	<u>93.7</u>	<u>12.50</u>
Pigment volume concentration		22.5%		35.2%

Epoxy-Polyamide, Amino Silane Experimental Primers

<u>Ingredient</u>	<u>Zinc Chromate</u>		<u>Strontium Chromate</u>	
	<u>Formula 5</u>		<u>Formula 6</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Zinc chromate	177.6	6.18	--	--
Strontium chromate	--	--	208.1	6.18
Fibrous magnesium silicate	29.2	1.23	29.2	1.23
Suspension agent	2.1	0.14	2.1	0.14
Epoxy resin, 450-550 epoxide eq.	197.4	19.64	197.4	19.64
Urea formaldehyde resin	16.7	1.96	16.7	1.96
Methyl isobutyl ketone	62.7	9.38	62.7	9.38
Butyl cellosolve	42.1	5.62	42.1	5.62
Butanol	25.3	3.75	25.3	3.75
Xylene	135.5	18.77	135.5	18.77
	<u>688.6</u>	<u>66.67</u>	<u>719.1</u>	<u>66.67</u>
<u>Component B, Catalyst</u>				
Polyamide resin	106.3	12.88	106.3	12.88
Methyl isobutyl ketone	33.0	4.94	33.0	4.94
Butyl cellosolve	22.2	2.96	22.2	2.96
Butanol	13.3	1.97	13.3	1.97
Xylene	71.3	9.88	71.3	9.88
Amino silane	6.0	0.70	6.0	0.70
	<u>252.1</u>	<u>33.33</u>	<u>252.1</u>	<u>33.33</u>
Pigment volume concentration		18.1%		18.1%

Vinyl Zinc Chromate Primers

<u>Ingredient</u>	<u>MIL-P-15930B</u>			
	<u>Formula 7</u>		<u>Formula 8</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
Basic zinc chromate	78.1	2.49	130.5	4.16
Fibrous magnesium silicate	48.9	2.06	10.9	0.46
Lampbalck	1.9	0.13	2.1	0.14
Aluminum stearate	1.0	0.12	1.1	0.13
Vinyl chloride-acetate copolymer	141.4	12.48	144.0	12.71
Tricresyl phosphate	12.2	1.26	12.4	1.28
Methyl isobutyl ketone	336.5	50.38	335.2	50.18
Toluene	224.4	31.08	223.4	30.94
	<u>844.4</u>	<u>100.00</u>	<u>859.6</u>	<u>100.00</u>

Pigment volume concentration

25.9%

25.9%

Epoxy Primers, MIL-P-23377A (Amended) and Amino Silane Type

<u>Ingredient</u>	<u>MIL-P-23377A</u>		<u>Amino Silane</u>	
	<u>Formula 9</u>		<u>Formula 10</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Strontium chromate	212.1	6.85	186.4	6.02
Rutile titanium dioxide	40.6	1.16	35.7	1.02
Micronized magnesium silicate	86.9	3.85	76.3	3.38
Diatomaceous silica	45.5	2.73	39.8	2.39
Suspension agent	12.0	0.80	10.7	0.71
Silicone resin, 60% N.V.	--	---	5.5	0.67
Epoxy resin solution, 75% N.V., 450-550 epoxide eq.	321.2	35.45	--	--
Epoxy resin, 450-550 epoxide eq.	--	---	321.2	31.96
Methyl isobutyl ketone	222.3	33.28	89.9	13.46
Butyl cellosolve	--	--	60.5	8.07
Butyl alcohol	--	--	36.1	5.35
Xylene	--	--	194.7	26.97
Toluene	114.7	15.88	--	--
	<u>1055.3</u>	<u>100.00</u>	<u>1056.8</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin solution, 70% N.V.	191.0	24.14	--	--
Amino silane	--	--	29.7	3.49
Butyl alcohol	146.2	21.66	6.1	0.90
Isopropyl alcohol	146.3	22.33	--	--
Toluene	230.1	31.87	--	--
Xylene	--	--	58.6	8.11
	<u>713.6</u>	<u>100.00</u>	<u>94.4</u>	<u>12.50</u>
Pigment volume concentration		27.5%		27.5%

Epoxy Primers, Pigmentation and PVC of MIL-P-15930B

<u>Ingredient</u>	<u>Polyamide</u>		<u>Amino Silane</u>	
	<u>Formula 11</u>		<u>Formula 12</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Basic zinc chromate	245.9	7.84	208.6	6.65
Fibrous magnesium silicate	154.1	6.49	130.6	5.50
Lampblack	6.1	0.41	5.2	0.35
Aluminum stearate	3.2	0.38	2.7	0.32
Silicone resin, 60% N.V.	6.5	0.79	5.5	0.68
Epoxy resin, 450-550 epoxide eq.	259.6	25.83	329.5	32.79
Methyl isobutyl ketone	97.4	14.58	89.7	13.43
Butyl cellosolve	65.5	8.73	60.5	8.06
Butyl alcohol	39.2	5.81	36.1	5.35
Xylene	210.4	29.14	194.0	26.87
	<u>1087.9</u>	<u>100.00</u>	<u>1062.4</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin	139.9	16.96	--	--
Amino silane	--	--	29.7	3.49
Methyl isobutyl ketone	138.7	20.76	--	--
Butyl cellosolve	93.5	12.46	--	--
Butyl alcohol	56.0	8.30	6.1	0.91
Xylene	299.8	41.52	58.5	8.10
	<u>727.9</u>	<u>100.00</u>	<u>94.3</u>	<u>12.50</u>
Pigment volume concentration	25.9%		25.9%	

Epoxy Primers, PVC of MIL-P-15930B, 90% Basic Zinc Chromate

<u>Ingredient</u>	<u>Polyamide</u>		<u>Amino Silane</u>	
	<u>Formula 13</u>	<u>Formula 14</u>	<u>Formula 13</u>	<u>Formula 14</u>
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Basic zinc chromate	401.8	12.81	341.9	10.90
Fibrous magnesium silicate	34.0	1.43	28.7	1.21
Lampblack	6.4	0.43	5.5	0.37
Aluminum stearate	3.3	0.40	2.8	0.34
Silicone resin, 60% N.V.	6.5	0.80	5.5	0.68
Epoxy resin, 450-550 epoxide eq.	258.9	25.76	329.5	32.79
Methyl isobutyl ketone	97.5	14.60	89.7	13.43
Butyl cellosolve	65.7	8.76	60.5	8.06
Butyl alcohol	39.3	5.82	36.2	5.37
Xylene	210.8	29.19	193.9	26.85
	<u>1124.2</u>	<u>100.00</u>	<u>1094.2</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin	139.5	16.91	--	--
Amino silane	--	--	29.7	3.49
Methyl isobutyl ketone	138.7	20.76	--	--
Butyl cellosolve	93.5	12.47	--	--
Butyl alcohol	56.1	8.31	6.1	0.91
Xylene	300.0	41.55	58.5	8.10
	<u>727.8</u>	<u>100.00</u>	<u>94.3</u>	<u>12.50</u>
Pigment volume concentration		25.9%		25.9%

Epoxy Primers, PVC 35.2%, Pigmentation of MIL-P-15930B

<u>Ingredient</u>	<u>Polyamide</u>		<u>Amino Silane</u>	
	<u>Formula 15</u>		<u>Formula 16</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Basic zinc chromate	315.2	10.05	278.5	8.88
Fibrous magnesium silicate	197.5	8.32	174.5	7.35
Lampblack	7.9	0.53	6.9	0.49
Aluminum stearate	4.0	0.48	3.5	0.42
Silicone resin, 60% N.V.	5.4	0.66	4.9	0.60
Epoxy resin, 450-550 epoxide eq.	214.3	21.32	282.5	28.11
Methyl isobutyl ketone	98.0	14.67	90.6	13.56
Butyl cellosolve	66.0	8.80	61.0	8.13
Butyl alcohol	39.4	5.84	36.5	5.40
Xylene	211.8	29.33	195.6	27.09
	<u>1159.5</u>	<u>100.00</u>	<u>1134.5</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin	115.5	14.00	--	--
Amino silane	--	--	26.2	3.08
Methyl isobutyl ketone	143.6	21.50	--	--
Butyl cellosolve	96.8	12.90	--	--
Butyl alcohol	58.1	8.60	6.4	0.95
Xylene	310.5	43.00	61.2	8.47
	<u>724.5</u>	<u>100.00</u>	<u>93.8</u>	<u>12.50</u>
Pigment volume concentration		35.2%		35.2%

Epoxy Primers, PVC 35.2%, 90% of Pigment Basic Zinc Chromate

<u>Ingredient</u>	<u>Polyamide</u>		<u>Amino Silane</u>	
	<u>Formula 17</u>		<u>Formula 18</u>	
	<u>Pounds</u>	<u>Gallons</u>	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Epoxy Resin</u>				
Basic zinc chromate	511.0	16.29	431.9	13.77
Fibrous magnesium silicate	43.0	1.81	36.1	1.52
Lampblack	8.2	0.55	6.9	0.46
Aluminum stearate	4.3	0.51	3.7	0.44
Silicone resin, 60% N.V.	5.3	0.65	4.6	0.57
Epoxy resin, 450-550 epoxide eq.	211.8	21.07	267.1	26.58
Methyl isobutyl ketone	98.8	14.79	94.7	14.18
Butyl cellosolve	66.5	8.87	63.8	8.50
Butyl alcohol	39.8	5.89	38.1	5.65
Xylene	213.5	29.57	204.5	28.33
	<u>1202.2</u>	<u>100.00</u>	<u>1151.4</u>	<u>100.00</u>
<u>Component B, Catalyst</u>				
Polyamide resin	114.1	13.83	--	--
Amino silane	--	--	24.7	2.91
Methyl isobutyl ketone	143.9	21.54	--	--
Butyl cellosolve	97.0	12.93	--	--
Butyl alcohol	58.2	8.62	6.1	9.90
Xylene	311.0	43.08	62.7	8.69
	<u>724.2</u>	<u>100.00</u>	<u>93.5</u>	<u>12.50</u>
Pigment volume concentration		35.2%		35.2%

Polyurethane Primer, Pigmentation and PVC of MIL-P-15930B

<u>Ingredient</u>	<u>Formula 19</u>	
	<u>Pounds</u>	<u>Gallons</u>
<u>Component A, Pigmented Polyester</u>		
Basic zinc chromate	262.9	8.38
Fibrous magnesium silicate	164.5	6.93
Lampblack	6.4	0.43
Aluminum stearate	3.3	0.40
Silicone resin, 60% N.V.	0.6	0.06
Polyester resin, 260-280 hydroxy number	245.5	22.46
Ethyl acetate (urethane grade)	228.2	30.39
Methyl ethyl ketone	73.2	10.93
Cellosolve acetate (urethane grade)	90.1	11.12
Xylene	63.5	8.79
Zinc octoate, 35% N.V.	0.8	0.11
	<u>1139.0</u>	<u>100.00</u>
 <u>Component B, Hexamethylene Diisocyanate Adduct</u>		
Diisocyanate adduct, 75% N.V.	299.2	33.50
Cellosolve acetate (urethane grade)	60.6	7.48
Methyl ethyl ketone	60.4	9.02
	<u>420.2</u>	<u>50.00</u>
 Pigment volume concentration		 25.9%

APPENDIX C - TEST DATA

TABLE I

Panama Exposure, Breakwater

Steel - Zinc Phosphate Pretreated, TT-C-490 Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE II)

Primer	Topcoat	6 Months						15 Months						21 Months					
		Under-		Sub-	Under-		Sub-	Under-		Sub-	Under-		Sub-	Under-		Sub-			
		Score	cut		Score	cut		Score	cut		Score	cut		Score	cut		Score	cut	
1	TT-E-529 None	3 3	3 3	5 A-4	5 4	0-1/4 0-1/4	0-1/4 0-1/4	5 B-0	5 0-2	0-1/2 -	0-1/2 -	5 -	5 -	5 -	5 -				
2	TT-E-529 None	2 0-3/8	3 3	5 A-1	3-8 3-8	0-1/4 -	0-5/16 -	5 -	2-8 -	0-3/8 -	0-3/8 -	5 -	2-8 -	5 -	2-8 -				
3	TT-E-529 None	2 2	2 2	5 A-2	5 3-8	0-3/8 0-1/2	0-3/8 0-1/2	5 B-3	5 3-8	0-1/2 -	0-1/2 -	5 -	5 3-8	5 -	5 -				
4	TT-E-529 None	2 2	2 2	5 5	5 5	0-3/8 0-3/8	0-3/8 0-3/8	5 B-2	5 3-8	0-1/2 -	0-1/2 -	5 -	5 3-8	5 -	5 -				
5	TT-E-529 None	0-5/16 0-5/16	0-1/4 0-5/16	5 A-4	5 4	0-1/2 0-1/2	0-1/2 0-1/2	5 A-2	5 4	0-1 -	0-1 -	5 -	5 4	5 -	5 -				
6	TT-E-529 None	0-5/16 0-5/16	0-1/4 0-1/2	5 A-3	5 3-8	0-1/2 -	0-1/2 -	5 -	5 -	0-3/4 -	0-3/4 -	5 -	5 -	5 -	5 -				

TABLE 2

Panama Exposure, Breakwater

Aluminum - Solvent Cleaned
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	Topcoat	6 Months						15 Months			21 Months				
		Under-		Sub-		Score	Under-		Sub-		Score	Under-		Sub-	
		cut	Surface	strate	Surface		strate	cut	Surface	strate		cut	Surface	strate	
1	TT-E-529 None	0-1 0-1	5 B-0	5 0-6	0-1 -	0-1	0-1	5 B-3	3-6	-	-	-	-	-	
2	TT-E-529 None	5 5	5 C-1	5 4	5 -	4	-	5 -	5	5	5	4	-	5	
3	TT-E-529 None	3 5	5 5	5 5	0-1 3	0-1	0-1	5 5	5 5	-	1	5	-	5	
4	TT-E-529 None	3 5	5 5	5 5	3 5	5	5	5 5	5 5	3	4	5	5	5	
5	TT-E-529 None	5 5	5 5	5 5	4 4	5	5	5 5	5 5	3	4	5	5	5	
6	TT-E-529 None	5 5	5 5	5 5	5 5	5	5	5 B-3	5 3-8	4	5	5	5	5	

TABLE 3

Panama Exposure, Breakwater

Aluminum - Chemically Pretreated, MIL-C-5541, Type II
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Topcoat	Exposure Time - Ratings (Appendix A, TABLE II)											
		6 Months				15 Months				21 Months			
		Score	Under-cut	Surface	Substrate	Score	Under-cut	Surface	Substrate	Score	Under-cut	Surface	Substrate
1	TT-E-529 None	4	4	5	5	4	4	5	5	4	4	5	5
		4	4	5	5	3	4	5	5	2	4	5	5
2	TT-E-529 None	5	5	5	5	5	5	5	5	4	4	5	5
		5	5	C-0	4	-	-	-	-	-	-	-	-
3	TT-E-529 None	5	5	5	5	5	5	5	5	4	5	5	5
		5	5	5	5	5	5	5	5	4	5	5	5
4	TT-E-529 None	5	5	5	5	5	5	5	5	4	5	5	5
		5	5	5	5	5	5	5	5	5	5	5	5
5	TT-E-529 None	5	5	5	5	4	5	5	5	4	5	5	5
		5	5	5	5	5	5	5	5	5	5	5	5
6	TT-E-529 None	5	5	5	5	4	5	5	5	4	5	5	5
		5	5	5	5	5	5	5	5	4	5	5	5

TABLE 4

Panama Exposure, Breakwater

Magnesium - Solvent Cleaned
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	Topcoat	6 Months						15 Months						21 Months							
		Under-		Sub-		Score	Surface	Under-		Sub-		Score	Surface	Under-		Sub-		Score	Surface	Sub-	
		cut	0-5/16	0	1-6			cut	0	3	3-8			cut	0	3	3-8				cut
1	TT-E-529 None	0	0-5/16	0	0	5	5	-	-	-	-	-	-	-	-	-	-	-	-	-	
2	TT-E-529 None	0	4	0	3	A-3	0	3	3	3	0	A-2	2-8	1	1	1	1	B-2	1-6	-	
3	TT-E-529 None	3	5	2	5	5	5	3	1	3	0-1/2	0-1/2	2-8	5	5	1	1	A-4	4-6	-	
4	TT-E-529 None	4	5	4	5	5	5	4	5	4	5	A-2	3-8	5	5	4	5	C-4	5	-	
5	TT-E-529 None	4	3	5	4	5	5	4	1	0-1/2	4	A-3	5	5	0-1/2	0-1/4	3	5	A-3	5	4-8
6	TT-E-529 None	0	3	2	0	8-2	2-6	-	-	-	-	-	2-6	3	-	-	-	-	-	-	-

TABLE 5

Panama Exposure, Breakwater

Magnesium - Chemically Pretreated, MIL-M-3171 Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE II)

Primer	Topcoat	Exposure Time - Ratings (Appendix A, TABLE II)											
		6 Months			15 Months			21 Months					
		Under- cut	Surface	Sub- strate	Score	Under- cut	Surface	Sub- strate	Score	Under- cut	Surface	Sub- strate	
1	TT-E-529 None	4 3	5 A-1	5 1-6	3 -	4 -	5 -	5 -	3 -	3 -	5 -	5 -	5 -
2	TT-E-529 None	5 4	5 A-3	5 4-8	4 4	5 5	5 A-3	5 2-6	4 -	4 -	5 -	5 -	5 -
3	TT-E-529 None	5 5	5 5	5 5	4 4	5 5	5 A-4	5 4-8	4 4	4 5	5 5	5 4-8	5 4-8
4	TT-E-529 None	5 5	5 5	5 5	4 4	5 5	5 5	5 4	4 5	4 5	5 5	5 4-8	5 4-8
5	TT-E-529 None	5 5	5 5	5 5	4 4	5 5	5 5	5 5	4 4	4 5	5 5	5 4-8	5 4-8
6	TT-E-529 None	5 5	5 5	5 5	4 4	5 5	5 A-3	5 3-8	4 4	4 5	5 A-3	5 3-8	5 A-3

TABLE 6

Panama Exposure, Breakwater

Magnesium - Chemically Pretreated, MIL-M-3171 Type III
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Topcoat	Exposure Time - Ratings (Appendix A, TABLE II)											
		6 Months				15 Months				21 Months			
		Score	Under-cut	Surface	Substrate	Score	Under-cut	Surface	Substrate	Score	Under-cut	Surface	Substrate
1	TT-E-529 None	4	4	5	5	4	4	5	5	3	3	5	5
2	TT-E-529 None	5	5	5	5	4	5	5	5	4	5	A-3	A-3
3	TT-E-529 None	5	5	5	5	4	5	5	5	4	5	5	5
4	TT-E-529 None	5	5	5	5	4	5	5	5	4	5	5	5
5	TT-E-529 None	5	5	5	5	5	5	5	5	5	5	5	5
6	TT-E-529 None	5	5	5	5	5	5	5	5	5	5	5	5

TABLE 8

Panama Exposure, Breakwater

Steel - Zinc Phosphate Pretreated, TT-C-490 Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	6 Months			15 Months			21 Months		
	Score	Under- cut	Sub- strate	Score	Under- cut	Sub- strate	Score	Under- cut	Sub- strate
1	3	3	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
4	2	2	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
7	2	2	5	0-3/8	0-3/8	5	0-5/8	0-5/8	5
8	3	3	5	0-3/8	0-3/8	5	0-1/2	0-1/2	B-4
9	2	2	5	0-3/8	0-3/8	5	0-9/16	0-9/16	5
10	2	2	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
11	1	1	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
12	2	2	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
13	1	1	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
14	3	3	5	0-3/8	0-3/8	5	0-1/2	0-1/2	B-3
15	1	1	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
16	2	2	5	0-5/16	0-5/16	5	0-1/2	0-1/2	B-4
17	1	1	5	0-3/8	0-3/8	5	0-1/2	0-1/2	5
18	2	2	B-3	0-1/2	0-1/2	B-3	0-5/8	0-5/8	B-3
19	3	3	5	0-5/16	0-5/16	5	0-1/2	0-1/2	B-4

TABLE 9

Panama Exposure, Breakwater

Aluminum - Alkali Cleaned
 Topcoat - TT-F-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	6 Months			15 Months			21 Months		
	Under-	Sub-	Sub-	Under-	Sub-	Sub-	Under-	Sub-	Sub-
	cut	strate	strate	cut	strate	strate	cut	strate	strate
1	2	5	5	0-1	5	5	-	5	-
4	4	5	4	4	5	5	3	5	5
7	4	5	5	0-1/2	5	5	0-5/8	5	5
8	5	5	5	4	5	5	3	5	5
9	5	5	5	4	5	5	3	5	5
10	5	5	5	5	5	5	5	5	5
11	5	5	5	0-1/2	5	5	0-5/8	5	5
12	4	5	5	0-1/4	5	5	0-1/4	5	5
13	5	5	5	4	5	5	4	5	5
14	5	5	5	4	5	5	4	5	5
15	5	5	5	4	5	5	4	5	5
16	5	5	5	4	5	5	4	5	5
17	5	5	5	5	5	5	5	5	5
18	5	5	5	5	5	5	5	5	5
19	3	5	5	0-3/4	5	5	-	5	-

TABLE 10
Panama Exposure, Breakwater
Aluminum - Chemically Pretreated, MIL-C-5541, Type II
Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE 11)											
	6 Months			15 Months			21 Months			21 Months		
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate
1	4	5	5	0-1/4	4	5	0-1/4	4	5	0-1/4	4	5
4	5	5	5	4	4	5	4	4	5	4	4	5
7	5	5	5	5	4	5	4	4	5	4	4	5
8	5	5	5	4	4	5	4	4	5	4	4	5
9	5	5	5	5	5	5	5	5	5	5	5	5
10	5	5	5	5	5	5	5	5	5	5	5	5
11	5	5	5	5	5	5	5	5	5	5	5	5
12	5	5	5	4	4	5	4	4	5	4	4	5
13	5	5	5	5	5	5	5	5	5	5	5	5
14	5	5	5	4	4	5	4	4	5	4	4	5
15	5	5	5	4	4	5	4	4	5	4	4	5
16	5	5	5	4	4	5	4	4	5	4	4	5
17	5	5	5	5	5	5	5	5	5	5	5	5
18	5	5	5	5	5	5	5	5	5	5	5	5
19	5	5	5	4	4	5	4	4	5	4	4	5

TABLE 11

Panama Exposure, Breakwater

Magnesium - Alkali Cleaned
 Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	6 Months			15 Months			21 Months		
	Score	Under- cut	Sub- strate	Score	Under- cut	Sub- strate	Score	Under- cut	Sub- strate
1	3	3	5	0-3/8	0-3/8	B-3	-	-	-
4	5	5	5	5	5	5	4	5	5
7	4	4	4	2	2	B-3	0-1/4	0-1/4	B-3
8	4	5	4	2	2	B-4	0-1/4	0-1/4	B-0
9	4	5	4	3	3	B-3	1	1	B-2
10	5	5	4	4	4	B-2	4	4	B-2
11	4	4	5	0-1/2	0-1/2	C-4	0-1/2	0-1/2	B-4
12	5	5	5	4	4	5	4	4	5
13	2	5	5	0-1/2	0-1/2	A-4	0-1/2	0-1/2	B-3
14	4	5	5	4	5	A-4	4	5	A-4
15	5	5	5	4	4	5	3	3	5
16	5	5	5	4	4	5	4	4	5
17	4	4	5	3	3	B-3	0-1/2	0-1/2	B-3
18	5	5	5	4	4	A-3	4	4	B-3
19	3	5	4	0-1/4	0-1/4	B-0	-	-	-

TABLE 12

Panama Exposure, Breakwater

Magnesium - Anodically Pretreated, MIL-M-45202, Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE 11)											
	6 Months			15 Months			21 Months			21 Months		
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate
1	5	5	5	4	4	4	4	5	5	4	4	5
4	5	5	5	4	4	4	4	5	5	4	4	5
7	5	5	5	4	4	4	4	5	5	4	4	5
8	5	5	5	4	4	4	4	5	5	4	4	5
9	5	5	5	4	4	4	4	5	5	4	4	5
10	5	5	5	4	4	4	4	5	5	4	4	5
11	5	5	5	4	4	4	4	5	5	4	4	5
12	5	5	5	4	4	4	4	5	5	4	4	5
13	5	5	5	4	4	4	4	5	5	4	4	5
14	5	5	5	4	4	4	4	5	5	4	4	5
15	5	5	5	4	4	4	4	5	5	4	4	5
16	5	5	5	4	4	4	4	5	5	4	4	5
17	5	5	5	4	4	4	4	5	5	4	4	5
18	5	5	5	4	4	4	4	5	5	4	4	5
19	5	5	5	4	4	4	4	5	5	4	4	5

TABLE 13

Panama Exposure, Rain Forest

Steel - Zinc Phosphate Pretreated, TT-C-490 Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE 11)											
	6 Months			15 Months			21 Months					
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate			
1	5	5	5	5	5	5	5	5	5	5	5	
4	5	5	5	5	5	5	5	5	5	5	5	
7	5	5	5	4	5	5	4	5	5	5	5	
8	5	5	5	5	5	5	5	5	5	5	5	
9	5	5	5	5	5	5	5	5	5	5	5	
10	5	5	5	5	5	5	5	5	5	5	5	
11	5	5	5	5	5	5	5	5	5	5	5	
12	5	5	5	5	5	5	5	5	5	5	5	
13	5	5	5	5	5	5	5	5	5	5	5	
14	5	5	5	5	5	5	5	5	5	5	5	
15	5	5	5	5	5	5	5	5	5	5	5	
16	5	5	5	5	5	5	5	5	5	5	5	
17	5	5	5	5	5	5	5	5	5	5	5	
18	5	5	5	5	5	5	5	5	5	5	5	
19	5	5	5	5	5	5	5	5	5	5	5	

TABLE 14

Panama Exposure, Rain Forest

Aluminum - Alkali Cleaned

Topcoat - TT-E-529, Class A, Olive Drab

Exposure Time - Ratings (Appendix A, TABLE 11)

Primer	6 Months			15 Months			21 Months		
	Under-	Sub-	Under-	Sub-	Under-	Sub-	Under-	Sub-	
	cut	strate	cut	strate	cut	strate	cut	strate	
1	5	5	0-1/2	5	0-1/2	5	0-1/2	5	
4	5	5	4	5	4	5	0-1/2	5	
7	5	5	5	5	5	5	5	5	
8	5	5	5	5	5	5	5	5	
9	5	5	5	5	5	5	5	5	
10	5	5	5	5	5	5	5	5	
11	5	5	4	5	4	5	3	5	
12	5	5	5	5	5	5	5	5	
13	5	5	5	5	5	5	5	5	
14	5	5	5	5	5	5	5	5	
15	5	5	5	5	5	5	5	5	
16	5	5	5	5	5	5	5	5	
17	5	5	5	5	5	5	5	5	
18	5	5	5	5	5	5	5	5	
19	5	5	0-1/4	5	0-5/8	5	0-5/8	5	

TABLE 15

Panama Exposure, Rain Forest

Aluminum - Chemically Pretreated, MIL-C-5541, Type II
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE 11)											
	6 Months			15 Months			21 Months					
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate			
1	4	5	5	4	5	5	3	5	5	5	5	
4	5	5	5	5	5	5	4	5	5	5	5	
7	5	5	5	5	5	5	4	5	5	5	5	
8	5	5	5	5	5	5	5	5	5	5	5	
9	5	5	5	5	5	5	5	5	5	5	5	
10	5	5	5	5	5	5	5	5	5	5	5	
11	5	5	5	5	5	5	4	5	5	5	5	
12	5	5	5	5	5	5	4	5	5	5	5	
13	5	5	5	5	5	5	5	5	5	5	5	
14	5	5	5	5	5	5	5	5	5	5	5	
15	5	5	5	5	5	5	5	5	5	5	5	
16	5	5	5	5	5	5	5	5	5	5	5	
17	5	5	5	5	5	5	5	5	5	5	5	
18	5	5	5	5	5	5	5	5	5	5	5	
19	5	5	5	4	5	5	5	5	5	5	5	

TABLE 16

Panama Exposure, Rain Forest
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE 11)											
	6 Months			15 Months			21 Months			24 Months		
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate
1	5	5	5	5	C-3-1/64	4-1/64	5	5	5	5	C-0-1/64	3-1/64
4	5	5	5	5	5	5	5	5	5	5	5	5
7	5	5	5	5	5	5	5	5	5	5	5	5
8	5	5	5	5	5	5	5	5	5	5	C-0-1/32	C-0-1/32
9	5	C-0-1/32	5	-	-	-	-	-	-	-	-	-
10	5	C-0-1/32	5	5	C-2-1/32	5	5	5	5	5	C-0-1/32	5
11	5	5	5	5	5	5	5	5	5	5	C-0-1/32	3-1/32
12	5	5	5	5	5	5	5	5	5	5	5	5
13	5	5	5	5	5	5	5	5	5	5	5	5
14	5	5	5	5	5	5	5	5	5	5	5	5
15	5	5	5	5	5	5	5	5	5	5	C-2-8	4
16	5	5	5	5	5	5	5	5	5	5	C-2-8	4
17	0-1/4	5	5	0-1/4	5	5	0-1/2	0-1/2	5	5	5	5
18	5	5	5	5	5	5	5	5	5	5	C-4-8	4
19	5	C-0-8	3	-	-	-	-	-	-	-	-	-

TABLE 17

Panama Exposure, Rain Forest

Magnesium - Anodically Pretreated, MIL-M-45202 Type I
 Topcoat - TT-E-529, Class A, Olive Drab

Primer	Exposure Time - Ratings (Appendix A, TABLE II)											
	6 Months			15 Months			21 Months					
	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate	Under- cut	Surface	Sub- strate
1	5	5	5	5	5	5	5	5	5	5	5	5
4	5	5	5	5	5	5	5	5	5	5	5	5
7	5	5	5	5	5	5	5	5	5	5	5	5
8	5	5	5	5	5	5	5	5	5	C-0-1/32	5	4
9	5	5	5	5	5	5	5	5	5	5	5	5
10	5	5	5	5	5	5	5	5	5	5	5	5
11	5	5	5	5	5	5	5	5	5	5	5	5
12	5	5	5	5	5	5	5	5	5	5	5	5
13	5	5	5	5	5	5	5	5	5	5	5	5
14	5	5	5	5	5	5	5	5	5	C-4-1/64	5	5
15	5	5	5	5	5	5	5	5	5	C-4-1/64	5	5
16	5	5	5	5	5	5	5	5	5	5	5	5
17	5	5	5	5	5	5	5	5	5	5	5	5
18	5	5	5	5	5	5	5	5	5	5	5	5
19	5	5	5	5	5	5	5	5	5	C-3-8	5	4

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R&D		
<i>(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)</i>		
1 ORIGINATING ACTIVITY (Corporate author) U.S. Army Aberdeen Research & Development Center Coating & Chemical Laboratory Aberdeen Proving Ground, Maryland 21005		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3 REPORT TITLE DEVELOPMENT OF A MULTI-METAL PRIMER		
4 DESCRIPTIVE NOTES (Type of report and inclusive dates) Final Report		
5 AUTHOR(S) (Last name, first name, initial) Koutek, Stanley F.		
6 REPORT DATE October 1969	7a. TOTAL NO. OF PAGES 45	7b. NO. OF REFS
8a. CONTRACT OR GRANT NO. AMCMS Code No. 502E.11.29500	9a. ORIGINATOR'S REPORT NUMBER(S) CCL #272	
b. PROJECT NO. IT062105A329	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
c.		
d.		
10. AVAILABILITY/LIMITATION NOTICES This document has been approved for public release and sale; its distribution is unlimited. Qualified requesters may obtain copies of this report from Defense Documentation Center.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY U.S. Army Materiel Command Washington, D. C. 20315	
13. ABSTRACT Some currently employed specification epoxy primers and experimental formulations were exposed at the Panama test sites for corrosion resistance studies. Inhibiting pigments considered included strontium, zinc and basic zinc chromates up to 90% by weight of the total pigmentation at different pigment volume concentrations. Polyamide and amino-silane curing agents were used. Experimental vinyl and polyurethane primers offered no significant improvement in corrosion resistance when compared to two existing specification primers, particularly on pretreated substrates. It is recommended that MIL-P-52192, Primer Coat, Epoxy be used for ferrous substrates and MIL-P-23377, Primer Coating, Epoxy Polyamide, Chemical and Solvent Resistant, for aluminum, magnesium or bi-metallic materials.		

DD FORM 1473
1 JAN 64

42

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Epoxy, Polyurethane, Vinyl Primers Corrosion Resistance Tropical Exposure, Ferrous Metals Non-ferrous Metal						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.