

AD 721 292



AD

AMMRC CR 71-2/1

THE EFFECTS OF THE SURFACE LAYER
ON PLASTIC DEFORMATION AND CRACK PROPAGATION

MARCH 1971

I. R. KRAMER
MARTIN MARIETTA CORPORATION
DENVER DIVISION
DENVER, COLORADO

DDC
RECEIVED
APR 28 1971

SEMI-ANNUAL

This document has been approved for public release and sale; its distribution is unlimited.

Prepared for

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

**BEST
AVAILABLE COPY**

AMMRC CR 71-2/1

THE EFFECTS OF THE SURFACE LAYER
ON PLASTIC DEFORMATION AND CRACK PROPAGATION

I. R. KRAMER
MARTIN MARIETTA CORPORATION
DENVER DIVISION
DENVER, COLORADO
MARCH 1971

SEMI-ANNUAL

ARPA ORDER 180-0-7400

This document has been approved for public release and sale; its distribution is unlimited.

Prepared for

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

ABSTRACT

We have measured the rate of crack propagation as a function of frequency in Ripling type specimens of aluminum 2014-T6. It was observed that the rate of crack propagation was decreased from 1.7×10^{-5} in/cycle to 1.2×10^{-6} in/cycle when the frequency is increased from 1 to 20 cycles/second. It was also observed that the plot of crack length vs. number of cycles is linear indicating a constant rate of growth up to a crack length of one inch. The effect of prestressing followed by aging at 250°F for 2 to 4 hours was to decrease the rate of crack propagation from 1.02×10^{-6} to 9.8×10^{-7} in/cycle. This shows that prestressing followed by aging has a beneficial effect on the crack growth resistance of aluminum 2014-T6.

Center notched specimens of titanium (6 Al-4V) were tested in tension under a cyclic stress of 7,000 to 28,000 psi. In the untreated specimen, the crack started to grow after 50,000 cycles. However, in the specimen which was prestressed 100,000 psi and the surface layer removed, the rate of crack propagation was zero. This shows that prestressing and surface removal has a beneficial effect on titanium (6 Al-4V).

FOREWORD

This report was prepared by the Denver Division of Martin Marietta Corporation Under U. S. Army Contract No. DAAG 46-70-C-0102. The contract is sponsored by Advanced Research Project Agency under ARPA Order No. 188-0-7400 and is being administered by the Army Materials and Mechanics Research Center, Watertown, Massachusetts, with Dr. Eric B. Kula, AMXMR-RM, serving as Technical Supervisor.

BLANK PAGE

I. INTRODUCTION


Under this contract, we are investigating the effect of surface layer on the rate of crack propagation and based on this knowledge, we propose to improve the crack propagation resistance of metals used in pressure vessels. The qualification of pressure vessel hardware is usually achieved by the proof test method. The maximum size of the flaw that is present can be predicted from fracture mechanics. However, cracks can grow below the critical stress intensity K_{IC} and can cause leak failure. Therefore, the subcritical crack growth characteristics of metals are important in pressure vessel material selection. An evaluation of the crack growth rate under sustained or cyclic loading under the service stress gives a measure of reliability of the hardware.

The evidence that surface layer is important in crack propagation rate may be obtained by measurements of fatigue life and surface layer stress in a vacuum environment. It is well established that the fatigue life of metals is much greater in vacuum than under atmospheric conditions. The rate of crack propagation is much slower under vacuum and thus the number of cycles required to propagate a crack is increased. We have measured the surface layer stress of titanium (6 Al-4V) under corrosive environment and found it is much greater than that under atmospheric conditions. Further, the rate of relaxation was also much slower.

II. EXPERIMENTAL RESULTS

We have procured 1/8" thick sheet of aluminum 2014-T6 alloy. A calculation shows that in order to get away from the end effects and get crack propagation below the yield stress, the minimum width of the sheet required for center notched specimens is 6". The capacity of our MTS system is only 6,000 pounds. Therefore, we have decided to use the Ripling M-4 specimen for aluminum 2014-T6. Another advantage of the Ripling specimen is that the taper keeps the stress intensity K constant and independent of the crack length. Ripling type specimens as shown in Figure 1 were machined out of the sheet stock. A portion of the sheet stock was cut into blanks 6" x 6" and prestressed to 33,000 psi and later Ripling specimens were machined out. These specimens will be referred to as prestressed specimens. All the specimens were stress relieved and electrolytically polished to remove 0.005 from the surface. A starter flaw was introduced with a file and jeweler's saw. The specimens were loaded in a MTS machine. A special loading jig was designed and manufactured to prevent buckling of the specimen. Lubricated teflon was used to minimize friction between the backing plate and specimen. The MTS machine was programmed to cycle the load between two limits. The effect of changing the frequency of loading in a typical test is shown in Figure 2. It is observed that the rate of crack propagation da/dN , where da is the change in crack length with a change in the number of cycles dN , decreases from 1.7×10^{-5} in/cycles to 1.2×10^{-5} in/cycles when the frequency of the applied load is increased from 1 to 20 cycles per second. It is also observed in Figure 2 that the plot of crack length vs. number of cycles is linear indicating a constant da/dN which means that the K value is independent of the crack length. Therefore, all measurements were confined to the first one inch of crack length. The effect of prestressing 33,000 psi and surface removal (SSR) on the rate of crack propagation is shown in Figure 3. It is observed that SSR treatment increases da/dN from 1.03×10^{-6} to 1.14×10^{-6} inch/cycle. The effect of prestressing followed by aging at 250°F for two and four hours is also shown in Figure 3. It is observed that prestressing followed by aging definitely reduces the rate of crack propagation from 1.03×10^{-6} to 9.8×10^{-7} inch/cycle. We have previously shown that the fatigue life of aluminum 7075-T6 was increased by a similar treatment.

We have measured the rate of crack propagation in titanium (6 Al-4V) Ripling specimens. The crack did not remain on its path and had strong tendency to veer off to one side or the other. Grooving procedures were employed without much success. Therefore, we have decided to test the titanium (6 Al-4V) alloy in tension. Center notched specimens as shown in Figure 4 were machined out of 0.067" sheet stock and annealed at 1300°F for one hour. Another batch of specimens was pre-stressed to 100,000 psi. The surface of all the specimens was electrochemically polished. The specimens were drilled with an 1/8" drill and starter cracks were put in with a jeweler's saw. The specimens were loaded in a MTS machine. The crack length as a function of number of cycles for specimens cycled under a load (28,000 psi - 7,000 psi) is shown in Figure 5. It is observed that in untreated specimens, the starter crack starts propagating in 50,000 cycles and the rate of crack propagation increases with crack length. However, for the SSR treated specimens the starter crack did not propagate at all even after 1,000,000 cycles. This shows that SSR treatment is beneficial. At present we are increasing the stress to compare the rate of crack propagation in the untreated and SSR treated specimens of titanium (6 Al-4V). In the case of aluminum 2014-T6 we are increasing the amount of prestress to see if there is any beneficial effect on the crack propagation resistance. In our previous work on 7075-T6 aluminum, it was found that the fatigue life increased with increasing prestress, up to the proportional limit.






Figure 2 Crack Growth Behavior of Al 2014-T6






Figure 3 Crack Growth Behavior of Al 2014 T6





DOCUMENT CONTROL DATA - R & D

Security classification of this data is controlled and changing classification must be entered when the original document is changed.

1. **Organization (Corporate Author)**
Martin Marietta Corporation
Denver Division
Denver, Colorado

2. **Report Status - Classification**
 Unclassified
 3. **Source**
 N/A

4. **Report Title**
The Effects of the Surface Layer on Plastic Deformation and Crack Propagation

5. **Publication Number (Type of report and the issue date)**
Semi Annual Report - January 1971

6. **Author(s) (Last name, middle initial, first name)**
Kramer, Irvin R.

7. **Report Date**
January 1971

8. **Contract or Grant Number**
DAAG 46-70-C-0102

9. **Project Number**
ANCRS 5910.2166013

10. **Organization Report Number**
AMRC CR 71-2/1

11. **Other Report Number (any other numbers that may be assigned this report)**
MCR-71-2

12. **Publication Statement**
This document has been approved for public release and sale: Its distribution is unlimited.

13. **Supplementary Notes**
ARPA Order 188-O-7400

14. **Ordering Institution Address**
Army Materials and Mechanics Research Center
Watertown, Massachusetts 02172

15. **Summary**
 We have measured the rate of crack propagation as a function of frequency in Ripling type specimens of aluminum 2014-T6. It was observed that the rate of crack propagation was decreased from 1.7×10^{-5} in/cycle to 1.2×10^{-6} in/cycle when the frequency is increased from 1 to 20 cycles/second. It was also observed that the plot of crack length vs. number of cycles is linear indicating a constant rate of growth up to a crack length of one inch. The effect of prestressing followed by aging at 250°F for 2 to 4 hours was to decrease the rate of crack propagation from 1.02×10^{-6} to 9.8×10^{-7} in/cycle. This shows that prestressing followed by aging has a beneficial effect on the crack growth resistance of aluminum 2014-T6.

Center notched specimens of titanium (6 Al-4V) were tested in tension under a cyclic stress of 7,000 to 28,000 psi. In the untreated specimen, the crack started to grow after 50,000 cycles. However, in the specimen which was prestressed 100,000 psi and the surface layer removed, the rate of crack propagation effect on titanium (6 Al-4V).

KEY WORDS	LINE A		LINE B		LINE C	
	DD-1	DT	DD-1	DT	DD-1	DT
Crack Propagation						
Stress Intensity						
Crack Growth						
Surface Layer						
Rippling Specimen						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantor, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report on day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, c, & d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign dissemination and documentation of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 100 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical content. T.O. assignment of links, rules, and weights is optional.