

AFML-TR-72-39


AD 746686

Dielectric Constant and Loss Data

W. B. Westphal and A. Sils
Massachusetts Institute of Technology

Technical Report AFML-TR-72-39

April 1972



Approved for Public Release, Distribution Unlimited

Reproduced by
**NATIONAL TECHNICAL
INFORMATION SERVICE**
U S Department of Commerce
Springfield VA 22151

Air Force Materials Laboratory
Air Force Systems Command
Wright-Patterson Air Force Base, Ohio

NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

AC	
NTIS	Section ☒
FIG	Section ☐
UNA	☐
JUSTI. G. 10.4	
BY	
DISTRIBUTION/AVAILABILITY CODES	
DISC	SPECIAL
A	

Copies of this report should not be returned unless return is required by security considerations, contractual obligations, or notice on a specific document.

Unclassified
Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Laboratory for Insulation Research Massachusetts Institute of Technology Cambridge, Mass. 02139		2a. REPORT SECURITY CLASSIFICATION Unclassified	
		2b. GROUP	
3. REPORT TITLE Dielectric Constant and Loss Data			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Report			
5. AUTHOR(S) (First name, middle initial, last name) William B. Westphal and Aina Sils			
6. REPORT DATE April 1972		7a. TOTAL NO. OF PAGES 224	7b. NO. OF REFS None
8a. CONTRACT OR GRANT NO. F33615-71C-1274		9a. ORIGINATOR'S REPORT NUMBER(S)	
b. PROJECT NO. 737101			
c.		9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.		AFML-TR-72-39	
10. DISTRIBUTION STATEMENT Distribution Unlimited			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Air Force Materials Laboratory Air Force Systems Command Wright-Patterson Air Force Base, Ohio	
13. ABSTRACT The main body of this report includes data on high-temperature materials, primarily organic crystals, ceramics and glasses. Additional sections include plastics and materials with less heat resistance. This report is mainly a recompilation of data on dielectric materials measured after Vol. VI of <u>Tables of Dielectric Materials</u>, 1958. Data from progress reports and the following L.I.R. and Air Force technical reports are included: Tech. Rep. 114, Tech. Rep. 182, Tech. Rep. 203, AFML-TR-65-396, AFML-TR-70-138, AFML-TR-71-66. Data on ferroelectrics measured following the <u>Tables of Dielectric Materials</u> are excluded. The index is intended to be a complete reference to Vols. IV, V, and VI of <u>Tables</u> as well as the present report (P.R. in index).			

Unclassified

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Dielectric constant Dielectric loss Electrical permittivity High-temperature materials Inorganics Minerals Rocks Organic materials Plastics Liquids						

Unclassified

Security Classification

ib

DIELECTRIC CONSTANT AND LOSS DATA

W. B. Westphal and A. Sils

Approved for Public Release; Distribution Unlimited

FOREWORD

This report was prepared by the Massachusetts Institute of Technology, Laboratory for Insulation Research, Cambridge, Massachusetts, under USAF Contract F33615-71C-1274. This Contract was initiated under Project No. 7371, "Exploratory Development in Electrical, Electronic, and Magnetic Materials," Task No. 737101, "Dielectric Materials." The work was administered under direction of the AF Materials Laboratory, with Mr. W.G.D. Frederick (AFML/LPE) acting as project engineer.

This report was compiled from February 1, 1971 to January 31, 1972, and was submitted in February 1972 by the authors for publication.

This technical report has been reviewed and is approved.


CHARLES E. EHRENFRIED
Major, USAF
Chief, Electromagnetic Materials Br.
Materials Physics Division
Air Force Materials Laboratory

ABSTRACT

The main body of this report includes data on high-temperature materials, primarily organic crystals, ceramics and glasses. Additional sections include plastics and materials with less heat resistance.

This report is mainly a recompilation of data on dielectric materials measured after Vol. VI of Tables of Dielectric Materials, 1958. Data from progress reports and the following L.I.R. and Air Force technical reports are included: Tech. Rep. 114, Tech. Rep. 182, Tech. Rep. 203, AFML-TR-65-396, AFML-TR-70-138, AFML-TR-71-66.

Data on ferroelectrics measured following the Tables of Dielectric Materials are excluded. The index is intended to be a complete reference to Vols. IV, V, and VI of Tables as well as the present report (P.R. in index).

Preceding page blank

TABLE OF CONTENTS

	Page
I. Inorganic Compounds	1
Aluminum nitride	
Carborundum, hot-pressed	1
Aluminum oxide	
Single-crystal sapphire, Linde	2,3
" " " , Union Carbide	4
Alberox A-935	5
" A-950	5
" A-962	5
American Lava AlSiMag 576	6
" " " 614	6
" " " 719	6
Armour Research, density 3.32 g/cm ³	7,8
" " density 3.23 g/cm ³	9,10
" " density 3.84 g/cm ³	12,13
" " hot-pressed, in graphite	14
" " with 10% titanate addition	15,16,17
Mixtures	18
Centralab 205	19
" 206	19
Carborundum 1542	19
Coors AD-99	19
" AD-995	20
" MC-2014	20
" RR	20
" NBS 10F2	20
Diamonite B-890-2	21
" P-3662	21
" P-3142-1	21
Frenchtown 7225	21
General Electric AT-100	22

Preceding page blank

Table of Contents (cont.)

	Page
Aluminum oxide (cont.)	
General Electric Lucalox	23,24
" " multicrystalline A-919	25
" " " A-923	26
" " " A-976	27
" " " A-1000	28
" " " A-1004	29
International Pipe and Ceramic TC-301	30
" " " TC-302-H	30
" " " TC-351	30
" " " V-69	30
Kearfott high-purity	31
Minneapolis Honeywell A-127 and A-203	31
National Beryllia Alox	31
Norton Company 99.5%	31
Raytheon	32
Steatit-Magnesia A-18	32,33
U.S. Stoneware A-212	34
" " A-216	34
" " A-312	34
" " 610	34
" " Std. 3050°F	35
Western Gold and Platinum AL-300	36
" " " " AL-300 (modified)	36
" " " " AL-400	37
" " " " AL-500	37
" " " " AL-995	37
" " " " AL-1009	37
Barium fluoride	
Single crystal, M.I.T. Crystal Physics Laboratory	38,39
Beryllium oxide	
Single crystal KSC 7011A, Electronic Space Products Inc.	39
Multicrystalline, American Lava 754	40
Brush B-6	40
" B-7-6	40
" B-7-37	40

Table of Contents (cont.)

	Page
Beryllium oxide (cont.)	
Brush F-1	41
Coors BD98	41
National Beryllia cold-pressed, high-purity BeO	41
" " Berlex	41
Multicrystal, translucent, North American Aviation	42,43
Beryllium silicate crystal KSC 7013, Electronic Space Products	44
Bismuth silicate ceramic, M.I.T., Laboratory for Insulation Research	44
Boron nitride	
Average κ' versus density	45
Hot-pressed, Battelle Memorial Institute	45
" " Carborundum Company	46
" " , Grade A, Carborundum Company	47
" " , Grade HP, " "	48
" " , Grade M, " "	49
Pyrolytically deposited, Union Carbide Boralloy	50,51
Pyrolytic, Raytheon	52,53
" laminate, Union Carbide	54
Hot-pressed, Grade HDO056, Union Carbide	54
" " , Grade HDO086, " "	54
" " , Grade HDO092, " "	55
" " , Grade HDO093, " "	55
" " , Grade HDO094, " "	55
" " , Grade HBN, " "	56
" " , Grade HBR, " "	57
Cold-pressed, Union Carbide	57
Calcium carbonate, single crystal mineral (Calcite)	58
Calcium fluoride	
Single crystal, M.I.T., Crystal Physics Laboratory	59
Doped with Y_2O_3 , M.I.T., Department of Metallurgy	60
Cerium fluoride	
Multicrystal, M.I.T., Laboratory for Insulation Research	61

Table of Contents (cont.)

	Page
Chromium oxide	
Single crystal, hexagonal, m.p. 1990°C, Linde	62
Cobalt oxide	
Cobalt oxide/nickel oxide mixed crystal, M.I.T., Crystal Physics Laboratory	63
Copper halides	
Pressed powders, M.I.T., Laboratory for Insulation Research	63
Hafnium oxide	
Multicrystal, Zircoa Y-790	64
Lanthanum aluminate,	
Single crystal, National Lead	65
Lead halides, M.I.T., Crystal Physics Laboratory	
Lead bromide, orthorhombic, m.p. 373°C	66
Lead chloride	66
Lead bromide/lead chloride mixed crystals	66
Magnesium aluminate (spinel)	
Single crystal, Union Carbide	66
Magnesium-aluminum silicate	
Multicrystalline (Cordierite ceramic), Raytheon	67
Magnesium carbonate	
Pressed powder	67
Magnesium oxide	
Multicrystalline, Kodak IRTRAN-5	67
Single crystal, Norton	68
M.I.T., Laboratory for Insulation Research	68,69
MgO ceramic, Minneapolis Honeywell	70,71
Magnesium metasilicate	
Multicrystalline, F-66, Bell Telephone Labs.	72
International Pipe and Ceramic Corp. TC-503	72
Magnesium orthosilicate	
Multicrystalline, General Electric F-118, F-202	73
Steatit-Magnesia A.G. Frequentia M	74
Magnesium titanate	
Multicrystalline, U.S. Sonics	75

Table of Contents (cont.)

	Page
Manganese fluoride	
Tetragonal crystal, Columbia University	75
Mercury compounds, hot-pressed	76
Nickel oxide	
Single crystal, M.I.T., Crystal Physics Laboratory	77
Phosphate glass, American Optical	77
Rubidium manganese fluoride	
Single crystal, M.I.T., Crystal Physics Laboratory	77
Silicon	
Single crystal, cubic, Brown University	78
Intrinsic, M.I.T., Crystal Physics Laboratory	78
Silicon carbide	
Carborundum	79
With BeO, National Beryllia Carberlox	80
Silicon dioxide	
Natural quartz crystal, Fort Monmouth	80,81
Glasses	
American Optical Amersil, clear	82
" " " , translucent	82
Corning 7940	83
Dynasil 4000	84
General Electric Type 101, clear	85,86,87
Spectrosil A, Thermal American Fused Quartz Co.	88
" B, " " " " "	88
Vitreosil, optical grade, " " " "	88
" , commercial " " " "	88
Mixed silicate glasses	
Corning Lab. No. 119BUC	89
" Code 1723	89
Lancaster 7352	89
" 7357	90
" L1957	91
" L8100	92
Soda silicate glass, M.I.T., Laboratory for Insulation Research	93

Table of Contents (cont.)

	Page
Mixed silicate glasses (cont.)	
Owens-Illinois EE 9	93
" " EE 10	93
Owens Corning, X994	93
Pittsburgh Plate Glass Co., Plate glass	94
" " " " , Sheet glass	94
Sintered	
Brunswick slip-cast	95
" " " with 2.5% Cr ₂ O ₃	95
Corning 7941	96
Corning multiform glass	96
Silica slip-cast, Dynasil	96
Fibers	
Quartz fiber, Philco Ford (manufacturer: Fiber Materials Inc.), AS-3DX-1R	97
Silica fiber composites, Philco Ford 1-XB-O-M	98
" " " " " AS-3DX 176-17	98
" " " in aluminum phosphate matrix, Whittaker Corporation	99
Silicon nitride	
Pyrolytic, North American Aviation	100
Ceramic, Admiralty Materials Laboratory	100
" , Raytheon	100
" , Union Carbide	101
Silver iodide	
Pressed powder, M.I.T., Laboratory for Insulation Res.	102
Sodium chloride	
With BiCl ₃ , M.I.T., Crystal Physics Laboratory	103-105
Strontium fluoride	
Single crystal, cubic, M.I.T., Crystal Physics Lab.	106, 107
Tantalum oxide	
Ceramic, Ciba optical grade powder, fired at M.I.T., Laboratory for Insulation Research	108
Thallium halides, M.I.T., Crystal Physics Laboratory	109

Table of Contents (cont.)

	Page
Thorium oxide	
Ceramic, nuclear grade Zircoa	110,111,112,
Ceramic, M.I.T., Lab. Ins. Res.	113,114
Vanadium oxide	
Pressed powder samples, M.I.T., Lab. Ins. Res.	114
Yttrium oxide	
Single crystal, M.I.T., Lab. Ins. Res.	115
Ceramic, nuclear grade Zircoa	116
Zinc oxide	
Single crystal, hexagonal, Litton Industries	117
Zirconium oxide	
Ceramic, technical grade Zircoa "C"	118
" nuclear grade Zircoa Y-904	119
" nuclear grade Zircoa Y-1362	120,121
" Zircolite, Air Force Materials Laboratory	122
Zirconium silicate (zircon)	
Single crystal, mineral	123,124,125
II. Minerals, Rocks, Soils, and Miscellaneous Inorganics	
Single crystal minerals	
Apatite	126,127
Astrophyllite	127
Benitoite	127
Beryl	128,129
Calcite, see Sec. I	
Neptunite	129
Quartz, see Sec. I	
Spodumene	130,131,132
Topaz	133,134
Tourmaline	134
Zircon, see Sec. I	
Crushed minerals	
Halite	135
Limonite	135
Magnesite	135
Quartz powder	135

Table of Contents (cont.)

	Page
Rocks	
Basalt, Hawaiian, high-density	136
" " low-density	137
" " deep-ocean	137
Granite, Quincy	138
" Virginia	138
Greenstone, Virginia	139
Limestone, Lucerne Valley, Raytheon	139
Lunar rocks and synthetic basalt	139
Rhyolite	140
Sandstone, almond, Raytheon	140
Soils	
Fullers earth, Foxboro	141
Hawaiian	141,142
Mass. loams	143
Desert sand	143
Miscellaneous Inorganics	
Sands (Holliston and Slatterville No. 60)	144
Ices, glacial	145,146,147
CFI 1003 and CFI 1006 attenuator materials	148
Corning 0330, 7941, and 9606	149
Ferrites, General Ceramics:	
3308D, 3310, 3321, 3330, "Q"-3	150
R-1, R-4, R-5, R-6	151,152
Havelex, glass-bonded micas:	
Types 1080, 1090, 1101, 2101, 2103, 2801, 2803	153
Isomica 4950, General Electric	153
Mycalex 410, 500, 555, 560, 620	153,154,155
Asphalt pavement and asphalts	156
Concrete pavement	157
Salt, Raytheon	158
Service boards, John Manville, The Sippican Corp.	158

Table of Contents (cont.)

	Page
 III. Organic Compounds	
American Concrete Products, artificial concrete	159
American Cyanamid, cyanoethylated cotton moulding	159
Cymac 325	160
Amicon Corporation, conformal coating 1517-36-3	160
Amphenol Corp., polyethylene, irradiated	161
AVCO Research, polyvinylidene fluoride	161
Avisun Corporation, polypropylene	162,163
The Budd Company, polytetrafluoroethylene, fiberglas laminate, Diclad-522	163
The Budd Company, Copper-clad laminate PE1153	164,165
The Carborundum Company, EKONOL (polyester resin)	166
Chemplast Inc., polytetrafluoroethylene film	166
H. I. Crowley Co., polyiron (carbonyl) attenuator	167
Custom Materials, Inc., custom load 4101, 707-4, and 707-(3.75)	167
Dodge Industries, Inc., FLUORGLAS E 650/2-1200 (TFE-fibe. glas laminate)	167
Dow Corning, moulding compound 306	168
Silastic RTV 501, 521, 1602, 5350, S-6538	168
Sylgard 182, 184, DC-92.007	168
E. I. Dupont de Nemours & Co., "H"-film	169,170,171
Kapton (Type 500 H film)	171
Nonex honeycombs	172
Teflon FEP (1963)	173
Teflon FEP (1964)	173
" TEF-7 (1964)	173
" TFE-6C (1964)	173
" T-100, Lot 38180	174
" 100X (FEP) 1960 and TFE	174
" 9033, Lot 10601	174
Electronized Chemicals Corp., Polyguide	175
Emerson and Cuming, A-19 attenuator material	175
Eccogel 1265	176
Eccofoam FH	176

Table of Contents (cont.)

	Page
Organic compounds (cont.)	
General Electric, RTV-11	176
Silicone rubber SE900	177
Lexan	177
3-M , "3M" board	178
Scotchcast 221	178
Monsanto, polyimide foams, HD-139, -140, -144	178
Nopco Chemical Corp., polyurethane rigid foam	179
Polymer Corporation, Fluorosint (1960)	179
Quantum Inc., radar tape	180
Raytheon Company, plastics	180
Rex, Wm. Brand Division of American Enka Corp., Rexolite 1422 (1964)	181
Rexolite 2200 (1964), Rexolite 2200 (1965)	182
Rexolene P	183
Rogers Corporation, Duroid (1" thick sheet)	184
Duroid 5870 (1966)	185
Shell Chemical Company, Epon 828 + PMDA epoxies	186,187
The Sippican Corporation, polystyrene foam	188
Polyurethane foam	188
Tellite Corporation, Tellite 3A	188
Union Carbide Corp., Plastics Division, Polysulfone	189
U.S. Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio	
Fiberglass laminates	189,190
IV. Miscellaneous Organics	
Coal, Powdered, Kennecott Copper, Peabody Coal Division	191
" single lump, M.I.T., National Magnet Laboratory	192
Balsa wood, The Sippican Corporation	192
Particle boards, " "	193
Wood products (pine board, fir plywood, birch plywood, Marinite)	193
V. Liquids	
Allied Chemical Corporation	
Fluorocarbon derivative P-1C	194

Table of Contents (cont.)

	Page
Liquids (cont.)	
Dow Chemical, Dowtherm A	194
E. I. Dupont de Nemours & Co., fluorinated ethers:	
FPS-1418, FPS-1419, FPS-1420	194
Esso, Teresso V-78	195
Hercules, Inc., DI-CUP, VUL-CUP	196
Pennwalt Corporation, Lucidol Division, Lucidol	196
Lupersol 130	196
U.S. Bureau of Fisheries, mullet oil	197
U.S. Peroxygen Division, Argus Chemical Corp.,	
USP 333	197
Wallace & Tiernan Inc., Lupersol 101	197
VI. Foodstuffs	
Cooking oil, Kremax, Armour	198
Beef steak, lean, frozen and vacuum-dried	199
Potatoes, raw	199
Potato flakes	199
Potato chips	199
Potato starch, granular and gelatinized	200,201
Coffee, instant	202
Tea, instant, powder	202
Eggwhite	202
Bread	202
Bread dough	202

DIELECTRIC PARAMETERS

Dielectric parameters in the present report have the following notation:

κ' , ϵ'/ϵ_0 , dielectric constant relative to vacuum

κ'' , ϵ''/ϵ_0 , dielectric loss factor relative to vacuum

$\tan \delta$, or $\tan \delta_d$, dielectric loss tangent (dissipation factor)

κ'_m , μ'/μ_0 , magnetic permeability relative to vacuum

κ''_m , μ''/μ_0 , magnetic loss factor

$\tan \delta_m$, magnetic loss tangent



σ , a.c. volume conductivity in mho-cm

ρ , a.c. volume resistivity in ohm-cm

I. INORGANIC COMPOUNDS

Aluminum nitride, hot-pressed,
at 8.5 GHz, 25°C, $\kappa' = \pm 0.1$


The Carborundum Co.



Al₂O₃ single-crystal sapphire, low frequency
 peak dispersion due to silver diffusion.
 To be re-evaluated to higher temperatures
 with platinum electrodes.

The Linde Air Products Co.



E II



Al_2O_3 single-crystal sapphire

Linde Air Products Co.

$E \perp$



Aluminum oxide, single crystal

Sapphire Al_2O_3

Density at 25°C = 3.9840 g/cm³

Union Carbide
Electronics Division

Loss tangents at 8.5 GHz, 25°C:

$E \perp c$, <.00002

$E \parallel c$, <.00005

Freq. 3.45-3.33 GHz, $E \perp c$

Dielectric constants at 3 GHz:

T°C	$E \perp c$	$E \parallel c$	T°C	κ	$\tan \delta$
25	9.390*	11.584*	25	9.39	< .0001
-75	9.292	11.433	80	9.41	< .0001
-195	9.257	11.357	240	9.49	< .0001
			377	9.62	< .0001
			526	9.83	< .0001
			617	9.95	< .0001
			713	10.08	< .00015

Variation of dielectric constant at 25°C with inclination of electric field direction with respect to optic axis was calculated from elliptic polarization function:

$$\kappa = \left[\frac{11.584^2 \times 9.39^2 (1 + \cot^2 \theta)}{11.584^2 + 9.39^2 \cot^2 \theta} \right]^{1/2}$$

θ	κ
0	
10	11.494
20	11.246
30	10.895
40	10.507
50	10.1295
60	9.820
70	9.584
80	9.439

Average κ for random oriented full-density ceramic:

$$\kappa_{av} = 10.071 \text{ from } \kappa_{av} = (9.39 \times 11.584)^{1/3}$$

or 10.121 for approximate value $(11.584 + 2 \times 9.390)/3$.

* These values are in reasonable agreement with optically measured values of 11.56 and 9.406 [E.E. Russell and Bell, J. Opt. Soc. Am. 57, 543 (1967)].


Aluminum oxide
Multicrystalline (alumina)

Alberox Corp. A-950

95% Al_2O_3


density: 3.663 g/cm³

T °C	K'	tan δ
25	9.01	.00051
100	9.14	.00055
200	9.30	.00074
300	9.46	.00108
400	9.53	.00149
500	9.79	.00192
600	9.95	.00237
700	10.13	.00288
750	10.22	.00320
800	10.31	.00367
850	10.41	.0051
892	10.50	.010
3.89 - 3.61 GHz		
8.5 GHz		
25	8.98	.00058



Alberox Corp. A-962

96.2% Al_2O_3



Alberox Corp. A-935

93.5% Al_2O_3




Density 3.623 g/cm³

8.52 GHz

T °C	K'	tan δ
25	8.65	.00155
100	8.73	.00208
200	8.84	.00305
300	8.95	.00423
400	9.06	.0057
500	9.18	.0081
540	9.24	.010

Alumina (cont.)

American Lava



Alumina, high-purity

Armour Research Foundation


From Alcoa 99.99% Al with HF, fired air 1820°C

Spectrographic analysis: concentration of elements in
parts per million:


Si	Mg	Fe	Ca	Cu
111	58	38	3	5

Density 3.32 g/cm³

Fired silver electrodes



Density 3.32



Alumina, high-purity


Armour Research Foundation


From Reynolds 99.999% Al with HF, fired air 1840°C

Spectrographic analysis: concentration of elements
in parts per million:

Si	Mg	Fe	Ca	Ni	Cr	Cu
60	30	60	15	5	4	3

Density 3.23 g/cm³





Alumina oxide with added silicic acid

Armour Research Foundation



Fired air 1890°C

850 ppm Si, 550 ppm Na

Fired silver electrodes


Density 3.49 g/cm³


E-20



Alumina, high purity, hot-pressed in C
Density 3.84 g/cm³



Armour Research Foundation








Alumina, hot-pressed,
in graphite

Armour Research Foundation


















Change in dielectric constant
with temperature for various
aluminas at ca. 4000 MHz



Alumina (cont.)






Alumina (cont.)



Alumina (cont.)

(85%-90% Al_2O_3)



Frenchtown 7225

8.52 GHz, 25°C

$\epsilon' = 8.8 \pm 0.05$

$\tan \delta = 0.0013 \pm 0.0002$

on two samples

Aluminum oxide, multicrystalline


General Electric Company
Electronic Components Division

AT-100 (near 100% Al_2O_3 , fine grained)



Density, g/cm^3 : (10^2 to 10^8 Hz) - 3.956
(4; 8 GHz) - 3.955

T°C	Frequency in Hz						
	10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
25 K	9.98	9.98	9.98	9.98	9.98	9.98	9.96
$10^6 \tan \delta$	7	<1	<1	<1	<1.5	<7	48
100 K	10.09	10.09	10.09	10.09	10.09	10.09	
$10^6 \tan \delta$	52	6	<1	<1	<1.5	<7	
200 K	10.21	10.21	10.21	10.21	10.21	10.21	
$10^6 \tan \delta$	603	128	45	20	10	<7	
300 K	10.42	10.37	10.355	10.35	10.35	10.35	
$10^4 \tan \delta$	61.3	16.3	5.27	2.28	.62	.12	
400 K	10.84	10.68	10.57	10.46	10.44	10.44	
$\tan \delta$	.0307	.0133	.00407	.00103	.00034	.00006	
500 K	12.60	11.28	10.86	10.71	10.63	10.62	
$\tan \delta$	.289	.069	.0237	.0044	.00082	.0002	

Al_2O_3 ceramic, General Electric Co. "Lucalox." Curves show data on samples bought in 1963. Tabulation of data on earlier samples, 1962, show appreciably lower microwave loss.



Alumina (cont.)



A-919 (97% Al_2O_3 , magnesia-free)

General Electric Co.

Density, g/cm^3 : (10^2 to 10^8 Hz) - 3.747
(8.5×10^9 Hz) - 3.750

		Frequency in Hz						
		10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
$T^{\circ}\text{C}$								
25	κ	10.33	9.95	9.62	9.45	9.38	9.37	9.35
	$\tan \delta$	.0240	.0251	.0206	.0082	.00139	.00030	
100	κ	10.29	9.88	9.60	9.51	9.49	9.49	.00069
	$\tan \delta$	.0316	.0252	.0123	.00303	.00048	.00025	
200	κ	9.74	9.62	9.60	9.59	9.59	9.59	
	$\tan \delta$	.0210	.0046	.00089	.00021	.00006	<.0001	
300	κ	10.32	9.89	9.79	9.78	9.77	9.77	
	$\tan \delta$	.0760	.0237	.00475	.00097	.00033	.00010	
400	κ	14.38	11.13	10.18	9.96	9.90	9.89	
	$\tan \delta$	1.65	.295	.0590	.0106	.00195	.00063	
500	κ	16.56	13.67	11.44	10.37	10.08	10.03	
	$\tan \delta$		6.83	.866	.122	.0203	.0035	

Aluminum oxide, multicrystalline

A-923 (97% Al_2O_3)

General Electric Company

Density, g/cm^3 : (10^2 to 10^8 Hz) - 3.740
(8.5×10^9 Hz) - 3.740

Frequency in Hz

$T^\circ\text{C}$	10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
25 κ	10.26	10.23	10.10	9.61	9.28	9.27	9.24
tan δ	.00227	.00432	.0173	.0357	.00952	.00165	.00067
100 κ	10.33	10.30	10.19	9.72	9.40	9.39	
tan δ	.00330	.00352	.0178	.0320	.0118	.00157	
200 κ	10.18	9.73	9.55	9.53	9.50	9.50	
tan δ	.0349	.0238	.0073	.00200	.0089	.00040	
300 κ	10.38	9.84	9.74	9.65	9.64	9.64	
tan δ	.0678	.0232	.0074	.00313	.00167	.00112	
400 κ	12.50	10.48	9.97	9.82	9.80	9.79	
tan δ	.205	.082	.0228	.00735	.0035	.0017	
500 κ	16.72	13.93	10.98	10.08	9.95	9.91	
tan δ	8.03	1.20	.240	.0444	.00976	.0037	

A-923 (97% Al_2O_3)

Density 3.740 g/cm^3

Freq. 3.74 - 3.37 GHz

$T^\circ\text{C}$	κ	tan δ	$T^\circ\text{C}$	κ	tan δ
25	9.31	.00039	705	10.42	.00215
99	9.41	.00042	800	10.63	.00265
184	9.58	.00053	903	10.86	.0033
281	9.72	.00070	973	10.98	.0040
356	9.84	.00090	1025	11.17	.0045
430	9.96	.00112	1050	11.22	.0050
562	10.17	.00160	1109	11.38	.0060
			1132	11.41	.010

Aluminum oxide, multicrystalline

General Electric Company

A-976 (near 100%)

T°C	Frequency in Hz						8.5 x 10 ⁹
	10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷	
25 κ	9.90	9.90	9.90	9.90	9.90	9.90	9.81
10 ⁶ tanδ	70	34	20	10	<10	<10	66
100 κ	10.01	10.01	10.00	10.00	10.00	10.00	
10 ⁵ tanδ	15	7	3	1.5	<1	<1	
200 κ	10.14	10.12	10.11	10.11	10.11	10.1	
10 ⁵ tanδ	66	23	8	6	3	<1	
300 κ	10.32	10.29	10.26	10.26	10.26	10.26	
10 ⁴ tanδ	25	11	3.8	1.1	.4	.2	
400 κ	10.65	10.50	10.43	10.42	10.41	10.41	
10 ⁴ tanδ	395	102	27.8	8.7	2.9	1.0	
500	11.30	10.81	10.65	10.59	10.58	10.56	
10 ³ tan	461	118	22.4	4.59	1.97	1.1	

Density of disk - 3.919; density of cylinder - 3.917

Aluminum oxide, multicrystalline

A-1000 (99.8% Al_2O_3 , fine grained)

General Electric Company

Density, g/cm^3 : (10^2 to 10^8 Hz) - 3.900
(8.5×10^9) - 3.896

T°C	Frequency in Hz						
	10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
25 κ	10.08	10.08	10.07	10.04	9.98	9.96	9.77
tan δ	.00048	.00048	.00135	.00354	.00664	.00612	.00258
100 κ	10.20	10.16	10.15	10.15	10.15	10.15	
tan δ	.00184	.00077	.00037	.00058	.00208	.0061	
200 κ	10.39	10.36	10.33	10.33	10.31	10.29	
tan δ	.00344	.00198	.00101	.00045	.00051	.00170	
300 κ	10.65	10.55	10.51	10.47	10.45	10.44	
tan δ	.0193	.0059	.00226	.00079	.00049	.00065	
400 κ	11.86	10.89	10.68	10.63	10.60	10.58	
tan δ	.213	.0461	.00936	.00208	.00076	.00057	
500 κ	33.3	13.98	11.28	10.83	10.80	10.76	
tan δ	1.212	.585	.130	.0201	.00341	.00135	

Aluminum oxide, multicrystalline

General Electric Company

A-1004 (94% Al_2O_3)

At 25°C: 2×10^4 Hz, $\kappa = 10.10$, $\tan \delta = .0426$; 5×10^4 Hz, $\kappa = 9.76$, $\tan \delta = .0536$;
 3×10^5 , $\kappa = 9.19$, $\tan \delta = .0341$.

Density, g/cm³: (10^2 to 10^8 Hz) - 3.645(8.5×10^9 Hz) - 3.649



Frequency in Hz

T°C	10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
25 κ	10.48	10.41	10.26	9.51	9.10	9.00	9.01
tan δ	.00226	.00716	.0319	.0534	.0142	.00228	.00125
100 κ	10.63	10.55	10.48	9.89	9.19	9.10	
tan δ	.00355	.00555	.0208	.0505	.0271	.0515	
200 κ	10.49	9.73	9.34	9.25	9.21	9.20	
tan δ	.0450	.0439	.0171	.0047	.00163	.00105	
300 κ	10.52	9.81	9.55	9.44	9.37	9.36	
tan δ	.0767	.043	.0132	.0059	.0022	.0020	
400 κ	12.63	10.39	9.78	9.54	9.43	9.36	
tan δ	.227	.0887	.033	.0136	.0072	.0040	
500 κ	19.19	12.59	10.55	10.03	9.83	9.74	
tan δ	1.16	.452	.121	.0298	.0133	.0071	



A-1004 (94% Al_2O_3), density 3.649 g/cm³

Freq. 1.80 - 3.61 GHz

T°C	κ	tan δ
25	9.02	.00076
100	9.11	.00078
200	9.26	.00081
300	9.40	.00093
400	9.55	.00109
500	9.69	.00128
600	9.84	.00177
650	9.92	.00335
700	10.00	.0093







International Pipe and Ceramic
TC-351, at 8.52 GHz



High-purity alumina at 50 GHz, 25°C
 $\kappa' = 9.5$, $\tan \delta = 1 \times 10^{-5}$


Kearfott

Alumina (cont.)




Alumina (cont.)

Aluminum oxide, multicrystal, 1959
Raytheon Company





Steatit-Magnesia A.G.







Aluminum oxide A-18
(multicrystalline)
Density 3.676 g/cm³


Steatit-Magnesia Aktiengesellschaft




Alumina (cont.)




Alumina (cont.)





Alumina: Western Gold and Platinum

AL-300 modified
Density 3.771 g/cm³
4.1 to 3.85 GHz




T °C	κ'	$\tan \delta$
25	9.39	.00037
122	9.48	.00037
185	9.55	.00038
258	9.63	.00038
339	9.74	.00041
393	9.79	.00045
500	9.95	.00055
572	10.08	.00064
788	10.43	.00120
881	10.63	.00219

At 25°C

f (Hz)	κ'	$\tan \delta$
10^7	9.44	.00012
10^9	9.40	.00035
3×10^9	9.39	.00037
8.5×10^9	9.38	.00046




Alumina (cont.)



Aluminum oxide, AL-500 Western Gold and Platinum (multicrystalline) Density 3.665 g/cm³



At 25°C

f (Hz)	K'	tan δ
10 ⁷	9.07	.00026
10 ⁹	9.03	.00062
3x10 ⁹	9.02	.00070
8.5x10 ⁹	see the graph below	




Barium fluoride
Single crystal

Massachusetts Institute of Technology
Crystal Physics Laboratory



Barium fluoride (cont)
Single Crystal

Massachusetts Institute of Technology
Crystal Physics Laboratory



Beryllium oxide
BeO crystal KSC 7011A
Electronic Space Products Inc.

$E \parallel c$ axis
 10^2 to 10^7 Hz
 $\kappa' = 7.41 \pm 0.1$
 $\tan \delta < 0.0006$

Beryllium oxide (cont.)




American Lava

AlSiMag 754 (99.5% BeO)


Density 2.851 g/cm³

8.52 GHz

T °C	κ'	$\tan \delta$
25	6.86	.00031
300	6.98	.00055
500	7.13	.00062



Beryllium oxide (cont.)




Coors Porcelain Co.

Beryllia BD98

8.52 GHz

T°C	κ'	$\tan \delta$
25	6.67	.00050
300	6.87	.00072
500	7.13	.00102




National Beryllia Corp.



Berlox

8.52 GHz

T°C	κ'	$\tan \delta$
25	6.64	.00043
300	6.77	.00068
500	6.98	.00093



Beryllium oxide, multicrystal



Beryllium silicate crystal KSC 7013


Electronic Space Products Inc.

E || optic axis

f (Hz)	κ'	$\tan \delta$
10^2	$5.1 \pm .5$	.0025
10^5	"	$.0003 \pm 2$

$\text{Bi}_4\text{Si}_3\text{O}_{12}$ ceramic

Laboratory for Insulation Research




Boron nitride, hexagonal,

3000°C sublimes

Average dielectric constant versus density

X-ray density 2.25 g/cm³



Boron nitride


Battelle Memorial Institute

(hot-pressed, after vacuum treatment)

Density in g/cm³

8.52 GHz, 25°C

Sample	Density	κ	$\tan \delta$
115H7	—	4.37	.00030
118H7	2.132	4.87	.00025



Boron nitride, hot-pressed
Grade A, 25°C

Carborundum

All tan δ values are multiplied by 10^4

Sample No.	Density (g/cm ³)	Field direct.	(Hz)	10^2	10^3	10^4	10^5	10^6	10^7	10^8
1	2.084	unknown	κ	4.13	4.12	4.090	4.087	4.086	4.080	4.08
			tan δ	11.8	10.4	7.9	4.3	3.1	2.7	2.6
2	2.040	$\perp$	κ	4.40	4.40	4.39	4.39	4.39	4.38	
			tan δ	8.7	6.3	6.0	3.1	1.8	1.0	
3	2.066	$\parallel$	κ	3.99	3.99	3.98	3.98	3.98	3.97	
			tan δ	6.9	5.6	4.5	3.0	2.4	1.1	
				(Hz) 3×10^8	10^9	3×10^9	8.5×10^9	1.4×10^{10}	2.4×10^{10}	
4 (various not meas.)		unknown	κ	4.46	4.46	4.46		4.6	4.61	
			tan δ	4.0	3.3	3.4		5.8	3.5	
5	2.099	unknown	κ				4.605			
			tan δ				20			
6	2.091	$\perp$	κ	4.62	4.615	4.599				
			tan δ	2.6	3.7	3.8				
7	2.097	mixed	κ	4.36	4.359	4.352				
			tan δ	2.2	1.3	1.5				
8	2.069	$\perp$	κ				4.586			
			tan δ				6.4			
9	2.077	$\perp$	κ				4.550			
			tan δ				3.6			
9	"	$\parallel$	κ				4.268			
			tan δ				4.5			
10		$\perp$	κ					4.268		
			tan δ					4.5		
11	2.093	$\perp$	κ					4.53		
			tan δ					4.5		
11	"	$\parallel$	κ					4.28		
			tan δ					10.4		
12	2.090	$\perp$	κ						4.56	
			tan δ						5.3	
13	2.095	$\perp$	κ						4.54	
			tan δ						4.6	
13	"	$\parallel$	κ						4.24	
			tan δ						3.2	

Boron nitride, hot-pressed
Grade HP, 25°C

The Carborundum Company
Refractories & Electronics Division
Whirlpool Technical Center
Niagara Falls, N.Y., 14302

All tan δ values multiplied by 10^4


Sample No.	Density (g/cm ³)	Field direct.	(Hz)	10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷	10 ⁸
1	2.120	unknown	κ	4.59	4.56	4.54	4.54	4.54	4.54	4.54
			tan δ	8.5	3.58	2.30	2.3	2.3	2.8	3.5
2	1.762	$\perp$	κ	4.14	4.02	3.97	3.96	3.96	3.96b	
			tan δ	414	174	41.6	9.9	3.4	2.0	
3	2.131	$\parallel$	κ	4.71	4.64	4.54	4.46	4.40	4.32	
			tan δ	100	110	120	125	141	123	
			(Hz)	3×10^8	10^9	3×10^9	8.5×10^9	1.4×10^{10}	2.4×10^{10}	
4 (various not meas.)		unknown	κ	4.59	4.59	4.59	4.39	4.62	4.57	
			tan δ	2.7	3.5	4.2	6.55	6.0	6.0	
5	1.999	unknown	κ							
			tan δ							
6	2.033	$\perp$	κ	4.47	4.468	4.457				
			tan δ	5.3	4.6	6.0				
7	1.748	mixed	κ	3.88	3.880	3.876				
			tan δ	4.1	4.7	4.0				
8	2.111	$\perp$	κ				4.584			
			tan δ				8.0			
9	2.061	$\perp$	κ				4.552			
			tan δ				7.1			
9	"	$\parallel$	κ				4.507			
			tan δ				7.7			
10	2.117	$\perp$	κ					4.75		
			tan δ					8.0		
11	2.063	$\perp$	κ					4.55		
			tan δ					8.7		
11	"	$\parallel$	κ					4.51		
			tan δ					8.8		
12	2.118	$\perp$	κ							4.69
			tan δ							8.5
13	2.066	$\perp$	κ							4.61
			tan δ							7.7
13	"	$\parallel$	κ							4.48
			tan δ							9.2


Boron nitride, hot-pressed, with silica
Grade M, 25°C

Carborundum

Sample No.	Density (g/cm ³)	Field direct.	(Hz)	All tan δ values multiplied by 10 ⁴					
				10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷
1	2.143	unknown	κ	3.71	3.70	3.69	3.69	3.69	3.68
			tan δ	4.0	2.78	2.22	2.07	1.63	1.8
2	2.107	$\perp$	κ	4.34	4.33	4.32	4.30	4.30	4.30
			tan δ	16.9	14.3	10.5	6.6	3.7	1.9
3	2.109	$\parallel$	κ	3.76	3.76	3.76	3.75	3.75	3.75
			tan δ	7.4	7.0	6.7	4.6	3.4	3.6
			(Hz)	3x10 ⁸	10 ⁹	3x10 ⁹	8.5x10 ⁹	1.4x10 ¹⁰	2.4x10 ¹⁰
4	(various not meas.)		κ	4.24	4.24	4.24		4.32	
			tan δ	2.8	3.1	3.7		5.5	
5	2.145		κ				4.328		
			tan δ				4.1		
6	2.137	$\perp$	κ	4.27	4.27	4.255			
			tan δ	3.8	4.9	4.9			
7	2.118	mixed	κ	3.99	3.992	3.983			
			tan δ	3.9	4.5	5.2			
8	2.095	$\perp$	κ				4.192		
			tan δ				6.6		
9	2.120	$\perp$	κ				4.332		
			tan δ				6.2		
9		$\parallel$	κ				3.668		
			tan δ				8.5		
10	2.125	$\perp$	κ					4.23	
			tan δ					5.4	
11	2.123	$\perp$	κ					4.293	
			tan δ					11.0	
11	"	$\perp$	κ					3.63	
			tan δ					7.8	
12	2.066	$\perp$	κ						4.22
			tan δ						6.1
13	2.121	$\perp$	κ						4.28
			tan δ						7.9
"		$\parallel$	κ						3.64
			tan δ						10.5

BN, pyrolytically deposited, High-Temperature Materials, Inc., "Boralloy." The microwave data show a small peak possibly due to loss of impurities (perhaps OH ions) at about 800°C. Graphite electrodes and prepurified N₂ used in low-frequency measurements which showed variations among different samples.






Pyrolytic boron nitride


Raytheon

Density 1.23 g/cm³




At 5.74 to 5.65 GHz

Density 1.398 g/cm³



Density 1.23 g/cm³

At 9.21 to 9.04 GHz



Boron nitride
Pyrolytic

Raytheon Company

Post-treated samples, measured at 8.52 GHz, 25°C

Density (g/cm ³)	κ	$\tan \delta$
1.233	2.994	.00008 $\pm$.00002
1.237	3.013	.00005 $\pm$.00003

Sample 2A + 2B, density at 25°C 1.381

T°C	5.07 to 5.00 GHz	
	κ	$\tan \delta$
25	3.199	<.0002
200	3.212	<.0002
400	3.226	<.0002
600	3.241	.0002 $\pm$.0001
800	3.255	.0002 $\pm$.0001
1000	3.272	.0002 $\pm$.0001
1200	3.288	.0002 $\pm$.0001
1300	3.297	.0003 $\pm$.0002
1400	3.309	.0007 $\pm$.0004

Test for anisotropic effects at 8.52 GHz, 25°C, by rotation and reversal of sample:

$$\kappa_{\max} = 3.0018$$


$$\kappa_{\min} = 2.9894$$

Boron nitride


Pyrolytic laminate,
Union Carbide

T °C		
25	5.15±.05	.00025±.00005
173		.00025±.0001
225		
341		
470		
610		
800		
978		.0003±.0001

Boron nitride,
Grade HD0086, density 1.940 g/cm³,
5.17 to 4.96 GHz



Boron nitride, hot-pressed
Grade HD0056



Boron nitride, grade HD 0086

8.52 GHz

T °C	E	K'	tan delta
25		4.31	.00053
25	⊥	4.10	.00055
100	⊥	4.08	.00059
200	⊥	4.07	.00066
300	⊥	4.06	.00075
400	⊥	4.05	.00086
500	⊥	4.05	.00102

Boron nitride, hot-pressed

Union Carbide

Grade HD 0092,

Density 1.9745 g/cm³

At 8.52 GHz

$$\kappa_{\min} = 3.993 \quad \tan \delta = 0.00025$$

$$\kappa_{\max} = 4.091 \quad \tan \delta = 0.00026$$

T°C	At 4.54 to 4.47 GHz	
	κ	$\tan \delta$
25	4.08	.00026
113	4.08	.0003
185	4.09	.0005
322	4.09	.00055
423	4.10	.00040
530	4.11	.00035
639	4.12	.00040
752	4.13	.00045
863	4.13	.00050
943	4.14	.00050
1021	4.15	.00055
1096	4.16	.00080
1170	4.16	.0013
1219	4.17	.0019
1287	4.18	.0034
1373	4.19	.0040
1427	4.20	.0028
1446	4.22	.0023
1460	4.24	.0044
1470	4.24	.0046

Grade HD 0093

Density 1.9165 g/cm³

At 8.52 GHz

$$\kappa' = 3.998 \pm 0.002$$

$$\tan \delta = 0.00052$$

T°C	At 4.53 to 4.44 GHz	
	κ	$\tan \delta$
25	4.003	.0005
207	4.048	.0004
393	4.072	.00045
513	4.088	.0004
593	4.101	.0007
798	4.146	.0030
852	4.166	.0052
891	4.204	.0040
1018	4.320	.0028
1077	4.479	.0057
1094	4.485	.0071
1110	4.54	.01
943	4.25	.0026
860	4.19	
25	4.01	

Density check after run 1.916

Grade HD 0094, at 8.52 GHz

Sample 2: density 1.303 g/cm³

T°C	κ	$\tan \delta$
25	3.004	.00033

Sample 1: density 1.307 g/cm³

T°C	κ	$\tan \delta$
25	3.016	.00033
93	3.02 $\pm$.03	.00030
192		.00035
339		.00037
471		.00040
602	3.04 $\pm$.03	.00040
705		.00047
754		.00060
793		.00095
843		.0020
954		.0085
999		.0135

At 5.30 to 5.26 GHz



Density: 1.303 g/cm³

T°C	κ	$\tan \delta$
25	3.004	.00033
120	3.008	.00037
203	3.012	.00039
325	3.018	.00044
404	3.021	.00043
498	3.026	.00046
601	3.032	.00046
721	3.039	.00065
812	3.047	.00186
884	3.053	.00447
908		>.01

Hot-pressed boron nitride, grade HBN

Carbon Products Division
Union Carbide Corp.
(Formerly National Carbon Co.)

4.95 to 4.88 GHz



Density 2.054 g/cm³

1" cylinder, 8.52 GHz

T °C	E	K'	$\tan \delta$
25	⊥	4.38	.00050
25		4.52	.00056
100		4.52	.00056
200		4.51	.00061
300		4.50	.00064
400		4.49	.00066
500		4.48	.00073

Boron nitride, hot-pressed
Grade HBR


Union Carbide Corporation
Carbon Products Division

E $\perp$ direction of pressing

T°C		10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷
25	κ	4.77	4.77	4.76	4.76	4.76	4.76
	10 ⁴ tan δ	18.2	7.1	4.9	1.5	1.4	0.9
100	κ	4.85	4.80	4.78	4.78	4.78	4.78
	10 ⁴ tan δ	165	45.4	9.4	4.1	2.1	0.6
200	κ	5.26	4.96	4.85	4.82	4.81	4.81
	10 ⁴ tan δ	596	277	101	39	5.4	23
300	κ	5.75	5.25	5.00	4.89	4.85	4.85
	10 ⁴ tan δ	855	526	231	109	33.8	12.5
400	κ	6.75	5.70	5.21	5.00	4.88	4.87
	10 ⁴ tan δ	28.0	11.57	4.95	2.3	1.2	.37
500	κ	8.07	6.46	5.62	5.31	5.08	4.93
	tan δ	1.994	.389	.109	.0419	.024	.014

Boron nitride, Cold-pressed

Union Carbide Corporation



Rod sample, at 8.52 GHz

Density: 1.474 g/cm³




At 25°C:

$$\kappa' = 3.412; \tan \delta = .00046$$

Calcium carbonate (calcite)
Single crystal mineral,
hexagonal, decomposes at 894°C


E || c, crystal No. 1

E ⊥ c, crystal No. 2





Calcium fluoride crystal
Single crystal, cubic, m.p. 1360°C

M.I.T., Crystal Physics
Laboratory




For more complete data see K. V. Rao
and A. Smakula, J. Appl. Phys. 37,
319 (1966).





Cerium fluoride, multicrystal,
at 1 MHz





M.I.T., Laboratory for Insulation
Research



	At 25°C	
Freq.	10^5	6×10^7
κ	2.66	15.8
$\tan \delta$	3.86	0.253

Cr_2O_3 single crystal

The Linde Air Products Company



Cobalt oxide

Massachusetts Institute of Technology
Crystal Physics Laboratory

Cobalt oxide-nickel oxide

At 25°C, 1 MHz

	κ	$\tan \delta$
CoO	12.9	.0005
CoO-NiO	40	.39

50/50 mole percent

For complete data see: K. V. Rao and A. Smakula, J. Appl. Phys.
36, 2031 (1965).


Copper halide pressed powders Massachusetts Institute of Technology
Laboratory for Insulation Research

Measured values at 14 GHz

Sample density/X-ray density



	κ'	$\tan \delta$
CuBr	4.85/5.17	$6.33 \times .001$
CuCl	3.68/4.10	$6.52 \times .001$
CuI		$27.8 \times .112$

Hafnium oxide (multicrystal) stabilized with
 Y_2O_3 , nuclear grade Zircoa Y-790, density
 7.445 g/cm^3 (m.p. 2810°C), see also p. 118



Lanthanum aluminate (LaAlO_3),
single crystal (m.p. 1612°C)
Elec. field in $[111]$ direction

National Lead



Lead halides

M. I. T. Crystal Physics Laboratory

	Electric field dir.		At 1 MHz, 25°C		Activation energy for "intrinsic" conduction
	parallel to		κ'	$\tan \delta$	
PbBr ₂	a	4.72	52.7	.0052	-
	b	8.06	56.3	.0033	-
	c	9.55	25.3	.0033	-
PbCl ₂	a	4.53	47.4	.11	.30 eV
	b	7.62	51.3	.065	.28 eV
	c	9.05	24.8	.051	.42 eV
PbCl ₂ -PbBr ₂ c 85/15 mol %			28.5	.016	1.1 eV

For additional data on these materials see: A. Smakula, Tech. Rep. No. 6,
(Final Report under Contract Nonr 1841(88)), M. I. T., Crystal Phys. Lab.,
March 11, 1965.

Magnesium aluminate (spinel) MgOAl₂O₃

Single crystal


Union Carbide

Density at 25.0°, 3.57389 g/cm³At 8.52, 25°C: $\kappa' = 8.26 \pm .04$ $\tan \delta = .00009 \pm .00002$

Freq. 4.23 - 4.07 GHz

T°C	$\kappa \pm 02$	$\tan \delta$
25	8.28	.0001
150	8.42	.0002
231	8.54	.0002
297	8.64	.0003
421	8.85	.0010
455	8.91	.0025

Magnesium aluminum silicate
 Cordierite ceramic, at 8.52 GHz
 Density 2.44 g/cm³
 Raytheon Company



Magnesium carbonate, hard-packed
 fine powder, reagent grade,
 at 8.52 GHz, 25°C:

K'	$\tan \delta$
1.282	.0109

Density .189 g/cm³

Transparent MgO ceramic
 IRTRAN-5
 Density = 3.57 g/cm³, 25°C

Kodak

f (Hz)	K'	$\tan \delta$
10 ²	9.82	.0014
8.5 × 10 ⁹	9.72	.00045

Magnesium oxide, single crystal

Norton


50 GHz

κ'
9.72


$\tan \delta \times 10^{-4}$
0.3

MgO ceramic


Laboratory for Insulation Research
Density 3.30 g/cm³




MgO ceramic, L.I.R. (cont.)



MgO ceramic, Minneapolis Honeywell Regulator Co., 99.95% MgO,
density 3.52 g/cc.



MgO ceramic, Minneapolis Honeywell Regulator Co. (cont.)



Magnesium metasilicate,
multicrystalline, F-66

Bell Telephone Laboratories

14 GHz


T °C	κ'	$\tan \delta$
25	6.37	.0012
100	6.39	.0012
200	6.43	.0012
300	6.47	.0012
400	6.52	.0013
500	6.58	.0015
600	6.67	.0020
700	6.75	.0047
800	6.85	.0165

50 GHz

25	6.25	.0012
----	------	-------

International Pipe and Ceramic Corp.
(Gladding McBean and Co.)

Steatite TC-503, 8.52 GHz



Magnesium orthosilicate, multicrystalline

General Electric
Electronic Components Div.

F-118



Density: disk 3.087, cylinder 3.071 g/cm³

Freq. Hz	25°C		100°C		200°C		300°C		400°C		500°C		550°C	
	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$
10 ²	6.625	.00098	6.70	.00445	6.80	.00134	6.91	.00636	7.23	.0662	8.78	.421		
10 ³	6.62	.00027		.00065	6.79	.00076	6.89	.00198	7.04	.0127	7.44	.0890		
2x10 ³				.00086										
3x10 ³				.00098	6.78	.00057								
4x10 ³				.00108										
5x10 ³				.00110										
6x10 ³				.00107										
8x10 ³				.00102										
10 ⁴	6.62	.00013	6.70	.00090	6.78	.00044	6.88	.00090	6.98	.00334	7.20	.0188		
10 ⁵	6.62	.000110	6.69	.00024	6.78	.00064	6.87	.00051	6.96	.00123	7.14	.0049		
5x10 ⁵					6.77	.00098								
10 ⁶	6.62	.000072	6.69	.00016	6.77	.00074	6.85	.00046	6.96	.00069	7.09	.00329		
10 ⁷	6.62	.00011	6.69	.00024	6.77	.00025	6.84	.00083	6.95	.00023	7.08	.00149		
10 ⁸														
8.5 x 10 ⁹	6.59	.00083	6.64	.00086	6.73	.00092	6.81	.00100	6.90	.00109	6.98	.00119	7.03	.00124
1.4x10 ¹⁰														
2.4x10 ¹⁰														

F-202


Freq. Hz	25°C		100°C		200°C		300°C		400°C		500°C		550°C	
	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$
10 ²	6.77	.000515	6.86	.00107	6.99	.00277	7.26	.02835	9.74	.508	14.73	4.29		
10 ³	6.76	.000293	6.85	.00063	6.98	.00202	7.14	.0076	7.70	.142	10.08	.822		
10 ⁴	6.76	.000240	6.84	.00056	6.96	.00124	7.08	.0037	7.34	.0293	8.13	.178		
10 ⁵	6.76	.000233	6.83	.00035	6.95	.00077	7.06	.0017	7.22	.00705	7.40	.0474		
10 ⁶	6.76	.000245	6.83	.00032	6.94	.00067	7.06	.00120	7.18	.0025	7.31	.00975		
10 ⁷	6.76	.00025	6.83	.00025	6.94	.00052	7.05	.00098	7.15	.00153	7.28	.00394		
10 ⁸														
8.5x10 ⁹	6.74	.00080	6.81	.00090	6.92	.0015	7.02	.0014	7.13	.0019	7.23	.0027	7.28	.0031
1.4x10 ¹⁰														
2.4x10 ¹⁰														

Density of disk 3.087, cylinder 3.086 g/cm³



Magnesium titanate (MgTiO_3)
Density 3.21 g/cm^3

U. S. Sonics



Manganese fluoride crystal (MnF_2)

Columbia University

f (Hz) K' $\tan \delta$

10^3 $7.2 \pm .2$.043

10^7 $6.7 \pm .2$ $<.004$

$E \perp$ to platelike, unoriented crystal

Mercury compounds, hot-pressed

Theor. density	Compound	Sample No.	Density (g/cm ³)	T°C	10^2	10^3	10^4	10^5	10^6	10^7	8.5×10^9
6.27	HgI ₂	1	-	25	κ	13.7			11.8		13.4
					$\tan \delta$	.191			.0034		.0037
		2	5.48	25	κ	14.3			12.57		
					$\tan \delta$	.208			.0026		
		3	5.69	25	κ						13.9
					$\tan \delta$						< .003
		4	5.56	25	κ	16.11	13.15	12.41	12.39	12.38	12.37
					$\tan \delta$	.828	.154	.0268	.00427	.00117	.00043
				50	κ	44.35	16.87	13.50	12.98	12.90	12.85
					$\tan \delta$	2.33	.888	.168	.0264	.0047	.00095
				25	κ	15.45	13.03	12.45	12.42	12.41	12.40
					$\tan \delta$	.713	.185	.0334	.0057	.00149	.00076
7.15	HgCl	1	5.36	25	κ	7.49	7.48	7.48	7.46	7.45	
					$\tan \delta$	.0013	.00044	.00029	.00034	.00040	.00029
				50	κ	7.62	7.61	2.59	7.58	7.57	7.57
					$\tan \delta$	.00328	.00005	.00046	.00021	.00028	.00039
				25	κ	7.58	7.58	7.57	7.57	7.56	7.56
					$\tan \delta$	.00050	.00027	.00018	.00021	.00034	.00046
7.73	HgS	1	5.19	25	κ	9.75	9.72	9.68	9.64	9.62	9.58
					$\tan \delta$	.0036	.0035	.0029	.0021	.0017	.0011
				50	κ	9.64	9.61	9.58	9.56	9.53	9.49
					$\tan \delta$	.00324	.00225	.00188	.00174	.00181	.00144
				25	κ	9.63	9.62	9.62	9.61	9.58	9.57
					$\tan \delta$	.00207	.00177	.00162	.00165	.00147	.00119

Nickel oxide, NiO, single crystal

M. I. T., Crystal Physics Lab.

At 25°C, 1 MHz

$$\kappa' = 11.9$$

$$\tan \delta = .0154$$

For complete data see: K. V. Rao and A. Smakula, J. Appl. Phys. 36, 2031-2038 (1965).

Phosphate glass


American Optical

50 GHz

	κ'	$\tan \delta \times 10^{-4}$
2043X	5.00	52
2273X	4.74	26

Rubidium manganese fluoride

Massachusetts Institute of Technology
Crystal Physics Laboratory




Silicon crystal, undoped


Brown University

Apparent properties of 1 cm cube sample with
evaporated gold electrodes.

Silicon single crystal



Radiation damaged single crystal



Silicon crystal, intrinsic
at 25°C

M. I. T., Crystal Physics Lab.

f (Hz)	κ'	$\tan \delta$	ρ (ohm-cm)
10^3	-	-	4100
1.4×10^{10}	12.0	.0090	1190

Silicon carbide type attenuator materials


Carborundum

Nominal resistivity (ohm-cm)	Temperature (°C)	f (Hz)	κ'	$\tan \delta$	Measured resistivity (ohm-cm)
35	25	3×10^8	167	0.96	37.2
	25	10^9	107	0.686	24.4
	25	3×10^9	60	0.58	17.2
	25	8.5×10^9	47.7	0.55	8.05
0.1	25	8.5×10^9	2130	1.85	0.069
50	25*	10^6	10,150	1.17	151
	25**	10^6	29,450	1.36	45
	25*	10^7	2810	1.21	56.5

* Two-terminal measurement.


** Four-terminal measurement, different sample

Nominal 50-ohm material at 10^7 Hz




Carberlox 20, 30, 40
BeO and silicon carbide ceramic

National Beryllia Corp.



Silicon dioxide, natural quartz crystal,
Y-cut plate, silver paint electrodes, at 25°C

Fort Monmouth



Quartz, continued

Y-cut plate

At 25°C, $\kappa' = 4.40$

$$1/\kappa' \left(\frac{d\kappa'}{dt} \right) = -2.8 \times 10^{-5} / ^\circ\text{C}$$





Z-cut plate, E || optic axis

At 25°C, $\kappa' = 4.64$



$$1/\kappa' \left(\frac{d\kappa'}{dt} \right) = -3.9 \times 10^{-5} / ^\circ\text{C}$$

Silver electrodes

Pt electrodes




Silicon dioxide Glasses




Silicate glasses

Fused silica, Corning 7940




Corning Glass Works

Microwave data on fused silica, Corning 7940, density = 2.20027 g/cm³. Data with foil taken on one sample at 6.1 GHz, data with paint taken on second sample at 4.3 GHz.





Corning 7940 continued




Silicon dioxide, high purity glasses
Dynasil 4000

Dynasil Corporation of America
Berlin, New Jersey 08009




SiO₂, glass, Type 101 clear, fused quartz,
99.97 to 99.98% SiO₂

General Electric
Silicon dioxide Dept.




At 50 GHz, 25°C, $\kappa' = 3.80$, $\tan \delta = 0.0002$

SiO₂, glass (cont.)



Silicon dioxide (cont.)



Silicon dioxide, high-purity glasses (cont.)

Spectrosil A

Thermal American Fused Quartz Co.
Montville, N.J. 07045

25°C, 8.52 GHz: $\kappa' = 3.826 \pm .003$

$10^4 \tan \delta = 1.9 \pm .4$

Spectrosil B

25°C, 8.52 GHz: $\kappa' = 3.825 \pm .003$

$10^4 \tan \delta = 1.5 \pm .2$

Frequency in Hz

T°C		10^2	10^3	10^4	10^5	10^6	10^7
25	κ	3.823	3.823	3.823	3.823	3.823	3.823
	$10^6 \tan \delta$	<4	<4	6	7	<40	<130
100	κ	3.83	3.83	3.83	3.83	3.83	3.83
	$10^6 \tan \delta$	<4	<4	<8	<10	<40	<130
197	κ	3.84	3.84	3.84	3.84	3.84	3.84
	$10^6 \tan \delta$	264	44	15	<20	<40	<130
300	κ	3.86	3.86	3.86	3.86	3.86	3.86
	$10^4 \tan \delta$	151	15.9	2	<.4	<.6	<1.3
398	κ	3.89	3.86	3.86	3.86	3.86	3.86
	$10^2 \tan \delta$	15.9	1.76	.219	.04	<.02	<.02
486	κ	3.98	3.89	3.87	3.87	3.87	3.87
	$\tan \delta$	.79	.0883	.00954	.0015	.0005	.0002

Vitreosil, optical grade

25°C, 8.52 GHz, $\kappa' = 3.811 \pm .005$; $10^4 \tan \delta = 1.17 \pm .2$

Vitreosil, commercial grade

25°C, 8.52 GHz, $\kappa' = 3.805 \pm .01$; $10^4 \tan \delta = .80 \pm .13$

Mixed silicate glasses

Corning Lab. No. 119BUC
magnetic glass

Corning Glass Works

25°C, 8.52 GHz

κ'	$\tan \delta$	κ'_m	$\tan \delta_m$
20.8	0.157	1.006	0.372

Corning Code 1723 glass

14 GHz


24 GHz

T°C	κ'	$\tan \delta$	T°C	κ'	$\tan \delta$
25	6.18	.0069	25	6.13	.0075
85	6.21	.0067	85	6.16	.0075
144	6.24	.0065	155	6.20	.0074
231	6.27	.0063	251	6.24	.0073
305	6.31	.0061	333	6.28	.0074
339	6.33	.0060	419	6.32	.0073
396	6.36	.0059	446	6.35	.0073
464	6.40	.0057	510	6.39	.0074
502	6.43	.0056			

Lancaster

No. 7552

Resistivities measured at 100 Hz





Silica glasses (cont.)


Lancaster

(Mixed silicate glasses), resistivities measured at 100 Hz

7357




7357






Lancaster glasses (cont.)

L1957



Lancaster glasses (cont.)

No. L 8100



Mixed silicate glasses (cont.)

M.I.T., Laboratory for Insulation Research

Soda silicate glass	50 GHz	
	κ	$\tan \delta \times 10^{-4}$
1) 9% Na ₂ O, 91% SiO ₂	4.90	158
2) 12% Na ₂ O, 88% SiO ₂	5.08	178

Sample EE 9

Owens-Illinois
Toledo, Ohio 43601


Sample EE 10

EE 9 Freq., 8.52 GHz			EE 10 Freq., 8.52 GHz		
T ^o C	κ	$\tan \delta$	T ^o C	κ	$\tan \delta$
25	5.84	.0070	25	8.17	.0082
97	5.86	.0070	97	8.25	.0082
199	5.90	.0071	202	8.36	.0083
314	5.97	.0072	292	8.47	.0084
421	6.02	.0073	416	8.63	.0089
506	6.03	.0077	501	8.76	.0096
607	6.17	.0081	605	8.98	.0123
32	5.82	.0069	27	8.19	.0080

Silicate glasses (cont.)

X994


Owens Corning




Glasses (cont.)

Pittsburgh Plate Glass Co.

Plate glass



Sheet glass



Silicon dioxide, sintered

Slip-cast

Density 1.957 g/cm³

Brunswick

Freq., Hz	25°C		100°C		200°C		300°C		400°C		500°C	
	κ	10 ⁴ tan δ	κ	10 ⁴ tan δ	κ	tan δ	κ	tan δ	κ	tan δ	κ	tan δ
10 ²	3.38	7.1	3.39	11.0	3.44	.0190	4.42	.896	7.91	9.51	19.1	33.8
3x10 ²	3.38	8.6										
10 ³	3.38	8.8	3.38	7.8	3.41	.99364	3.64	.178	5.09	1.66	7.57	9.00
2x10 ³	3.38	7.3										
5x10 ³			3.38	7.7								
10 ⁴	3.37	6.2	3.38	7.6	3.41	.00158	3.47	.0246	3.90	.334	5.10	1.47
5x10 ⁴			3.38	8.3					3.5			
10 ⁵	3.37	4.5	3.37	8.3	3.41	.00099	3.46	.00465	3.54	.055	3.90	.290
2x10 ⁵			3.37	7.5								
10 ⁶	3.37	3.7	3.37	6.1	3.40	.00081	3.45	.00158	3.49	.0089	3.61	.0483
6x10 ⁶			3.37	3.6								
10 ⁷	3.37	2.5	3.37	3.2	3.40	.00068	3.45	.0008	3.49	.0021	3.55	.0112
8.5x10 ⁹	3.364	6.6										

Silicon dioxide, with 2.5% chromium oxide

Slip-cast,

Density 1.928 g/cm³

Brunswick

Freq., Hz	25°C		100°C		200°C		300°C		400°C		500°C	
	κ	tan δ	κ	tan δ	κ	tan δ	κ	tan δ	κ	tan δ	κ	tan δ
10 ²	3.33	.00345	3.43	.0057	3.57	.0292	4.59	.935	8.73	9.39	36.7	42.4
10 ³	3.33	.00257	3.42	.0043	3.51	.0113	3.72	.179	5.17	1.76	13.5	10.1
10 ⁴	3.32	.00174	3.36	.0034	3.48	.0071	3.59	.0292	3.95	.324	6.09	2.41
10 ⁵	3.32	.00152	3.34	.0027	3.40	.0054	3.51	.0109	3.63	.0537	4.39	.425
10 ⁶	3.31	.00093	3.33	.0020	3.38	.0040	3.49	.0101	3.56	.0149	3.82	.094
10 ⁷	3.31	.00035	3.32	.0017	3.34	.0022	3.42	.0076	3.53	.0106	3.68	.032
8.5x10 ⁹	3.29	.00112										

Silicon dioxide, sintered

Code 7941

Density 1.923 g/cm³

Corning Glass

Freq., ~8.5 GHz

Corning Multiform Glass

T ^o C	κ	$\tan \delta$
25	3.323	.0005
279	3.351	.0009
517	3.378	.0014
769	3.408	.0023
910	3.431	.0028
1043	3.451	.0037
1205	3.455	.0051
1372	3.513	.0091

At 8.52 GHz, 25^oC, density = 1.906 g/cm³

$\kappa = 3.27$; $\tan \delta = .00063$

Silica, slip-cast

Dynasil Corp. of America

8.6 GHz, 25^oC

<u>Sample</u>	Density (g/cm ³)	κ	$\tan \delta$
DSCX-3	1.970	3.395	.00058
DSCX-8E	2.038	3.513	.00054

Quartz fiber

Sample AS-3DX-1R

Source: Philco Ford Corp.
Newport Beach, Calif. 92663

Manufacturer: Fiber Materials Inc.
Graniteville, Mass. 01829

Freq., 8.52 GHz		
T°C	K	tan δ
25*	3.02	.0054
25	2.98	.0019
98	2.97	.0018
198	2.96	.0016
307	2.95	.0015
418	2.95	.0014
497	2.945	.0014
591	2.95	.0016
729	2.96	.0022
828	2.975	.0029
905	2.99	.0035
995	3.01	.0042

* As received, other values after vacuum bake
for 24 hours at 125°C.

Silica fiber composites

Philco-Ford Corp., Aeronutronic Div.

Sample 1-VH-O-M-1, 25°C		(Hz) 10 ⁵	10 ⁶	10 ⁷	7.5x10 ⁷	1.8x10 ⁸
As received,	K	2.779	2.777	2.777	2.775	2.772*
density 1.536 g/cm ³	10 ⁴ tan δ	4.6	8.3	6.4	13.4	17*
After 18 hrs.	K			2.77	2.77	2.77*
vacuum oven 80°C	10 ⁴ tan δ			4.6	9.1	11.5*

* Extrapolated values.

Silica fiber composites (cont.)

Philco-Ford Corp., Aeronutronic Div.

Sample 1-XB-O-M

Density 1.653 g/cm³

8.52 GHz

	T ^o C	K	tan δ
As received, Face 1 up	25	2.919	.0062
Face 2 up	25	2.956	.0064

After vacuum oven

80^oC, 10 days

Face 2 up	25	2.938	.00162
Face 1 up	25	2.895	.00169
	115	2.89	.0012
	246	2.89	.0006
	357	2.90	.0005
	438	↓	.0006
	535		.0008
	608		.0010
	710		.0014
	805		.0020
	908		.0026
	972		.0028
	1000		.0031*

* Extrapolated values. 25 2.89 .00042

Sample AS-3DX 176-17 at 8.5 GHz, density = 1.626 g/cm³

T ^o C	K	tan δ
25	2.873 ± .005	.00355
94	2.86 ± .01	.00199
203	2.86	.00054
288	2.85	.00040
377	2.85	.00043
466	2.85	.00054
535	2.86 ± .02	.00068
289	2.85	.00042
27	2.840 ± .005	.00038 ± .00003


Silica fibers in aluminum phosphate matrix
ChemCeram

Whittaker Corp.


<u>Sample</u>	T°C	8.52 GHz		Density (g/cm ³)
		κ	$\tan \delta$	
1, as received	5	2.73	.0051	1.547
2, as "	25	2.70	.0060	1.543
2, dried*	25	2.68	.0043	(wt. loss .049%)
2, room humidity	25	2.70	.0050	
	116	2.70	.0050	
	235	2.71	.0053	
	410	2.71	.0080	
	495	2.71	.0105	
	580	2.72	.0140	
	673	2.72	.0177	
	760	2.72	.0228	
	827	2.73	.0265	
	916	2.74	.0315	
	967	2.75	.038	
	25	2.71	.0047	

* 4 days at 120°C in vacuum oven.

Silicon nitride, pyrolytic



North American Aviation



Silicon nitride ceramic

At 8.52 GHz, density 2.449 g/cm³

T°C

25

170

323

446

586

674

714

864

912

991

509

348

K

5.54

5.54

5.54

5.55

5.55

5.56

5.57

5.58

5.59

5.63

5.55

5.54

tan delta

.0036

.00375

.0040

.00365

.0030

.0050

.0054

.00615

.00630

.00665

.0034

.0040

Silicon nitride ceramic,

after vacuum drying at 100°C, at 8.5 GHz

Density 2.128 g/cm³

Raytheon Company

T°C

25

K

5.15



tan delta

0.00037

Silicon nitride ceramic,
technical grade,
density 2.456 g/cm^3 ,
measured in dry nitrogen

Haynes Stellite
Division of Union Carbide


(a)
Dielectric constant
vs. frequency



(b)
Dielectric loss
factor versus
frequency

Silver iodide, pressed powder
at 10,000 psi, 27°C,
aged several weeks
unless noted


Massachusetts Institute of Technology
Laboratory for Insulation Research




Sodium chloride, doped
(0.075 mole % BiCl_3)

M.I.T., Crystal Physics Laboratory

Variation of dielectric constant with
temperature at different frequencies




Dielectric loss as a function of
temperature at different frequencies




Sodium chloride, doped (cont.)
(1.23 mole % BiCl_3)

Variation of dielectric constant with
temperature at different frequencies




Dielectric loss as a function of
temperature at different frequencies




Sodium chloride (cont.)

Specific conductivity as a function of $1/T$
at different frequencies

(0.075 mole % BiCl_3)




(1.23 mole % BiCl_3)



Strontium fluoride


M. I. T., Crystal Physics Lab.

For more complete data see
K. V. Rao and A. Smakula,
J. Appl. Phys. 37, 319 (1966).




Strontium fluoride (cont.)
Single crystal

M.I.T., Crystal Physics Lab.



Ta₂O₅ ceramic, hot-pressed from
Ciba optical grade powder,
density 8.27 g/cm³

Massachusetts Institute of Technology
Laboratory for Insulation Research




Thallium halides

M. I. T., Crystal Physics Lab.


Material	κ' , 25°C 10 ⁶ Hz	κ' , 4°K	$\tan \delta$, 25°C 10 ⁶ Hz	Activation energy for conduction in eV
TlF pressed	19.7	-	.00015	-
TlCl	31.9	-	.00006	.73
TlBr	30.4	-	.00005	.77
TlI polycrystalline	20.4	20.0	.00024	-
KRS6 (TlCl) _{.7} -(TlBr) _{.3}	32.2	38.4	.000075	.71
KRS5 (TlBr) _{.42} -(TlI) _{.58}	32.4	-	.00016	.66
TlI + CsI .01	32.5	39.4	.000068	.65

For more complete data see reports under Contract AF 19(628)-395.

Thorium oxide ceramic, nuclear grade Zircoa, measured in air except at room temperature in dry nitrogen. Densities: of disk 9.852 g/cm³; cylinder 9.774 g/cm³




Dielectric constant κ'' vs. frequency and temperature shows build-up of low-frequency polarization and small temperature coefficient at 10^7 Hz.



Dielectric loss tangent at low temperatures shows peak moving to high frequencies with a low activation energy (0.51 eV).


Thorium oxide ceramic (cont.)

Dielectric loss factor κ'' versus frequency shows ease of conduction when many hot electrons are available




Thorium oxide ceramic (cont.)


Conductivity vs. reciprocal temperature shows intrinsic conduction range having activation energy of 1.70 eV.



ThO₂ ceramic, Laboratory for Insulation Research; minor constituents
Mg, Pb, Zn; traces of Ca, Cu, Fe, Si; density = 8.77 g/cm³



ThO₂ ceramic, Laboratory for Insulation Research; minor constituents Mg, Pb, Zn; traces of Ca, Cu, Fe, Si; density - 8.77 g/cc.



Vanadium oxide (V₂O₃)



M. I. T., Lab. Ins. Research

Pressed powder samples, -185°C:


f (Hz)	κ' meas.	κ' corr. to full density	Density g/cm ³
10 ⁵	6.52	15.2	2.60
10 ⁶	4.72	14.5	2.28

Yttrium oxide
 Y_2O_3 crystal


M.I.T., Laboratory for Insulation Res.




Yttrium oxide, nuclear grade (high purity 99.8%) ceramic, Zircoa;
densities: of disk 5.1000, cylinder 4.917 g/cm³.



(a) Dielectric constant versus frequency




(b) Dielectric loss factor vs. frequency shows two dipole regions



(c) Conductivity versus $1/T$ does not show intrinsic region

Zinc oxide, single crystal

Airtron Div. of Litton Industries



Measurements of 1 and 300 MHz
with electric field $\parallel$ to c axis.
At 14 GHz field was perpendicu-
lar.



Second sample heat treated


Major frequency
resonances
(kHz)

222
482
600
677
740

Dielectric constant


Hz	κ
10^2	12.29
10^3	12.07
10^4	11.90
10^5	12.13
10^6	8.35
9.5×10^6	






Zirconium oxide (ZrO_2), mono-cubic, stabilized with lime (CaO), technical grade ceramic Zircoa "C", densities of disk 5.696 g/cm³, of cylinder 5.646 g/cm³. Dielectric constant vs. frequency showing large grain-boundary polarization.

Dielectric loss factor versus frequency.




See also page 121




Zirconium oxide stabilized with 8% Y_2O_3 nuclear grade ceramic Zircoa Y-904; densities of disk 5.444 g/cm³, of cylinder 5.647 g/cm³. Dielectric constant versus frequency

Dielectric loss factor versus frequency


See also p. 121






Zirconium oxide stabilized with 7.5% CaO, nuclear grade ceramic Zircoa Y-1362, densities of disk 5.087 g/cm³, of cylinder 5.015 g/cm³. Dielectric constant vs. frequency

Dielectric loss factor versus frequency.




See also p. 121

Zirconium oxide, nuclear grade, conductivity of heavy oxides at 100 Hz vs. $1/T$. Activation energies for each approach 1.25 eV.




Zirconium oxide, "Zircolite" ceramic

Air Force Materials Laboratory
Wright-Patterson Air Force
Base, Ohio




Zirconium silicate (zircon), ZrSiO_4 ,
single crystal, all samples from
one crystal

E || c
Sample 1, run 1,
 N_2 to 200°C , air to 500°C ,
Ag electrodes



E || c
Sample 2, run 1,
same conditions as for Sample 1




Zircon (cont.)

E || c

Sample 2, run 2


Argon atmosphere throughout the run, Ag electrodes



E ⊥ c


Sample 1, run 1

N₂ to 200°C, air to 500°C, Ag electrodes




Zircon (cont.)

$E \perp c$
 Sample 1, run 2
 N_2 to $500^\circ C$, Ag electrodes



$E \perp c$
 Sample 1, run 3
 Air to $500^\circ C$, Pt electrodes



II. MINERALS, ROCKS, SOILS, AND MISCELLANEOUS INORGANICS


Single-crystal minerals

Apatite

$E \perp c$

Sample 1, run 1, 25°C


1 MHz, $\kappa' = 10.1$



$E \perp c$


Sample 1, run 2,

repeat of run 1



Apatite (cont.)



E || c, 25°C, 1 MHz, $\kappa' = 8.58$




Astrophyllite Unoriented crystal		10 ² Hz	10 ³ Hz	10 ⁴ Hz
		κ' 15.42	15.17	14.83
	tan δ	0.035	0.021	0.014
Benitoite BaTiS ₃ O ₉ . unoriented cryst.		κ' 23.8	19.6	19.2
		tan δ 0.374	0.090	0.0195

Beryl

E || c



Beryl, E 1 c



Neptunite, $(\text{Na}, \text{K})_2(\text{Fe}, \text{Mn})(\text{Si}, \text{Ti})_5\text{O}_{12}$
data on unoriented crystal


	10^3 Hz	10^4 Hz
κ'	8.33	8.19
$\tan \delta$	0.0335	0.069

Spodumene

E || a


○ rising temperature

▽ lowering temperature




Spodumene (cont.)


E || b



E || b




E || a



Spodumene (cont.)

E || c




At 10 MHz, 25°C
 K'


E || a 8.05
b 7.82
c 9.31

Topaz

κ'' at 10 MHz




E || a




Topaz (cont.)

$E \parallel b$




$E \parallel c$




Tourmaline

$E \perp c$, piezoelectrically active
at 1 MHz



$E \parallel c$



Crushed minerals

Halite (rock-like pieces of porous salt), at 50% R.H., 25°C, 14 GHz

Sample	κ'	$\tan \delta$	Density (g/cm ³)
1, surface	4.52 - 4.63	.0056 - .0057	1.808
2, "	4.68 - 4.82	.0106 - .0103	1.861
3, "	3.81 - 3.83	.0127 - .0109	1.565
4, "	3.95 - 4.00	.0104 - .0134	1.670
5, 1' down	3.69 - 3.94	.0198 - .0125	1.500
6, "	3.25 - 3.50	.0077 - .0113	1.422
7, 3' "	4.17 - 4.18	.036 - .046	1.646
7, dried	4.12 - 4.19	.0193 - .0206	1.640

Limonite, crushed, density 1.733 g/cm³

Harvard College Observatory

	10 ⁹ Hz		3 x 10 ⁹	
T°C	κ'	$\tan \delta$	κ'	$\tan \delta$
25	4.17	.0108	3.73	.046
475	3.65	.0134	3.63	.0193
404	3.62	.0076	3.60	.0113
325	3.61	.0057	3.58	.0084
250	3.61	.0048	3.57	.0073
185	3.60	.0045	3.56	.0064
107	3.58	.0047	3.55	.0059
22	3.56	.0057	3.53	.0055

Limonite, 8.52 GHz

Sample 1, coarse, 25°C

$\kappa' = 3.95 - 4.01$ depending on rotation
 $\tan \delta = 0.18 - 0.059$

Sample 2, fine, 25°C

$\tan \delta = 0.0122 - 0.0127$

Sample 3	T°C	κ'	$\tan \delta$
	25	3.82	.0012
	510	3.60	.0085
	400	3.55	.0047
	300	3.52	.0039
	200	3.50	.0042
	100	3.48	.0043
	25	3.49	.0043

Sample in equilibrium with room
humidity approx. 50%.

Magnesite, crushed powder, hard-packed


25°C, 50% R.H., 8.52 GHz, $\kappa' = 3.29$, $\tan \delta = .0054 - .0059$, density 1.11 g/cm³

Quartz powder, 8.52 GHz, pre-dried in oven at 100°C, density 1.22 g/cm³

T°K	κ'	$\tan \delta$
80	2.446	.0021
200	2.460	.0027
300	2.472	.0028
400	2.483	.0027
500	2.495	.0031
600	2.497	.0035

Rocks

Hawaiian high-density basalt




- % H₂O on dry weight basis 0.358
% H₂O on dry volume basis 0.956
density 2.6756 g/cm³
- Dry after 3 days in oven at 105°C
density 2.669 g/cm³
- ▲ % H₂O on dry weight basis 0.377
% H₂O on dry volume basis 1.005
density 2.677 g/cm³

Hawaiian high-density basalt 50% relative humidity

Density 2.717 g/cm³

	Sample 1	Sample 2	Sample 3	Sample 3	Sample 3	Sample 4
Freq. (Hz)	3x10 ⁸	10 ⁷	3x10 ⁸	10 ⁹	3x10 ⁹	8.5x10 ⁹
κ	8.36	9.90	9.30	9.08	8.85	8.40
tan δ	.043	.080	.034	.033	.037	.04
μ'/μ _o	1.174	1.17	1.113	1.10	1.08	1.01
tan δ _m	.0077	<.002	.0075	.026	.072	.06

Hawaiian low-density basalt



- % H₂O on dry weight basis 0.441
% H₂O on dry volume basis 0.0617
density 1.401 g/cm³
- Dry (after 3 days in oven at 105°C)
density 1.400 g/cm³
- ▲ % H₂O on dry weight basis 2.71
% H₂O on dry volume basis 3.79
density 1.438 g/cm³

Hawaiian low-density basalt 50% relative humidity


Freq. (Hz)	10 ⁷	3x10 ⁸	10 ⁹	3x10 ⁹
K	4.9	3.74	3.51	3.30
tan δ	.068	.085	.0481	.053
μ'/μ _o	1.047	1.047	1.040	1.035
tan δ _m	<.002	.0040	.002	.002

Hawaiian deep-ocean basalt No change after heating to 200°C

Freq. (Hz)	10 ⁵	10 ⁶	10 ⁷	8.5x10 ⁹
K	188	153	124	10.2
tan δ	93.5	11.6	.146	.560
ρ	1025	1015	995	36.9


Quincy granite

Density 2.631 g/cm³
Temp. run in dry N₂



Virginia granite or marble

Temperature run in dry N₂




Quincy granite

T°C	10 ² Hz	10 ³ Hz	10 ⁴ Hz	10 ⁵ Hz	T°C	1 kHz	σ
25	κ' 10.5	9.26	8.01	2.06	26	9.26	4.50×10^{-10}
	$\tan \delta$ 0.0796	0.0875	0.0875	0.0705	69	10.3	4.58
	σ 4.64×10^{-11}	4.5×10^{-10}	3.9×10^{-10}	2.76×10^{-8}	105	10.9	4.64
200	κ' 15.4	12.47	11.07	9.78	147	11.5	5.31
	$\tan \delta$ 0.21	0.121	0.088	0.090	204	12.51	8.61×10^{-10}
	σ 1.797×10^{-10}	8.37×10^{-10}	5.40×10^{-9}	4.88×10^{-8}	251	14.87	1.85×10^{-9}
400	κ' 64.5	32.9	19.42	12.86	305	19.3	3.38×10^{-9}
	$\tan \delta$ 1.02	0.60	0.374	0.252	345	23.4	5.51×10^{-9}
	σ 3.65×10^{-9}	1.097×10^{-8}	4.03×10^{-8}	1.797×10^{-7}	400	32.9	1.09×10^{-8}
600	κ' 293	106	42.5	22.0	466	34.4	9.5×10^{-8}
	$\tan \delta$ 6.85	2.31	1.03	0.94	553	81.3	9.34×10^{-8}
	σ 1.114×10^{-7}	1.16×10^{-9}	2.43×10^{-7}	6.60×10^{-7}	601	106	1.16×10^{-9}
800	κ' 4195	238	84	37.4	700	172	4.25×10^{-7}
	$\tan \delta$ 14.4	9.64	3.05	1.11	806	243	1.311×10^{-6}
	σ 1.116×10^{-6}	1.275×10^{-6}	1.423×10^{-6}	2.30×10^{-6}	874	26,800	1.84×10^{-4}
1000	κ'	47000	6100	710	996	45,900	3.57×10^{-4}
	$\tan$	14.0	12.6	12.4			
	σ	3.65×10^{-4}	4.26×10^{-4}	4.89×10^{-4}			

Virginia Greenstone

Density 2.936 g/cm³, temperature run in dry N₂

(-----) R. H. 52%



Limestone, from Lucerne Valley

50% R. H., 25°C, 14 GHz

Raytheon

Sample	K'	tan delta	Density
1	8.21 - 8.45	.0038 - .0080	2.667
2	8.62 - 8.64	.0178 - .0189	2.646


Synthetic basalt and lunar rocks, Apollo 11 and 12, see:

- D.H. Chung, W. B. Westphal, and G. Simmons, "Dielectric Properties of Apollo 11 Lunar Samples and their Comparison with Earth Materials," J. Geophys. Res. 75, 6524-6531 (1970).
- D. H. Chung, W. B. Westphal, and G. Simmons, "Dielectric Properties of Apollo 12 Lunar Samples," a paper (T64c) presented at the 1970 Am. Geophys. Union Meeting, Washington D.C., April 23, 1970.
- D. H. Chung, W. B. Westphal, and G. Simmons, "Dielectric Behavior of Lunar Samples: Electromagnetic Probing of the Lunar Interior," Proc. Second Lunar Sci. Conf., Vol. 3, MIT Press, 1971, pp. 2381-2390.

Rocks (cont.)

Rhyolite

Density 2.655 g/cm³, temperature run in dry N₂




Sandstone, almond, oil-bearing as cored, 25°C

Raytheon


Frequency in MHz

Sample		1	3	10	60	100
1	κ'	5.64	5.23	4.90	4.55	4.50
	$\tan \delta$	0.131	0.104	0.084	0.059	0.049
2	κ'	6.13	6.09	6.07	6.06	6.06
	$\tan \delta$	0.0100	0.0084	0.0059	0.0047	0.0051
3	κ'	6.05	6.04	6.01	5.91	5.87
	$\tan \delta$	0.0068	0.0079	0.00855	0.0095	0.0097
4	κ'	5.33	5.08	4.92	4.75	4.73
	$\tan \delta$	0.060	0.057	0.051	0.036	0.027
5	κ'	5.40	5.16	4.93	4.68	4.61
	$\tan \delta$	0.080	0.068	0.058	0.042	0.032
6	κ'	22.9	11.24	9.20	6.60	6.20
	$\tan \delta$	1.88	1.39	0.68	0.338	0.29
7	κ'	6.15	6.12	6.10	6.04	6.00
	$\tan \delta$	0.0088	0.0093	0.0096	0.0102	0.0105

Soils
Fullers Earth, at 8.52 GHz



Hawaian



- % H₂O on weight basis
- % H₂O on volume basis
- Density 0.8634 g/cm³
- Dry after 3 days in oven at 105°C
- Density .7627 g/cm³
- ▲ % H₂O on dry weight basis = 72.27
- % H₂O on volume basis = 50.60
- Density 1.2133 g/cm³

Soils

Hawaiian soil saturated with distilled H_2O

% H_2O on dry weight basis = 127.5

% H_2O on volume basis = 63.0


Density 1.303 g/cm^3

Freq. (Hz)	10^3	10^4	10^5	10^6	9.5×10^6	7×10^7
κ	29,700	988	230	1295	81.5	64.2
$\tan \delta$	135	43.9	20.05	3.32	.776	.185

Hawaiian soil with approximately 25% H_2O
on dry weight basis. Density $\approx .88 \text{ g/cm}^3$.

Freq. (Hz)	10^2	10^3	10^4	10^5	10^6	10^7	3×10^8	1×10^9	3×10^9	8.5×10^9
κ	10560	940	68.0	21.66	12.04	6.88	5.12	4.90	4.45	3.97
$\tan \delta$	2.30	4.43	7.25	2.67	.827	.389	.105	.079	.81	.135

Mass. loams, at 10 MHz, 25°C



Desert sand (Raytheon)

15% R. H. . 25°C. 14 GHz

$\kappa' = 2.88$

$\tan \delta = 0.0115$

Density = 1.633 g/cm³

Miscellaneous Inorganics

Sands

<u>Sample</u>	<u>Condition</u>		10^8	3×10^8	10^9
Holliston sand	As received $d = 1.54$	κ	2.73	2.70	2.67
		$\tan \delta$	0.0044	0.00278	0.00217
		% H_2O	0.09	0.06	0.06
	Dry $d = 1.54$	κ	2.70	2.69	2.67
		$\tan \delta$	0.0022	0.00235	0.0017
	1% H_2O $d = 1.53$	κ	3.25	3.22	3.12
		$\tan \delta$	0.0084	0.059	0.062
	3% H_2O $d = 1.39$	κ	3.40	3.35	3.30
		$\tan \delta$	0.0224	0.0930	0.120
	10% H_2O $d = 1.45$	κ	7.25	7.15	6.85
		$\tan \delta$	0.056	0.054	0.056
	93% RH $d = 1.58$	κ	2.87	2.85	2.81*
		$\tan \delta$	0.006	0.020	0.063*
Slatterville sand No. 60	As received $d = 1.60$		2.84	2.82	2.80
			0.0070	0.0033	0.0033
	Dry $d = 1.60$		2.82	2.80	2.78
			0.0038	0.0024	0.0016
	1% H_2O $d = 1.53$		2.80	2.72	2.67
			0.032	0.040	0.50
	3% H_2O $d = 1.48$		3.60	3.51	3.19
			0.947	0.061	0.089
	10% H_2O $d = 1.54$		7.50	7.35	7.06
			0.090	0.109	0.081
	93% RH $d = 1.60$		2.92	2.90	2.84
			0.004	0.0106	0.0364

* % H_2O = 0.385

Miscellaneous Inorganics
Ices, glacial

Dielectric Constants

Sample, Source	Density (g/cm ³)	Temp. (°/C)	Frequency in MHz					
			110*	150	300	500	1000	2700
Dartmouth Firm ice No. 12	0.898	-1	3.22	3.21	3.20	3.20	3.20	3.201
		5	3.21	3.20	3.20	3.20	3.20	3.195
		10	3.20	3.19	3.19	3.19	3.19	3.188
		20	3.18	3.18	3.18	3.18	3.18	3.175
		30	3.17	3.16	3.16	3.16	3.16	3.163
		40	3.15	3.15	3.15	3.15	3.15	3.151
		50	3.14	3.14	3.14	3.14	3.14	3.139
		60	3.13	3.13	3.13	3.13	3.13	3.129
Dartmouth Sea ice No. 14	0.917	-1	3.41	3.38	3.34	3.31	3.28	
		5	3.33	3.31	3.29	3.27	3.26	
		10	3.28	3.26	3.25	3.24	3.24	
		15	3.26	3.24	3.24	3.23	3.22	
		20	3.23	3.22	3.21	3.20	3.20	3.197
		25	3.22	3.21	3.20	3.19	3.19	3.184
		30	3.21	3.20	3.19	3.18	3.17	3.173
		40	3.19	3.18	3.17	3.16	3.16	3.159
Tuto Tunnel	0.902	50	3.18	3.17	3.16	3.15	3.15	3.144
		60	3.15	3.15	3.14	3.14	3.14	3.133
		-1	3.22	3.21	3.20	3.20	3.20	3.197
		5	3.20	3.19	3.19	3.19	3.19	3.189
		10	3.19	3.18	3.18	3.18	3.18	3.182
		20	3.17	3.17	3.17	3.17	3.17	3.170
		30	3.16	3.16	3.16	3.16	3.16	3.159
		40	3.15	3.15	3.15	3.15	3.15	3.149
Little America	0.881	50	3.14	3.14	3.14	3.14	3.14	3.138
		60	3.13	3.13	3.13	3.13	3.13	3.129
		-1	3.09	3.08	3.07	3.07	3.07	3.065
		5	3.07	3.06	3.06	3.06	3.06	3.057
		10	3.06	3.05	3.05	3.05	3.05	3.050
		20	3.04	3.04	3.04	3.04	3.04	3.036
Arctic	0.835	30	3.03	3.03	3.03	3.03	3.03	3.025
		40	3.01	3.01	3.01	3.01	3.01	3.012
		50	3.00	3.00	3.00	3.00	3.00	3.000
		-1	2.90					2.880
		5	2.89					2.875
		10	2.88					2.870
		20	2.86					2.861
		30	2.85	2.85	2.85	2.85	2.85	2.852
		40	2.85	2.85	2.85	2.84	2.84	2.844
		50	2.84	2.84	2.84	2.84	2.84	2.835
		60	2.83	2.83	2.83	2.83	2.83	2.827

* 110 MHz values are extrapolated, not measured.

Ices (cont)


Loss Tangent

Frequency in MHz


Sample, Source	Temp. (°C)	110 *	150	300	500	1000	2700
Dartmouth No. 12	-1	.0030	.0022	.00108	.00052	.0004	.00038
	5	.0019	.00144	.00076	.00040		.00034
	10	.00145	.00110	.00055	.00028		.00030
	20	.00092	.00068	.00033	.00019		.00024
	30	.00059	.00043	.00021	.00013		.00020
	40	.00034	.00026	.00013	.00008		.00016
	50	.00020	.00014	.00008	.00005		.00014
	60	.00008	.00005	.00003	.00003		.00013
Dartmouth No. 14	-1	.039	.037	.0225	.0200	.0122	
	5	.026	.025	.0200	.0130	.0080	
	10	.0195	.0190	.0145	.0097	.0067	
	15	.017	.0157	.0107	.0082	.0054	
	20	.015	.0130	.0091	.0068	.0045	.0044
	25	.013	.0106	.0067	.0047	.0030	.0029
	30	.010	.0080	.0048	.0033	.00205	.00185
	40	.0058	.0045	.0026	.0017	.00112	.00065
	50	.0028	.0023	.0015	.00098	.00062	.00030
	60	.0014	.0012	.00078	.00054	.00035	.00016
Tuto Tunnel	See data for Dartmouth No. 12 (no measurable difference)						
Little America	-1	.0049	.0037	.0018	.00106	.00054	.00038
	5	.0035	.0026	.0013	.00072	.00037	.00032
	10	.00286	.00217	.00108	.00056	.00025	.00027
	20	.0020	.00154	.00078	.00038	.00018	.00024
	30	.00146	.00116	.00057	.00029	.00014	.00020
	40	.00105	.00085	.00044	.00025	.00013	.00014
	50	.00076	.00057	.00030	.00021	.00012	-
* 110 MHz values are extrapolated, not measured.							
Arctic	-1			-			.00033
	5			-			.00029
	10			Cooling failed, sample melted			.00024
	20			-			.00018
	30			.00045			.00016
	40			.00032			.00014
	50			.00022			.00013
	60			.00015			.00013

Ices (cont.)

Dartmouth No. 12




Sea ice




Miscellaneous Inorganics (cont.)
CFI 1003

Ceramics for Industry
Attenuator materials



CFI 1006



Miscellaneous Inorganics (cont.)

Corning Code 0330

3 GHz

κ



6.58

Corning Glass


25°C

$\tan \delta$


.0055




Ferrites




R-1




R-4



R-5



R-6



Miscellaneous Inorganics

Havelex, glass-bonded mica
At 8.52 GHz, 25°C

Haveg Industries, Inc.
Taunton Division

Type	κ'	$\tan \delta$
1080	6.35	.0025
1090	6.17	.0058
1101	8.89	.0027
2101	6.35	.0013
2103	9.2	.0021
2801	6.35	.0020
2803	6.05 -	.00255 -
	6.39	.0026

Isomica 4950


General Electric
Electronic Components Div.

Vacuum baked for 36 hrs. at 125°C, E || sheet

Freq. (MHz)	κ	$\tan \delta$
300	5.33	.0013
8520	5.31	.00207
8520	5.32*	.0025*

* 50% relative humidity.


Mycalex 410




Note: all Mycalex samples from sheet stock. 10^2 through 10^8 Hz, E $\perp$ sheet.
 3×10^8 to 2.4×10^{10} Hz, E || sheet.

Mycalex (cont.)


500



555






560



Mycalex (cont.)

620



Asphalt pavement

Sample	Density	(Hz)	10^5	10^6	10^7	10^8
S	Dry	κ	4.51	4.34	4.21	4.14
		$\tan \delta$	.0280	.0221	.0181	.0198
S	Wet	κ	42.0	17.7	9.03	6.54
		$\tan \delta$	.875	.638	.444	.233
L	Dry	κ	4.79	4.73	4.70	4.61
		$\tan \delta$	.0187	.0158	.0123	.0121
L	Wet	κ	14.48	9.28	6.65	6.01
		$\tan \delta$	.368	.280	.190	.104

Raytheon

Asphalt pavement at 40% R. H., 25°C, 14 GHz

Sample No.	Thickness (cm)	Density (g/cm ³)	H ₂ O (%)	Orientation	κ'	$\tan \delta$
1	0.1			Independent	4.73	.0114
2	0.1			"	4.62	.0103
3	0.1				5.03	.0120
4	0.1				5.48	.0095
5	0.91	2.35	.754	Face 1	6.02	.021
				Face 1, 90°	5.53	.052
				Face 2	5.37	.204
				Face 2, 90°	5.44	.102

Liquid asphalt

Esso

f (Hz)	κ'	$\tan \delta$
1×10^9	2.46	.0017
3×10^9	2.46	.0019
8.5×10^9	2.46	.0013

Solid asphalt formed by burning liquid for 2 days at 300°C

1.5×10^6	2.64	.0043
10^7	2.64	.0030
1.8×10^7	2.64	.0027
4×10^7	2.64	.0025
8.5×10^9	2.63	.0018

Miscellaneous Inorganics

Concrete pavement

California Highway Department

Sample	Density	(MHz)	0.1	1	10	100
S1	Dry	κ	9.05	7.97	7.01	6.57
		$\tan \delta$	.0946	.0913	.0730	.0536
S1	Wet	κ	176.5	69.2	23.5	13.2
		$\tan \delta$	.822	1.088	.734	.485

Concrete pavement at 40% R. H. , 25°C, 14 GHz

Raytheon

1	0.1			Various	5.03-5.06	.026-.029
2	0.1			Various	5.06-5.17	.034-.030
3	0.335	2.14	2.21	Face 1	5.21	.059
				Face 1, 90°	5.20	.0612
				Face 2	5.30	.0509
				Face 2, 90°	5.26	.0505
				Face 1	4.71	.0470
4	0.453	2.04	2.81	Face 1, 90°	4.60	.0455
				Face 2	4.70	.0487
				Face 2, 90°	4.55	.0487

Miscellaneous Inorganics

Salt

Raytheon

<u>Sample</u>	<u>Condition</u>		10^8	3×10^8	10^9
Granulated purified salt	As received $d = 1.39$	κ	3.28	3.27	3.25
		$\tan \delta$	0.0019	0.0018	0.0040
		% H_2O	0.05	0.06	.08
	Dry $d = 1.39$	κ	3.25	3.25	3.23
		$\tan \delta$	0.0009	.0006	0.0012
Fine flake salt	As received $d = 0.960$	κ	2.72	2.67	2.63
		$\tan \delta$	0.026	0.037	0.025
		% H_2O	0.28	0.36	0.40
	Dry $d = 0.956$	κ	2.64	2.63	2.62
		$\tan \delta$	0.0017	0.0014	0.0031

John Manville Service Boards at 25°C The Sippican Corporation

MHz	Style 61 - 1/4"		Style 71 - 1/8"	
	κ	$\tan \delta$	κ	$\tan \delta$
0.05	12.78	0.429	5.18	0.342
1	6.43	0.347	3.46	0.150
60	3.87	0.091	3.07	0.017
300*	4.20	0.188	3.54	0.043
1000*	3.98	0.137	3.50	0.024
0.05*	149.	0.733	61.8	0.625
1*	46.3	0.740	15.8	1.09

* Electric field in plane of sheet, others E sheet.

III. ORGANIC COMPOUNDS

(Listed according to manufacturer or source)

Artificial concrete



American Concrete Products

Material measured to be isotropic in κ within 0.5%

Freq. (MHz)	150	300	1000	3000
κ	6.06	6.04	6.02	6.0
$\tan \delta$	0.0107	0.0134	0.0125	0.0123

Cyanoethylated cotton moulding


American Cyanamid



Cymac 325,

American Cyanamid

including effect of van De Graaff irradiation



Conformal coating 1517-36-3
25°C, 50% relative humidity

Amicon Corporation

Freq. (Hz)	K	tan δ
10^2	4.31	0.0206
10^3	4.21	0.0204
10^6	3.76	0.0298

Volume resistivity 3.7×10^{13} ohm-cm

Surface resistivity $>6 \times 10^{14}$ ohms per square


Polyethylene, irradiated
At 25°C

Source: Amphenol Corp.

Freq. (Hz)	κ'	$\tan \delta$
10^3	$2.28 \pm .02$	$.59 \pm .05$
10^6		$.82 \pm .05$
10^8		$2.3 \pm .3$
4×10^8	$2.27 \pm .02$	$2.9 \pm .5$
10^9		$2.8 \pm .3$
3×10^9		$2.6 \pm .3$
8.5×10^9	$2.260 \pm .01$	$2.5 \pm .2$

Polyvinylidene fluoride

AVCO Research



Polypropylene

Avisun Corporation
Post Road
Markus Hook, Pa. 19061

Freq., Hz	T°C	Natural		Plateable 12-270A	
		κ	$10^4 \tan \delta$	κ	$10^4 \tan \delta$
10^2	25	2.26	1.50	2.41	15.2
2×10^2			1.30		
4×10^2			1.18		
10^3			1.36	2.41	11.8
3×10^3			1.50		
10^2			1.65	2.39	10.5
2×10^4			1.68		
5×10^4			1.66		
10^5		2.25	1.51	2.38	8.70
10^6		2.25	0.96	2.37	7.25
10^7		2.25	1.26	2.36	6.55
10^8		2.25	2.04	2.36	8.2
3×10^8		2.25	2.8	2.35	12.4
10^9		2.25	4.7	2.35	17.5
3×10^9		2.25	4.0	2.35	15.7
5×10^9	25	2.245	3.7	2.344	12.1
	-55	2.265	3.0	2.352	6.0
	-75	2.271	2.7		
	-195	2.308	0.7 ± 0.3	2.375	2.8
8.5×10^9	25	2.245	3.6	2.343	12.3

Polypropylene (cont.)
Natural, at 8.52 GHz

Avisun Corporation

Sample	Density (g/cm ³)	T°C	κ	tan δ
1 stacked sheet pcs		25	2.246	.00033
2 stacked injection molded pcs		25	2.236	.00035
3 rod	.9073	25	2.245	.00037

Polypropylene, plateable
12-270A, at 8.52 GHz

Avisun Corporation

Sample	Density	T°C	κ	tan δ
4 stacked injection molded pcs	.9500	25	2.442	.00145
5 rod	.9303	25	2.343	.00123

Polytetrafluoroethylene, fiberglass laminate

The Budd Company
Polychemicals Division

		All values of tan δ multiplied by 10 ⁴										
T°C	Freq. (Hz)	10	10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷	5.5x10 ⁷	9x10 ⁷	3.14x10 ⁹ *	
25	κ	2.739	2.740	2.738	2.737	2.735	2.734	2.733	2.732	2.731	2.712	
	1 tan δ	8.6	7.0	6.7	6.1	6.3	6.95	7.7	10.0	11.7	22.5	
100	κ		2.710	2.705	2.704	2.698	2.696	2.683			2.680	
	1 tan δ		11.1	8.10	8.25	7.17	7.07	7.7			31	
250	κ		2.554	2.534	2.522	2.503	2.502	2.49				
	1 tan δ		79.0	36.3	20.35	14.9	11.6	10.6				
-78	κ		2.796	2.793	2.790	2.784	2.78	2.78			2.752	
	1 tan δ		4.2	5.9	6.8	7.1	7.7	9.8			17	
-195	κ	2.801	2.799	2.794	2.792	2.787					2.758	
	1 tan δ	.0005	2.2	4.5	5.1	5.4					12	
-269	κ	2.789	2.789	2.784	2.783	2.780						
	1 tan δ	.0003	1.2	2.0	2.2	2.1						

* Copper cavity

E || sheet

T°C	Freq. (Hz)	3x10 ⁸	10 ⁹	3x10 ⁹	8.5x10 ⁹	1.4x10 ¹⁰	2.4x10 ¹⁰
25	κ	3.155	3.153	3.152	3.146	3.133	3.127
	tan δ	28	30	33	40	48	52
100	κ				3.11		
	tan δ				39		
250	κ				3.03		
	tan δ				36		
-54	κ				3.17	3.13	
	tan δ				35	39	
-195	κ				3.22	3.12	
	tan δ				28	31	

Copper-clad laminate PE1153

The Budd Co., Polychem Division

E $\perp$			10^2	10^3	10^4	10^5	10^6	10^7
3-terminal, liquid im- mersion, unclad *	25	κ			2.420			
		$\tan \delta$						
Declad †	25	κ			2.451			
		$\tan \delta$						
3-terminal, clad	26	κ	2.650	2.465	2.438	2.432		
		$\tan \delta$	.0945	.0279	.00484	.00093		
	-195	κ	2.416	2.415	2.414	2.411		
		$\tan \delta$	.00030	.00033	.00036	.00022		
	-54	κ	2.433	2.421	2.417	2.413		
		$\tan \delta$	.00042	.00050	.00052	.00031		
2-terminal, clad, meas. 12-21-70	25	κ	2.495	2.475	2.471	2.469	2.468	2.468
		$\tan \delta$	.01816	.00307	.00083	.00050	.00055	.00035
3-terminal, clad, 2nd sample	25	κ	2.843	2.504	2.457	2.449		
		$\tan \delta$	.141	.0491	.00811	.00126		
	96	κ	2.486	2.398	2.389	2.384		
		$\tan \delta$	.0708	.01343	.00230	.00050		
	250	κ	2.257	2.240	2.232	2.222		
		$\tan \delta$	.0263	.00568	.00238	.00111		
	25	κ	2.759	2.510	2.459	2.451		
		$\tan \delta$	.0970	.0390	.00748	.00115		
	-54	κ	2.484	2.484	2.484	2.479	2.464	2.456
		$\tan \delta$	.00034	.00044	.00065	.00062	.00059	.00110
	-195	κ	2.490	2.487	2.485	2.484	2.482	2.470
		$\tan \delta$	.00029	.00038	.00053	.00028	.00049	.00091
2-terminal, clad	25	κ				2.462	-	2.458
		$\tan \delta$				.00050	-	.00033
	96	κ	2.474	2.464	2.461	2.460	2.458	2.455
		$\tan \delta$	.01193	.00226	.00084	.00059	.00058	.00068
	250	κ	2.333	2.319	2.312	2.309	2.298	2.295
		$\tan \delta$	.01013	.00340	.00177	.00147	.00097	.00070
	25	κ	2.422	2.415				
		$\tan \delta$	.00995	.00189				
E $\parallel$								
2-terminal, unclad	25	κ	2.434	2.533	2.431	2.428	2.416	2.413
		$\tan \delta$	.0037	.00094	.00061	.00035	.00052	.0005

* Refers to sheet stock received without copper.

† Refers to a sample made by mechanically stripping the copper-clad sheet.

Resonant-Cavity Measurements:

~ 8.5 GHz, sample constrained in parallel direction, allowed to expand with temperature against a force 30 lb/sq in the perpendicular direction. Unclad stock.

T °C	E $\perp$		E $\parallel$		Thickness cm
	κ	$\tan \delta$	κ	$\tan \delta$	
-194	2.466	.00063	2.420	.00095	1.911
-54	2.437	.00070	2.397	.00104	1.917
23	2.421	.00091	2.383	.00130	1.924
96	2.396	.00117	2.367	.00147	1.948
250	2.296	.0022	2.246	.00185	2.093

Standing-wave method, 25°C

E $\parallel$, one piece unclad	2.387	.00128
----------------------------------	-------	--------

EKONOL (polyester resin)

The Carborundum Company

Sample 1

Frequency, Hz	T°C	κ	$\tan \delta$
10^2	25	3.216	.00289
10^3		3.210	.00316
10^4		3.185	.00336
10^5		3.168	.00348
10^6		3.156	.00325
10^7		3.148	.00220
10^8		3.140	.00215
8.5×10^9		3.120	.00281
	99	3.11	.0030
	155	3.08	.0040
	207	3.07	.0061
	284	3.04	.0104
	350	3.03	.0230
	420	3.03	.0230
	217	2.99	.0067
	25	2.96	.0025

Sample 2

T°C	Freq., Hz	10^2	10^3	10^4	10^5	10^6	10^7
25	κ	2.958	2.954	2.942	2.939	2.923	2.891
	$\tan$	0.00136	0.00201	0.00251	0.00325	0.00337	0.0021
100		2.982	2.962	2.955	2.945	2.926	2.898
	$\tan$	0.00367	0.00263	0.00262	0.00303	0.00391	0.0040
180	κ	3.252	3.182	3.130	3.077	3.031	2.993
	$\tan$	0.0444	0.0160	0.0120	0.0108	0.0099	0.0096
250	κ	4.606	3.415	3.244	3.177	3.096	3.050
	$\tan$	0.767	0.188	0.0368	0.0151	0.0131	0.0138
325	κ	23.57	5.646	3.574	3.267	3.190	3.140
	$\tan$	1.52	1.194	0.316	0.0567	0.0161	0.0127

Polytetrafluoroethylene film

Zitex



Density 0.463 g/cm³

25°C, 8.52 GHz: $\kappa = 1.194$, $\tan \delta = .00010$

Chemplast Inc.

150 Dey Road

Wayne, N.J. 07470



Custom Materials

Custom load 4101

Freq. (GHz)	T°C	κ	$\tan \delta_e$	μ'/μ_0	$\tan \delta_m$
3	25	13.8	.050	2.69	.451
8.5	25	13.3	.031	1.65	.747
8.5	-67	13.7	.006	1.57	.748
8.5	85	14.5	.051	1.68	.735

Custom 707-4

25°C, 8.52 GHz: $\kappa = 4.04$, $\tan \delta = .00090$

Custom 707-(3.75)

25°C, 8.52 GHz: $\kappa = 3.753$, $\tan \delta = .00076$

Custom Materials Inc.

FLUORGLAS E 650/2-1200

TFE-fiberglas laminate

Dodge Industries, Inc.

Freq., GHz	T°C	κ	E $\perp$		E $\parallel$	
			$\tan \delta$	κ	$\tan \delta$	κ
8.5	23	2.505	.0014	2.847	.0036	2.847
4	-195	2.533	.00082	2.896	.00172	2.896

Moulding compound 306

T°C	1 GHz		3 GHz	
	κ'	$\tan \delta$	κ'	$\tan \delta$
25	3.92	.00538	3.87	.00622
76	3.91	.0052	3.86	.0058
103	3.90	.0052	3.85	.0058
129	3.89	.0051	3.84	.0056
150	3.87	.0050	3.83	.0055
216	3.83	.0050	3.78	.0051
255	3.80	.0052	3.75	.0051
305	3.77	.0056	3.72	.0054
410	3.68	.0064	3.63	.0068
504	3.62	.0058	3.58	.0066
301	3.75	.0048		

Dow Corning

T°C	8.52 GHz	
	κ'	$\tan \delta$
-55	3.85	.0060
25	3.84	.0067
61	3.835	.00655
118	3.825	.0064
147	3.82	.00635
199	3.807	.00625
315	3.74	.00615
400	3.66	.0061
499	3.57	.0060
296	3.72	.0061

Silastic RTV 501

T°C	1000 MHz	3000 MHz	8500 MHz
-55	κ' 3.17	3.07	
	$\tan \delta$ 0.025	0.037	
23	κ' 2.89	2.88	2.87
	$\tan \delta$ 0.0053	0.0104	0.0175
150	κ' 2.62	2.62	
	$\tan \delta$ 0.042	0.0045	
RTV 521	23	κ' 3.33	3.32
		$\tan \delta$ 0.0086	0.0153
RTV 1602	-55	κ' 3.09	3.03
		$\tan \delta$ 0.0220	0.0308
	23	κ' 2.93	2.92
		$\tan \delta$ 0.0073	0.0117
	150	κ' 2.77	2.75
		$\tan \delta$ 0.0044	0.0060
RTV 5350	-55	κ' 3.22	3.14
		$\tan \delta$ 0.0234	0.0287
	23	κ' 3.06	3.05
		$\tan \delta$ 0.0043	0.0088
	150	κ' 2.82	2.79
		$\tan \delta$ 0.0040	0.0043
S-6538	-55	κ' 3.01	2.96
		$\tan \delta$ 0.0242	0.0260
	23	κ' 2.99	2.98
		$\tan \delta$ 0.0069	0.0124
	150	κ' 2.78	2.77
		$\tan \delta$ 0.0039	0.0047
Sylgard 182	-55	κ' 2.90	2.86
		$\tan \delta$ 0.0200	0.024
	23	κ' 2.79	2.77
		$\tan \delta$ 0.0081	0.0120
	150	κ' 2.50	2.48
		$\tan \delta$ 0.0026	0.0040

Sylgard 182, at 1 MHz

T°C	κ	$\tan \delta$
25	2.86	.00132
70	2.72	.00080
25 again	-	.00109
25 (after 24 hrs. in H ₂ O) wt. gain 0.019%	2.86	.00142

Dow Corning

Sylgard 184, at 25°C



Freq. (Hz)	50	10 ³	10 ⁵	10 ⁶
κ	2.86	2.86	2.84	2.84
10 ⁴ $\tan \delta$	2	10.2	18.4	14.0


Sylgard 184 (2nd sample at 1 MHz)

T°C	κ'	$\tan \delta$
25	2.88	.00123
70	2.70	.00071
25	-	.00040
25 (after 24 hrs. in H ₂ O) wt. gain 0.0252%	2.89	.00129

DC-92,007


8.52 GHz, 25°C, 50% R.H., $\kappa' = 4.92$; $\tan \delta = 0.091$





"H"-film (cont.)

E. I. Dupont de Nemours and Co.



"Kapton"

E. I. Dupont de Nemours and Co.

Type 500 H film, at 25°C, 45% relative humidity

Electric field in plane of sheet, $\kappa \pm 0.05$, $\tan \delta \pm 0.0005$

After 48 hrs. at 100°C

Freq. (GHz)	κ	$\tan \delta$	κ	$\tan \delta$
0.3	3.43	.0074	-	-
1	3.40	.0076	3.30	.0041
3	3.37	.0080	3.28	.0044
8.5	3.33	.0087	3.26	.0047
24	3.25	.0098	-	-

After 12 to 18 hrs. vacuum bake at 425°C, 2 microns, 8.52 GHz:


$\kappa = 3.03 \pm 0.1$, $\tan \delta = .0015 \pm .0003$

Nonex honeycombs
At 8.52 GHz

E. I. du Pont de Nemours and Company

Sample No.	Density	<u>a direction</u>		<u>b direction</u>		<u>c direction</u>	
		E $\perp$ double-layer seam		E $\parallel$ double-layer seam		E $\parallel$ holes	
		κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$
1	1.398	1.0348	.00089	1.0441	.00141	1.0855	.00212
2	2.892	1.0519	.00165	1.0669	.00229	1.0951	.00350
3	3.938	1.0788	.00176	1.1258	.00326	1.1444	.0041
4	4.039	1.0808	.00187	1.1020	.00278	1.1265	.0049
5	4.124	1.0827	.00274	1.1045	.00359	1.1351	.0046
6	4.259	1.0863	.00197	1.1340	.00382	1.1270	.0045
7	4.701	1.0928	.00315	1.1115	.00297	1.1455	.0047
8	5.603	1.0990	.00205	1.1781	.00468	1.1869	.0065
8*	5.603	1.1010	.00330	1.1667	.00628		

* At 100°C, all other values at 25°C





Teflon FEP (1963)


E. I. DuPont de Nemours and Co.

Density = 2.153 g/cm³, at 25°C, 8.52 GHz
 $\kappa' = 2.058$, $\tan \delta = 0.00108$

Teflon FEP (1964)




TFE-7 (1964)




TFE-6C (1964)

Teflon T-100, *) Lot 38180
Density at 25°C = 2.152 g/cm³

E. I. Dupont de Nemours and Co.



Teflon 100X (FEP) 1960 and TFE
Effect of Van De Graaff irradiation, 25°C



*) Electric data also apply to:

Teflon 9033, Lot 10601, density at 25°C = 2.147 g/cm³


"Polyguide"

Electronized Chemicals Corp.

		3 GHz		8.52 GHz		% wt. increase
		κ'	$\tan \delta$	κ'	$\tan \delta$	
As received	25°C	2.32	.00034	2.319	.00030	
	-48°C			2.320	.00017	
	74°C			2.300	.00040	
After 24 hrs. H ₂ O		2.32	.00047	2.320	.00038	.007

Emerson and Cumming A-19

graphite fiber loaded plastic, November 1966



"Eccogel" 1265

Emerson & Cuming

T°C	Freq. (Hz)		10 ³		10 ⁶	
	K	tan δ	K	tan δ	K	tan δ
25	7.60	.025	7.20	.0595	4.05	.1115
70					6.02	.0545
25 again					-	.0897
25 (after 24 hrs. in H ₂ O) wt. gain 1.08%					5.38	.128

"Eccof foam FH"

Emerson & Cuming

3.938 lb/cu.ft.

8.52 GHz		24 GHz	
K	tan δ	K	tan δ
1.0856	.00161	1.0798	.00165

RTV-11

General Electric
Silicone Products Dept.



At 1 MHz

T°C	K	tan δ
25	3.25	.00285
70	3.05	.00372
25	-	.00242
25 (after 24 hrs in H ₂ O) wt. gain .035%	3.31	.00543

SE900 Silicone Rubber

General Electric

Δ Sample cured 1 hr at 300°F, measured at 50% R. H.
 ○ Normal cure



Lexan	General Electric	
f(Hz)	κ'	tan δ
8.5×10^9	2.77	.00615
2.5×10^{10}	2.75	.00593

"3M" board

3-M

		3 GHz		8.52 GHz		% wt. increase
		κ'	$\tan \delta$	κ'	$\tan \delta$	
As received	25°C	2.32	.00038	2.316	.00037	
	-48°C			2.316	.00015	
	74°C			2.300	.00040	
After 24 hrs H ₂ O	25°C	2.32	.00060	2.316	.00043	

Scotchcast 221

3-M

At 1 MHz

T°C	κ	$\tan \delta$
25	3.06	.0273
70	3.73	.1373
25	-	.0245
25 (after 24 hrs. in H ₂ O) wt. gain .274%	3.12	.0352

Polyimide foams

Monsanto

At 8.52 GHz

	Density (lbs/cu.ft.)	T°C	κ	$\tan \delta$
HD-139	8.4	25	1.1439	.00277
		150	1.128	.00040
		304	1.118	.00045
		25	1.126	.0014
HD-140	16.7	25	1.301	.00507
		154	1.264	.00094
		307	1.260	.00121
		25	1.260	.00037
HD-144	21.8	25	1.412	.00635
		148	1.355	.00135
		303	1.382	.00190
		28	1.351	.0068

Polyurethane rigid foam, at 399 MHz

Nopco Chemical Corp.


3.80 lbs/cu. ft

7.54 lbs/cu. ft

T [°] F	K'	tan δ	K'	tan δ
77	1.087	.00136	1.165	.00242
116	1.088	.00176	1.170	.00276
164	1.093	.00208	1.175	.00344

Fluorosint (1960)

Polymer Corp.



Radar tape

At 14.2 GHz

Quantum Inc.
Lufbery Ave.
Wallingford, Conn.

T ^o C	K	tan δ
25	3.56	.0132
150	3.37	.0055
320	3.32	.0074
477	3.36	.0130

Plastics

Raytheon Company

Resin - "Bakelite" epoxy (Union Carbide)
 - CY-178 epoxy (Ciba Products)
 Hardener - hexahydrothalic Anhydride, HHPA (Allied Chem.)


	10 ⁵ Hz		73 ^o F	
	K	tan δ	K	tan δ
<u>Resin 100 parts</u>				
ERL-4221 ^a	3.42	.0145	3.33	.0165
ERL-4221/ERRA-4090 ^b	4.13	.0193	4.05	.0233
ERL-4289 ^c	3.40	.0123	3.34	.0160
ERL-4259 ^d	3.93	.0172	3.82	.0151
ERL-4259 ^e	3.44	.0159	3.33	.0234
ERL-4221/ERRA-4090 ^f	3.84	.0175	3.74	.0153
CY-178 ^g	3.38	.0177	3.31	.0179
ERL-4221/ERRA-4090 ^h	4.52	.0302	4.42	.0270

- a. 90 parts HHPA, 0-silica.
- b. 65 parts HHPA, 0-silica.
- c. 65-HHPA, 0-silica.
- d. 65-HHPA, 115-silica.
- e. 90 parts hardener liquid anhydride (Ciba), 0-silica.
- f. 65-HHPA, 85-silica.
- g. 65-HHPA, 0-silica.
- h. 65-HHPA, 118-silica.

Rexolite 1422 (1964),


Wm. Brand Rex Division
of American Enka Corp.

including effect of Van De Graaff irradiation (1960)



Rexolite 2200 (1964),

including effect of Van De Graaff irradiation (1960)




Rexolite 2200 (1965)

		3 GHz		8.52 GHz		% wt. increase
		κ'	$\tan \delta$	κ'	$\tan \delta$	
As received	25°C	2.65	.00169	2.65	.00170	
	-48°C			2.64	.00110	
	74°C			2.645	.00209	
After 24 hrs. H ₂ O	25°C	2.66	.0026	2.66	.00343	.055

Rexolene P


Wm. Brand Rex Division
of American Enka Corp.



Duroid (1" thick sheet)

Rogers Corporation



T °C	3.7 GHz		4.3 GHz		Cavity length (inches)
	E //	$\tan \delta$	E $\perp$	$\tan \delta$	
25	2.476	.00156	2.317	.00125	2.015
81.5	2.458	.00176	2.301	.00153	2.042
106.8	2.447	.00178	2.289	.00140	2.055
125	2.438	.00176	2.282	.00142	2.067
152	2.425	.00166	2.268	.00149	2.083
176	2.412	.00160	2.255	.00155	2.106
202	2.399	.00159	2.239	.00167	2.127
250	2.370	.00165	2.203	.00202	2.159
310	2.301	.00182	2.130	.0024	2.320
362	2.031	.00225	1.878	.0015	2.869



Epon 828/PMDA casting

Shell Chemical Company

156 pts. { Epon 828 epoxy 100 pts. by weight
PMDA (pyromellitic dianhydride) 56 pts. by weight
plus
20 pts. { Tetrahydrofurfural alcohol 99 pts. by weight
Dicyandiarnide 1 pt. by weight




Epon 828/PMDA casting

Shell Chemical Company

Epon 828 epoxy 100 pts. by weight

PMDA (pyromellitic dianhydride) 31 pts. by weight



Polystyrene foam
Polyurethane foam

The Sippican Corporation

Sample	Hz	5×10^4	10^6	6×10^7	3×10^8	1×10^9
I, white polystyrene κ		1.060	1.060	1.060	1.058	1.057
3 lbs/cu.ft. D.F.		.000083	<.00002	<.0002	.00004	<.00005
II, blue polystyrene κ		1.0368	1.0367	1.037	1.037	1.037
2 lbs/cu.ft. D.F.		.000061	<.00002	<.0002	.0001	<.00005
III, polyurethane κ		1.0846	1.082	1.080	1.078	1.077
4 lbs/cu ft. D.F.		.00143	.00151	.0018	.00164	.00208
IV, polyurethane κ		1.155	1.148	1.145	1.144	1.143
6 lbs/cu.ft. D.F.		.00207	.00289	.0033	.00295	.00347


Tellite 3A

Tellite Corp.

	T ^o C	κ'	$\tan \delta$	κ'	$\tan \delta$	% weight increase
As received	25	2.31	.00028	2.311	.00022	
	-48			2.318	.00020	
	74			2.294	.00027	
After 24 hrs H ₂ O	25	2.31	.00036	2.311	.0003~	.003

Polysulfone, 25°C, 50% R. H.

Union Carbide Corp.
Plastics Division




Fiberglass laminate

Air Force Materials Laboratory



with polybenzimidazole resin (approx. 24%)

density 1.949 g/cm³




Fiberglass laminates

Air Force Materials Laboratory



Fiberglass laminate with 181 glass cloth and a polyol cross-linked polyimide resin, 8.52 GHz

Fiberglass laminate with 181 glass cloth and a polyimide resin, 8.52 GHz



Fiberglass laminate with 181 glass cloth and epoxy resin, 8.52 GHz

IV. MISCELLANEOUS ORGANICS

Coal, powdered

Peabody Coal Division
Kennecott Copper

Room humidity, 8.5 GHz

Sample No.	κ'	κ''	$\tan \delta$	σ (ohm-cm) ⁻¹	ρ (g/cm ³)
1-421	4.65	.892	.191	4.22x10 ⁻³	.780
1-422	5.85	1.21	.206	5.73	.842
1-424	5.76	1.15	.199	5.42	.813
0-1071	4.84	1.02	.209	4.81	.759
1-429	4.33	.800	.184	3.68	.768
1-436	5.23	1.11	.211	5.24	.756
1-423	5.17	1.13	.217	5.35	.740
1-427	5.07	1.09	.215	5.17	.759
1-425	4.66	.885	.189	4.18	.792
0-1075	4.16	.788	.189	3.73	.775

Sample No.	Freq., Hz	10 ²	10 ³	10 ⁴	10 ⁵	10 ⁶	10 ⁷
1-421	κ'	1626.	123.	40.8	21.1	15.5	9.11
$\rho=.850$	κ''	10886.	1122.	153.	24.2	9.56	3.02
	$\tan \delta$	6.69	9.10	3.75	1.14	.613	.331
	σ	6.0E-7	6.2E-7	8.5E-7	1.3E-6	5.3E-6	1.6E-5
1-422	κ'		720.	100.	39.4	18.7	11.1
	κ''		7368.	930.	92.8	18.8	5.12
$\rho=.850$	$\tan \delta$		10.2	9.28	2.36	1.01	.462
	σ		4.1E-6	5.1E-6	5.1E-6	1.0E-5	2.7E-5

Coal, single lump

Massachusetts Institute of Technology
National Magnet Laboratory

Frequency, Hz	10^6	8.5×10^9
κ'	-	8.4
κ''	-	2.47
$\tan \delta$	-	.294
σ	1×10^{-4}	.117

Balsa wood

The Sippican Corporation

Frequency, MHz	κ	$\tan \delta$
0.05	2.190	.123
1	1.928	.0614
60	1.727	.0620
300*	1.417	.046
1000*	1.404	.047

*) Electric field grain, others E along grain

Particle boards

The Sippican Corporation

<u>Sample</u>	Freq., Hz	E $\perp$ sheet		E $\parallel$ sheet	
		5×10^4	10^6	3×10^8	10^9
1. U.S. Plywood fiber face	κ tan δ	3.16 .0345	2.94 .0410	2.91 .109	2.69 .105
2. U.S. Plywood fiber face, all phenolic	κ tan δ	3.48 .0745	3.02 .0582	2.85 .102	2.66 .096
3. U.S. Plywood Novoply	κ tan δ	3.12 .0261	2.98 .0320	2.87 .099	2.67 .100
4. Evans Products, MDF	κ tan δ	3.32 .0230	3.20 .0368	3.08 .106	2.85 .101
5. Evans Products, underlayment grade	κ tan δ	3.26 .0229	3.13 .0360	3.00 .110	2.76 .104

Wood products

The Sippican Corporation

25°C, E in plane of sheet							
<u>Material</u>	Freq., Hz	5×10^4	5×10^5	3×10^6	1.8×10^7	$3 \times 10^{7*})$	3×10^8
Pine board	κ tan δ	2.90 .0228	2.81 .037	2.68 .055	2.38 .081	2.31 .087	2.06 .090
Fir plywood	κ tan	3.18 .060	2.97 .068	2.78 .064	2.54 .064	2.47 .065	2.25 .074
Birch plywood	κ tan	2.87 .033	2.74 .041	2.62 .0505	2.38 .062	2.32 .063	2.16 .067
Marinite	κ tan	2.88 .49	2.33 .148	2.07 .054	2.00 .0219	1.98 .020	1.910 .0200

*) Values at 30 MHz are interpolated, not measured.

V. LIQUIDS


Fluorocarbon derivative P-1C
At 25°C

Allied Chemical Corporation

Freq. (GHz)	κ	$\tan \delta$
1	1.92	.0050
3	1.92	.0140
8.52	1.89	.029
14	1.87	.038

Dowtherm A


Dow Chemical





Fluorinated ethers, at 27°C
TOC = <6 to 28

E. I. Dupont de Nemours & Co.

Freq. (Hz)	FPS-1418		FPS-1419		FPS-1420	
	b.p. 148°C κ	$\tan \delta$	b.p. 101°C κ	$\tan \delta$	b.p. 153°C κ	$\tan \delta$
10^2	1.890	3×10^{-6}	1.859	1.6×10^{-5}	2.570	3.23×10^{-3}
10^5	1.890	3×10^{-6}	1.859	2×10^{-6}	2.570	1.6×10^{-5}
10^8	1.888	.00243	1.857	4.2×10^{-4}	2.53	.0126
10^9	1.851	.0142	1.833	.0042	2.420	.0952
3×10^9	1.838	.0124	1.832	.0075	2.213	.0995
8.5×10^9	1.797	.0068	1.798	.0084	2.026	.0907



Teresso V-78 (cont.)



Hercules, Inc.

DI-CUP
dicumyl peroxide

25°C

κ	$\tan \delta$
2.79	.0073
↓	.00081
	.000115
	.000064
	.00040
	.0032
2.97	.0025
2.73	.0050
2.70	.0082
2.57	.0078
2.515	.0044
2.495	

VUL-CUP
a,a¹-bis(t-butyl peroxy) diisopropylbenzene

25°C

Freq., Hz	κ	$\tan \delta$
10 ²	2.633	.0011
10 ³	↓	.00011
10 ⁴		.000013
10 ⁵		10 ⁻⁵
10 ⁶		.00005 ± 2
1.8x10 ⁷		
6x10 ⁹	2.63	.005 ± 2
10 ⁸	2.60	.0206
10 ⁹	2.56	.0378
3x10 ⁹	2.40	.056
8.5x10 ⁹		

99°C

10 ⁹	2.26	.0116
3x10 ⁹	2.24	.0184

Pennwalt Corp., Lucidol Div.

Lucidol
t-butyl perbenzoate

25°C

Freq., Hz	κ	$\tan \delta$
10 ²	-	-
10 ³	-	-
10 ⁴	12.17	.17
10 ⁵	12.17	.017
10 ⁶	12.1	.0027
10 ⁷	12.0	.0095
10 ⁸	11.2	.0044
10 ⁹	5.70	.252
3x10 ⁹	4.07	.337
8.5x10 ⁹	3.23	.460

Lupersol 130
2,5 dimethyl-2,5-di(t-butylperoxy)hexyne-3

25°C

Freq., Hz	κ	$\tan \delta$
10 ²	2.656	.00123
10 ³	↓	.000123
10 ⁴		.000012
10 ⁵		.000023
10 ⁶		.00012
10 ⁷	2.655	.00121
10 ⁸	2.65	.0066
10 ⁹	2.56	.0235
3x10 ⁹	2.50	.0344
8.5x10 ⁹	2.39	.0505

99°C

2.33	.0076
2.32	.0154

Mullet oil

Freq., GHz	24 ± 0.5°C	
	κ	tan δ
1	2.54	.068
8.5	2.52	.0507
14	2.42	.0468
24		.0384

U.S. Bureau of Fisheries

	10 ± 1°C	
	κ	tan δ
	-	-
	2.50	.0458
	2.39	.0443
	2.36	.0380

USP 333

U.S. Peroxygen Div., Argus Chemical Corp.

Freq., Hz	25°C	
	κ	tan δ
10 ²	3.818	.0170
10 ³	↓	.00170
10 ⁴		.00017
10 ⁵		.000027
10 ⁶		.00021
10 ⁷	3.81	.00157
10 ⁸	3.75	.0146
10 ⁹	3.60	.0842
3x10 ⁹	3.30	.130
8.5x10 ⁹	2.80	.1735

Lupersol 101

Wallace & Tiernan Inc.



2,5-dimethyl-2,5-di(t-butylperoxy)hexane

at 25°C		
Freq., Hz	κ	tan δ
10 ⁴	2.66	.000088
10 ⁵	2.66	.000144
10 ⁶	2.66	.000053
10 ⁷	2.65	.00049
10 ⁸	2.64	.0050
10 ⁹	2.62	.0217
3x10 ⁹	2.58	.0387
8.5x10 ⁹	2.41	.057
2.4x10 ¹⁰	2.26	.045
at 99°C		
10 ⁹	2.02	.0040
3x10 ⁹	2.02	.0068

VI. FOODSTUFFS

Kremax

Armour



Frozen lean steak

T°F	150 MHz		1000 MHz		3000 MHz	
	κ	$\tan \delta$	κ	$\tan \delta$	κ	$\tan \delta$
-75	3.42	.022	3.33	.0164	3.22	.0105
-60	3.61	.040	3.42	.026	3.40	.014
-50	3.70	.058	3.46	.036	3.44	.0185
-40	3.82	.072	3.51	.050	3.46	.024
-30	3.92	.094	3.60	.066	3.55	.032
-20	4.18	.102	3.80	.089	3.70	.040
-10	4.50	.138	4.10	.12	3.80	.054
0	5.33	.18	4.40	.165	3.95	.076
10	6.35	.24	5.18	.223	4.37	.108
20	9.55	.39	9.50	.203	7.30	.174
30	33	.60	20.8	.254	8.40	.250
40	53.5	.22	33.0	.32	8.30	.208
50	53.0	.21				

Vacuum-dry lean beef

-60			1.495	.00320	1.471	.00335
-40	1.535	.0060	1.497	.00375	1.473	.00395
-20	1.548	.0080	1.502	.00446	1.475	.0047
0	1.562	.0102	1.511	.00535	1.480	.0057
20	1.582	.0132	1.520	.0066	1.483	.0068
40	1.60	.0168	1.530	.0080	1.490	.0082
60	1.62	.0216	1.542	.0096	1.500	.0099
80	1.648	.0264	1.558	.0111	1.509	.0119
100			1.571	.0127	1.522	.0138
120			1.587	.0143	1.535	.0147
140			1.604	.0160	1.545	.0175
160			1.622	.0176	1.560	.0193
180			1.642	.0198	1.590	.0214

Potato (Maine, 78.9% H₂O), 25°C

f (GHz)	κ'	$\tan \delta$
.3	130	.83
1	87	.39
3	81	.38



Potato flakes, density 0.284

.3	1.50	.034
1	1.485	.030
3	1.47	.029


Potato chips

partly cooked	1	5.76	.36
	3	5.18	.55
cooked	1	1.89	.034
	3	1.86	.036

Potato starch,
granular and gelatinized, at 10 GHz, 25°C



Potato starch,
granular and gelatinized, at 3.0 GHz, 25°C



Nescafe				Nestea		
f (Hz)	κ'	$\tan \delta$	σ	κ'	$\tan \delta$	σ
10^2	1.557	.0115	9.93×10^{-13}	1.290	.00442	3.17×10^{-13}
10^3	1.529	.0113	9.58×10^{-12}	1.281	.00384	2.73×10^{-12}
10^4	1.490	.0103	8.52×10^{-11}	1.276	.00301	2.13×10^{-11}
10^5	1.488	.0090	7.43×10^{-10}	1.270	.00245	1.73×10^{-10}
10^6	1.471	.0089	7.27×10^{-9}	1.267	.00230	1.62×10^{-9}
10^7	1.453	.0093	7.52×10^{-8}	1.260	.00196	1.37×10^{-8}
3×10^8	1.432	.0106	2.53×10^{-7}	1.24	.0023	4.75×10^{-7}
10^9	1.39	.0098	7.57×10^{-6}	1.22	.0024	1.63×10^{-7}
3×10^9	1.36	.0093	2.11×10^{-5}	1.21	.0026	5.25×10^{-6}
8.5×10^9	1.34	.0086	5.65×10^{-5}	1.20	.0033	1.87×10^{-5}
density 0.241 g/cm ³				0.126 g/cm ³		

Eggwhite

Frequency	κ'	$\tan \delta$	ρ
3×10^9	35	.5	
9.2×10^9	13	1.1	
$10^4, 10^5$			35

Bread

1.2×10^7	11	3.35	
-------------------	----	------	--

Dough

10^7	2×10^5	2.25	1
--------	-----------------	------	---

MATERIALS AND COMPANY INDEX

- "Acrawax" C, IV-56
- Acrylate resins, IV-34,35;V-10
- Acrylonitrile-butadiene copolymer, IV-53
- Admiralty Materials Laboratory's silicon nitride, ceramic, P.R.-100
- AFC Alumina, V-21
- AF Materials Laboratory's Zircolite, P.R.-122
- Aircraft-Marine Products, Inc., IV-14; V-74
- Air Reduction Sales Co., V-20
- Air Seal, IV-52
- "Alathon," IV-27,70
- Alberox Corp., P.R.-5
- "Alberox" A-935, A-950, and A-962, P.R.-5
- Alcohols, IV-62
- "Alite" A-389-25 and A-389-P-30, VI-20
- AP-212 and AP-216,V-21
- AP-312, V-21,51
- APO-512-6 and APO-512-7, VI-21
- Alkyd resins, IV-47-49,123,124; V-112,113
- Allied Chemical Corp., P.R.-194
- Allied Chemical fluorocarbon derivative P-1C, P.R.-194
- Allison, William M., and Co., IV-58
- Allyl resins, IV-47,48
- Allymer CR-39, CR-39+glass, IV-48
- "Alox," National Beryllia, P.R.-31
- "AlSiMag" A-35, IV-3,80
- "AlSiMag" A-196, IV-3,78,79
- "AlSiMag" 211, IV-3
- "AlSiMag" 288, IV-3,81
- "AlSiMag" 243, IV-3,82; VI-34
- "AlSiMag" 393, IV-3
- "AlSiMag" 475, V-5,59-61
- "AlSiMag" 491, IV-6,100
- "AlSiMag" 491 (blue), V-1,32,33
- "AlSiMag" 505, IV-82
- "AlSiMag" 513 (pink), V-1,34,35
- "AlSiMag" 544, V-21,31
- "AlSiMag" 548, V-21,31
- "AlSiMag" 576, V-2,36,37; P.R.-6
- "AlSiMag" 577, V-4,58
- "AlSiMag" 602, V-21,75
- "AlSiMag" 614, VI-10; P.R.-6
- "AlSiMag" 652, V-21; VI-8,9
- "AlSiMag" 719; P.R.-6
- "AlSiMag" 754, P.R.-40
- "AlSiMag" 5050, V-234; VI-44
- Alumina (including porcelains), IV-6,96-100; V-1-4,21,23,30-52; VI-7-21; P.R.-5-37
- "AFC," V-21,30
- "Alite," see U.S. Stoneware, V-21,51; VI-20,21
- "Alberox" A-935, A-950, and A-962, P.R.-5
- American Lava
- "AlSiMag" 393, IV-3
- "AlSiMag" 491, IV-6,100; V-1,32,33
- "AlSiMag" 513, V-1,34,35
- "AlSiMag" 544, V-2,21,31
- "AlSiMag" 548, V-21,31
- "AlSiMag" 576, V-2,36,37
- "AlSiMag" 602, V-21
- "AlSiMag" 652, V-21,38,39; VI-8,9
- "AlSiMag" 719, P.R.-6
- Armour Research, Alcoa, P.R.-7,8
- E-11, P.R.-9,10
- E-20, P.R.-11
- A-75, P.R.-15-17
- A-76, P.R.-12-14
- mixtures, P.R.-18
- Centralab 205 and 206, P.R.-19
- Carborundum 1542, P.R.-19
- Coors
- AB-2, IV-6,98,99
- AD-99, VI-14,15; P.R.-19
- AD-995, P.R.-20
- AL-100, V-2,40
- AL-200, IV-6,96,97; V-2,40; VI-11-13
- EI-95, VI-16,17
- MC-2014, P.R.-20
- RR, P.R.-20
- Coors-NBS 10F2, P.R.-20
- Corning
- JD-40, V-2,41
- JD-82, V-2,41

Alumina (cont.)

Corning

JB-123, V-2
WD-131, V-2
JB-123, V-2, 41

Diamonite

B-890, V-2, 42
B-890-2, P.R.-21
P3142, V-2, 43
P3142-1, P.R.-21
P-3459, V-2, 44
P-3530-40, V-3, 45
P-3662, P.R.-21

Frenchtown

4462, IV-6; V-48
6096, V-3, 48
7225, P.R.-21
7873, V-3, 49

General Ceramic

ADH-211, V-3

General Electric

AT-100, P.R.-22
A-919, P.R.-25
A-923, P.R.-26
A-976, P.R.-27
A-1000, P.R.-28
A-1004, P.R.-29
"Lucalox," P.R.-23, 24

International Pipe & Ceramic

TC-301, P.R.-30
TC-302-H, P.R.-30
TC-351, P.R.-30
V-69, P.R.-30

Kearfott

high-purity, V-3, 46, 47; P.R.-30
hot-pressed in carbon,
VI-18, 19

Knox porcelain, IV-6, 100

Minneapolis Honeywell

A-127 and A-203, P.R.-31

National Beryllia "Alox"

P.R.-31

Norton 99.5%, P.R.-31

7X, V-3, 49
17Z, V-3

Raytheon 1959, P.R.-32

402B, V-3

"Sintox," V-3

Steatit-Magnesia A.G. A-18, P.R.-32, 33

Stupakoff 15

1510, V-3, 51
1540, V-3, 50
1542E, V-3,

Stupakoff

1542P, V-3, 50
1550, V-3, 50

U.S. Stoneware

A-212, P.R.-34
A-216, P.R.-34
AP-212, V-21
AP-216, V-21
A-312, P.R.-34
AP-312, P.R.-34
"Alite" A-389-25, VI-20
"Alite" A-389-P-30, VI-21
"Alite" APO-512-6, VI-21
"Alite" APO-512-7, VI-21
610, P.R.-34
Std. 3050°F, P.R.-35

Western Gold & Platinum

AL-300, V-4, 52; P.R.-36
AL-300, modified, P.R.-36
AL-400, P.R.-37
AL-500, P.R.-37
AL-995, P.R.-37
AL-1009, V-4; P.R.-37

Aluminum nitride, Carborundum, hot-pressed, P.R.-1

Aluminum oxide, Linde, single crystal, IV-1, 72; V-1, 26-28 P.R.-2, 3

Aluminum oxide, Union Carbide, single crystal, P.R.-4

Aluminum oxide, multicrystalline, see alumina

Aluminum oxide mixtures, VI-50, 51

Aluminum silicates, V-3, 6

"Alvar" 11/90, IV-34

Amber, IV-55

Amber Mines, Inc., IV-55

American Concrete Products, P.R.-159

American Cyanamid Co., Plastics Dev. Labs., IV-21-23, 38, 46, 112, 118-121; V-8, 106, 107; P.R.-159, 160

American Cyanamid Co., Plastics and Resins Div., VI-65

American Cyanamid, cyanoethylated cotton molding, P.R.-159

American Cyanamid "Cymac" 325, P.R.-160

American Cyanamid, see "Laminac," "Melmac," "Beetle"

American Cyanamid 405 resin, V-8

American Feldmuehle Corp., V-21, 30

American Lava, IV-3, 4, 6, 78-82, 88-93, 100; V-1, 4, 5, 21, 31-37, 58-61, 75, 234; VI-8-10, 34, 44; P.R.-6, 40

American Lava, see "AlSiMag"

American Optical Co., IV-9; P.R.-77,82
 American Optical Amersil, P.R.-82
 American Optical, phosphate glass,
 IV-9; P.R.-77
 American Phenolic Corp., see Amphenol
 American Smelting and
 Refining Co., IV-13
 Amersil, clear, translucent,
 P.R.-82
 Amicon Corp., P.R.-160
 Amicon Corp., conformal coating
 1517-36-3, P.R.-160
 Ammonium dihydrogen phosphate, IV-1
 Amphenol Corp., IV-28; P.R.-161
 Amphenol Corp., polyethylene,
 irradiated, P.R.-161
 "Amplifilm," IV-14; V-74
 Aniline-formaldehyde resins, IV-21
 Apatite, P.R.-126,127
 "Apiezon" Wax "W," IV-56
 "Araldite" Adhesive, Type I,
 (natural and silver, IV-50
 "Araldite" casting resin, Type B,
 IV-49,125
 "Araldite" casting resin G, IV-49
 "Araldite" E-134, IV-49
 Argus Chemical Corp., U.S. Per-
 oxygen Div., P.R.-197
 Armour Research, P.R.-7-18,198
 "Aroclor" 1221, 1232, 1242,
 1248, IV-63
 1254, IV-63; VI-78-83
 1260, 1262, 5442, IV-64
 1268, 4465, 5460, IV-15
 Armour Research, aluminum
 oxide, P.R.-7-18
 Asbestos, IV-13
 Asbestos filled plastics, IV-16;
 V-8,9,84,85,96,97
 Asphalt pavement and
 asphalts, P.R.-156
 Asphalts and cements, IV-56
 Astrophyllite, P.R.-127
 "Atlac" 382, V-11,12
 Atlas Powder Co., V-11,12
 Attenuator materials: IV-43-45;
 V-13,15,17,18,22,234-244;
 VI-44,45; P.R.-79,80,81,
 148,175
 AVCO Research, P.R.-161
 AVCO Research, polyvinylidene
 fluoride, P.R.-161
 Avisun Corp., P.R.-162, 163
 Avisun polypropylene,
 natural & plateable,
 P.R.-162,163
 Bakelite Corp., IV-15,16,20,
 27-29,36,48,57,58,64;
 V-12; P.R.-180
 "Bakelite" BM-120, IV-15,16,69
 "Bakelite" BM-250, BT-48-306,
 BM-16981, and BM-16981
 powder, IV-16
 "Bakelite" BM-262, BM-1895, IV-20-69
 "Bakelite" BRS-16631 + glass, IV-48
 BV-17085 + glass, IV-16
 PLLA-5005, V-12
 "Bakelite" polystyrenes, IV-36
 "Bakelite" polyvinyl chloride-
 acetate, see "Vinylites"
 Balata, precipitated, IV-51
 Balsa wood, Sippican Corp., P.R.-192
 Barium fluoride, single crystal,
 P.R.-38,39
 Barium-strontium titanate, IV-5,6
 Barium titanate, IV-5; V-1
 Barium titanate and plastic
 mixtures, IV-43
 Basalt, Hawaiian, high-density,
 P.R.-136
 low-density, P.R.-137
 deep ocean basalt, P.R.-137
 Basalt, synthetic, P.R.-139
 Battelle Memorial Institute, P.R.-45
 Battelle boron nitride, hot-
 pressed, P.R.-45
 "Bayol," "Bayol"-D, -F, -16, IV-65,66
 Beef steak, lean, frozen and
 vacuum dried, P.R.-199
 Beeswax, white, yellow, IV-57
 "Beetle" resin, IV-23
 Bell Telephone Laboratories, IV-3,83;
 V-56,57; VI-28,29; P.R.-72
 Bell Labs. F-66, IV-3,83; V-56,57;
 P.R.-72
 Benitoite, P.R.-127
 Bentonite, IV-14; V-74
 Benzenes and diphenyls,
 chlorinated, IV-63
 Benzenes, chloro-, IV-64
 Benzoguanamine-formaldehyde resin,
 IV-23
 "Berlox," BeO, P.R.-41
 Beryl, P.R.-128,129
 Beryllia, IV-6; V-21,24,52,53; VI-22-
 27; P.R.-39-43
 American Lava "AlSiMag" 754,
 P.R.-40
 Beryllium Corp. hot-pressed,
 V-21,53
 crucible grade, V-21,52

Beryllia (cont.)

Brush

B-6, P.R.-40
B-7-6, P.R.-40
B-7-37, P.R.-40
cold-pressed, VI-24,25
F-1, P.R.-41
hot-pressed, VI-22,23
sintered, VI-26,27

Coors BD-98, P.R.-41

National Beryllia "Berlox,"
P.R.-41

cold-pressed, P.R.-41

North American translucent,
P.R.-42,43

Norton, IV-6

Beryllium Corp., The, V-21,52,53

Beryllium oxide, multicrystalline,
see Beryllia

Beryllium oxide, single crystal,
Electronic Space Products,
P.R.-39

Beryllium orthosilicate, single
crystal KSC 7013, Elec.
Space Products, P.R.-44

Biphenyl, diisopropyl and monoiso-
propyl, V-19

Biphenyls, chlorinated, IV-15,63,64

Birch plywood, P.R.-193

Bismuth silicate ceramic, P.R.-44

Bitumen, natural, IV-56

"Boltaron" 6200-10, V-10

"Boralloy," P.R.-50,51

Boron nitride, V-6,76,77; VI-48,49;
P.R.-45-57

Boron nitride, density effect,
P.R.-45

Boron nitride, Battelle, hot-
pressed, P.R.-45

Carborundum, hot-pressed, 1956,
V-6,76,

Carborundum, hot-pressed,

Grade A, P.R.-47

Grade HP (1962), P.R.-46,48

Grade M, P.R.-49

High-Temperature Materials,
pyrolytic, P.R.-50,51

National Carbon, see Union Carbide
and Carbon

Raytheon, pyrolytic, P.R.-52,53

Union Carbide & Carbon,
pyrolytic (see High Temperature
Materials)

pyrolytic laminate, P.R.-54

cold-pressed, P.R.-57

Boron nitride (cont.)

Union Carbide & Carbon (cont.)

hot-pressed HBR, P.R.-56

HBN, P.R.-57

HD-0025, VI-48,49

HD-0056, P.R.-54

HD-0086, P.R.-54

HD-0092, P.R.-55

HD-0093, P.R.-55

HD-0094, P.R.-55

Boron nitride alloys, V-6,79;VI-50,51

Brand-Rex Co., IV-40;VI-11,105;P.R.-181-183

Bread and bread dough, P.R.-202

Bromund, E. A., and Co., IV-57

Brown Univ. silicon, single cryst., P.R.-78

Brunswick Corp., Defense Products

Division, P.R.-95

Brunswick slip-cast, SiO₂, P.R.-95

Brush BeO

B-6, P.R.-40

B-7-6, P.R.-40

B-7-37, P.R.-40

cold-pressed, VI-24,25

F-1, P.R.-41

hot-pressed, VI-22,23

sintered, VI-26,27

Brush Electronics Co., IV-1, 73;
VI-22,27; P.R.-40,41

Budd Company, The, P.R.-164,165

Budd copper-clad laminate, PE1153,
P.R.-164,165

Budd DiClad-522, polytetrafluoro-
ethylene, fiberglass laminate,
P.R.-164

Buna S (GR-S) and compounds, IV-52

Bureau of Standards casting resin,
IV-40

Butadiene-acrylonitrile copolymer,
IV-53

Butadiene, chloro-, IV-53,62

Butadiene-styrene copolymer, IV-38,52

"Butvar," low OH and 55/98, IV-34

n-Butyl alcohol, IV-62

Butyl rubbers, IV-52

Butyraldehyde, IV-62

Cable oil 5314 and PL101270, IV-65

Calcite, P.R.-58

Calcium carbonate, single crystal
mineral, P.R.-58

Calcium fluoride, single crystal,
V-1; P.R.-59-61

MIT, LIR, V-1

MIT, Crystal Physics Lab., P.R.-59

MIT, Ceramics Lab., P.R.-60

mixture with "Teflon," V-10

Calcium titanate, IV-5
 California Research Corp., IV-65
 Candy and Co., Inc., IV-57
 Cantol Wax Co., IV-59
 "Carberlox," National Beryllia,
 P.R.-80
 Carbon, diamond, V-1
 Carbon and plastic mixtures,
 IV-32,41; V-239,240
 Carbon tetrachloride, IV-62
 Carbonyl iron and plastic
 mixtures, V-15
 Carborundum Co., The,
 V-6,76-79; VI-46,47;
 P.R.-1,19,46-49,
 79,166
 Carborundum boron nitride,
 Grade A, Grade HP, and
 Grade M, P.R.-46-49
 hot-pressed, V-6,76,77
 silicon nitride alloy, V-6,79
 Carborundum EKONOL (polyester
 resin), P.R.-166
 Carborundum silicon carbide,
 P.R.-79
 Carborundum 1542, P.R.-19
 Catalin Corp. of America, IV-16-
 18, 36, 39,119
 "Catalin" 200, 500, and 700 base,
 IV-16,17
 "Catalin" 8012, IV-39, 119
 "Catalin" EK 2784, IV-39
 Celanese Corp. of America, IV-24,
 25, 114,115; V-9,10,12,90
 Celanese MR-31C, MR-33C, Mx-186,
 and Mx-218; V-12
 Cellular Rubber Products, Inc.,
 IV-51
 Cellulose acetate LL-1, IV-23
 Cellulose acetate + plasticizer,
 IV-24
 Cellulose acetates, IV-23,24; V-9
 Cellulose derivatives, IV-23-25;
 V-9,90,91,92; P.R.-159
 Cellulose nitrate and camphor, IV-25
 Cellulose propionate, IV-25,114;
 V-9,90
 Cellulose triacetate ("CTA"),
 V-9,92
 Cements and asphalts, IV-56
 Cenco "Sealstix," IV-56
 Centralab. :
 aluminas 205, 206, P.R.-19
 steatites 302, 400, 410, 452,
 IV-3,84-87
 Centralab. Div., Globe-Union, Inc.,
 IV-3,84-87; P.R.-19
 Central Scientific Co., IV-56
 "Ceram" 61-1, V-5,65
 "Ceram" 61-2, V-5,66
 "Ceram" 61-3, V-5,67
 "Ceram" 61-4, V-6,68
 "Ceram" 61-5, V-6,69
 Ceramics for Industry, P.R.-148
 Ceramics for Industry
 CFI 1003, CFI 1006 attenuator
 materials, P.R.-148
 Cerese Wax AA and brown, IV-57
 Ceresin, white and yellow, IV-57
 Cerium fluoride, ceramic,
 MIT, LIR, P.R.-61
 Cesium bromide, V-1
 Cesium iodide, V-1
 Cetylacetamide, IV-56
 "Chemelac" M1405, M1406, M1407,
 M1411, and M1412, IV-32
 "Chemelac" M1414, IV-32; V-241
 "Chemelac" M1418-2, M1418-5,
 M1422, and M1423, IV-33
 "Chemelac" B-3, IV-56
 Chemplast, Inc., P.R.-166
 Chemplast "Zitex," low-density
 polytetrafluoroethylene film,
 P.R.-166
 Chlorinated benzenes and biphenyls,
 IV-15,63,64; VI-78-83
 β -chloroethyl-2,5-dichlorobenzene,
 IV-64
 Chlorostyrenes, ortho and para,
 copolymer, IV-42
 Chlorotrifluoroethylene dimer,
 trimer, V-18
 Chlorotrifluoroethylene tetramer,
 pentamer, hexamer, V-19
 Chromium oxide, Linde, single
 crystal, P.R.-62
 Ciba Co., Inc., IV-21,49,50,125;
 P.R.-108; P.R.-186
 Ciba epoxy resins, IV-49,50,125; P.R.-180
 "Cibanite," IV-21
 Ciba tantalum oxide, optical grade
 powder, P.R.-108
 Climax Molybdenum Co., VI-45
 Clinoenstatite, see magnesium
 metasilicate
 Coal, powdered, P.R.-191
 single lump, P.R.-192
 Cobalt ferrite, MIT samples, V-136,
 177,206

Cobalt oxide,
 Cobalt oxide, nickel oxide
 mixed crystal, MIT,
 Crystal Physics Lab.,
 P.R.-63
 Coffee, P.R.-202
 Columbia Univ., P.R.-75
 Columbia University manganese
 fluoride, tetragonal '
 crystal, P.R.-75
 Components and Systems Lab.,
 see U.S. Components and
 Systems Lab.,
 Concrete pavement, P.R.-157
 Concrete, artificial, P.R.-159
 Conformal coating, Amicon
 Corp., P.R.-160
 "Conolon" 506, V-8
 Continental Diamond Fibre Co.,
 IV-18,19,21,26,27,31,32;
 V-8,12,14,80-83,88,93,
 104,108,114
 (now a division of The Budd Co.,
 see also Budd)
 Cooking oil, Kremax, Armour,
 P.R.-198
 Coors alumina
 AB-2, IV-6,98,99
 AD-99, VI-14,15; P.R.-19
 AD-995, P.R.-20
 AL-100, V-2,40
 AI-200, IV-6,96,97;
 V-21; VI-11-13
 EI-95, VI-16,17
 MC-2014, P.R.-20
 RR, P.R.-20
 NBS 10F2, P.R.-20
 Coors BeO BD-98, P.R.-41
 Coors Porcelain Co., IV-6,94-99;
 V-2,21; VI-11-17; P.R.-19-20,
 41
 "Copolene" B, IV-28
 Copper halides, ressed
 powder, MIT, LIR
 copper bromide, P.R.-63
 copper chloride, P.R.-63
 copper iodide, P.R.-63
 Cordierite, P.R.-67
 "Corfoam" 114, IV-19
 Cornell Aeronautical Labs.,
 IV-48,124
 Corning aluminas
 JD-40, JD-82, JB-183,
 V-2,41
 JB-123 and W.D-131, V-2
 Corning Fotoceram, VI-40,41
 Corning Fotofoarm, VI-36-39
 Corning Glass Code Nos. 0010,
 0014, 0080, 0090, 0100, 0120,
 0330, 1723, 1770, 1990, 1991,
 3320, 7040, 7050, IV-9,102;
 P.R.-89,149
 7052, 7055, 7060, 7070, IV-10,
 102; V-62,63
 7230, 7570, 7720, 7740, 7750,
 IV-10
 7900, 7911, IV-10; V-5,64; VI-35
 7911, IV-10,103
 7940, P.R.-83
 7941, P.R.-96
 Corning 7945 multifilm glass, P.R.-96
 Corning Glass Nos. 8460, 8830,
 IV-10
 8603, V-5
 8871, 9010, Lab. No. 189CS,
 IV-11
 Corning Glass code 9606, VI-42,43
 Corning Glass No. 119BUC, P.R.-89
 Corning Glass Works, IV-9-11,26,
 41,42,102,103; V-2,5,6,41,62-71;
 VI-35-43; P.R.-83,89,96
 Cotton molding, Amer. Cyanamid,
 P.R.-159
 Crepe, pale and compounds, IV-51
 Cresylic-acid formaldehyde
 resins, IV-18,19,68,70
 "Crolite" No. 29, IV-4
 "Cronar," V-13,109
 Crowley Co., polyiron attenuator,
 P.R.-167
 Crowley, Henry I, and Co., Inc.,
 IV-4,7; V-217-219; P.R.-167
 "Crowloy" 20, IV-7; V-217
 "Crowloy" 70, IV-7
 "Crowloy" BX113, IV-7; V-218
 "Crowloy" BX114, IV-7; V-219
 Crystals, inorganic, IV-1,2,72-77;
 V-1,26-30,133-135; VI-2-6,
 P.R.-2,4,38,3944,58,59,60,62,
 63,65,66,68,77,78,80,81,103-
 105,106,107,109,115,117,123-134
 Crystals, organic, IV-15
 Custom Materials, Inc., P.R.-167
 Custom Materials, Load 4101, 707-4,
 707-(3.75), P.R.-167
 "Cyma-2," 325, VI-65; P.R.-160
 "Dacron"-filled plastics, V-8,10,12,
 14,110
 "Darex" No. 3, 43E, X-34, X-43, IV-38

"DeKhotinsky" cement, IV-56
 Delaware Research and Development Corp., V-9
 Dennison Mfg. Co., IV-58
 Desert sand, P.R.-143
 Dewey and Almy Chemical Co., Organic Chemicals Division, IV-38
 "Diala" Oil, IV-66
 Diallyl phenyl phosphonate resin, IV-48
 Diamond, V-1
 Diamonite Products Div. U.S. Ceramic Tile Co., V-2,3,42-45; P.R.-21
 "Diamonite" B-890, V-2,42 B-890-2, P.R.-21
 "Diamonite" P-3142, V-2,43 P-3142-1, P.R.-21
 P-3459, V-2,44
 P-3530-40, V-3,45
 P-3662, P.R.-21
 Diatomaceous-earth ceramic, IV-6,101
 Dibutyl sebacate, IV-62
 Dichloronaphthalenes, mixture of the 1,2-, 1,4- and 1,5-isomers, IV-58
 Dichloropentanes Nos. 14 and 40, IV-63
 2,5-Dichlorostyrene, IV-64
 DI-CUP, P.R.-196
 Diisopropyl biphenyl, V-19
 "Dilectene" 100, IV-21
 "Dilecto" (hot punching) XXX-P-26, IV-19; V-80,81
 "Dilecto" ("Mecoboard"), IV-18; V-82,83
 "Dilecto" GB-112S, IV-27
 "Dilecto" GB-112T, IV-31,32; V-104
 "Dilecto" GB-116E and GB-126E, V-14
 "Dilecto" GB-181E, V-14,114
 "Dilecto" GB-261S, IV-26; V-93
 "Dilecto" GM-1, V-8,88
 "Dilecto" GM-PE, V-12,108
 Dinitrobenzene, VI-77
 Dioctyl sebacate, IV-62
 Diphenyl, see biphenyl
 Dodge Industries, Inc., P.R.-167
 Dodge Industries FLUORGLAS E 650/C 1200, P.R.-167
 Dow Chemical Co., IV-36-42,46,64, 117; V-91; P.R.-194
 Dow Chemical "Dowtherm" A, P.R.-194
 Dow Corning Corp., IV-26,27,41,42, 54,55,66,67,126; V-9,20,94, 95; VI-52-57; P.R.-168
 Dow Corning fluids 200 and 500, IV-66
 550 and 710, IV-67
 Dow Corning molding compound 306, P.R.-168
 Dow Corning resins 996 and 2101, IV-26
 2103, IV-26,27
 2105, V-9,94
 2106, V-9,95-101; VI-57
 Xk-7141; VI-56
 R-7501, VI-52,53
 R-7521, VI-54,55
 Dow Corning Silastics 120, 125, 150, 152, 160, 167, 180, IV-54
 181 and 250, IV-54,126
 6167, IV-55,126
 6181, X4342, IV-55
 XF6620, IV-55; V-20
 X6734 and 7181, IV-55
 RTV 501, 521, 1602, 5350, S-6538, P.R.-168
 Dow Corning Sylgard 182, 184, and DC-92.007, P.R.-168
 Dow C-244, IV-36
 Dow experimental plastic Q-166, Q-166 + fiberglass, Q-200.5, IV-39
 Dow experimental plastic Q-247.1, IV-36
 Q-344, IV-40
 Q-406, IV-37,117
 Q-409, IV-42
 Q-475.5, IV-40
 Q-764.6 and Q-767.2, IV-37
 Q-817.1, IV-37,117
 "Dowtherm" A, P.R.-194
 Dupont, E. I. de Nemours and Co. Electrochemicals Dept., IV-33,64
 Film Department, V-9,13,92
 Organic Chemicals Dept. (Elastomers Div.), IV-53; P.R.-194
 Photo Products Dept., V-13,109
 Pigments Dept. IV-4
 Plastics Dept., P.R.-169-171, 173,174

Dupont, E. I. de Nemours
and Co. (cont.)
Polychemicals Dept., IV-23,25,
27, 32,34,35,58,113; V-10,89;
VI-58
Textile Fibers Dept., V-8,10,
12, 14, 110; P.R.-172
Dupont de Nemours fluorinated
ethers, Organic Chemicals
Dept., P.R.-194
Dupont de Nemours "H" film,
Plastics Dept., P.R.-169-171
Dupont de Nemours "Kapton,"
500 H film, Plastics
Dept., P.R.-171
Dupont de Nemours Nonex honey-
combs, Textile Fibers
Dept., P.R.-172
Dupont Teflon FEP, TFE, T-100,
100X, 9033, TEF-7, TFE-6c,
Plastics Dept., Chestnut
Run Lab., IV-32; V-24;
VI-58; P.R.-173,174
"Durez" 1601, natural, IV-17
"Durez" 11863, IV-20
Durez Plastics, Div., Hooker
Electrochemical Co.
IV-17,20
"Durite" No. 500, IV-17
"Durite" No. 221X, IV-19
Durite Plastics, Inc., now
the Borden Co., IV-17,19
"Duroid" (1" thick sheet),
P.R.-184
"Duroid" 5650, VI-59-61
"Duroid" 5850, VI-62-64
Dynasil Corp. of America,
P.R.-84,96
Dynasil 4000 glass, P.R.-84
Dynasil slip-cast, P.R.-96

East Coast Aeronautics, Inc., V-11
Eastman Kodak Co., IV-15,62; P.R.-67
"Ecco" L65, V-11
"Eccofoam" FH, Emerson & Cuming,
P.R.-176
"Eccofoam" GL, V-8
"Eccofoam" HiK (1000°F), V-7
"Eccofoam" HiK (500°F), V-14,115
"Eccofoam" PS, V-10
"Eccogel" 1265, Emerson & Cuming,
P.R.-176
"Eccosorb" HFX122, V-13,237
"Eccosorb" HFX123, V-13,238

"Eccosorb" HF155, HF680, HF853,
HF1000, HF2050, V-13
"Eccosorb" MF110, MF112, MF114, and
MF116, V-15
"Eccosorb" MF117, V-15,242
Eggwhite, P.R.-202
EKONOL (polyester resin), P.R.-166
Electronic Mechanics, Inc.,
IV-13,108
Electronized Chemicals Corp.,
P.R.-175
Electronized Chemical "Polyguide",
P.R.-175
Emerson & Cuming, V-7,8,10,11,13-15,
115, 237, 238, 242; P.R.-175-176
Emerson & Cuming A-19 attenuator
material, P.R.-175
Emerson & Cuming
"Eccofoam" FH, P.R.-176
"Eccofoam" GL, V-8
"Eccofoam" HiK (1000°F), V-7
"Eccofoam" HiK (500°F), V-14,115
"Eccofoam" PS, V-10
Emerson & Cuming "Eccogel" 1265,
P.R.-176
Elastomers, IV-51-55; V-127-129
"Elvacet" 42A-900, IV-33
"Elvanol" 51A-05, 50A-42, 70A-05,
72A-05, 72A-51, IV-33
Engineering Research and Dev. Lab.,
see U.S. Army Eng. Res. and
Dev. Lab.
Enjay Co., Inc., IV-28,39,50
"Ensolute" M22240, M22239, 3036,
IV-31
"Epon" Resin RN-48, IV-50
"Epcn" 828, V-16,116-125; VI-68-75;
P.R.-186,187
"Epon" X-131, V-16; VI-74-76
Epoxy resins, IV-49,50, 125; V-14-
16, 114, 126; VI-67-76; P.R.-180
Epoxy laminates with
"Dacron," V-14
"Fiberglas," IV-50; V-14,16,22,
114,124,125; VI-67,72-76
"Nylon," V-14
"Orlon," V-14
E resin, IV-50
Esso Laboratories, see Enjay Co.,
P.R.-195
Esso "Teresso" oil, V-78; P.R.-195
"Estawax," IV-57
Ethers, fluorinated, P.R.-194
"Ethocel" LT5, IV-25, 115; V-91

Ethyl alcohol, IV-62
 Ethyl cellulose, IV-25, 115; V-91
 Ethylene Chemical Corp., V-10
 Ethylene Glycol, IV-62
 Ethylpolychlorobenzene, IV-64
 "Ferramic" A, V-159, 191, 220
 "Ferramic" B, V-160, 192, 221
 "Ferramic" C, V-161, 193, 222
 "Ferramic" D, V-162, 194, 223
 "Ferramic" E, V-163, 195, 224
 "Ferramic" G, V-164, 196, 225
 "Ferramic" H-1, V-4, 166, 198
 "Ferramic" H, V-165, 197, 226
 "Ferramic" I, V-167, 227
 "Ferramic" J, V-168, 199, 228
 "Ferramic" K, V-169, 229
 "Ferramic" N, V-200
 "Ferramic" Q (rec'd Dec. 1953),
 V-170, 230
 "Ferramic" Q (rec'd Aug. 1954),
 V-171, 201, 231
 "Ferramic" Q₂, VI-32, 33
 "Ferramic" Q-3, P.R.-150
 "Ferramic" R-1, R-4, R-5,
 R-6, P.R.-150
 "Ferramic" MF874, V-172, 202
 "Ferramic" 1118, V-173, 232
 "Ferramic" 1326B, V-174, 203
 "Ferramic" 1331, V-175, 204, 233
 "Ferramic" 3308, P.R.-150
 "Ferramic" 3310 (experimental),
 V-176; P.R.-150
 "Ferramic" 3321, P.R.-150
 "Ferramic" 3330, P.R.-150
 Ferrites and garnets, IV-7;
 V-4, 54, 133-204, 206-233;
 VI-28-33; P.R.-150
 "Ferrottron" 119, V-17, 205, 244
 "Ferrottron" 308, 309, V-18
 Ferroxcube Corp. of America, V-4
 "Ferroxcube" 105, V-4
 "Fiberfrax" board, V-6, 78;
 VI-46, 47
 "Fiberglas" laminates, IV-16, 18,
 22, 25-27, 31, 32, 47-50, 68;
 V-8-11, 13, 14, 16, 22, 86-88,
 93-95, 98-101, 104; VI-56, 57;
 P.R.-189-190
 "Fiberglas" see E glass, Owens-
 Corning X994 laminates or
 resin
 "Fibestos" 2050TVA C-1686, IV-24
 Films, see trade names as
 Croner, Nylar, Kapton,
 Quantum tape, etc., or
 chemical name
 Filtered Resin Products, Inc., IV-56
 Fir plywood, P.R.-193
 Fluorinated ethers, P.R.-194
 Fluorocarbon derivative P-1C, P.R.-194
 FLUOROGLAS E 650, 2-1200, P.R.-167
 "Fluorosint" (1960), P.R.-179
 Foam, alkyd diisocyanate, chlorinated,
 IV-124
 epoxy, V-14
 polyimide, P.R.-178
 polystyrene, IV-37; P.R.-188
 polymethane, P.R.-179, 188
 "Foamglas," IV-11
 Formaldehyde resins
 aniline, IV-21
 benzoguanamine, IV-23
 cresol, IV-18, 19, 68, 70
 melamine, IV-21, 22, 112
 phenol, IV-15-19, 109-111; V-80-87
 phenolaniline, IV-20
 urea, IV-23
 Formica Co., The, IV-17, 20, 21, 25,
 46, 47
 "Formica" FF-41 (sheet, rod stock),
 IV-21, 68
 "Formica" FF-55, IV-21, 69
 "Formica" G7, G6, IV-25
 "Formica" Grade MF-66, IV-20, 68
 "Formica" XX, LF, IV-17, 68
 "Formica" YN-25, IV-17
 "Formica" Z65, IV-46
 "Formica" Z80, IV-47
 "Formvar," Type E, IV-34
 "Forticel" No. 28102, IV-25; V-90
 "Forticel" JLB-(H), V-9
 "Forticel" JMB-(H), V-9
 "Fortiflex" A, V-10
 "Fotoceram" (843 GU) and (843 GZ),
 V-5; VI-40, 41
 "Fotoform" B(843 GU), V-5; VI-36, 37
 "Fotoform" C(843 GU), V-5; VI-38, 39
 "Fractol" A, IV-66
 Frenchtown Porcelain Co., IV-6;
 V-3, 48, 49; P.R.-21
 Frenchtown alumina
 4462, IV-6; V-3, 48
 6096, V-3, 48
 7225, P.R.-21
 7873, V-3, 49
 Fullers earth, Foxboro, P.R.-141
 Furfurdehyde resin, phenol, IV-19
 Fused quartz, IV-11, 104; V-72, 73;
 P.R.-85-87

"Gafite" cast polymer, IV-34
 Gasoline, aviation, 100 and 91 octane, IV-65
 General Aniline and Film Corp., IV-34,46
 General Cable Corp., IV-52
 General Ceramics Co., IV-4,8,83; V-3,4,54,55,159-176, 191-204, 220-233; VI-32,33; P.R.-150-152,176,177
 General Ceramics ADH-211, V-3 BM3054, V-4,55
 7294, IV-4, V-55
 General Ceramics "Ferramics, see "Ferramics"
 General Electric Co., IV-63-65
 Chemical Materials Dept., IV-48
 Electronic Components Div., IV-13,106,107; P.R.-22-29, 73,153,154
 Lamp Div., IV-11,104; V-72,73
 Plastics Dept. IV-50
 Silicone Products Dept., IV-55; P.R.-85-87, 176,177
 General Electric fused quartz, Type 101, IV-11,104; V-72,73
 General Electric Isomica 4950, P.R.-153
 General Electric "Lexan," P.R.-177
 General Electric F-118,F-202 magnesium orthosilicate, P.R.-73
 General Electric "Mycalex," P.R.-153,154
 General Electric silicone rubber RTV-11, P.R. 176
 SE900, P.R. 177
 General Mills, Inc., IV-23
 Geon 2046,80365,80384, IV-29
 Gilsonite, IV-56
 Glass, alkaline lead silicate, IV-11
 Glass, alkali silica, IV-12,105; P.R.-93, see also mixed silicate glass and various glass mfgs.
 Glass, aluminum borosilicate, IV-10
 aluminum zinc-phosphate, IV-9
 barium borosilicate, IV-10
 borosilicate, IV-9,101
 Glass, Dynasil 4000, P.R.-84
 "E", IV-11
 General Electric 101, clear, P.R.-85-87
 iron-sealing, IV-9,102
 Glass, lead-barium, IV-9
 lime-alumina-silicate, IV-9
 low alkali, potash-lithia-borosilicate, IV-10,102; V-62-63
 mixed silicate, P.R.-89-94
 phosphate 2043x, 2279x, IV-9
 potash-lead silicate, IV-9
 potash-soda-barium silicate, IV-9
 silica, IV-10,103;V-64; P.R.-82-88
 soda-borosilicate, IV-9,10
 soda-lead-borosilicate, IV-10
 soda-lime-silicate, IV-9,11
 soda-potash-borosilicate, IV-9
 soda-potash-lead-silicate, IV-9
 soda-potash-lithia-borosilicate, IV-10
 soda-silica, IV-11
 soda-silicate, P.R.-93
 Glass, "Spectrosil" A, P.R.-88
 "Spectrosil" B, P.R.-88
 "Vitreasil," optical Grade, P.R.-88
 "Vitreasil," commercial grade, P.R.-88
 Glass ceramic 9606, VI-42,43
 Glass Lamicoid No. 6038, IV-21,70
 Glass and mica, IV-13,69,106-108, P.R.-153-155
 Glass powder and plastic mixtures, IV-41,42
 Glasses, IV-9-12,101-105; V-5,6,62-73; VI-35-43; P.R.-82-94
 Glastic Corp., IV-47,49
 "Glastic" GF, MM, MP and A-2, IV-49
 "Glastic" S and MF, IV-47
 Glyco Products Co, IV-56,59
 "Glyptol" No. 1201 (red), IV-48
 Goodrich, B.F., Chemical Co., IV-29,30
 Goodyear Aircraft Corp., IV-48; V-8,9, 84-87,96-101
 Goodyear Tire and Rubber Co., Plastics Dept., IV-40,51,52
 Granite, Quincy, P.R.-138
 Virginia, P.R.-138
 Grease, Dow Corning, No. 4, IV-67
 high vacuum, V-20
 Grease, "KEL-F" No. 40, IV-63
 Greenstone, Virginia, P.R.-139
 GR-1 (butyl rubber) and compound, IV-52
 GS-S (Buna S) and compounds, IV-51
 Gulf Oil Corp., IV-58; VI-84,85

Gulf 303 oil, VI-84,85
Gutta-percha, IV-51

Hafnium oxide, multicrystalline,
Zirconia, P.R.-64

Halite, P.R.-135

"Hallowax" No. 1001, IV-57

No. 11-314, IV-58

Oil 1000, IV-64

Hardman, H. V., Co., Inc.,
IV-49,51

Harshaw Chemical Co., The,
IV-1,2; V-1,30

Hartwell, N.H., and Sons, Inc.,
V-10

Haveg Industries, Inc.,
Taunton Div., P.R.-153

"Havelex" glass-bonded micas:
Types 1080,1090,1101,2101,
2103,2801,2803, P.R.-153

Hawaiian soil, P.R.-141,142

Haynes Stellite, Div. of
Union Carbide and Carbon,
P.R.-101

Heptacosafuorotributyl, IV-63

Heptane, IV-62

Hercules Powder Co., Inc.
IV-23; V-16; P.R.-196

Hercules DI-CUP, dicumyl
peroxide, P.R.-196
VUL-CUP, a,a'-bis(t-butyl
peroxy) diisopropylbenzene,
P.R.-196

Hexachlorobutadiene, IV-62

Hexamethylene-adipamide polymer,
IV-23,113

Hexane, V-19

"H"-film, P.R.-169-171

Hood Rubber Co., IV-22

Hooker Electrochemical Co.,
IV-62; V-13

Hooker J2A, V-13

Houghton Labs., Inc.,
IV-50; V-15,16,126

Hunson, C.W., V-7

"Hycar" OR "Cell-tite, IV-52

Hydrocarbon polymer, cross-
linked, IV-50

Hydrocarbons, petroleum,
IV-65-66; VI-84,85

12-Hydroxystearin, IV-58

"Hysol" 6000 and 6020, IV-50

6000 HD, V-15,126

6030-B, V-15

XL-6060, V-15

XE-6080, V-16

"Hy-tuf" laminate Grade GF181, IV-50

Ice, IV-1; P.R.-145-147

Ignition sealing compound No. 4, IV-67

Instant coffee, powder, P.R.-202

Instant tea, powder, P.R.-202

International Pipe & Ceramic, P.R.-30,72

International Pipe & Ceramic alumina,
P.R.-30

International Pipe & Ceramic
steatite, P.R.-72

Iron and plastic mixtures, IV-43,44;
V-243

Iron-manganese oxide and plastic
mixtures, IV-45

IRTRAN-5, Kodak MgO, multicrystal,
P.R.-67

Irrington tape, V-17

Irrington Varnish and Insulator Co.,
V-17

Isobutylene-isoprene copolymer, IV-52

Isomica 4950, General Electric
P.R.-153

Jet fuels JP-1, JP-3, IV-65; JP-4, V-19

Johns-Manville, IV-13; P.R.-158

"Kapton," P.R.-171

Kearfoot alumina, V-3,46,47; VI-18,19

Kearfoot Co., Inc., V-3,46,47; VI-18,19

Kearney, James R., Corp., IV-52

"Kel-F," IV-31

"Kel-F" Alkanes 464, 695, V-18

8126, 10157,12188, V-19

Grade 300 and 300-P25, IV-31,116

X200, V-10,102,103

grease No. 40, IV-63

oil, Grade No. 1 and No. 3, IV-63

oil, Grade No. 10, IV-63,

V-130,131

wax No. 150, IV-58

Kellogg, N.W., Co., The, IV-31,58,

63,116; V-10,18,19,102,103,

130,131

Kennecott Copper, P.R.-191

Kerosene, IV-65

Knox Porcelain Corp., IV-6,100

Kodak Co., see Eastman Kodak Co.

Kodak INTRAN-5, P.R.-67

"Koroseal" SCS-243, IV-30

"Kralastic" BE, BN, D, EBNU, F, IV-53

KRS-5, IV-2,76

KRS-6, IV-2,75

Kuhn-Libby Co., IV-57

"Laminac" 4115, IV-46,120

4-205, IV-46,121

"Laminac" 4232, V-106,107
 PDL7-627 and PDL7-650,
 IV-46,120
 Laminate BD-44 and BK 174,
 IV-47,48
 Laminated Plastics, Inc.,
 see Glastic Corp.
 Laminates and impregnated batts,
 see filler or resin:
 Asbestos-filled plastics
 "Dacron"-filled plastics
 Epoxy laminates
 "Fiberglas" laminates
 Melamine GMG
 "Nylon"-filled plastics
 "Orlon"-filled plastics
 Paper laminates
 Phenoloc resin plus fillers
 Polyester resin plus fillers
 Polystyrene plus fillers
 Silicone resin plus fillers
 Lancaster Glass Co., P.R.-89-92
 Lancaster mixed silicate glasses,
 7352, 7357, L1957, L9100,
 P.R. 89-92
 Lanthanum aluminate, single
 crystal, National Lead, P.R.-65
 Lava, V-21,75
 Lead bromide, single crystal,
 MIT, Crystal Phys.Lab., P.R.-66
 Lead chloride, P.R.-66
 Lead chloride/lead bromide, P.R.-66
 Leather, sole, IV-60
 "Lexan," General Electric, P.R.-177
 Limestone, P.R.-139
 Limonite, P.R.-135
 Linde Air Products Co., The,
 IV-1,2,72,77; V-1,26-28;
 VI-2-6; P.R.-2,3,62
 Liquids, aliphatic, IV-62,63;V-18,
 19,130,131
 aromatic, IV063,64;V-19; VI-78-
 83; see Table of Contents of
 the Present Report
 inorganic, IV-61; V-18
 organic, IV-62-67; V-18,19,
 20; VI-78-87; see Table of
 Contents of the Present report
 Liquids, petroleum, IV-65,66;
 VI-84, 85; P.R.-195
 silicone, IV-66,67;V-20;VI-86,87
 Lithium fluorine, IV-1
 Lithium-nickel ferrite, V-137,178
 Litton Industries, P.R.-117
 "Loalin," IV-36
 Lovell Chemical Co., IV-57,58; V-16
 "Lucalox," General Electric, P.R.-23,24
 Lucent Products Ltd., VI-66
 "Lucidol," P.R.-196
 "Lucite" HC 202, V-10
 "Lucite" HM-119 and HM-140, IV-34,70
 "Lucite," sintered, IV-34
 "Lucoflex," IV-30
 Lucoflex Plastic Fabricating, Inc., IV-30
 "Lumarith" XFA-H4 and 22361, IV-24,25,70
 Lunar rocks, Apollo 11 and 12, P.R.-139
 "Lupersol" 101, P.R.-197
 "Lupersol" 130, P.R.-196
 "Lustrex" loaded glass mat, IV-41
 3-M Company, IV-63; V-16,17,22; VI- 67; P.R.-17
 "3-M" board, P.R.-178
 3-M "Scotchcast" 221, P.R.-178
 Magnesia
 Kodak ITRAN-5, P.R.-67
 MIT, LIR, P.R.-68,69
 Minneapolis Honeywell, P.R.-70,71
 Magnesite, P.R.-135
 Magnesium aluminate (spinel), single
 crystal, Union Carbide, P.R.-66
 Magnesium-aluminum silicate (cordierite),
 multicrystalline, Raytheon, P.R.-67
 Magnesium carbonate, pressed powder, P.R.-67
 Magnesium ferrite (MIT samples), V-138,
 179,207
 Magnesium-manganese ferrite (MIT samples),
 V-139,140,180,181,208
 Magnesium-manganese-zinc ferrite (MIT
 samples), V-141,182
 Magnesium manganite, V-4,54
 Magnesium metasilicate, steatite fired
 to clinoenstatite, multicrystalline,
 Bell Telephone Labs. F-66, P.R.-72
 Intern. Pipe & Ceramic TC503, P.R.-72
 Magnesium orthosilicate, multicryst.,
 General Electric F-118, P.R.-73
 F-202, P.R.-73
 Magnesium orthosilicate, Steatite-Magnesia
 A.G. Frequentia M, P.R.-74
 Magnesium oxide, IV-1; V-29; P.R.-67-71
 Norton, single crystal, IV-1; V-29;
 P.R.-68
 Magnesium silicate, IV-3,78-82; VI-34
 Magnesium titanate, IV-4; P.R.-75

Magnesium titanate and plastic mixture, IV-43
 Magnetite and plastic mixtures, IV-44,45
 Mallinckrodt Chemical Works, IV-44,45,61,62
 Manganese fluoride, single crystal, Columbia Univ., P.R.-75
 Manganese-magnesium ferrite, (MIT samples), V-139,140, 180,181,208
 Manganese-magnesium-zinc ferrite (MIT samples), V-141,182
 Marble S-303, IV-13
 Marbon, Chemical Div. of Borg-Warner Corp., IV-38
 "Marbon" S Buna S hardboard, IV-52
 "Marbon" S (Code 7206), S-1 (Code 7254), 8000 and 9200, IV-38
 Marco Chemicals, Inc., now Celanese Corp. of America, IV-47
 Marco Resin "MR"-21C, "MR"-23C, and "MR"-25C, IV-47
 "Marcol," IV-65
 Marinite, P.R.-193
 Markite Co., V-22,235,236
 "Markite" 3985, V-22,235
 "Markite" 12812, V-22,236
 "Marlex" 50, V-10
 Martin Co., The, VI-57
 Mass. loams, P.R.-143
 Massachusetts Institute of Technology
 Cryogenic Engineering Laboratory, V-18
 Crystal Physics Lab., P.R.-38,39,59,63,66,77, 78,103-105,106,107,109
 Laboratory for Insulation Research, IV-1,2,5,11, 12,26,37,41-46,62,64, 105; V-1,133-136,138, 139,142-158,177,179, 180,183-190,206-216, 239,240,243; P.R.-44, 61,63,68,69,93,102, 110-114,115,116

M.I.T. (cont.)
 Lincoln Laboratory, V-140,141,176, 178,181,182; VI-30,31
 Metallurgy Department, P.R.-60
 National Magnet Laboratory (now Francis Bitter Natl. Mag. Lab.), P.R.-192
 Mathieson Chemical Corp., see Olin Mathieson
 Mathieson Plastic CY-8 and CQ-10DM, IV-41
 Meat, IV-60; P.R.-199
 "Mecoboard," IV-18; V-82-83
 Melamine-formaldehyde resins, IV-21,22, 112; V-8,88
 Melamine GMG, IV-21,70
 "Melmac" 7278 + "E" glass, IV-22
 "Melmac" molding compound 1500, 1502, IV-22,112
 "Melmac" resin 592, IV-21
 "Melmac" Type 1077 (Ivory WB 48), IV-21
 Mercury compounds, hot-pressed
 mercurous chloride, P.R.-76
 mercuric iodide, P.R.-76
 mercuric sulfide, P.R.-76
 Meta-dinitrobenzene, VI-77
 Methacrylate resins, IV-34,35
 "Methocel," IV-25
 Methyl alcohol, IV-62
 Methyl cellulose, IV-25
 Methylstyrene polymer, VI-65
 Methylstyrene-styrene copolymer, IV-39
 Mica, Canadian, IV-13
 Mica, glass-bonded, IV-13,69,106-108; P.R.-153-155
 Mica, ruby, IV-13
 Mica and glass, IV-13,69,106-108; V-7,79
 Mica-filled plastics, IV-16,17,18,20; V-7
 "Micaramic," V-7
 "Micarta" No. 254, IV-18
 "Micarta" No. 259, IV-22,68
 "Micarta" No. 299, IV-19,68
 "Micarta" No. 496, IV-18,68,70
 Mica Insulator Co., IV-21
 "Millimar," IV-56
 Minneapolis-Honeywell Regulator Co., P.R.-31,70,71
 Minneapolis-Honeywell alumina, P.R.-31
 Minneapolis-Honeywell magnesium oxide, ceramic, P.R.-70-71
 Minnesota Mining and Mfg. Co., now 3-M Co., IV-63; V-16,17,22; VI-67; P.R.-178

Minn. Mining & Mfg. EC-612, V-17
 "Missileon," V-17
 Mitchell-Rand Insulation Co.,
 Inc., IV-57-59
 Molding compounds, XM-3, IV-20
 301, V-9,94; P.R.-168
 "Moly-Sulfide," VI-45
 Monoisopropyl biphenyl, V-19
 Monsanto Chemical Co., Plastics
 Div., IV-15,18,20,22,24,30,
 36,37,41-45,63,64; VI-78-83;
 P.R.-178
 Monsanto OS-45, OS-59, and OS-82,
 V-19
 Monsanto polyimide foam, P.R.-178
 Morse, Herbert B., and Co.,
 V-16,17
 Morse 200, V-16
 280, 300, 400, 6060-C, and
 6062, V-17
 Mullet oil, P.R.-197
 Mullite, V-3
 Multifilm glass, Corning, P.R.-96
 Muscovite, IV-13
 Mycalex Corp. of America,
 IV-13; V-7,79; P.R.-153-155
 "Mycalex" K10, IV-13
 "Mycalex" 400, IV-13,69
 "Mycalex" 410, 500, 555, 560, 620,
 P.R.-153-155
 "Mycalex" 2821, IV-13,106,107
 "Mykroy" Grade 8 and 38, IV-13,108
 "Mylar" A, V-13

 Napthalene, IV-15
 Napthalene, chloro-, IV-64
 Narmco Resins and Coatings Co.,
 V-8
 National Beryllia "Carberlox,"
 P.R.-80
 National Beryllia Corp., P.R.-31,
 41,80
 National Beryllia high-purity
 BeO, P.R.-41
 National Carbon Co., Inc., V-18;
 VI-48-51; P.R.-4,50,51,54-57,
 66,101,189; now div. of Union
 Carbide & Carbon
 National Lead, P.R.-65
 National Lead LaAlO₃ single
 crystal, P.R.-65
 National Research Corp., V-3
 Naugatuck Chemical, Div. of
 U.S. Rubber Co., IV-47,53

 Naugatuck Laminating Resin MP and MT,
 IV-47
 Neoprene GN and compound, IV-53
 Neptunite, P.R.-129
 Nickel ferrite (MIT samples), V-133-135,
 142,143,182,209
 Nickel-lithium ferrite (MIT samples),
 V-137,178
 Nickel oxide, single crystal, P.R.-49
 Nickel-zinc ferrite (MIT samples),
 V-144-157,184-190, 210-216
 Nitrobenzene, IV-64
 Nitrobenzene, meta-di, VI-77
 Nitrogen, gas, V-20
 Nitrogen, liquid, V-18
 Nitrous oxide gas, V-20
 Nonex honeycombs, P.R.-172
 Nopco Chemical Corp., P.R.-179
 Nopco Chemical polyurethane foam,
 P.R.-179
 North American Aviation Co., P.R.-42,
 43,100
 North American Aviation silicon
 nitride, pyrolytic, P.R.-100
 North American Aviation translucent
 BeO, P.R.-42,43
 Norton Co., IV-1,6; V-3,29,49; P.R.-31,68
 Norton 99.5% Al₂O₃, P.R.-31
 Norton 7X, V-3,49
 Norton 17Z, V-3
 Norton MgO single crystal, P.R.-68
 "Nylon" 66 and 610, IV-23
 "Nylon" FM 10, 001, IV-23,113; V-89
 "Nylon"-filled plastics, IV-17; V-8,12,
 14,82,83

 Oil, HB-40, IV-63
 Oils, petroleum, IV-65,66; V-19;VI-84,85
 Olin Mathieson Chemical Corp., IV-41;
 V-20
 "Opalwax," IV-58
 "Orlon"-filled plastics, V-8,10,12,14
 Owens Corning CR-262, 57M, EA63, EA73,
 X600, V-6
 Owens-Corning X994, P.R.-93
 Owens-Corning Fiberglas Corp., IV-11,16,
 22,47,48; V-6,8,13; P.R.-93
 Owens-Illinois Glass Co., P.R.-93
 Owens-Illinois EE9, EE 10,mixed silicate
 glass, P.R.-93
 "Ozokerite," IV-58

Panelyte, Grade 140 and 776,
 IV-17,22
 Paper, Kraft, V-18
 Royalgrey, IV-60
 Paper laminates, IV-17,19,
 21-23,46; V-80
 Paraffin, natural, IV-58
 Paraffin wax 132° ASTM and
 135° AMP, IV-58
 "Paraplex" P13, IV-48,122
 "Paraplex" P43, IV-48; V-12,111
 "Parowax," IV-58
 Particle boards, U.S. Plywood
 & Evans Products, P.R.-193
 Pavement, see concrete or
 asphalt
 "Pelron" 9420, 9422, 9423, and
 9424, V-11
 Pennsylvania Industrial
 Chemical Corp., IV-39,50
 Pennwalt Corp, P.R.-196
 Pennwalt "Lucidol," t-butyl
 perbenzoate, P.R.-196
 Pennwalt "Lupersol" 130,
 2,5-dimethyl-2,5-di(t-
 butylperoxy) hexyne-3,
 P.R.-196
 "Penton," V-16
 "Perfluorodihexyl ether, IV-63
 "Permafil," 3256, IV-50
 "Permo" potting compound,
 No. 49 and No. 51, IV-49,51
 Petroleum oils, IV-65,66;
 VI-84, 85; P.R.-195
 Phenol-aniline-formaldehyde
 resins, IV-20
 Phenol-formaldehyde resins,
 IV-15-19,109-111
 Phenol-furfuraldehyde resin,
 IV-19
 Phenolic, expanded, IV-19
 Phenolic paper laminate JH-1410,
 IV-18
 Phenolic resin with asbestos,
 V-8, 84,85
 with "Dacron," V-8
 with "Fiberglas," V-8,
 86,87
 with "Nylon," V-8
 with "Orlon," V-8
 Phenolic spheres, V-12
 Phenolics, IV-15-20,109-111;
 V-8,80-87
 Philco-Ford Co., P.R.-97,98
 Philco-Ford silica fiber composites,
 1-XB-0-M, P.R.-98
 AS-3DX-176-17, P.R.-98
 Philips Chemical Co., V-10
 Philips Petroleum Co., V-19
 "Phoresin," IV-48
 Phosphate glasses, IV-9; P.R.-77
 Picatinny Arsenal, see U.S. War
 Department
 "Piccolastic" D-125, IV-39
 "Piccopale," Resin, IV-50
 Pine board, P.R.-193
 Pipestone, V-7
 Pittsburgh Corning Corp., IV-11;
 V-13,19
 Pittsburgh Plate Glass Co., P.R.-94
 Plaskon Div., IV-22,23,47,49,123;
 V-112,113
 "Plaskon" 911, IV-47
 "Plaskon" Alkyd 411, 420, 422, 440,
 440A and 442, IV-49
 "Plaskon" Alkyd Special, Electrical
 Granular, IV-49,123; V-112,113
 "Plaskon" melamine, IV-22
 "Plaskon" urea, natural and brown,
 IV-23
 "Plasticell," IV-31
 Plastic Metals, Div. of National
 U.S. Radiator Corp., IV-43,44
 Plastics, Raytheon, P.R.-180
 "Plast-Iron" and plastic mixtures,
 IV-43,44
 Plate glass, P.R.-94
 Plax Corp. IV-35
 "Plexiglass," IV-34
 "Plicene" Cement, IV-56
 "Pliobond" M-190-C, IV-52
 "Pliolite" and "Pliolite" GR, IV-51
 "Pliolite" S5, S3, S6B and S6, IV-40
 Plywood, birch, P.R.-193
 fir, P.R.-193
 Polaroid Corp., IV-35,37,40; V-11
 Polaroid Resin C, IV-40
 "Polelectron" No. 24, IV-46
 "Policap," V-16
 "Polinel," IV-58
 Polyamide resins, IV-23,113; V-8, 12,14,
 82,83,89
 Polybutene, IV-59
 Polybutyl methacrylate, IV-35
 Poly-2-chlorobutadiene-1,3, IV-53
 Polychlorostyrenes, IV-41,42

Polychlorotrifluoroethylene, IV-31,
 58,63,116; V-10,102,103
 Polycyclohexyl methacrylate, IV-35
 Polycyclostyrene, V-11
 Polydiallyl phthalate, IV-48
 Poly-2,5-dichlorostyrene, IV-40-
 42,70
 Poly-2,5-dichlorostyrene + fillers,
 IV-42-45; V-243
 Poly-3,4-dichlorostyrene, IV-42
 Polyesters, IV-46-48,120-123;
 V-11,12,13,106-111
 Polyester resin with "Dacron,"
 V-12,110
 Polyester resin with "Fiberglas,"
 IV-47,48; V-12,13,22,106,107,
 108
 Polyester resin with "Nylon,"
 V-12
 Polyester resin with "Orlon,"
 V-12
 Polyester resin with phenolic
 spheres, V-12
 Polyether, chlorinated, V-16
 Polyethylene, irradiated,
 P.R.-161
 Polyethyl methacrylate, IV-35
 Polyethylene, IV-27,28,70; V-10
 Polyethylene DE-3401, IV-27
 Polyethylene (effect of milling),
 IV-28
 "Polyglas" D⁺, IV-42
 "Polyglas" M⁺, IV-22
 "Polyglas" P⁺, IV-41
 "Polyglas" S, IV-26
 "Polyguide," P.R.-175
 Polyimide foam, P.R.-178
 Polyiron attenuator, P.R.-167
 Polyisobutylene, Run 5047-2,
 IV-28
 Polyisobutylene B-100 + Marbon B,
 IV-28
 Polyisobutylmethacrylate, IV-35
 Polymer Corp. of Pennsylvania,
 V-17,18,205,244; VI-66;
 P.R.-179
 Polymethyl methacrylate, IV-34,
 70; V-10
 "Polypenco" Q-200, 5; VI-66
 Polypropylene, Avisun Corp.,
 P.R.-162,163
 Polysiloxane resin, IV-26,27;V-9;
 VI-52-57
 Polystyrene, IV-35-37,117
 Polystyrene, cast in vacuo and cast
 in air, IV-37
 cross-linked, IV-39,40,119; V-11,
 105; VI-66
 hydrogenated, IV-46
 α -methylstyrene, IV-37,117
 Polystyrene + chlorinated diphenyl,
 IV-37
 Polystyrene Fibers Q-107, IV-37
 Polystyrene + fillers, IV-41; V-10,
 239, 240
 Polystyrene foam, P.R.-188
 Polystyrene Foam Q-103, IV-37
 Polysulfone, P.R.-189
 Polytetrafluoroethylene, IV-31-33,
 70; V-10,104; VI-58-64;
 P.R.-166,173,174
 Polytetrafluoroethylene tape,
 P.R.-166
 "Polythene" A-3305, IV-27,70
 Polytrifluorostyrene, V-11
 Polyurethane foams, Nopco, P.R.-179,
 Sippican, P.R.-188
 Polyvinyl acetal, IV-34
 Polyvinyl acetate, IV-33
 Polyvinyl alcohol-acetates, IV-33
 Polyvinyl butyral, IV-34
 Poly-N-vinylcarbazole, IV-46
 Polyvinyl chloride 1006, 1018, 1216,
 1406, W-174, W-175, and W-176, IV-30
 Polyvinyl chloride-acetate, IV-28-31
 Polyvinyl chloride-acetate +
 plasticizer, IV-28,29
 Polyvinyl chlorides, IV-28-31; V-10
 Polyvinylcyclohexane, IV-46
 Polyvinyl formal, IV-34
 Polyvinylidene and vinyl chlorides, IV-31
 Polyvinylidene fluoride, AVCO, P.R.-161
 Poly- α -vinyl naphthalene, IV-46
 Poly-2-vinylpyridine, IV-46
 Polyvinyl resins, IV-27-46
 Polyvinyltoluene, IV-37,117
 Poly-p-xylylene, IV-37
 Porcelain, wet and dry process, IV-6,100
 Porcelain No. 4462, IV-6
 Porcelains, IV-6, 94-100; V-2,3,5,21,40,
 59-61
 Porous Ceramic AF-497, IV-6,101

Porous ceramics, see low-density alumina, silica, silicates
 Potassium bromide, IV-1
 chloride, V-1
 dihydrogen phosphate, IV-1,73
 Potato chips, P.R.-199
 Potato flakes, P.R.-199
 Potatoes, raw, P.R.-199
 Potato starch, granular and gelatinized, P.R.-200,201
 "Primol"-D, IV-66
 Proctor and Gamble Co., IV-60
 n-Propyl alcohol, IV-62
 "Prystal," IV-17
 "Pyralin," IV-25
 "Pyranol" 1467, 1476, and 1478, IV-63,64
 "Pyrex," IV-10
 "Pyroceram" 9606, VI-42
 "Pyrotex," V-8

 Quantum, Inc., P.R.-180
 Quantum Radar tape, P.R.-180
 Quartz, fused, IV-11,104;V-6,72,73; P.R.-85-88
 Quartz crystal, natural, P.R.-80,81
 Quartz fiber, AS-3DX-1R, Philco-Ford, P.R.-97
 Quartz sand, powder, P.R.-135
 "Quinorgo" No. 3000, IV-13
 "Quinterra," IV-13

 Radar tape, Quantum, Inc., P.R.-180
 Raybestos-Manhattan, Inc., V-8,9
 Raytheon Mfg. Co., V-3; P.R.-32, 52,53,67,100,139,158,180
 Raytheon Al₂O₃, multicrystal, P.R.-32
 boron nitride, pyrolytic, P.R.-52,53
 magnesium-aluminum silicate (Cordierite ceramic), P.R.-67
 silicon nitride, ceramic, P.R.-100
 Raytheon 402B, V-3
 "Resimene" 803-A, IV-22
 Resin (polyester), EKONOL, P.R.-166
 Resinous Products Div., see Rohm and Haas Co.
 "Resinox" 7934, IV-20
 "Resinox" 10231, IV-18,109

 "Resinox" 10900, IV-18,110
 Resins, natural, IV-55,56
 Rex, Corp., IV-40; V-11,105
 Rex, William Brand, Div. of American Enka (now Brand-Rex Co.), P.R.-181-183
 "Rexolene" P, P.R.-183
 "Rexolite" 1422, IV-40; V-105;P.R.-181
 "Rexolite" 2101, V-11
 "Rexolite" 2200, P.R.-182
 Rezolin, Inc., IV-19
 "Rhyolite," P.R.-140
 Robertson, H. H., Co., IV-48,123; V-12,19
 "Rocketon," V-17
 Rocks, see Table of Contents of the Present Report
 Rogers Corp., VI-59-64; P.R.-184,185
 Rogers Corp. "Duroid" (1" thick sheet), P.R.-184
 "Duroid" 5870 (1966), P.R.-185
 Rogers Paper Mfg. Co., IV-60
 Rohm and Haas Co., IV-30,34,48,62, 122; V-12,111
 "Royalite" 149-11, M21982-1 and M22190, IV-53
 RTV-11, General Electric, P.R.-176
 Rubber Chemical Sales Department of Organic Chemicals Div., V-11,19
 Rubber, butyl (GR-I), IV-52
 Rubber, cellular, IV-51
 Rubber, cyclized, IV-51,52
 Rubber, GR-S (Buna S) and compounds, IV-52
 Rubber, Hevea and compounds, IV-51
 Rubber, natural, IV-51
 Rubber, nitrile, IV-53
 Rubber, silicone, IV-54,55,126; V-127-129, P.R.- 177
 Rubber Reserve Corp., IV-51,52
 Rubidium manganese fluoride, single crystal, MIT, Crystal Physics Lab., P.R.-49
 Rutgers University, School of Ceramics, V-4
 Rutgers' wallastonite E16, V-4
 Rutile, IV-2,4,77

 S-40 and S-60 resins, IV-39
 St. Regis Paper Co., Panelyte Division, IV-17,22
 Salts, granulated and fine flakes, Raytheon, P.R.-158
 Sand and resin mixtures, see epoxy, silicone, etc.

Sands

Desert, P.R.-143
Holliston, P.R.-144
Quartz, P.R.-135
Slattersville, P.R.-144
Soil, IV-14
Sandstone, almond, P.R.-140
"Santicizer" 9, IV-15
Sapphire, IV-72; V-1,26-28;
VI-2-6; P.R.-2-4
"Saran" B-115, IV-31
Sauereisen Cements Co., V-7
Sauereisen Cement No. 1, V-7
"Scotchcast" 221, P.R.-178
"Scotchply" Type 1001, V-16
"Scotchply" Type 1002, V-22;
VI-67
"Scotchply" XPM-107, V-22
"Scotch" tape No. 39, V-17
Sealing Wax, Red Express,
IV-58
Sealing compound, V-17
"Selectron" 5003 + glass, .
IV-47
"Selectron" 5084 monomer,
V-19
"Selectron" 5084 resin, V-13
Selenium, amorphous, IV-13
Selenium, multicrystalline,
IV-1
Service boards, John Manville's,
P.R.-158
Sharples Chemicals Div.,
Penn. Salt Mfg. Co., IV-63
Shawinigan Products Corp.,
IV-34
Sheet glass, P.R.-94
Shellac, natural Zinfo, pure C
garnet and garnet de-
waxed, IV-56
Shell Chemical Corp., IV-50;
V-16,116-125; VI-68-76;
P.R.-186,187
Shell Chemical "Epon" 828 +
PMDA epoxies, P.R.-186,187
Shell Development Co., IV-48-48
Shell Oil Co., IV-56,66
Silastics, 120, 125, 150, 152,
160, 167, 180, IV-54
181, IV-54,126
250, IV-54,126
6167, IV-55,126
6181, X4342, IV-55
XF6734, IV-55

Silastics (cont.)

7181, IV-55
RTV 501, 521, 1602, 5350,
S-6538, P.R.-168
Silica, fused 915c, IV-11,103;
V-70,71
Silica, slip-cast, Brunswick,
P.R.-95
Dynasil, P.R.-96
Silica fiber composites, P.R.-98,99
Silicate glasses, IV-9-11, 101,102;
V-5,62-69; VI-35-43; P.R.-89-94
Silicon, single crystal, intrinsic,
cubic, MIT, Crystal Physics Lab.,
P.R.-78
Silicon, single crystal, undoped,
Brown University, P.R.-78
Silicon carbide, multicrystalline,
Carborundum, P.R.-79
Silicon carbide with BeO, National
Beryllia Corp. "Carberlox,"
P.R.-80
Silicon dioxide, fused, IV-11,103;
V-70,71; P.R.-82-88
Silicon dioxide, natural quartz
mineral, Fort monmouth, P.R.-80,81
Silicon dioxide, sintered,
Brunswick slip-cast, P.R.-95
" " " with 2.5%
Cr₂O₃, P.R.-95
Corning Code 7941, P.R.-96
Corning multifilm glass, P.R.-96
Silica slip-cast, Dynasil, P.R.-96
Silicon dioxide fibers
Quartz fiber sample, Philco Ford,
AS-3DX-1R, P.R.-97
Silica fiber composites, Philco
Ford 1-XB-O-M, P.R.-98
AS-#DX 176-17, P.R.-98
Silica fiber composites in
aluminum phosphate matrix,
Whittaker Corp., P.R.-99
Silicon dioxide glasses
"Amersil" (clear, translucent),
P.R.-82
Corning 7940, P.R.-83
Dynasil 4000, P.R.-84
G.E. 101, clear, P.R.-85-87
"Spectrosil" A, P.R.-88
"Spectrosil" B, P.R.-88
"Vitreosil," optical grade, P.R.-88
"Vitreosil," commercial grade,
P.R.-88

Silicon dioxide, mixed silicate glasses, see also Glass
 Corning Lab. No. 119BUC, P.R.-89
 Corning Lab. Code 1723, P.R.-89
 Lancaster 7352, 7357, L1957, L9100, P.R.-89-92
 Owens-Corning X994, P.R.-93
 Owens-Illinois EE9 and EE 10, P.R.-93
 Pittsburgh Plate Glass Co., Plate glass, P.R.-94
 Sheet glass, P.R.-94
 Silicon nitride, ceramic
 Admiralty Labs., P.R.-100
 Raytheon, P.R.-100
 Union Carbide & Carbon, P.R.-101
 Silicon nitride, pyrolytic, P.R.-100
 Silicon nitrite alloy, V-6,79
 Silicone alloys C-1147 and C-1328, V-9
 Silicone fluids
 DC XF-6620, V-20
 SF96-40, IV-67; VI-86,87
 SF96-100 and SF96-1000, IV-67
 DC200 and DC500, IV-66
 DC550 and DC710, IV-67
 Silicone glass laminates, IV-26,27; V-9,93-95,100,101; VI-56,57
 Silicone grease, V-20
 Silicone laminate DC2105, V-9,94
 Silicone laminate DC2106, V-9,95
 Silicone molding compound XM-3, IV-26
 Silicone resin DC301, V-9,94
 Silicone resin DC996 and DC2101, IV-26
 Silicone resins, IV-25-27; V-9;VI-52-57
 Silicone resins with asbestos, V-9, 96,97
 Silicone resins with "Fiberglas," V-9, 93-95,98-101;VI-56,57
 Silicone rubber SE-450, IV-55; V-127
 SE-555, IV 55
 SE900, P.R.-177
 SE-977, IV-55; V-129
 RTV-11, P.R.-176
 Silicone rubbers, IV-54,55,126; V-127-129; P.R.-176-177
 Silicone varnish, IV-26; V-18
 Silver iodide, Pressed powder, MIT, Lab. Ins. Res., P.R.-102
 Sintered silicon dioxide, P.R.-95,96
 "Sintox," V-3
 Sippican Corp., The, P.R.-158, 188,192
 Sippican polystyrene foam, P.R.-188
 Sippican polyurethane foam, P.R.-188
 Sippican service boards, P.R.-158
 Snow, IV-1
 Soap, IV-60
 Socony Mobil Oil Co., Inc., IV-57,58
 Formerly Socony-Vacuum Oil Co., Inc.
 Soda silicate glass, MIT, Lab. Ins. Res., P.R.-93
 Sodium chloride, IV-2; P.R.-103
 Sodium chloride, aqueous solutions, IV-61
 Southern Alkali Corp., IV-48
 "Spectrosil" A, P.R.-88
 "Spectrosil" B, P.R.-88
 Sperry Gyroscope Co., V-18
 Spinel, P.R.-66
 Spodumene, P.R.-130-132
 Sponge Rubber Products Co., IV-19, 31,52
 Sprague Electric Co., IV-39
 Spruce Pine Mica Co., V-7
 Stanco Distributors, Inc., IV-65,66
 Standard Oil Co. of N.J., IV-58
 Standard Oil Development Co., see Enjay Co., Inc.
 Steak, beef, IV-60; P.P.-199
 Steatite bodies, IV-3,4,78-87; V-4,55-57; VI-34; P.R.-72-74
 Steatite Body 7292, IV-4,83
 Steatite Type 303,400, 410 and 452, IV-3,84-87
 Steatit-Magnesia A.G., P.R. 32,74
 Steatit-Magnesia A-18, P.R.-32-33
 Steatit-Magnesia Frequentia M, P.R.-74
 Sterling Varnish Co., The, V-18
 Sterling M50 varnish on paper, V-18
 Strontium fluoride, single crystal, MIT, Crystal Physics Lab., P.R.-106,107
 Strontium titanate, IV-5
 Strontium titanate and plastic mixtures, IV-43
 Stupakoff Ceramic and Mfg. Co., IV-6,101; V-3,4,50,51
 Div. of the Carborundum Co.
 Stupakoff 1510, V-3,51
 1540, V-3,50
 1542E, V-3
 1542P, V-3,50
 1550, V-4,50

"Stycast", HiK, LoK and
 TPM-3, V-11
 "Stypol" 16B monomer, V-19
 "Stypol" 16B resin, IV-48,
 123; V-110
 "Stypol" 16C resin, IV-48
 "Stypol" 16D resin, IV-48; V-12
 "Styraloy" 22, IV-38
 "Styramic" No. 18, IV-37
 "Styramic" HT, IV-42,43
 Styrene copolymers, cross-
 linked, IV-39,40,119;
 V-11,105
 Styrene copolymers, linear,
 IV-38,39,118,119
 Styrene dimer, IV-64
 Styrene N-100, dry and
 saturated with water,
 V-64
 Styrene-acrylonitrile co-
 polymer, IV-38,53,118
 "Styrofoam" 103.7, IV-37
 "Styron" C-176,411-A, 475,
 666 and 671, IV-36
 Suet, IV-60
 Sulfur, crystalline, IV-2
 sublimed, IV-2
 "Supramica" 500, V-7,79
 Sylgard 182, 184, D92.007,
 P.R.-168
 Syncor Products Co., V-6
 Synthetic basalt, P.R.-139

 "Tam Ticon" B, BS, C, MC,
 and S, IV-4,5,43
 "Tam Ticon" T-S, T-L and
 T-M, IV-4
 Tantalum oxide, ceramic,
 Ciba powder, fired at
 L.I.R., MIT, P.R.108
 Taylor Fibre Co., IV-18,27,111
 Taylor Grade GGG, IV-18,111
 Grade GSC and GSS, IV-27
 Tea, powder, P.R.-202
 "Teflon," IV-31-33,70; V-24,
 104; VI-58-64; P.R.-173-174
 "Teflon" 9033, P.R.-174
 "Teflon" FEP (1963), P.R.-173
 "Teflon" TFE (1964), P.R.-173
 "Teflon" TEF-7 (1964), P.R.-173
 "Teflon" TFE-6C (1964), P.T.-173
 "Teflon" T-100, P.R.-174
 "Teflon" 100X, P.R.-174

 "Teflon" + calcium fluoride,
 IV-32; V-10
 "Teflon" fiberglass laminates,
 GB-112T; IV-31,32; V-104; P.R.-164
 FLUORGLAS E, P.R.-167
 Duroids, VI-62-64; P.R.-184,185
 Tellite Corporation, P.R.-188
 Tellite 3A, P.R.-188
 "Tenite" I 008A H₂, H₄, M, MH,
 S and S₄, IV-24
 "Tenite" II 2054A H₂, H₄, MH, MS,
 S₂, S₄, IV-24
 Tennessee Eastman Corp., IV-24
 Tennessee Marble, Inc., IV-13
 Teresso V-78, P.R.-195
 Terphenyl, meta-, nona, ortho-,
 and para-, IV-15
 Terphenyls, chlorinated, IV-64
 Tetrachloroethylene, IV-62
 Tetra alkyd silicate ester, V-19
 Thallium bromide, IV-2,75
 Thallium bromide-chloride, IV-2,75;
 P.R.-109
 Thallium-bromide-iodide, IV-2,76;
 P.R.-109
 Thallium chloride, V-1; P.R.-109
 Thallium fluoride pressed powder,
 P.R.-109
 Thallium iodide, IV-2,74; P.R.-109
 Thermal American Fused Quartz Co.,
 P.R.-88
 Thermoplastic Composition 1766 EX
 and 3738, IV-58
 3767A, IV-59
 Thiokol Chemical Corp., IV-54
 "Thiokol" Type FA, PRI and ST, IV-54
 Thorium oxide, ceramic, Zircoa, P.R.-110,112
 MIT, Lab. Ins. Res., P.R.-113,114
 TI Pure R-200, IV-4
 Titanate ceramics, IV 3,6
 Titania and titanate bodies, IV-4-6,
 88-93
 Titanium Alloy Mfg. Div., National
 Lead Co., IV-4,5,42,43
 Titanium dioxide, rutile, IV-2,4,77
 Titanium dioxide ceramics, IV-4,5
 Titanium dioxide + plastic mixtures,
 IV-33,42
 Tobe Deutschmann, VI-78-83
 Toluene sulfonamides, mixtures of
 ortho- and para-isomers, IV-15
 Topaz, P.R.-133,134
 Tourmaline, P.R.-134

"Transil" Oil 10C, IV-65
 Trichlorobenzenes, mixture
 of isomeric, IV-64
 Trichloronaphthalenes,
 mixture of isomeric, IV-64
 α -Trinitrotoluene, IV-15

 UDP 333 Liquid, P.R.-197
 "Ultron" Wire Compound UL300,
 UL1004 and UL24001, IV-30
 Union Carbide & Carbon Corp.,
 V-18; P.R.-4,50,51,54-57,
 66,101,180,181
 Union Carbide boron nitride,
 hot-pressed, Grade HD0056,
 HD0086, HD0092, HD0093,
 HD0094, HBN, HBR, P.R.-54-57
 cold-pressed, P.R.-57
 pyrolytically deposited,
 "Boralloy," P.R.-50,51
 pyrolytic laminate, P.R.-54
 Union Carbide magnesium aluminate
 (spinel), P.R.-66
 Union Carbide "Polysulfone,"
 P.R.-189
 Union Carbide silicon nitride,
 ceramic, P.R.-101
 Union Carbide R-63 Varnish,
 V-18
 Urea-formaldehyde resins, IV-23
 U.S. Army Engineering Research
 and Dev. Lab., Fort
 Belvoir, Va., IV-2,74-76; VI-77
 U.S. Army Res. and Dev. Labs.,
 Fort Monmouth, N.J., P.R.-80,81
 U.S. Bureau of Fisheries,
 mullet oil, P.R.-197
 U.S. Ceramic Tile Co., see
 Diamondite Products Div.
 U.S. Gasket Co., IV-32,33
 U.S. Industrial Chemical Co., IV-62
 U.S. National Bureau of Standards,
 IV-40; P.R.-20
 U.S. Peroxygen Division, Argus
 Chemical Corp., P.R.-197
 U.S. Peroxygen USP 333 Liquid,
 P.R.-197
 U.S. Polymeric Chemicals, Inc.,
 V-9
 U.S. Rubber Co., IV-31,40,52,
 53,56
 U.S. Sonics, P.R.-75
 U.S. Sonics magnesium titanate,
 multicrystal, P.R.-75

U.S. Stoneware Co., The, V-21,51;
 VI-20,21; P.R.-34,35
 U.S. Stoneware Al_2O_3 , A-212, A-216,
 A-312, 610, Std. 30500F, P.R.-34,35
 U.S. War Department, Picatinny
 Arsenal, IV-15

 Vanadium oxide, pressed powder,
 P.R.-114
 Varnished glass cloth, V-18
 Varnished linen tape, V-17
 Varnished paper, V-18
 "Vaseline," IV-65
 "Vibron" 140 and 141, IV-40
 Victor Chemical Works, IV-48
 "Vinylite" QYNA, VG-5544 and VG-5901,
 IV-28
 "Vinylite" VG-5904, VYHH, VYNS, and
 VYNW, IV-29
 "Vinylite" VU-1900, IV-29,70
 2-Vinylpyridine-styrene copolymer,
 IV-46
 "Vistawax," IV-59
 "Vitreosil," commercial grade, P.R.-88
 "Vitreosil," optical grade, P.R.-88
 VUL-CUP, P.R.-196

 Wallace & Tiernan, Inc., P.R.-197
 Wallace & Tiernan "Lupersol" 101,
 2,5-dimethyl-2,5-di(*t*-butylperoxy)
 hexane, P.R.-197
 War Dept., Picatinny Arsenal, see
 U.S. War Department
 Water, conductivity, IV-61
 Wax 3760, IV-59
 Wax Compound F-590 and No. 1340, IV-59
 Wax S-1167 and S-1184, IV-59
 Waxes, IV-56-59; V-16,17
 Weber, Hermann, and Co., IV-51
 "Wesgo" AL-300, V-4,52
 "Wesgo" AL-1009, V-4
 Western Gold & Platinum Works,
 V-4,52; P.R.-36,37
 Western Gold & Platinum aluminum oxide,
 AL-300, AL-300 (modified), AL-400,
 AL-500 (multicryst.), AL-995, AL-1009,
 P.R.-36,37
 Westinghouse Electric Corp.,
 Research Lab., IV-18,19,22
 Whittaker Corp., P.R.-99
 Whittaker silica fiber composites,
 P.R.-99
 Wollastonite, V-4,58
 Wood, IV-59; P.R.-193
 Wood, pine board, Sippican,
 P.R.-193

Wood, birch plywood, Sippican,
P.R.-193
fir plywood, Sippican, P.R.-193
Marinite board, Sippican,
P.R.-193

Ytterbium ferrite, VI-28-31
Yttrium oxide, ceramic, Zircoa,
P.R.-116
Yttrium oxide, single crystal,
MIT, Lab. Ins. Res., P.R.-115

Zinc ferrite (MIT samples), V-158
Zinc-magnesium-manganese ferrite
(MIT samples), V-141,182
Zinc-nickel ferrite (MIT samples),
V-144-157

Zinc oxide, single crystal,
Airtron Div., Litton
Industries, P.R.-117
Zinsser, Wm., and Co., IV-55,56,
Zircoa ceramics:

"C", P.R.-118
Thorium oxide, P.R.-110-112
Y-790, P.R.-64
Y-904, P.R.-119
Y-1362, P.R.-120,121
"Zircolite," ceramic, P.R.-122
Zircon, P.R.-123-125
Zirconia,

Zircoa "C", Y-904, Y-1362,
P.R.-118-121
"Zircolite," P.R.-122
Zirconium oxide ceramics,
see Zirconia

Zirconium silicate (zircon),
ceramic, IV-6,94,95; V-5,
59-61
single crystal, P.R.-123-125
"Zitex," P.R.-166
Zophar Mills, Inc., IV-59