

UNCLASSIFIED

AD NUMBER
AD820805
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; SEP 1967. Other requests shall be referred to Air Force Weapons Lab., Kirtland AFB, NM 87117.
AUTHORITY
AFWL ltr, 30 Nov 1971

THIS PAGE IS UNCLASSIFIED

NOTICE: When Government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

UNCLASSIFIED

AD 820805

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION ALEXANDRIA VIRGINIA



UNCLASSIFIED

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
Springfield, Va 22151

This document has been reproduced
for public release and sale
without restriction in its entirety

UNCLASSIFIED

DDC REPORT BIBLIOGRAPHY SEARCH CONTROL NO. /FAYE2

AD-820 805 20/11
STANFORD RESEARCH INST MENLO PARK CALIF POULTER LABS

EQUATION OF STATE OF SOLIDS. II. ALUMINUM AND
TEFLON.

(U)

DESCRIPTIVE NOTE: TECHNICAL REPT. 6 MAY 66-6 MAY 67,
SEP 67 52P ANDERSON, G. D. ;FAHRENBRUCH,

A. L. ;

CONTRACT: AF 29(601)-7214
PROJ: AF-5710, SRI-FGU-6047
MONITOR: AFWL TR-67-43

UNCLASSIFIED REPORT
DISTRIBUTION: NO FOREIGN WITHOUT APPROVAL OF AIR
FORCE WEAPONS LAB., ATTN: WLRP. KIRTLAND
AFB, N. MEX. 87117.

DESCRIPTORS: (•EQUATIONS OF STATE, •ALUMINUM),
(•HALOCARBON PLASTICS, EQUATIONS OF STATE),
SHOCK WAVES, PRESSURE, VOLUME, STRESSES,
EXPLOSION EFFECTS, POWDER METALS, PROJECTILES,
VELOCITY, HELIUM, CODING, COMPUTERS, SOLIDS,
TARGETS

(U)

IDENTIFIERS: ALUMINUM ALLOY 2024, GAS GUNS,
HUGONIOTS, TEFLON

(U)

THE PRESSURE-VOLUME-ENERGY (P-V-E) EQUATION
OF STATE OF ALUMINUM AND TEFLON HAS BEEN
INVESTIGATED. THE P-V-E EQUATION OF STATE OF
A MATERIAL IS NEEDED TO SOLVE NONREACTIVE FLOW
PROBLEMS USING COMPUTER CODES SUCH AS PUFF.
EXPLOSIVELY INDUCED SHOCK WAVES HAVE BEEN USED TO
GENERATE HUGONIOT CURVES FOR SOLID AND POROUS
SPECIMENS OF ALUMINUM AND TEFLON. FOR ALUMINUM
IT IS FOUND THAT THE FOLLOWING P-V-E EQUATION
OF STATE CAN REPRODUCE THE EXPERIMENTAL DATA QUITE
NICELY: $P = BE + G(V)$ B IS A CONSTANT AND
G IS AN ARBITRARY FUNCTION OF V. THIS
CORRESPONDS TO $\gamma/V = \text{CONSTANT}$, WHERE γ IS
GRUNEISEN'S RATIO. BECAUSE OF THE SPREAD OF THE
TEFLON DATA IN THE P-V PLANE, IT WAS NOT
POSSIBLE TO OBTAIN A P-V-E FIT. HOWEVER, THE
DATA IMPLY THAT GRUNEISEN'S RATIO VARIES FROM ABOUT
0.7 TO 1.4 AT HIGH PRESSURES. GAS GUN EXPERIMENTS
USING MANGANIN WIRE PRESSURE RECORDINGS WERE
PERFORMED. SOUND SPEEDS DEDUCED FROM THESE RECORDS
IMPLY THAT TEFLON BECOMES ANOMALOUSLY STIFF UNDER
SHOCK. (AUTHOR)

(U)

UNCLASSIFIED

/FAYE2

AD820805

FILE COPY

AFWL-TR-67-43

**EQUATION OF STATE OF SOLIDS
II
ALUMINUM AND TEFLON**

G. D. Anderson
A. L. Fahrenbruch
Stanford Research Institute
Poulter Laboratories
Menlo Park, California 94025
Contract AF 29(601)-7214

TECHNICAL REPORT NO AFWL-TR-67-43

September 1967

AIR FORCE WEAPONS LABORATORY
Research and Technology Division
Air Force Systems Command
Kilgus Air Force Base
New Mexico

OCT 10 1967

AFWL-TR-67-43

AFWL-TR-67-43

EQUATION OF STATE OF SOLIDS

II

ALUMINUM AND TEFLON

G. D. Anderson
A. L. Fahrenbruch

Stanford Research Institute
Poulter Laboratories
Menlo Park, California 94025
Contract AF 29(601)-7214

TECHNICAL REPORT NO AFWL-TR-67-43

This document is subject to special export control and each transmittal to foreign governments or foreign nationals may be made only with prior approval of AF (WEP), Kirtland AFB, N. M. 87117. Distribution is limited because of the technology discussed in report.

FOREWORD

This report was prepared by the Poulter Laboratories, Stanford Research Institute, Menlo Park, California, under Contract AF 29(601)-7214. The research was performed under Program Element 6.16.46.01D, Project 5710, Subtask 15.018, and was funded by the Defense Atomic Support Agency (DASA).

Inclusive dates of research were 6 May 1966 to 6 May 1967. The report was submitted 11 July 1967 by the Air Force Weapons Laboratory Project Officer, Captain Raymond J. Lawrence, Jr. (WLRP).

The project supervisor was Dr. G. P. Anderson and the project leader was Mr. A. L. Fahrenbruch. The authors wish to thank Drs. D. G. Doran and M. Cawperthwaite for their contributions through discussions on equations of state, and Miss B. V. Loo for shot analysis and computations.

Contractor's report number is SRI Project FCI-6047.

This technical report has been reviewed and is approved.

John T. Vela
RAYMOND J. LAWRENCE, JR.
Captain, USAF
Project Officer

Harry F. Kizzo
HARRY F. KIZZO
Major, USAF
Chief, Physics Branch

Claude K. Stambaugh
CLAUDE K. STAMBAUGH
Colonel, USAF
Chief, Research Division

ABSTRACT

(Distribution Limitation Statement No. 2)

The pressure-volume-energy (P-V-E) equation of state of aluminum and Teflon has been investigated. The P-V-E equation of state of a material is needed to solve nonreactive flow problems using computer codes such as PUFF. Explosively induced shock waves have been used to generate Hugoniot curves for solid and porous specimens of aluminum and Teflon. For aluminum it is found that the following P-V-E equation of state can reproduce the experimental data quite nicely:

$$P = bE + g(V)$$

b is a constant and g is an arbitrary function of V . This corresponds to $\gamma = \text{constant}$, where γ is Gruneisen's ratio. Because of the spread of the Teflon data in the P-V plane, it was not possible to obtain a P-V-E fit. However, the data imply that Gruneisen's ratio varies from about 0.7 to 1.4 at high pressures. Gas gun experiments using manganin wire pressure recordings were performed. Sound speeds deduced from these records imply that Teflon becomes anomalously stiff under shock.

CONTENTS

Section	Page
I INTRODUCTION	1
II EXPERIMENTAL TECHNIQUE	3
1. Explosive Technique	3
2. Gas Gun Technique	3
3. Specimen Materials	3
III EXPERIMENTAL RESULTS AND ANALYSIS	9
1. Aluminum	9
2. Teflon	14
IV CONCLUSIONS AND SUMMARY	29
Appendix	33
References	35
Distribution	36

This page intentionally left blank.

ILLUSTRATIONS

Figure

Figure		Page
1	Cross-Section View of Target Assembly Mounted on Muzzle of Gas Gun	4
2	Target Assembly	6
3	Shock Velocity vs. Particle Velocity for Porous Aluminum	11
4	Hugoniot for Aluminum	12
5	Shock Velocity vs. Particle Velocity for Teflon	16
6	Teflon Hugoniot Data	17
7	Gage Record and Wave Profile for Shot 12,872-- Second Gage	20
8	Gage Record and Wave Profile for Shot 12,897-- (a) First Gage (b) Second Gage	21 22
9	Gage Record and Wave Profile for Shot 12,937-- (a) First Gage (b) Second Gage	24 25
10	Gage Record and Wave Profile for Shot 12,873-- (a) First Gage (b) Second Gage	26 27

TABLES

Table		Page
I	Solid and Porous Aluminum Hugoniot Data	10
II	Teflon Hugoniot Data from Explosive Tests	15
III	Teflon Hugoniot Data from Gun Shots	18
IV	Teflon Sound Speed Data	30

SECTION I
INTRODUCTION

In order to predict the shock wave propagation and flow resulting from a stress suddenly applied on the surface of a material, it is necessary to know the pressure-volume-energy (p-v-E) equation of state of the material under consideration. Equations of state for use in the PUFF code are of particular interest. It has been the practice to use a Mie-Grüneisen form of equation of state to describe solids. This equation of state is derived by using an assembly of harmonic oscillators as a model to describe solids. It is assumed that the logarithmic change of frequency with volume is the same for all frequencies and this leads to Grüneisen's ratio, which depends upon specific volume (Ref. 1). The purpose of this work has been to study the range of pressures and volumes for which it is valid to apply the Mie-Grüneisen equation of state to solids and to determine Grüneisen's ratio.

The work reported here is a continuation of work described in Reference 2. Specifically, the work has been aimed at obtaining equation of state data on aluminum and Teflon,* using shock wave compression of porous specimens. The emphasis in the earlier work was on aluminum. The present work has concentrated on generating more Teflon data although some porous aluminum data were obtained to supplement the earlier data. The new aluminum data slightly shift one of the Hugoniot's that was obtained earlier.

The new high-pressure Teflon data are in good agreement with those obtained earlier. In addition to the high pressure data from explosive tests, some lower pressure data from gas gun experiments are presented. The low pressure data include manganin wire gage measurements of stress profiles at different depths in the target material.

* Trademark, E. I. du Pont de Nemours and Co.

SECTION II
EXPERIMENTAL TECHNIQUE

1. Explosive Technique

The explosive technique used to generate the high pressure aluminum and Teflon data is described in detail in Ref. 2. The technique consists of explosively accelerating a flat metal plate that impacts a 2024 aluminum driver plate upon which the samples are mounted. Measurements are made of the free-surface velocity of the aluminum driver plate and of the shock velocity through the sample. These data, combined with the loading and unloading curves in the pressure-particle velocity plane for the 2024 aluminum, are sufficient to compute Hugoniot points for the sample material using the impedance match technique (Ref. 3). In this technique, it is assumed that a steady state plane shock wave exists in the sample material and in the 2024 aluminum driver plate. Experiments on samples of varying thickness indicate that this assumption is valid for homogeneous samples if care is taken to prevent side and rear rarefactions from overtaking and interacting with the shock. The assumption is more questionable in very heterogeneous media such as granular or porous materials. The data have been treated here assuming steady state.

All measurements of shock and free-surface velocity were made optically by using a rotating mirror streak camera. The present data were obtained on 70-mm film using a Beckman and Whitley Model 770 camera. This camera has a maximum writing speed of 10 mm/ μ sec as compared to a maximum of 3.84 mm/ μ sec for the 35-mm-camera used in the earlier work.

2. Gas Gun Technique

Low-pressure experiments on Teflon were performed using a 2-1/2-inch-diameter gas gun projectile to generate shock waves. The projectile head is made either of Teflon to match the target or of 2024 aluminum. A schematic diagram of the shot assembly mounted at the muzzle of the gun is shown in Fig. 1. The projectile is accelerated down the evacuated

This page intentionally left blank.


gun barrel by helium from a high pressure reservoir. The projectile velocity is measured near the muzzle of the barrel by a linear array of four pins spaced at intervals of one-tenth foot. The arrival of the projectile is also detected by three radial velocity pins placed in front of the specimen impact surface. Four tilt pins, passing through the target in a square array at 90° intervals, record the actual impact and provide a measure of the nonsimultaneity of impact (tilt). Tilt is minimized by carefully preparing flat target and projectile faces and aligning the target face perpendicular to the axis of the gun barrel. The target alignment technique has been described by Linde and Schmidt (Ref. 3).

Stress-time profiles in the target were recorded using manganin wire gages. Two gages were mounted in each target assembly as shown in Fig. 2. One gage wire is mounted on the impact surface and is covered by either a 0.001-inch layer of Mylar or a thin Teflon shim. The second gage wire is placed between two Teflon disks, which are bonded together with a thin layer of epoxy. In making a stress measurement, a constant current is passed from a triggered power supply through the piezoresistive element from terminal A to A' (Fig. 2). The initial resistance and the change in resistance of the element due to passage of the wave are measured by recording the voltage B-B' as a function of time. The ratio of the change in resistance to the initial resistance (this is equivalent to the ratio of the change in voltage to the initial voltage for a constant current) is proportional to the stress. A detailed description of the operation of the gage is given in Ref. 4.

3. Specimen Materials

The porous aluminum specimens were cold pressed to the desired density from Reynolds No. 40 atomized aluminum powder, which is greater than 99 percent pure aluminum. For specimens of porosity $m = 1.4$ and $n = 1.7$,

* Porosity m is defined by $m = c_0/c_{app}$ where c_0 is the crystal density at standard conditions and c_{app} is the apparent density under the same conditions






FIG 2 TARGET ASSEMBLY

the powder was screened and only those particles less than 200 μ were used. The specimens were quite strong mechanically, machinable, and easily handled. Specimens of porosity $m = 2.0$ were made of powder between 200 μ and 300 μ . These were somewhat more fragile. The raw material and specimen preparation were reported in Ref. 2. Specimens were nominally 1/8 inch thick by 1 inch in diameter.

The solid and porous Teflon were obtained from the Avco Corporation, where low pressure work on aluminum and Teflon was also performed. The preparation of these samples is described in Ref. 5.

SECTION III
EXPERIMENTAL RESULTS AND ANALYSIS

1. Aluminum

The Hugoniot data for solid and porous aluminum are presented in Table I. All of the data reported in Ref. 2 are included so that Table I is a complete summary. The data for porous aluminum are plotted in the shock velocity-particle velocity plane in Fig. 3. The straight lines in the figure are drawn as guides and do not represent fits to the data. The Hugoniots in the pressure-volume plane are presented in Fig. 4 (the labels $t = 3/16$ in. and $t = 3/8$ in. refer to the sample thickness). The Hugoniot for solid aluminum was taken from the work of Al'tshuler et al. (Ref. 6). They quote a value of 2.71 g/cm^3 for the initial density of aluminum. To make their Hugoniot comparable to the data reported here on aluminum of initial density 2.70 g/cm^3 , each of their volumes at a given pressure was changed by a factor of $1.1/2.70$. This maintains the shape of the curve but translates it slightly to the right, i.e., toward larger specific volumes. The solid Hugoniot curve was then fitted by

$$\Gamma_H = 16899.5 - 134327.5V + 363023V^2 - 333405V^3 \quad (1)$$

where V is specific volume in cm^3/g and P_H is Hugoniot pressure in kilobars. To fit the porous aluminum pressure-volume ($P-V$) data, smooth curves were drawn through the points. From these curves and the solid aluminum Hugoniot, the internal energy as a function of pressure at a given volume was computed by using the Hugoniot energy relation

$$E_H = E_0 + (1/2)P_H(mV_0 - V) \quad (2)$$

where m is the porosity. The values of the initial internal energy E_0 and the initial specific volume V_0 were taken as $1.66 \times 10^5 \text{ ergs/gm}$ and

Table 1
SOLID AND POROUS ALUMINUM HUGONIOT DATA

Shot No.	Initial Volume (cm ³ /gm)	Shock Velocity (mm/μsec)	Particle Velocity (mm/μsec)	Pressure (kbar)	Final Volume (cm ³ /gm)	Internal Energy Change (10 ⁹ erg/gm)
m = 1.0						
11.477	0.370	7.31	1.45	286	0.297	10.65
11.570	0.370	7.75	1.80	377	0.284	16.21
11.563	0.370	8.77	2.46	583	0.266	30.31
11.460	0.370	9.06	2.58	633	0.265	33.23
11.562	0.370	9.13	2.71	667	0.260	36.56
m = 1.4						
11.477	0.519	5.08	1.88	154	0.328	17.57
12.776	0.518	5.17	1.89	189	0.328	17.95
12.791	0.518	5.36	1.84	191	0.339	17.09
12.283	0.519	6.43	2.45	334	0.321	30.09
12.535	0.518	6.83	2.70	357	0.313	36.59
12.908	0.518	6.90	2.77	368	0.310	38.27
10.591	0.520	7.19	3.03	418	0.299	46.18
10.562	0.521	7.79	3.42	511	0.283	58.25
12.536	0.521	7.97	3.45	528	0.296	59.40
m = 1.7						
11.155	0.629	5.43	2.43	210	0.347	29.61
11.286	0.631	5.82	2.67	246	0.341	35.67
11.062	0.629	5.93	2.69	254	0.344	36.19
10.875-1	0.630	6.58	3.05	319	0.338	46.57
10.926-2	0.631	6.50	3.06	316	0.333	46.76
10.926	0.631	6.83	3.20	347	0.335	51.35
11.330	0.631	6.90	3.25	355	0.334	52.72
10.591	0.633	6.91	3.26	356	0.334	53.22
10.894	0.637	7.29	3.44	397	0.333	58.95
11.505	0.631	7.49	3.58	426	0.330	64.11
10.592	0.635	7.55	3.66	436	0.327	67.14
m = 2.0						
11.155	0.741	5.09	2.58	177	0.365	33.19
11.286	0.741	5.57	2.82	212	0.364	33.85
11.062	0.741	5.64	2.85	218	0.367	40.76
10.926	0.741	5.72	3.37	305	0.369	56.73
11.330	0.740	6.79	3.41	313	0.369	58.06
10.894	0.741	7.16	3.60	348	0.368	64.50
11.379	0.744	7.29	3.85	377	0.351	74.08
11.305	0.741	7.32	3.78	373	0.360	71.05




FIG 3 SHOCK VELOCITY vs PARTICLE VELOCITY FOR POROUS ALUMINUM




FIG. 4 HUGONIOTS FOR ALUMINUM

0.370 cm³/gm, respectively. As can be seen from Fig. 4, a maximum of three energy-pressure points can be computed at a given volume in the volume range where the Hugoniot for $m = 1$, 1.4, and 1.7 overlap.

Several points can be computed near $V = V_0$ from the Hugoniot for $m = 2$ 0. Plots of the energy vs. pressure at constant volume are straight lines, indicating that $(\partial P/\partial E)_V$ is a function only of volume: furthermore, the fact that all slopes are nearly the same indicates that $(\partial P/\partial E)_V$ is nearly constant. The energy-pressure-volume equation of state data can then be fitted by a form

$$P = bE - g(V) \quad (3)$$

where $b = (\partial P/\partial E)_V$, a constant, and g is an arbitrary function of V . From the pressure-energy plots, an average value of $b = 5.15$ gm/cm³ was obtained. The function $g(V)$ was computed by substituting Eqs. (1) and (2) into Eq. (3) for P and E , respectively. A fit for $g(V)$ was then found to be given by

$$g(V) = 8721.138 - 66012.96V + 171688.7V^2 - 154117.1V^3 \quad (4)$$

where V is in cm³/gm and $g(V)$ is in kilobars. The Hugoniot curves drawn in Fig. 4 were generated from the equation of state given by Eq. (3) with $b = 5.15$ gm/cm³ and $g(V)$ given by Eq. (4). This form of the equation of state is a Mie-Grüneisen equation with γ/V a constant, where γ is Grüneisen's ratio.

The Hugoniot curves in the pressure-volume plane for the various porosities are given by

$$P_H(V) = \frac{bE_0 + g(V)}{1 - \frac{\gamma}{2}(mV_0 - V)} \quad (5)$$

The minimum volume to which a porous material can be compressed is given by

$$V_{\min} = mV_0 - \frac{2}{b} \quad (6)$$

Setting $V_{\min} = V_0$ in Eq. (6) shows that the Hugoniot of aluminum of porosity $m = 2.05$ would be a vertical line passing through $V_0 = 0.370 \text{ cm}^3/\text{g}$. The Hugoniot curves for $m = 1.4, 1.7$, and 2.0 drawn in Fig. 4 were generated by Eq. (5). With the exception of the highest pressure point for $m = 2.0$, Eq. (5) seems to fit the data quite well.

A fit to the data using $\mu = (\rho/\rho_0 - 1)$ as a variable is discussed in the Appendix.

2. Teflon

The Hugoniot data for Teflon obtained from the explosive tests are presented in Table II. Plots of the data in the shock velocity-particle velocity plane and the pressure-volume plane are presented in Figs. 5 and 6, respectively. The four lowest pressure points for solid Teflon on Figs. 5 and 6 are from gas gun shots (Table III). These four points and the lowest pressure explosive data point for solid Teflon exhibit a slightly steeper slope in the shock velocity-particle velocity plane than do the remaining points. This change in slope produces the cusp shown by the dashed line in the pressure-volume diagram. However, the lowest pressure explosive data point is questionable because the optical record was poor, and so the cusp is shown as a dashed line to indicate that not too much significance should be attached to it.

Since the Hugoniot data for the two porosities of Teflon ($m = 1.42$ and $m = 2.77$) do not overlap in volumes, only two energy-pressure points can be computed for any one volume. The uncertainties in the volume at a given pressure on the Hugoniots of porous Teflon are also quite large. Values of the average Gruneisen ratio as calculated from the offsets of the Hugoniots in Fig. 6 run from 1.2 to 1.4 when calculated between the solid and $m = 2.77$ Hugoniots. Quite large internal energy increases occur along the Hugoniot of porosity $m = 2.77$, and it is quite possible that some decomposition takes place.

The gage records for gas gun shots (Table III) generally indicate a lower pressure than that computed by the impedance match technique using the projectile velocity and the shock velocity in the sample.

Table II
TEFLON HUGONIOT DATA FROM EXPLOSIVE TESTS

Shot No.	Initial Density (gm/cm ³)	Shock Velocity (mm/μsec)	Particle Velocity (mm/μsec)	Pressure (kbar)	Final Volume (cm ³ /gm)	Energy Increase (10 ⁹ erg/gm)
$m = 1.00$						
12,495	2.157	3.529	1.075	82.0	0.3224	5.78
12,778	2.168	5.120	1.835	203.0	0.2959	16.78
11,570	2.169	5.589	2.215	269.0	0.2782	24.58
12,284	2.175	5.628	2.205	269.5	0.2760	24.75
12,283	2.170	5.994	2.415	314.0	0.2752	29.56
12,535	2.169	6.360	2.685	368.0	0.2678	35.54
11,563	2.163	6.830	2.945	435.0	0.2629	43.37
11,460	2.172	7.105	3.080	476.0	0.2608	47.50
11,562	2.163	7.262	3.200	504.0	0.2582	51.35
12,536	2.169	7.543	3.375	552.5	0.2547	57.26
$m = 1.42$						
12,495	1.533	2.639	1.255	50.5	0.3442	7.77
12,778	1.524	4.354	2.120	140.5	0.3366	22.45
11,570	1.517	4.909	2.555	190.3	0.3160	32.64
12,284	1.525	4.952	2.535	191.5	0.3201	32.13
12,535	1.516	5.774	3.065	268.0	0.3094	46.92
11,563	1.524	6.207	3.373	319.0	0.2995	56.87
11,562	1.515	6.683	3.660	371.0	0.2981	66.97
12,536	1.516	6.992	3.855	408.5	0.2959	74.28
$m = 2.77$						
12,495	0.7967	2.048	1.420	23.0	0.3849	10.00
12,778	0.7606	3.741	2.493	71.0	0.4385	31.10
11,570	0.7828	4.374	2.985	103.0	0.4757	44.87
12,284	0.7782	4.340	2.980	100.8	0.4027	44.46
12,535	0.7870	5.129	3.600	146.0	0.3788	65.13
11,563	0.7782	5.646	3.985	175.5	0.3780	79.58
11,562	0.7828	6.086	4.335	207.0	0.3676	84.12
12,536	0.7869	6.419	4.565	231.0	0.3670	104.1




FIG. 5 SHOCK VELOCITY vs PARTICLE VELOCITY FOR TEFLON




FIG. 6 TEFLON HUGONIU DATA

Table III

TEFLON RUONINOT DATA FROM GUN SHOTS

Shot No.	Projectile		Shock Velocity (mm/ μ sec)	Pressure (kbar)			Particle Velocity (mm/ μ sec)	Volume ^b (cm ³ /gm)
	Velocity (mm/ μ sec)	Material		Impedance Match	Gage 1	Gage 2 ^a		
12,872	0.417	Teflon	1.92	8.7	8.6 ^c	8.1	0.208	0.410
12,897	0.311	Aluminum	2.00	10.8	8.8 ^d	9.1	0.247 ^e	0.403
12,857	0.741	Teflon	2.17	17.6	15.9 ^c	15.6	0.370	0.342
12,873	0.781	Aluminum	2.67	33.5	34.2 ^f	29.8	0.578 ^e	0.361

^aGage 2 is approximately 6.4 mm behind Gage 1 except Shot 12,897, in which it is 4.76 mm from Gage 1.

^bFrom shock and particle velocities.

^cGage on impact surface covered by 1 mil Mylar.

^dGage 1.5 mm from impact surface.

^eFrom impedance match using measured shock velocity.

^fGage 1.7 mm from impact surface.


In Shot 12,872 the projectile head was a 3.03 mm disk of Teflon backed by aluminum. The Teflon target had one gage on the impact surface covered by a 0.001-inch layer of Mylar and a second gage 6.44 mm from the impact surface. Due to a timing error, the fast sweep oscilloscope record from the first gage was lost. A plot of the record from the second gage is shown in Fig. 7. This gage record indicates a double wave structure with a 2 to 3 kbar wave leading the 8 kbar peak wave by about 0.15 μ sec. This structure was also observed on the long duration records of the second gage but not on the long duration record of the first gage, and thus exhibits the properties of a propagating double wave. Upon impact a shock is induced in the Teflon projectile head, which propagates back and reflects from the aluminum projectile as a second shock into the Teflon. The arrival of this second shock at the deeper gage produces the second pressure rise seen at about 2.25 μ sec after arrival of the first wave. The final stress behind this wave is 12.3 kbar and a distance-time construction of the wave and particle paths indicates that the velocity of the reflected shock is about 3 mm/ μ sec with respect to the material.

For Shot 12,897 the projectile head was of 2024 aluminum. The peak pressures recorded by the two gages were somewhat higher than in Shot 12,872. The wave profiles, shown in Fig. 8, do not exhibit the "precursor" structure that was seen in the preceding shot (12,872). Both gage records show a very rapid pressure rise to 7 or 8 kbar and then a more gradually rounded rise to the peak stress. Similar behavior has been observed in polyethylene (Ref. 7). The decrease in pressure late in the gage record is due to the arrival of the rarefaction originating at the rear surface of the projectile. The time of arrival of this rarefaction indicates a sound speed of 2.82 mm/ μ sec at about 9 kbar in Teflon.

FIG. 8 GAGE RECORD AND WAVE PROFILE FOR SHOT 12.897

(a) FIRST GAGE

12



Reproduced from
best available copy.

FIG. 7 GAGE RECORD AND WAVE PROFILE FOR SHOT 12.872 SECOND GAGE

SHOWN FROM PROJECTILE

12



Shot 12,857 had a Teflon projectile head, which was 3.12 mm thick, backed by 2024 aluminum. The Teflon target had one gage on the surface covered by 0.001 inch Mylar and a second gage imbedded in Teflon 6.47 mm from the impact surface. The oscilloscope records and wave shapes from these records are plotted in Fig. 9. A polarization signal, possibly from shocking the Mylar cover, is observed before the pressure rise on the record from the first gage. Both gages record some oscillations before settling down to record the final peak pressure. However, the overshoot of pressure indicated by the first gage is not recorded by the second gage. Again the arrival of the reflected shock originating at the interface between Teflon and aluminum on the projectile is seen to arrive at the first gage about 2.25 μ sec after the first wave and at the second gage at about 0.8 μ sec after the arrival of the first wave. Recall that the time bases on the gage records begin with the arrival of the first wave at the gage position.

In the highest pressure gun shot, 12,873, an aluminum projectile struck the Teflon target. The oscilloscope records and plots of the wave shapes are presented in Fig. 10. The records indicate a rounding of the wave front and a decrease in peak pressure amplitude as the wave propagates from gage 1 to gage 2. The small oscillation that appears on the wave front was observed in varying degrees on all but the lowest pressure shot. Both gage records show a decrease in pressure resulting from the arrival of the rarefaction originating from the back surface of the projectile. From the time of arrival of this rarefaction a sound speed of 3.77 mm/ μ sec at 34 kbar was computed. Note in the record from gage 2 the arrival of a shock reflected from the potting compound behind the Teflon target.

FIG. 8 (Continued)

(b) SECOND GAGE

FIG. 9 (Concluded)

(b) SECOND GAGE

SHOCK FROM PROJECTILE
ARRIVAL OF REFLECTED

25

FIG. 9 GAGE RECORD AND WAVE PROFILE FOR SHOT 12,857

(a) FIRST GAGE

SHOCK FROM PROJECTILE
ARRIVAL OF REFLECTED

26

FIG 10 (Concluded)

(b) SECOND GAGE

REFLECTION FROM
BACK OF ALUMINUM
PROJECTILE
REFLECTED SHOCK
FROM POTTING
COMPOUNDS

27

FIG 10 GAGE RECORD AND WAVE PROFILE FOR SHOT 12873

(a) FIRST GAGE

REFLECTION FROM BACK OF AL PROJECTILE
ELASTIC RELIEF
PLASTIC RELIEF

26

SECTION IV

CONCLUSIONS AND SUMMARY

The pressure-volume-energy data for aluminum in the region of the P-V plane bounded by the Hugoniot of solid aluminum to 700 kbar and the vertical line through $V_0 = 0.370 \text{ cm}^3/\text{g}$ up to about 400 kbar are well represented by a simple Mie-Grüneisen equation of state of the form

$$P = bE + g(V) \quad (3a)$$

where b is a constant equal to 5.15 gm/cm^3 . The function $g(V)$ is a cubic in V given by

$$g(V) = 8721.138 - 66012.96V + 171668.7V^2 - 154117.1V^3 \quad (4a)$$

This form of the Mie-Grüneisen equation in which the pressure is directly proportional to the internal energy at a given volume implies that Grüneisen's ratio $\gamma = V(3P/3E)_V$ is proportional to volume.

Owing to the steepness of the Hugoniot curves in the P-V plane it is extremely difficult to accurately determine an average Grüneisen's ratio from offsets in pressure and energy at a given volume. The shock wave data give the locus of points on the P-V-E surface but, because of the steepness of the surface compared with the precision of the experiments, it is very difficult to obtain accurate values for the derivatives of the surface. What has been done by introducing Eq. (3) has been to assume a form of P-V-E equation of state and force it to fit the data. There may be other analytical forms that fit the data equally well or perhaps even better. However, the simplicity of Eq. (3) in which pressure is proportional to energy would seem to make it desirable for computational work.

This page intentionally left blank.

There is not enough overlap in volume of the Hugoniot of solid and porous Teflon to permit more than two energy-pressure points to be obtained at one volume. Values of Gruneisen's ratio computed from the offsets in pressure and energy along the Hugoniot curves vary by a factor of 2 (0.7 to 1.4). The zero pressure value estimated from static values of the bulk modulus, thermal expansion coefficient, and specific heat is about 0.313 (Ref. 2).

Sound speeds computed from the time of arrival at the gages of the rarefaction originating from the back surface of the aluminum projectiles on Shots 12,897 and 12,873 appear anomalously high. An estimate of the slope of the Hugoniot in the P-V plane can be obtained from the slope of the Teflon Hugoniot in the shock velocity-particle velocity plane (U-u plane). Since the U-u Hugoniot has less curvature than the P-V Hugoniot, the derivative du/du can probably be more accurately determined from a plot of the data than can the derivative dp/dv . The two derivatives are related by

$$\frac{dp_H}{dv} = c_0^2 u^2 \left[\frac{u \frac{du}{du} + u}{u \frac{du}{du} - u} \right] \quad (7)$$

The "Hugoniot sound speed" c_H is then defined by

$$c_H^2 = -v^2 \frac{dp_H}{dv} \quad (8)$$

c_H should be an upper limit for the sound speed of a hydrodynamic material. From a graphical evaluation of the slope of the U-u curve for Teflon at the Hugoniot points for Shots 12,897 and 12,873, values of c_H have been estimated (Table IV).

Table IV

Shot No	Pressure (kbar)	TEFLON SOUND SPEED DATA			
		U (mm./μsec.)	u (mm./μsec.)	$\frac{du}{du}$ (mm./μsec.)	c_H (mm./μsec.)
12,897	10.8	2.03	0.208	2.22	2.37
12,873	33.5	2.67	0.575	2.00	3.31
					2.82
					3.77

In the two shots, the measured values of the sound speed, $c(\text{meas})$, appear to be 18 and 14 percent higher than c_H , the sound speed estimated from the slope of the Hugoniot curve. The implication of these admittedly meager data is that the material has undergone a change in properties, becoming stiffer than indicated by the Hugoniot. If one assumes that the material has rigidity and approximates the bulk modulus by c_H^2 , the corresponding shear modulus is estimated to be ≈ 20 percent of the bulk modulus, and Poisson's ratio is ≈ 0.4 . Although this is not an unreasonable number, its determination may be only a mathematical exercise. Also, there are two phase transitions in Teflon at about room temperature. One is at atmospheric pressure and the other at about 6.5 kbar. These phase transitions may be related to the anomalous behavior described above.

APPENDIX

ANALYTICAL FITS TO THE EXPERIMENTAL DATA

The cubic fit to the Hugoniot of solid aluminum is given by Eq. (1). The coefficients are quite large numbers of oscillating sign, so that the pressure at a given volume is given by a sum of small differences of large numbers. This behavior indicates that a cubic fit to the data is probably not the best form. However, time does not permit further investigation of fits to the data to be included in this report.

For use in PUFF the variable $\mu = \rho/\rho_0 - 1$ is used rather than the specific volume. A fit to the Hugoniot of solid aluminum in the variable μ is

$$P_H = 778.518\mu + 1165.95\mu^2 + 1416.69\mu^3 \quad (9)$$

where P_H is in kilobars. Here all coefficients are of the same sign. In the same manner in which the arbitrary function $g(V)$ was determined, an arbitrary function $F(\mu)$ was found to fit the equation of state to the form

$$P(\mu, E) = bE + F(\mu) \quad (10)$$

the function $F(\mu)$ is given by

$$F(\mu) = -8.375 + 788.28\mu + 545.5\mu^2 + 523.97\mu^3 \quad (11)$$

Another form in which Eq. (10) can be used is

$$P(\mu, E) = P_H(\mu) \left[1 - \frac{b\mu}{20} \right] + b(E - E_0) \quad (12)$$

This page intentionally left blank.

where $P_H(u)$ is given by Eq. (9) and $b = 3.15 \text{ gm/cm}^3$. Comparing Eqs. (10) and (12) it is seen that $F(u)$ is simply a fit to

$$F(u) = P_H(u) \left[1 - \frac{bu}{2c} \right] - bE_0 \quad (13)$$

REFERENCES

1. Rice, M. H., R. G. McQueen, and J. M. Walsh, "Compression of Solids by Strong Shock Waves," *Solid State Physics*, F. Seitz and P. Turnbull, eds., Academic Press, New York, 1958, Vol. 6.
2. Anderson, G. D., A. L. Fahrenbruch, and D. G. Doran, "Equation of State of Solids. Aluminum and Teflon," *AFWL-TR-66-147*, August 1965.
3. Linde, R. K., and D. N. Schmidt, "Measuring the Sub-microsecond Response of Shock-Loaded Materials," *Rev. Sci. Instr.* **37**, 1 (1966).
4. Keough, D. D., and W. Wilkinson, "Manganin-Wire Shock-Transducer Investigation," *AFWL-TR-65-170*, December 1965.
5. Morgan, D. T., M. Rockowitz, and A. L. Atkinson, "Measurement of the Gruneisen Parameter and the Internal Energy Dependence of the Solid Equation of State of Aluminum and Teflon," *AFWL-TR-65-117*, October 1965.
6. Al'tshuler, L. V., S. B. Korner, A. A. Bakanova, and R. F. Trunin, "Equation of State for Aluminum, Copper, and Lead in the High Pressure Region," *Soviet Phys./JETP* **II**, 373 (1960).
7. Anderson, G. D., W. J. Murri, R. C. Alverson, and S. V. Managud, "Stress Relaxation in the Shock Compression of Solids, Final Report SRI Project FG0-5783, Contract AF 29(601)-7119, AFWL-TR-67-26, February 1967.

DISTRIBUTION

No. cys

HEADQUARTERS USAF
 1 Hq USAF (AFTAC/TD-3, Capt Herman), Wash, DC 20330
 1 USAF Dep, The Inspector General (AFIC), Norton AFB, Calif 92409
 1 USAF Directorate of Nuclear Safety (AFINS), Kirtland AFB, NM 87117
 MAJOR AIR COMMANDS
 AFSC, Andrews AFB, Wash, DC 20331
 (SCTSW)
 (SCTLI)
 1 AUL, Maxwell AFB, Ala 36112
 1 USAFITT-L, Wright-Patterson AFB, Ohio 45433
 AFSC ORGANIZATIONS
 1 AFSC STLO, R&T Div, AFUPO, Los Angeles, Calif 90045
 1 AFSC STLO (RTSAS), Suite 104, 363 S. Taaffe Ave, Sunnyvale, Calif 94086
 2 FTD (TDBTL), Wright-Patterson AFB, Ohio 45433
 5 AF Materials Laboratory, Wright-Patterson AFB, Ohio 45433
 1 AF Avionics Laboratory, Wright-Patterson AFB, Ohio 45433
 1 AF Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio 45433
 1 AF Aero-Propulsion Laboratory, Wright-Patterson AFB, Ohio 45433
 ASD, Wright-Patterson AFB, Ohio 45433
 (ASAPR)
 (ASRCP)
 (ASAMC)
 1 SEG, Wright-Patterson AFB, Ohio 45433
 (SEPIR)
 (SESOS, Mr. J. L. Wilkinson)
 1 ORA (RRRD), Holloman AFB NM 88330
 1 AEDC (AEYD), Arnold AFB, Tenn 37289
 1 ESD (ESTI), L. G. Hardcom Fld, Bedford, Mass 01731
 1 APGC (PCBPS-12), Eglin AFB, Fla 32542
 1 RADC (ENAL-1), Griffiss AFB, NY 13462
 1 AFRPL (RPI), Edwards AFB, Calif 93523

DISTRIBUTION (cont'd)

No. cys

SAMSO, AFUPO, Los Angeles, Calif 90045
 (SSSD)
 (SSUPM)
 (SSTDS)
 (SSTSE)
 (SMT)
 (SMT)
 (SMYSE, Capt R. Jackson)
 (SMTG)
 (SMTG)
 (SMTSH-1)
 1 KIRTLAND AFB ORGANIZATIONS
 AFSC, Kirtland AFB, NM 87117
 (SVEH)
 (SWT)
 1 ADC (ADSHO, Special Weapons Office, Kirtland AFB, NM 87117
 1 AFIC, Albuquerque Liaison Office (MCMQ), Kirtland AFB, NM 87117
 1 SAC Res Rep (SACLO), Kirtland AFB, NM 87117
 1 TAC Liaison Office (TACLO-S), Kirtland AFB, NM 87117
 AFWL, Kirtland AFB, NM 87117
 (NLIL)
 (WLAA)
 (WLDC)
 (WLDN)
 (WLR)
 (WLR, Dr. Guenther, Lt Asay)
 (WLR)
 (WLR, Mr. Aubrey)
 (WLR)
 (WLR)
 (WLR)
 OTHER AIR FORCE AGENCIES
 Director, USAF Project RAND, via: AFLO, The RAND Corp, 1700 Main St, Santa Monica, Calif 90406
 (RAND Physics Div)
 (RAND Library)
 (Dr. Olin Nance)

DISTRIBUTION (cont'd)

No.	CYS	
1	1	QAR (RRS), 1400 Wilson Blvd, Arlington, Va 22209
1	1	AFSR, 1400 Wilson Blvd, Arlington, Va 22209
1	1	AFCR, L. G. Hanscom Fld, Bedford, Mass 01731
1	1	Office of Asst Scy AF, Asst for Laboratories, ATTN: Dr. W. L. Lehmann, Wash, DC 20301
ARMY ACTIVITIES		
1	1	Chief of Research and Development, Dept of the Army (CRD/P, Scientific and Technical Info Div), Wash, DC 20310
1	1	Commanding Officer, Harry Diamond Laboratories, ATTN: Library, Wash, DC 20438
1	1	US Army Materiel Command, NIKE-X Fld Ofc (WMCPM-NXE-PB, Lt Col F. G. Thomas), Bell Telephone Laboratories, Inc, Whippany, NJ 07981
1	1	Redstone Scientific Information Center, US Army Missile Command (Chief, Document Section), Redstone Arsenal, Ala 35890
1	1	Commanding Officer, Ballistic Research Laboratories, Aberdeen Proving Ground, Md 21005
1	1	(AMGR-1B, Mr. J. J. Mazzaro)
1	1	(AMGR)
1	1	(R. Eichelberger)
1	1	Commanding Officer, Picatinny Arsenal, Dover, N.J. 07801
1	1	(SN/PA-VCL, Samuel Feltman Research Laboratories)
1	1	(SM/PA-TN, Nike-X Engineering Division)
1	1	Commanding Officer, US Army Research Office-Durham, Box CH, Duke Station, Durham, NC 27706
1	1	Chief of Engineers (ENGM-EM), Dept of the Army, Wash, DC 20315
1	1	Director, Army Rsch Ofc, 3045 Columbia Pike, Arlington, Va 22204
1	1	Director, US Army Engineer Research and Development Laboratories, ATTN: STINFO Branch, Ft Belvoir, Va 22060
1	1	Commanding General, White Sands Missile Range (Tech Lib), White Sands, NM 55002
NAVY ACTIVITIES		
1	1	Office of the Chief of Naval Operations, Dept of the Navy, Wash, DC 20350
1	1	(OP-75, ATTN: L.R., Atomic Energy Div)
1	1	(OP-754)
1	1	Chief of Naval Research, Dept of the Navy, Wash, DC 20390
2	1	Commanding Officer, Naval Research Laboratory, Wash, DC 20390
1	1	Commanding Officer and Director, US Naval Radiological Defense Laboratory, San Francisco, Calif 94135

DISTRIBUTION (cont'd)

No.	CYS	
1	1	Commanding Officer and Director, Navy Electronics Laboratory (Code 4223), San Diego, Calif 92152
1	1	Commanding Officer and Director, Naval Ship Research and Development Center, Wash, DC 20007
1	1	Commanding Officer and Director, Naval Civil Engineering Laboratory, Port Hueneme, Calif 93041
1	1	Commanding Officer and Director, Naval Applied Science Laboratory, Brooklyn, NY 11251
1	1	Commander, Naval Ordnance Test Station (Code 753), China Lake, Calif 93557
1	1	Commander, Naval Ordnance Laboratory, ATTN: Dr. Rudlin, White Oak, Silver Spring, Md 20910
1	1	Director, Special Projects Office, Dept of the Navy, Wash, DC 20360
1	1	Office of Naval Research, Wash, DC 20360
1	1	Director of Naval Warfare Analyses, Institute of Naval Studies, Ofc of Chief Navy Ops, 545 Technology Sq, Cambridge, Mass 02139
1	1	Commanding Officer, NMEP (Code WE), Kirtland AFB, NM 87117
1	1	Ordnance Systems Command, Dept of the Navy, Wash, DC 20360
1	1	Director, Laboratory Programs, Naval Material Command, ATTN: Dr. G. N. Johnson, Wash, DC 20360
OTHER DOD ACTIVITIES		
2	2	Director, DASA, Wash, DC 20300
2	2	(Document Library Branch)
2	2	(Maj Lowery, J. Moulton)
1	1	Commander, Fld Cmd, DASA, Sandia Base, NM 87115
1	1	(FCAG3, Spec Wpns Pub Dir)
1	1	(Col Neuer, Test Comd)
1	1	Director, Weapon Systems Evaluation Group, Wash, DC 20305
1	1	Director, ARPA, DOD, The Pentagon, Wash, DC 20301
1	1	Ofc Dir Defense Rsch & Eng, ATTN: J. Jackson, Ofc Atomic Programs, Rm 3E1071, The Pentagon, Wash, DC 20330
20	20	DDC (TIAG), Cameron Station, Alexandria, Va 22314
AEC ACTIVITIES		
1	1	USAF (hq Lib, Rpts Sect), Mail Sta G-017, Wash, DC 205
1	1	USAF (Chief, Div Tech Info Ext), Box 62, Oak Ridge, Tenn 37831
1	1	USCRL (Tech Info Div), Berkeley, Calif 94720
1	1	Brookhaven National Laboratory, Upton, Long Island, NY 11973
1	1	Oak Ridge National Lab (Tech Lib), Oak Ridge, Tenn 37831

DISTRIBUTION (cont'd)

No.	Org
1	Sandia Corp, Box 5800, Sandia Base, NM 87115
1	(C. D. Broyles)
1	(C. D. Lundergan)
1	(L. M. Barker)
1	(W. Hartmann)
1	(B. M. Blucher)
1	(W. B. Benedick)
1	(R. Graham)
1	(R. Clem)
1	(T. B. Lane)
1	(Information Distribution Division)
1	Sandia Corp, P. O. Box 969, Livermore, Calif 94551
1	(Tech Library)
1	(P. Glides)
1	(A. N. Blackwell)
1	UCLRL, ATTN: Director's Ofc, P. O. Box 868, Livermore, Calif 94551
1	(Dr. N. G. Magnuson, Jr.)
1	(R. Duff)
2	(C. J. Taylor, D. Gambie)
1	(Dr. R. B. Carr, Mech Eng Dept, L-722)
1	Director, LASH, P. O. Box 1663, Los Alamos, NM 87554
1	(Helen Redman, Rpt Lib)
1	(D. Evers)
1	(W. Deal)
1	(J. Taylor)
1	(R. McQueen)
1	Argonne National Lab, Lib Svcs Dept, Rept Sect, Bldg 243, RM-CL-125, 9700 S. Cass Ave, Argonne, Ill 60440
1	USAE, Albuquerque, NM 87115 ATTN: Wpn Sys Safety Br, P. O. Box 5400,
1	Courant Institute of Mathematical Sciences, AEC Computing and Applied Math Cn (Tech Lib), 251 Mercer St, New York, NY 10017
1	OTHER
1	Langley Research Cn (NASA), ATTN: Assoc Dir, Langley Sta, Hampton, Va 23365
1	National Bureau of Standards, Radiological Equipment Sect, Wash, DC 20234

DISTRIBUTION (cont'd)

No.	Org
1	Director, National Bureau of Standards, Central Radio Propagation Laboratory, Boulder, Colo 80302
1	Manned Spacecraft Cn (NASA), ATTN: Chief, Tech Info Div, Houston, Tex 77001
1	Institute for Defense Analysis, Rm 24257, Pentagon, Wash, DC 20330
1	THRU: AFPA
1	Research Analysis Corp (M. I. Emerson, Librarian), McLean, Va 22101
1	MIT, Lincoln Laboratory (Doc Lib), P. O. Box 73, Lexington, Mass 02173
1	Aerospace Corp, P. O. Box 95085, Los Angeles, Calif 90045
1	(W. Barry)
1	(S. Siegel)
1	(R. M. Cooper)
1	(J. McClelland)
1	TRW Systems, Eng Mech Lab, One Space Park, R 1/1004, Redondo Beach, Calif 90278
1	(F. B. Fay, Staff Eng)
1	(Dr. J. Slaughter)
1	Aerospace Corp, San Bernardino Open, P. O. Box 1308, San Bernardino, Calif 92402
1	(Ali M. Naqvi)
1	(J. Kehler)
1	(D. Glenn)
1	(C. Francis)
1	Johns Hopkins University, Applied Physics Laboratory, 8621 Georgia Ave, Silver Spring, Md 20910
1	AVCO Corp, RAD Div, 201 Lowell St, Wilmington, Mass 01887
1	(Chief Librarian)
1	(M. C. Atkins)
1	(W. L. Bade)
1	EG&G, ATTN: A. R. Clyde, 690 Sunset Rd, Las Vegas, Nev 89101
1	Northrop Corp, ATTN: D. V. Keller, Applied Mech Dept, 2323 Teller Rd, Newbury Park, Calif 91320
1	MIT Lincoln Laboratory, P. O. Box 73, Lexington, Mass 02173
1	(Dr. J. H. Pannell)
1	(Dr. E. Pike)
1	E. H. Plesset Assoc, Inc., 2444 Wilshire Blvd, Santa Monica, Calif 90403

DISTRIBUTION (cont'd)

No.	CVS	
1		Battelle Memorial Institute, 505 King Ave, Columbus, Ohio 43201
1		(Library)
1		(Dr. R. Castle)
1		The Dikewood Corp, 4805 Menaul Blvd NE, Albuquerque, NM 87110
1		General Atomic Div, General Dynamics Corp, P. O. Box 608, San Diego, Calif 92112
1		(Library)
1		(J. Nuace)
1		(R. Brightman)
1		General Electric Co, MSD, ATTN: Dr. F. A. Lucy, Rm M9505, P. O. Box 8555, Philadelphia, Pa 19101
1		General Electric Co, ATTN: A. A. Sinigalli, Dev Engr, Spacecraft Dept, King of Prussia Park, P. O. Box 8661, CC6P 7, Rm 7246, Philadelphia, Pa 19101
1		DASA Information and Analysis Cntr, IEMPO, General Electric Co, 816 State St, Santa Barbara, Calif 93102
1		MIT, Div of Industrial Cooperation, 77 Massachusetts Ave, Cambridge, Mass 02139
1		Paul Weidinger, CE, 777 Third Ave, New York, NY 10017
1		University of Illinois, ATTN: Dr. M. M. Newmark, Head, Civil Engineering Dept, 1114 Civil Engineering Bldg, Urbana, Ill 61801
1		College Park Metallurgy Cntr, Bureau of Mines, ATTN: Library, College Park, Md 20740
1		University of Massachusetts, Head, Civil Engineering Dept, Amherst, Mass 01002
1		University of Michigan, ATTN: Prof. B. G. Johnston, Dept of Civil Engineering, Ann Arbor, Mich 48104
1		Space Technology Laboratories, Inc., P. O. Box 1930, Redondo Beach, Calif 90278
50		Stanford Research Institute, ATTN: Dr. G. G. Doran, Dir, Shockwave Physics Div, Menlo Park, Calif 94022
1		Washington State University, Dept of Physics, Pullman, Wash 99163
1		(Dr. G. R. Fowles)
1		(G. Duval)
1		Lockheed Missiles and Space Co, ATTN: Dr. D. Moffat, 1111 Lockheed Way, Sunnyvale, Calif 94086
1		Bell Telephone Laboratories, Inc., Whippany, NJ 07981
1		(J. W. Foss)
1		(Dr. W. Troutman)

DISTRIBUTION (cont'd)

No.	CVS	
1		Kaman Nuclear, Garden of the Gods Road, Colorado Springs, Colo 80907
1		(F. H. Shelton)
1		(D. Williams)
1		(L. Botheil)
1		(Dr. A. P. Bridges)
1		Boeing Aerospace Div, P. O. Box 3985, Seattle, Wash 98124
1		(G. Butler)
1		(D. Young)
1		(J. Penning)
1		Douglas Aircraft Corp, 3000 Ocean Park Blvd, Santa Monica, Calif 90405
1		(B. Barnett)
1		(J. Peck)
1		(D. H. Dean)
1		(R. Reck)
1		(B. Love)
1		Aerofjet General Corp, ATTN: Dr. Fischer, 1171 Wadsworth Ave, Downey, Calif 90241
1		Physics International Corp, 2700 Merced St, San Leandro, Calif 94577
1		(Dr. W. Biernhard)
1		(Dr. C. Godfrey)
1		Shock Hydrodynamics, Inc., 15010 Ventura Blvd, Sherman Oaks, Calif 91403
1		(R. Bjork)
1		(H. Wagner)
1		General Motors Mfg Dev Corp, General Motors Tech Cen, Warren, Mich 48090
1		(C. Walden)
1		(J. Jones)
1		(W. Isbell)
1		Union Carbide Corp, P. O. Box 278, Tarrytown, NY 10017
1		(Dr. C. Zarby)
1		(Dr. F. LoSacco)
1		Applied Theory, Inc., ATTN: Dr. J. Trullio, 1930 Cotner Ave, Los Angeles, Calif 90025
1		McDonnell Acft Corp, ATTN: L. Lacini, P. O. Box 575, St Louis, Mo 63116
1		Aeroneutronic, ATTN: Dr. R. Grandey, Ford Rd, Newport Beach, Calif 92660

APML-TR-67-43

DISTRIBUTION (cont'd)

- | | |
|---------|--|
| No. CYS | |
| 1 | MITT Co-P, Attn: Dr. Harmon, Rte 62 & Middlesex Turnpike, Bedford, Mass 01736 |
| 1 | Autonetics, Div of North American Aviation, Inc., P. O. Box 4181, Anaheim, Calif 92803 |
| 1 | Braddock, Dean & McDonald, Inc., P. O. Box 1411, El Paso, Tex 79901 |
| 1 | Martin Co, Denver Div, Denver, Colo 80201 |
| 1 | Institute for Defense Analyses, ATTN: Dr. Mayer, 400 Army-Navy Dr, Arlington, Va 22202 |
| 1 | Director, Applied Physics Lab, Johns Hopkins University, ATTN: Dr. Stoe, 8621 Georgia Ave, Silver Spring, Md 20910 |
| 1 | Official Record Copy Capt Viola, WLRP |

UNCLASSIFIED
Security Classification

(Security classification of title, body of abstract and indexing classification must be entered when the original report is classed.) 1. ORIGINATING ACTIVITY (Corporate Source) Stanford Research Institute, Poulter Laboratories Menlo Park, California 94025		2. REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
3. REPORT TITLE EQUATION OF STATE OF SOLIDS: ALUMINUM AND TEFLON		4. DESCRIPTIVE NOTES (Type of report and inclusive dates) 6 May 1966-6 May 1967	
5. AUTHOR (Last Name, First Name, Initial) Anderson, G. D.; Fahrenbruch, A. L.		6. REPORT DATE August 1967	
7. CONTRACT OR GRANT NO AF 29(601)-7214		8. TOTAL NO OF PAGES 52	
9. PROJECT NO 5710		10. ORIGINATOR'S REPORT NUMBER APML-TR-67-43	
11. SUPPLEMENTARY NOTES SR Project FCI-6047		12. SPONSORING MILITARY ACTIVITY AFML (WLRP) Kirtland AFB, NM 87117	
13. ABSTRACT (Distribution Limitation Statement No. 2) The pressure-volume energy (P-V-E) equation of state of aluminum and Teflon has been investigated. The P-V-E equation of state of a material is needed to solve nonreactive flow problems using computer codes such as PUFF. Explosively induced shock waves have been used to generate Hugoniot curves for solid and porous specimens of aluminum and Teflon. For aluminum it is found that the following P-V-E equation of state can reproduce the experimental data quite nicely: $P = bE + g(V)$ where b is a constant and g is an arbitrary function of V. This corresponds to $V =$ constant, where γ is Gruneisen's ratio. Because of the spread of the Teflon data in the P-V plane, it was not possible to obtain a P-V-E fit. However, the data imply that Gruneisen's ratio varies from about 0.7 to 1.4 at high pressures. Gas gun experiments using manganin wire pressure recordings were performed. Sound speeds deduced from these records imply that Teflon becomes anomalously stiff under shock.			

DD FORM 1473
1 JAN 67

UNCLASSIFIED
Security Classification

UNCLASSIFIED
Security Classification

14	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	Equation of state Hugoniot Gruneisen parameter Shock transport						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY.** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (Corporate author) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted" or "Unclassified". Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10. Enter the classification of the report. Enter the group number. Also, when applicable, enter the optional marking have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Enter the inclusive dates when a specific reporting period is covered.

5. **AUTHORS:** Enter the name(s) of author(s) as shown on the report. Enter the rank and branch of service. If military, show rank and branch of service. If civilian, show the principal author as an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total pages count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been entered and any other report numbers (either by the originator or by the sponsor), enter these numbers.

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign dissemination and distribution of this report by DDC is not authorized."
- (3) "If a Government agency may obtain copies of this report directly from DDC. Other qualified users must request through."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory (including for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be included. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS) (S) (C) or (U). There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as indicators of its content. They are used to facilitate the selection of that no security classification is required. They may be used as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical content. The assignment of index, title, and weights is optional.

AFPC (NAPS NM)

UNCLASSIFIED
Security Classification

Unclassified

When this document is no longer required
by your activity, DESTROY IT in accordance
with applicable security regulations.

DO NOT RETURN IT TO DDC

Unclassified

When this document is no longer required
by your activity, DESTROY IT in accordance
with applicable security regulations.

DO NOT RETURN IT TO DDC

Unclassified

Unclassified