

UNCLASSIFIED

AD NUMBER
AD826116
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; 02 FEB 1968. Other requests shall be referred to Air Force Materials Laboratory, Attn: MAAM, Wright-Patterson AFB, OH 45433. Export Control.
AUTHORITY
afsc, usaf ltr, 2 mar 1972

THIS PAGE IS UNCLASSIFIED

Oxidation-Resistant Coatings for Refractory Metals

E. C. Allen • February 2, 1968

AD826116

COATING-PROCESS DEVELOPMENT FOR COLUMBIUM AND TANTALUM ALLOYS

Solar has deposited coatings consisting of chromium-titanium-silicon on Cb-752 and D-43 columbium alloys from fused fluoride or chloride salt baths by means of electrolytic and nonelectrolytic techniques.⁽¹⁾ Thermodynamic and kinetic considerations limited the order in which the individual elements could be applied, and chromium and titanium could not be codeposited. The order of deposition found most practical was chromium, silicon, and titanium. A subsequent diffusion treatment produced primarily $(Cr, Ti)_5Si_3$. The resulting oxidation resistance afforded the substrate was about 7 to 15 1-hour cycles in 2000 to 2600 F temperature range. Premature failure occurred by eruptions within the coatings, but the cause was not positively identified.

TRW is developing manufacturing methods for coating columbium and tantalum alloys.^(2,3) In the former, a production-scale facility is being developed to apply chromium-titanium-silicon coating to large (26 x 26 x 40 inches) columbium-alloy parts. Both vacuum-pack and slurry-application methods will be utilized. In the other work, a process is being developed for application of W/Si-W duplex coating on tantalum alloys (12 x 12 x 18 inches). The tungsten barrier is applied by chemical vapor depositions, electrophoretic deposition, or slurry-sinter techniques. The silicide coating is formed by a vacuum-pack or vacuum-slip-pack process.

COATING DEVELOPMENT FOR COLUMBIUM AND TANTALUM ALLOYS

A variety of protective coatings for columbium alloys has been investigated by Solar.⁽⁴⁾ Thermal expansion, interdiffusion, and oxidation resistance were determined on potentially ductile sublayer columbium alloys, MA1* and MA1₃ aluminides, and MSi₂ and M₅Si₃ silicides. Diffusion barriers between titanium-chromium modifier and substrate were also evaluated; molybdenum and tungsten were the most effective. Coating systems studied included V-(80Cr-20Ti)-Si, V-(Cr-Ti)-Al-Si, (95Mo-5Ti)-Si, and Mo-Cr-(Fe-25Cr-5Al), and were generally applied by pack cementation. The vanadium-containing systems were designed to reduce Laves phase formation and severity of the interstitial sink effect, while (95Mo-5Ti)-Si had expansion coefficients similar to those of the substrate. The metal coat-

* M stands for columbium, titanium, chromium, vanadium, molybdenum, tungsten, zirconium, hafnium, tantalum, or various combinations.

ing was intended to enhance ductility by having an all body-centered-cubic sequence, but interdiffusion appeared to limit the system to 10 hours at 2300 F. The V-(80Cr-20Ti)-Si coating, the most extensively studied, exhibited a minimum oxidation life of about 100 1-hour cycles at 1600 and 2400 F on D-43, Cb-752, and Cb-132M columbium alloys. The addition of aluminum to the coating had little effect. On the basis of limited tests, the slurry-sinter coating of (95Mo-5Ti)-Si with 10 percent iron or glass impregnation appeared to give even greater oxidation protection. The V-(80Cr-20Ti)-Si/D-43 or Cb-752 systems were extensively evaluated for aerospace and gas-turbine applications, and included seven different oxidation tests as well as tensile, creep, bend, and fatigue tests. The coating process reduced tensile strength of 0.012- and 0.030-inch-thick sheet generally 20 to 30 percent at 77 and 2200 F, reduced 10⁶-cycle fatigue strength 50 percent at 77 F, and, for Cb-752 only, caused embrittlement at 77 F. Fatigue strength was unchanged after expansion for 15 hours at 2400 F. Creep results indicate that the coating could withstand up to 5 percent elongation at 2200 and 2400 F.

TRW is also developing aluminide and silicide coatings for protection of columbium alloys for hundreds of hours at 2500 F.⁽⁵⁾ Beneficial modifications are expected by additions of vanadium, molybdenum, chromium, and titanium. Deposition technique for vanadium and molybdenum are being developed.

In another program, TRW is developing coatings for tantalum alloys for use in oxidizing atmospheres at 2000 to 3500 F.⁽⁶⁾ In a three-part program, the following coatings are being evaluated: (1) hafnium-tantalum, tungsten/iridium, tungsten/silicon, (2) 18 hafnium alloys leading to layered, metal-bonded oxide coatings, the outer layer of which is formed in situ during oxidation, and (3) metal-bonded refractory oxide over an intermediate diffusion-alloy layer. Since discouraging results were obtained in the first two phases, future efforts will be devoted to the third phase.

COATING DEVELOPMENT FOR TUNGSTEN

Complex oxides of different structure types are being evaluated by Battelle's Columbus Laboratories as candidates for protecting tungsten at 3500 F.⁷ The oxides are SrZrO_3 (perovskite), $\text{Nd}_2\text{Zr}_2\text{O}_7$ (pyrochlore), and $\text{Yb}_2\text{Zr}_2\text{O}_7$ (fluorite). The vaporization, structural stability, and interaction with tungsten and oxygen are being investigated under vacuum, reducing, inert, and oxidizing environments.

FEB 5 1968

AFMC 57441273 - D. L. Smith & Co

PROPERTY STUDIES OF COATED COLUMBIUM AND TANTALUM ALLOYS

NASA Langley has investigated protection of Ta-10W alloy by the slurry Sn-23.5Al-Mo coating.⁽⁸⁾ The coating provided protection for about 2 hours in static air at 2900 F. Flowing air (subsonic) reduced the lifetime by a factor of four. Addition of more molybdenum (7 compared with 5.5 percent) appeared to give some increase in life in flowing air. Use of 6-minute cycles reduced the lifetime by a factor of two in static air. The coating caused little change in substrate tensile strength and elastic modulus at temperatures up to 2900 F even after 5 hours' exposure at 2600 F. However, room-temperature elongation of 0.008-inch-thick sheet was reduced by about a factor of two, and 0.025-inch-thick sheet was somewhat less affected. Elongation was about 10 to 20 percent at 2000 to 2900 F, and about 5 percent at 1700 F. Prior exposure for 5 hours at 2600 F reduced the tensile elongations to 1 to 7 percent. Limited tests indicated that graded intermetallic/oxide coatings (MoSi₂ or WSi₂/stabilized ZrO₂) have good spalling resistance after cyclic oxidation.

The performance capabilities of fused-slurry, complex silicide coatings on columbium alloy sheet has been evaluated by Lockheed-California.⁽⁹⁾ Sylcor R512E (20Cr-20Fe-60Si) protected Cb-752 alloy over 8 hours at 2600 F at 0.1 torr, and over 8 hours at 2800 F at 1 and 10 torr air pressure. The system survived twenty 2.2-hour cycles of temperature up to 2500 F and pressures of 0.01 to 1000 torr, which simulated reentry conditions. Temperature capabilities of similar systems Cb-752/R512A (20 Cr-5Ti-75Si), D-43/R512A, and D-43/R512E appeared to be about 100 F lower.

McDonnell-Douglas is also evaluating the system Cb-752/R512E under temperature (up to 2600 F) -pressure (10⁻⁴ to 25 torr)-stress (0-40,000 psi) -time profiles representative of hypersonic flight.⁽¹⁰⁾ Particular attention will be given to joints, faying surfaces, defect sensitivity, and reuse capability of spacecraft hardware.

McDonnell-Douglas is developing self-sustaining, radiating, coated tantalum-alloy structures for operation to 3600 F.⁽¹¹⁾ Oxidation-resistance and room- and elevated-temperature mechanical-property tests are being conducted on various systems, including T-222 tantalum alloy and Solar (95W-5Ti)-Si and Sylcor W/WSi₂ coating systems. Fabricability tests are being conducted with the intention of eventual testing of full-scale leading-edge and flat-panel components.

Fundamental processes involved in the protection of columbium and tantalum by their silicides are being studied at the City College Research Foundation.⁽¹²⁾ The program consists of four parts: (1) establishment of thermochemical data for silicides employing an entirely solid-state electrochemical cell, (2) protection of both coating and substrate by glasses formed during oxidation, (3) use of coating modifiers to promote the formation of glassy films, and (4) interactions between intermediate phases, coating, and substrate, and the use of diffusion barriers to retard growth of intermediate phases.

A portion of a recent University of Dayton Research Institute effort was concerned with evaluation of D-43/R512A silicide and Cb-752, WC-103, and WC-129/Vac-Hyd Lunite 2 aluminide.⁽¹³⁾ The as-coated D-43 columbium alloy retained full bend ductility to -60 F and showed no evidence of room-temperature embrittlement after 30 hours in static air at 2600 F. The excellent throwing power of the silicide was evident by complete penetration of spot-welded lap joints. Lifetimes of 12 and 23 hours at 2600 F at 95 percent reliability were found for the 2.75- and 4.4-mil-thick coating, respectively. Somewhat better performance was noted at 2400 F. In contrast, the Lunite 2 and modified Lunite 2 (ND 66-1) coatings failed in less than 2 hours at 2600 F and survived about 2 to 5 hours at 2400 F.

REFERENCES

- (1) Steinman, J.B., et al, "Refractory Metal Coatings by the Fused Salt Method", Report AFML-TR-67-318, International Harvester Company, Solar Division, San Diego, Calif., Contract AF 33(615)-2173 (October, 1967), DMIC No. 70395.
- (2)* Kmiecik, H.A., Nejedlik, J.F., and Fisch, H.A., "Manufacturing Method for High Temperature Coatings of Large Columbium Parts", TRW, Inc., Cleveland, O. paper presented at the 13th Refractory Composite Working Group Meeting, Seattle, Wash., July 18-20, 1967, Contract AF 33(615)-2018, DMIC No. 70359.
- (3)* Kmiecik, H.A., Nejedlik, J.F., and Fisch, H.A., "Scale-up of W/Si-W Coating Process", TRW Incorporated, Cleveland O., paper presented at the 13th Refractory Composite Working Group Meeting, Seattle, Wash., July 18-20, 1967, Contract AF 33(615)-3405, DMIC No. 70360.
- (4) Stetson, A. R. and Metcalfe, A.G., "Development of Coatings for Columbium Base Alloys Part I-Basic Property Measurements and Coating System Development", Report AFML-TR-67-139 Part I, International Harvester Company, Solar Division, San Diego, Calif., Contract AF 33(615)-1598 (September, 1967).
- (5)* Kmiecik, H.A., Nejedlik, J.F., and Fisch, H.A., "Coatings for Long Term-Intermediate Temperature Protection of Columbium Alloys", TRW Incorporated, Cleveland, O. paper presented at the 13th Refractory Composites Working Group Meeting, Seattle, Wash., July 18-20, 1967, Contract AF 33(615)-1521, DMIC No. 70357.
- (6)* Kmiecik, H.A., Nejedlik, J.F., and Fisch, H.A., "High Temperature Coating Development", TRW Incorporated, Cleveland, O., paper presented at the 13th Refractory Composites Working Group Meeting, Seattle, Wash., July 18-20, 1967, Contract AF 33(615)-5011, DMIC No. 70358.
- (7) Preliminary information reported by Battelle Memorial Institute, Columbus Laboratories, Columbus, O., U.S. Air Force Contract AF 33(615)-5249.

- (8)* Stein, B.A. and Wichorek, G.R., "Results of Current Studies on Coated Tantalum Alloy Sheet at NASA Langley Research Center", NASA, Langley Research Center, Hampton, Va., paper presented at the 13th Refractory Composites Working Group Meeting, Seattle, Wash., July 18-20, 1967, DMIC No. 70510.
- (9)* Childers, M.G., "Behavior of Sylcor RS12E Coated Cb-752 Columbian Alloys in a Low Pressure Environment" Lockheed-California Company, Burbank, Calif., paper presented at the 13th Refractory Composites Working Group Meeting, Seattle, Wash., July 18-20, 1967, DMIC No. 70374.
- (10) Preliminary information Reported by McDonnell-Douglas Corp., St. Louis, Mo. under U.S. Air Force Contract F 33615- 67-C-1574.
- (11) Preliminary information reported by McDonnell-Douglas Corp., St. Louis, Mo. under U.S. Air Force Contract AF 33(615)-3935.
- (12) Preliminary information reported by the City College Research Foundation, City College, New York City University, New York, N.Y., under NASA Grant NGR 33-013-017.
- (13) Wurst, J.C., et al, "The Evaluation of Materials for Aerospace Applications", Report AFML-TR-67-165, University of Dayton Research Institute, Dayton, O., Contract AF 33(615)-1312 (June, 1967).

* These references were covered in detail in DMIC Memorandum 227, which is available on request to qualified DMIC users.

DMIC Reviews of Recent Developments present brief summaries of information which has become available to DMIC in the preceding period (usually 3 months), in each of several categories. DMIC does not intend that these reviews be made a part of the permanent technical literature. Copies of referenced reports are not available from DMIC; most can be obtained from the Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314.

R. W. Endebrock, Editor

Best Available Copy