

UNCLASSIFIED

AD NUMBER

AD826770

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution authorized to U.S. Gov't. agencies and their contractors; Critical Technology; AUG 1967. Other requests shall be referred to Office of Naval Research, Washington, DC 20360. This document contains export-controlled technical data.

AUTHORITY

onr notice, 27 jul 1971

THIS PAGE IS UNCLASSIFIED

826 770



Lexington Laboratories, Inc.

84 SHERMAN STREET
CAMBRIDGE, MASS. 02140
Area Code 617 • 864-5020

VAPOR PHASE GROWTH OF RUBY MONOCRYSTALS

Final Technical Summary Report

1 May 1964 - 31 August 1967

Robert C. Folweiler - Author

Contract No. Nonr-4574(00)-2
ARPA Order - 306

December 1967

This document is subject to special export controls and each transmittal to foreign governments, foreign nationals or representatives thereof may be made only with prior approval of Physics Branch, Code 581, Office of Naval Research, Washington, D.C. The distribution of this document is limited because the information is embargoed under the Department of State ITIARs.

VAPOR PHASE GROWTH OF RUBY MONOCRYSTALS

Final Technical Summary Report

1 May 1964 - 31 August 1967

Robert C. Folweiler - Author

Contract No. Nonr-4574(00)-2
ARPA Order - 306

December 1967

This research is part of Project DEFENDER, sponsored by Advanced Research Projects Agency, Department of Defense and technically monitored by the Office of Naval Research (Physics Branch).

Reproduction in whole or in part is permitted by the U. S. Government. [REDACTED]

[REDACTED].

This document is subject to special export controls and each transmittal to foreign governments, foreign nationals or representatives thereto may be made only with prior approval of Physics Branch (Code 421), Office of Naval Research, Washington, D.C.

BLANK PAGE

FOREWORD

This report was prepared by Robert C. Folweiler of Lexington Laboratories, Inc., 84 Sherman Street, Cambridge, Massachusetts 02140, under Contract Nonr-4574(00)-2, covering the period July 1966 to July 1967. Contract monitor was Dr. Van O. Nicolai of the Office of Naval Research.

P. S. Schaffer was principal investigator from the inception through April 1967, when R. C. Folweiler assumed the duties. R. C. Folweiler and H. A. Hobbs designed the furnace configuration and accessory equipment. Outstanding support was provided by L. G. Terrenzio and B. A. Albanese throughout. Many helpful suggestions and comments were provided by R. L. Coble and W. D. Kingery.

ABSTRACT

Improvements in apparatus and control of process parameters have led to the growth of a ruby weighing more than 200 grams. Several major limiting features of the process including furnace size, crystal purity, doping techniques, and pumping systems were improved in conjunction with a continuing study of process parameters. A significant breakthrough was made when a furnace construction technique was developed which did not limit furnace size. A four inch inside diameter furnace was constructed using this technique and has performed satisfactorily. In an investigation of doping techniques, additional sources of chromium vapor have been investigated, and chromyl chloride (CrO_2Cl_2) has proved to be satisfactory.

Previous measurements of laser characteristics determined have demonstrated that vapor grown ruby is of high optical quality and compares favorably to other available crystals in pumping behavior, light scattering, and interferometric properties.

TABLE OF CONTENTS

	Page No.
FOREWORD.....	i
ABSTRACT.....	ii
TABLE OF CONTENTS.....	iii
LIST OF FIGURES.....	iv
1.0 INTRODUCTION.....	1
2.0 REVIEW OF PREVIOUS WORK.....	2
2.1 Overall Process.....	2
2.2 Doping Technique.....	2
2.3 Purity.....	4
2.4 Crystalline Perfection.....	4
2.5 Laser Properties.....	4
3.0 EXPERIMENTAL APPARATUS.....	5
3.1 Furnace Configuration.....	5
3.2 Furnace Safety Apparatus.....	7
3.3 Vapor Train Modifications.....	8
3.4 Doping Techniques.....	8
3.5 Downstream Modifications.....	9
3.6 Seed Orientation.....	9
3.7 Injector Design.....	10
4.0 RESULTS AND DISCUSSION.....	11
4.1 Furnace Assembly.....	11
4.2 Crystal Growth.....	11
4.3 Laser Evaluation.....	15
4.4 Crystalline Purity.....	16
5.0 SUMMARY.....	17
6.0 REFERENCES.....	18
DD FORM 1473 DOCUMENT CONTROL DATA - R & D..	19

LIST OF FIGURES

	Page No.
Figure 1: Schematic of Furnace Design.....	6
Figure 2: Rubies Grown Simultaneously in Horizontal "Cross Flow" Furnace...	12
Figure 3: Largest Ruby Grown by Chemical Vapor Deposition.....	14

1.0 INTRODUCTION

Single crystals of aluminum oxide in both doped and undoped forms have been synthesized for a number of years utilizing the Verneuil technique, and in the past decade the Czochralski technique has been applied to production of high quality ruby and sapphire. Almost no effort, however, was expended on utilization of the chemical vapor deposition process for synthesis of useful single crystal material of aluminum oxide until about five years ago.


Single crystals of other materials have been synthesized by vapor transport and/or reaction techniques, but for the most part, the results have been either small crystals or films¹. For instance, considerable effort has been expended in attempting chemical vapor deposition of silicon carbide with the continuing result that little progress has been made since most crystals are of millimeter size². The most significant use of chemical vapor deposition techniques at the present time has been for the production of both highly-oriented and isotropic polycrystalline materials such as pyrolytic graphite, boron nitride, and a variety of refractory metallic and intermetallic compounds. Although these materials have not enjoyed great economic success, the chemical vapor deposition process continues to hold considerable promise for certain geometric forms, and specific materials which are best produced by this process. The process can take place isothermally with no thermal strain resulting from the growth process. In addition, purity may be improved substantially by the application of various techniques which can be utilized only in this process. Finally, a number of adjustable variables are available by which one may change the stoichiometry and properties of the deposited material.

2.0 REVIEW OF PREVIOUS WORK

Previous work done under this contract is summarized in this section^{3,4,5}.

2.1 Overall Process

The basic process utilizes the controlled oxidation of a volatile aluminum compound, aluminum chloride (AlCl_3). The source of oxygen used has been carbon dioxide (CO_2), which at the temperatures involved dissociates: $\text{CO}_2 \rightleftharpoons \text{CO} + 1/2\text{O}_2$. The process proceeds utilizing the following overall reaction:



Aluminum chloride is generated by direct chlorination of aluminum metal because of the relative ease with which chlorine gas may be metered directly using a standard flow meter compared to either the direct monitoring of aluminum chloride flows (which would require more difficult metering techniques) or indirect techniques such as evaporation and transport by a carrier gas. High purity aluminum metal as a source material is readily available, as is chlorine of reasonable purity.

A stoichiometric excess of hydrogen is used to reduce one of the thermodynamic variables. Addition of one of the product gases, CO, improves the stability of the growth process, probably due to the reduction of the initial thermodynamic driving force.

2.2 Doping Techniques

Doping of the product with chromium in order to produce ruby required replacing part of the aluminum in the oxide lattice by chromium. While perhaps superficially simple, the substitution was difficult because of subtle

The first of these is the fact that the
 government has been unable to raise the
 necessary funds to meet its obligations.
 This is due to a number of factors,
 including the fact that the government
 has been unable to raise the necessary
 funds to meet its obligations. This is
 due to a number of factors, including
 the fact that the government has been
 unable to raise the necessary funds to
 meet its obligations. This is due to a
 number of factors, including the fact
 that the government has been unable to
 raise the necessary funds to meet its
 obligations. This is due to a number of
 factors, including the fact that the
 government has been unable to raise the
 necessary funds to meet its obligations.

[illegible]

2.3 Purity

The nature of the process leads to an overall purification which decreases the impurities which may be carried into the reaction chamber. Differential chlorination and evaporation rates in the chlorinator, plus different deposition coefficients in the reaction chamber lead to enhanced purity. Qualitative spectrochemical analyses indicated typical impurity contents in the range 10 - 30 ppm and as low as <3 ppm cation impurities. No highly quantitative determinations have been made for all the cation impurities.

2.4 Crystalline Perfection

Dislocation density observed in a vapor grown ruby crystal, reported previously, were observed to be 6.2×10^{-5} per cm^2 on the prism plane $\{11\bar{2}0\}$, a substantial improvement over the flame-fusion material used for the substrate. Undoped sapphire demonstrated a lower dislocation content, and a vapor nucleated and grown crystal demonstrated a dislocation density of 13 per cm^2 .

2.5 Laser Properties

A vapor grown rod doped with approximately 0.1 wt % chromium was tested for laser properties⁸. Pumping energy requirements were observed which were similar to ruby prepared by other techniques.

3.0 EXPERIMENTAL APPARATUS

The emphasis of the recent contractual period included major improvement in two areas: (1) size of final crystal and (2) doping techniques. Experiments were performed which led to substantial redesign of our reaction chambers.

3.1 Furnace Configuration

The most important change developed for the furnace configuration was the removal of the inherent size limitation placed on the reaction chamber resulting from use of impervious aluminum oxide tubes. These tubes, which contained the growth process at operating temperature and isolated it from the ambient atmospheric pressure, were a substantial source of difficulty. Frequent internal defects, plus geometric defects such as eccentricity led to failures of the tube under operating conditions. This problem became a serious difficulty as the size of the tube was increased over two inches inside diameter. Experiments indicated that molybdenum was stable in the slightly oxidizing atmosphere used for the reaction; it was therefore concluded that in all likelihood, a molybdenum heating element could be operated within the growth atmosphere without deleterious effects.

A furnace was designed and constructed based on this observation; its structural arrangement is indicated in Figure 1. A steel shell isolated the reactor from the external atmospheric pressure. A molybdenum heating element was helically wound on a porous aluminum oxide tube which provided mechanical support for the winding. A variety of insulating materials, powders, foams, and bubbles, were successfully utilized to provide thermal insulation. Flanges




Figure 1: Schematic of Furnace Design.

were provided for the injector and for the exhaust system.

The initial power supply for the larger inside diameter furnace utilized a silicon controlled rectifier (SCR) unit with the control signal obtained by monitoring the resistance of the winding element. It was subsequently found that at low pressures (under three Torr) electrical breakdown occurred within the furnace leading to failure of the SCRs or protective fuses, since they could not tolerate unusually high peak currents. This difficulty was alleviated in two different ways: 1) the pressure was maintained above this critical pressure and 2) the power supply was changed to a variable autotransformer type, as the latter can tolerate substantial short-term peak currents. Within the appropriate restrictions, both power supplies operated satisfactorily.

The utility of a tungsten-rhenium alloy thermocouple with the hot junction adjacent to the winding was investigated. The thermocouple proved generally adequate although failures were experienced when a rapid shut-down occurred, requiring the replacement of the thermocouple.

3.2 Furnace Safety Apparatus

Because the larger system involved substantially larger volumes of hydrogen than previously, and because there was a danger that the molybdenum winding might suffer catastrophic oxidation, a safety system was designed to operate upon signal from an aneroid pressure switch. Upon activation of this switch, a relay a) shut down the pumps, b) shut off the reactant gases, c) flooded the furnace with a non-flammable quenching gas at a high volume rate and d) turned off the power supply. The non-flammable quenching gas (90% helium, 10% hydrogen) chosen provided adequate

stability for the winding while simultaneously protecting personnel. The system has pressurized the furnace to atmospheric within two seconds and provided a small positive pressure in order to maintain outward diffusion.

3.3 Vapor Train Modifications

Previous work indicated substantial difficulty with the chlorine vapor train. Stainless steel tubing was not adequate, since substantial corrosion occurred on the interior surface. Most of the transfer system was replaced with polymers (polyethylene, polyvinyl chloride, polypropylene and tetrafluoroethylene). With the exception of some minor stress cracking in the polypropylene fittings, these materials performed well. The vapor transfer line for the aluminum chloride were changed to aluminum oxide tubing.

An attempt was made to eliminate the corrosion of certain stainless steel components (valves, meter tube fittings and related parts) by coating exposed surfaces with fluorinated ethylene-propylene (FEP). The coating was permeable to chlorine and did not eliminate the reaction.

3.4 Doping Techniques

Doping was previously performed by the direct chlorination of chromium metal in a boat adjacent to the growth area. Difficulties lead to the study of several other potential doping techniques including chromium carbonyl, chromium acetyl acetonate and chromyl chloride. These compounds have a substantial vapor pressure at temperatures near room temperature and thus may be handled in exterior generators.

The carbonyl and the acetyl acetonate were transported through the use of a carrier gas. Hydrogen,

carbon monoxide, and carbon dioxide were used. Both of the chromium compounds were vaporized from the solid state by heating them in a well stirred bath. Chromyl chloride (CrO_2Cl_2) is a liquid with a vapor pressure of approximately 20 Torr at 20°C . It was introduced into the system by utilizing chlorine as a carrier gas, saturating the chlorine with the compound by passing it through a gas washer in a controlled temperature bath.

3.5 Downstream Modifications

In earlier furnaces we had difficulty with both the pumping apparatus and the cooler sections of the furnace. Powder depositing from the flow stream clogged the exit tube after extended periods of operation. Provisions were made for a scraping device to remove any substantial build-up of powder before excessive difficulty occurred with the reaction.

We continued to utilize oil sealed mechanical pumps with a liquid nitrogen trap ahead of the pumps. In order to handle the increased capacity requirements for larger furnaces, pumps were manifolded and the liquid nitrogen trap enlarged. Total pressure control inside the reaction chamber was performed by a nitrogen ballast which loaded the pumps to capacity at the desired pressure.

3.6 Seed Orientation

Previous difficulties with the axial variation of chromium homogeneity along the rod led to a change in mounting orientation. The seeds in the new larger furnace were mounted in a "cross flow" configuration, whereby the long axis of the seed was held vertical, perpendicular to the flow stream. An aluminum oxide plaque was used to support the seeds.

This technique was considered advantageous because the seed lay in a single cross section within the furnace, where the chromium distribution was expected to be uniform. It also removed a downstream "seed" support assembly which had been used and caused difficulties both from creep-deformation during operation and from blockage due to interference with the flow stream.

3.7 Injector Design

Previous difficulties with injector plugging led to a redesign of that assembly. The new design consisted of two concentric tubes and a third smaller tube. During sapphire growth, the smaller tube introduced the aluminum trichloride into the outer annulus between the furnace wall and the large injector tube. The inner annulus conducted the reducing gases, CO and H₂. The innermost tube carried the oxidizing gas, CO₂, plus Cl₂ when utilized. All tubes ended at approximately the same distance into the furnace. The intent was to use the reducing gases to form a separating wall between the AlCl₃ and the CO₂ until the gases had moved downstream from the injector, thus avoiding reaction in the immediate area of the injector. This separation led to substantially reduced growth on the injector when growing sapphire.

When CrO₂Cl₂ was used as a dopant medium during ruby growth, however, we found that the presence of the CO₂ in the vapor train with the CrO₂Cl₂ in the inner tube caused premature reaction and resultant plugging. While growing ruby therefore, we have moved the CO₂ so that it is introduced with the CO and H₂. This change resulted in slightly more growth on the injector system than noted during sapphire runs.

4.0 RESULTS AND DISCUSSION

The furnace system described in the preceeding section has been operated for substantial periods of time. This improved apparatus, plus a better understanding of process variables has led to a substantially increased crystal size. A number of process variables and operating techniques were changed or adjusted until satisfactory growth was obtained.

4.1 Furnace Assembly

The modified furnace assembly with its newly designed pressure vessel, vapor train, and pumping modifications was continuously operated for a period exceeding 50 hours. A number of operational difficulties occurred, which led to apparatus modifications. Most were minor and readily corrected, except the problem of internal electrical breakdown. As mentioned previously, the problem of breakdown was controlled by the maintenance of an appropriate total pressure within the furnace.

4.2 Crystal Growth

Several experimental crystal growth runs were conducted utilizing the cross-flow arrangement. The results of one of the runs are shown in Figure 2, indicating one of the problems of this configuration. The resultant crystals had re-entrant surfaces and were substantially barrel-shaped, which is considered an unsatisfactory configuration for the final product. This barrel shape can be directly ascribed to the laminar flow conditions within the furnace. Since the flow was laminar ($N_{Re} \sim 1$), the velocity profile across the tube was approximately parabolic, which demonstrates that the flow velocity strongly influences growth rate. It




Figure 2: Rubies Grown Simultaneously in Horizontal "Cross Flow" Furnace.

was also apparent, even though N_{Re} was small, that there were turbulent eddies which occurred after a period of growth leading to the distorted forms as seen in the cross section.

In addition, substantial chromium banding within the crystals occurred which is visible in the inset of the photograph. This chromium banding was due to two factors, one of which was difficult to control. The banding was due in part to inadequate controls of the chromium generation apparatus, whether it be direct chlorination of the chromium metal or the introduction of a chromium compound. It seems fairly certain that the input flow variations which cause banding can be controlled adequately by appropriate commercially available methods. The problem of local eddies adjacent to the crystal is a substantially more difficult problem and would require modifications of the furnace assembly to permit rotation of the crystal. Preliminary studies have indicated that this would not be difficult to accomplish.

It is not clear at this time, however, that the cross-flow configuration is advantageous for growing rod-shaped crystals. A rectangular reaction chamber cross section, rather than the present circular cross section, would be required to avoid the barrel-shaped effect. By the use of this modified reaction chamber cross section, it is anticipated that large size cross-flow rubies could be grown.

An axial flow ruby was grown to substantial size as shown in Figure 3, in a furnace with vertical flow orientation⁹. This ruby retained the usual axial variation in chromium content previously experienced. However, the



Figure 3: Largest Ruby Grown by Chemical Vapor Deposition.

chromium variation was substantially lower than we have previously encountered and indicated that we can substantially improve the axial chromium variation by changes in the input gas flows. Almost all of the radial banding can be directly attributed to external variations in the gas saturation apparatus, either temperature or pressure. Steps have been taken to improve the control of these variables and this problem has been largely solved, although further experimentation is essential to determine the degree of control required.

The addition of the doping apparatus to the growth system required a shorter injector assembly in order to reduce the temperature at the exit of the injectors. This was done in an effort to reduce undesired pre-reaction in the general area of the end of the injector. Because the growth pattern of ruby was different from that observed on a sapphire run of otherwise similar parameters, it was concluded that a higher gas velocity is required in the furnace during ruby growth in order to produce a more desirable growth configuration. However, with the present pumping equipment, adequate velocity is not attainable.

Satisfactory seed material continues to be a substantial problem. Available Verneuil material is of low quality and, along with Czochralski material, has an inappropriate orientation for the most favorable vapor growth. A low angle orientation, preferably with the "c"-axis co-axial with the rod, has the best overall growth characteristics. Because of the epitaxial growth process, substrate misorientation defects continue into the overgrowth.

4.3 Laser Evaluation

Banding and internal defects were sufficiently extensive that evaluation of laser properties was not

considered desirable in the crystals grown under this portion of the contract.

4.4 Crystalline Purity

A sample of vapor grown material was analyzed by nuclear activation techniques for chlorine content. The analysis indicated a concentration of between four and six parts per million (PPM) chlorine¹⁰, significantly lower than the sample previously analyzed by vacuum fusion and reported to contain 0.15 wt. % chlorine⁵.

5.0 SUMMARY

5.1 Significantly larger ruby crystals (over 200 grams) were grown utilizing the chemical vapor deposition process than previously accomplished.

5.2 A new furnace construction technique was developed and proved which does not place any basic limit on crystal size.

5.3 New sources of chromium dopant were investigated. Chromyl chloride demonstrated some advantages over the direct chlorination of chromium metal.

5.4 Procurement of satisfactory substrate material presents a limit on the growth of quality material.

6.0 REFERENCES

1. Powell, C. F., Oxley, J. H., and Blocher, J. M., Editors, Vapor Deposition, J. Wiley & Sons, New York, 1966
2. Coble, R. L., personal communication
3. Schaffer, P. S., "Vapor Phase Growth of Alpha-Alumina Single Crystals", J. American Ceramic Society **48**, (1965) pp508-511
4. Schaffer, P. S., "Evaluation of Vapor Deposition Growth of Oxide Single Crystals from Metal Halides," final report, Contract Nonr-4574(00), (1965)
5. Schaffer, P. S., "Vapor Phase Growth of Ruby Monocrystals," Semi-annual technical reports, Contract Nonr-4574(00)-1, (Feb. 66 & Aug. 67) and Contract Nonr-4574(00)-2, (Feb. 67)
6. Schaffer, P. S., "Rubies for Reference Temperature Standards," final report RADC-TR-66-457 (1966)
7. Ellis, R. C., "An Investigation for Fabricating and Evaluating the Properties of Chemically Vapor Deposited Alumina and Magnesia," interim report, (Mar. 66-Mar. 67) Contract No. DA19-066-AMC-318(X), (1967)
8. O'Connor, J. R., Schaffer, P. S., and Bradbury, R. A., "Laser Properties of a Vapor-Grown Ruby," Appl. Physics Letters, **8**, pp336-7 (1966)
9. Folweiler, R. C., "Rubies for Temperature Standards," Final Report RADC-TR-67-575 (1967)
10. Anderson, R.L., "Measurements of Oxygen Self-Diffusion in Single Crystal Aluminum Oxide by Means of Proton Activation," M.I.T. ScD Thesis, Course III, Sept. 67

Unclassified

Security Classification

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Lexington Laboratories, Inc. 84 Sherman Street Cambridge, Massachusetts 02140		2a. REPORT SECURITY CLASSIFICATION Unclassified	
3. REPORT TITLE Vapor Phase Growth of Ruby Monocrystals		2b. GROUP	
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Final Report May 1964 - August 1967			
5. AUTHOR(S) (Last name, first name, initial) Polweiler, Robert C.			
6. REPORT DATE December 1967	7a. TOTAL NO. OF PAGES This document is subject to special	7b. NO. OF REFS 10	
8a. CONTRACT OR GRANT NO. Nonr-4574(00)-2	8b. CONTRACTOR'S REPORT NUMBER(S) to foreign governments, foreign nationals or representatives thereto may be made only with prior approval of Physics Branch (Code 492), Office of Naval Research, Washington, D.C.		
9. PROJECT NO. ARPA Order 306	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned to this report)		
10. AVAILABILITY/LIMITATION NOTICES Qualified requestors may obtain copies of this report from DDC.			
11. SUPPLEMENTARY NOTES Research is part of Project DEFENDER.		12. SPONSORING MILITARY ACTIVITY Office of Naval Research Department of the Navy Washington, D. C.	
13. ABSTRACT Improvements in apparatus and control of process parameters have led to the growth of a ruby weighing more than 200 grams. Several major limiting features of the process including furnace size, crystal purity, doping techniques, and pumping systems improved in conjunction with a continuing study of process parameters. A significant breakthrough was made when a furnace construction technique was developed which did not limit furnace size. A four inch inside diameter furnace was constructed using this technique and has performed satisfactorily. In an investigation of doping techniques, additional sources of chromium vapor have been investigated, and chromyl chloride (CrO_2Cl_2) has proved to be satisfactory. Previous measurements of laser characteristics determined have demonstrated that vapor grown ruby is of high optical quality and compares favorably to other available crystals in pumping behavior, light scattering, and interferometric properties. 12/54			

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Crystal Growth Ruby Lasers Chemical Vapor Deposition Vapor Phase Growth						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.