

UNCLASSIFIED

AD NUMBER

AD832322

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited. Document partially illegible.

FROM:

Distribution authorized to U.S. Gov't. agencies and their contractors; Critical Technology; MAY 1968. Other requests shall be referred to Army Electronics Command, AMSEL-KL-TD, Fort Monmouth, NJ. Document partially illegible. This document contains export-controlled technical data.

AUTHORITY

usaec ltr, 16 jun 1971

THIS PAGE IS UNCLASSIFIED

AD832322



Technical Report ECOM-01698-9

LONG-LIFE COLD CATHODE STUDIES FOR CROSSED-FIELD TUBES

PROGRESS REPORT

by

L. Lesensky - M. Arnum
C. McGeoch

May 1968

ECOM

UNITED STATES ARMY ELECTRONICS COMMAND · FORT MONMOUTH, N.J.


Contract DA28-043-AMC-01698 (E)

SPONSORED BY: ADVANCED RESEARCH PROJECTS AGENCY
ARPA ORDER NO. 345

RAYTHEON COMPANY
MICROWAVE AND POWER TUBE DIVISION
Waltham, Massachusetts

DISTRIBUTION STATEMENT

This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of CG, U.S. Army Electronics Command, Fort Monmouth, New Jersey.
Attn: AMSEL-KL-TD



PS. 132 for		
WHITE SECTION ☐		
BU.F SECTION ☒		
ANNOUNCED ☐		
DISPOSITION		
DISTRIBUTION/AVAILABILITY CODES		
ST.	AVAIL.	and/or SPECIAL
2		

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government indorsement or approval of commercial products or services referenced herein.

Disposition

Destroy this report when it is no longer needed. Do not return it to the originator.

Technical Report ECOM-01698-9

Reports Control Symbol

OSD-1366

May 1968

LONG-LIFE COLD CATHODE STUDIES
FOR CROSSED-FIELD TUBES

Ninth Quarterly Report
15 October 1967 to 15 January 1968

Report No. 9
Contract No. DA28-043-AMC-01698(E)
DA Project No. 7900-21-223-12-00

Prepared by

L. Lesensky

M. Arnum

C. McGeoch

RAYTHEON COMPANY
Microwave and Power Tube Division
Waltham, Massachusetts 02154

For

U.S. Army Electronics Command
Fort Monmouth, N. J. 07703

Sponsored by

Advanced Research Projects Agency
ARPA Order No. 345

DISTRIBUTION STATEMENT

This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of CG, U.S. Army Electronics Command, Fort Monmouth, New Jersey.
Attn: AMSEL-KL-TD

ABSTRACT

Further tests of the effects of high current-density electron bombardment (0.75 A/cm^2) and of residual oxygen ($\sim 5 \times 10^{-6}$ Torr) on the secondary-emission ratio (δ) were performed in the Electron Bombardment Vehicle (EBV) for the following samples:

1. Three samples of $9500 \text{ \AA}$ evaporated aluminum on copper.
2. Two samples of $300 \text{ \AA}$ Al_2O_3 on Al, anodically oxidized in tartaric acid.

Generally, δ_{max} varied from approximately 3.0 to 1.5. All samples showed good recovery due to O_2 and consistent degradation of δ due to electron bombardment.

Test of the QKS1397 CFA vehicle for more than 50 hours has demonstrated stabilized cathode emission from an aluminum cold cathode through the use of oxygen in the pressure range of 10^{-6} to 10^{-5} Torr. The stabilized emission level reached was approximately 4 A/cm^2 at a duty cycle of 0.001.

BLANK PAGE

TABLE OF CONTENTS

<u>Section</u>		<u>Page</u>
1.	Introduction	1
2.	Phase A - Materials Evaluation	1
2.1	Electron Bombardment Evaluation	
2.1.1	Electron Bombardment Vehicle (EBV) Testing of Evaporated Al on Cu Samples	2
2.1.1.1	Sample E-1	2
2.1.1.2	Sample E-2	3
2.1.1.3	Sample E-3	6
2.1.2	EBV Testing of Anodized-Alumina Samples	7
2.1.2.1	Sample A-1	7
2.1.2.2	Sample A-2	8
2.1.3	EBV Testing of Impregnated-Tungsten Sample	9
3.	Phase B - CFA Testing	10
3.1	QKS1397 Test Vehicle	10
3.1.1	Model No. 8B	10
3.1.2	Model No. 8C	12
4.	Conclusions	12
4.1	Phase A - Materials Evaluation	12
4.2	Phase B - CFA Testing	12
5.	Program for Next Interval	12
5.1	Phase A	12
5.2	Phase B	12

BLANK PAGE

LIST OF ILLUSTRATIONS

<u>Figure No.</u>	<u>Title</u>	<u>Page</u>
1.	$\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-1)	2
2.	$\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-1)	3
3.	$\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-2) Sheet 1	4
3.	$\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-2) Sheet 2	5
4.	$\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-3)	6
5.	$\delta_{\max}$ vs EBV Time for 300Å Anodized 6061 Aluminum (Sample A-1) Sheet 1	7
5.	$\delta_{\max}$ vs EBV Time for 300Å Anodized 6061 Aluminum (Sample A-1) Sheet 2	8
6.	$\delta_{\max}$ vs EBV Time for 300Å Anodized 1100 Aluminum (Sample A-2)	9
7.	$\delta_{\max}$ vs Hot/Cold EBV Time for Impregnated Tungsten Sample	10
8.	Emitter Life Test Data (AA 1100F Aluminum)	11

1. INTRODUCTION

The objective of the present cold cathode study program is to achieve long life cold-cathode performance for crossed-field amplifiers. This program is being performed for the United States Army Electronics Command, Fort Monmouth, New Jersey, under contract DA-28-043-AMC-01698(E).

In this study, selected cold cathode materials will be evaluated as to their secondary emission properties, their ability to withstand environmental factors expected in a crossed-field amplifier, and their crossed-field amplifier performance. Based on the above experimental information and pertinent theoretical calculations, a life prediction chart will be established for a number of cold cathode materials.

The program is divided into two concurrent phases, Phase A being concerned with the measurement of various pertinent properties of cold cathode materials outside of the tube environment, and Phase B involving the evaluation and life testing of selected cathodes in a crossed-field amplifier.

The first quarterly report of this contract (Technical Report ECOM 01698-1) contains a discussion of the objectives and plans for the over-all program. Quarterly Report No. 5 contains a description of the CFA test vehicles used in this program.

2. PHASE A - MATERIALS EVALUATION

2.1 Electron Bombardment Evaluation. During the present quarter, a number of samples were evaluated in the Electron Bombardment Vehicle (EBV), involving primarily the effect on secondary emission ratio (δ) of high current-density electron bombardment (up to 0.75 A/cm²) and recovery with oxygen. These samples were as follows:

- a. 9500 Å layer of aluminum evaporated on copper.
 - 1. Completion of sample E-1 (13 hours additional)
 - 2. Sample E-2 (80 hours)
 - 3. Sample E-3 (26 hours)
- b. 300 Å aluminum-oxide layer on aluminum (anodically oxidized, using tartaric acid)
 - 1. Sample A-1 (6061 Al) (60 hours)
 - 2. Sample A-2 (1100 Al) (55 hours)

In addition to the evaluation of the above samples in the cold EBV, an impregnated tungsten sample was evaluated briefly in the Hot/Cold EBV for 9 hours.

2.1.1 Electron Bombardment Vehicle (EBV) Testing of Evaporated Al on Cu Samples.

2.1.1.1 Sample E-1. Sample E-1 consisted of an evaporated aluminum layer (9500 Å) deposited on a chemically cleaned, wet-polished OFHC copper substrate. Samples E-2 and E-3, discussed below, were prepared in the same way.

E-1 data were reported in the 8th Quarterly Report (see Figure 4 therein) and are reproduced here as Figure 1. An additional 13 hours of




Figure 1 δ_{max} vs EBV Time for 9500Å Evaporated Aluminum on Copper

EBV data for E-1 are shown in Figure 2. The decrease of $\delta_{\max}$ due to the same sample. $\delta_{\max}$ decreased from 2.5 to 1.7 in five hours. Recovery of δ with O_2 was rapid with electron bombardment at 0.15 A/cm^2 , but negligible without electron bombardment. As suggested before, this difference in re-oxidation rates is believed to be due to the temperature difference.




Figure 2. $\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E 1)

2.1.1.2 Sample E-2. Sample E-2 was similar to E-1, consisting of a 9500Å layer of aluminum evaporated on copper. The results of 80 hours of evaluation in the EBV are shown in Figure 3. Residual vacuum without oxygen addition was approximately 5×10^{-8} Torr. Recovery with oxygen at 8×10^{-6} Torr is shown during hours three to 11. After a small increase (overnight) while equipment (including gun) was off, a large increase to a $\delta_{\max}$ in excess of 4.0 was observed. During this time, the gun heater and gun cathode were at temperature but without electron bombardment. The increase may have been due to gases released by the heater-cathode structure of the electron gun. Subsequent to this, electron bombardment at 0.75 A/cm^2 from hours 19 to 35 caused $\delta_{\max}$ to decrease from 4.0 to 1.4. This sample never again reached this high a δ value. The sample continued to show the expected response to O_2 and to high-density electron bombardment. The decrease of $\delta_{\max}$ due to bombardment at 0.75 A/cm^2 which occurred during hours 60-79 was quite slow. $\delta_{\max}$ decreased from 3.2 to 1.5 in 24 hours.





Figure 3. $\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-2)





Figure 3. δ_{max} vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-2)

Sheet 2

2.1.1.3 Sample E-3. Sample E-3 was similar to both E-1 and E-2, consisting of a 9500Å layer of aluminum evaporated on copper. The course of $\delta_{\max}$ as a function of evaluation time in the cold EBV is shown in Figure 4 for a 26-hour period. $\delta_{\max}$ varied between 2.6 and 1.5. The decrease of $\delta_{\max}$ with O₂ present and 3 mA bombardment during hours 3 - 5 was unexpected. The decrease in δ during hours 8 - 16.5 due to bombardment at 0.75 A/cm² was normal for this sample. Subsequently, a normal recovery due to O₂ was observed during hours 17 - 23. On disassembly of the apparatus, it was noted that the surface of the sample was gold colored rather than the usual color of aluminum. Thin, pure alumina films were not usually colored but rather transparent. The codeposited molybdenum-alumina films were colored. Perhaps, in the present case, some copper diffused into the film from below.





Figure 4. $\delta_{\max}$ vs EBV Time for 9500Å Evaporated Aluminum on Copper (Sample E-3)

2.1.2 EBV Testing of Anodized-Aluminum Samples

2.1.2.1 Sample A-1. Sample A-1 consisted of an aluminum sample (alloy 6061 - purity 97.5%) anodically oxidized to a depth of 300Å in a tartaric acid solution. The sample surface was highly polished before oxidation. This method is known to produce a non-porous oxide film. The results of 59 hours of evaluation in the EBV are shown in Figure 5. It can be seen that this sample responded to O₂, recovering δ at an O₂ pressure of 5×10^{-6} Torr with simultaneous bombardment at 0.15 A/cm². δ_{max} varied from a maximum of 2.7 to a minimum of 1.6. These values are similar to those of the evaporated-aluminum samples, described above.





Figure 5. $\delta_{\max}$ vs EBV Time for 300Å Anodized 6061 Aluminum (Sample A-1)




Figure 5. δ_{max} vs EBV Time for 300Å Anodized 6061 Aluminum (Sample A-1)

Sheet 2

2.1.2.2 Sample A-2. Sample A-2 was anodically-oxidized aluminum (alloy 1100 - purity 99.0+%). As for A-1, the tartaric acid method was used and the oxide thickness was a nominal 300Å. Figure 6 shows δ_{max} as a function of EBV time during 55 hours of evaluation.

After an initial value of δ_{max} of 1.7, the sample was electron bombarded at 3 mA without O₂ and δ_{max} increased to 3.0. It is suspected that a small air leak was present. The residual vacuum was approximately 3×10^{-7} Torr rather than the usual $2-5 \times 10^{-8}$ Torr.

Subsequent to the initial period, the value of δ_{max} varied between 3.0 and 2.2. The value of 2.2 persisted during an eight-hour period (hours 42.5 - 50.5) under 0.75 A/cm² bombardment. This sample apparently required an oxygen pressure of $< 10^{-7}$ Torr for recovery. The minimum δ_{max} of 2.2 was higher than the usual value of 1.5 to 1.7 for the other aluminum samples.




Figure 6. $\delta_{\max}$ vs EBV Time for 300Å Anodized 1100 Aluminum (Sample A-2)

2.1.3 EBV Testing of Impregnated-Tungsten Sample. An impregnated-tungsten sample was briefly evaluated in the Hot/Cold EBV, the test being terminated by the failure of the sample heater. The initial value of $\delta_{\max}$ was approximately 1.4 after system bakeout. Heating of the target at an estimated temperature of 1000°C resulted in activation to a $\delta_{\max}$ of 2.2. At this point, a weld opened in the target-heater connections, thus preventing further sample heating. The record of $\delta_{\max}$ vs time is shown in Figure 7.




Figure 7. $\delta_{\max}$ vs Hot/Cold EBV Time for Impregnated Tungsten Sample

3. PHASE B - CFA TESTING

3.1 QKS1397 Test Vehicle

3.1.1 Model No. 8B. Evaluation of cathode emission life of Model No. 8B was conducted on a cathode-pulsed modulator test station during the report period. The tube contained an aluminum (AA-1100 F) emitter 1.645 inch in diameter and 0.570 inch high (19 cm² area) and an oxygen dispenser to stabilize the emission. Initially, the operating point selected for test evaluation was:

f_o = 3.4 GHz
 p_o = 877 kW peak
 P_o = 1770W average
 B = 3000 gauss
 i_b = 100 amperes
 e_b = 28 kilovolts

In Figure 8, the solid line shows the peak tube current and the dashed line shows the oxygen-dispenser heater power, both as a function of time. With an initial peak drive power of 125 kW, a peak current of 100A was obtained at 0.002 duty factor. This level of emission could be maintained for just over an hour, after which it rapidly decayed to 55A. At this time, the peak drive power was raised to 150 kW after changing to a 0.001 duty factor. The emission recovered to 88 A, then a voltage breakdown occurred within the tube (due to temporary loss of rf drive power), and the emission rapidly fell off to 55 A again. The oxygen dispenser was now activated and recovered to 88A. Removal of the oxygen dispenser heater power resulted in a rapid decline of the peak tube current. At this time, the tube was "conditioned" for half an hour with only drive power present. The emission gradually recovered to 80A. An internal tube arc (again due to temporary




Figure 8. Emitter Life Test Data (AA 1100F Aluminum)

loss of drive power) caused the emission to decline. The emission test continued fairly smoothly (a few tube arcs) into the 52nd hour, with emission stabilized at approximately 77A. At 52+ hours, the dispenser heater shorted with 65W of heater power. Without oxygen dispenser power to maintain a partial pressure of oxygen in the tube, the emission gradually decreased, and the life test was terminated at approximately 82 hours.

3.1.2 Model No. 8C. The test vehicle was rebuilt as Model No. 8C with a cathode 1.645 inch in diameter and 0.670 inch axial height (22.4 cm²). The emitter material was aluminum deposited on an OFHC copper base to a thickness of 0.0005 inch. The rebuilt test vehicle was bake-out processed, and at the end of the report period was awaiting availability of a pulse modulator for initial tests.

4. CONCLUSIONS

4.1 Phase A - Materials Evaluation. Two additional evaporated alumina (9500Å) on copper samples showed consistent behavior of rapid recovery with O₂ as for previous sample discussed in the 8th Quarterly Report.

Tests on 300Å Al₂O₃ on Al samples, anodically oxidized in tartaric acid solution, showed good response to O₂ and consistent degradation at high current density electron bombardment without O₂.

4.2 Phase B - CFA Testing. Test of the QKS1397 CFA test vehicle for more than 50 hours has demonstrated stabilized cathode emission from an aluminum cold cathode through the use of oxygen in the pressure range of 10⁻⁶ to 10⁻⁵ Torr. The stabilized emission level reached was approximately 4 A/cm² at a duty cycle of 0.001.

5. PROGRAM FOR NEXT INTERVAL

5.1 Phase A

- a. Perform EBV testing of evaporated-alumina on molybdenum samples.
- b. Perform EBV testing of Be samples.
- c. Perform EBV testing of BeCu and AgMg samples.
- d. Perform Hot/Cold EBV testing of Nickel Cermet samples.

5.2 Phase B

- a. Life-test QKS1397 Model No. 8C at the highest cathode-emission level possible with the use of oxygen in the pressure range 10⁻⁶ - 10⁻⁵ Torr.
- b. Perform additional emission-performance testing of the impregnated-tungsten cold cathode in the QKS1194 test vehicle.

Unclassified

Security Classification

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Raytheon Company Microwave and Power Tube Division Waltham, Massachusetts		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP N/A
3. REPORT TITLE Long-Life Cold Cathode Studies for Crossed-Field Tubes		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Ninth Quarterly Report 15 October 1967 - 15 January 1968		
5. AUTHOR(S) (Last name, first name, initial) Lesensky, L; Arnum, M; and McGeoch, C.		
6. REPORT DATE May 1968	7a. TOTAL NO. OF PAGES 12	7b. NO. OF REFS 0
8a. CONTRACT OR GRANT NO. DA28-043-AMC-01698(E)	9a. ORIGINATOR'S REPORT NUMBER(S) PT-1782	
b. PROJECT NO. 7900-21-223-12-00		
c.	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.	ECOM-01698-9	
10. AVAILABILITY/LIMITATION NOTICES This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of CG, USAECOM, ATTN: AMSEL-KL-TD, Fort Monmouth, N.J. 07703		
11. SUPPLEMENTARY NOTES Advanced Research Projects Agency Contract ARPA Order No. 345	12. SPONSORING MILITARY ACTIVITY U. S. Army Electronics Command Fort Monmouth, N. J. 07703 AMSEL-KL-TD	
13. ABSTRACT Further tests of the effects of high current density electron bombardment ($0.75/\text{cm}^2$) and of residual oxygen ($\sim 5 \times 10^{-6}$ Torr) on the secondary-emission ratio (δ) were performed in the Electron Bombardment Vehicle (EBV) for the following samples: 1. Three samples of $9500\text{\AA}$ evaporated aluminum on copper. 2. Two samples of $300\text{\AA}$ Al_2O_3 on Al, anodically oxidized in tartaric acid. Generally, δ_{max} varied from approximately 3.0 to 1.5. All samples showed good recovery due to O_2 and consistent degradation of δ due to electron bombardment. Test of the QKS1397 CFA vehicle for more than 50 hours has demonstrated stabilized cathode emission from an aluminum cold cathode through the use of oxygen in the pressure range of 10^{-6} to 10^{-5} Torr. The stabilized emission level reached was approximately $4 \text{ A}/\text{cm}^2$ at a duty cycle of 0.001.		

14 KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Secondary Emission Cold Cathode Crossed-Field Amplifiers Electron Bombardment Ion Bombardment Thin Films Aluminum Oxide Beryllium Oxide						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as Index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.