

UNCLASSIFIED

AD NUMBER

AD845059

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution authorized to U.S. Gov't. agencies and their contractors; Critical Technology; DEC 1968. Other requests shall be referred to Army Electronics Command, Fort Monmouth, NJ. This document contains export-controlled technical data.

AUTHORITY

usaec ltr 16 jun 1971

THIS PAGE IS UNCLASSIFIED

AD



AD 845059

Technical Report ECOM-01698 11

**LONG-LIFE
COLD CATHODE STUDIES
FOR
CROSSED-FIELD TUBES**

PROGRESS REPORT

by

L. Lesensky - M. Arum

C. McGeoch

DECEMBER 1968

DDC
R
DEC 23 1968

ECOM

UNITED STATES ARMY ELECTRONICS COMMAND · FORT MONMOUTH, N J

Contract DA28-043-AMC-01698 (E)

SPONSORED BY: ADVANCED RESEARCH PROJECTS AGENCY
ARPA ORDER NO. 345

RAYTHEON COMPANY
MICROWAVE AND POWER TUBE DIVISION
Waltham, Massachusetts

SECURITY CLASSIFICATION

This document is subject to special export controls and such restrictions to foreign governments and foreign nationals may be made necessary with prior approval of C. O. 2, Army Electronics Command, Fort Monmouth.

ACQUISITION	
CRSTI	WHITE SEC 01
DDC	RED SEC 01
WIA AD PT 1	
JUSTICE	
BY	
DISTRIBUTION STATE	
DATE	
2	

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government indorsement or approval of commercial products or services referenced herein.

Disposition

Destroy this report when it is no longer needed. Do not return it to the originator.

Technical Report ECOM-01698-11

Reports Control Symbol
OSD-1366
December 1968

LONG-LIFE COLD CATHODE STUDIES
FOR CROSSED-FIELD TUBES

Eleventh Quarterly Report
15 April 1968 to 15 July 1968

Report No. 11
Contract No. DA28-043-AMC-01698(E)
DA Project No. 7900-21-223-12-00

Prepared by

L. Lesensky
M. Arnum
C. McGeoch

RAYTHEON COMPANY
Microwave and Power Tube Division
Waltham, Massachusetts 02154

For

U. S. Army Electronics Command
Fort Monmouth, N. J. 07703

Sponsored by

Advanced Research Projects Agency
ARPA Order No. 345

DISTRIBUTION STATEMENT

This document is subject to special export
controls and may be restricted in foreign
distribution in accordance with the
provisions of the Arms Export Control Act, U. S.
Army Electronics Command, Fort Monmouth,
New Jersey
FORM 8-68 (REV. 1-68)

ABSTRACT

Tests were continued on the effects of high current-density electron bombardment (0.75 A/cm^2) and of residual gases (O_2 , N_2 , and CO_2) on the secondary emission ratio (δ) in the Electron Bombardment Vehicle (EBV). Four samples were tested during the present report period, two anodized Be samples, one electron-beam evaporated aluminum-oxide on molybdenum sample and one naturally oxidized beryllium sample. δ_{max} was found to increase: 1) in all cases for O_2 , and 2) in the case of anodized 300°A Be and natural oxide Be for N_2 and CO_2 . The samples were bombarded at 0.15 A/cm^2 with the gas present at approximately 5×10^{-6} Torr pressure. Typical increases of δ_{max} were from 2.5 to 3.5.

The QKS1397 CFA test vehicle with an evaporated Al film on Cu cold cathode has continued to run successfully a total of 330 hours to date: the last 100 hours have been run without O_2 assistance.

The QKS1194 CFA test vehicle with an impregnated-tungsten cold cathode has run approximately 150 hours to date without thermal activation.

FOREWORD

Long-life cold cathode studies for crossed-field tubes are authorized by the United States Army Electronics Command, Fort Monmouth, New Jersey, under DA Project 7900-21-223-12-00. The work was prepared with the support of the Advanced Research Projects Agency under Order No. 345 and is conducted under the technical guidance of the U.S. Army Electronics Command, Fort Monmouth, New Jersey, 07703.

TABLE OF CONTENTS

<u>Section</u>	<u>Page</u>
Abstract	iii
Foreword	iv
1.	Introduction 1
2.	Phase A - Materials Evaluation 1
2.1	Electron Bombardment Evaluation 1
2.1.1	Anodized Be - 300 Å oxide layer 2
2.1.2	Anodized Be - 300 Å oxide layer 2
2.1.3	Beryllium 2
2.1.4	300 Å Al ₂ O ₃ Film on Molybdenum 10
3.	Phase B - CFA Testing 10
3.1	QK51197 Test Vehicle 10
3.1.1	Model No. 8C 10
3.2.2	Test of QK51194 with Impregnated Tungsten Emitter 15
4.	Conclusions 16
4.1	Phase A - Materials Evaluation 16
4.2	Phase B - CFA Testing 16
5.	Program for Next Interval 17
5.1	Phase A 16
5.2	Phase B 17

LIST OF ILLUSTRATIONS

		<u>Page</u>
Figure 1.	δ_{\max} vs EBV Time for 300 Å Anodized Beryllium	3
Figure 2.	δ_{\max} vs EBV Time for 300 Å Anodized Beryllium	6
Figure 3.	δ_{\max} vs EBV Time for Naturally Oxidized Beryllium	8
Figure 4.	δ_{\max} vs EBV Time for 300 Å Al ₂ O ₃ on Molybdenum	11
Figure 5.	QKS1397 No. 8C - Running Time vs Peak Current	13

1. INTRODUCTION

The objective of the present cold-cathode study program is to achieve long life cold-cathode performance for crossed-field amplifiers. This program is being performed for the United States Army Electronics Command, Fort Monmouth, New Jersey, under contract DA-28-043-AMC-01698(E).

In this study, selected cold cathode materials will be evaluated as to their secondary emission properties, their ability to withstand environmental factors expected in a crossed-field amplifier, and their crossed-field amplifier performance. Based on the above experimental information and pertinent theoretical calculations, a life prediction chart will be established for a number of cold cathode materials.

The program is divided into two concurrent phases, Phase A being concerned with the measurement of various pertinent properties of cold cathode materials outside of the tube environment, and Phase B involving the evaluation and life testing of selected cathodes in a crossed-field amplifier.

The first quarterly report of this contract (Technical Report ECOM 01698-1) contains a discussion of the objectives and plans for the over-all program. Quarterly Report No. 5 contains a description of the CFA test vehicles used in this program.

2. PHASE A - MATERIALS EVALUATION

2-1 Electron Bombardment Evaluation. During the present quarter, a number of samples were evaluated in the Electron Bombardment Vehicle (EBV). The effect on secondary emission ratio (δ) of high current-density electron bombardment (up to 0.75 A/cm²) was measured as well as the recovery of δ with oxygen, nitrogen, and carbon dioxide.

These samples were:

- a. A 300 Å layer of BeO on Be (anodically oxidized), to a total of 140 hours (a continuation from the last quarter, when this sample ran for 37 hours).
- b. Another anodically oxidized sample of 300 Å BeO on Be, 49 hours.
- c. Naturally oxidized Be sample, 58 hours.
- d. A sample of 300 Å electron-beam-evaporated Al₂O₃ on Mo.

Sample preparation during the present quarter consisted of:

- a. Three silver-magnesium (Ag-Mg) samples for EBV evaluation were processed by thermal oxidation to achieve an optimum secondary-emission ratio. Three additional Ag-Mg samples (not thermally oxidized) are available for EBV testing.

- b. Three beryllium-copper (Be-Cu) samples were optimally processed to oxidize the surface for high secondary-emission ratio. These and three other unprocessed ones are now available for EBV evaluation.

2.1.1 Anodized Be - 300Å - oxide layer

This sample, reported in the tenth quarterly, was run for an additional 103 hours (hrs 37 to 140) and the data is presented in Figure 1. During this time, the target was exposed to residual atmospheres of O₂ and N₂ at pressures of 5x10⁻⁶ Torr; the background pressure was always approximately 1x10⁻⁸ Torr. Bombardment levels of 0.75 A/cm² (15 ma) and 0.15 A/cm² (3 ma) were used. Maximum value of secondary-emission ratio (δ) varied from a low of 2.4 to a high of 3.9 during this period.

The data taken during the first 37 hours, reported in the previous quarterly, showed a positive response to O₂ at 1x10⁻⁵ Torr. Further evaluation showed a positive response to O₂ at the same pressure starting at hour 58. Continued bombardment of 0.75 A/cm² caused δ max to decrease to 3.2 after reaching a maximum of 3.9. Subsequent efforts to determine the restorative effects of N₂ were inconclusive. δ max remained between 2.8 and 3.0, with at most a small N₂ effect which was not reproducible. Rechecking the restorative effect of O₂ at hour 99 showed a negligible effect with δ max at ~ 2.8. This may be interpreted to imply a deteriorated sample. However, a positive response to N₂ at hour 130.5 showed an increase of δ max from 2.4 to 2.85. It seems reasonable to suppose that the "condition" of the sample at that time was such that recovery with N₂ or O₂ would only be evident if δ max fell below 2.8 and that recovery would occur to a maximum value of δ max of 2.8.

2.1.2 Anodized Be - 300Å oxide layer

EBV testing was carried out over a period of 49 hours for the second anodized Be sample, evaluating the effects of O₂, N₂, and CO₂. (Figure 2) The restorative effects of these gases at a pressure of approximately 5x10⁻⁶ to 7x10⁻⁶ Torr were all positive. δ max increased typically from 2.4 to 3.5 for O₂, and from 2.4 to 3.2 for both N₂ and CO₂. The sequence of the evaluations were O₂, N₂, N₂, CO₂, and O₂. The last O₂ treatment at hour 47 showed similar results to the initial O₂ treatment at hour 5.5. Between each gas treatment the previous gas was pumped away to a residual gas pressure of approximately 1x10⁻⁸ Torr, and the secondary-emission ratio was degraded by electron bombardment at 0.75 A/cm². It thus appears that O₂, N₂, and CO₂ have a significant beneficial effect on the δ of an anodized Be surface.

2.1.3 Beryllium

A naturally oxidized Be surface (oxidation due to exposure to air at room temperature) was evaluated in the EBV for 58 hours (Figure 3).

Beneficial effects were noted for O₂, N₂, and CO₂, all at the same pressure of 6x10⁻⁶ Torr. The sequence of gas treatments was O₂, N₂, O₂, CO₂, O₂. All showed significant effects but O₂ was perhaps the most





Figure 1, Sheet 1. δ_{max} vs EBV Time for 300Å Anodized Beryllium





Figure 1, Sheet 2. δ_{max} vs EBV Time for 300Å Anodized Beryllium




Figure 1, Sheet 3. δ_{max} vs EBV Time for 300Å Anodized Beryllium




Figure 2, Sheet 1. δ_{\max} vs EBV Time for 300Å Anodized Beryllium




Figure 2, Sheet 2. δ_{\max} vs EBV Time for 300 Å Anodized Beryllium




Figure 3. Sheet 1. δ_{max} vs EBV Time for Naturally Oxidized Beryllium




Figure 3, Sheet 2, δ_{max} vs EBV Time for Naturally Oxidized Beryllium

effective. Typically, the gas treatment increased δ_{\max} from approximately 2.5 to between 3.5 and 4.0. After several gas treatments it appeared that the rate of degradation of δ due to 0.75 A/cm^2 electron bombardment had slowed down. Note hours 25 to 40 and also 43 to 56.

2.1.4 300Å Al₂O₃ Film on Molybdenum

During a 41-hour period of EBV evaluation the sample was exposed to O₂, N₂, and CO₂ (Figure 4). The initial effect of O₂ at 6×10^{-6} Torr pressure was to increase δ_{\max} from 2 to 4.2. Subsequent degradation of δ_{\max} to 2.6 due to 0.75 A/cm^2 electron bombardment was followed by an unsuccessful attempt to increase δ due to N₂ at 6×10^{-6} Torr. Following this, an O₂ treatment at 6×10^{-6} Torr did increase δ_{\max} from 2.6 to 3.05. Although this was smaller than the initial effect, the N₂ effect was decidedly much smaller than that of O₂.

Subsequent gas treatments caused only small effects with δ_{\max} varying between 2.3 and 2.75. The results during this latter portion of the EBV evaluation (hours 23 to 42) are deemed inconclusive since the "condition" of the sample was not "normal" as evidenced by the lack of a strong, positive O₂ response.

3. PHASE B - CFA TESTING

3.1 QKS1397 Test Vehicle

3.1.1 Model No. 8C. Cathode emission life-test evaluation continued on Model 8C during the report period, at a cathode-pulsed modulation test station. This model features a cathode with 0.5-mil Al coating on an OFHC copper base.

Initially, the evaluation was conducted without the use of oxygen-assistance to determine the rate of emission deterioration. The operating level chosen was as follows:

Du	=	0.0017
f _o	=	3.3 GHz
P _{in}	=	63 kW
P _{out}	=	700 kW
e _b	=	30 kV
i _b	=	45 A
B	=	3000 gauss

Peak Cathode current density = 2.8 A/cm^2

Avg. Cathode current density = 9.8 mA/cm^2

In Figure 5, the peak current obtained is shown as a function of time for the life-test duration. The plot shows a gradual decrease in the peak current for the first hour and 40 minutes. The test vehicle was shut down for




Figure 4. Sheet 1. δ_{max} vs EBV Time for 300\AA Al_2O_3 on Molybdenum




Figure 1. Comparison of the measured and calculated values of the concentration of O_2 in the water column.




Figure 1: Comparison of the results of the two different methods used for the analysis of the data.




Figure 5, Sheet 2. QKS1397 No. 8C -
Running Time vs Peak Current

one hour, and - when restarted - the peak current was slightly higher than before. The peak current again gradually decreased for one hour and 30 minutes, and after a shutdown period of 15 minutes, the peak current was higher than before shutdown. For the next one hour and 45 minutes the peak emission gradually decreased.

At this time the oxygen dispenser was activated at 63 watts of heater power for five hours. No pulsed high voltage was applied to the test vehicle, but rf drive power was present throughout. At the end of the five-hour period, the life-test evaluation resumed without the use of oxygen assistance.

Continuous operation was maintained at 47 to 50 amperes (intentionally limited to 50 amperes) for 18 hours. A trigger unit malfunction caused the test vehicle to arc at this point, with resultant loss of emission. After repair and proper phasing adjustments the peak emission was re-established at its former level.

Stable operation was maintained in this manner for 35 hours. Severe moding was now observed due to an excessively warm electromagnet (lack of coolant). The electromagnet coolant flow was re-established, and the peak emission recovered to 50 amperes. Stable operation was maintained for 27.5 hours. At this time a vacuum leak developed in the tube, terminating further evaluation. The test vehicle has been repaired and is now awaiting available modulator space for continuation of life-test evaluation.

3.1.2 Test of QKS1194 with Impregnated Tungsten Emitter

The QKS1194 cold-cathode test vehicle was placed in the final stage amplifier position of a high-power, S-band chain system. The tube was operated at the set of operating conditions established earlier and tabulated below:

e_b	(anode voltage-cathode pulsed)	46 kV
I_b	(average anode current)	650 mA
i_b	(peak anode current)	36.1 A
t_p	(pulse duration)	80 μ sec
Du	(duty factor)	.018
P_o	(average output power)	22.5 kW
p_o	(peak output power)	1.25 MW
Gain		13 dB
Peak Cathode Current Density		1.6 A/cm ²
Avg-Cathode Current Density		29.1 mA/cm ²

The tube is now operating continuously around the clock and has accumulated over 150 hours at the established set of conditions. Operation is smooth and problem-free as evidenced by more than 60 hours of performance without a kick-out or shutoff. Low-gauss emission-current-boundary data

have been repeated every 50 hours and indicate no change in cold-cathode emission.

Operation will continue until approximately 500 test hours have been accumulated. Low-gauss emission-current-boundary data will be fully evaluated to determine if the life-testing environment has produced any emission enhancement or deterioration, and graphed data will be presented in a future report.

4. CONCLUSIONS

4.1 Phase A - Materials Evaluation

- a. Both the 300Å anodized Be as well as the naturally oxidized Be samples showed significant increases in δ_{\max} as a result of O₂, N₂, and CO₂ treatments. Typical increase of δ_{\max} was from 2.5 to 3.5 using a gas pressure of approximately 5×10^{-6} Torr with a residual pressure of 1×10^{-8} Torr.
- b. A sample of 300Å Al₂O₃ on Mo showed a significantly smaller N₂ effect than for O₂ in increasing δ_{\max} .

4.2 Phase B - CFA Testing

Operation of the QKS1397 CFA test vehicle for more than 330 hours, the last 100 hours during the present report period, has shown that the available emission from a deposited-aluminum cold cathode appears to have stabilized near 50 amperes (2.8 A/cm² pk, 4.8 mA/cm² avg.) at 0.0017 duty factor. Continuous use of the oxygen dispenser for maintaining the cathode emission was not required during the last 100-hour period; instead, prior to the test run, the cathode emitter was conditioned for five hours with oxygen and rf drive power alone.

Stable operation of the QKS1194 CFA test vehicle for over 150 hours at 1.6 A/cm² peak, 29.1 mA/cm² avg, can be realized without use of any oxygen dispenser operation.

5. PROGRAM FOR NEXT INTERVAL

5.1 Phase A

- a. Continue evaluating effect of other gases such as H₂, CO₂, N₂ and CO on Al and Be cold cathodes in the EBV.
- b. Evaluate both unprocessed and optimally oxidized Ag-Mg and Be-Cu samples in the EBV.

5.2 Phase B

- a. Continue operating test of QKS1397 Model 8C with Al on Cu cathode.
- b. Rebuild the QKS1397 test vehicle with an impregnated-tungsten cathode.
- c. Continue operating test of QKS1194 with impregnated tungsten cathode.

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified.)

1 ORIGINATING ACTIVITY (Corporate author) Raytheon Company Microwave and Power Tube Division Waltham, Massachusetts		2a REPORT SECURITY CLASSIFICATION Unclassified	
		2b GROUP N/A	
3 REPORT TITLE Long-Life Cold Cathode Studies for Crossed-Field Tubes			
4 DESCRIPTIVE NOTES (Type of report and inclusive dates) Eleventh Quarterly Report 15 April 1968 - 15 July 1968			
5 AUTHOR(S) (Last name, first name, initial) Lesensky, L., Arnum, M., and McGeoch, C.			
6 REPORT DATE December 1968		7a TOTAL NO. OF PAGES 17	7b NO. OF REFS 0
8a CONTRACT OR GRANT NO. DA28-043-AMC-01698(E)		9a. ORIGINATOR'S REPORT NUMBER(S) PT-1999	
b. PROJECT NO. 7900-21-223-12-00		9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) ECOM-01698-11	
c.			
d.			
10 AVAILABILITY/LIMITATION NOTICES This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with prior approval of CG, USAECOM, ATTN: AMSEL-KL-TD, Fort Monmouth, N. J. 07703			
11. SUPPLEMENTARY NOTES Advanced Research Projects Agency Contract ARPA Order No. 345		12. SPONSORING MILITARY ACTIVITY U. S. Army Electronics Command Fort Monmouth, N. J. 07703 AMSEL-KL-TD	
13 ABSTRACT Tests were continued on the effects of high current-density electron bombardment (0.75 A/cm^2) and of residual gases (O_2 , N_2 , and CO_2) on the secondary emission ratio (δ) in the Electron Bombardment Vehicle (EBV). Four samples were tested during the present report period, two anodized Be samples, one electron-beam-evaporated aluminum-oxide on molybdenum sample and one naturally oxidized beryllium sample. δ_{max} was found to increase: 1) in all cases for O_2 , and 2) in the case of anodized 300 Å Be and natural oxide Be for N_2 and CO_2 . The samples were bombarded at 0.15 A/cm^2 with the gas present at approximately 5×10^{-6} Torr pressure. Typical increases of δ_{max} were from 2.5 to 3.5. The QKS1397 CFA test vehicle with an evaporated Al film on Cu cold cathode has continued to run successfully a total of 330 hours to date, the last 100 hours having been run without O_2 assistance. The QKS1194 CFA test vehicle with an impregnated-tungsten cold cathode has run approximately 150 hours to date without thermal activation.			

KEY WORDS

LINK A

LINK B

LINK C

ROLE

WT

ROLE

WT

ROLE

WT

Secondary Emission
Cold Cathode
Crossed-Field Amplifiers
Electron Bombardment
Ion Bombardment
Thin Films
Aluminum Oxide
Beryllium Oxide

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.
- 2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.
- 2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.
3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.
4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.
5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.
6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.
- 7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.
- 7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.
- 8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.
- 8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.
- 9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.
- 9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).
10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.