



AFRL-AFOSR-VA-TR-2016-0025

SEARCH FOR AND STUDY OF NOVEL SUPERCONDUCTOR WITH HIGHER TC AND JC

**Ching-Wu Chu
UNIVERSITY OF HOUSTON SYSTEM**

**12/22/2015
Final Report**

DISTRIBUTION A: Distribution approved for public release.

**Air Force Research Laboratory
AF Office Of Scientific Research (AFOSR)/ RTB1
Arlington, Virginia 22203
Air Force Materiel Command**

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.

1. REPORT DATE (DD-MM-YYYY) 14-12-2015	2. REPORT TYPE Final	3. DATES COVERED (From - To) 15 Sep 2009 - 14 Sep 2015
--------------------------------------------------	--------------------------------	------------------------------------------------------------------

4. TITLE AND SUBTITLE Search for and Study of Novel Superconductor with Higher Tc and Jc	5a. CONTRACT NUMBER
	5b. GRANT NUMBER FA9550-09-1-0656
	5c. PROGRAM ELEMENT NUMBER

6. AUTHOR(S) Chu, Paul C. W.	5d. PROJECT NUMBER
	5e. TASK NUMBER
	5f. WORK UNIT NUMBER

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Houston 316 E. Cullen Building, 4800 Calhoun Houston TX 77204-2015	8. PERFORMING ORGANIZATION REPORT NUMBER
-----------------------------------------------------------------------------------------------------------------------------------------------------	-------------------------------------------------

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AF OFFICE OF SCIENTIFIC RESEARCH 875 NORTH RANDOLPH STREET ROOM 3112 ARLINGTON VA 22203	10. SPONSOR/MONITOR'S ACRONYM(S)
	11. SPONSOR/MONITOR'S REPORT NUMBER(S)

12. DISTRIBUTION/AVAILABILITY STATEMENT
Distribution A - Approved for Public Release

13. SUPPLEMENTARY NOTES

14. ABSTRACT
The AFOSR support has enabled us to discover new superconductors with higher Tc, for science and potential new applications, or with low Tc but with novel structure-types for new discoveries; to realize new superconducting mechanism for higher Tc; to unravel new physics important to high Tc and Jc; to discover new physics and phenomena in non-superconducting but related compounds for HTS development and devices; to develop single-crystal growth capability and new techniques; to evaluate immediately new discoveries; and to compete effectively against foreign HTS groups. A record Tc up to 49K was discovered in the rare-earth doped CaFe2As2 system, highest in the Fe-based 122 family; the unusually high Tc is attributed to the possible interfacial enhancement mechanism, opening up a new avenue to higher Tc. Interface effect in the artificially grown FeSe/STO system was carefully studied. More than ten new superconductors were discovered, and provide new directions and new synthetic routes to search for higher Tc. New physics and phenomena were discovered in both superconducting and non-superconducting compounds including cuprates, other Fe-based superconductors, multiferroics, topological insulators, and thermoelectric and thermal-conducting materials.

15. SUBJECT TERMS
High Temperature Superconductivity; Superconductivity; Multiferroics

16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES 10	19a. NAME OF RESPONSIBLE PERSON Paul C. W. Chu
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (Include area code) 713-743-8222

INSTRUCTIONS FOR COMPLETING SF 298

1. REPORT DATE. Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

2. REPORT TYPE. State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

3. DATES COVERED. Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

4. TITLE. Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

5a. CONTRACT NUMBER. Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

5b. GRANT NUMBER. Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

5c. PROGRAM ELEMENT NUMBER. Enter all program element numbers as they appear in the report, e.g. 61101A.

5d. PROJECT NUMBER. Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

5e. TASK NUMBER. Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

5f. WORK UNIT NUMBER. Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

6. AUTHOR(S). Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES). Self-explanatory.

8. PERFORMING ORGANIZATION REPORT NUMBER. Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES). Enter the name and address of the organization(s) financially responsible for and monitoring the work.

10. SPONSOR/MONITOR'S ACRONYM(S). Enter, if available, e.g. BRL, ARDEC, NADC.

11. SPONSOR/MONITOR'S REPORT NUMBER(S). Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

12. DISTRIBUTION/AVAILABILITY STATEMENT. Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

13. SUPPLEMENTARY NOTES. Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

14. ABSTRACT. A brief (approximately 200 words) factual summary of the most significant information.

15. SUBJECT TERMS. Key words or phrases identifying major concepts in the report.

16. SECURITY CLASSIFICATION. Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

17. LIMITATION OF ABSTRACT. This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

AFOSR Final Report: 9/15/2009 - 9/14/2015

Title: Search for and Study of Novel Superconductor with Higher T_c and J_c

Grant Number: FA9550-09-1-0656

PI: Dr. Ching-Wu Chu

Program Manager: Dr. Harold Weinstock

Accomplishments

- Synthesized and characterized large single crystals of rare-earth doped (Ca,RE)122 system with RE = , La, Ce, Pr and Nd, with onset- T_c of 42-49 K, higher than any compounds *R*-Ca-Fe-As previously known, and representing as the highest T_c in the Fe-based 122 family.
- Demonstrated the non-bulk nature, two superconducting transitions, and unusually high magnetic anisotropy in the (Ca,RE)122 system. The high onset- T_c is also found to be RE-independent and dopant concentration independent.
- Carried out detailed chemical composition, magnetization, transport, low temperature annealing effects, Raman, ARPES, and STM studies for the (Ca,RE)122 system, excluded the possibilities of the 49K SC transition being caused by an optimally doped 122, an oxygen-deficient 1111 phase due to contamination by oxygen, or an unknown residual-strain-induced precipitate resulting from the collapsed tetragonal phase transition, and attributed the cause for the unusually high T_c to the possible long-sought-after interfacial enhancement mechanism of naturally grown FeAs layers with different defect structures.
- Performed detailed dc, ac, sheet resistance and aging effect measurements on the 1-4 UC FeSe/STO thin films synthesized by Xue's group in Tsinghua, using a novel technique developed by us and observed: a Meissner state below ~ 20 K; a mesoscopic state with superconducting patches between ~ 20 and 45 K; and a yet-to-be-determined state between ~ 45 and 80 K with a logarithmic frequency dispersion.
- Designed a Fully Integrated MBE (Growth) and Characterization System (AFM/STM, ARPES, Magneto-resistance) to further investigate the interface superconductivity mechanism for different materials. The system will have the following specifications: (I) MBE thin film growth with (II) a load lock chamber, (III) a sample preparation chamber with the capability to accommodate an ARPES characterization system at a later stage, (IV) an STM/AFM chamber, and (V) a magneto-resistance chamber to be added later, with the help of world-wide MBE experts (Q. K. Xue in China and I. Bozovic at BNL) and in-house expert (A. Bensaoula). The system is expected to be delivered in September 2016 and we are ready to fabricate high quality thin films.
- Discovered the new superconductor (Ba,Na)Ti₂Sb₂O with T_c up to 5.5 K, displaying anti-perovskite Ti₂O layer structure (as compared to the CuO₂ planes in HTS).
- Discovered the new superconductor Zr₅Sb₃ with a T_c of 2.3 K, the first superconductor discovered by us in a compound system of Mn₅Si₃-structure type that consists of a large number of compounds.
- Discovered a series of Pt-related new superconductors with distinct structure features: SrPt₃P ($T_c = 8.6$ K) with anti-perovskite structure, SrPt₆P₂ ($T_c = 0.6$ K) with anti-trigonal prism structure, and SrPt₁₀P₄ ($T_c = 1.5$ K) with new type of structure.
- Systematically grew and studied a series of Pd-based new superconductors: layered compound β -PdBi₂, hole-doped PdBi_{2-x}Pb_x, and electron-doped Na_xPdBi₂ single crystals with maximum T_c at 5.5K.

- Induced bulk superconductivity up to 4 K in ZrTe₃ single crystals without chemical doping or physical pressure by processing induced-defects, and provided a new route to induce superconductivity in other materials such as multiferroics.
- Discovered precursor-dependent superconducting/nonsuperconducting properties in the Rb_xFe₂Se₂ single crystals with T_c up to 32-K.
- Carried out systematic pressure study up to 1.8GPa on all of the compounds mentioned above. Besides the above compounds, we also studied the pressure dependence in both superconducting compounds such as FeSe_{0.5}Te_{0.5} thin films and Fe pnictide 122s, and non-superconducting compounds such as SrCu₄As₂, Sr_{1-x}K_xCu₄As₂, and RFe₂Si₂.
- Synthesized the topological insulator Bi₂Se₃, and 3.8-K Cu_xBi₂Se₃ “topological superconductor” single crystals, carried out nanoscale Andreev reflection spectroscopy study on Cu_xBi₂Se₃ and called for a reexamination of the reported signature of topological superconductivity in Cu_xBi₂Se₃.
- Discovered a drastic superconducting-semiconducting transition in YBCO at ~ 30 GPa.
- Demonstrated that the pressure induced SC state in Ca122 is bulk through specific heat measurement under press, in contrast to previous suggestion.
- Continued to carry out systematically magnetic, resistivity, specific heat, Hall effect, high pressure, annealing effect to study both the normal and superconducting properties of different types of Fe-based superconductors.
- Attempted to look for superconductivity in the other 122 system without pnictides such as RFe₂Si₂ and R(Fe_{1-x}M_x)₂Si₂(x = 0-1) systems (R = La, Y and Lu, M = Ni, Mn and Cu). No superconductivity is observed, although some interesting long-range magnetic order is observed which is systemically changing with different rare earth elements and different transition metal doping.
- Attempted to look for superconductivity in Cu-based pnictide Cu-based compounds: 111 family- CaCuP, CaCuAs, SrCuP, SrCuAs, BaCuP, BaCuAs, EuCuP, EuCuAs; 122 family- CaCu_{2-x}As₂, SrCu_{2-x}As₂, BaCu_{2-x}As₂, EuCu_{2-x}As₂, EuCu₂Sb₂; and 142 family- KCu₄As₂, RbCu₄As₂, CaCu₄As₂, SrCu₄As₂, BaCu₄As₂, EuCu₄As₂, KCu₄As₂, NaCu₄Sb₂, and KCu₄Sb₂, in polycrystalline and single crystalline form, and some selected doping studies as well.
- Discovered two completely new phase of BaCu₂As₂ deriving from the typical ThCr₂Si₂ type with very sensitive temperature-dependent formation mechanism.
- Extended our research field to other AFOSR mission related system such as super-thermal-conducting materials, thermoelectric materials with higher ZT and better performance, topological insulators and superconductors, and 2D transition metal dichalcogenides.
- Provided experimental evidence of a temperature-induced orbital-selective Mott transition (OSMT) in the A_xFe_{2-y}Se₂ (A=K, Rb), in collaboration with Z. X. Shen’s group.
- Observed broken time reversal and parity symmetries of the superconducting state of LiFeAs through magnetic torque and magnetization measurements at high fields, in collaboration with Luis Balicas of NHMFL.
- Studied quasiparticle relaxation utilizing ultrafast optical spectroscopy in stoichiometric LiFeAs crystals and (K, Ba)Fe₂As₂ crystals in collaboration with M. K. Wu’s group at Academia Sinica.
- Calculated the Superfluid Density in the s_±-Wave State of Clean Iron-Based Superconductors and showed that the Uemura relation also holds for the Fe-based superconductors (Ting’s group).

- Theoretically investigated the Interaction-Induced Localization of Fermionic Mobile Impurities in a Larkin-Ovchinnikov Superfluid in a two-dimensional optical lattice and showed that the impurity atoms can localize and form pairs when the interaction between the impurity atoms and the LO superfluid is strong (Ting's group).
- Proposed the detection of time-reversal symmetry in topological surface states (Ting's group).
- Studied the 122, 111, and 11 compounds with emphasis on their electronic structures and atomic defects by our home built STM; also started to study the 111 and 11 compounds and observed unusual features that challenges existing theoretical models (Pan's group).
- Discovered the possibility of electrically charging multiferroic domain walls by applying a magnetic field to $\text{Mn}_{0.95}\text{Co}_{0.05}\text{WO}_4$.
- Found and explained a spontaneous polarization reversal in the multiferroic $\text{Mn}_{0.85}\text{Co}_{0.15}\text{WO}_4$ when cooled in external magnetic field; this property is most likely related to the formation of domains of different multiferroic phases and indicates a strong coupling across the domain walls.
- Investigated the details of the helical magnetic order of $\text{Mn}_{1-x}\text{Co}_x\text{WO}_4$ through magnetic, dielectric, and elastic neutron scattering experiments and acquired a fundamental understanding of the complex magnetic orders and the relation to ferroelectricity, have revealed the complete phase diagram showing multiple polarization flops upon Co doping.
- Determined the most fundamental magnetic exchange coupling constants of MnWO_4 through inelastic neutron scattering experiments and found that the interactions are long-ranged, extending to far distant neighbors.
- Studied the effect of nickel doping on the ferroelectric properties of MnWO_4 and found an unusual anti-correlation between the easy axis of the Ni spin and the orientation of the spin cycloid in the multiferroic phase.
- Grew large single crystals of several pure and doped multiferroics and demonstrated that the nature of dopants, including Fe, Co, Ni, Cu, Zn, can change the characteristics of the phase diagram in MnWO_4 .
- Observed a field-induced change of the electronic band gap in the multiferroic $\text{Ni}_3\text{V}_2\text{O}_8$ single crystals grown via floating zone optical furnace.
- Studied the pressure effect on the multiferroic properties of GdMn_2O_5 and found a pressure-induced splitting of the ferroelectric phase into two phases, indicating a decoupling of the rare earth and Mn spin systems due to the compression of the c-axis.
- Systematically studied the role of the rare earth moment in the magnetoelectric system $\text{RAl}_3(\text{BO}_3)_4$ for R=Tb, Ho, Er, Tm and solid solutions of different compounds.
- Discovered a giant magnetoelectric effect in $\text{HoAl}_3(\text{BO}_3)_4$ setting a record for the value of the field-induced polarization at this time.
- Discovered and studied the antiferromagnetic phase and the field-induced spin-flop transition in the polar compound LiCrP_2O_7 (isostructural to the magnetoelectric LiFeP_2O_7); found that the magnetic order in LiCrP_2O_7 is very different from LiFeP_2O_7 , which explains the missing magnetoelectric property in the former compound.
- Discovered an unusual magnetic order and strong magnetoelectric and magnetoelastic interactions in the polar compound LiFeP_2O_7 , and developed a comprehensive Landau theory describing the magnetic order and the magnetoelectric effect.
- Discovered a structural and magnetic transition in the new compound $\text{Nb}_2\text{O}_2\text{F}_3$ with extremely slow transformation kinetics. Pairing of Nb-Nb dimers is observed with electrons forming spin singlet states and quenching the magnetic moment.

- Discovered and studied the magnetic order and a temperature-induced spin rotation in the transition metal-organic compound $\text{CH}(\text{NH}_2)_2\text{Mn}(\text{HCOO})_3$; CN_2 molecules in this structure have a dipolar momentum and the question whether or not the dipoles order and give rise to a ferro-(antiferro-) electric state and multiferroic properties is of interest; first dielectric data show evidence for a dielectric transition just below room temperature.
- Studied the properties of low-dimensional, frustrated magnetic vanadate systems with super-super exchange interactions, $\text{A}\text{Ag}_2\text{M}[\text{VO}_4]_2$ ($\text{A}=\text{Ba}, \text{Sr}$ and $\text{M}=\text{Co}, \text{Ni}, \text{Cu}$), and discovered ferromagnetic as well as antiferromagnetic orders and novel magnetic properties.
- Determined the quantum criticality in doped Sr and Ba122.
- Discovered the existence of quantum (Shubnikov-de Haas) oscillations in metallic $\text{Bi}_2(\text{Te},\text{Se})_3$ arising from topological surface as well as trivial bulk states in different ranges of the applied magnetic field. This solves the conundrum why the surface oscillations have been so clearly observed by us in metallic $\text{Bi}_2(\text{Te},\text{Se})_3$.
- Detected weak antilocalization effects in Bi_2Te_3 topological insulators. We could show that the charge carrier density, but not their nature (electrons or holes), determine whether or not the antilocalization effects arise from bulk or topological surface states.
- Found quantum oscillations from topological surface states in the new topological insulator $\text{Sb}_2\text{Te}_2\text{Se}$. Here the quantum oscillations are very pronounced and no bulk oscillations could be detected.

Archival Publications

- “Electrical Characterization of Resistive Memory in Metal-Pr_{0.7}Ca_{0.3}MnO₃ Interface: A Future Non-Volatile Memory Device,” N. Das, Y. Y. Xue, Y. Q. Wang and C. W. Chu, Proceedings of the 10th Annual Non-Volatile Memory Technology Symposium (NVMTS), October 25-28, 2009 (IEEE, 2009), pp. 28-47.
- “Kinetics and Relaxation of Electroresistance in Transition Metal Oxides: Model for Resistive Switching,” N. Das, S. Tsui, Y. Y. Xue, Y. Q. Wang and C. W. Chu, Phys. Rev. B 80, 115411 (2009).
- “Critical Scaling of Transport Properties in the Phase Diagram of Iron Pnictide Superconductors K_xSr_{1-x}Fe₂As₂ and K_xBa_{1-x}Fe₂As₂,” M. Gooch, B. Lv, B. Lorenz, A. M. Guloy, and C. W. Chu, Journal of Applied Physics 107, 09E145 (2010).
- “Evidence for Multiple Gaps in Specific Heat of LiFeAs Crystals,” F. Wei, F. Chen, K. Sasmal, B. Lv, Z. J. Tang, Y. Y. Xue, A. M. Guloy and C. W. Chu, Phys. Rev. B 81, 134527 (2010).
- “Magnetic and Multiferroic Phases of Single-Crystalline Mn_{0.85}Co_{0.15}WO₄,” R. P. Chaudhury, F. Ye, J. A. Fernandez-Baca, Y. Q. Wang, Y. Y. Sun, B. Lorenz, H. A. Mook and C. W. Chu, Phys. Rev. B 82, 184422 (2010).
- “Magnetic Phase Diagram and Magnetoelectric Properties of Ho_{0.25}Nd_{0.75}Fe₃(BO₃)₄,” R. P. Chaudhury, B. Lorenz, Y. Y. Sun, L. N. Bezmaternykh, V. L. Temerov, and C. W. Chu, Journal of Applied Physics 107, 09D913 (2010).
- “Magnetoelectricity and Magnetostriction due to the Rare Earth Moment in TmAl₃(BO₃)₄,” R. P. Chaudhury, B. Lorenz, Y. Y. Sun, L. N. Bezmaternykh, V. L. Temerov and C. W. Chu, Phys. Rev. B 81, 220402(R) (2010).
- “Superconductivity in Ternary Iron Pnictides: AFe₂As₂ (A = Alkali Metal) and LiFeAs,” M. Gooch, B. Lv, K. Sasmal, J. H. Tapp, Z. J. Tang, A. M. Guloy, B. Lorenz and C. W. Chu, Physica C 470, S276 (2010).
- “A Possible Pressure-Induced Superconducting-Semiconducting Transition in Nearly Optimally Doped Single Crystalline YBa₂Cu₃O_{7-δ},” T. Muramatsu, D. Pham and C. W. Chu, Appl. Phys. Lett. 99, 052508 (2011).
- “Carrier Contribution to the Specific Heat Coefficient of Sr_{1-x}K_xFe₂As₂,” F. Y. Wei, B. Lv, F. Chen, Y. Y. Xue, and C. W. Chu, Phys. Rev. B 83, 024503 (2011).
- “Doping Dependence of Phase-Separation Morphology in (Sr,K)Fe₂As₂,” F. Y. Wei, B. Lv, F. Chen, K. Sasmal, J. Shulman, Y. Y. Xue, and C. W. Chu, Phys. Rev. B 83, 094517 (2011).
- “Electronic Band Structure of SrCu₄As₂ and KCu₄As₂: Metals with Diversely Doped CuAs Layers,” V. G. Hadjiev, B. Lv and C. W. Chu, Phys. Rev. B "Brief Reports" 84, 073105 (2011).
- “Generation of Negative Capacitance in a Nanocolloid,” J. Shulman, Y. Y. Xue, S. Tsui, F. Chen and C. W. Chu, J. Appl. Phys. 109, 034304 (2011).
- “Giant Magnetoelectric Effect in HoAl₃(BO₃)₄,” K.-C. Liang, R. P. Chaudhury, B. Lorenz, Y. Y. Sun, L. N. Bezmaternykh, V. L. Temerov and C. W. Chu, Phys. Rev. B "Rapid Communications" 83, 180417 (2011).
- “High-Pressure Study of Superconducting and Nonsuperconducting Single Crystals of the Same Nominal Composition Rb_{0.8}Fe₂Se₂,” M. Gooch, B. Lv, L. Z. Deng, T. Muramatsu, J. Meen, Y. Y. Xue, B. Lorenz and C. W. Chu, Phys. Rev. B 84, 184517 (2011).
- “Incommensurate Spin-Density Wave and a Multiband Superconductivity Phase in Na_xFeAs Revealed by Nuclear Magnetic Resonance,” M. Klanjšek, P. Jeglič, B. Lv, A. M. Guloy, C. W. Chu and D. Arčon, Phys. Rev. B 84, 054528 (2011).

- "Long-Range Magnetic Interactions in the Multiferroic Antiferromagnetic MnWO_4 ," F. Ye, R. S. Fishman, J. A. Fernandez-Baca, A. A. Podlesnyak, G. Ehlers, H. A. Mook, Y. Q. Wang, B. Lorenz and C. W. Chu, *Phys. Rev. B*, "Rapid Communications" 83, 140401 (2011).
- "Multiferroic Phase Control in MnWO_4 Doped with Fe, Co, and Zn: A Comparative Study," K.-C. Liang, R. P. Chaudhury, B. Lorenz, Y. Q. Wang, Y. Y. Sun and C. W. Chu, *Integrated Ferroelectrics* 131, 47 (2011).
- "Raman Scattering Study of Electron-Doped $\text{Pr}_x\text{Ca}_{1-x}\text{Fe}_2\text{As}_2$ Superconductors," A. P. Litvinchuk, B. Lv and C. W. Chu, *Phys. Rev. B* 84, 092504 (2011).
- "Robust Ferroelectric State in Multiferroic $\text{Mn}_{1-x}\text{Zn}_x\text{WO}_4$," R. P. Chaudhury, F. Ye, J. A. Fernandez-Baca, B. Lorenz, Y. Q. Wang, Y. Y. Sun, H. A. Mook and C. W. Chu, *Phys. Rev. B* 83, 014401 (2011).
- "The Evolution of HTS: T_c -Experiment Perspectives," C. W. Chu, Ch. 16 in *50 Years of Bardeen, Cooper and Schrieffer*, ed. by L. N. Cooper and D. Feldman (Singapore: World Scientific, 2011), p. 391.
- "Two-Gap Features in the Specific Heat of $(\text{M},\text{K})\text{Fe}_2\text{As}_2$ with $\text{M} = \text{Ba}, \text{Sr}$," F. Y. Wei, B. Lv, Y. Y. Xue and C. W. Chu, *Phys. Rev. B* 84, 064508 (2011).
- "Unusual Superconducting State at 49 K in Electron-Doped CaFe_2As_2 at Ambient Pressure," B. Lv, L. Z. Deng, M. Gooch, F. Y. Wei, Y. Y. Sun, J. K. Meen, Y. Y. Xue, B. Lorenz and C. W. Chu, *Proceedings of the National Academy of Sciences USA* 108, 15705 (2011).
- "A Possible Approach from BCS through HTS to RTS with Three Examples," C. W. Chu, *Physica C* 482, 33 (2012).
- " $\text{AAg}_2\text{M}[\text{VO}_4]_2$ ($\text{A} = \text{Ba}, \text{Sr}$; $\text{M} = \text{Co}, \text{Ni}$): A Series of Ferromagnetic Insulators," A. Möller, N. E. Amuneke, P. Daniel, B. Lorenz, C. R. dela Cruz, M. Gooch and C. W. Chu, *Phys. Rev. B* 85, 214422 (2012).
- " $\text{Ba}_{1-x}\text{Na}_x\text{Ti}_2\text{Sb}_2\text{O}$ ($0.0 \leq x \leq 0.33$): A Layered Titanium-Based Pnictide Oxide Superconductor," P. Doan, M. Gooch, Z. J. Tang, B. Lorenz, A. Möller, J. Tapp, C. W. Chu and A. M. Guloy, *Journal of the American Chemical Society* 134, 16520 (2012).
- "Cuprates—Superconductors with a T_c up to 164 K," C. W. Chu, Section 4.4 of Chapter 4, "Materials," in *100 Years of Superconductivity*, ed. by H. Rogalla and P. H. Kes (Boca Raton FL: Taylor & Francis/CRC, 2012), p. 244.
- "Field-Induced Continuous Rotation of the Polarization in Multiferroic $\text{Mn}_{0.95}\text{Co}_{0.05}\text{WO}_4$," K.-C. Liang, R. P. Chaudhury, Y. Q. Wang, Y. Y. Sun, B. Lorenz, and C. W. Chu, *Journal of Applied Physics* 111, 07D903 (2012).
- "Magnetic order and spin-flop transitions in the cobalt-doped multiferroic $\text{Mn}_{1-x}\text{Co}_x\text{WO}_4$," F. Ye, S. X. Chi, J. A. Fernandez-Baca, H. B. Cao, K.-C. Liang, Y. Q. Wang, B. Lorenz and C. W. Chu, *Phys. Rev. B* 86, 094429 (2012).
- "Magnetoelectricity in the System $\text{RAI}_3(\text{BO}_3)_4$ ($\text{R} = \text{Tb}, \text{Ho}, \text{Er}, \text{Tm}$)," K.-C. Liang, R. P. Chaudhury, B. Lorenz, Y. Y. Sun, L. N. Bezmaternykh, I. A. Gudim, V. L. Temerov and C. W. Chu, *Journal of Physics: Conference Series* 400, 032046 (2012).
- "Materials," C. W. Chu, Section 4.1 of Chapter 4, "Materials," in *100 Years of Superconductivity*, ed. by H. Rogalla and P. H. Kes (Boca Raton FL: Taylor & Francis/CRC, 2012), p. 233.
- "Pressure Effects on Strained $\text{FeSe}_{0.5}\text{Te}_{0.5}$ Thin Films," M. Gooch, B. Lorenz, S. X. Huang, C. L. Chien and C. W. Chu, *J. Appl. Phys.* 111, 112610 (2012).
- "Spin Dynamics in the Multiferroic Materials," F. Ye, R. S. Fishman, J. Haraldsen, B. Lorenz, C. W. Chu and T. Kimura, *J. Appl. Phys.* 111, 07E137 (2012).

- "The Complex Multiferroic Phase Diagram of $Mn_{1-x}Co_xWO_4$," K.-C. Liang, Y.-Q. Wang, Y. Y. Sun, B. Lorenz, F. Ye, J. A. Fernandez-Baca, H. A. Mook and C. W. Chu, *New Journal of Physics* 14, 073028 (2012).
- "Thermodynamic Evidence for Pressure-Induced Bulk Superconductivity in the Fe-As Pnictide Superconductor $CaFe_2As_2$," Y. Zheng, Y. Wang, B. Lv, C. W. Chu and R. Lortz, *New Journal of Physics* 14, 053034 (2012).
- "Weak Ferromagnetism and Internal Magnetoelectric Effect in Multiferroic $LiFeP_2O_7$," K.-C. Liang, W. Zhang, B. Lorenz, Y. Y. Sun, P. S. Halasyamani and C. W. Chu, *Phys. Rev. B* 86, 094414 (2012).
- "Absence of zero-energy surface bound states in $Cu_xBi_2Se_3$ studied via Andreev reflection spectroscopy," H. B. Peng, D. De, B. Lv, F. Y. Wei, and C. W. Chu, *Physical Review B* 88, 024515 (2013).
- "Anomalous hysteresis as evidence for a magnetic-field-induced chiral superconducting state in $LiFeAs$," G. Li, R. R. Urbano, P. Goswami, C. Tarantini, B. Lv, P. Kuhns, A. P. Reyes, C. W. Chu and L. Balicas, *Phys. Rev. B* 87, 024512 (2013).
- "Disorder-induced bulk superconductivity in $ZrTe_3$ single crystals via growth control," X. Y. Zhu, B. Lv, F. Y. Wei, Y. Y. Xue, B. Lorenz, L. Z. Deng, Y. Y. Sun, and C. W. Chu, *Phys. Rev. B* 87, 024508 (2013).
- "Experimental Investigation of the Electronic Structure of $Ca_{0.83}La_{0.17}Fe_2As_2$," Y. B. Huang, P. Richard, J. H. Wang, X. P. Wang, X. Shi, N. Xu, Z. Wu, A. Li, J. X. Yin, T. Qian, B. Lv, C. W. Chu, S. H. Pan, M. Shi and H. Ding, *Chinese Physics Letters* 30, 017402 (2013).
- "Hexagonal Manganites—(RMnO₃): Class (I) Multiferroics with Strong Coupling of Magnetism and Ferroelectricity," B. Lorenz, *ISRN Condensed Matter Physics* 2013, 497073 (2013).
- "High pressure study of the normal and superconducting states of the layered pnictide oxide $Ba_{1-x}Na_xTi_2Sb_2O$ with $x = 0, 0.10, \text{ and } 0.15$," M. Gooch, P. Doan, B. Lorenz, Z. J. Tang, A. M. Guloy, and C. W. Chu, *Supercond. Sci. Technol.* 26, 125011 (2013).
- "Nanoscale Surface Element Identification and Dopant Homogeneity in the High- T_c Superconductor $Pr_xCa_{1-x}Fe_2As_2$," I. Zeljkovic, D. Huang, C. L. Song, B. Lv, C. W. Chu and J. E. Hoffman, *Phys. Rev. B* 87, 201108(R) (2013).
- "Observation of Temperature-Induced Crossover to an Orbital-Selective Mott Phase in $A_xFe_{2-y}Se_2$ ($A=K, Rb$) Superconductors," M. Yi, D. H. Lu, R. Yu, S. C. Riggs, J. H. Chu, B. Lv, Z. K. Liu, M. Lu, Y.-T. Cui, M. Hashimoto, S.-K. Mo, Z. Hussain, C. W. Chu, I. R. Fisher, Q. Si and Z. X. Shen, *Phys. Rev. Lett.* 110, 067003 (2013).
- "Superconductivity in the Mn_5Si_3 -type Zr_5Sb_3 system," B. Lv, X. Y. Zhu, B. Lorenz, F. Y. Wei, Y. Y. Xue, Z. P. Yin, G. Kotliar and C. W. Chu, *Physical Review B* 88, 134520 (2013).
- "The Meissner and Mesoscopic Superconducting States in 1-4 Unit-Cell FeSe-Films up to 80 K," L. Z. Deng, B. Lv, Z. Wu, Y. Y. Xue, W. H. Zhang, F. S. Li, L. L. Wang, X. C. Ma, Q. K. Xue and C. W. Chu, arXiv:1311.6459 [cond-mat.supr-con]
- "The Rise of T_c : A Promising Paradigm via Interfacial Mechanism," C. W. Chu, B. Lv, L. Z. Deng, B. Lorenz, B. Jawdat, M. Gooch, K. Shrestha, K. Zhao, X. Y. Zhu, Y. Y. Xue, and F. Y. Wei, *Proceedings of the 10th International Conference on Materials and Mechanisms of Superconductivity (M2S-X)*, Washington DC, July 29 - August 3, 2012, *Journal of Physics: Conference Series* 449, 012014 (2013).
- "The simultaneous occurrence of superparamagnetism and superconductivity in nominal single crystalline $(Ca_{1-x}Pr_x)Fe_2As_2$ with $0 \leq x \leq 0.13$," B. Lv, F. Y. Wei, L. Z. Deng, Y. Y. Xue, and C. W. Chu, submitted for publication in *Appl. Phys. Lett.* (revised November 15, 2013).

- "Top-Seeded Single Crystal Growth, Structure, and Physical Properties of Polar LiCrP_2O_7 ," E. Pachoud, W. G. Zhang, J. H. Tapp, K.-C. Liang, B. Lorenz, C. W. Chu, and P. S. Halasyamani, *Crystal Growth & Design* 13, 5473 (2013).
- "Weak Coupling BCS-like Superconductivity in the Pnictide Oxide $\text{Ba}_{1-x}\text{Na}_x\text{Ti}_2\text{Sb}_2\text{O}$ ($x=0$ and 0.15)," M. Gooch, P. Doan, Z. J. Tang, B. Lorenz, A. M. Guloy, and C. W. Chu, *Phys. Rev. B* 88, 064510 (2013).
- "Anomalous Vibrational Properties of Cubic Boron Arsenide," V. G. Hadjiev, M. N. Iliev, B. Lv, Z. F. Ren, and C. W. Chu, *Physical Review B* 89, 024308 (2014).
- "Comparison of Pr-doped Ca 122 and Ca 112 Pnictides by Low-field Microwave Absorption Spectroscopy," A. R. Howard, J. D. Yuen, B. Lv, M. Salamon, C. W. Chu, and A. A. Zakhidov, *MRS Proceedings*, 1684, mrs14-1684-t13-05 doi:10.1557/opl.2014.869 (2014).
- "Control of Improper Ferroelectricity by Chemical Substitution and Magnetic Fields in Multiferroic $\text{Mn}_{1-x}\text{Cu}_x\text{WO}_4$," K.-C. Liang, Y. Q. Wang, Y. Y. Sun, B. Lorenz and C. W. Chu, *Ferroelectrics* 470, 43 (2014).
- "High Thermal Conducting Boron Arsenide: Crystal Growth and Characterization," B. Lv, Y. C. Lan, X. Q. Wang, Q. Zhang, Y. J. Hu, A. J. Jacobson, D. Broido, G. Chen, Z. F. Ren, and C. W. Chu, submitted to *Advanced Materials* (September 9, 2014).
- "Lattice dynamics and spin-phonon coupling in CaMn_2O_4 : A Raman study," V. G. Ivanov, V. G. Hadjiev, A. P. Litvinchuk, D. Z. Dimitrov, B. L. Shivachev, M. V. Abrashev, B. Lorenz, and M. N. Iliev, *Physical Review B* 89, 184307 (2014).
- "Magnetic and Structural Relationship of RFe_2Si_2 and $\text{R}(\text{Fe}_{1-x}\text{M}_x)_2\text{Si}_2$ ($x = 0-1$) Systems ($\text{R} = \text{La}$, Y and Lu , $\text{M} = \text{Ni}$, Mn and Cu)," I. Felner, B. Lv, and C. W. Chu, *Journal of Physics: Condensed Matter* 26, 476002 (2014).
- "Magnetic-field-induced shift of the optical band gap in $\text{Ni}_3\text{V}_2\text{O}_8$," P. Chen, B. S. Holinsworth, K. R. O'Neal, T. V. Brinzari, D. Mazumdar, Y. Q. Wang, S. McGill, R. J. Cava, B. Lorenz, and J. L. Musfeldt, *Phys. Rev. B* 89, 165120 (2014).
- "Magnetic field-induced spontaneous polarization reversal in multiferroic $\text{Mn}_{0.85}\text{Co}_{0.15}\text{WO}_4$," N. Poudel, K.-C. Liang, Y.-Q. Wang, Y. Y. Sun, B. Lorenz, F. Ye, J. A. Fernandez-Baca, and C. W. Chu, *Physical Review B* 89, 054414 (2014).
- "Molecular extraction in single live cells by sneaking in and out magnetic nanomaterials," Z. Yang, L. Z. Deng, Y. C. Lan, X. L. Zhang, Z. H. Gao, C. W. Chu, D. Cai, and Z. F. Ren, *Proceedings of the National Academy of Sciences USA* 111, 10966 (2014).
- "Observation of pseudogaplike feature above T_c in LiFeAs by ultrafast optical spectroscopy," K. H. Lin, K. J. Wang, C. C. Chang, Y. C. Wen, D. H. Tsai, Y. R. Wu, Y. T. Hsieh, M. J. Wang, B. Lv, C. W. Chu, and M. K. Wu, *Physical Review B* 90, 174502 (2014).
- "Shubnikov-de Haas oscillations from topological surface states of metallic $\text{Bi}_2\text{Se}_{2.1}\text{Te}_{0.9}$," K. Shrestha, V. Marinova, B. Lorenz, and C. W. Chu, *Physical Review B* 90, 241111 (2014).
- "Spectral origin of the colossal magnetodielectric effect in multiferroic DyMn_2O_5 ," A. B. Sushkov, Ch. Kant, M. Schiebl, A. M. Shuvaev, A. Pimenov, A. Pimenov, B. Lorenz, S. Park, S.-W. Cheong, M. Mostovoy, and H. D. Drew, *Physical Review B* 90, 054417 (2014).
- "Spontaneous Polarization Reversal in Multiferroic $\text{Mn}_{0.85}\text{Co}_{0.15}\text{WO}_4$ Induced by an External Magnetic Field," N. Poudel, B. Lorenz, K.-C. Liang, Y.-Q. Wang, Y. Y. Sun, F. Ye, J. A. Fernandez-Baca, and C. W. Chu, *IEEE Transactions on Magnetics* 50, 2503904 (2014).
- "Superconductivity in Titanium-Based Pnictide Oxide Compounds," B. Lorenz, A. M. Guloy, and C. W. Chu, *International Journal of Modern Physics B* 28, 1430011 (2014).

- "The Meissner and Mesoscopic Superconducting States in 1-4 Unit-Cell FeSe-Films," L. Z. Deng, B. Lv, Z. Wu, Y. Y. Xue, W. H. Zhang, F. S. Li, L. L. Wang, X. C. Ma, Q. K. Xue and C. W. Chu, *Phys. Rev. B* 90, 214513 (2014).
- "The Unusually High T_c in Rare-Earth-Doped Single Crystalline CaFe_2As_2 ," F. Y. Wei, B. Lv, L. Z. Deng, J. K. Meen, Y. Y. Xue, and C. W. Chu, *Philosophical Magazine* 94, 2562 (2014).
- "Why is the T_c So High in Fe-Based Pnictide and Chalcogenide Superconductors?," B. Lv, L. Z. Deng, Z. Wu, F. Y. Wei, K. Zhao, J. K. Meen, Y. Y. Xue, L. L. Wang, X. C. Ma, Q. K. Xue, and C. W. Chu, *MRS Proceedings*, 1684, mrss14-1684-t04-01 doi:10.1557/opl.2014.880 (2014).
- " $\text{BaMn}_9[\text{VO}_4]_6(\text{OH})_2$: A Unique Canted Antiferromagnet with a Chiral 'Paddle-Wheel' Structural Feature," Ke. Sun, A. P. Litvinchuk, J. Tapp, B. Lorenz, and A. Möller, *Inorganic Chemistry* 54, 898 (2015).
- "Chemical doping and high-pressure studies of layered $\beta\text{-PdBi}_2$ single crystals," K. Zhao, B. Lv, Y. Y. Xue, X. Y. Zhu, L. Z. Deng, Z. Wu and C. W. Chu, *Physical Review B* 92, 174404 (2015).
- "Defect-induced Superconductivity up to 49 K in $(\text{Ca}_{1-x}\text{R}_x)\text{Fe}_2\text{As}_2$," L. Z. Deng, B. Lv, K. Zhao, F. Y. Wei, Y. Y. Xue, Z. Wu and C. W. Chu, submitted to *Physical Review B* (November 18, 2015).
- "Effects of nickel doping on the multiferroic and magnetic phases of MnWO_4 ," N. Poudel, B. Lorenz, B. Lv, Y. Q. Wang, F. Ye, J. C. Wang, J. A. Fernandez-Baca, and C. W. Chu, submitted to *Ferroelectrics* (January 15, 2015).
- "Experimental study of the proposed super-thermal-conductor: BAs," B. Lv, Y. C. Lan, X. Q. Wang, Q. Zhang, Y. J. Hu, A. J. Jacobson, D. Broido, G. Chen, Z. F. Ren, and C. W. Chu, *Applied Physics Letters* 106, 074105 (2015).
- "Fatigue-free, superstretchable, transparent, and biocompatible metal electrodes," C. F. Guo, Q. H. Liu, G. H. Wang, Y. C. Wang, Z. Z. Shi, Z. G. Suo, C. W. Chu and Z. F. Ren, *Proceedings of the National Academy of Sciences USA* 112, 12332 (2015).
- "High-Pressure and Doping Studies on the Superconducting Antiperovskite SrPt_3P ," B. I. Jawdat, B. Lv, X. Y. Zhu, Y. Y. Xue, and C. W. Chu, *Physical Review B* 91, 094514 (2015).
- "High-Pressure Resistivity of YFe_2Si_2 and Magnetic Studies of $\text{Y}_{1-y}\text{Ho}_y\text{Fe}_2\text{Si}_2$ and $\text{YFe}_2(\text{Si}_{1-x}\text{Ge}_x)_2$ Systems," I. Felner, B. Lv, K. Zhao, and C. W. Chu, *Journal of Superconductivity and Novel Magnetism* 28, 1207 (2015).
- "Hole-Doped Cuprate High Temperature Superconductors," C. W. Chu, L. Z. Deng, and B. Lv, *Physica C* 514, 290 (2015).
- "n-type thermoelectric material $\text{Mg}_2\text{Sn}_{0.75}\text{Ge}_{0.25}$ for high power generation," W. S. Liu, H. S. Kim, S. Chen, Q. Jie, B. Lv, M. L. Yao, Z. S. Ren, C. P. Opeil, S. Wilson, C. W. Chu, and Z. F. Ren, *Proceedings of the National Academy of Sciences USA* 112, 3269 (2015).
- " $\text{Nb}_2\text{O}_2\text{F}_3$: A Reduced Niobium (III/IV) Oxyfluoride with a Complex Structural, Magnetic, and Electronic Phase Transition," T. T. Tran, M. Gooch, B. Lorenz, A. P. Litvinchuk, M. G. Sorolla II, J. Brgoch, C. W. Chu, and A. M. Guloy, *Journal of the American Chemical Society* 137, 636 (2015).
- "Observation of a robust zero-energy bound state in iron-based superconductor $\text{Fe}(\text{Te},\text{Se})$," J. X. Yin, Z. Wu, J. H. Wang, Z. Y. Ye, J. Gong, X. Y. Hou, L. Shan, A. Li, X. J. Liang, X. X. Wu, J. Li, C. S. Ting, Z. Q. Wang, J. P. Hu, P. H. Hor, H. Ding, and S. H. Pan, *Nature Physics* 11, 543 (2015).

- "Observation of universal strong orbital-dependent correlation effects in iron chalcogenides," M. Yi, Z.-K. Liu, Y. Zhang, R. Yu, J.-X. Zhu, J. J. Lee, R. G. Moore, F. T. Schmitt, W. Li, S. C. Riggs, J.-H. Chu, B. Lv, J. Hu, M. Hashimoto, S.-K. Mo, Z. Hussain, Z. Q. Mao, C. W. Chu, I. R. Fisher, Q. Si, Z.-X. Shen, and D. H. Lu, *Nature Communications* 6, 7777 (2015).
- "Polarization control at spin-driven ferroelectric domain walls," N. Leo, A. Bergman, A. Cano, N. Poudel, B. Lorenz, M. Fiebig, and D. Meier, *Nature Communications* 6, 6661 (2015).
- "Pressure Effect on Ferroelectric Properties of GdMn_2O_5 and TmMn_2O_5 ," N. Poudel, M. Gooch, B. Lorenz, C. W. Chu, J. W. Kim, and S.-W. Cheong, submitted to Proceedings of the 13th Joint MMM-Intermag Conference, San Diego, California, January 11-15, 2016, to be published in *IEEE Transactions on Magnetics* (November 6, 2015).
- "Pressure-induced decoupling of rare-earth moments and Mn spins in multiferroic GdMn_2O_5 ," N. Poudel, M. Gooch, B. Lorenz, C. W. Chu, J. W. Kim, and S. W. Cheong, *Physical Review B* 92, 144430 (2015).
- "Relationship between Thermoelectric Figure of Merit and Energy Conversion Efficiency," H. S. Kim, W. S. Liu, G. Chen, C. W. Chu, and Z. F. Ren, *Proceedings of the National Academy of Sciences USA* 112, 8205 (2015).
- "Separation of quantum oscillations from bulk and topological surface states in metallic $\text{Bi}_2\text{Se}_{2.1}\text{Te}_{0.9}$," K. Shrestha, D. E. Graf, V. Marinova, B. Lorenz, and C. W. Chu, submitted to *New Journal of Physics* (July 14, 2015).
- "Synthesis, Structure and Superconductivity in the New-Structure-Type Compound: SrPt_6P_2 ," B. Lv, B. I. Jawdat, Z. Wu, M. Sorolla II, M. Gooch, K. Zhao, L. Z. Deng, Y. Y. Xue, B. Lorenz, A. M. Guloy, and C. W. Chu, *Inorganic Chemistry* 54, 1049 (2015).

Degrees Awarded to Students Funded on Grant

- J. Shulman, Ph.D., Physics, December 2009, Dissertation: "A general mechanism for negative capacitance phenomena"
- N. Das, Ph.D., Physics, May 2010, Dissertation: "E-field Induced Resistive Switch in Transition Metal Oxide: A Model for Future Nonvolatile Memory Devices"
- R. P. Chaudhury, Ph.D., Physics, August 2010, Dissertation: "Effects of High Pressure, Magnetic Fields and Substitutions on Multiferroic Magnetoelectric Systems"
- M. Gooch, Ph.D., Physics, December 2010, Dissertation: "A Study of Magnetic Spin Fluctuations and Superconductivity in the Iron Pnictides"
- F. Y. Wei, Ph.D., Physics, August 2011, Dissertation: "Thermodynamics investigation of doping and correlation between magnetism and superconductivity in FeAs-based superconductors"
- K.-C. Liang, Ph.D., Physics, August 2013, Dissertation: "Effects of magnetic fields and substitutions on magnetoelectric and multiferroic systems"
- B. Jawdat, Ph.D., Physics, August 2015, Dissertation: "A Study of Superconductivity in a Series of Strontium Platinum Phosphides"
- L. Z. Deng, Ph.D., Physics, August 2015, Dissertation: "Possible Interface Enhanced Superconductivity in Iron Pnictides and Chalcogenides"
- K. Shrestha, Ph.D., Physics, December 2015, Dissertation: "Magnetotransport Studies on Topological Insulators"
- K. Zhao, Ph.D., Physics, December 2015, Dissertation: "Exploration of possible enhancement of superconductivity by interface, doping and pressure effects"

AFOSR Deliverables Submission Survey

Response ID:5583 Data

1.

1. Report Type

Final Report

Primary Contact E-mail

Contact email if there is a problem with the report.

cwchu@uh.edu

Primary Contact Phone Number

Contact phone number if there is a problem with the report

713-743-8222

Organization / Institution name

University of Houston

Grant/Contract Title

The full title of the funded effort.

Search for and Study of Novel Superconductor with Higher Tc and Jc

Grant/Contract Number

AFOSR assigned control number. It must begin with "FA9550" or "F49620" or "FA2386".

FA9550-09-1-0656

Principal Investigator Name

The full name of the principal investigator on the grant or contract.

Ching-Wu Chu

Program Manager

The AFOSR Program Manager currently assigned to the award

Dr. Harold Weinstock

Reporting Period Start Date

09/15/2009

Reporting Period End Date

09/14/2015

Abstract

We have discovered a record Tc up to 49K in the rare-earth doped CaFe₂As₂ system with RE = La, Ce, Pr, and Nd, highest in the Fe-based 122 superconductor family. Detailed studies have demonstrated the system's non-bulk nature, two superconducting transitions, unusually high magnetic anisotropy, and RE-independent and dopant-concentration-independent nature. The unusually high Tc is attributed to the possible long-sought-after interfacial enhancement mechanism [proposed by Allender-Bray-Bardeen (ABB)] via naturally grown FeAs layers with different defect density, opening up a new avenue to higher Tc (ABB suggested possible room temperature Tc via this mechanism). We have developed a novel technique for detailed magnetic studies of the artificially grown FeSe/STO system, and observed: a Meissner state below ~ 20 K; a mesoscopic state with superconducting patches between ~ 20 and 45 K; and a yet-to-be-determined state between ~ 45 and 80 K with a logarithmic frequency dispersion. We have discovered more than ten new superconductors of new structure

DISTRIBUTION A: Distribution approved for public release

types, with anti-perovskite feature as cuprate, as first superconductor in large compound family, or through novel synthetic routes. These findings will enable our capability and extend our directions to look for more new superconductors with higher Tc. New physics and phenomena were also discovered in both superconducting and non-superconducting compounds such as: superconducting-semiconducting transition in YBCO under high pressure; raising questions regarding topological superconductivity in the $Cu_xBi_2Se_3$; temperature-induced orbital-selective Mott transition (OSMT) in Fe-chalcogenides; field-induced spin-flop transition in the polar compound $LiCrP_2O_7$; and quantum oscillations from topological surface states of metallic $Bi_2(SeTe)_3$. In addition, the studies of multiferroic and magnetoelectric compounds have led to several milestones in the $RAI_3(BO_3)_4$, $Mn_{1-x}Co_xWO_4$, and $LiFeP_2O_7$ materials. Moreover, we have extended our studies to other AFOSR mission-related systems such as super-thermal-conducting materials, thermoelectric materials with higher ZT and better performance, and 2D transition metal dichalcogenides.

Distribution Statement

This is block 12 on the SF298 form.

Distribution A - Approved for Public Release

Explanation for Distribution Statement

If this is not approved for public release, please provide a short explanation. E.g., contains proprietary information.

SF298 Form

Please attach your SF298 form. A blank SF298 can be found [here](#). Please do not password protect or secure the PDF. The maximum file size for an SF298 is 50MB.

[AFD-070820-035.pdf](#)

Upload the Report Document. File must be a PDF. Please do not password protect or secure the PDF. The maximum file size for the Report Document is 50MB.

[151214-AFOSR-final-rpt-090915-150914.pdf](#)

Upload a Report Document, if any. The maximum file size for the Report Document is 50MB.

Archival Publications (published) during reporting period:

[See report document]

Changes in research objectives (if any):

None

Change in AFOSR Program Manager, if any:

None

Extensions granted or milestones slipped, if any:

None

AFOSR LRIR Number

LRIR Title

Reporting Period

Laboratory Task Manager

Program Officer

Research Objectives

Technical Summary

Funding Summary by Cost Category (by FY, \$K)

	Starting FY	FY+1	FY+2
Salary			
Equipment/Facilities			
Supplies			
Total			

Report Document

Report Document - Text Analysis

Report Document - Text Analysis

Appendix Documents

2. Thank You

E-mail user

Dec 11, 2015 16:01:39 Success: Email Sent to: cwchu@uh.edu
