

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188		
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 19-08-2015		2. REPORT TYPE Conference Proceeding		3. DATES COVERED (From - To) -	
4. TITLE AND SUBTITLE Large mode area Yb-doped photonic bandgap fiber lasers			5a. CONTRACT NUMBER W911NF-12-1-0332		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHORS Iyad Dajani, , Benjamin Pulford, , Thomas Ehrenreich, , Roger Holten, , Christopher Vergien, , Guancheng Gu, , Fanting Kong, , Thomas Hawkinsb, , Liang Dong			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES Clemson University Research Foundation Office of Sponsored Programs Clemson University Research Foundation Clemson, SC 29631 -0946			8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS (ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSOR/MONITOR'S ACRONYM(S) ARO		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) 62072-EL-HEL.20		
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
14. ABSTRACT All-solid photonic bandgap fibers (PBGF) can be spectrally tailored to suppress amplified spontaneous emission (ASE) and stimulated Raman scattering (SRS). Furthermore, this type of fiber is attractive for realizing high-power narrow-linewidth amplifiers as large mode areas can be attained while maintaining single-mode operation. Notably, an Yb-doped PBGF with a core diameter of ~50 μm and a calculated effective area of 1450 μm ² was fabricated using the stack and draw technique (Figure 1). The microstructures in the cladding are comprised of germanium-doped silica. A low refractive index polymer coating provides a numerical aperture of 0.46 for pumping purposes.					
15. SUBJECT TERMS fiber lasers, photonic bandgap fibers					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	15. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Liang Dong
a. REPORT UU	b. ABSTRACT UU	c. THIS PAGE UU			19b. TELEPHONE NUMBER 864-656-5915

Report Title

Large mode area Yb-doped photonic bandgap fiber lasers

ABSTRACT

All-solid photonic bandgap fibers (PBGF) can be spectrally tailored to suppress amplified spontaneous emission (ASE) and stimulated Raman scattering (SRS). Furthermore, this type of fiber is attractive for realizing high-power narrow-linewidth amplifiers as large mode areas can be attained while maintaining single-mode operation. Notably, an Yb-doped PBGF with a core diameter of $\sim 50 \text{ }\mu\text{m}$ and a calculated effective area of $1450 \text{ }\mu\text{m}^2$ was fabricated using the stack and draw technique (Figure 1). The microstructures in the cladding are comprised of germanium-doped silica. A low refractive index polymer coating provides a numerical aperture of 0.46 for pumping purposes. The absorption was estimated to be 1 dB/m at a pump wavelength of 976 nm. Approximately 11 m of this fiber was mounted on a cold spool possessing a diameter of 53 cm. The PBGF was pumped in a counter-propagating configuration using 976 nm diodes from Laserline. The master oscillator was a non-planar-ring oscillator (NPRO) operating at 1064 nm. The output of the NPRO was then coupled into a phase modulator for stimulated Brillouin scattering (SBS) suppression and then amplified using a multi-stage amplifier system manufactured by IPG. The phase modulation frequency was set at 400 MHz and the modulation depth was chosen such that three equal peaks corresponding to the carrier frequency and the two adjacent sidebands were generated. As much as 20 W were used to seed the PBGF. A plot of the signal power vs. pump power is shown in Figure 2. The output signal power obtained was 587 W; which represents to the best of our knowledge the highest power reported to date for a PBGF amplifier. The slope efficiency for this amplifier was $\sim 70\%$. At the highest output power, there was little sign of SBS.

Conference Name: SPIE PhotonicsWest, paper 9344-5, San Francisco, February 2015

Conference Date: February 08, 2015

High-Power Narrow-Linewidth Large Mode Area Photonic Bandgap Fiber Amplifier

Benjamin Pulford^a, Iyad Dajani^a, Thomas Ehrenreich^a, Roger Holten^a, Christopher Vergien^a,
Guancheng Gu^b, Fanting Kong^b, Thomas Hawkins^b, Liang Dong^b

^a Air Force Research Laboratory, 3550 Aberdeen Ave SE, Kirtland AFB, NM, USA 87117

^b ECE/COMSET, Clemson University, 91 Technology Drive, Anderson, SC, 29625, USA

ABSTRACT

All-solid photonic bandgap fibers (PBGF) can be spectrally tailored to suppress amplified spontaneous emission (ASE) and stimulated Raman scattering (SRS). Furthermore, this type of fiber is attractive for realizing high-power narrow-linewidth amplifiers as large mode areas can be attained while maintaining single-mode operation. Notably, an Yb-doped PBGF with a core diameter of $\sim 50\text{ }\mu\text{m}$ and a calculated effective area of $1450\text{ }\mu\text{m}^2$ was fabricated using the stack and draw technique (Figure 1). The microstructures in the cladding are comprised of germanium-doped silica. A low refractive index polymer coating provides a numerical aperture of 0.46 for pumping purposes. The absorption was estimated to be 1 dB/m at a pump wavelength of 976 nm. Approximately 11 m of this fiber was mounted on a cold spool possessing a diameter of 53 cm. The PBGF was pumped in a counter-propagating configuration using 976 nm diodes from Laserline. The master oscillator was a non-planar-ring oscillator (NPRO) operating at 1064 nm. The output of the NPRO was then coupled into a phase modulator for stimulated Brillouin scattering (SBS) suppression and then amplified using a multi-stage amplifier system manufactured by IPG. The phase modulation frequency was set at 400 MHz and the modulation depth was chosen such that three equal peaks corresponding to the carrier frequency and the two adjacent sidebands were generated. As much as 20 W were used to seed the PBGF. A plot of the signal power vs. pump power is shown in Figure 2. The output signal power obtained was 587 W; which represents to the best of our knowledge the highest power reported to date for a PBGF amplifier. The slope efficiency for this amplifier was $\sim 70\%$. At the highest output power, there was little sign of SBS.

Keywords: Photonic bandgap fiber, Yb-doped fiber amplifiers, stimulated Brillouin scattering




Fig. 1 Yb-doped all-solid PBGF with a core diameter of $\sim 50\ \mu\text{m}$ and a cladding diameter of $\sim 400\ \mu\text{m}$. The core is comprised of 7 active rods.




Fig. 2 Output signal power vs. launched power for PBGF amplifier. The slope efficiency is $\sim 70\%$.