

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188		
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 19-08-2015		2. REPORT TYPE Conference Proceeding		3. DATES COVERED (From - To) -	
4. TITLE AND SUBTITLE Polarizing 50µm core Yb-doped photonic bandgap fiber			5a. CONTRACT NUMBER W911NF-12-1-0332		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHORS Guancheng Gu, , Thomas Hawkins, , Joshua Parsons, , Maxwell Jones, , Christopher Dunn, , Monica T. Kalichevsky-Dong, , Benjamin Pulford, , Iyad Dajani, Liang Dong, Fanting Kong,			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES Clemson University Research Foundation Office of Sponsored Programs Clemson University Research Foundation Clemson, SC 29631 -0946			8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS (ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSOR/MONITOR'S ACRONYM(S) ARO		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) 62072-EL-HEL.21		
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
14. ABSTRACT Polarizing optical fibers are an important component for building compact fiber lasers with linearly polarized laser output. Conventional single-mode optical fibers with birefringence can only preserve the polarization when the incident beam is launched properly. Recent reports demonstrate that the birefringence in photonic bandgap fibers (PBFs) can provide single-polarization operation by shifting the transmission band of the light with orthogonal polarizations, thus to create the staggered region in which only one polarization light can propagate [add ref]. Here, we demonstrate a 50µm core Yb-doped polarizing photonic bandgap fiber (PBF) for single polarization operation.					
15. SUBJECT TERMS fiber lasers, photonic bandgap fibers					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	15. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Liang Dong
a. REPORT UU	b. ABSTRACT UU	c. THIS PAGE UU			19b. TELEPHONE NUMBER 864-656-5915

Report Title

Polarizing 50 μ m core Yb-doped photonic bandgap fiber

ABSTRACT

Polarizing optical fibers are an important component for building compact fiber lasers with linearly polarized laser output. Conventional single-mode optical fibers with birefringence can only preserve the polarization when the incident beam is launched properly. Recent reports demonstrate that the birefringence in photonic bandgap fibers (PBFs) can provide single-polarization operation by shifting the transmission band of the light with orthogonal polarizations, thus to create the staggered region in which only one polarization light can propagate [add ref]. Here, we demonstrate a 50 μ m core Yb-doped polarizing photonic bandgap fiber (PBF) for single-polarization operation of high power linearly polarized fiber lasers. The single-polarization operates through the entire transmission band from 1040nm to 1180nm with polarization extinction ratio (PER) of >6dB/m. 5 meter long fiber was also tested in a laser configuration and a linearly polarized laser output at 1026nm was achieved with PER value of 27dB without using any polarizers.

Conference Name: SPIE PhotonicsWest, paper 9344-2, San Francisco, February 2015.

Conference Date: February 08, 2015

Polarizing 50 μ m core Yb-doped photonic bandgap fiber

Fanting Kong^{*a}, Guancheng Gu^a, Thomas Hawkins^a, Joshua Parsons^a, Maxwell Jones^a, Christopher Dunn^a, Monica T. Kalichevsky-Dong^a, Benjamin Pulford^b, Iyad Dajani^b and Liang Dong^a

^aECE/COMSET, Clemson University, 91 Technology Drive, Anderson, SC, 29625, USA

^bKirtland Air Force Base, Albuquerque, NM 87117, USA

Polarizing optical fibers are an important component for building compact fiber lasers with linearly polarized laser output. Conventional single-mode optical fibers with birefringence can only preserve the polarization when the incident beam is launched properly. Recent reports demonstrate that the birefringence in photonic bandgap fibers (PBFs) can provide single-polarization operation by shifting the transmission band of the light with orthogonal polarizations, thus to create the staggered region in which only one polarization light can propagate [add ref]. Here, we demonstrate a 50 μ m core Yb-doped [birefringent-polarizing photonic bandgap fiber \(PBF\)](#) ~~fiber~~ ~~with~~ ~~for~~ single-polarization operation ~~for~~ ~~of~~ high power linearly polarized fiber laser [applications](#). The single-polarization operates through the entire transmission band from 1040nm to 1180nm with polarization extinction ratio (PER) of ≥ 6 dB/m. 5 meter long fiber was also tested in a laser configuration and a linearly polarized laser output at 1026nm was achieved with PER value of 27dB [without using any polarizers](#).




Fig. 1. Cross-section of passive birefringent PBF.

Fig.1 shows the cross-section image of a passive birefringent PBF fiber. The out-cladding (OD) is 255 μ m flat-to-flat and 270 μ m corner-to-corner. The periodical lattice structure in the cladding is made of germanium doped high-index rods which provide photonic bandgap effect and guide light in the core. The missed seven high-index rods at the center form the core of the fiber which is 40 μ m and 62 μ m along the slow and fast axis respectively. The birefringence of 3.2×10^{-4} in this fiber is obtained by incorporating six low-index boron-doped rods on either side of the core, which also provide light confinement by total internal reflection in addition to the bandgap guiding in other directions.




Fig.2. Transmission band in passive birefringent PBF.

The transmission band in this passive fiber was tested by launching un-polarized white light into 3m long fiber bended at 55cm diameter and measuring the transmitted light in the core, which is shown in Fig.2. The transmission band was measured from 990nm to 1110nm within the 3rd order photonic bandgap of the PBF fiber, with robust single-mode operation near the high-frequency bandgap edge and multimode operation near the low-frequency bandgap edge, as illustrated by inserted photos in Fig. 2. These inserted mode pattern images were taken by using a tunable laser scanning within the transmission band.




Fig. 3. Transmission band along fast and slow axis in 30cm Yb-doped birefringent PBF.

The Yb-doped active birefringent PBF fiber was similar to the passive fiber and was rescaled from previous tested passive PBF in order to move 1064nm wavelength to the high-frequency edge of the bandgap with where robust single-mode operation can be achieved. Polarized white light was launched into 30cm long straight active fiber and the transmission was measured for light polarized along fast and slow axis individually, shown in Fig. 3. The dashed line represents the transmission for light polarized along the slow fast axis, which is about ≥ 1.8 dB lower than the light polarized along the slowfast axis within the entire transmission band from 1040nm to 1170nm. This higher transmission loss for the slowfast-axis polarization edation light is due to the fact that light at the fast axis has lower effective mode index due to the birefringence from the stress rods and is therefore weakly guided. The fast-axis mode is closer to the modes in the photonic cladding and guided in the core is easily coupled into cladding when the effective refractive index of core-guided mode is reduced close to the bottom of photonic bandgap. This refractive index reduction is caused by the birefringence in the fiber along slow axis. Thise differential polarization transmission loss results in the single polarization operation in this fiber with a PER value of ≥ 6 dB/m. This is likely much higher in coiled fibers.

5m long active PBF fiber was also tested in a laser configuration when bended at 55cm coil diameter. A lasing efficiency of 56% relative to the absorbed pump power was achieved at 1026nm lasing wavelength. The laser output is linearly polarized with a PER value of 27dB.