



**AFRL-AFOSR-VA-TR-2016-0226**

---

QUANTUM PISTON - QUANTUM PRESERVATION, SIMULATION  
AND TRANSFER IN OXIDE NANOSTRUCTURES

**Jeremy Levy**  
**UNIVERSITY OF PITTSBURGH**  
**3520 FIFTH AVE**  
**PITTSBURGH, PA 15213-3320**

---

**06/28/2016**  
**Final Report**

**DISTRIBUTION A: Distribution approved for public release.**

Air Force Research Laboratory  
AF Office Of Scientific Research (AFOSR)/RTB1

Arlington, Virginia 22203  
Air Force Materiel Command

**REPORT DOCUMENTATION PAGE**

Form Approved  
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

**PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.**

<b>1. REPORT DATE (DD-MM-YYYY)</b> 23-06-2016	<b>2. REPORT TYPE</b> Final SF 298	<b>3. DATES COVERED (From - To)</b> 14-Sep-2011 to 31-Mar-2016
--	---------------------------------------	---

<b>4. TITLE AND SUBTITLE</b> QUANTUM PISTON - QUANTUM PRESERVATION, SIMULATION AND TRANSFER IN OXIDE NANOSTRUCTURES	<b>5a. CONTRACT NUMBER</b>
	<b>5b. GRANT NUMBER</b> FA9550-10-1-0524
	<b>5c. PROGRAM ELEMENT NUMBER</b>

<b>6. AUTHOR(S)</b> Jeremy Levy (PI)	<b>5d. PROJECT NUMBER</b> 406200
	<b>5e. TASK NUMBER</b>
	<b>5f. WORK UNIT NUMBER</b>

<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b> University of Pittsburgh Office of Research 123 University Place Pittsburgh, PA 15213	<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  I#0019713
---	--

<b>9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> Air Force Office of Scientific Research 875 North Randolph Street, RM 3112 Arlington, VA 22203	<b>10. SPONSOR/MONITOR'S ACRONYM(S)</b>
	<b>11. SPONSOR/MONITOR'S REPORT NUMBER(S)</b>

**12. DISTRIBUTION/AVAILABILITY STATEMENT**  
Distribution A -- Approved for Public Release

**13. SUPPLEMENTARY NOTES**

**14. ABSTRACT**  
The main purposes of the theoretical activity supported by this MURI have been to (1) understand the causes and nature of the magnetic and superconducting ordering of the electrons at the LAO/STO interface and (2) determine whether Majorana zero modes might exist and be detected in nanowires 'drawn' at these interfaces by the University of Pittsburgh team.  
Important experimental advances have brought us close to a regime in which quantum simulation will be possible. True quantum simulation requires a deep (first-principles-level) understanding of the host material that is performing the simulation. A lot of the research that was conducted involves basic characterization (quantum transport) in LAO/STO nanostructures that have not been patterned in to artificial lattices. We have however performed preliminary results (presented at conferences) that show that this approach is both feasible and highly promising. The ability to transfer quantum information from one physical embodiment to another represents an essential building block in any quantum architecture. Work in this area has mainly involved diamond, a superconducting semiconductor with long-lived defect complexes (nitrogen-vacanc

**15. SUBJECT TERMS**  
oxide nanoelectronics, superconductivity, quantum information

<b>16. SECURITY CLASSIFICATION OF:</b>			<b>17. LIMITATION OF ABSTRACT</b>  SAR	<b>18. NUMBER OF PAGES</b>  7	<b>19a. NAME OF RESPONSIBLE PERSON</b> Jeremy Levy
<b>a. REPORT</b>  U	<b>b. ABSTRACT</b>  U	<b>c. THIS PAGE</b>  U			<b>19b. TELEPHONE NUMBER (Include area code)</b> 412-624-2736

## INSTRUCTIONS FOR COMPLETING SF 298

**1. REPORT DATE.** Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

**2. REPORT TYPE.** State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

**3. DATES COVERED.** Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

**4. TITLE.** Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

**5a. CONTRACT NUMBER.** Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

**5b. GRANT NUMBER.** Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

**5c. PROGRAM ELEMENT NUMBER.** Enter all program element numbers as they appear in the report, e.g. 61101A.

**5d. PROJECT NUMBER.** Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

**5e. TASK NUMBER.** Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

**5f. WORK UNIT NUMBER.** Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

**6. AUTHOR(S).** Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

**7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES).** Self-explanatory.

**8. PERFORMING ORGANIZATION REPORT NUMBER.** Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

**9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES).** Enter the name and address of the organization(s) financially responsible for and monitoring the work.

**10. SPONSOR/MONITOR'S ACRONYM(S).** Enter, if available, e.g. BRL, ARDEC, NADC.

**11. SPONSOR/MONITOR'S REPORT NUMBER(S).** Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

**12. DISTRIBUTION/AVAILABILITY STATEMENT.** Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

**13. SUPPLEMENTARY NOTES.** Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

**14. ABSTRACT.** A brief (approximately 200 words) factual summary of the most significant information.

**15. SUBJECT TERMS.** Key words or phrases identifying major concepts in the report.

**16. SECURITY CLASSIFICATION.** Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

**17. LIMITATION OF ABSTRACT.** This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

# QUANTUM PISTON - QUANTUM PRESERVATION, SIMULATION AND TRANSFER IN OXIDE NANOSTRUCTURES

## Overview

This supersemi MURI project aimed to develop the unique properties of superconducting semiconductors to achieve Quantum Preservation, Simulation and Transfer in Oxide Nanostructures. We we have pursued three technical approaches:

1. Quantum Preservation: Using predicted topological properties of superconductors in two dimensions, we will develop ways for preserving quantum information in a way that is immune to a wide variety of decoherence mechanisms, thus paving the way for a scalable quantum information technology.
2. Quantum Simulation: The extreme nanoscale precision with which the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interface can be gated will be used to program fundamental couplings at near-atomic scales and quantum simulation of "metasuperconductors".
3. Quantum Transfer: New mechanisms for the transfer of quantum information between long-lived localized states (nitrogen-vacancy centers) and delocalized states (superconducting resonators) will be developed.

## Quantum Preservation

Both experimental and theoretical approaches were taken with regard to topological protection (quantum preservation) afforded by theoretically predicted Majorana fermion-based quantum bits. The theory of Majorana fermions has been extended by Nayak to allow them to exist in systems that lack long-range superconducting order. In addition, they have developed a model to accommodate both magnetism and superconductivity at the LAO/STO interface.

The main purposes of the theoretical activity supported by this MURI have been to (1) understand the causes and nature of the magnetic and superconducting ordering of the electrons at the LAO/STO interface and (2) determine whether Majorana zero modes might exist and be detected in nanowires 'drawn' at these interfaces by the University of Pittsburgh team.

In thinking about the possibility of Majorana zero modes in nanowires are LAO/STO interfaces, it became clear that one important feature of superconductivity in these wires is that it is quasi-one-dimensional (i.e. not induced by proximity to a 3D bulk superconductor, as in proposed semiconductor 'Majorana wires'). Therefore, we had to answer the question of whether Majorana zero modes could be supported by quasi-one-dimensional superconductors, which necessarily have superconducting order with power-law decay, not true long-ranged order. In the published paper listed above, we showed that such a superconductor could (under the right circumstances) support Majorana zero modes.

## Quantum Simulation

Important experimental advances have brought us close to a regime in which quantum simulation will be possible. True quantum simulation requires a deep (first-principles-level) understanding of the host material that is performing the simulation. A lot of the research that was conducted involves basic characterization (quantum transport) in LAO/STO nanostructures that have not been patterned in to

artificial lattices. We have however performed preliminary results (presented at conferences) that show that this approach is both feasible and highly promising.

### Quantum Transfer

The ability to transfer quantum information from one physical embodiment to another represents an essential building block in any quantum architecture. Work in this area has mainly involved diamond, a superconducting semiconductor with long-lived defect complexes (nitrogen-vacancy or NV centers). A central goal of the project was to integrate diamond with LAO/STO heterostructures. This approach proved to be highly challenging, if technically feasible. Structures have been shared with Eom, Levy, Schlom and Pan. Eom and Schlom have also grown epitaxial LAO/STO heterostructures on cubic SiC/Si substrates by PLD with high pressure RHEED.

### Cross-Cutting Activities

A number of cross-cutting activities (growth of superconducting-semiconductor structures, atomic-scale characterization, electrical and optical experiments) will take place, serving multiple tasks. The successful development of new quantum technologies from this research will enable new and powerful types of quantum speedups of computational tasks, including solutions to large systems of linear equations, fully quantum-mechanical simulation of materials, and interoperability among quantum platforms.

### Quantum Transport in LAO/STO

A major focus in Quantum Preservation has been the development of superconducting nanowires and possible topological phases that could be used to support Majorana fermions. The first fully superconducting nanowires were demonstrated. The normal state of these structures is unusual in that the four-terminal resistance is independent of the length of the channel and always of order  $h/e^2$ . In addition, some unusual nonlocal Hall effects have been observed which imply an unusually long coherence length in the system. We also observe greatly enhanced mobility that extends up to room temperature.

### Rashba Spin-Orbit Coupling

We study origin of Rashba spin-orbit interaction at SrTiO<sub>3</sub> surfaces and LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interfaces by considering the interplay between atomic spin-orbit coupling and inversion asymmetry at the surface or interface. We show that in a simple tight-binding model involving 3d t<sub>2g</sub> bands of Ti ions, the induced spin-orbit coupling in the dx<sub>z</sub> and dy<sub>z</sub> bands is cubic in momentum whereas the spin-orbit interaction in the dx<sub>y</sub> band has linear momentum dependence. We also find that the **spin-orbit interaction in one-dimensional channels at LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interfaces is linear in momentum for all bands**. We discuss implications of our results for transport experiments on SrTiO<sub>3</sub> surfaces and LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interfaces. In particular, we analyze the effect of a given spin-orbit interaction term on magnetotransport of LaAlO<sub>3</sub>/SrTiO<sub>3</sub> by calculating weak antilocalization corrections to the conductance and to universal conductance fluctuations.

### 1D Superconductivity in LAO/STO

We report quasi-1D superconductivity at the interface of LaAlO<sub>3</sub> and SrTiO<sub>3</sub>. The material system and nanostructure fabrication method supply a **new platform for superconducting nanoelectronics**. Nanostructures having line widths  $w \sim 10$  nm are formed from the parent two-dimensional electron liquid using conductive atomic force microscope lithography. Nanowire cross-sections are small

compared to the superconducting coherence length in LaAlO<sub>3</sub>/SrTiO<sub>3</sub>, placing them in the quasi-1D regime. Broad superconducting transitions versus temperature and finite resistances in the superconducting state well below  $T_c \approx 200$  mK are observed, suggesting the presence of fluctuation- and heating-induced resistance. The superconducting resistances and  $V-I$  characteristics are tunable through the use of a back gate. Four-terminal resistances in the superconducting state show an unusual dependence on the current path, varying by as much as an order of magnitude. This new technology, i.e., the ability to ‘write’ gate-tunable superconducting nanostructures on an insulating LaAlO<sub>3</sub>/SrTiO<sub>3</sub> ‘canvas’, opens possibilities for the development of new families of reconfigurable superconducting nanoelectronics.

#### *Nonlocal transport in LAO/STO*

The oxide heterostructure LaAlO<sub>3</sub>/SrTiO<sub>3</sub> supports a two-dimensional electron liquid with a variety of competing phases, including magnetism, superconductivity, and weak antilocalization because of Rashba spin-orbit coupling. Further confinement of this two-dimensional electron liquid to the quasi-one-dimensional regime can provide insight into the underlying physics of this system and reveal new behavior. Here, we describe magnetotransport experiments on narrow LaAlO<sub>3</sub>/SrTiO<sub>3</sub> structures created by a conductive atomic force microscope lithography technique. **Four-terminal local-transport measurements on Hall bar structures about 10 nm wide yield longitudinal resistances that are comparable to the resistance quantum  $h/e^2$  and independent of the channel length.** Large nonlocal resistances (as large as  $10^4 \Omega$ ) are observed in some but not all structures with separations between current and voltage that are large compared to the two-dimensional mean-free path. The nonlocal transport is strongly suppressed by the onset of superconductivity below about 200 mK. The origin of these anomalous transport signatures is not understood, but may arise from coherent transport defined by strong spin-orbit coupling and/or magnetic interactions.

#### *Theory of magnetism and superconductivity at LAO/STO*

We formulated a model for magnetic and superconducting ordering in one-dimensional nanostructures at LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interfaces containing both localized magnetic moments and itinerant electrons. Although these both originate in Ti 3d orbitals, the former may be due to electrons more tightly bound to the interface, while the latter are extended over several layers. Only the latter contribute significantly to metallic conduction and superconductivity. In our model, the interplay between the two types of electrons, which is argued to be ferromagnetic, combined with strong spin-orbit coupling of the itinerant electrons, leads to magnetic ordering. Furthermore, we propose a model for interfacial superconductivity, consisting of random superconducting grains in the bulk SrTiO<sub>3</sub> driven, via coupling to the interface conduction band, towards long-ranged or quasi-long-ranged order. Most interestingly, **the magnetic order and strong spin-orbit coupling can lead in this manner to unconventional interfacial superconductivity, yielding a possible realization of Majorana physics.**

#### *Effect of ferroelastic domain walls*

The ability to control materials properties through interface engineering is demonstrated by the appearance of conductivity at the interface of certain insulators, most famously the {001} interface of the band insulators LaAlO<sub>3</sub> and TiO<sub>2</sub>-terminated SrTiO<sub>3</sub> (STO). Transport and other measurements in this system show a plethora of diverse physical phenomena. To better understand the interface conductivity, we used scanning superconducting quantum interference device microscopy to image the magnetic field locally generated by current in an interface. At low temperature, **we found that the current flowed in conductive narrow paths oriented along the crystallographic axes**, embedded in a

less conductive background. The configuration of these paths changed on thermal cycling above the STO cubic-to-tetragonal structural transition temperature, implying that the local conductivity is strongly modified by the STO tetragonal domain structure. The interplay between substrate domains and the interface provides an additional mechanism for understanding and controlling the behaviour of heterostructures.

#### *Nonlocal transport*

Effects from **nonequilibrium superconductivity** play a major role in the physics of superconducting nanoelectronics. Notably, charge imbalance arising from the point at which the superconducting device contacts normal-metal leads is prevalent, particularly in reduced dimensions. We investigate nonlocal transport signatures in quasi-1D nanostructures formed at the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interface. The nonlocal resistances correlate with the bias, magnetic field, and back gate dependence of the superconducting state. We attribute these signatures to charge imbalance or spin-dependent excitations. Understanding and control over these effects are important for further development of superconducting nanoelectronics in this material system, including the ability to probe the interaction of superconductivity and other rich physics in LaAlO<sub>3</sub>/SrTiO<sub>3</sub> on the nanoscale.

#### *Electron Pairing Without Superconductivity*

Strontium titanate (SrTiO<sub>3</sub>) is the first and best known superconducting semiconductor. It exhibits an extremely low carrier density threshold for superconductivity, and possesses a phase diagram similar to that of high-temperature superconductors—two factors that suggest an unconventional pairing mechanism. Despite sustained interest for 50 years, direct experimental insight into the nature of electron pairing in SrTiO<sub>3</sub> has remained elusive. Here we perform transport experiments with nanowire-based single-electron transistors at the interface between SrTiO<sub>3</sub> and a thin layer of lanthanum aluminate, LaAlO<sub>3</sub>. Electrostatic gating reveals a series of two-electron conductance resonances—paired electron states—that bifurcate above a critical pairing field  $B_p$  of about 1–4 tesla, an order of magnitude larger than the superconducting critical magnetic field. For magnetic fields below  $B_p$ , these resonances are insensitive to the applied magnetic field; for fields in excess of  $B_p$ , the resonances exhibit a linear Zeeman-like energy splitting. Electron pairing is stable at temperatures as high as 900 millikelvin, well above the superconducting transition temperature (about 300 millikelvin). **These experiments demonstrate the existence of a robust electronic phase in which electrons pair without forming a superconducting state.** Key experimental signatures are captured by a model involving an attractive Hubbard interaction that describes real-space electron pairing as a precursor to superconductivity.

#### *Magnetism in LAO/STO*

##### *Room temperature electronically controlled ferromagnetism*

Reports of emergent conductivity, superconductivity and magnetism have helped to fuel intense interest in the rich physics and technological potential of complex-oxide interfaces. Here we employ magnetic force microscopy to search for room-temperature magnetism in the well-studied LaAlO<sub>3</sub>/SrTiO<sub>3</sub> system. Using electrical top gating to control the electron density at the oxide interface, **we directly observe the emergence of an in-plane ferromagnetic phase as electrons are depleted from the interface.** Itinerant electrons that are reintroduced into the interface align antiferromagnetically with the magnetization at first screening and then destabilizing it as the conductive regime is approached. Repeated cycling of the gate voltage results in new, uncorrelated magnetic patterns. This newfound

control over emergent magnetism at the interface between two non-magnetic oxides portends a number of important technological applications.

#### Growth of LAO/STO Heterostructures

Much of what was proposed for this project relates to LaAlO<sub>3</sub>/SrTiO<sub>3</sub> (LAO/STO) heterostructures, which are grown primarily in the Eom group. They have provided structures that have been shared throughout the team, including Levy, Awschalom, Schlom and Pan. One key scientific finding of Eom relates to the effect of **different lattice constant single crystal substrates to produce LAO/STO interfaces with controlled levels of biaxial epitaxial strain**. Tensile strained SrTiO<sub>3</sub> destroys the conducting 2DEG, while compressively strained SrTiO<sub>3</sub> retains the 2DEG, but with a carrier concentration reduced in comparison to the unstrained LAO/STO interface. The critical LaAlO<sub>3</sub> overlayer thickness for 2DEG formation increases with SrTiO<sub>3</sub> compressive strain. First-principles calculations suggest that a strain-induced electric polarization in the SrTiO<sub>3</sub> layer is responsible for this behavior. It is directed away from the interface and hence creates a negative polarization charge opposing that of the polar LaAlO<sub>3</sub> layer. This both increases the critical thickness of the LaAlO<sub>3</sub> layer, and reduces carrier concentration above the critical thickness, in agreement with our experimental results. Our findings suggest that epitaxial strain and induced polarization can be used to tailor 2DEGs properties of the LAO/STO heterointerface.

Eom's group **demonstrated LaAlO<sub>3</sub>/SrTiO<sub>3</sub> heterointerfaces grown by 90° off-axis sputtering** which allows uniform films over a large area. The electrical transport properties of the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> heterointerface are similar to those grown by pulsed laser deposition. We also demonstrated room-temperature conductive probe-based switching of quasi-one-dimensional structures. This work demonstrates that a scalable growth process can be used to create the two-dimensional electron gas system at oxide heterointerfaces.

#### Diamond-based Heterostructures and N-V Centers

Our MURI team was able to integrate **phase-pure EuO on both single-crystal diamond** and on epitaxial diamond films grown on silicon utilizing reactive molecular-beam epitaxy. The epitaxial orientation relationship is (001) EuO || (001) diamond and [110] EuO || [100] diamond. The EuO layer is nominally unstrained and ferromagnetic with a transition temperature of  $68 \pm 2$  K and a saturation magnetization of  $5.5 \pm 0.1$  Bohr magnetons per europium ion on the single-crystal diamond, and a transition temperature of  $67 \pm 2$  K and a saturation magnetization of  $2.1 \pm 0.1$  Bohr magnetons per europium ion on the epitaxial diamond film.

The properties of **NV centers** were developed for a number of **quantum measurement** challenges. Extension of nuclear magnetic resonance (NMR) to nanoscale samples has been a longstanding challenge because of the insensitivity of conventional detection methods. We demonstrated the use of an individual, near-surface nitrogen-vacancy (NV) center in diamond as a sensor to detect proton NMR in an organic sample located external to the diamond. Using a combination of electron spin echoes and proton spin manipulation, we showed that the NV center senses the nanotesla field fluctuations from the protons, enabling both time-domain and spectroscopic NMR measurements on the nanometer scale.

**Theoretical calculations and analysis of the vibronic structure of the spin-triplet optical transition in diamond nitrogen-vacancy (NV) centres** were carried out. The electronic structure of the defect is

described using accurate first-principles methods based on hybrid functionals. We devise a computational methodology to determine the coupling between electrons and phonons during an optical transition in the dilute limit. As a result, our approach yields a smooth spectral function of electron–phonon coupling and includes both quasi-localized and bulk phonons on equal footings. The luminescence lineshape is determined via the generating function approach. We obtain a highly accurate description of the luminescence band, including all key parameters such as the Huang–Rhys factor, the Debye–Waller factor, and the frequency of the dominant phonon mode. More importantly, our work provides insight into the vibrational structure of NV centres, in particular the role of local modes and vibrational resonances. In particular, we find that the pronounced mode at 65 meV is a vibrational resonance, and we quantify localization properties of this mode. These excellent results for the benchmark diamond (NV) centre provide confidence that the procedure can be applied to other defects, including alternative systems that are being considered for applications in quantum information processing.

Electric field noise from **surface charge fluctuations can be a significant source of spin decoherence** for near-surface nitrogen-vacancy (NV) centers in diamond. This conclusion is based on the increase in spin coherence observed when the diamond surface is covered with high-dielectric-constant liquids, such as glycerol. Double-resonance experiments show that improved coherence occurs even though the coupling to nearby electron spins is unchanged when the liquid is applied. Multipulse spin-echo experiments reveal the effect of glycerol on the spectrum of NV frequency noise.

#### Silicon Carbide Divacancy Centers

A new discovery made by Awschalom during the MURI relates to the development of long-lived spin states in SiC. Schlom has demonstrated epitaxial growth of SrTiO<sub>3</sub> (111) on SiC, and hence this new hybrid system constitutes a new focus for our MURI team, but falling within the original goals of the project. Alternative solid state materials for hosting quantum information processing are explored. Multiple polytypes of SiC have been identified as viable candidates.

Crystal defects can confine isolated electronic spins and are promising **candidates for solid-state quantum information**. Alongside research focusing on nitrogen-vacancy centres in diamond, an alternative strategy seeks to identify new spin systems with an expanded set of technological capabilities, a materials-driven approach that could ultimately lead to ‘designer’ spins with tailored properties. Here we show that the 4H, 6H and 3C polytypes of SiC all host coherent and optically addressable defect spin states, including states in all three with room-temperature quantum coherence. The prevalence of this spin coherence shows that crystal polymorphism can be a degree of freedom for engineering spin qubits. Long spin coherence times allow us to use double electron–electron resonance to measure magnetic dipole interactions between spin ensembles in inequivalent lattice sites of the same crystal. Together with the distinct optical and spin transition energies of such inequivalent states, these interactions provide a route to dipole-coupled networks of separately addressable spins.

It was demonstrated that the spin of **optically addressable point defects can be coherently driven with ac electric fields**. Based on magnetic-dipole forbidden spin transitions, this scheme enables spatially confined spin control, the imaging of GHz-frequency electric fields, and the characterization of defect spin multiplicity. We control defect ensembles in SiC, but our methods apply to spin systems in many semiconductors, including the diamond nitrogen-vacancy center. Electrically driven spin resonance offers a viable route towards scalable quantum control of electron spins in a dense array.

**Multipulse magnetometry** exploits all three magnetic sublevels of the  $S=1$  nitrogen-vacancy center in diamond to achieve enhanced magnetic field sensitivity. Based on dual frequency microwave pulsing, the scheme is twice as sensitive to ac magnetic fields as conventional two-level magnetometry. We derive the spin evolution operator for dual frequency microwave excitation and show its effectiveness for double-quantum state swaps. Using multipulse sequences of up to 128 pulses under optimized conditions, we show enhancement of the SNR by up to a factor of 2 in detecting NMR statistical signals, with a 4× enhancement theoretically possible.

We demonstrate optically pumped dynamic nuclear polarization of  $^{29}\text{Si}$  nuclear spins that are strongly coupled to paramagnetic color centers in 4H- and 6H-SiC. The  $99\% \pm 1\%$  degree of polarization that we observe at room temperature corresponds to an effective nuclear temperature of 5  $\mu\text{K}$ . By combining ab initio theory with the experimental identification of the color centers' optically excited states, we quantitatively model how the polarization derives from hyperfine-mediated level anticrossings. These results lay a foundation for SiC-based quantum memories, nuclear gyroscopes, and hyperpolarized probes for magnetic resonance imaging.

### Characterization

**High-resolution TEM measurements** of LAO/STO heterostructures have been performed by Pan, and they have helped to understand the role of interdiffusion across the LAO/STO interface as well as the electronic polarity of this interface. Determination of the microstructures and interfacial properties of  $\text{LaAlO}_3 / \text{SrTiO}_3$  device structures by transmission electron microscopy (TEM) in combination with focused ion beam TEM specimen preparation. We found that Nb in prelayer diffused into Au electrode and that the LAO/STO interface, where the 2DEG forms, is directly contacting to the prelayer but not the Au electrode. These studies provide important feedback to the nanofabrication of the device structures. Determination of microstructures and interfacial atomic structure of  $\text{LaAlO}_3 / \text{SrTiO}_3 / \text{SiC}$  heterostructures grown by molecular beam epitaxy. It was found that the  $\text{SrTiO}_3$  grows epitaxially on the (001) SiC substrate, showing a rough surface and a high density of vertical twin boundaries due to the existence of two different twinning variants. As a result, the  $\text{LaAlO}_3$  over-layer has a poor microstructure and a rough interface to the  $\text{SrTiO}_3$  layer.

1.

**1. Report Type**

Final Report

**Primary Contact E-mail**

Contact email if there is a problem with the report.

jlevy@pitt.edu

**Primary Contact Phone Number**

Contact phone number if there is a problem with the report

4126242736

**Organization / Institution name**

University of Pittsburgh

**Grant/Contract Title**

The full title of the funded effort.

Quantum Preservation, Simulation and Transfer in Oxide Nanostructures

**Grant/Contract Number**

AFOSR assigned control number. It must begin with "FA9550" or "F49620" or "FA2386".

FA9550-10-1-0524

**Principal Investigator Name**

The full name of the principal investigator on the grant or contract.

Jeremy Levy

**Program Manager**

The AFOSR Program Manager currently assigned to the award

Dr. Harold Weinstock

**Reporting Period Start Date**

9/15/2010

**Reporting Period End Date**

3/31/2016

**Abstract**

The main purposes of the theoretical activity supported by this MURI have been to (1) understand the causes and nature of the magnetic and superconducting ordering of the electrons at the LAO/STO interface and (2) determine whether Majorana zero modes might exist and be detected in nanowires 'drawn' at these interfaces by the University of Pittsburgh team.

Important experimental advances have brought us close to a regime in which quantum simulation will be possible. True quantum simulation requires a deep (first-principles-level) understanding of the host material that is performing the simulation. A lot of the research that was conducted involves basic characterization (quantum transport) in LAO/STO nanostructures that have not been patterned in to artificial lattices. We have however performed preliminary results (presented at conferences) that show that this approach is both feasible and highly promising.

The ability to transfer quantum information from one physical embodiment to another represents an essential building block in any quantum architecture. Work in this area has mainly involved diamond, a superconducting semiconductor with long-lived defect complexes (nitrogen-vacancy or NV centers). A central goal of the project was to integrate diamond with LAO/STO heterostructures. This approach proved to be highly challenging, if technically feasible. Structures have been shared with Eom, Levy, Schlom and Pan. Eom and Schlom have also grown epitaxial LAO/STO heterostructures on cubic SiC/Si substrates by

PLD with high pressure RHEED.

A number of cross-cutting activities (growth of superconducting-semiconductor structures, atomic-scale characterization, electrical and optical experiments) will take place, serving multiple tasks. The successful development of new quantum technologies from this research will enable new and powerful types of quantum speedups of computational tasks, including solutions to large systems of linear equations, fully quantum-mechanical simulation of materials, and interoperability among quantum platforms.

### **Distribution Statement**

**This is block 12 on the SF298 form.**

Distribution A - Approved for Public Release

### **Explanation for Distribution Statement**

**If this is not approved for public release, please provide a short explanation. E.g., contains proprietary information.**

### **SF298 Form**

**Please attach your SF298 form. A blank SF298 can be found [here](#). Please do not password protect or secure the PDF. The maximum file size for an SF298 is 50MB.**

[sf0298.pdf](#)

**Upload the Report Document. File must be a PDF. Please do not password protect or secure the PDF. The maximum file size for the Report Document is 50MB.**

[AFOSR Final Report 2016.pdf](#)

**Upload a Report Document, if any. The maximum file size for the Report Document is 50MB.**

### **Archival Publications (published) during reporting period:**

1. G Cheng, PF Siles, F Bi, C Cen, DF Bogorin, C-W Bark, CM Folkman, J-W Park, C-B Eom, G Medeiros-Ribeiro and J Levy, "Sketched oxide single-electron transistor", *Nature Nanotechnology* 6, 343 (2011).
2. L. Fidkowski, R. M. Lutchyn, C. Nayak and M. P. A. Fisher, "Majorana zero modes in one-dimensional quantum wires without long-ranged superconducting order", *Phys. Rev. B* 84, 195436 (2011).
3. W. F. Koehl, B. B. Buckley, F. J. Heremans, G. Calusine, and D. D. Awschalom, "Room temperature coherent control of defect spin qubits in silicon carbide", *Nature* 479, 84 (2011).
4. Y. W. Xie, Y. Hikita, C. Bell, and H. Y. Hwang, "Control of electronic conduction at an oxide heterointerface using surface polar adsorbates," *Nature Communications* 2, 494 (2011).
5. S. H. Baek et al, "Giant piezoelectricity on Si for hyperactive MEMS", *Science* 334, 958 (2011).
6. L. Méchin, C. Adamo, S. Wu, B. Guillet, S. Lebargy, C. Fur, J.-M. Routoure, S. Mercone, M. Belmeguenai, and D.G. Schlom, "Epitaxial La<sub>0.7</sub>Sr<sub>0.3</sub>MnO<sub>3</sub> Thin Films Grown on SrTiO<sub>3</sub> Buffered Silicon Substrates by Reactive Molecular-Beam-Epitaxy," *Physica Status Solidi (a)* 209 (2012) 1090-1095.
7. S.H. Baek, J. Park, D.M. Kim, V.A. Aksyuk, R.R. Das, S.D. Bu, D.A. Felker, J. Lettieri, V. Vaithyanathan, S.S.N. Bharadwaja, N. Bassiri-Gharb, Y.B. Chen, H.P. Sun, C.M. Folkman, H.W. Jang, D.J. Kreft, S.K. Streiffer, R. Ramesh, X.Q. Pan, S. Trolrier-McKinstry, D.G. Schlom, M.S. Rzchowski, R.H. Blick, and C.B. Eom, "Giant Piezoelectricity on Si for Hyperactive MEMS," *Science* 334 (2011) 958-961.
8. Lukasz Fidkowski, Roman M. Lutchyn, Chetan Nayak, Mathew P.A. Fisher, "Majorana Zero Modes in 1D Quantum Wires Without Long-Ranged Superconducting Order," *Phys. Rev. B* 84, 195436.
9. J. P. Veazey, G. Cheng, S. Lu, M. Tomczyk, F. Bi, M. Huang, S. Ryu, C. W. Bark, K. H. Cho, C. B. Eom, P. Irvin and J. Levy, "Nonlocal current-voltage characteristics of gated superconducting sketched oxide nanostructures", *EPL (Europhysics Letters)* 103, 57001 (2013)
10. Joshua P Veazey, Guanglei Cheng, Patrick Irvin, Cheng Cen, Daniela F Bogorin, Feng Bi, Mengchen Huang, Chung-Wung Bark, Sangwoo Ryu, Kwang-Hwan Cho, Chang-Beom Eom and Jeremy Levy, "Oxide-based platform for reconfigurable superconducting nanoelectronics", *Nanotechnology*, 24, 375201 (2013)
11. J. P. Podkaminer, T. Hernandez, M. Huang, S. Ryu, C. W. Bark, S. H. Baek, J. C. Frederick, T. H. Kim, K. H. Cho, J. Levy, M. S. Rzchowski, and C. B. Eom, "Creation of a two-dimensional electron gas and conductivity switching of nanowires at the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interface grown by 90° off-axis sputtering", *Applied Physics Letters*, 103, 071604 (2013)

DISTRIBUTION A: Distribution approved for public release.

12. Guanglei Cheng, Joshua P. Veazey, Patrick Irvin, Cheng Cen, Daniela F. Bogorin, Feng Bi, Mengchen Huang, Shicheng Lu, Chung-Wung Bark, Sangwoo Ryu, Kwang-Hwan Cho, Chang-Beom Eom, and Jeremy Levy, "Anomalous Transport in Sketched Nanostructures at the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> Interface", *Physical Review X*, 3, 011021 (2013)
13. Patrick Irvin, Joshua P. Veazey, Guanglei Cheng, Shicheng Lu, Chung-Wung Bark, Sangwoo Ryu, Chang-Beom Eom, and Jeremy Levy, "Anomalous High Mobility in LaAlO<sub>3</sub>/SrTiO<sub>3</sub> Nanowires", *Nano Lett.*, 13 (2), 364-368 (2013)
14. Bela Bauer and Chetan Nayak, "Area laws in a many-body localized state and its implications for topological order", *J. Stat. Mech.* P09005 (2013)
15. Parsa Bonderson, Chetan Nayak and Xiao-Liang Qi, "A time-reversal invariant topological phase at the surface of a 3D topological insulator", *J. Stat. Mech.* P09016 (2013)
16. Eugeniu Plamadeala, Michael Mulligan, and Chetan Nayak, "Short-range entangled bosonic states with chiral edge modes and T duality of heterotic strings", *Phys. Rev. B* 88, 045131 (2013)
17. Younghyun Kim, Roman M. Lutchyn, and Chetan Nayak, "Origin and transport signatures of spin-orbit interactions in one- and two-dimensional SrTiO<sub>3</sub>-based heterostructures", *Phys. Rev. B* 87, 245121 (2013)
18. Parsa Bonderson and Chetan Nayak, "Quasi-topological phases of matter and topological protection", *Phys. Rev. B* 87, 195451 (2013)
19. Matthew B. Hastings, Chetan Nayak, and Zhenghan Wang, "Metaplectic anyons, Majorana zero modes, and their computational power", *Phys. Rev. B* 87, 165421 (2013)
20. Lukasz Fidkowski, Hong-Chen Jiang, Roman M. Lutchyn, and Chetan Nayak, "Magnetic and superconducting ordering in one-dimensional nanostructures at the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interface", *Phys. Rev. B* 87, 014436 (2013)
21. Beena Kalisky, Eric M. Spanton, Hilary Noad, John R. Kirtley, Katja C. Nowack, Christopher Bell, Hiroki K. Sato, Masayuki Hosoda, Yanwu Xie, Yasuyuki Hikita, Carsten Woltmann, Georg Pfanzelt, Rainer Jany, Christoph Richter, Harold Y. Hwang, Jochen Mannhart & Kathryn A. Moler, "Locally enhanced conductivity due to the tetragonal domain structure in LaAlO<sub>3</sub>/SrTiO<sub>3</sub> heterointerfaces", *Nature Materials* 12, 1091 (2013)
22. Linze Li, Peng Gao, Christopher T. Nelson, Jacob R. Jokisaari, Yi Zhang, Sung-Joo Kim, Alexander Melville, Carolina Adamo, Darrell G. Schlom, and Xiaoqing Pan, "Atomic Scale Structure Changes Induced by Charged Domain Walls in Ferroelectric Materials", *Nano Lett.* 13, 5218 (2013)
23. Peng Gao, Jason Britson, Jacob R. Jokisaari, Christopher T. Nelson, Seung-Hyub Baek, Yiran Wang, Chang-Beom Eom, Long-Qing Chen & Xiaoqing Pan, "Atomic-scale mechanisms of ferroelastic domain-wall-mediated ferroelectric switching", *Nature Communications* 4, 2791 (2013)
24. H. J. Mamin, M. Kim, M. H. Sherwood, C. T. Rettner, K. Ohno, D. D. Awschalom, D. Rugar, "Nanoscale Nuclear Magnetic Resonance with a Nitrogen-Vacancy Spin Sensor", *Science* 339, 557 (2013)
25. David M. Toyli, Lee C. Bassetta, Bob B. Buckley, Greg Calusine and David D. Awschalom, "Engineering and quantum control of single spins in semiconductors", *MRS Bulletin* 38, 139 (2013)
26. David D. Awschalom, Lee C. Bassett, Andrew S. Dzurak, Evelyn L. Hu, Jason R. Petta, "Quantum Spintronics: Engineering and Manipulating Atom-Like Spins in Semiconductors", *Science* 339, 1174 (2013)
27. Abram L. Falk, Bob B. Buckley, Greg Calusine, William F. Koehl, Viatcheslav V. Dobrovitski, Alberto Politi, Christian A. Zorman, Philip X.-L. Feng & David D. Awschalom, "Polytype control of spin qubits in silicon carbide", *Nature Communications* 4, 1819 (2013)
28. Akash Levy, Feng Bi, Mengchen Huang, Shicheng Lu, Michelle Tomczyk, Guanglei Cheng, Patrick Irvin, and Jeremy Levy, "Writing and Low-Temperature Characterization of Oxide Nanostructures", *J. Vis. Exp.*, 89, e51886 (2014)
29. Joseph A. Sulpizio, Shahl Ilani, Patrick Irvin, and Jeremy Levy, "Nanoscale Phenomena in Oxide Heterostructures", *Annual Review of Materials Research*, 44, 117-149 (2014)
30. Feng Bi, Mengchen Huang, Sangwoo Ryu, Hyungwoo Lee, Chung-Wung Bark, Chang-Beom Eom, Patrick Irvin & Jeremy Levy, "Room-temperature electronically-controlled ferromagnetism at the LaAlO<sub>3</sub>/SrTiO<sub>3</sub> interface", *Nature Communications* 5, 5019 (2014)
31. Eugeniu Plamadeala, Michael Mulligan, and Chetan Nayak, "Perfect metal phases of one-dimensional and anisotropic higher-dimensional systems", *Phys. Rev. B* 90, 241101(R) (2014)
32. Matthew B. Hastings, Chetan Nayak, Zhenghan Wang, "On Metaplectic Modular Categories and Their

- Applications", Communications in Mathematical Physics 330, 45(2014)
33. Jennifer Cano, Meng Cheng, Michael Mulligan, Chetan Nayak, Eugeniu Plamadeala, and Jon Yard, "Bulk-edge correspondence in  $(2 + 1)$ -dimensional Abelian topological phases", Phys. Rev. B 89, 115116 (2014)
34. Roger S. K. Mong, David J. Clarke, Jason Alicea, Netanel H. Lindner, Paul Fendley, Chetan Nayak, Yuval Oreg, Ady Stern, Erez Berg, Kirill Shtengel, and Matthew P. A. Fisher, "Universal Topological Quantum Computation from a Superconductor-Abelian Quantum Hall Heterostructure", Phys. Rev. X 4, 011036 (2014)
35. A. Melville, T. Mairoser, A. Schmehl, M. Fischer, S. Gsell, M. Schreck, D. D. Awschalom, T. Heeg, B. Holländer, J. Schubert and D. G. Schlom, "Epitaxial growth of europium monoxide on diamond", Appl. Phys. Lett. 103, 222402 (2013)
36. P. V. Klimov, A. L. Falk, B. B. Buckley, and D. D. Awschalom, "Electrically Driven Spin Resonance in Silicon Carbide Color Centers", Phys. Rev. Lett. 112, 087601 (2014)
37. Abram L. Falk, Paul V. Klimov, Bob B. Buckley, Viktor Ivády, Igor A. Abrikosov, Greg Calusine, William F. Koehl, Ádám Gali, and David D. Awschalom, "Electrically and Mechanically Tunable Electron Spins in Silicon Carbide Color Centers", Phys. Rev. Lett. 112, 187601 (2014)
38. H. J. Mamin, M. H. Sherwood, M. Kim, C. T. Rettner, K. Ohno, D. D. Awschalom, and D. Rugar, "Multipulse Double-Quantum Magnetometry with Near-Surface Nitrogen-Vacancy Centers", Phys. Rev. Lett. 113, 030803 (2014)
39. Audrius Alkauskas, Bob B Buckley, David D Awschalom and Chris G Van de Walle, "First-principles theory of the luminescence lineshape for the triplet transition in diamond NV centres", New Journal of Physics 16, 037026 (2014)
40. Guanglei Cheng, Michelle Tomczyk, Shicheng Lu, Joshua P. Veazey, Mengchen Huang, Patrick Irvin, Sangwoo Ryu, Hyungwoo Lee, Chang-Beom Eom, C. Stephen Hellberg & Jeremy Levy, "Electron pairing without superconductivity", Nature 521, 196 (2015)
41. Jennifer Cano, Meng Cheng, Maissam Barkeshli, David J. Clarke, and Chetan Nayak, "Chirality-protected Majorana zero modes at the gapless edge of Abelian quantum Hall states", Phys. Rev. B 92, 195152 (2015)
42. Kiryl Pakrouski, Michael R. Peterson, Thierry Jolicoeur, Vito W. Scarola, Chetan Nayak, and Matthias Troyer, "Phase Diagram of the  $\nu=5/2$  Fractional Quantum Hall Effect: Effects of Landau-Level Mixing and Nonzero Width", Phys. Rev. X 5, 021004 (2015)
43. Abram L. Falk, Paul V. Klimov, Viktor Ivády, Krisztián Szász, David J. Christle, William F. Koehl, Ádám Gali, and David D. Awschalom, "Optical Polarization of Nuclear Spins in Silicon Carbide", Phys. Rev. Lett. 114, 247603 (2015)
44. M. Kim, H. J. Mamin, M. H. Sherwood, K. Ohno, D. D. Awschalom, and D. Rugar, "Decoherence of Near-Surface Nitrogen-Vacancy Centers Due to Electric Field Noise", Phys. Rev. Lett. 115, 087602 (2015)

**2. New discoveries, inventions, or patent disclosures:**

**Do you have any discoveries, inventions, or patent disclosures to report for this period?**

Yes

**Please describe and include any notable dates**

UPITT Ref. No.: 03092

Foley Ref. No.: 076333-0683

Title: Oxide Interface Displaying Electronically Controllable Ferromagnetism

Assigned Application No.: 14/801,410

Filed: July 16, 2015

**Do you plan to pursue a claim for personal or organizational intellectual property?**

No

**Changes in research objectives (if any):**

**Change in AFOSR Program Manager, if any:**

**Extensions granted or milestones slipped, if any:**

One NCE after Period 5 was requested and granted.

**AFOSR LRIR Number**

**LRIR Title**

**Reporting Period**

**Laboratory Task Manager**

**Program Officer**

**Research Objectives**

**Technical Summary**

**Funding Summary by Cost Category (by FY, \$K)**

	Starting FY	FY+1	FY+2
Salary			
Equipment/Facilities			
Supplies			
Total			

**Report Document**

**Report Document - Text Analysis**

**Report Document - Text Analysis**

**Appendix Documents**

**2. Thank You**

**E-mail user**

Jun 27, 2016 13:31:02 Success: Email Sent to: jlevy@pitt.edu