



Dynamics of Photoexcitation at Nanostructured Carbon Interfaces

Martin Zanni
UNIVERSITY OF WISCONSIN SYSTEM MADISON WI

07/14/2015
Final Report

DISTRIBUTION A: Distribution approved for public release.

Air Force Research Laboratory
AF Office Of Scientific Research (AFOSR)/ RTE
Arlington, Virginia 22203
Air Force Materiel Command

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188				
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.								
1. REPORT DATE (DD-MM-YYYY) 7-03-2015		2. REPORT TYPE Final		3. DATES COVERED (From - To) 3/15/12 -3/14/15				
4. TITLE AND SUBTITLE Dynamics of Photoexcitation and Photocatalysis at Nanostructured Carbon Interfaces				5a. CONTRACT NUMBER				
				5b. GRANT NUMBER FA9550-12-1-0063				
				5c. PROGRAM ELEMENT NUMBER				
6. AUTHOR(S) Zanni, Martin				5d. PROJECT NUMBER				
				5e. TASK NUMBER				
				5f. WORK UNIT NUMBER				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Wisconsin System Research and Sponsored Programs 21 N. Park Street, Suite 6401 Madison, WI 53715-1218				8. PERFORMING ORGANIZATION REPORT NUMBER MSN152143				
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) USAF, AFRL DUNS 143574726 AF Office of Scientific Research 875 Randolph St., Room 3112 Arlington, VA 22203 Julia Stewart (937) 255-0208; julia.stewart@afosr.af.mil				10. SPONSOR/MONITOR'S ACRONYM(S)				
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)				
12. DISTRIBUTION/AVAILABILITY STATEMENT Distribution A - Approved for Public Release								
13. SUPPLEMENTARY NOTES								
14. ABSTRACT During this grant, we have made major contributions to the understanding and practice of photoexcitation and photocatalysis at nanostructured carbon interfaces. There were two aspects to this grant. One aspect was to study the dynamics of films of carbon nanotubes for next generation photovoltaics and photodetectors. The other was to study the dynamics of CO2 reduction using solvated electrons. We made excellent progress on both fronts, with each direction leading to publications in high-impact journals. With regard to the carbon nanotubes, the highlight was developing a new technique that we called two-dimensional white-light (2D WL) spectroscopy. With it, we mapped the energy flow through thin films of semiconducting carbon nanotubes with unprecedented resolution. This work was published in Nature Communications. Regarding CO2 reduction, we demonstrated highly selective photochemical reduction of CO2 to CO with virtually no reduction of hydrogen (published in Angewandte Chemie). We have also identified conditions under which CO2 can be also reduced to CO using inexpensive diamond nanocrystals, like that commonly used as a polishing grit. Please see our full report for a more complete abstract and description of our progress.								
15. SUBJECT TERMS carbon nanotubes, CO2 reduction, exciton transfer, ultrafast spectroscopy								
16. SECURITY CLASSIFICATION OF: <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 33%; padding: 2px;">a. REPORT</td> <td style="width: 33%; padding: 2px;">b. ABSTRACT</td> <td style="width: 33%; padding: 2px;">c. THIS PAGE</td> </tr> </table>			a. REPORT	b. ABSTRACT	c. THIS PAGE	17. LIMITATION OF ABSTRACT		18. NUMBER OF PAGES
a. REPORT	b. ABSTRACT	c. THIS PAGE						
19a. NAME OF RESPONSIBLE PERSON Martin Zanni			19b. TELEPHONE NUMBER (Include area code) 608-262-4783					

Reset

INSTRUCTIONS FOR COMPLETING SF 298

1. REPORT DATE. Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

2. REPORT TYPE. State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

3. DATES COVERED. Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

4. TITLE. Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

5a. CONTRACT NUMBER. Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

5b. GRANT NUMBER. Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

5c. PROGRAM ELEMENT NUMBER. Enter all program element numbers as they appear in the report, e.g. 61101A.

5d. PROJECT NUMBER. Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

5e. TASK NUMBER. Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

5f. WORK UNIT NUMBER. Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

6. AUTHOR(S). Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES). Self-explanatory.

8. PERFORMING ORGANIZATION REPORT NUMBER. Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES). Enter the name and address of the organization(s) financially responsible for and monitoring the work.

10. SPONSOR/MONITOR'S ACRONYM(S). Enter, if available, e.g. BRL, ARDEC, NADC.

11. SPONSOR/MONITOR'S REPORT NUMBER(S). Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

12. DISTRIBUTION/AVAILABILITY STATEMENT. Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

13. SUPPLEMENTARY NOTES. Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

14. ABSTRACT. A brief (approximately 200 words) factual summary of the most significant information.

15. SUBJECT TERMS. Key words or phrases identifying major concepts in the report.

16. SECURITY CLASSIFICATION. Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

17. LIMITATION OF ABSTRACT. This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

Dynamics of Photoexcitation and Photocatalysis at Nanostructured Carbon Interfaces

Michael S. Arnold, Robert J. Hamers, and Martin T. Zanni

Department of Materials Science and Engineering and Department of Chemistry
University of Wisconsin-Madison

Abstract

During this grant, we have made major contributions to the understanding and practice of photoexcitation and photocatalysis at nanostructured carbon interfaces. There were two aspects to this grant. One aspect was to study the dynamics of films of carbon nanotubes for next generation photovoltaics and photodetectors. The other was to study the dynamics of CO₂ reduction using solvated electrons. We made excellent progress on both fronts, with each direction leading to publications in high-impact journals. With regard to the carbon nanotubes, the highlight was developing a new technique that we called two-dimensional white-light (2D WL) spectroscopy. With it, we mapped the energy flow through thin films of semiconducting carbon nanotubes with unprecedented resolution. We learned that energy does not hop between parallel tubes as one might expect from typical resonant-types of energy transfer processes, but instead occurs at the intersections between tubes, leading to dramatic changes in the direction of energy propagation. This work was published in *Nature Communications*. Regarding CO₂ reduction, we demonstrated highly selective photochemical reduction of CO₂ to CO with virtually no reduction of hydrogen (published in *Angewandte Chemie*) and have explored how to optimize this process using an understanding of the kinetics of solvated electron reactions. At moderate (10-20 atmosphere) pressures of CO₂ the rate of CO₂ reduction greatly exceeds the rate of H⁺ reduction at pH=3.5, yielding high selectivity for CO₂ reduction over H⁺ reduction. Selective reduction of CO₂ without oxidation of the diamond photocatalyst also requires providing a mechanism for a corresponding oxidation reaction, either by using a secondary Pt electrode or by including a hole scavenger such as sulfite. We have since identified conditions under which CO₂ can be also reduced to CO using inexpensive diamond nanocrystals, like that commonly used as a polishing grit.

Detailed Accomplishments:

1. Dynamics of energy transport in coupled carbon nanotube materials for next generation solar cells

In previous annual reports we summarized our experiments using pump-probe spectroscopy to probe energy transfer in thin films of electronic-type controlled semiconducting carbon nanotubes. Semiconducting carbon nanotubes are intriguing materials for photovoltaic and photodetector devices, as well as FETs and other devices, because they have strong optical absorptivity, ultrafast charge and energy transport, excellent stability, and economical solution-processability. We made excellent progress in better characterizing these exciting materials and in the synthesis of variations of these thin films. The pump-probe experiments were published in *ACS Nano* and *Nano Letters*, which are premiere journals for the nanosciences.

During the last year of this grant, we made a technological breakthrough in the way that energy transfer can be monitored in these and many other materials. The absorption spectrum of this film stretches from the visible to the near-infrared, which is a good property for light harvesting applications, but makes it difficult to study experimentally. The standard approach is to study one electronic transition at a time, using a tunable pump pulse followed by a continuum probe pulse, like we did in the first two years of our

grant. Now, we have developed a new technique that we call two-dimensional white light spectroscopy (2D WL). 2D WL spectroscopy uses a broadband continuum as the pump source that enables us to simultaneously examine a spectral range spanning from 500-1400 nm. The 2D WL spectra resolve energy transfer between all possible combinations of excitonic states in the band gap-selected nanotubes, thereby providing an instantaneous and comprehensive snapshot of the dynamical pathways. We observe exciton hopping, exciton dissociation, and anti-correlated energy levels; all of which have important implications in the development of carbon nanotube electronics and optoelectronics. This work was published in *Nature Communications*. We have also demonstrated it on quantum dots and on pentacene thin films to establish it as a general tool for measuring energy transfer. We are very excited about this technique and have been getting much attention for its implementation.

Accomplishments in synthesizing tailored coupled carbon nanotube materials and devices: We have post-synthetically isolated two populations of electronic-type sorted semiconducting carbon nanotubes, with bandgap distributions tailored for photovoltaic devices, for measurements of ultrafast photoexcitation dynamics in isolated thin films and solar cells made from coupled nanotubes. First, we have used poly(fluorene) derivatives to isolate an intentionally polydisperse mixture consisting of 5 discrete bandgaps of nanotubes ranging from 1.17 eV to 0.93 eV. Each nanotube can be spectrally resolved, allowing us to map inter-nanotube energy transfer kinetics. Second, we have isolated nearly monochiral (7, 5) nanotubes with a bandgap of 1.17 eV, allowing us to probing energy transfer kinetics without energy loss. We have learned so far how to decrease and increase inter-nanotube coupling in nanotube thin films by controlling the polymer:nanotube ratio within the films. Moreover, we have discovered how to tailor inter-tube coupling by controlling the film morphology. Towards this end, we have discovered how to create extremely porous and low density films of semiconducting nanotubes by co-casting the nanotubes with a sacrificial polymer and eliminating the polymer using a critical point drying process. This process creates aerogel structures that are 99.8% porous. These samples were instrumental as controls in our *ACS Nano* paper for determining the mechanisms of inter-fiber energy transfer because the fibers are so well separated in these samples that inter-fiber energy transfer is suppressed. Moreover we discovered that the pores can be back-filled with solution-processable C₆₀-derivative electron acceptors and the films then partially re-condensed to create bulk heterojunctions with improved power conversion efficiency compared to planar devices (published in *Small*).

2. Dynamics of CO₂ reduction via solvated electrons

During the last year we identified conditions necessary to achieve highly selective photochemical reduction of CO₂ to CO in aqueous media. One of the most striking aspects of this work is that by using modest internal pressures in the photolysis cell, we are able to almost completely eliminate the electrochemical reduction of H⁺ to the hydrogen atom $\text{H}^+ + \text{e}^-_{(\text{aq})} \rightarrow \text{H}^\bullet_{(\text{aq})}$. This is an important result, because in virtually all previous studies of CO₂ reduction in aqueous media, formation of H₂ is the predominant product. This remarkable selectivity for CO₂ reduction is due in large part to the kinetic rates of electron-transfer reactions: Although the rate constant for $\text{H}^+ + \text{e}^-_{(\text{aq})} \rightarrow \text{H}^\bullet_{(\text{aq})}$ is large, by using modest (10-20 atmospheres) for p_{CO₂}, the overall rate for $\text{CO}_2 + \text{e}^-_{(\text{aq})} \rightarrow \text{CO}_2^{\cdot-}_{(\text{aq})}$ can be made to exceed that for $\text{H}^+ + \text{e}^-_{(\text{aq})} \rightarrow \text{H}^\bullet_{(\text{aq})}$, leading to >95% selectivity for CO₂ reduction even at pH=3.5. A second critical parameter is having a mechanism for removing valence-band holes before they induce oxidation

of the diamond (which also forms CO). Every electron emitted from diamond must be accompanied by an oxidation process to maintain charge neutrality; however, diamond's shallow valence band position yields only low rates for the necessary oxidation processes. We found two approaches to solving this problem: (1) using a secondary Pt electrode to oxidize water, or (2) including a hole scavenger (such as sulfite) in the reaction mixture. The use of a small (~ -0.5 V) potential to the diamond also helps. We confirmed selectivity of reaction and the absence of competing oxidation of diamond itself using isotope labeling studies. Our experiments showed that gas-phase $^{13}\text{CO}_2$ yielded exclusively ^{13}CO with no significant ^{12}CO .

While our initial work indicated that nanodiamond was particularly prone to oxidation, we also found that inexpensive diamond nanopowder (<125 nm) can achieve similarly high selectivity provided that a suitable hole scavenger is used. Product distributions were measured by FTIR and NMR spectroscopy. Illumination-induced changes in diamond nanoparticle oxidation state and aggregation state were also performed. Ultimately this work demonstrates that inexpensive diamond nanopowder can be an effective homogeneous photocatalyst for CO_2 reduction.

We also provided diamond electrodes for investigations by Dr. Tim Berto in Prof. John Berry's group investigating the electrolyte composition on the electrochemical reduction of CO_2 . That work showed that, contrary to reports published by other groups, tetraalkylammonium ions are not catalysts for CO_2 reduction.

Complete List of publications supported in-full or in-part by this grant

Randy D. Mehlenbacher, Thomas J. McDonough, Maksim Grechko¹, Meng-Yin Wu, Michael S. Arnold, Martin T. Zanni, Energy Transfer Pathways in Semiconducting Carbon Nanotubes Revealed using Two Dimensional White-Light Spectroscopy, *Nature Communications*, 6, 6732 (2015).

Shea MJ, Mehlenbacher RD, Zanni MT, Arnold MS. 2014. Experimental Measurement of the Binding Configuration and Coverage of Chirality-sorting Polyfluorenes on Carbon Nanotubes. *J. Phys. Chem. Lett.* 5, 3742 (2014)

Shu Yao, Rose Ruther, Linghong Zhang, Ryan Franking, Robert Hamers, and John Berry, J. "Covalent attachment of catalyst molecules to conductive diamond: CO_2 reduction using "smart" electrodes", *J. Am. Chem. Soc.* 2012, 134, 15632-15635.

Grechko M, Ye Y, Mehlenbacher RD, McDonough TJ, Wu M-Y, Jacobberger RM, Arnold MS, Zanni MT. 2014. Diffusion Assisted Photoexcitation Transfer in Coupled Semiconducting Carbon Nanotube Thin Films. *ACS Nano*. 8(6):5383–5394.

Michael S. Arnold, Jeffrey L. Blackburn, Jared J. Crochet, Stephen K. Doorn, Juan G. Duque, Aditya Mohite, and Hagen Telg, Recent Developments in the Photophysics of Single-Wall Carbon Nanotubes for Active and Passive Material Elements in Thin Film Photovoltaics, *Phys. Chem. Chem. Phys.*, 2013, 15, 14896-14918.

Grechko, M. and Zanni MT. "Quantification of transition dipole strengths using 1D and 2D spectroscopy for the identification of molecular structures via exciton delocalization: Application to α -helices" *JCP*, 137, 184202 (2012). PMID: 23163364 *Highlighted on cover.

Yu, Y.; Li, J.; Geng, D.; Wang, J.; Zhang, L.; Andrew, T. L.; Arnold, M. S.; Wang, X., Development of Lead Iodide Perovskite Solar Cells Using Three-Dimensional Titanium Dioxide Nanowire Architectures. *ACS Nano* 2015, 9 (1), 564-572.

Ye Y, Bindl DJ, Jacobberger RM, Wu M-Y, Singha Roy S, Arnold MS, Semiconducting Carbon Nanotube Aerogel Bulk Heterojunction Solar Cells, *Small* 10 (16), pp 3299-3306 (2014).

Timothy C. Berto, Linghong Zhang, Robert J. Hamers, and John F. Berry. "Electrolyte Dependence on CO₂ Electroreduction: Tetraalkylammonium Ions are Not Electrocatalysts", *ACS Catalysis* **2015**, 5, 703-707.

Linghong Zhang, Di Zhu, Gilbert M. Nathanson, and Robert J. Hamers, "Selective Photochemical Reduction of Aqueous CO₂ to CO by Solvated Electrons", *Angewandte Chemie* **2014**, 53, 9746+.

Linghong Zhang and Robert J. Hamers, "Achieving Selective CO₂ Photoreduction to CO with Diamond Nanoparticles", in preparation (manuscript complete, nearly ready for submission).

Archival Publications (published) **during reporting period:**

Randy D. Mehlenbacher, Thomas J. McDonough, Maksim Grechko¹, Meng-Yin Wu, Michael S. Arnold, Martin T. Zanni, Energy Transfer Pathways in Semiconducting Carbon Nanotubes Revealed using Two Dimensional White-Light Spectroscopy, *Nature Communications*, 6, 6732 (2015).

Shea MJ, Mehlenbacher RD, Zanni MT, Arnold MS. 2014. Experimental Measurement of the Binding Configuration and Coverage of Chirality-sorting Polyfluorenes on Carbon Nanotubes. *J. Phys. Chem. Lett.* 5, 3742 (2014)

Shu Yao, Rose Ruther, Linghong Zhang, Ryan Franking, Robert Hamers, and John Berry, J. "Covalent attachment of catalyst molecules to conductive diamond: CO₂ reduction using "smart" electrodes", *J. Am. Chem. Soc.* 2012, 134, 15632-15635.

Grechko M, Ye Y, Mehlenbacher RD, McDonough TJ, Wu M-Y, Jacobberger RM, Arnold MS, Zanni MT. 2014. Diffusion Assisted Photoexcitation Transfer in Coupled Semiconducting Carbon Nanotube Thin Films. *ACS Nano*. 8(6):5383–5394.

Michael S. Arnold, Jeffrey L. Blackburn, Jared J. Crochet, Stephen K. Doorn, Juan G. Duque, Aditya Mohite, and Hagen Telg, Recent Developments in the Photophysics of Single-Wall Carbon Nanotubes for Active and Passive Material Elements in Thin Film Photovoltaics, *Phys. Chem. Chem. Phys.*, 2013, 15, 14896-14918.

Grechko, M. and Zanni MT. "Quantification of transition dipole strengths using 1D and 2D spectroscopy for the identification of molecular structures via exciton delocalization: Application to α -helices" *JCP*, 137, 184202 (2012). PMID: 23163364 *Highlighted on cover.

Yu, Y.; Li, J.; Geng, D.; Wang, J.; Zhang, L.; Andrew, T. L.; Arnold, M. S.; Wang, X., Development of Lead Iodide Perovskite Solar Cells Using Three-Dimensional Titanium Dioxide Nanowire Architectures. ACS Nano 2015, 9 (1), 564-572.

Ye Y, Bindl DJ, Jacobberger RM, Wu M-Y, Singha Roy S, Arnold MS, Semiconducting Carbon Nanotube Aerogel Bulk Heterojunction Solar Cells, Small 10 (16), pp 3299-3306 (2014).

Timothy C. Berto, Linghong Zhang, Robert J. Hamers, and John F. Berry. "Electrolyte Dependence on CO₂ Electroreduction: Tetraalkylammonium Ions are Not Electrocatalysts", ACS Catalysis **2015**, 5, 703-707.

Linghong Zhang, Di Zhu, Gilbert M. Nathanson, and Robert J. Hamers, "Selective Photochemical Reduction of Aqueous CO₂ to CO by Solvated Electrons", Angewandte Chemie **2014**, 53, 9746+.

Changes in research objectives (if any): None.

Extensions granted or milestones slipped, if any: None.

1.

1. Report Type

Final Report

Primary Contact E-mail**Contact email if there is a problem with the report.**

zanni@chem.wisc.edu

Primary Contact Phone Number**Contact phone number if there is a problem with the report**

608-262-4783

Organization / Institution name

University of Wisconsin-Madison

Grant/Contract Title**The full title of the funded effort.**

Dynamics of Photoexcitation and Photocatalysis at Nanostructured Carbon Interfaces

Grant/Contract Number**AFOSR assigned control number. It must begin with "FA9550" or "F49620" or "FA2386".**

FA9550-12-1-0063

Principal Investigator Name**The full name of the principal investigator on the grant or contract.**

Martin Zanni, Michael Arnold, and Robert Hamers

Program Manager**The AFOSR Program Manager currently assigned to the award**

Mike Berman

Reporting Period Start Date

3/15/12

Reporting Period End Date

3/14/15

Abstract

During this grant, we have made major contributions to the understanding and practice of photoexcitation and photocatalysis at nanostructured carbon interfaces. There were two aspects to this grant. One aspect was to study the dynamics of films of carbon nanotubes for next generation photovoltaics and photodetectors. The other was to study the dynamics of CO₂ reduction using solvated electrons. We made excellent progress on both fronts, with each direction leading to publications in high-impact journals. With regard to the carbon nanotubes, the highlight was developing a new technique that we called two-dimensional white-light (2D WL) spectroscopy. With it, we mapped the energy flow through thin films of semiconducting carbon nanotubes with unprecedented resolution. We learned that energy does not hop between parallel tubes as one might expect from typical resonant-types of energy transfer processes, but instead occurs at the intersections between tubes, leading to dramatic changes in the direction of energy propagation. This work was published in Nature Communications. Regarding CO₂ reduction, we demonstrated highly selective photochemical reduction of CO₂ to CO with virtually no reduction of hydrogen (published in Angewandte Chemie) and have explored how to optimize this process using an understanding of the kinetics of solvated electron reactions. At moderate (10-20 atmosphere) pressures of CO₂ the rate of CO₂ reduction greatly exceeds the rate of H⁺ reduction at pH=3.5, yielding high selectivity for CO₂ reduction over H⁺ reduction. Selective reduction of CO₂ without oxidation of the diamond

photocatalyst also requires providing a mechanism for a corresponding oxidation reaction, either by using a secondary Pt electrode or by including a hole scavenger such as sulfite. We have since identified conditions under which CO₂ can be also reduced to CO using inexpensive diamond nanocrystals, like that commonly used as a polishing grit.

Distribution Statement

This is block 12 on the SF298 form.

Distribution A - Approved for Public Release

Explanation for Distribution Statement

If this is not approved for public release, please provide a short explanation. E.g., contains proprietary information.

SF298 Form

Please attach your SF298 form. A blank SF298 can be found [here](#). Please do not password protect or secure the PDF. The maximum file size for an SF298 is 50MB.

[AFOSR_form_final.pdf](#)

Upload the Report Document. File must be a PDF. Please do not password protect or secure the PDF. The maximum file size for the Report Document is 50MB.

[afosr_progress_report_final_v1.pdf](#)

Upload a Report Document, if any. The maximum file size for the Report Document is 50MB.

Archival Publications (published) during reporting period:

Randy D. Mehlenbacher, Thomas J. McDonough, Maksim Grechko¹, Meng-Yin Wu, Michael S. Arnold, Martin T. Zanni, Energy Transfer Pathways in Semiconducting Carbon Nanotubes Revealed using Two Dimensional White-Light Spectroscopy, Nature Communications, 6, 6732 (2015).

Shea MJ, Mehlenbacher RD, Zanni MT, Arnold MS. 2014. Experimental Measurement of the Binding Configuration and Coverage of Chirality-sorting Polyfluorenes on Carbon Nanotubes. J. Phys. Chem. Lett. 5, 3742 (2014)

Shu Yao, Rose Ruther, Linghong Zhang, Ryan Franking, Robert Hamers, and John Berry, J. "Covalent attachment of catalyst molecules to conductive diamond: CO₂ reduction using "smart" electrodes", J. Am. Chem. Soc. 2012, 134, 15632-15635.

Grechko M, Ye Y, Mehlenbacher RD, McDonough TJ, Wu M-Y, Jacobberger RM, Arnold MS, Zanni MT. 2014. Diffusion Assisted Photoexcitation Transfer in Coupled Semiconducting Carbon Nanotube Thin Films. ACS Nano. 8(6):5383–5394.

Michael S. Arnold, Jeffrey L. Blackburn, Jared J. Crochet, Stephen K. Doorn, Juan G. Duque, Aditya Mohite, and Hagen Telg, Recent Developments in the Photophysics of Single-Wall Carbon Nanotubes for Active and Passive Material Elements in Thin Film Photovoltaics, Phys. Chem. Chem. Phys., 2013, 15, 14896-14918.

Grechko, M. and Zanni MT. "Quantification of transition dipole strengths using 1D and 2D spectroscopy for the identification of molecular structures via exciton delocalization: Application to α -helices" JCP, 137, 184202 (2012). PMID: 23163364 *Highlighted on cover.

Yu, Y.; Li, J.; Geng, D.; Wang, J.; Zhang, L.; Andrew, T. L.; Arnold, M. S.; Wang, X., Development of Lead Iodide Perovskite Solar Cells Using Three-Dimensional Titanium Dioxide Nanowire Architectures. ACS Nano 2015, 9 (1), 564-572.

Ye Y, Bindl DJ, Jacobberger RM, Wu M-Y, Singha Roy S, Arnold MS, Semiconducting Carbon Nanotube Aerogel Bulk Heterojunction Solar Cells, Small 10 (16), pp 3299-3306 (2014).

Timothy C. Berto, Linghong Zhang, Robert J. Hamers, and John F. Berry. "Electrolyte Dependence on CO₂ Electroreduction: Tetraalkylammonium Ions are Not Electrocatalysts", ACS Catalysis 2015, 5, 703-707.

Linghong Zhang, Di Zhu, Gilbert M. Nathanson, and Robert J. Hamers, "Selective Photochemical Reduction of Aqueous CO₂ to CO by Solvated Electrons", Angewandte Chemie 2014, 53, 9746+.

Changes in research objectives (if any):

None

Change in AFOSR Program Manager, if any:

None

Extensions granted or milestones slipped, if any:

None

AFOSR LRIR Number

LRIR Title

Reporting Period

Laboratory Task Manager

Program Officer

Research Objectives

Technical Summary

Funding Summary by Cost Category (by FY, \$K)

	Starting FY	FY+1	FY+2
Salary			
Equipment/Facilities			
Supplies			
Total			

Report Document

Report Document - Text Analysis

Report Document - Text Analysis

Appendix Documents

2. Thank You

E-mail user

Jul 10, 2015 10:08:01 Success: Email Sent to: zanni@chem.wisc.edu