

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188		
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 27-09-2018		2. REPORT TYPE Final Report		3. DATES COVERED (From - To) 15-Oct-2017 - 14-Oct-2018	
4. TITLE AND SUBTITLE Final Report: Novel Permanent Magnets based on Nanowire Assemblies			5a. CONTRACT NUMBER W911NF-17-1-0529		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER 611102		
6. AUTHORS			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES University of Texas at Arlington 701 South Nedderman Drive Box 19145 Arlington, TX 76019 -0145			8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS (ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSOR/MONITOR'S ACRONYM(S) ARO		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) 71164-MS.3		
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	15. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Ping Liu
a. REPORT UU	b. ABSTRACT UU	c. THIS PAGE UU			19b. TELEPHONE NUMBER 817-272-2815

RPPR Final Report
as of 02-Oct-2018

Agency Code:

Proposal Number: 71164MS

Agreement Number: W911NF-17-1-0529

INVESTIGATOR(S):

Name: Ph.D Ping Liu

Email: pliu@uta.edu

Phone Number: 8172722815

Principal: Y

Organization: **University of Texas at Arlington**

Address: 701 South Nedderman Drive, Arlington, TX 760190145

Country: USA

DUNS Number: 064234610

EIN: 756000121

Report Date: 14-Jan-2019

Date Received: 27-Sep-2018

Final Report for Period Beginning 15-Oct-2017 and Ending 14-Oct-2018

Title: Novel Permanent Magnets based on Nanowire Assemblies

Begin Performance Period: 15-Oct-2017

End Performance Period: 14-Oct-2018

Report Term: 0-Other

Submitted By: Ph.D Ping Liu

Email: pliu@uta.edu

Phone: (817) 272-2815

Distribution Statement: 1-Approved for public release; distribution is unlimited.

STEM Degrees:

STEM Participants:

Major Goals: This short-term project was aimed at understanding the proximity effect in ferromagnetic nanowire assemblies.

Accomplishments: See the technical report with details.

Training Opportunities: Nothing to Report

Results Dissemination: Nothing to Report

Honors and Awards: Nothing to Report

Protocol Activity Status:

Technology Transfer: Nothing to Report

PARTICIPANTS:

Participant Type: Faculty

Participant: J. Ping Liu

Person Months Worked: 1.00

Funding Support:

Project Contribution:

International Collaboration:

International Travel:

National Academy Member: N

Other Collaborators:

Participant Type: Postdoctoral (scholar, fellow or other postdoctoral position)

Participant: Jeotikanta Mohapatra

Person Months Worked: 12.00

Funding Support:

Project Contribution:

International Collaboration:

International Travel:

RPPR Final Report
as of 02-Oct-2018

National Academy Member: N
Other Collaborators:

Participant Type: Graduate Student (research assistant)

Participant: Meiyang Xing

Person Months Worked: 12.00

Funding Support:

Project Contribution:

International Collaboration:

International Travel:

National Academy Member: N

Other Collaborators:

ARTICLES:

Publication Type: Journal Article

Peer Reviewed: Y

Publication Status: 1-Published

Journal: ACS Appl. Mater. Interfaces

Publication Identifier Type:

Publication Identifier:

Volume: 2018

Issue: 10

First Page #: 27233

Date Submitted: 9/27/18 12:00AM

Date Published: 7/23/18 5:00AM

Publication Location:

Article Title: Exchange coupling in soft magnetic nanostructures and its direct effect on their theranostic properties

Authors: Vikas Nandwana, Ruiying Zhou, Jeotikanta Mohapatra, Sungkyu Kim, Pottumarthi Prasad, J. Ping Liu, \

Keywords: magnetic nanostructures, exchange coupling, contrast enhancement, thermal activation, theranostics

Abstract: Exchange coupling between hard and soft magnetic materials at the nanoscale exhibits novel or improved physical properties for energy and data storage applications. Recently, exchange coupling has also been explored in core/shell magnetic nanostructures (MNS) composed of hard and soft magnetic spinel ferrites, but applications have been limited in biomedicine due to the presence of "toxic" cobalt based ferrites as hard magnetic component. We report core/shell MNS where both core and shell components are soft magnetic ferrites (Fe₃O₄, MnFe₂O₄, and Zn_{0.2}Mn_{0.8}Fe₂O₄) and show that exchange coupling still exists due to the difference in their anisotropy. The physical properties (saturation magnetization, susceptibility, anisotropy, r₂ relaxivity, and specific absorption rate) of core/shell MNS are compared with the same size single phase counterparts which excludes any size dependent effect and gives the direct effect of exchange coupling. After optimization of core and shell components and

Distribution Statement: 1-Approved for public release; distribution is unlimited.

Acknowledged Federal Support: Y

RPPR Final Report
as of 02-Oct-2018

Publication Type: Journal Article

Peer Reviewed: Y

Publication Status: 1-Published

Journal: Phys. Chem. Chem. Phys.

Publication Identifier Type:

Publication Identifier:

Volume: 2018

Issue: 20

First Page #: 12879

Date Submitted: 9/27/18 12:00AM

Date Published: 4/6/18 5:00AM

Publication Location:

Article Title: Size-dependent magnetic and inductive heating properties of Fe₃O₄ nanoparticles: Scaling laws across the superparamagnetic size

Authors: Jeotikanta Mohapatra, Zeng Fanhao, Kevin Elkins, Meiying Xing, Madhav Ghimire, Sunghyun Yoon, Sa

Keywords: nanoparticles, size distribution, hyperthermia

Abstract: An efficient heat activating mediator with an enhanced specific absorption rate (SAR) value is attained via control of the iron oxide (Fe₃O₄) nanoparticle size from 3 to 32 nm. Monodispersed Fe₃O₄ nanoparticles are synthesized via a seed-less thermolysis technique using oleylamine and oleic acid as the multifunctionalizing agents (surfactant, solvent and reducing agent). The inductive heating properties as a function of particle size reveal a strong increase in the SAR values with increasing particle size up to 28 nm. In particular, the SAR values of ferromagnetic nanoparticles (416 nm) are strongly enhanced with the increase of ac magnetic field amplitude than that for the superparamagnetic (3–16 nm) nanoparticles. The enhanced SAR values in the ferromagnetic regime are attributed to the synergistic contribution from the hysteresis and susceptibility loss. Specifically, the 28 nm Fe₃O₄ nanoparticles exhibit an enhanced SAR value of 801 W g⁻¹ which is nearly an order higher than that of

Distribution Statement: 1-Approved for public release; distribution is unlimited.

Acknowledged Federal Support: Y

Final Technical report:

Effects of packing density on the magnetic properties of cobalt nanowire assemblies

1. Introduction

During the last decade, a significant research effort has been given to the synthesis and characterization of magnetic nanowires (NWs), particularly the single-crystal hcp-structured Co NWs. Co NWs with the aspect ratio from 10 to 66 have been synthesized via a solvothermal method by controlling the growth process (Fig.1). The increased aspect ratio leads to enhanced coercivity of the nanowire assemblies up to an optimum value of 12.5 kOe at 300 K, which is close to the theoretical limit of the coercive field (14.3 kOe). To realize a permanent magnet made from the high coercivity nanowires, the effect of packing density on the magnetic properties need to be explored in detail, which is of a fundamental importance to the understanding of nanostructured magnetic materials.

2. Description of the research work

In the past year we have prepared Co NW assemblies with packing densities varying from 2.1 to 6.5 g/cm³, using the as-prepared Co NWs with coercivity (H_c) about 5.5 kOe. The corresponding H_c at room temperature increases from 5.5 kOe to 6.1 kOe with the increase in packing density from 2.1 to 4.5 g/cm³, and the H_c decreases while the packing density further increases. A similar trend in the H_c value has also been found at different temperatures as shown in Figure 2. Moreover, the remanence (M_r) increased from 72.0 to 82.5 emu/g with the increased packing density. The initial increase in H_c and M_r values may be due to enhanced magnetostatics interactions between the nanowires upon increased packing density. However, above the density of 4.5 g/cm³, the H_c decreases possibly due to the proximity effect as it has been noticed in the ΔM plot. The ΔM plot shows a negative peak at high field and it becomes prominent with the increase of density (Figure 3).




Figure 1: (a) TEM image and (b) XRD pattern of Co nanowires. Figure 1a shows the Co nanowires are cylinder shapes of typical size about 100 to 180 nm in length and an average diameter of 10 nm. X-ray diffraction shows that the wires have an expected hcp crystal structure.




Figure 2. (a) Packing density dependence of coercivity at different temperature. Figure 1. (b) SEM image of the Co NWs assemblies. The inset image is the Co NWs assembly pellet.




Figure 3. (a) Delta M of compacted Co NWs assemblies with different packing densities.

3. Publications

1. Vikas Nandwana, Ruiying Zhou, Jeotikanta Mohapatra, Sungkyu Kim, Pottumarthi Prasad, J. Ping Liu, Vinayak Dravid, *Exchange coupling in soft magnetic nanostructures and its direct effect on their theranostic properties*, **ACS Appl. Mater. Interfaces**, 10 (32), pp 27233–27243, **2018**.

2. Jeotikanta Mohapatra, Zeng Fanhao, Kevin Elkins, Meiyong Xing, Madhav Ghimire, Sunghyun Yoon, Sanjay R Mishra, J. Ping Liu, *Size-dependent magnetic and inductive heating properties of Fe₃O₄ nanoparticles: Scaling laws across the superparamagnetic size*, **Phys. Chem. Chem. Phys.**, **2018**, 20, 12879-12887.

3. Meiyong Xing, Jeotikanta Mohapatra, and J. Ping Liu, *Effect of packing density on magnetic properties of Co nanowire assemblies*, in preparation.