

FR-2014

REPORT NO. A-2014

DATE March 4, 1943

SUBJECT

Report of Test on Insulating Material Submitted by Louthan Manufacturing

Company.

NAVAL RESEARCH LABORATORY
BELLEVUE, D. C.

DISTRIBUTION STATEMENT A APPLIES
Further distribution authorized by UNLIMITED only.

March 4, 1943

NRL Report No. R-2014
Buships Problem #38

NAVY DEPARTMENT

Report of

Test on Insulating Material

Submitted by

Louthan Manufacturing Co.

NAVAL RESEARCH LABORATORY
ANACOSTIA STATION
WASHINGTON, D.C.

Number of Pages: Text - 4

Authorization Bureau of Ships letter S67/61(933-2) of
Feb. 20, 1943 to NRL.

Date of Test: 13 February 1943 to 25 February 1943

Prepared by: J. E. Martin, Contract Employee

Reviewed by: W. B. Burgess, Principal Radio Engineer,
Head, Measurement & Direction Finding Section

A. Hoyt Taylor, Chief Physicist
Superintendent, Radio Division

Approved by: W. L. Pryor Jr., Commander, U.S.N.

Approved by: A. H. Van Keuren, Rear Admiral, U. S. N.
Director

Distribution:
Buships (10)

1e1

TABLE OF CONTENTS

<u>Subject</u>	<u>Page</u>
Authorization1
Object of Test.1
Conclusions1a
Recommendations1a
Description of Material under Test.2
Method of Test2
Data Recorded During Test3
Probable Error in Results3
Results of Test4
Conclusions4

APPENDICES

Dielectric Properties	Table I
Moisture Absorption Test	Table II

AUTHORIZATION

1. This problem was authorized by Bureau of Ships letter reference (a). References (b), (c), and (d) are also pertinent.

References:

- (a) Bureau of Ships letter S67/61 (933-2) of Feb. 20, 1943 to NRL.
- (b) Bureau of Ships letter S67/61 (5-23-480) of May 23, 1941 to NRL.
- (c) Bureau of Ships letter S67/61 (480V) of July 17, 1942 to NRL.
- (d) Specifications RE 13A 317F.

OBJECT OF TEST

2. The object of the test was to determine whether the samples of Steatite Body SX-1 submitted by Louthan Manufacturing Company comply with reference (d) for Grade F or G insulating material.

3. The dry and wet loss factors were determined by measurements made at 1000 kc, in compliance with paragraph 2 of reference (c), paragraph 6-1 of reference (d), and in accordance with A.S.T.M. Standards on Testing Electrical Insulating Materials of December 1941. The wet loss factor was measured after the samples had been immersed in distilled water for 48 hours.

4. Moisture absorption measurements were made in accordance with paragraph 6-2 of reference (d) and paragraph 3 of reference (c).

CONCLUSIONS

It is concluded:

(a) That the three samples of steatite submitted by Louthan Manufacturing Company comply with reference (d) for Grade F insulating material and that the moisture absorption does not exceed 0.10%.

RECOMMENDATIONS

It is recommended:

(a) That the steatite submitted by the Louthan Manufacturing Company be approved as Grade F ceramic insulating material.

DESCRIPTION OF MATERIAL UNDER TEST

5. The three samples numbered 583, 584 and 585 by NRL were approximately 5.6 inches square and 0.236 inch in thickness.

METHOD OF TEST

6. Physical measurements of the samples were made with micro-meters and a metric rule; the electrical measurements, by the parallel substitution method of susceptance variation. The dielectric properties were determined from these data.

7. The standard measuring circuit consists of the following equipment:

1000 kc crystal controlled master oscillator power amplifier, assembled by NRL.

NRL Standard inductance No. 6.

General Radio quartz insulated precision condenser, Type 722-Q, serial No. 460.

General Radio vacuum tube voltmeter, Type 726-A, serial No. 1483.

8. The factor of merit of the variable capacitor is stated by the manufacturer to be better than 0.003×10^{-12} Farads. The factor of merit of the entire test circuit is better than 1.11×10^{-12} Farads or one C.G.S. electrostatic unit. The effective Q of the entire measuring circuit is approximately 344 units, measured at 1000 kc.

9. The dry loss factor was determined after allowing the test samples to come to a static equilibrium of ambient temperature and relative humidity with that of the standard measuring circuit, which is assumed to occur in about 24 to 48 hours. Each sample was made into a capacitor by applying foil to both surfaces with petroleum oil. The factors of merit of the standard circuit with and without the samples were measured and each expressed as the ratio of total effective conductance to the resonant angular velocity. The difference between the two factors thus measured is equal to the factor of merit of the sample. When the conductance of the sample is small and can be neglected in comparison with its susceptance, the power factor

is equal to the ratio of the factor of merit to the capacitance. The capacitance is equal to the difference in reading of the standard, taken at resonance, with and without the sample; provided, the residual inductance (L) of standard capacitor is sufficiently small to make W^2LCs , negligible as compared to unity.

10. The dielectric permittivity (K) was determined from physical measurements made upon the sample, as outlined in A.S.T.M. Standards. The loss factor is defined as the product of the power factor and the dielectric permittivity. The wet loss factor was determined in a similar manner after the samples had been immersed in distilled water for a period of 48 hours in compliance with reference (d).

11. The moisture absorption tests were carried out on newly fractured pieces as detailed in paragraph 6-2 of reference (d) where the newly fractured surface was approximately 50% of the unfractured surface of each sample. The samples were soaked in distilled water at room temperature for 100 hours during which time the water was boiled for a period of 1 hour during the first 25th, 49th and 74th hours. At the end of 100 hours the samples were removed from the water, carefully dried with filter paper and weighed immediately. The samples were then placed in a desiccator for a period of 96 hours after which time they were weighed dry.

DATA RECORDED DURING TEST

12. The data recorded during test are given in Tables I and II.

PROBABLE ERROR IN RESULTS

13. The error in the determination of the power factor is not greater than 2%, while that of the loss factor is not greater than 3%. The error in the determination of the weight in the moisture absorption test is approximately 0.00125%.

The data relating to dielectric properties have been corrected for the fringing of the dielectric flux external to the periphery of the electrodes.

Corrections to include the residual errors in the standard measuring circuit have not been applied to these data.

RESULTS OF TEST

14. Results of tests are given in Tables I and II and may be summarized as follows: The data recorded in Table I show that the samples comply with paragraph 6-1 of reference (d) for Grade F insulating material.

15. Table II shows that the samples passed the moisture absorption test as detailed in paragraph 6-2 of reference (d) and paragraph 3 of reference (e).

CONCLUSIONS

16. It is concluded:

(a) That the three samples of steatite submitted by The Louthan Manufacturing Company comply with reference (d) for Grade F insulating material and that the moisture absorption does not exceed 0.10%.

Table I

Dielectric Properties of Steatite Body SX-1
Louthan Manufacturing Company

NRL No.	Dielectric Constant		Power Factor %		Loss Factor %		Grade
	Dry	Wet	Dry	Wet	Dry	Wet	
583	5.51	5.51	0.259	0.338	1.43	1.86	F
584	5.52	5.52	0.265	0.325	1.46	1.79	F
585	5.53	5.53	0.308	0.413	1.70	2.28	F

Table II

Moisture Absorption

NRL No.	Weight in grams		Gain in Weight grams	Gain %
	Dry	Wet		
583	34.361	34.364	0.003	0.0087