

UNCLASSIFIED

AD

AD-E404 423

Technical Report ARMET-TR-20074

SOLUBILITY REPORT OF 2,4,6-TRINITROTOLUENE (TNT)

Dr. Kelley Caflin

December 2022



U.S. ARMY COMBAT CAPABILITIES DEVELOPMENT
COMMAND ARMAMENTS CENTER

Munitions Engineering and Technology Center

Picatinny Arsenal, New Jersey

Approved for public release; distribution is unlimited.

UNCLASSIFIED

UNCLASSIFIED

The views, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement by or approval of the U.S. Government.

Destroy by any means possible to prevent disclosure of contents or reconstruction of the document. Do not return to the originator.

UNCLASSIFIED

UNCLASSIFIED

REPORT DOCUMENTATION PAGE

1. REPORT DATE December 2022		2. REPORT TYPE Final		3. DATES COVERED START DATE April 2015		END DATE June 2019	
4. TITLE AND SUBTITLE Solubility Report of 2,4,6-Trinitrotoluene (TNT)							
5a. CONTRACT NUMBER		5b. GRANT NUMBER				5c. PROGRAM ELEMENT NUMBER	
5d. PROJECT NUMBER		5e. TASK NUMBER				5f. WORK UNIT NUMBER	
6. AUTHOR(S) Dr. Kelley Caflin							
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army DEVCOM AC, METC Energetics and Warheads Directorate (FCDD-ACM-EW) Picatinny Arsenal, NJ 07806-5000						8. PERFORMING ORGANIZATION REPORT NUMBER N/A	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army DEVCOM AC, ESIC Knowledge & Process Management Office (FCDD-ACE-K) Picatinny Arsenal, NJ 07806-5000				10. SPONSOR/MONITOR'S ACRONYM(S)		11. SPONSOR/MONITOR'S REPORT NUMBER(S) Technical Report ARMET-TR-20074	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.							
13. SUPPLEMENTARY NOTES							
14. ABSTRACT Solubilities of 2,4,6-trinitrotoluene (TNT) in five solvents were studied using the Avantium Crystal16™ parallel crystallizer. Solubility curves were constructed by monitoring the clear point of increasingly concentrated solute/solvent mixtures over a range in temperature. The solubility curves constructed were primarily exponential in nature. van't Hoff plots were also constructed from the solubility data.							
15. SUBJECT TERMS Solubility 2,4,6-trinitrotoluene TNT Crystal16 Crystallizer							
16. SECURITY CLASSIFICATION OF:				17. LIMITATION OF ABSTRACT		18. NUMBER OF PAGES	
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U		SAR		17	
19a. NAME OF RESPONSIBLE PERSON Kelley Caflin				19b. PHONE NUMBER (Include area code) (973) 724-2657			

UNCLASSIFIED

CONTENTS

	Page
Introduction	1
Experimental Section	1
Materials	1
Solubility Measurements	1
Results and Discussion	2
Conclusions	7
References	9
Distribution List	11

FIGURES

1	Chemical structure of TNT	1
2	TNT solubility curves in acetone	3
3	TNT solubility curves in ethyl acetate	4
4	TNT solubility curves in ethanol	5
5	TNT solubility curves in cyclohexane	6
6	TNT solubility curves in chloroform	7

UNCLASSIFIED

ACKNOWLEDGMENTS

The author would like to thank Dr. Reddy Damavarapu and Philip Samuels for funding this research. The author would also like to thank Peggy Sanchez for her guidance with initial solubility measurements of TNT in ethanol and ethyl acetate.

INTRODUCTION

The solubility of materials in other materials is a function of the interactions between the solute and the solvent. It is common to hear the phrase amongst chemists: “like dissolves like.” Materials with polar groups tend to be more soluble in polar solvents, such as water, while nonpolar substances tend to dissolve in materials like hydrocarbons. Interactions between solute–solvent molecules may include hydrogen bonding or dipole–dipole interactions (for polar materials) and van der Waals interactions (for nonpolar). Temperature is also known to affect the solubility of materials. In general, the solubility of a solid material in liquid increases with temperature.

In this study, several solubility experiments were carried out for 2,4,6-trinitrotoluene (TNT). Its chemical structure can be seen in figure 1. The solubility of TNT in various solvents was determined. The resulting solubility data can be used for synthesis, recrystallization, and formulation purposes.




Figure 1
Chemical structure of TNT

EXPERIMENTAL SECTION

Materials

The TNT used for ethanol, chloroform, and cyclohexane was Flake TNT, NSN: 1376006283333, lot: CIB93B006-076. The specific lot of TNT for ethyl acetate and acetone was not recorded; however, it was stock Flake TNT. Flake TNT was crushed using a mortar and pestle to reduce sample size to ease filling of vials and stir bar mixing. Solvents used for solubility experiments were purchased from commercial sources and used without further purification. They are as follows: reagent grade acetone from Pharmco-AAPER, Brookfield, CT; ethyl acetate (99.99% extra dry AcroSeal from Acros Organics, Belgium) from Fisher Scientific, Pittsburgh, PA; ethanol: Sigma Aldrich 200 Proof Anhydrous $\geq 99.5\%$, lot: SHBJ3722; cyclohexane: Uvasol Cyclohexane, lot: I0927322 749; and chloroform: Uvasol Chloroform, lot: K50753747 842.

Solubility Measurements

Solubility measurements of TNT were acquired on an Avantium Crystal16™ and analyzed using CrystalClear software. Solvents investigated were acetone, ethyl acetate, ethanol, cyclohexane, and chloroform. In each experiment, the solute was weighed into a small, clear, and colorless high-performance, liquid-chromatography-type vial equipped with a magnetic stir bar. A solvent was added and the exact concentration of the solution was recorded. The vials were placed into the Avantium Crystal16™, and temperature was cycled three times from 20 °C to approximately 5 °C below the boiling point of the solvent with 60-min equilibration periods between heating and cooling. Ramp rates were 0.5 and -0.3 °C/min.

The solubility of each vial solution was determined by identifying clear point temperatures, which are defined as the temperature at which the turbidity of the solution decreases upon heating and the solution becomes transparent. Graphing the clear point temperatures versus the concentration of the solution yields a solubility curve and associated equation.

RESULTS AND DISCUSSION

A van't Hoff plot was constructed from each solubility curve using the following equation:

$$\ln x = -\frac{\Delta H}{R} \left(\frac{1}{T} - \frac{1}{T_0} \right) \quad (1)$$

where x is the solute mole fraction, ΔH is the dissolution enthalpy, R is the ideal gas constant, T_0 is a reference temperature (K), and T is the saturation temperature (K) of the mole fraction x (ref. 1). The results of this equation are a linear relationship of the natural logarithm of x ($\ln x$) versus T^{-1} when the entropy and enthalpy are constant with temperature change. Using the resulting trend line, one can calculate the solubilities at other temperatures. Shown in figures 2 through 6 are the solubility curves of TNT in acetone, ethyl acetate, ethanol, cyclohexane, and chloroform.




Figure 2
TNT solubility curves in acetone




Figure 3
TNT solubility curves in ethyl acetate




Figure 4
TNT solubility curves in ethanol




Figure 5
TNT solubility curves in cyclohexane




Figure 6
TNT solubility curves in chloroform

CONCLUSIONS

Solubility curves and van't Hoff plots of 2,4,6-trinitrotoluene (TNT) were constructed for five solvents using the Avantium Crystal16™ parallel crystallizer. The solubility curves constructed were exponential in nature. The resulting regression lines show limited variation with all R^2 values greater than 0.9771. The solubility curves or van't Hoff plots can be used to predict solubility at the temperature of interest.

UNCLASSIFIED

REFERENCES

1. ter Horst, J. H., Deij, M. A., and Cains, P. W., "Discovering New Co-Crystals," Crystal Growth & Design, Vol. 9, No. 3, pp. 1531-1537, 2009.

UNCLASSIFIED

DISTRIBUTION LIST

U.S. Army DEVCOM AC
ATTN: FCDD-ACE-K
FCDD-ACM-EW, K. C. Caflin
Picatinny Arsenal, NJ 07806-5000

Defense Technical Information Center (DTIC)
ATTN: Accessions Division
8725 John J. Kingman Road, Ste. 0944
Fort Belvoir, VA 22060-6218

GIDEP Operations Center
P.O. Box 8000
Corona, CA 91718-8000
gidep@gidep.org

UNCLASSIFIED

REVIEW AND APPROVAL OF CCDC ARMAMENTS CENTER REPORTS

THIS IS A:



TECHNICAL REPORT



SPECIAL REPORT



MEMORANDUM REPORT



ARMAMENT GRADUATE SCHOOL REPORT

FUNDING SOURCE ^{JEMTP}

[e.g., TEX3; 6.1 (ILIR, FTAS); 6.2; 6.3; PM funded EMD; PM funded Production/ESIP; Other (please identify)]

Solubility Report of 2,4,6-Trinitrotoluene (TNT)

Title

Project

Dr. Kelley Caffin

Author/Project Engineer

Report number/Date received (to be completed by LCSD)

x2657

B3028

FCDD-ACM-EW

Extension

Building

Author's/Project Engineers Office (Division, Laboratory, Symbol)

PART 1. Must be signed before the report can be edited.

- a. The draft copy of this report has been reviewed for technical accuracy and is approved for editing.
- b. Use Distribution Statement A ☒, B ☐, C ☐, D ☐, E ☐, or F ☐ for the reason checked on the continuation of this form. Reason: _____
 1. If Statement A is selected, the report will be released to the National Technical Information Service (NTIS) for sale to the general public. Only unclassified reports whose distribution is not limited or controlled in any way are released to NTIS.
 2. If Statement B, C, D, E, or F is selected, the report will be released to the Defense Technical Information Center (DTIC) which will limit distribution according to the conditions indicated in the statement.
- c. The distribution list for this report has been reviewed for accuracy and completeness.

Steven M. Nicolich

Division Chief

(Date)

PART 2. To be signed either when draft report is submitted or after review of reproduction copy.

This report is approved for publication.

Steven M. Nicolich

Division Chief

(Date)

LCSD 49 supersedes SMCAR Form 49, 20 Dec 06

Approved for public release; distribution is unlimited.

UNCLASSIFIED