

AD-A013447

RIA-80-U268

FA 5047

AD

A013-447

HYDROGEN BONDING IN NITROCELLULOSE
AND ITS IMPLICATIONS ON
DETERRING OF SMALL ARMS PROPELLANT

TECHNICAL
LIBRARY

July 1975

Approved for public release; distribution unlimited.



Munitions Development & Engineering Directorate

U.S. ARMY ARMAMENT COMMAND
FRANKFORD ARSENAL
PHILADELPHIA, PENNSYLVANIA 19137

DISPOSITION INSTRUCTIONS

Destroy this report when is no longer needed. Do not return it to the originator.

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Hydrogen Bonding in Nitrocellulose and Its Implications on Deterring of Small Arms Propellant

B. W. BRODMAN, M. P. DEVINE, and M. T. GURBARG

Munition Development and Engineering Directorate
Frankford Arsenal
Philadelphia, Pennsylvania 19137

ABSTRACT

The hydrogen bonding characteristics of well-characterized nitrocellulose samples were studied by means of IR spectroscopy. Results obtained for nitrocellulose samples of varying nitrogen content showed that the strength of the hydrogen bond increases with decreasing nitrogen content. In addition, atmospheric moisture was found to hydrogen bond with nitrocellulose hydroxyl groups. The implications of these findings on the deterring phase of the small arms propellant manufacturing process are discussed.

INTRODUCTION

A previous study [1] established that hydrogen bonding occurs between small arms propellant burning rate modifiers which are called deterrents (di-n-butyl phthalate, camphor, ethyl centralite, and methyl

centralite) and unesterified hydroxyl groups in nitrocellulose (NC). These deterrent molecules are diffused into the spherical NC-based small arms propellant grains in order to reduce the initial burning rate of the propellant bed when the surface area is at maximum. A knowledge of the concentration profile of the deterrent molecule as a function of distance into the grain as well as the physical and chemical interactions involved is important for interior ballistic computer simulation and a host of manufacturing and storage problems. An important consideration in describing the deterring mechanism is a determination of the factors which would reduce the possibility of hydrogen bonding between deterrent molecules and NC hydroxyl groups. For this reason a detailed study of hydroxyl interaction in well-characterized NC samples was performed.

A previous study based on measurement of γ -OH in the IR region indicated that hydrogen bonding may occur in NC films. Cherubin [2] determined the γ -OH for NC films having two different nitration levels (11.8 and 5.7%N) and cellulose. The reported γ -OH for NC of 11.8%N was 3559 cm^{-1} , for 5.7%N was 3597 cm^{-1} , and for cellulose was 3356 cm^{-1} . These NC samples were not well characterized and no molecular weight or viscosity data was given. Based on this data, it appears that the author concluded that hydrogen bonding does occur in NC and that it is enhanced by increasing nitrate ester presence.

It should be pointed out that the 11.8%N NC corresponds to 0.8 hydroxyl groups per repeat unit and that the 5.7%N NC corresponds to 2.20 hydroxyl groups per repeat unit. This raises the possibility that hydrogen bonding occurred within a repeat unit in the 5.7%N NC.

EXPERIMENTAL

The five well-characterized NC samples used in this study were obtained from Picatinny Arsenal. Raw NC samples obtained from Hercules, Inc. were dissolved in acetone and then fractional precipitation was accomplished by means of the addition of various water/acetone solutions having increasing water content. Data for number and weight-average molecular weight calculations were obtained from a Waters Model 200 gel permeation chromatograph. The solvent used in all cases for the gel permeation chromatography was acetone and the support medium was Porasil. Five 4-ft columns of varying permeability Porasil 1500X, 1000X, 400X, 250X, and 60X were used.

Nine polystyrene standards obtained from Waters were used to calibrate the chromatograph. These standards ranged in molecular weight from 5,000 to 2,610,000. Number- and weight-average molecular weights for the nitrocellulose were calculated using the summation of heights method and are given in Table 1. NC samples of narrow molecular weight distribution are not commercially available and this is the reason for the use of polystyrene standards. It

TABLE 1. Molecular Weight Data for Various Nitrogen Content NC Samples

%N in NC	M_w	M_n	M_w/M_n
12.10	141,500	84,500	1.67
12.20	154,800	92,400	1.68
12.30	230,400	224,800	1.03
12.60	139,600	90,450	1.54
13.16	128,200	76,000	1.69

should be pointed out that since the M_w and M_n were calculated from the chromatographic data, they are strongly dependent on the standards used to calibrate the GPC system. For this reason the data are not as accurate as one would want. However, the data does show the relative trends between samples with sufficient accuracy.

All of the NC samples were dissolved in MC&B reagent grade ethyl acetate, and these solutions were cast as films on salt plates. After film casting, the plates were placed in a vacuum desiccator and subjected to a roughing pump vacuum for several hours. IR spectra for each sample were run with and without a dry air purge. All spectra were obtained on a Perkin-Elmer IR spectrophotometer model 621.

DISCUSSION

The γ -OH for the NC samples described in the experimental section were measured in the IR region and are reported in Table 2. Significant interactions within a repeat unit were excluded since the range of the nitrogen content of the samples used corresponds to less than one hydroxyl group per repeat unit. Table 2 includes the γ -OH for each sample measured in atmosphere and under a dry air purge. It can be seen that in all cases the γ -OH for the samples measured in air were shifted to lower frequencies. Further, a broad peak from 3620 - 3680 cm^{-1} (with numerous shoulders) was present in all samples run in air but was absent in all samples run under the dry air purge.

Measurement of γ -OH in air did not give reproducible results as evidenced by the wide range of values reported in Table 2. This was not the case for the samples run under purge conditions.

Therefore, it appears that atmospheric moisture is involved in a NC hydroxyl group interaction. In order to gain further insight into the suspected water-NC interaction, several spectra were run of NC

TABLE 2. γ -OH for Various Nitrogen Content NC Samples

% N in NC	γ -OH ^a (cm ⁻¹)	γ -OH ^b (cm ⁻¹)
12.10	3514	3525
12.20	3502-3536	3544
12.30	3514	3538-3540
12.60	3528-3532	3558
13.16	3528-3550	3560

^aRun in air, expanded spectra (represents five runs).

^bRun under purge condition, expanded spectra (represents five runs).

exposed to deuterium oxide. The only noticeable effect was a significant reduction in intensity of the 3620-3680 cm⁻¹ peak. Unfortunately, the D₂O related shift of the 3620-3680 cm⁻¹ peak could not be observed, either because of low intensity or interference with a NC and D₂O peak. Another complicating factor was the presence of some H₂O-NC interaction as evidenced by the persistence of a peak at 3620-3680 cm⁻¹.

Examination of the data for the purge runs shows a trend toward higher frequencies with increasing nitrogen content. The only exception is the 12.3%N NC sample. This trend corresponds to stronger hydrogen bond formation with increasing number of hydroxyl groups. The four samples which followed this trend had a very similar M_w/M_n (Table 1), while the 12.3%N NC had a significantly lower value, indicating a much narrower molecular weight distribution. It therefore appears that the molecular weight uniformity of NC influences the strength of the hydrogen bonds.

The findings of this study are contrary to the conclusion of Cherubin [2] who believes that the -ONO₂ group participated in hydrogen bonding and that an increase in nitrogen content led to strong hydrogen bonds. The spectra for each sample used in this study were examined in the -ONO₂ asymmetric stretch region (1650 cm⁻¹) [3] and no shift was observed. Thus it appears that the -ONO₂ group does not participate in hydrogen bonding under these conditions. The conclusions of this study are that hydrogen bonding does occur in NC and that this bonding is only due to hydroxyl interactions. Further, the strength of this interaction increases with the number of OH groups present. Finally, the NC-OH groups can enter into weak hydrogen bonding with water.

The implications of these findings on the deterrent concentration profile for small arms propellant will now be briefly discussed.

Interaction between NC hydroxyl groups are in all cases weaker than the deterrent carbonyl-NC hydroxyl interaction. With higher nitrogen contents, the NC-OH interaction becomes even weaker. The weakest interaction obtained in this study was with the 13.1%N NC which is approximately the nitrogen content used for small arms propellants. Therefore, it appears that the interaction between NC hydroxyl groups would not prevent the bonding of deterrent during impregnation.

ACKNOWLEDGMENT

The authors gratefully acknowledge the assistance of Dr. Y. Carignan of the Picatinny Arsenal Feltman Research Laboratories for supplying the nitrocellulose samples used in this study.

REFERENCES

- [1] B. W. Brodman, M. P. Devine, and M. T. Gurbang, J. Appl. Polym. Sci., **18**, 943 (1974).
- [2] G. Cherubin, J. Chim. Phys., **57**, 361 (1960).
- [3] L. J. Bellamy, The Infra-red Spectra of Complex Molecules, Wiley, New York, 1958, p. 301.

Accepted by editor December 17, 1973

Received for publication December 19, 1973

DISTRIBUTION

Commander
U.S. Army Materiel Command
5001 Eisenhower Avenue
Alexandria, VA 22333

1 Attn: AMCDL,
Dr. Dillaway

1 Attn: AMCDL-CS,
Dr. Crenshaw

1 Attn: AMCRD,
Dr. Kaufman

1 Attn: AMCRD-W,
Weapons Division

1 Attn: AMCRD-T,
Dr. El Bisi

1 Attn: AMCRP-D,
Dr. Dellastatious

1 Attn: AMCPM,
Project Manager

1 Attn: AMCRD-MT

1 Attn: AMCRD-TC

1 Attn: AMCRD-TE

1 Attn: AMCRD-TP

1 Attn: AMCDL

Commander
U.S. Army Test & Evaluation Command
Aberdeen Proving Ground, MD 21005

1 Attn: AMSTE-BC

1 Attn: AMSTE-BG

1 Attn: AMSTE-BA

1 Attn: Technical Library

Commander
U.S. AMC Aberdeen Research & Develop-
ment Center
Aberdeen Proving Ground, MD 21005

2 Attn: AMXRD-BD,
Technical Director

1 Attn: AMXRD-BD,
Mr. Comer

1 Attn: AMXRD-BD,
Mr. Grollman

1 Attn: AMXRD-L,
Technical Library

Commander
Picatinny Arsenal
Dover, NJ 07801

1 Attn: Technical Director

1 Attn: Dr. J. Picard

2 Attn: Scientific & Technical
Information Branch

1 Attn: Dr. Y. Carignan

1 Attn: Dr. D. Downs

1 Attn: Dr. T. Gora

1 Attn: Mr. C. Lenchitz

Commander
Harry Diamond Laboratories
Washington, DC 20438

1 Attn: AMXDO-TIB

1 Attn: AMXDO-TD/002

Commander
Technical Library, Bldg. 313
Aberdeen Proving Ground, MD 21005

Commander
U.S. Army Armament Command
Rock Island Arsenal
Rock Island, IL 61201

1 Attn: AMSAR-MT
Mr. G. Cowan

1 Attn: AMSAR-RDG,
Mr. S. Spaulding

1 Attn: AMSAR,
Technical Info Office

1 Attn: AMSAR-RE

1 Attn: AMSAR-RDT

1 Attn: AMSAR-LMC

1 Attn: AMSAR-ASF

1 Attn: AMSAR-RD-G,
Larry Moore

Commander
Air Force Armament Laboratory
Eglin AFB, FL 32542

1 Attn: DLOS

1 Attn: AFATL-DLDG,
Mr. D. Davis

1 Attn: ADTC-ADLEG,
Lt. Cook

1 Attn: ADTC (ADBPS-12)

Commander
Air Materiel Area
Attn: MMECA
Hill AFB, UT 84401

Commander
U.S. Naval Ordnance Laboratory
Attn: Technical Director
White Oak, MD 20910

Commander
U.S. Naval Ordnance Station
Attn: Technical Director
Indian Head, MD 20640

Commander
U.S. Naval Weapons Laboratory
Attn: Technical Director
Dahlgren, VA 22448

Commander
U.S. Naval Air Systems Command
Attn: AIR-604 (3)
Washington, DC 20360

Commander
Watervliet Arsenal
Attn: Technical Director
Watervliet, NY 12189

Commander
Lake City Army Ammunition Plant
Independence, MO 64056

1 Attn: SARLC-IE
Quality Assurance Division

1 Attn: SARLC-ATL
Ammunition Technical
Laboratory

Commander
Radford Army Ammunition Plant
Attn: SMURO-AD, J. Horvarth
Radford, VA 24141

Commander
Twin Cities Army Ammunition Plant
Box 689
Minneapolis, MN 55440

Commander
U.S. Army Aviation Systems Command
Attn: AMSAV-E
12th & Spruce Streets
St. Louis, MO 63166

Commander
U.S. Army Electronics Command
Attn: AMSEL-DL
Ft. Monmouth, NJ 07703

Commander
U.S. Army Tank Automotive Command
Warren, MI 48090

1 Attn: AMSTA-CL

1 Attn: CDC Liaison Officer

Commander
U.S. Army Missile Command
Huntsville, AL 35809

1 Attn: AMSMI-R,
Dr. J. Merrit

1 Attn: AMSMI-R,
R. Mitchell

Commander
U.S. Army Mobility Equipment
Research & Development Center
Ft. Belvoir, VA 22060

1 Attn: Technical Document Center,
Bldg 315

1 Attn: AMSME-RZT

Commander
U.S. Army Materials & Mechanics
Research Center
Watertown, MA 02172

Commander
Badger Army Ammunition Plant
Attn: SMUBO-Q, E. Johnson
Baraboo, WI 53913

Commander
U.S. Army White Sands Missile Range
Attn: Technical Library
NM 88002

Commander
Edgewood Arsenal
Attn: SAREA-RB
Edgewood Arsenal, MD 21010

Commander
U.S. Army Aberdeen Research & Develop-
ment Center - BRL
Aberdeen Proving Ground, MD 21005

1 Attn: BRL,
Dr. R.J. Eichelberger,
Director

1 Attn: Dr. Austin Barrows

1 Attn: Dr. Eli Freedman

1 Attn: Dr. Ingo May

1 Attn: Dr. Michael Schroeder

1 Attn: Denis F. Strenzwilk

1 Attn: Dr. Kevin White

Commander
U.S. Army Tropic Test Center
Attn: STETC-MO-A (Tech Ly)
Drawer 943
Ft. Clayton, Canal Zone 07827

Commander
U.S. Army Research Office (Durham)
Box CM, Duke Station
Durham, NC 27706

Commander
U.S. Naval Ordnance Systems Command
Attn: ORD-9132
Washington, DC 20360

Commander
U.S. Naval Ordnance Laboratory
Attn: Code 730, Library
Silver Spring, MD 20360

Office of Vice Chief of Staff
Department of the Army
Attn: CSAVCS-W-TIS
Washington, DC 20310

Commander
U.S. Naval Weapons Center
China Lake, CA 93555

1 Attn: J. Sherman

1 Attn: Code 4522

1 Attn: Code 4581

Headquarters
Defense Atomic Support Agency
Washington, DC

Headquarters
USAF (AFCSAI)
Washington, DC 20330

Advanced Research Projects Agency(2) 1 Attn: AOA-M/107-B
Department of Defense
Washington, DC 20301 1 Attn: TD/107-1

Director 1 Attn: PD/64-4
U.S. Army Aeronautical Research G. White
Laboratory
Moffett Naval Air Station, CA 94035 1 Attn: MD/220-1
Mr. S. Miller

Director 2 Attn: MDP-R/64-2
U.S. Army Research Office B. Brodman
Attn: Library
3045 Columbia Pike
Arlington, VA 22204 2 Attn: MDP-R/64-2
M.P. Devine

AFSOR (SREP, Dr. B. Wolfson) 1 Attn: MDP-R/64-3
1400 Wilson Blvd. H. A. Kirshner
Arlington, VA 22209

Chemical Propulsion Information 3 Attn: TSP-L/51-2
Agency (3) (1 - Reference copy,
Applied Physics Laboratory 1 - Circulation copy,
The Johns Hopkins University 1 - Record Copy)
Silver Spring, MD 20910

Director
Institute for Defense Analyses
Attn: RESD, Technical Info Office
400 Army-Navy Drive
Arlington, VA 22202

Director
NASA Scientific & Technical
Information Facility
Attn: SAF/DL, Acq Div
P.O. Box 33
College Park, MD 20470

Dr. Henry Prask
National Bureau of Standards
Reactor Radiation Division, Bldg 235
Washington, DC

Defense Documentation Center (12)
Cameron Station
Alexandria, VA 22314

Frankford Arsenal:

Printing & Reproduction Division
FRANKFORD ARSENAL
Date Printed: 1 August 1975


UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER FA-TA-75047	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) HYDROGEN BONDING IN NITROCELLULOSE AND ITS IMPLICATIONS ON DETERRING OF SMALL ARMS PROPELLANT		5. TYPE OF REPORT & PERIOD COVERED Technical Engineering Abstract
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) B.W. Brodman M.P. Devine M.T. Gurbarg		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS FRANKFORD ARSENAL Attn: SARFA-MDP-R Philadelphia, PA 19137		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS: 611102.11.857 DA: 1T161102A32C03
11. CONTROLLING OFFICE NAME AND ADDRESS Picatinny Arsenal		12. REPORT DATE July 1975
		13. NUMBER OF PAGES 9
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE N/A
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Propellant Manufacture Small Arms Deterrents Small Arms Propellant Hydrogen Bonding Propellant Combustion		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The hydrogen bonding characteristics of well-characterized nitrocellulose samples were studied by means of IR spectroscopy. Results obtained for nitrocellulose samples of varying nitrogen content showed that the strength of the hydrogen bond increases with decreasing nitrogen content. In addition, atmospheric moisture was found to hydrogen bond with nitro-cellulose hydroxyl groups. The implications of these findings on the deterring phase of the small arms propellant manufacturing process are discussed.		

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)



UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)