AD-A013 722

HANDBOOK OF THE INFRARED OPTICAL PROPERTIES OF A1203, CARBON, MGO, AND ZRO2. VOLUME I

Milo E. Whitson, Jr.

Aerospace Corporation

Prepared for:

Space and Missile Systems Organizations


4 June 1975

DISTRIBUTED BY:

NTIS

National Technical Information Service
U. S. DEPARTMENT OF COMMERCE

Best
Available
Copy



Approved

S. Siegel, Director
Chemistry and Physics Laboratory

Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

Gerald M. Mavko
2nd Lt, U.S. Air Force
Project Officer

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER SAMSO-TR-75-131, Vol. I	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) HANDBOOK OF THE INFRARED OPTICAL PROPERTIES OF Al_2O_3, CARBON, MgO, AND ZrO_2, VOLUME I		5. TYPE OF REPORT & PERIOD COVERED Interim 6. PERFORMING ORG. REPORT NUMBER TR-0075(5548)-2, Vol. I
7. AUTHOR(s) Milo E. Whitson, Jr.		8. CONTRACT OR GRANT NUMBER(s) F04701-74-C-0075
9. PERFORMING ORGANIZATION NAME AND ADDRESS The Aerospace Corporation El Segundo, Calif. 90245		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Air Force Rocket Propulsion Laboratory Edwards AFB, Calif. 93523		12. REPORT DATE 4 June 1975 13. NUMBER OF PAGES 409
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) Space and Missile Systems Organization Air Force Systems Command Worldway Postal Center, P.O. Box 92960 Los Angeles, Calif. 90009		15. SECURITY CLASS. (of this report) Unclassified 15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

Approved for public release; distribution unlimited.

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Infrared	Emissivity	Carbon
Optical Properties	Reflectivity	Magnesium Oxide
Ceramic Oxides	Transmission	Zirconium Dioxide
Refractive Index	Aluminum Oxide	

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

This handbook presents the compiled results of a comprehensive survey of the open literature relevant to the infrared optical properties of aluminum oxide, carbon, magnesium oxide, and zirconium dioxide. Literature data were critically reviewed and representative data chosen on mathematically constructed for refractive and extinction indices, spectral and total emissivities, reflectance, and transmittance over the 1 to 1000 μm spectral range. All data are presented in both graphic and tabular format, and a cross-referenced bibliography is included.

DD FORM 1473 (FACSIMILE)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

INTROL .CTION

This report is the compiled results of the comprehensive literature search performed for the Particle Optical Properties Measurements (POPM) program. All data relevant to the infrared optical properties of aluminum oxide, carbon, magnesium oxide, and zirconium dioxide found in the search were critically evaluated and summarized. These data were carefully reviewed and the "best" data for each material were selected. On the basis of this review, areas in which further research is required were noted.

The report is divided into three major sections: Section I contains the representative or "best" data for the refractive index, extinction index, spectral and total emissivities, reflectance, and transmittance of each material; Section II lists all relevant literature found in the search; and Section III presents in tabular and graphic formats the digitized data from the literature. Each major section is divided by material into categories that are further divided by optical property.

It would be useful if, for all surveyed data, a meaningful estimate of experimental error could be made. An examination of the literature revealed that error analyses are seldom included in papers, and even descriptions of experimental apparatus and procedures are often lacking. This greatly hampers the proper evaluation of published data, and in many cases has necessitated the use of a comparison technique. The method used to construct each representative curve is described in Section I and in general consists of either a mathematical fit to collections of data points from many sources, or selections of "best" data connected to form broad coverage over a temperature or spectral range. The rationale for including Section III, with its many sets of tabulated data, is to permit the user of this handbook to use data gathered for specific types of materials.

Wherever possible the data in this handbook were taken from published tables. Where these were not available, the curves in the literature were linearly enlarged and digitized using an Oscillogram and Film Semi-Automatic Reader (OSCAR), manufactured by Benson-Lehner Corporation. It is felt that the uncertainties in the tabulated data arise principally from basic experimental errors and journal reproduction uncertainties. Digitization was done over the complex spectra in such a way that a linear interpolation between

points would be valid, so in spectral regions that are highly structured the digitized points are densely packed and in smooth regions the points are widely spaced. The abstract accompanying the tabulated data in Section III identifies those data sets where the digitization was of discrete points in the original papers.

A few remarks concerning the notation used in this handbook need to be made. First, the actual numerical values of the optical parameters are listed in the tables, except for R and T, which in the tables are listed in percent and thus have values between 0 and 100. Second, the extinction index, k, is consistently presented here, even when the original published data were given as the absorption coefficient, α. k and α are related by the expression,

$$k = \frac{\lambda}{4\pi} \alpha .$$

α is conventionally given in units of cm^{-1}, in which case λ must be given in cm ($1\mu = 10^{-4}$ cm).

Symbols Used in this Handbook

λ:	Wavelength (microns)
T:	Temperature (degrees Kelvin, ^{o}K)
n:	Refractive index (dimensionless)
k:	Extinction index (dimensionless)
α:	Absorption coefficient (cm^{-1} or mm^{-1})
$\epsilon(\lambda)$:	Spectral emissivity (tabulated in percent)
$\epsilon(T)$:	Total hemispherical emissivity (tabulated in percent)
R:	Reflectance (tabulated in percent)
TR:	Transmittance (tabulated in percent)

CONTENTS

			PAGE
Section I.		REPRESENTATIVE DATA	I-1
	I-1.	Aluminum Oxide Properties	I-1
	1.1	Refractive Index, n	I-1
	1.2	Extinction Index, k	I-5
	1.3	Spectral Emissivity	I-10
	1.4	Total Normal Emissivity	I-19
	1.5	Reflectance	I-22
	1.6	Transmittance	I-29
	1.7	Experimental and Calculated Absorption Peaks and Oscillator Frequencies	I-37
	1.8	Conclusions: Areas Needing Further Research	I-39
	I-2.	Carbon Properties	I-41
	2.1	Refractive Index, n	I-41
	2.2	Extinction Index, k	I-44
	2.3	Spectral Emissivity	I-47
	2.4	Total Normal Emissivity	I-59
	2.5	Reflectance	I-59
	2.8	Conclusions: Areas Needing Further Research	I-61
	I-3.	Magnesium Oxide Properties	I-61
	3.1	Refractive Index, n	I-61
	3.2	Extinction Index, k	I-66
	3.3	Spectral Emissivity	I-71
	3.4	Total Normal Emissivity	I-75
	3.5	Reflectance	I-78
	3.6	Transmittance	I-87
	3.7	Absorption Peaks	I-95
	3.8	Conclusions: Areas Needing Further Research	I-98

Preceding page blank

CONTENTS...Continued

		PAGE
Section I.		
I-4.	Zirconium Dioxide Properties	I-99
4.1	Refractive Index, n	I-99
4.2	Extinction Index, k	I-100
4.3	Spectral Emissivity	I-103
4.4	Total Normal Emissivity	I-108
4.5	Reflectance	I-111
4.6	Transmittance	I-115
4.7	Absorption Peaks	I-120
4.8	Conclusions: Areas Needing Further Research	I-122
Section II.	BIBLIOGRAPHY	II-1
II-1.	Aluminum Oxide References, by Property	II-1
1.1	Refractive Index, n	II-1
1.2	Extinction Index, k	II-2
1.3	Spectral Emissivity	II-4
1.4	Total Normal Emissivity	II-6
1.5	Reflectance	II-7
1.6	Transmittance	II-9
1.7	Miscellaneous	II-11
II-2	Carbon References, by Property	II-13
2.1	Refractive Index, n	II-13
2.2	Extinction Index, k	II-14
2.3	Spectral Emissivity	II-15
2.4	Total Normal Emissivity	II-17
2.5	Reflectance	II-18
2.6	Transmittance	II-19
2.7	Miscellaneous	II-20

CONTENTS... Continued PAGE

Section II.

II-3. Magnesium Oxide References, by Property II-23
3.1 Refractive Index, n II-23
3.2 Extinction Index, k II-24
3.3 Spectral Emissivity II-26
3.4 Total Normal Emissivity II-27
3.5 Reflectance II-28
3.6 Transmittance II-30
3.7 Miscellaneous II-32

II-4. Zirconium Dioxide References, by Property II-35
4.2 Extinction Index, k II-35
4.3 Spectral Emittance II-36
4.4 Total Normal Emissivity II-37
4.5 Reflectance II-38
4.6 Transmittance II-39
4.7 Miscellaneous II-40

II-5. Author Index II-41

Section III. TABULATED DATA III-1
III-1. Aluminum Oxide Data III-1
1.1 Refractive Index, n III-1
1.2 Extinction Index, k III-29
1.3 Spectral Emissivity III-73
1.4 Total Normal Emissivity III-147
1.5 Reflectance III-155
1.6 Transmittance III-229

III-2. Carbon Data III-291
2.1 Refractive Index, n III-291
2.2 Extinction Index, k III-305
2.3 Spectral Emissivity III-321
2.4 Total Normal Emissivity III-393
2.5 Reflectance III-441

CONTENTS... Continued

	PAGE
Section III.	
III-3. Magnesium Oxide Data	III-449
3.1 Refractive Index, n	III-449
3.2 Extinction Index, k	III-479
3.3 Spectral Emissivity	III-533
3.4 Total Normal Emissivity	III-543
3.5 Reflectance	III-549
3.6 Transmittance	III-641
III-4. Zirconium Dioxide Data	III-721
4.1 Refractive Index, n	III-721
4.2 Extinction Index, k	III-723
4.3 Spectral Emissivity	III-727
4.4 Total Normal Emissivity	III-739
4.5 Reflectance	III-749
4.6 Transmittance	III-765

*NOTE ADDED IN PROOF CONCERNING A NEW REFERENCE

D. P. DeWitt, Handbook of the Optical, Thermal and Mechanical Properties of Six Polycrystalline Dielectric Materials, Purdue Univ. Thermophys. Prop. Res. Ctr., TPRC - Report 19, Dec., 1972.

In this handbook, the refractive and extinction indices, transmittance, emittance, reflectance, absorptance, and scattering coefficient for aluminum oxide, calcium fluoride, magnesium fluoride, magnesium oxide, silicon dioxide, and titanium dioxide are presented. These data have been gathered from open literature sources, many of which are presented and evaluated in the present Aerospace Corp./AFRPL handbook. This reference provides an excellent general survey of aluminum and magnesium oxide properties over, in the main, the short to medium infrared spectral regions, but no attempt has been made to produce digitized data sets for the source data, or to provide sets of representative optical properties, as has been done in the present report.

I-1 ALUMINUM OXIDE PROPERTIES


I-1.1 Refractive Index, n — Aluminum Oxide


The refractive index of sapphire has been extensively studied at T = 300°K, but data for other temperatures are sparse. Piriou (Ref. 1N-9) has studied sapphire at 1773°K from 9μ to 33μ, and Loewenstein (Ref. 1N-3) at T = 1.5°K. Their results indicate that the refractive index changes very little with temperature except near resonant lattice frequencies. A representative curve for sapphire at T = 300°K has been constructed using the data from references 1N-3, 1N-5, 1N-9, and 1N-11. No bulk alumina refractive index data were located in the literature, and refractive index data for powders were found only in Streed (Ref. 1N-12) and are of uncertain value, since the sapphire refractive index reported in this source was greatly at variance with all other measurements. No experimental measurements of n from 6μ to 9μ, aside from Reference 1N-12, have been located, and the representative curve has been constructed in this region by linear interpolation. Where the ordinary and extraordinary indices have been measured (~30μ and longer), the ordinary value of n has been used. All measured values of n_o and n_e are tabulated in Section III-1.1.


The representative curve is shown in Figure I-1.1 and is tabulated in Table I-1.1. Section I-1.7 gives in tabular form the lattice frequencies of aluminum oxide which relate to the structure seen in the optical properties curves.

Table I-1.1 Aluminum Oxide Refractive Index - Representative Data

λ	n	λ	n	λ	n	λ	n
1.u14	1.755E+00	1.129	1.753E+00	1.367	1.749E+00	1.395	1.749E+00
1.5c9	1.747E+00	1.693	1.744E+00	1.709	1.743E+00	1.81[illegible]	1.741E+00
1.970	1.738E+00	2.153	1.734E+00	2.249	1.732E+00	2.325	1.731E+00
2.437	1.728E+00	3.244	1.714E+00	3.267	1.704E+00	3.303	1.702E+00
3.330	1.701E+00	3.422	1.698E+00	3.507	1.695E+00	3.707	1.688E+00
4.259	1.664E+00	4.272	1.627E+00	4.954	1.627E+00	5.600	1.542E+00
6.100	1.477E+00	6.600	1.411E+00	7.100	1.346E+00	7.600	1.288E+00
8.100	1.214E+00	8.600	1.148E+00	9.111	1.081E+00	9.317	1.054E+00
9.[illegible]39	1.[illegible]12E+00	9.906	9.[illegible]66E-01	10.200	7.857E-01	10.552	5.293E-01
10.958	1.874E-01	11.223	1.640E-02	11.863	1.320E-02	12.964	1.320E-02
14.272	1.320E-02	15.395	6.600E-03	15.569	4.504E-01	15.719	1.631E+00
15.793	2.[illegible]53E-01	15.858	1.111E+01	16.007	6.476E-01	16.138	4.372E-01
16.399	3.[illegible]24E-01	16.678	4.438E-01	16.940	6.377E-01	17.138	1.275E+00
17.[illegible]211	1.[illegible]86E+00	17.274	2.646E+00	17.359	4.020E+00	17.425	5.218E+00
17.[illegible]488	8.[illegible]72E+00	17.621	1.195E+01	17.666	1.119E+01	17.702	1.068E+01
17.789	9.[illegible]72E+00	17.840	9.263E+00	17.927	8.341E+00	18.012	7.862E+00
18.134	7.[illegible]22E+00	18.221	6.510E+00	18.406	5.605E+00	18.581	5.065E+00
18.916	4.[illegible]39E+00	19.174	3.988E+00	19.554	3.399E+00	19.782	3.044E+00
20.[illegible]177	2.[illegible]96E+00	20.422	1.828E+00	20.717	8.777E-01	20.833	4.668E-01
21.[illegible]246	1.[illegible]11E+00	21.437	6.256E-02	21.647	1.183E-01	22.252	7.232E-01
22.[illegible]772	1.[illegible]17E+00	22.554	2.262E+00	22.647	3.813E+00	22.727	5.416E+00
22.[illegible]731	6.[illegible]87E+00	23.017	1.421E+01	23.049	1.280E+01	23.069	1.187E+01
23.[illegible]103	1.[illegible]47E+01	23.216	1.042E+01	23.314	9.[illegible]98E+00	23.466	8.319E+00
23.[illegible]563	8.[illegible]37E+00	23.779	7.545E+00	23.937	6.940E+00	24.227	6.377E+00
24.[illegible]617	5.[illegible]45E+00	25.193	4.681E+00	25.589	4.086E+00	25.969	3.376E+00
26.[illegible]182	4.[illegible]11E+00	26.276	5.007E+00	26.323	5.628E+00	26.780	5.274E+00
27.[illegible]227	4.[illegible]26E+00	27.800	4.530E+00	28.901	4.158E+00	30.204	3.905E+00
31.[illegible]477	3.[illegible]84E+00	33.190	3.761E+00	33.330	3.630E+00	33.333	3.636E+00
34.[illegible]439	3.[illegible]57E+00	34.483	3.557E+00	35.[illegible]19	3.522E+00	35.714	3.522E+00
37.[illegible]637	3.[illegible]45E+00	37.040	3.451E+00	38.460	3.428E+00	39.462	3.428E+00
40.[illegible]000	3.[illegible]38E+00	41.667	3.350E+00	41.670	3.350E+00	43.478	3.320E+00
43.[illegible]480	3.[illegible]32E+00	45.455	3.267E+00	45.460	3.287E+00	47.619	3.268E+00
47.[illegible]622	3.[illegible]25E+00	50.[illegible]00	3.2[illegible]E+00	52.630	3.220E+00	52.632	3.226E+00
55.[illegible]556	3.[illegible]19E+00	55.560	3.198E+00	56.689	3.211E+00	58.377	3.202E+00
58.[illegible]824	3.[illegible]18E+00	60.132	3.192E+00	61.996	3.185E+00	62.500	3.167E+00
64.[illegible]022	3.[illegible]17E+00	66.138	3.170E+00	66.667	3.147E+00	68.446	3.162E+00
70.[illegible]872	3.[illegible]15E+00	71.429	3.132E+00	73.[illegible]75	3.148E+00	76.[illegible]336	3.142E+00
76.[illegible]923	3.[illegible]11E+00	79.365	3.[illegible]36E+00	82.713	3.130E+00	83.333	3.106E+00
86.[illegible]2d1	3.[illegible]25E+00	90.171	3.120E+00	90.909	3.096E+00	94.518	3.115E+00
100.[illegible]000	3.[illegible]87E+00	104.380	3.[illegible]66E+00	110.250	3.102E+00	111.110	3.079E+00
116.690	3.098E+00	124.070	3.094E+00	125.000	3.073E+00	132.280	3.091E+00
141.650	3.[illegible]87E+00	142.860	3.068E+00	152.670	3.084E+00	165.290	3.082E+00
166.670	3.062E+00	1[illegible].510	3.079E+00	198.410	3.077E+00	200.000	3.058E+00
220.280	3.075E+00	248.140	3.074E+00	250.000	3.055E+00	283.290	3.072E+00
331.130	3.[illegible]E+00	33[illegible].330	3.052E+00	396.830	3.070E+00		


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1-1.1
ALUMINUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1-1.1
ALUMINUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1-1.1
ALUMINUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
15.0
13.5
12.0
10.5
9.0
7.5
6.0
4.5
3.0
1.5
0.0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.

I-1.2 Extinction Index, k - Aluminum Oxide

Figure I-1.2 shows the representative curve for the extinction index of high-density alumina and sapphire at T = 300°K, constructed from the data of Grimm (Ref. 1K-1), Piriou (Ref. 1K-12, 1K-13) and Loewenstein (Ref. 1K-5) for the spectral range 2μ to 340μ. Small changes in k do occur and these are presented in Section III - 1.2 showing the temperature effect to 2300°K. All values of k are for the ordinary ray; extraordinary ray data is located in Section III-1.2.

Only one reference, 1K-4, was found for the thin film extinction index, and one, 1K-16, for powdered alumina, and these are summarized in Section III-1.2. Reference 1K-16 is of uncertain value for powdered alumina, since the values of k reported for sapphire in this reference deviate considerably from all other published values.


Section I-1.7 contains absorption peak information showing where fine structure in the extinction index is to be expected. Section I-1.6 gives transmittance data that also shows spectral regions having fine structure, and also gives powder transmittance data.


Table I-1.2 The Extinction Index of High Density Alumina and Sapphire at 300°K


λ	k	λ	k	λ	k
2.452	6.530E-07	2.244	6.661E-07	2.381	6.783E-07
2.5+0	6.994E-07	2.694	7.031E-07	2.885	7.268E-07
3.092	7.524E-07	3.280	7.810E-07	3.444	8.095E-07
3.554	8.364E-07	3.658	8.727E-07	3.830	9.471E-07
3.9+8	1.014E-06	4.089	1.110E-06	4.230	1.216E-06
4.350	1.337E-06	4.491	1.502E-06	4.[illegible]13	1.682E-06
4.741	1.895E-06	4.853	2.148E-06	4.929	2.336E-06
5.015	2.559E-06	5.084	2.795E-06	5.133	3.102E-06
5.171	3.709E-06	5.212	4.563E-06	5.256	5.859E-06
5.293	7.860E-06	5.346	1.084E-05	5.384	1.374E-05
5.434	1.813E-05	5.478	2.338E-05	6.728	1.717E-03
6.798	1.890E-03	6.855	2.028E-03	6.885	2.236E-03
6.941	2.781E-03	6.979	3.068E-03	7.024	3.409E-03
7.050	3.481E-03	7.088	3.332E-03	7.127	3.538E-03
7.244	4.247E-03	7.337	5.119E-03	7.438	6.039E-03
7.526	7.283E-03	7.559	7.607E-03	7.595	7.787E-03
7.633	7.376E-03	7.658	6.979E-03	7.685	6.856E-03
7.729	7.714E-03	7.772	8.396E-03	7.834	8.871E-03
7.859	8.614E-03	7.937	8.523E-03	8.009	8.660E-03
8.050	9.115E-03	8.085	8.816E-03	8.125	8.273E-03
8.204	7.884E-03	8.232	8.003E-03	8.274	8.225E-03
8.347	9.214E-03	8.406	9.801E-03	8.452	1.015E-02
8.496	1.090E-02	8.522	1.152E-02	8.592	1.254E-02
8.667	1.324E-02	8.761	1.304E-02	8.743	1.372E-02
8.825	1.498E-02	8.920	1.721E-02	8.988	1.841E-02
9.096	1.961E-02	9.128	1.930E-02	9.212	1.892E-02
9.269	1.873E-02	9.339	1.967E-02	9.399	2.092E-02
9.447	2.154E-02	9.598	2.189E-02	9.681	2.276E-02
9.946	2.648E-02	10.052	2.827E-02	10.140	2.856E-02
10.272	3.071E-02	10.438	3.747E-02	10.603	4.808E-02
10.758	6.327E-02	10.922	2.170E-01	11.186	4.701E-01
11.391	7.265E-01	11.869	9.665E-01	12.179	1.170E+00
12.316	1.467E+00	12.879	1.591E+00	13.292	1.798E+00
13.639	2.015E+00	14.008	2.235E+00	14.352	2.482E+00
14.638	2.712E+00	14.961	2.968E+00	15.168	3.184E+00
15.339	3.402E+00	15.451	3.734E+00	15.551	4.[illegible]E+00
15.612	4.408E+00	15.712	4.655E+00	15.772	4.247E+00
15.851	3.208E+00	15.908	2.919E+00	16.062	3.281E+00
16.413	4.406E+00	16.730	5.360E+00	16.845	5.869E+00
17.049	7.366E+00	17.274	9.451E+00	17.357	1.073E+01
17.4+0	1.251E+01	17.549	9.802E+00	17.652	5.588E+00
17.722	3.439E+00	17.806	2.002E+00	17.969	1.345E+00

Table I-1.2 (Continued)

λ	k	λ	k	λ	k
18.182	8.810E-01	18.474	2.358E-01	18.852	3.057E-01
19.403	1.092E-01	19.902	4.274E-02	20.302	1.512E-01
20.610	3.517E-01	20.860	8.876E-01	21.092	1.492E+00
21.335	2.466E+00	21.527	3.189E+00	21.736	3.810E+00
21.832	4.372E+00	22.060	5.638E+00	22.296	7.574E+00
22.330	9.633E+00	22.651	1.087E+01	22.832	1.437E+01
23.023	3.083E+00	23.143	1.742E+00	23.289	1.114E+00
23.578	6.443E-01	23.979	2.498E-01	24.431	1.052E-01
24.724	9.862E-02	25.185	2.959E-01	25.593	5.062E-01
25.818	8.514E-01	26.011	1.345E+00	26.150	2.590E+00
26.385	1.423E+00	26.716	4.274E-01	27.017	2.465E-01
28.179	3.287E-03	29.726	1.085E-01	33.213	1.578E-01
66.667	1.008E-02	71.429	9.095E-03	76.923	8.570E-03
83.333	7.958E-03	90.909	7.379E-03	100.000	6.923E-03
111.111	6.455E-03	125.000	5.769E-03	142.857	5.229E-03
166.657	4.377E-03	200.000	3.501E-03	250.000	2.387E-03
333.333	2.653E-03				


EXTINCTION INDEX OF ALUMINUM OXIDE
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1-1.2
SAPPHIRE AND HIGH DENSITY ALUMINA
T=300K
REPRESENTATIVE DATA


EXTINCTION INDEX OF ALUMINUM OXIDE
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
FIGURE 1-1.2
SAPPHIRE AND HIGH DENSITY ALUMINA
T=300K
REPRESENTATIVE DATA


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE I-1.2
SAPPHIRE AND HIGH DENSITY ALUMINA
T=300K
REPRESENTATIVE DATA
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.

I-1.3 Spectral Emissivity, $\epsilon(\lambda)$ — Aluminum Oxide


Representative curves for the spectral emissivity of bulk alumina, bulk sapphire, and powdered sapphire are presented in this section. Supplementary to this in Section III-1.3 are data for liquid alumina droplet emissivity and surface roughness effects on alumina emissivity. Additional data on emissivity are contained in Section I-1.4, where the reflectance data are summarized. Since Kirchhoff's law $\epsilon = 1-R$ applies only to the proper angular complements, a conversion of all reflectance to emissivity has not been made.

I-1.3.1 Bulk Al_2O_3

The bulk forms of Al_2O_3, sapphire (α-Al_2O_3) and alumina have different emissive properties, as shown in Figures I-1.3a, b, and c. All bulk Al_2O_3 shows a distinct emissivity maximum from approximately 4 μ to 11 μ, the onset of this peak shifting to shorter wavelengths as the sample temperature is increased. Representative data for sapphire are from Stierwalt (Ref. 1SE-16) over a temperature range 4.2°K to 200°K and a spectral range 1 μ to 125 μ; the data of Blau (Ref. 1SE-5) for 99 percent pure alumina over a temperature range of 800°K to 1300°K is taken to be representative of the pressed and sintered forms of Al_2O_3. A precision of 4 ± percent as claimed by Blau (Ref. 1SE-5) is taken to be representative of all data shown in Figures I-1.3.1 and I-1.3.2, although no explicit statement of precision is given by the other references shown. The effect of differences in sample surface preparation on Al_2O_3 emissivity has been studied by Richmond (Ref. 1SE-13) and has been found to be negligible below 14 μ. The relatively minor effect of temperature can be seen in the data of Section III-1.3. Data from other researchers on many bulk forms of Al_2O_3 are included in Section III-1.3 in graphical and tabular form, where are also more detailed descriptions of the representative data.

Table I-1.3.1a Spectral Emissivity of Aluminum Oxide, T = 200°K — Representative Data

λ	ε	λ	ε	λ	ε
4.025	7.775E-02	4.202	7.350E-02	4.377	7.125E-02
4.[illegible]	8.150E-02	4.778	9.475E-02	4.973	1.115E-01
5.163	1.345E-01	5.342	1.685E-01	5.523	1.318E-01
5.7+4	2.425E-01	5.914	2.959E-01	6.068	3.578E-01
6.156	4.385E-01	6.311	5.312E-01	6.444	6.175E-01
6.581	6.938E-01	6.732	7.710E-01	6.896	8.448E-01
7.010	8.770E-01	7.145	9.066E-01	7.300	9.271E-01
7.4+8	9.414E-01	7.655	9.529E-01	8.025	9.621E-01
8.336	9.685E-01	8.780	9.719E-01	9.254	9.744E-01
9.611	9.711E-01	9.889	9.662E-01	10.135	9.545E-01
10.36+	9.269E-01	10.556	8.788E-01	10.723	8.240E-01
10.830	7.761E-01	11.015	6.758E-01	11.142	5.947E-01
11.254	5.023E-01	11.331	4.060E-01	11.345	3.478E-01
11.+15	3.312E-01	11.523	3.161E-01	11.674	2.844E-01
11.747	2.547E-01	11.868	2.396E-01	12.095	2.243E-01
12.342	2.166E-01	12.533	2.077E-01	12.709	1.995E-01
12.877	1.825E-01	13.036	1.710E-01	13.297	1.573E-01
13.520	1.532E-01	13.710	1.410E-01	13.843	1.268E-01
13.977	1.168E-01	14.199	1.125E-01	14.530	1.135E-01
14.896	1.138E-01	15.036	1.280E-01	15.258	1.575E-01
15.3+3	1.990E-01	15.614	2.202E-01	15.867	2.795E-01
16.007	2.322E-01	16.181	1.920E-01	16.386	2.872E-01
16.545	2.430E-01	16.728	2.683E-01	16.866	3.066E-01
17.093	3.294E-01	17.350	3.575E-01	17.611	4.[illegible]E-01
17.897	4.650E-01	18.089	5.443E-01	18.144	5.650E-01
18.3+0	6.208E-01	18.951	6.835E-01	19.565	7.565E-01
19.752	6.408E-01	19.970	5.433E-01	20.197	5.594E-01
20.358	6.611E-01	20.437	6.415E-01	20.616	6.500E-01
20.753	5.504E-01	20.790	3.780E-01	20.803	2.033E-01
20.9+7	1.473E-01	21.048	8.600E-02	21.174	6.809E-02
21.3+0	5.925E-02	21.840	6.325E-02	22.270	9.425E-02
22.021	1.250E-01	22.997	1.580E-01	23.416	1.910E-01
23.7+9	2.202E-01	23.827	2.440E-01	24.007	2.949E-01
24.217	3.389E-01	24.473	3.591E-01	24.701	3.555E-01
24.385	3.627E-01	24.955	3.923E-01	25.396	4.924E-01
25.6+3	5.267E-01	26.276	5.738E-01	27.316	6.135E-01
28.4+7	6.388E-01	30.426	6.630E-01	32.668	6.767E-01
34.959	6.812E-01	37.484	6.835E-01	40.496	6.835E-01
44.669	6.835E-01				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE I-1.3.1A
SAPPHIRE
T=200K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.




SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE I-1.3.1A
SAPPHIRE
T=200K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
5.
10.
15.
20.
25
30.
35.
40.
45.
50.


Table I-1.3.1b Spectral Emissivity of Alumina, T=873°K — Representative Data

λ	ε	λ	ε	λ	ε	λ	ε
1.974	.724	2.967	.453	3.967	.520	4.970	.735
5.375	.923	6.357	.972	7.975	.964	8.942	.983
9.961	.954	10.971	.924	11.984	.717	12.985	.673
14.011	.639						

Table I-1.3.1c Spectral Emissivity of Alumina, T = 1373°K — Representative Data

λ	ε	λ	ε	λ	ε	λ	ε
1.965	.565	2.937	.445	3.926	.482	4.941	.726
5.342	.845	6.332	.965	7.969	.925	8.931	.937
9.943	.944	10.935	.842	11.972	.650	12.974	.630
13.953	.651						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1-1.3.1C
ALUMINA
T=1300K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1-1.3.1B
ALUMINA
T=873K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)

I-1.3.2 Powdered Aluminum Oxide

The representative spectral emissivity of powdered Al_2O_3 over a particle size range of 0.06 · 30 μ and a temperature of 300°K is shown in Figure I-1.3.2. The values of $\epsilon(\lambda)$ reported by Aronson (Ref. 1SE-2) and Streed (Ref. 1SE-17) are much higher for $\lambda > 12\mu$ than the bulk materials, but do show the decrease at 11μ from a plateau starting at approximately 4μ. The sharp peak occuring at 3μ is due to water contamination of the sample and is not present in the high temperature data. The complete set of particle emissivity data is contained in Section III-1.3. The representative curve is for 9 WCA alumina particles at 300°K as measured by Aronson (Ref. 1SE-2).

Table I-1.3.2 Representative Data, Alumina Particles, T = 300°K

λ	ε	λ	ε	λ	ε
7.330	7.441E-01	7.371	7.676E-01	7.398	7.451E-01
7.433	7.544E-01	7.482	7.587E-01	7.549	7.856E-01
7.533	7.817E-01	7.672	7.841E-01	7.705	7.913E-01
7.727	7.861E-01	7.756	7.876E-01	7.778	7.911E-01
7.835	7.859E-01	7.831	7.896E-01	7.856	7.983E-01
7.831	8.106E-01	7.914	8.081E-01	7.981	8.042E-01
8.014	8.153E-01	8.042	8.239E-01	8.068	8.326E-01
8.097	8.329E-01	8.118	8.291E-01	8.172	8.291E-01
8.201	8.399E-01	8.233	8.425E-01	8.261	8.387E-01
8.289	8.437E-01	8.315	8.640E-01	8.341	8.793E-01
8.369	8.839E-01	8.394	8.887E-01	8.437	8.869E-01
8.488	8.855E-01	8.518	8.941E-01	8.577	8.956E-01
8.634	8.968E-01	8.634	9.081E-01	8.672	9.192E-01
8.746	9.345E-01	8.775	9.357E-01	8.834	9.503E-01
8.933	9.641E-01	8.979	9.620E-01	9.043	9.715E-01
9.117	9.684E-01	9.261	9.796E-01	9.265	9.912E-01
9.401	9.904E-01	9.638	9.960E-01	9.319	9.959E-01
10.050	9.921E-01	10.263	9.867E-01	10.354	9.604E-01
10.434	9.492E-01	10.502	9.368E-01	10.590	9.321E-01
10.305	9.123E-01	10.709	9.115E-01	10.728	9.007E-01
10.787	8.975E-01	10.819	8.891E-01	10.877	8.891E-01
10.926	8.745E-01	10.965	8.696E-01	11.039	8.610E-01
11.114	8.541E-01	11.179	8.550E-01	11.226	8.576E-01
11.276	8.541E-01	11.359	8.487E-01	11.456	8.418E-01
11.479	8.339E-01	11.546	8.353E-01	11.625	8.353E-01
11.683	8.462E-01	11.737	8.406E-01	11.777	8.503E-01
11.882	8.573E-01	11.950	8.625E-01	12.012	8.739E-01
12.123	8.745E-01	12.169	8.822E-01	12.235	8.855E-01
12.338	8.904E-01	12.433	8.908E-01	12.497	8.847E-01
12.555	8.892E-01	12.664	8.879E-01	12.710	8.852E-01
12.735	8.898E-01	12.874	8.820E-01	12.979	8.817E-01
13.031	8.814E-01	13.185	8.849E-01	13.302	8.839E-01
13.323	8.729E-01	13.657	8.758E-01	13.725	8.771E-01
13.780	8.724E-01	13.904	8.647E-01	14.084	8.652E-01
14.199	8.674E-01	14.374	8.531E-01	14.501	8.575E-01
14.590	8.590E-01	14.683	8.634E-01	14.842	8.615E-01
14.994	8.624E-01	15.122	8.884E-01	15.235	8.971E-01
15.373	8.795E-01	15.452	8.531E-01	15.558	8.336E-01
15.653	8.334E-01	15.737	8.415E-01	15.774	8.580E-01
15.892	8.716E-01	15.964	8.822E-01	16.070	8.783E-01
16.135	8.639E-01	16.394	8.497E-01	16.584	8.059E-01
16.669	7.681E-01	16.861	7.374E-01	16.950	7.336E-01

Table I-1.3.2 Representative Data, Alumina Particles, T = 300°K (continued)

λ	ε	λ	ε	λ	ε
17.310	7.512E-01	17.618	7.597E-01	17.220	8.359E-01
17.329	8.[illegible]	17.432	8.218E-01	17.584	8.202E-01
17.[illegible]	8.323[illegible]	17.733	8.425E-01	17.852	8.524E-01
17.[illegible]	8.[illegible]	18.[illegible]	8.783E-01	18.123	8.899E-01
18.232	8.[illegible]	18.[illegible]	8.936E-01	18.599	8.886E-01
18.[illegible]	8.[illegible]	18.[illegible]	8.[illegible]	19.188	8.630E-01
19.355	8.[illegible]	19.[illegible]	8.713E-01	19.836	8.681E-01
[illegible].118	8.[illegible]	20.[illegible]	8.382E-01	20.474	8.365E-01
[illegible].241	8.[illegible]	20.492	8.751E-01	20.709	8.896E-01
1.[illegible]16	9.[illegible]	21.255	8.955E-01	21.443	8.758E-01
1.[illegible]	8.[illegible]	22.260	8.247E-01	22.525	8.076E-01
2.[illegible]	7.[illegible]	23.[illegible]	8.308E-01	23.272	8.163E-01
3.[illegible]	8.[illegible]	23.759	8.556E-01	24.018	8.756E-01
4.[illegible]	8.[illegible]	24.756	8.[illegible]81E-01	24.963	8.469E-01
5.270	8.[illegible]	25.651	8.[illegible]22E-01		




FIGURE I-1.3.2
POWDERED ALUMINA
T=300K
REPRESENTATIVE DATA




FIGURE I-1.3.2
POWDERED ALUMINA
T=300K
REPRESENTATIVE DATA

I-1.4 Total Normal Emissivity, $\epsilon(T)$ — Aluminum Oxide

The total emissivities of bulk alumina and sapphire have been measured in the literature for temperatures ranging from 63°K to 1800°K. The representative curve for alumina data, constructed by fitting a third order polynomial to data from References 1TE-4 and 1TE-5 is shown in Table I-1.4 and Figure I-1.4. $\epsilon(T) = 0.77$ at low temperatures, then goes through an apparent minimum of about 0.37 at 1660°K. No experimental error is quoted for these data.

$\epsilon(T)$ for sapphire is given in Section III-1.4 in tabulated form in Ref. 1TE-2 and 1TE-6, and appears to be less than the alumina emissivity over the range of temperatues covered, 200°K to 1273°K.

One reference (1TE-3) gives $\epsilon(T)$ for rocket exhaust particles from T = 1389°K to 2222°K. This is presented in Section III-1.4.

Table I-1.4 Bulk Alumina Total Emittance — Representative Data

T(°K)	ε(T)	T(°K)	ε(T)	T(°K)	ε(T)	T(°K)	ε(T)
100	0.0	400	0.0	700	0.0	1000	0.0




Figure I-1.4 The Total Normal Emissivity of Aluminum Oxide as a Function of Temperature

I-1.5. Reflectivity - Aluminum Oxide

Reflectivity data for sapphire, bulk alumina, alumina powders and films at 300°K are tabulated in Section III. Representative curves for sapphire, bulk alumina, and alumina powder are presented here. Since the reflectivity of a sample is highly dependent upon surface conditions, the representative curve should be interpreted only in a relative sense. No attempt has been made to normalize the curves used as representative reflectivities.

I-1.5.1. Sapphire

The 300°K data of Aronson (Ref. 1R-3) and Barker Ref. 1R-4) have been taken as representative and plotted together in Figure I-1.5.1. Reflection maxima are seen to occur at approximately 14.5μ, 17.5μ, 21.7μ, 23.0μ, 27 to 29μ, and 52μ. Lattice parameter information deduced from these and other data are presented in Section I-1.7.

I-1.5.2 Bulk Alumina


The reflectance of bulk alumina at short wavelengths has been found to be much higher than sapphire reflectance. The data for $\lambda > 9\mu$ are similar to sapphire. The data of Clark (Ref. IR-6) and Harris (Ref. IR-18) are plotted as representative data in Figures I-1.5.2 and tabulated in Table I-1.5.2.


I-1.5.3 Alumina Powder

The reflectivity for 3.5μ mean diameter alumina platelets at 300°K from 7μ to 30μ is shown in Figure I-1.5.3. These data are from Aronson (Ref. 1R-1) and data for particle sizes up to 100μ are plotted and tabulated in Section III-1.5. The small peak between 10μ and 12μ has been observed for spinel alumina by Levy (Ref. 1R-10). The gross features of the alumina powder reflectance match those of the sapphire.

Table I-1.5.1 Sapphire - Representative Data

λ	R	λ	R	λ	R
.890	7.418E+00	1.905	7.319E+00	2.957	7.191E+00
3.944	6.879E+00	5.006	5.901E+00	5.996	4.695E+00
7.054	3.516E+00	8.082	2.170E+00	9.037	9.362E-01
9.627	2.837E-01	10.044	4.397E-01	10.476	1.433E+00
10.894	4.936E+00	11.104	1.988E+01	11.224	3.511E+01
11.367	5.019E+01	11.577	6.996E+01	11.895	7.977E+01
12.074	8.134E+01	12.322	7.960E+01	12.550	8.247E+01
12.716	8.372E+01	13.119	8.468E+01	13.411	8.682E+01
13.907	8.811E+01	14.442	8.865E+01	14.942	8.675E+01
15.327	8.566E+01	15.883	8.820E+01	16.248	8.466E+01
16.501	7.958E+01	16.685	7.431E+01	17.015	7.255E+01
17.268	6.734E+01	17.388	5.987E+01	17.603	4.991E+01
18.015	3.491E+01	18.338	2.492E+01	18.776	1.489E+01
19.288	3.745E+00	19.411	3.064E+00	19.484	5.078E+00
19.607	4.235E+01	19.735	7.455E+01	19.854	8.222E+01
20.087	8.673E+01	20.466	8.898E+01	20.722	8.913E+01
20.917	9.177E+01	21.211	9.244E+01	21.552	9.327E+01
21.927	9.270E+01	22.556	8.989E+01	24.327	8.416E+01
25.117	7.952E+01	25.533	7.459E+01	25.964	6.724E+01
26.623	5.973E+01	27.279	5.450E+01	27.999	5.082E+01
29.041	4.655E+01	29.977	4.367E+01	30.983	4.198E+01
31.981	4.074E+01	32.978	3.949E+01	34.014	3.901E+01
35.015	3.840E+01	52.480	2.363E+01	57.878	2.207E+01
62.682	2.061E+01	65.676	2.034E+01	68.473	2.172E+01
70.142	2.318E+01	74.354	2.657E+01	77.764	2.927E+01
79.815	3.067E+01	87.183	2.974E+01	91.298	3.071E+01
95.528	3.262E+01	101.010	3.441E+01	105.263	3.352E+01
109.588	3.173E+01	116.505	3.037E+01	132.450	3.083E+01
143.366	3.111E+01	148.331	3.032E+01	158.103	2.848E+01
170.213	2.646E+01	172.414	2.542E+01	179.910	2.447E+01
195.752	2.307E+01	243.408	2.110E+01	346.821	1.967E+01
621.762	1.900E+01	621.762	1.900E+01		


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE I-1.5.1
SAPPHIRE
T=300 K
REPRESENTATIVE DATA


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE I-1.5.1
SAPPHIRE
T=300 K
REPRESENTATIVE DATA




FIGURE 1-1.5.1
SAPPHIRE
T=300 K
REPRESENTATIVE DATA





FIGURE 1-1.5.2
BULK ALUMINA
T=300 K
REPRESENTATIVE DATA


Table I-1.5.2 Bulk Alumina Reflectivity - Representative Data

λ	R	λ	R	λ	R	λ	R
.259	1.121E+01	.271	1.682E+01	.281	2.395E+01	.292	3.144E+01
.299	3.431E+01	.304	4.063E+01	.311	4.566E+01	.313	4.901E+01
.333	5.217E+01	.340	5.411E+01	.350	5.929E+01	.356	6.323E+01
.384	6.954E+01	.375	7.325E+01	.390	7.778E+01	.409	8.094E+01
.429	8.[illegible]8E+01	.439	8.365E+01	.447	8.266E+01	.455	8.183E+01
.468	8.[illegible]7E+01	.483	8.550E+01	.495	8.682E+01	.510	8.793E+01
.528	8.[illegible]5E+01	.556	8.682E+01	.564	8.637E+01	.612	8.595E+01
.632	8.[illegible]3E+01	.651	8.640E+01	.665	8.736E+01	.673	8.982E+01
.683	9.297E+01	.691	9.691E+01	.699	9.399E+01	.703	9.141E+01
.744	9.133E+01	.746	9.246E+01	.768	9.307E+01	.786	9.319E+01
.813	9.[illegible]4E+01	.844	9.299E+01	.879	9.260E+01	.917	9.231E+01
.942	9.224E+01	.971	9.261E+01	.995	9.238E+01	1.018	9.156E+01
1.041	9.114E+01	1.061	9.065E+01	1.104	9.070E+01	1.136	9.100E+01
1.161	9.131E+01	1.228	9.[illegible]E+01	1.290	9.270E+01	1.[illegible]	9.368E+01
1.364	9.436E+01	1.402	9.475E+01	1.441	9.445E+01	1.491	9.431E+01
1.553	9.[illegible]E+01	1.572	9.345E+01	1.605	9.277E+01	1.665	9.272E+01
1.715	9.[illegible]E+01	1.769	9.[illegible]E+01	1.837	9.244E+01	1.905	9.244E+01
1.937	9.[illegible]E+01	1.998	9.[illegible]E+01	2.030	9.268E+01	2.062	9.222E+01
2.094	9.114E+01	8.074	6.[illegible]E+00	8.173	6.[illegible]E+00	8.467	5.429E+00
8.798	4.[illegible]E+00	9.122	3.[illegible]E+00	9.441	2.377E+00	9.794	1.286E+00
9.941	1.[illegible]E+00	10.[illegible]	1.675E+00	10.172	3.117E+00	10.273	5.623E+00
10.377	8.[illegible]E+00	10.[illegible]	1.496E+01	10.538	2.401E+01	10.612	3.371E+01
10.689	4.[illegible]E+01	10.[illegible]	5.556E+01	10.831	6.558E+01	10.904	7.479E+01
10.931	8.[illegible]E+01	11.[illegible]	8.556E+01	11.130	8.798E+01	11.220	8.944E+01
11.415	9.[illegible]E+01	11.[illegible]	9.211E+01	11.965	9.305E+01	12.362	9.374E+01
12.715	9.[illegible]E+01	13.[illegible]	9.506E+01	13.376	9.582E+01	13.781	9.583E+01
14.[illegible]2	9.[illegible]E+01	14.[illegible]	9.552E+01	14.627	9.443E+01	14.816	9.258E+01
15.[illegible]5	9.[illegible]E+01	15.[illegible]	8.532E+01	15.458	8.073E+01	15.682	7.677E+01
15.[illegible]3	7.[illegible]E+01	15.[illegible]	7.812E+01	15.821	8.279E+01	15.899	8.798E+01
15.[illegible]4	8.[illegible]E+01	16.[illegible]	8.770E+01	16.406	8.280E+01	16.831	7.512E+01
17.238	6.[illegible]E+01	17.[illegible]	5.999E+01	18.024	5.116E+01	18.454	4.363E+01
18.[illegible]8	3.[illegible]E+01	19.[illegible]	2.751E+01	19.849	2.009E+01	20.214	1.287E+01
20.[illegible]6	1.[illegible]E+01	20.[illegible]	1.377E+01	20.614	6.202E+01	20.514	2.991E+01
20.[illegible]4	4.[illegible]E+01	20.[illegible]	1.693E+01	20.614	7.352E+01	20.673	8.062E+01
21.[illegible]2	8.[illegible]E+01	21.[illegible]	9.[illegible]E+01	21.283	9.221E+01	21.560	8.838E+01
21.799	8.[illegible]E+01	22.[illegible]	7.762E+01	22.520	7.07[illegible]E+01	22.948	6.[illegible]E+01
23.[illegible]3	5.[illegible]E+01	23.894	4.931E+01	24.[illegible]2	4.138E+01		

Table I-1.5.3 Powdered Aluminum Oxide Reflectivity — Representative Data

λ	R	λ	R	λ	R
7.225	6.692E+01	7.325	2.422E+01	7.443	2.143E+01
7.524	1.000E+02	7.624	1.657E+01	7.728	1.475E+01
7.833	4.323E+01	7.902	1.122E+01	8.094	8.638E+00
8.158	6.822E+00	8.317	4.752E+00	8.477	2.169E+00
8.538	1.198E+00	8.723	4.959E-01	8.842	1.653E-02
8.934	2.668E-01	9.434	2.086E-01	9.537	4.132E-02
9.934	2.333E-01	10.067	8.159E-01	10.265	1.260E+00
10.508	1.822E+00	10.528	1.880E+00	10.712	2.293E+00
11.050	3.114E+00	11.114	3.084E+00	11.283	4.421E+00
11.462	4.907E+00	11.693	5.774E+00	12.025	5.616E+00
12.362	5.535E+00	12.554	5.366E+00	12.938	5.533E+00
13.315	5.622E+00	13.915	5.132E+00	14.309	5.021E+00
14.731	5.026E+00	15.231	5.026E+00	15.534	5.317E+00
15.973	4.938E+00	16.255	5.384E+00	16.888	7.190E+00
17.551	7.273E+00	17.959	5.317E+00	17.810	5.317E+00
18.323	7.211E+00	18.998	7.321E+00	19.409	5.343E+00
19.292	7.128E+00	19.933	2.107E+00	20.025	2.822E+00
20.759	1.219E+00	21.106	2.107E+00	21.734	4.339E+00
22.839	5.754E+00	22.138	4.979E+00	23.386	5.317E+00
24.388	4.859E+00	24.788	4.050E+00	25.239	2.459E+00
25.622	2.231E+00	25.959	5.302E+00	26.559	7.231E+00
27.162	5.273E+00	28.165	5.289E+00	28.563	7.231E+00
29.437	5.289E+00				


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1-1.5.3
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
100
90
80
70
60
50
40
30
20
10
0


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1-1.5.3
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
5
10.
15.
20.
25.
30.
35.
40.
45.
50.
100
90
80
70
60
50
40
30
20
10
0

I-1.6. Transmittance - Aluminum Oxide

The transmittance of Al_2O_3 is shown in Tables I-1.6a through I-1.6e for T = 300°K. The transmittance is a weak function of temperature, and variations with T that occur over some spectral ranges are tabulated in Section III-1.6. The unnormalized transmittances of various thicknesses of sapphire and alumina powder shown in the figures are taken from Oppenheim (Ref. 1T-17), Piriou (Ref. 1T-19), White (Ref. 1T-22), Dorsey (Ref. 1T-1) and Loewenstein (Ref. 1T-9). The structure observed in the optical properties of alumina is tabulated in terms of normal lattice frequencies and absorption bands in Section I-1.7.


Table I-1.6 Aluminum Oxide Transmittance — Representative Data


a. Sapphire of unspecified thickness (from Ref. 1T-17).

λ	T	λ	T	λ	T	λ	T
1.029	8.305E+01	1.397	8.466E+01	2.338	8.310E+01	3.513	8.538E+01
4.189	8.389E+01	4.374	7.871E+01	4.598	6.784E+01	4.792	5.579E+01
4.998	4.288E+01	5.409	2.151E+01	5.619	1.267E+01		

b. Sapphire, T = 0.062 mm (from Ref. 1T-19).

λ	T	λ	T	λ	T	λ	T
6.102	8.513E+01	6.198	8.250E+01	6.239	8.109E+01	5.943	8.699E+01
6.391	7.941E+01	6.505	7.896E+01	6.566	7.814E+01	6.315	7.997E+01
6.693	7.441E+01	6.778	7.262E+01	6.815	7.147E+01	6.625	7.612E+01
6.923	6.548E+01	6.959	6.350E+01	6.989	6.281E+01	6.888	6.765E+01
7.081	6.213E+01	7.135	5.988E+01	7.203	5.684E+01	7.049	5.343E+01
7.321	5.210E+01	7.388	4.988E+01	7.458	4.846E+01	7.263	4.436E+01
7.507	4.489E+01	7.535	4.376E+01	7.571	4.345E+01	7.478	4.688E+01
7.622	4.569E+01	7.651	4.648E+01	7.690	4.549E+01	7.596	4.433E+01
7.746	4.221E+01	7.759	4.124E+01	7.804	4.060E+01	7.724	4.345E+01
8.019	4.070E+01	8.054	4.056E+01	8.075	4.134E+01	7.909	4.114E+01
8.106	4.376E+01	8.128	4.471E+01	8.152	4.509E+01	8.086	4.244E+01
8.221	4.461E+01	8.268	4.365E+01	8.296	4.227E+01	8.182	4.321E+01
8.357	3.988E+01	8.384	3.842E+01	8.415	3.745E+01	8.336	4.136E+01
8.488	3.610E+01	8.514	3.523E+01	8.548	3.359E+01	8.448	3.666E+01
8.580	3.135E+01	8.604	3.092E+01	8.635	3.109E+01	8.558	3.248E+01
8.701	3.059E+01	8.730	2.932E+01	8.772	2.727E+01	8.671	3.138E+01
8.864	2.338E+01	8.918	2.179E+01	8.963	2.038E+01	8.815	2.520E+01
9.044	1.913E+01	9.107	1.962E+01	9.151	2.014E+01	8.999	1.970E+01
9.234	1.916E+01	9.251	2.068E+01	9.282	2.029E+01	9.206	2.046E+01
9.408	1.739E+01	9.482	1.781E+01	9.579	1.703E+01	9.364	1.810E+01
9.676	1.583E+01	9.749	1.523E+01	9.839	1.442E+01	9.625	1.672E+01
9.979	1.216E+01	10.028	1.173E+01	10.073	1.140E+01	9.915	1.338E+01
10.195	1.096E+01	10.261	1.082E+01	10.335	8.636E+00	10.136	1.157E+01
10.491	8.389E+00	10.541	4.859E+00	10.593	3.877E+00	10.397	7.984E+00
10.738	1.780E+00	10.795	1.062E+00	10.828	3.838E-01	10.668	2.779E+00


TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6A
SAPPHIRE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6B
SAPPHIRE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


c. Alumina Powder


λ	T	λ	T	λ	T	λ	T
12.000	7.25[illegible]E+01	12.[illegible]19	9.6[illegible]E+01	12.193	9.225E+01	12.307	5.985E+01
12.341	5.80[illegible]E+01	12.[illegible]45[illegible]	9.[illegible]49[illegible]E+01	12.556	5.251E+01	12.761	4.989E+01
12.984	4.75[illegible]E+01	13.[illegible]247	4.[illegible]52[illegible]E+01	13.536	4.329E+01	13.335	4.171E+01
14.155[illegible]	4.[illegible]62[illegible]E+01	14.[illegible]35[illegible]	3.984E+01	14.[illegible]966	4.318E+01	14.733	4.041E+01
14.955	4.017E+01	15.[illegible]463	3.96[illegible]E+01	16.035	3.902E+01	16.560	3.848E+01
16.767	3.822E+01	17.[illegible]024	3.75[illegible]E+01	17.243	3.683E+01	17.483	3.646E+01
17.677	3.647E+01	17.884	3.689E+01	18.106	3.793E+01	18.253	3.951E+01
18.430	4.373E+01	18.[illegible]45	4.758E+01	18.654	5.194E+01	18.792	5.667E+01
18.963	6.340E+01	19.[illegible]12[illegible]	6.919E+01	19.308	7.684E+01	19.463	8.403E+01
19.540	8.[illegible]E+01	19.[illegible]619	9.298E+01	19.672	9.473E+01	19.724	9.724E+01
19.762	9.816E+01	19.[illegible]829	9.872E+01	19.969	9.921E+01	20.078	9.853E+01
20.201[illegible]	9.[illegible]E+01	20.[illegible]358	9.311E+01	20.486	8.988E+01	20.621	8.728E+01
20.742	8.[illegible]82[illegible]	20.[illegible]559	8.474E+01	20.911	8.397E+01	20.984	8.252E+01
21.090	7.9[illegible]E+01	21.190	7.644E+01	21.291	7.296E+01	21.394	7.036E+01
21.472	6.743E+01	21.[illegible]367	6.478E+01	21.716	6.150E+01	21.864	5.898E+01
22.033	5.[illegible]E+01	22.266	5.412E+01	22.482	5.271E+01	22.631	5.229E+01
22.795	5.213E+01	22.[illegible]968	5.231E+01	23.142	5.316E+01	23.265	5.446E+01
23.439	5.[illegible]E+01	23.[illegible]95	5.9[illegible]E+01	23.728	6.152E+01	23.821	6.393E+01
23.891	6.351E+01						

d. Alumina Powder

λ	T	λ	T	λ	T
14.037	3.[illegible]53[illegible]E+01	14.317	3.609E+01	14.940	3.648E+01
15.209	3.5[illegible]0[illegible]E+01	15.376	3.315E+01	15.585	3.009E+01
15.747	2.757E+01	15.878	2.676E+01	16.037	2.922E+01
16.1[illegible]55	3.[illegible]80[illegible]E+01	16.315	3.[illegible]09E+01	16.50[illegible]	3.280E+01
16.522	2.448E+01	16.922	2.073E+01	16.773	1.638E+01
16.996	1.[illegible]47[illegible]E+01	17.190	1.733E+01	17.430	2.778E+01
17.671	3.[illegible]80[illegible]E+01	17.897	4.532E+01	18.123	5.058E+01
18.361	5.[illegible]65[illegible]E+01	18.677	6.[illegible]15E+01	18.899	7.222E+01
19.1[illegible]9	7.[illegible]5[illegible]E+01	19.476	7.[illegible]50E+01	19.723	6.955E+01
20.[illegible]033	6.4[illegible]1[illegible]E+01	20.209	6.[illegible]96E+01	20.[illegible]40	6.391E+01
20.985	6.552[illegible]E+01	21.464	6.342E+01	21.447	5.342E+01
21.[illegible]28	4.[illegible]84[illegible]E+01	21.601	3.[illegible]48E+01	21.990	2.255E+01
22.[illegible]22	2.[illegible]74[illegible]E+01	22.[illegible]12	3.[illegible]67E+01	23.[illegible]40	4.434E+01
23.[illegible]16	[illegible].272E+01	23.933	6.[illegible]65E+01	24.931	[illegible].204E+01
25.[illegible]99	[illegible].392E+01	25.673	6.352E+01	25.875	5.791E+01
26.382	6.356E+01	26.981	6.889E+01	27.967	7.555E+01
28.[illegible]91	[illegible].815E+01	29.87[illegible]	7.860E+01	62.488	7.934E+01
110.2[illegible]2	[illegible].[illegible]15E+01	53.163	8.[illegible]32E+01	212.658	8.029E+01
268.815	[illegible].[illegible]43E+01				


TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6C
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6D
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6D
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
0
10
20
30
40
50
60
70
80
90
100

TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6D
ALUMINA POWDER
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
0
10
20
30
40
50
60
70
80
90
100

e. Sapphire

λ	T	λ	T	λ	T
1000.000	6.725E+01	845.631	6.552E+01	725.640	5.697E+01
624.545	6.938E+01	562.283	6.725E+01	505.790	6.087E+01
458.250	6.353E+01	418.668	6.000E+01	386.260	5.459E+01
358.369	5.955E+01	335.279	5.763E+01	313.619	5.789E+01
295.834	5.196E+01	277.596	5.195E+01	263.485	5.405E+01
250.000	5.410E+01	238.144	5.350E+01	227.807	5.172E+01
217.252	5.118E+01	208.724	4.957E+01	200.419	4.800E+01
192.804	4.510E+01	185.409	4.442E+01	177.800	4.405E+01
172.417	4.194E+01	167.266	4.092E+01	161.582	4.024E+01
156.371	3.916E+01	151.615	3.959E+01	146.978	3.988E+01
135.230	3.717E+01	131.757	3.605E+01	128.315	3.351E+01
125.106	3.237E+01				


TRANSMITTANCE OF ALUMINUM OXIDE
FIG. I-1.6E
SAPPHIRE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
0
10
20
30
40
50
60
70
80
90
100

I-1.7 Classical Oscillator Frequencies and Observed Absorption Peaks of Al_2O_3

These data were compiled from Aronson (Ref. 1R-3), Piriou (Ref. 1N-9, 1T-19), Barker (Ref. 1R-4) and Dorsey (Ref. 1T-1). Redundant measurements have not been removed.

λ (μ)	ν (cm^{-1})	Comments	Reference
28.669	348.8		1N-9
25.974	385 ± 1%	ordinary ray	1R-4
25.907	386	strong	1T-1
25.773	388	longitudinal mode, ord. ray	1R-4
25.000	400	extraordinary ray	1R-4
22.936	436	forbidden	1R-4
22.779	439	forbidden	1R-4
22.763	439.3		1N-9
22.624	442 ± 1%	ordinary ray	1R-4
22.472	445	strong	1T-1
22.321	448	forbidden	1R-4
22.222	450	forbidden	1R-4
22.786	459	forbidden	1R-4
21.186	472	forbidden	1R-4
20.833	480 ± 1%	longitudinal mode, ord. ray	1R-4
20.704	483	forbidden	1R-4
20.534	487	strong	1T-1
19.531	512	longitudinal mode, ext. ray	1R-4
17.575	569 ± 1%	ordinary ray	1R-4

λ (μ)	ν (cm^{-1})	Comments	Reference
17.559	569.5		1N-9
17.513	571	forbidden	1R-4
17.153	583		1T-1
17.153	583 ± 1%	extraordinary ray	1R-4
16.892	592	forbidden	1R-4
16.722	598	forbidden	1R-4
16.000	625 ± 1%	longitudinal mode, ord. ray	1R-4
15.773	634		1N-9
15.748	635 ± 1%	ordinary ray	1R-4
15.699	637	forbidden	1R-4
15.674	638	strong	1T-1
15.385	650	forbidden	1R-4
15.290	654 ± 1%	extraordinary ray	1R-4
12.987	770	forbidden	1R-4
12.820 ± 0.05	780 ± 3%		1N-9
12.407	806	forbidden	1R-4
11.481	871	longitudinal mode, ord. ray	1R-4
11.313 ± 0.039	884 ± 3%		1N-9
11.111	900 ± 1%	longitudinal mode, ext. ray	1R-4
10.040	996		1T-19
9.390	1065	strong	1T-19
9.009	1110	strong	1T-19
8.591	1164	strong	1T-19
8.403	1190	medium	1T-19
8.039	1244	strong	1T-19
7.819	1279	strong	1T-19
7.541	1326	strong	1T-19
7.299	1370	medium	1T-19
6.978	1433	strong	1T-19
6.711	1490	strong	1T-19
6.289	1590	medium	1T-19
5.556	~1800	medium	1T-19

I-1.8 Conclusions: Areas Needing Further Research

An examination of the Al_2O_3 literature shows that more research is needed for the following infrared optical properties:

(a) Refractive Index:

Sapphire - no reliable data from 6-9μ have been found.

Bulk Alumina - no measurements of the refractive index have been made.

Powders - the only data obtained are of uncertain value.

(b) Extinction Index:

Powders - the only data obtained are of uncertain value.

(c) Spectral Emittance:

Bulk Alumina - no measurements beyond 15μ have been made

Powdered Alumina - the measurements made for powders indicate only that the emissive properties of particles have not yet been determined.

(d) Total Emissivity:

Powders - except for one Reference (1TE-3) no information has been obtained on $\epsilon(T)$ for powdered materials.

(e) Reflectivity:

Bulk Alumina - a gap exists from 2μ to 8μ.

Powders - no high temperature measurements have been made. The 300°K measurements of Aronson (Ref. 1R-1) cover 7μ to 30μ.

I-2 CARBON PROPERTIES


I-2.1 Refractive Index, n — Carbon

Very few measurements of the refractive index of carbon or graphite exist in the literature. Figure I-2.1 and Table I-2.1 present the data of Foster (Ref. 2N-2) for graphite, which is taken to be representative of carbon and graphite. Refractive index measurements on soot (Ref. 2N-1, 2N-2) indicate that n (λ) increases with wavelength for both graphite and soot, and that the soot data are within a factor of 2 of the graphite data. Glassy carbon measurements (Ref. 2N-10) to 2 μ are in good agreement with the representative curve, as are the pyrolytic graphite data of Lenham (Ref. 2N-6) which extend to 17μ. Fair agreement exists between the representative curve and carbon film data (Ref. 2R-4).

Preceding page blank

Table I-2.1 Carbon and Graphite Refractive Index - Representative Data

λ	n	λ	n	λ	n	λ	n
.975	1.8[illegible]E+[illegible]	1.028	1.873E+00	1.095	1.932E+00	1.207	2.015E+00
1.329	2.[illegible]94E+[illegible]	1.456	2.170E+00	1.583	2.246E+00	1.749	2.316E+00
1.909	2.388E+[illegible]	2.103	2.458E+00	2.324	2.528E+00	2.570	2.599E+00
2.771	2.65[illegible]E+[illegible]	2.989	2.703E+00	3.187	2.749E+00	3.394	2.795E+00
3.584	2.839E+[illegible]	3.775	2.879E+00	3.990	2.916E+00	4.298	2.977E+00
4.[illegible]20	3.[illegible]1[illegible]E+[illegible]	4.728	3.051E+00	4.931	3.084E+00	5.139	3.118E+00
5.34[illegible]	3.1[illegible]E+[illegible]	5.552	3.190E+00	5.727	3.238E+00	5.906	3.279E+00
[illegible].[illegible]8[illegible]	3.32[illegible]E+[illegible]	6.228	3.361E+00	6.381	3.402E+00	6.594	3.437E+00
[illegible].[illegible]3[illegible]	3.47[illegible]E+[illegible]	6.954	3.482E+00	7.089	3.472E+00	7.234	3.429E+00
7.[illegible]3[illegible]	3.[illegible]0[illegible]E+[illegible]	7.458	3.399E+00	7.562	3.416E+00	7.674	3.461E+00
7.8[illegible]4	3.[illegible]7E+[illegible]	7.957	3.559E+00	8.116	3.608E+00	8.293	3.659E+00
8.435	3.761E+[illegible]	8.708	3.745E+00	8.950	3.784E+00		


REFRACTIVE INDEX OF CARBON
FIGURE 1-2.1
CARBON
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
5.0
4.5
4.0
3.5
3.0
2.5
2.0
1.5
1.0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


I-2.2 Extinction Index, k - Carbon

The measurements of k for carbon, graphite, and pyrolytic graphite found in the literature are in very poor agreement over all wavelengths. The value of k at 1μ seems to be between 0.5 and 1.0, but the behavior with wavelength is not clearly defined. Krascella (Ref. 2K-7) shows k for carbon smoothly rising to 2.0 at 1.0μ. Foster (Ref. 2K-3) shows for graphite a rise to 1.2 at 4μ, then finally a decrease to 0.8 at 10.0μ. Hennig (Ref. 2K-4) observes for lamellar graphite a rise from 1μ to 2μ of 0.7 to 3.6.

In the absence of coherent information on the extinction index, the data of Foster (Ref. 2K-3) have been chosen as representative. Figure I-2.2 shows these data. All other references are included in Section III-2.2.

Table I-2.2 Carbon Extinction Index - Representative Data

λ	k	λ	k	λ	k	λ	k
.990	6.78[illegible]E-01	1.120	9.237E-01	1.234	9.652E-01	1.390	1.014E+00
1.073	1.[illegible]E+00	1.[illegible]	1.[illegible]E+00	2.[illegible]	1.148E+00	2.183	1.[illegible]E+00
2.[illegible]	1.21[illegible]E+00	2.653	1.245E+00	2.884	1.273E+00	3.155	1.298E+00
3.[illegible]	1.[illegible]E+00	3.720	1.335E+00	3.994	1.351E+00	4.311	1.356E+00
4.[illegible]	1.361E+00	[illegible]	1.362E+00	5.219	1.357E+00	5.364	1.351E+00
5.[illegible]	1.351E+00	5.681	1.353E+00	5.825	1.357E+00	5.971	1.360E+00
6.[illegible]	1.359E+00	6.250	1.354E+00	6.[illegible]	1.350E+00	6.561	1.341E+00
6.69[illegible]	1.33[illegible]E+00	6.843	1.343E+00	6.944	1.364E+00	7.088	1.420E+00
7.2[illegible]	1.[illegible]E+00	7.284	1.519E+00	7.358	1.575E+00	7.414	1.598E+00
7.[illegible]	1.[illegible]E+00	7.[illegible]	1.[illegible]E+00	7.716	1.574E+00	7.795	1.519E+00
7.87[illegible]	1.[illegible]E+00	7.933	1.391E+00	8.[illegible]	1.335E+00	8.144	1.281E+00
8.2[illegible]	1.[illegible]E+00	8.391	1.169E+00	8.534	1.114E+00	8.69[illegible]	1.061E+00
8.[illegible]	1.[illegible]E+00	9.079	9.647E-01	9.372	9.119E-01	9.628	8.643E-01
9.892	8.258E-01						


EXTINCTION INDEX OF CARBON
FIGURE 1-2.2
CARBON
T=300K
REPRESENTATIVE DATA
1E 1
1E 0
1E-1
1E-2
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

I-2.3 Spectral Emissivity - Carbon

a) The spectral emissivities of high purity graphite and carbon as measured by various authors are sufficiently similar from 1μ to 5μ, the range of most experimental studies, to be considered the same. Wide variations exist in the published data, and the temperature dependence of $\epsilon(\lambda)$, if any, is poorly defined. Nine representative curves have been chosen ranging from 1105°K to 2850°K. All cover the 1μ to 4μ range, and two, 1105°K and 1420°K, extend to 13μ. Few conclusions regarding $\epsilon(\lambda)$ in this temperature range can actually be drawn, unfortunately, except that $\epsilon(\lambda) > 0.7$ to about 9μ.

b) Pyrolytic Graphite - pyrolytic graphite is a highly anisotropic material with C face (a-b plane) and A face (c-plane) emittances varying by over a factor of 3 or 4 for much of the spectral regions surveyed.

The data of Kibler (Ref. 2SE-13) indicate for the A face (c-plane) that at 0.5μ, $\epsilon(\lambda)$ is low, but rises to a peak around 1.25μ, then slowly drops (except for $\epsilon(\lambda)$ at T = 1914°K, which rises slowly and levels off around 2.0μ). There seems to be no simple increase or decrease with temperature. Wilson's (Ref. 2SE-17) data show $\epsilon(\lambda)$ high ($\sim$1.0) at short wavelengths, with a rapid drop in the infrared. Autio and Scala (Ref. 2SE-3) show generally lower values of $\epsilon(\lambda)$. There is presently no way to choose any one set of data as representative.

The C face is shown by all researchers to have a much lower emissivity that the A face. Kibler (Ref. 2SE-13) has observed a value of $\epsilon(\lambda) < 0.3$ for $\lambda < 1.0\mu$, which slowly increases with wavelength and decreases with increasing temperature.

For both emissivities, readers are referred to Section III-2.3 for measurements made at specific temperatures. For

T = 1400°K, refer to Autio (Ref. 2SE-3); for T = 1600° to 2800°K, refer to Kibler (Ref. 2SE-13); and for T above 2800°K, refer to Wilson (Ref. 2SE-17).

Figure I-2.3 shows, for an example only, $\epsilon(\lambda)$ for the A and C faces from 1800°K to 1900°K.

Table I-2.3 Carbon Spectral Emissivities - Representative Data

a) $T = 1105^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
2.331	.823	2.450	.867	2.727	.882	2.915	.897
3.057	.845	3.365	.835	3.500	.840	3.836	.823
3.[illegible]	.[illegible]	[illegible]	.792	4.449	.781	[illegible]	.778
5.322	.775	[illegible]	.774	5.406	.753	5.638	.742
[illegible]	.720	6.[illegible]	.722	6.466	.740	6.882	.772
[illegible]	.784	7.[illegible]	.790	7.492	.784	7.799	.762
9.196	.734	8.553	.714	9.091	.761	9.805	.693
11.[illegible]	.[illegible]	11.948	.673	11.251	.667	11.763	.645
12.[illegible]	.[illegible]	12.207	.633				

b) $T = 1273^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
.[illegible]	.857	.77[illegible]	.875	.941	.887	1.112	.894
[illegible]	.[illegible]	1.[illegible]	.[illegible]	1.[illegible]	.902	2.359	.902
.734	.[illegible]	3.[illegible]	.905	3.395	.905	3.763	.907
[illegible]	.[illegible]	[illegible]	.911	4.706	.914	5.054	.917
[illegible]	.[illegible]						

c) $T = 1420^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.891	2.196	.967	3.396	.987	3.787	.991
[illegible]	.[illegible]	[illegible]	.935	5.356	.894	5.905	.857
[illegible]	.[illegible]	[illegible]	.892	5.611	.864	6.923	.885
7.[illegible]	.934	7.685	.[illegible]	7.86[illegible]	.934	8.224	.913
[illegible]	.[illegible]	[illegible]	.[illegible]	9.25[illegible]	.880	9.318	.880
[illegible]	.877	[illegible]	.[illegible]	11.561	.834	11.879	.825
[illegible]	.[illegible]	[illegible]	.833	12.[illegible]	.850	12.925	.875
13.[illegible]	.891	13.[illegible]	.89	13.915	.898		

Reproduced from best available copy.

Table I-2.3 (Continued)

d) T = 1473°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	.743	.875	.820	.888	.998	.914
1.160	.921	1.338	.929	1.546	.931	1.871	.931
[illegible]	[illegible]	[illegible]	[illegible]	2.988	.936	3.367	.937
[illegible]	[illegible]	[illegible]	[illegible]	4.509	.941	4.872	.944
[illegible]	[illegible]	5.330	.948	5.486	.951		

e) T = 1673°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	.756	.881	.858	.902	1.010	.928
[illegible]	[illegible]	1.186	.945	1.264	.951	1.463	.953
[illegible]	[illegible]	[illegible]	[illegible]	2.586	.953	2.877	.955
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	4.145	.964
[illegible]	[illegible]	4.748	.973	5.079	.971	5.378	.971

f) T = 1873°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	.717	.892	.783	.914	.875	.932
[illegible]	[illegible]	[illegible]	[illegible]	1.224	.960	1.349	.962
1.745	.962	[illegible]	[illegible]	2.318	.964	2.574	.967
[illegible]	[illegible]	[illegible]	[illegible]	3.649	.969	3.769	.970
[illegible]	[illegible]	4.473	.973	4.837	.975	5.163	.976

Table I-2.3 (Continued)

g) T = 1882°K, pyrolytic graphite, a-face

λ	ε	λ	ε	λ	ε	λ	ε
.500	.795	.570	.819	.639	.842	.788	.861
.606	.882	.893	.896	.978	.985	1.066	.985
1.149	.912	1.264	.918	1.369	.985	1.479	.899
1.634	.888	1.816	.876	1.968	.863	2.142	.849
2.285	.842	2.431	.833	2.619	.825	2.828	.817
3.024	.887	3.248	.795	3.429	.784	3.638	.771
3.841	.757	3.975	.748	4.876	.741		

h) T = 1808°K, pyrolytic graphite, c-face

λ	ε	λ	ε	λ	ε	λ	ε
1.183	.301	1.359	.325	1.508	.345	1.096	.367
1.838	.386	2.059	.403	2.279	.415	2.506	.427
2.763	.433	2.971	.445	3.198	.451	3.452	.457
3.717	.463	3.983	.495	4.231	.473	4.469	.473
4.715	.475	4.910	.475	5.320	.477		

Table I-2.3 (Continued)

i) T = 2150°K, pyrolytic graphite, c-face

λ	ε	λ	ε	λ	ε	λ	ε
.495	.757	.994	.820	1.473	.860	1.968	.885
2.456	.900	2.939	.908	3.422	.917	3.922	.921
4.417	.922	4.860	.923				

j) T = 2360°K, pyrolytic graphite, c-face

λ	ε	λ	ε	λ	ε	λ	ε
.835	.769	1.778	.809	2.856	.839	3.325	.837
3.332	.895	3.992	.808	4.788	.845	5.266	.871

k) T = 2850°K, pyrolytic graphite, c-face

λ	ε	λ	ε	λ	ε	λ	ε
.396	.929	.644	.905	.798	.910	1.193	.881
1.593	.895	1.998	.873	2.395	.847	2.793	.863




FIGURE I-2.3A
GRAPHITE
T=1105K
REPRESENTATIVE DATA




FIGURE I-2.3B
GRAPHITE
T=1273K
REPRESENTATIVE DATA




FIGURE I-2.3C
GRAPHITE
T=1420K
REPRESENTATIVE DATA




FIGURE I-2.3D
GRAPHITE
T=1473K
REPRESENTATIVE DATA




FIGURE I-2.3E
GRAPHITE
T=1673K
REPRESENTATIVE DATA




FIGURE I-2.3F
GRAPHITE
T=1873K
REPRESENTATIVE DATA




FIGURE I-2.3G
A-FACE PYROLYTIC GRAPHITE
T=1882K
REPRESENTATIVE DATA




FIGURE I-2.3H
C-FACE PYROLYTIC GRAPHITE
T=1808K
REPRESENTATIVE DATA




FIGURE I-2.31
ATJ GRAPHITE
T=2150K
REPRESENTATIVE DATA





FIGURE I-2.32
ATJ GRAPHITE
T=2360K
REPRESENTATIVE DATA


SPECTRAL EMISSIVITY OF CARBON
SPECTRAL EMISSIVITY
.9
.8
.7
.6
.5
.4
.3
.2
.1
0.
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1-2.3K
ATJ GRAPHITE
T=2800K
REPRESENTATIVE DATA

I-2.4 Total Normal Emissivity, ϵ(T) - Carbon

A representative value for ϵ(T) of unpolished carbon or graphite, including the graphites H1LM, H3LM, AGX, AGKSP, ATJ, ATJS, AUC, GA, GBE, GNH, 60 580, 7087, 7100 and 3474D, and L113SP high purity carbon, for temperatures ranging from 500 to 3000°K is approximately 0.85 $\pm$ 5 percent.

Section III-2.4 contains the processed data for ϵ(T) found in the literature for many specific varieties of carbons and graphites.

Touloukian (Ref. 2TE-8) shows pyrolytic graphite as being highly anisotropic in ϵ(T), just as it was in $\epsilon(\lambda)$; the single temperature measurements of Wilson (Ref. 2TE-10) at temperatures above 2200°K do not confirm this behavior however. Both sets of data are presented in Section III-2.4.

In using these ϵ(T) data one must take care to apply them only to materials with surfaces prepared in a manner similar to that in which the original samples were prepared. Surface oxidation can cause very large changes in emissivity, and polishing can orient the surface microcrystals, resulting in pyrolytic-like emissivities for graphites.

I-2.5 Reflectance - Carbon

Correlation between reflectivities and emissivities is very poor for all published reflectivity data except Wilson's (Ref. 2R-5) which are included in Section I-2.3. Section III-2.5 presents one single crystal reflectivity and two polycrystalline graphite reflectivities, none of which have any meaningful properties in common.

I-2.8 Conclusions: Areas Needing Further Research

No particulate optical properties have been measured for pure particles, and the variations found in the data for soot make extrapolation of the information to carbon very uncertain.

The refractive index and extinction index for bulk carbon, graphite, and pyrolytic graphite are not known with enough certainty to state if they are higher or lower at 8μ compared to 1μ, and so need to be measured carefully.

The spectral emissivities of bulk graphite, pyrolytic graphite, and carbon are known to approximately $\pm$ 5 percent for some materials, but the variations with temperature are not clearly determined. Also, no $300^{\circ}K$ emissivity measurements have been made. The total normal emissivity is known to be 0.85 $\pm$ 5 percent for a wide range of materials, and measurements are only necessary for specific materials where great precision is desired.

In summary, most optical properties of carbon are poorly known, and all, with the possible exception of $\epsilon(T)$, need further research.

I-3 MAGNESIUM OXIDE PROPERTIES

I-3.1 Refractive Index, n — Magnesium Oxide

Figure I-3.1 shows the representative curve for the MgO refractive index at 300°K. No fine structure is visible except for the maximum in the region of 25.5μ. Data for single crystal MgO, MgO evaporated films, and polycrystalline MgO are in good agreement from 1μ to 9μ; for wavelengths longer than 9μ, only single crystal measurements have been made. Measurements of n at high temperatures can be found in Section III-3.1.


The representative curve was constructed using the data of Kodak (Ref. 3N-6), Piriou (Ref. 3N-8) and Stephens (Ref. 3N-11).


Table I-3.1 Representative Refractive Index — Magnesium Oxide


λ	n	λ	n	λ	n	λ	n
1.014	1.723E+00	1.129	1.721E+00	1.367	1.717E+00	1.538	1.715E+00
1.693	1.713E+00	1.709	1.713E+00	1.813	1.711E+00	1.970	1.709E+00
2.249	1.705E+00	2.325	1.703E+00	3.303	1.685E+00	3.508	1.681E+00
4.258	1.650E+00	5.138	1.631E+00	5.350	1.624E+00	5.500	1.618E+00
5.750	1.607E+00	6.000	1.596E+00	6.250	1.584E+00	6.500	1.572E+00
6.750	1.559E+00	7.000	1.545E+00	7.250	1.531E+00	7.500	1.515E+00
7.750	1.499E+00	8.000	1.482E+00	9.109	1.337E+00	9.784	1.344E+00
11.228	1.238E+00	11.727	1.155E+00	12.787	8.925E-01	13.263	7.454E-01
13.609	5.790E-01	14.032	3.445E-01	14.105	3.007E-01	14.580	1.653E-01
14.820	1.499E-01	15.049	1.481E-01	15.299	1.532E-01	15.645	1.717E-01
15.998	1.952E-01	16.322	1.618E-01	16.626	1.368E-01	17.030	1.159E-01
17.395	1.048E-01	17.934	9.750E-02	18.133	9.580E-02	19.238	1.827E-01
20.071	1.157E-01	20.768	1.306E-01	21.379	1.510E-01	22.123	1.958E-01
22.635	2.318E-01	23.121	2.739E-01	23.328	3.141E-01	23.484	3.558E-01
24.972	2.150E+00	25.229	2.949E+00	25.319	3.580E+00	25.323	4.351E+00
25.393	6.455E+00	25.434	9.980E+00	25.467	1.321E+01	25.655	1.889E+01
25.862	1.670E+01	25.991	1.496E+01	26.173	1.325E+01	26.412	1.171E+01
26.745	1.816E+01	27.003	8.562E+00	27.917	7.027E+00	29.213	5.896E+00
31.048	4.926E+00	32.926	4.191E+00	36.122	3.841E+00	41.517	3.571E+00
47.752	3.384E+00	57.463	3.270E+00	68.926	3.178E+00	68.926	3.178E+00
95.822	3.102E+00	104.790	3.165E+00	105.208	3.183E+00	106.210	3.194E+00
108.270	3.200E+00	109.670	3.185E+00	111.850	3.204E+00	112.280	3.197E+00
112.220	3.189E+00	112.420	3.193E+00	114.840	3.202E+00	116.080	3.205E+00
118.930	3.192E+00	119.390	3.197E+00	120.000	3.184E+00	120.140	3.189E+00
120.940	3.180E+00	121.370	3.185E+00	122.000	3.190E+00	123.010	3.179E+00
128.000	3.169E+00	130.600	3.164E+00	130.730	3.159E+00	131.470	3.156E+00
132.640	3.174E+00	132.720	3.164E+00	134.120	3.170E+00	135.280	3.158E+00
137.170	3.145E+00	139.540	3.157E+00	141.360	3.150E+00	143.680	3.163E+00
145.640	3.132E+00	145.700	3.144E+00	148.020	3.140E+00	148.250	3.150E+00
150.690	3.136E+00	151.800	3.164E+00	153.450	3.151E+00	153.940	3.162E+00
154.550	3.159E+00	156.880	3.155E+00	157.560	3.166E+00	159.750	3.163E+00
162.290	3.155E+00	165.260	3.150E+00	167.200	3.153E+00	168.830	3.161E+00
171.770	3.159E+00	174.550	3.146E+00	179.460	3.164E+00	182.740	3.148E+00

Table I-3.1 (Continued)

λ	n	λ	n	λ	n	λ	n
182.750	3.156E+00	183.180	3.159E+00	186.530	3.155E+00	187.310	3.169E+00
191.040	3.157E+00	191.080	3.163E+00	194.180	3.148E+00	197.960	3.144E+00
201.320	3.144E+00	202.680	3.138E+00	207.850	3.142E+00	213.370	3.148E+00
216.270	3.126E+00	222.630	3.139E+00	222.770	3.131E+00	230.460	3.148E+00
234.520	3.136E+00	235.360	3.142E+00	235.508	3.132E+00	239.410	3.114E+00
239.550	3.119E+00	240.320	3.124E+00	247.738	3.128E+00	248.810	3.132E+00
250.150	3.137E+00	255.000	3.129E+00	255.270	3.124E+00	256.580	3.143E+00
261.540	3.122E+00	263.070	3.129E+00	272.030	3.132E+00	272.360	3.145E+00
280.740	3.142E+00	286.250	3.129E+00	308.860	3.135E+00	313.050	3.153E+00
323.840	3.147E+00	333.800	3.122E+00	346.490	3.118E+00	361.240	3.123E+00
387.900	3.070E+00	388.210	3.074E+00	409.660	3.098E+00	410.970	3.102E+00
430.800	3.107E+00	454.400	3.110E+00	476.420	3.091E+00	501.310	3.083E+00
511.680	3.136E+00	535.640	3.089E+00	541.050	3.115E+00	578.570	3.138E+00
622.560	3.140E+00	624.680	3.146E+00	672.388	3.158E+00	719.860	3.108E+00
797.130	3.158E+00	878.500	3.149E+00				


REFRACTIVE INDEX OF MAGNESIUM OXIDE
FIGURE 1-3.1
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.0
4.0
6.0
8.0
10.0
12.0
14.0
16.0
18.0
20.0
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFRACTIVE INDEX OF MAGNESIUM OXIDE
FIGURE 1-3.1
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.0
4.0
6.0
8.0
10.0
12.0
14.0
16.0
18.0
20.0
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


REFRACTIVE INDEX OF MAGNESIUM OXIDE
FIGURE 1-3.1
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA
REFRACTIVE INDEX, N
20.0
18.0
16.0
14.0
12.0
10.0
8.0
6.0
4.0
2.0
0.0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)

I-3.2 Extinction Index, k — Magnesium Oxide

Figure I-3.2 shows the representative curves for the MgO extinction coefficient at T = 300°K. High temperature measurements are graphed and tabulated in Section III-3.2. The extinction coefficient shows little structure except in the 10.2μ, 11.6μ and 25μ regions. Measurements made by Hanna (Ref. 3K-3, 3K-4) indicate that, except at short wavelengths (< 9μ), single crystal MgO and polycrystalline MgO have similar transmissive properties.


The representative curve was constructed using the data of Oppenheim (Ref. 3K-10), Andermann (Ref. 3K-1), Hanna (Ref. 3K-4), and Rowntree (Ref. 3K-15). A linear interpolation was made from 55μ to 90μ, an area of the spectrum where the data of Plendl (Ref. 3K-13) indicate a lack of structure.


Table I-3.2 Magnesium Oxide Extinction Coefficient, T = 300°K — Representative Data


λ	k	λ	k	λ	k
4.0[illegible]1	5.513[illegible]	5.498	1.515E-07	5.750	2.813E-06
6.[illegible]	7.61[illegible]	6.25[illegible]	1.621E-[illegible]	6.500	2.799E-[illegible]
6.[illegible]	4.[illegible]23	6.[illegible]	1.506E-[illegible]	7.[illegible]52	7.106E-[illegible]
7.251	9.419[illegible]	7.462	1.191E-05	7.625	4.391E-04
7.[illegible]	1.[illegible]	7.967	1.903E-[illegible]	8.251	2.371E-[illegible]
8.[illegible]	2.814[illegible]	8.672	3.159E-[illegible]	8.8431	3.507E-[illegible]
8.[illegible]	3.766[illegible]	9.244	4.722E-[illegible]	9.331	6.239E-[illegible]
9.[illegible]	7.42[illegible]	9.552[illegible]	2.[illegible]24E-[illegible]	9.611	2.614E-[illegible]
9.[illegible]	2.[illegible]36	9.799	3.[illegible]94E-[illegible]	9.891	4.486E-[illegible]
9.935	3.99[illegible]	10.[illegible]99	3.912E-[illegible]	10.198	5.334E-[illegible]
10.30[illegible]	4.[illegible]	10.[illegible]01	2.310E-[illegible]	10.[illegible]65	2.[illegible]24E-[illegible]
10.[illegible]	2.[illegible]24	10.746	2.799E-[illegible]	10.[illegible]49	4.418E-[illegible]
11.[illegible]	6.1211	11.104	3.933E-[illegible]	11.224	1.346E-[illegible]
11.[illegible]	1.65[illegible]	11.494	1.899E-[illegible]	11.638	2.243E-[illegible]
11.777	2.[illegible]	11.941	2.346E-[illegible]	12.[illegible]48	1.644E-[illegible]
12.192	1.40[illegible]	12.359	1.410E-[illegible]	12.[illegible]03	1.459E-[illegible]
12.[illegible]72	1.97[illegible]	12.833	2.456E-[illegible]	13.[illegible]83	3.479E-[illegible]
13.34[illegible]	1.[illegible]42	13.[illegible]14	6.[illegible]3E+[illegible]	13.[illegible]47	8.922E+[illegible]
15.77[illegible]	1.184[illegible]	16.07[illegible]	1.284E+[illegible]	16.327	1.346E+[illegible]
16.617	1.437[illegible]	16.839	1.585E+[illegible]	17.157	1.695E+[illegible]
17.[illegible]38	1.793[illegible]	17.[illegible]59	1.917E+[illegible]	18.[illegible]27	2.063E+[illegible]
18.[illegible]44	2.174[illegible]	18.769	2.307E+[illegible]	19.129	2.479E+[illegible]
19.[illegible]99	2.[illegible]86[illegible]	19.[illegible]05	2.825E+[illegible]	20.266	3.084E+[illegible]
20.[illegible]1	3.325[illegible]	21.[illegible]53	3.619E+[illegible]	21.576	3.998E+[illegible]
22.[illegible]53	4.[illegible]91[illegible]	22.[illegible]64	4.[illegible]96E+[illegible]	23.145	5.676E+[illegible]
23.[illegible]39	6.[illegible]33	24.[illegible]92	9.922E+[illegible]	33.497	5.249E-[illegible]
33.[illegible]8	2.221[illegible]	34.[illegible]90	2.184E-[illegible]	35.569	2.153E-[illegible]
36.[illegible]93	2.119[illegible]	37.[illegible]80	2.[illegible]89E-[illegible]	38.563	2.062E-[illegible]
39.[illegible]8	2.[illegible]31[illegible]	40.[illegible]9[illegible]	1.999E-[illegible]	42.380	1.981E-[illegible]
44.[illegible]17	1.956[illegible]	45.887	1.938E-[illegible]	47.755	1.935E-[illegible]
50.[illegible]25	1.932[illegible]	52.802	1.942E-[illegible]	55.877	1.966E-[illegible]
91.514	1.336[illegible]	95.991	1.356E-[illegible]	100.655	1.164E-[illegible]
110.[illegible]23	1.[illegible]20[illegible]	112.889	8.374E-[illegible]	120.871	5.433E-[illegible]
121.[illegible]37	6.[illegible]09[illegible]	125.648	5.[illegible]80E-[illegible]	130.649	3.991E-[illegible]
130.[illegible]39	3.[illegible]42[illegible]	131.[illegible]1[illegible]	4.319E-[illegible]	139.[illegible]14	3.516E-[illegible]
169.[illegible]47	3.[illegible]02[illegible]	151.[illegible]1[illegible]	2.[illegible]97E-[illegible]	151.492	3.381E-[illegible]
151.[illegible]23	3.[illegible]82[illegible]	160.271	2.613E-[illegible]	174.175	2.708E-[illegible]
161.[illegible]92	2.[illegible]19[illegible]	189.823	2.268E-[illegible]	190.133	2.206E-[illegible]
190.[illegible]7[illegible]	2.148E-[illegible]	200.[illegible]70	2.086E-[illegible]	211.[illegible]28	2.262E-[illegible]

Table I-3.2 Continued

λ	k	λ	k	λ	k
211.877	1.989E-03	228.900	2.028E-03	228.959	1.766E-03
250.744	1.883E-03	250.744	1.833E-03	250.916	1.791E-03
261.146	1.794E-03	268.486	1.595E-03	268.609	1.725E-03
269.239	1.672E-03	269.101	1.547E-03	290.860	1.648E-03
291.467	1.602E-03	291.670	1.459E-03	307.286	1.393E-03
307.580	1.338E-03	307.642	1.309E-03	307.928	1.357E-03
330.870	1.116E-03	331.254	1.180E-03	331.945	.365E-03
352.999	1.325E-03	349.370	1.087E-03	350.357	1.116E-03
350.338	1.220E-03	372.539	9.272E-04	373.058	1.179E-03
400.277	6.598E-04	400.923	1.043E-03	428.543	8.663E-04
429.073	9.088E-04	469.824	8.709E-04	497.012	7.595E-04
497.815	7.836E-04	526.549	6.293E-04	527.405	7.417E-04
554.379	5.415E-04	581.518	5.872E-04	620.979	6.124E-04
645.511	6.054E-04				


EXTINCTION INDEX OF MAGNESIUM OXIDE
EXTINCTION INDEX, K
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
1E-8
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE I-3.2
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA


EXTINCTION INDEX OF MAGNESIUM OXIDE
EXTINCTION INDEX, K
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
1E-8
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
WAVELENGTH(MICRONS)
FIGURE I-3.2
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA


EXTINCTION INDEX OF MAGNESIUM OXIDE
1E 1
1E 0
1E-1
1E-2
1E-3
1E-4
1E-5
1E-6
1E-7
1E-8
EXTINCTION INDEX, K
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)
FIGURE I-3.2
MAGNESIUM OXIDE
T=300K
REPRESENTATIVE DATA

I-3.3 Spectral Emissivity, $\epsilon(\lambda)$ – MgO

Only three sources for magnesium oxide spectral emissivity were found, all for the polycrystalline form. The data of Clark (Ref. 3SE-4) and Stierwalt (Ref. 3SE-10) at $T = 1600^{\circ}K$ and $200^{\circ}K$ are presented here in Figures I-3.3 a and b.


Table I-3.3 Representative Spectral Emissivity, MgO


a) T = 200°K


λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.027	[illegible].647	.123	5.175	.035	5.711	.063
[illegible]	.139	[illegible].315	.179	6.755	.249	7.002	.258
7.275	.274	[illegible]	.331	7.669	.398	7.953	.426
[illegible]	.459	[illegible].522	.493	8.672	.542	8.385	.742
9.379	.875	9.687	.971	9.898	.981	10.301	.975
11.769	.981	12.115	.987	12.553	.969	12.772	.953
12.980	.922	13.358	.776	13.239	.609	13.631	.447
[illegible]	.330	[illegible].991	.257	14.907	.237	15.234	.250
[illegible]	.223	[illegible].880	.204	15.703	.157	15.975	.118
[illegible]	.178	[illegible].553	.153	17.866	.036	18.775	.023
[illegible]	.118	[illegible].365	.614	23.535	.013	24.440	.010
[illegible]	.228	[illegible].376	.556	25.084	.131	25.238	.237
[illegible]	.311	25.967	.357	26.464	.415	27.004	.449
[illegible]	.475	[illegible].771	.493	28.460	.512	28.782	.536
[illegible]	.548	29.364	.532	29.749	.547	30.179	.551
[illegible]	.574	31.768	.594	32.400	.603	32.779	.606
33.174	.598	33.546	.590	33.898	.585	34.309	.592
35.357	.614	36.432	.624	38.199	.640		

b) T = 1600°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.227	[illegible]	.136	2.000	.151	2.500	.141
[illegible]	.144	[illegible]	.156	[illegible]	.205	[illegible]	.260
[illegible]	.338	[illegible]	.545	[illegible]	.645	[illegible]	.687
[illegible]	.735	[illegible]	.827	[illegible]	.878	[illegible]	.879
[illegible]	.929	[illegible]	.959	[illegible]	.970	[illegible]	.978
[illegible]	.977	[illegible]	.977	[illegible]	.980	[illegible]	.982
[illegible]	.979	[illegible]	.962	14.000	.910	[illegible]	.842
[illegible]	.960						


SPECTRAL EMISSIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.3A
MAGNESIUM OXIDE
T=200K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


SPECTRAL EMISSIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.3A
MAGNESIUM OXIDE
T=200K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


SPECTRAL EMISSIVITY OF MAGNESIUM OXIDE
FIGURE I-3-38
MAGNESIUM OXIDE
T=1600K
REPRESENTATIVE DATA
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

I-3.4 Total Normal Emissivity, $\epsilon(\lambda)$ – Magnesium Oxide

The total emissivity of polycrystalline MgO nas been measured for temperatures ranging from 29°K to 1800°K. The representative curve for magnesia data, constructed by fitting a third order polynomial to data from References 3TE-6 and 3TE-8 is shown in Figure I-3.4, and tabulated in Table I-3.4.

ϵ (T) is seen to decrease with temperature from a high of ~0.7 to under 0.3 at 1500°K. This behavior is very similar to that of ϵ (λ) of alumina.

No experimental error is quoted for these data.

Table I-3.4 Polynomial Fit to the Experimental Data

T	ε (T)	T	ε(T)	T	ε(T)
20.000	0.7201	920.000	0.4262	1820.000	0.3021
40.000	0.7170	940.000	0.4189	1840.000	0.3069
60.000	0.7136	960.000	0.4117	1860.000	0.3121
80.000	0.7099	980.000	0.4046	1880.000	0.3178
100.000	0.7060	1000.000	0.3976	1900.000	0.3239
120.000	0.7018	1020.000	0.3907	1920.000	0.3306
140.000	0.6974	1040.000	0.3839	1940.000	0.3377
160.000	0.6928	1060.000	0.3773	1960.000	0.3453
180.000	0.6879	1080.000	0.3708	1980.000	0.3534
200.000	0.6829	1100.000	0.3644	2000.000	0.3620
220.000	0.6776	1120.000	0.3582	2020.000	0.3711
240.000	0.6721	1140.000	0.3522	2040.000	0.3808
260.000	0.6664	1160.000	0.3463	2060.000	0.3910
280.000	0.6606	1180.000	0.3407	2080.000	0.4017
300.000	0.6546	1200.000	0.3352	2100.000	0.4130
320.000	0.6484	1220.000	0.3299	2120.000	0.4248
340.000	0.6421	1240.000	0.3248	2140.000	0.4372
360.000	0.6356	1260.000	0.3199	2160.000	0.4502
380.000	0.6290	1280.000	0.3153	2180.000	0.4638
400.000	0.6222	1300.000	0.3108	2200.000	0.4779
420.000	0.6153	1320.000	0.3067	2220.000	0.4926
440.000	0.6083	1340.000	0.3027	2240.000	0.5080
460.000	0.6012	1360.000	0.2990	2260.000	0.5240
480.000	0.5940	1380.000	0.2956	2280.000	0.5405
500.000	0.5867	1400.000	0.2924	2300.000	0.5578
520.000	0.5793	1420.000	0.2895	2320.000	0.5756
540.000	0.5719	1440.000	0.2869	2340.000	0.5941
560.000	0.5643	1460.000	0.2846		
580.000	0.5567	1480.000	0.2826		
600.000	0.5491	1500.000	0.2809		
620.000	0.5414	1520.000	0.2795		
640.000	0.5337	1540.000	0.2784		
660.000	0.5259	1560.000	0.2777		
680.000	0.5182	1580.000	0.2773		
700.000	0.5104	1600.000	0.2773		
720.000	0.5026	1620.000	0.2776		
740.000	0.4948	1640.000	0.2783		
760.000	0.4870	1660.000	0.2793		
780.000	0.4793	1680.000	0.2808		
800.000	0.4715	1700.000	0.2826		
820.000	0.4639	1720.000	0.2848		
840.000	0.4562	1740.000	0.2874		
860.000	0.4486	1760.000	0.2905		
880.000	0.4411	1780.000	0.2939		
900.000	0.4336	1800.000	0.2978		




Figure I-3.4 The Total Emissivity of Polycrystalline Magnesium Oxide as a Function of Temperature

I-3.5 Reflectance — Magnesium Oxide

Figure I-3.5a presents the representative curve for single crystal MgO at T = 300°K as measured by Hanna (Ref. 3R-7). Figures I-3.5b and c, measured by Piriou (Ref. 3R-13), are taken as representative for this material for 1080 and 2225°K.

Measurements of the reflectivity of polycrystalline MgO and MgO powder are shown in Figures I-3.5d and I-3.5e, respectively, for T = 300°K. No high temperature measurements were found in the literature. No polycrystalline data beyond 2μ were found, or powder reflectance data at wavelengths longer than 14μ.

Not included in the representative data are the measurements by Arlt (Ref. 3R-2) of the angular spectral reflectivity of MgO powders, which are presented in Section III-3.5.


Table I-3.5 Magnesium Oxide Reflectivity — Representative Data


a) Single Crystal Magnesia, T = 300°K


λ	R	λ	R	λ	R
2.654	5.758E+00	2.876	5.758E+00	3.023	5.761E+00
3.246	5.709E+00	3.544	5.676E+00	3.924	5.632E+00
4.339	5.557E+00	4.954	5.444E+00	5.499	5.258E+00
6.123	4.941E+00	6.796	4.503E+00	7.414	4.031E+00
8.085	3.463E+00	8.748	2.763E+00	9.470	1.805E+00
10.167	7.191E-01	10.526	5.186E-02	11.595	2.343E+00
12.942	8.201E+00	14.572	2.620E+01	15.894	3.519E+01
15.338	3.719E+01	16.108	3.779E+01	16.734	3.894E+01
17.356	4.169E+01	18.023	4.587E+01	19.530	4.746E+01
19.530	5.820E+01	21.286	6.860E+01	23.466	8.898E+01
23.466	7.725E+01	26.126	7.291E+01	29.208	4.903E+01
29.325	6.577E+01	39.030	3.346E+01	39.046	4.436E+01
46.523	3.695E+01	58.091	2.859E+01	58.307	3.221E+01
77.630	2.901E+01	118.415	2.612E+01	120.922	2.782E+01


b) Single Crystal Magnesia, T = 1080°K


λ	R	λ	R	λ	R
33.210	2.423E+01	31.472	2.287E+01	31.168	2.485E+01
29.184	2.713E+01	23.485	2.898E+01	27.941	3.129E+01
27.393	3.433E+01	26.884	3.654E+01	26.362	3.931E+01
25.821	4.138E+01	25.473	4.302E+01	25.031	4.386E+01
24.432	4.497E+01	23.357	4.564E+01	23.164	4.548E+01
22.040	4.537E+01	21.608	4.555E+01	21.034	4.530E+01
20.338	4.355E+01	19.924	4.413E+01	19.354	4.306E+01
19.191	4.241E+01	18.744	4.146E+01	18.457	4.071E+01
18.103	3.922E+01	17.969	3.838E+01	17.659	3.692E+01
17.344	3.574E+01	17.274	3.471E+01	17.085	3.337E+01
16.868	3.161E+01	16.722	3.082E+01	16.490	2.921E+01
16.307	2.828E+01	16.162	2.792E+01	15.951	2.780E+01
15.712	2.778E+01	15.479	2.779E+01	15.172	2.748E+01
14.936	2.632E+01	14.632	2.514E+01	14.390	2.163E+01
14.152	1.859E+01	14.044	1.573E+01	13.891	1.304E+01
13.783	9.971E+00	13.637	8.895E+00	13.418	4.069E+00
13.273	2.926E+00	13.175	1.733E+00	12.927	1.281E+00
12.741	5.359E-01	12.492	5.355E-01	12.009	3.972E-01
11.193	3.972E-01	10.850	5.269E-01	10.405	7.296E-01
9.388	1.167E+00	9.403	1.451E+00		


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.5A
MAGNESIUM OXIDE. SINGLE CRYSTAL
T=300K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.5A
MAGNESIUM OXIDE. SINGLE CRYSTAL
T=300K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.5A
MAGNESIUM OXIDE. SINGLE CRYSTAL
T=300K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.58
MAGNESIUM OXIDE, SINGLE CRYSTAL
T=1080K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
60
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.58
MAGNESIUM OXIDE, SINGLE CRYSTAL
T=1080K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


Tab. I-3.5 (Continued)

c) Single Crystal Magnesia, T = 2225°K

λ	R	λ	R	λ	R
33.293	2.415E+01	31.854	2.604E+01	30.978	2.827E+01
32.000	3.133E+01	29.229	3.234E+01	28.495	3.450E+01
27.522	3.635E+01	26.794	3.760E+01	26.154	3.843E+01
25.435	3.837E+01	24.986	3.916E+01	24.546	3.900E+01
23.911	3.853E+01	22.463	3.734E+01	21.515	3.586E+01
20.775	3.437E+01	20.146	3.311E+01	19.460	3.144E+01
18.342	2.955E+01	18.326	2.765E+01	17.783	2.607E+01
17.585	2.536E+01	17.218	2.491E+01	17.020	2.459E+01
16.917	2.417E+01	16.454	2.397E+01	16.094	2.316E+01
15.314	2.259E+01	15.563	2.112E+01	15.470	2.037E+01
15.223	1.875E+01	15.127	1.772E+01	14.917	1.605E+01
14.859	1.522E+01	14.738	1.316E+01	14.679	1.232E+01
14.537	1.031E+01	14.492	9.679E+00	14.322	7.855E+00
14.271	7.612E+00	14.132	5.164E+00	14.044	4.458E+00
13.909	3.616E+00	13.750	2.302E+00	13.512	1.305E+00
13.381	1.623E+00	13.137	6.134E-01	12.508	3.324E-01
11.706	3.324E-01	11.221	3.072E-01	10.824	5.188E-01
10.294	8.187E-01	9.758	1.256E+00	9.400	1.451E+00
9.035	1.678E+00				

d) Polycrystalline Magnesia, T = 300°K

λ	R	λ	R	λ	R	λ	R
.549	8.522E+01	.633	8.546E+01	.657	8.584E+01	.676	8.651E+01
.697	8.822E+01	.714	8.919E+01	.733	8.988E+01	.820	8.986E+01
.923	8.988E+01	1.032	8.988E+01	1.071	9.007E+01	1.116	9.060E+01
1.183	9.117E+01	1.191	9.173E+01	1.247	9.172E+01	1.284	9.201E+01
1.325	9.242E+01	1.397	9.292E+01	1.460	9.358E+01	1.515	9.388E+01
1.562	9.446E+01	1.607	9.482E+01	1.664	9.525E+01	1.706	9.516E+01
1.752	9.537E+01	1.796	9.597E+01	1.788	9.626E+01	1.819	9.607E+01
1.853	9.551E+01	1.837	9.497E+01	1.911	9.446E+01	1.944	9.508E+01
1.971	9.564E+01	1.986	9.630E+01	2.051	9.630E+01		


REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.5C
MAGNESIUM OXIDE, SINGLE CRYSTAL
T=2225K
REFRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
90
80
70
60
50
40
30
20
10



REFLECTIVITY OF MAGNESIUM OXIDE
FIGURE 1-3.5C
MAGNESIUM OXIDE, SINGLE CRYSTAL
T=2225K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
90
80
70
60
50
40
30
20
10

Table I-3.5 (Continued)

e) Powdered Magnesia, T = 300°K

λ	R	λ	R	λ	R	λ	R
.666	9.3693E+01	.987	9.670[illegible]+01	1.183	9.663E+01	1.393	9.479E+01
1.062	9.+79[illegible]+01	1.785	9.381[illegible]+01	1.962	9.117E+01	1.963	9.237E+01
2.186	9.343[illegible]+01	2.376	9.099[illegible]+01	2.598	9.072E+01	2.614	8.856E+01
2.662	8.411[illegible]+01	2.787	8.[illegible]+01	2.882	5.043E+01	3.014	4.676E+01
3.197	4.85[illegible]+01	3.333	5.447[illegible]+01	3.600	6.057E+01	3.793	6.307E+01
4.[illegible]	6.252[illegible]+01	4.196	5.088E+01	4.402	5.711E+01	4.597	5.377E+01
4.731	5.23[illegible]+01	5.021	5.106[illegible]+01	5.191	4.873E+01	5.404	4.535[illegible]+01
5.621	4.67[illegible]+01	5.826	3.461[illegible]+01	6.020	2.376E+01	6.197	1.854[illegible]+01
6.443	1.+41[illegible]+01	6.617	7.368[illegible]+00	6.783	6.40[illegible]+00	7.014	6.345[illegible]+00
7.236	5.8[illegible]+00	7.404	8.155[illegible]+00	7.596	1.165E+01	7.810	1.133E+01
8.[illegible]	8.32[illegible]+00	8.457	7.76[illegible]+00	8.985	6.005[illegible]+00	9.494	3.502E+00
10.[illegible]3	[illegible]+00	10.487	9.753[illegible]-01	10.995	1.293E-01	12.038	0.
13.[illegible]2	0.	13.985	7.051[illegible]-02				




FIGURE I-3.5D
MAGNESIUM OXIDE, POLYCRYSTALLINE
T=300K
REPRESENTATIVE DATA




FIGURE I-3.5E
MAGNESIUM OXIDE POWDER
T=300K
REPRESENTATIVE DATA

I-3.6 Transmittance - Magnesium Oxide

Figure I-3.6a and Table I-3.6a present the representative data for bulk magnesia transmittance at T = 300°K. Data are listed in Section III-3.6 for transmittance at temperatures up to 1270°K, over a limited range of wavelengths. These data are composed of three unnormalized sets taken from Oppenheim (Ref. 3T-12), Piriou (Ref. 3T-13) and Hanna (Ref. 3T-6).

Figure I-3.6b and Table I-3.6b present the data of Sirvastava (Ref. 3T-15) for powdered MgO at T = 300°K. No high temperature powder transmission measurements have been found in the literature.

The structure observed in these transmission spectra is defined in Section I-3.7, where principal lattice frequencies and absorption bands are listed.

Table I-3.6a Bulk Magnesium Oxide Transmittance — Representative Data

1μ to 10μ

λ	T	λ	T	λ	T	λ	T
1.239	8.523E+01	2.297	8.646E+01	3.506	8.758E+01	4.011	8.904E+01
4.953	8.665E+01	5.297	8.663E+01	5.751	8.455E+01	6.001	8.274E+01
6.193	7.953E+01	6.193	7.644E+01	6.503	6.890E+01	6.801	5.572E+01
7.435	4.360E+01	7.480	3.395E+01	7.715	2.385E+01	8.019	1.535E+01
8.549	9.259E+00	8.912	7.019E+00	9.241	4.046E+00		


8μ to 12μ


λ	T	λ	T	λ	T
13.536	4.013E-01	13.197	1.229E+00	12.919	3.235E+00
12.772	5.493E+00	12.658	8.352E+00	12.580	1.164E+01
12.466	1.510E+01	12.372	1.781E+01	12.284	1.899E+01
12.228	1.823E+01	12.133	1.543E+01	12.045	1.206E+01
11.948	9.757E+00	11.870	7.550E+00	11.794	6.195E+00
11.711	7.098E+00	11.600	8.151E+00	11.521	8.277E+00
11.437	1.199E+01	11.352	1.430E+01	11.255	1.708E+01
11.195	1.891E+01	11.157	2.212E+01	11.102	2.705E+01
11.058	3.178E+01	11.013	3.725E+01	10.998	3.978E+01
10.954	4.256E+01	10.905	4.490E+01	10.832	4.758E+01
10.783	5.031E+01	10.740	5.272E+01	10.721	5.653E+01
10.723	5.979E+01	10.683	6.178E+01	10.655	6.295E+01
10.571	6.363E+01	10.509	6.333E+01	10.435	6.188E+01
10.377	6.042E+01	10.339	5.811E+01	10.288	5.535E+01
10.260	5.247E+01	10.226	5.011E+01	10.215	4.796E+01
10.159	4.635E+01	10.114	4.740E+01	10.058	4.999E+01
9.983	5.270E+01	9.915	5.631E+01	9.851	6.017E+01
9.778	6.425E+01	9.707	6.807E+01	9.605	7.271E+01
9.501	7.577E+01	9.340	7.878E+01	9.182	8.129E+01
9.044	8.304E+01	8.824	8.452E+01	8.641	8.498E+01
8.463	8.503E+01	8.202	8.503E+01		


Table I-3.6a (Continued)

27μ to 59μ

λ	T	λ	T	λ	T
59.627	4.607E+01	54.964	4.513E+01	52.291	4.427E+01
49.296	4.366E+01	45.865	4.261E+01	44.653	4.190E+01
42.381	4.046E+01	40.565	3.910E+01	38.930	3.723E+01
37.709	3.554E+01	36.068	3.306E+01	34.594	2.974E+01
32.978	2.615E+01	31.515	2.154E+01	30.575	1.772E+01
29.537	1.297E+01	28.874	9.373E+00	28.299	6.023E+00
27.723	2.117E+00	27.591	1.069E+00		


TRANSMITTANCE OF MAGNESIUM OXIDE
FIG. 1-3.6A
MAGNESIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF MAGNESIUM OXIDE
FIG. 1-3.6A
MAGNESIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF MAGNESIUM OXIDE
FIG. I-3.6A
MAGNESIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.




TRANSMITTANCE OF MAGNESIUM OXIDE
FIG. I-3.6A
MAGNESIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


Table I-3.6b Powdered Magnesium Oxide Transmittance – Representative Data

λ	T	λ	T	λ	T
5.044	8.794E+01	5.072	8.788E+01
5.143	8.843E+01	5.196	8.871E+01
5.272	8.792E+01	5.299	8.715E+01
5.367	8.626E+01	5.468	8.626E+01
5.660	8.582E+01	5.659	8.524E+01
5.760	8.288E+01	5.807	8.147E+01
5.898	7.815E+01	5.926	7.613E+01
6.016	7.076E+01	6.050	6.823E+01
6.121	6.592E+01	6.169	6.514E+01
6.249	6.277E+01	6.292	6.066E+01
6.355	5.485E+01	6.392	5.026E+01
6.459	3.899E+01	6.501	3.257E+01
6.579	2.073E+01	6.619	1.471E+01
6.658	1.175E+01	6.665	1.053E+01
6.746	7.170E+00	6.761	7.778E+00
6.815	1.961E+01	6.839	2.349E+01
6.918	2.371E+01	6.943	1.908E+01
6.989	8.594E+00	7.016	6.528E+00
7.069	1.485E+01	7.098	2.196E+01
7.148	3.404E+01	7.159	3.963E+01
7.228	4.755E+01	7.258	5.304E+01
7.328	6.422E+01	7.376	6.993E+01
7.516	7.720E+01	7.604	7.954E+01
7.865	8.330E+01	8.012	8.437E+01
8.294	8.533E+01	8.487	8.484E+01
8.762	8.311E+01	8.817	8.171E+01
8.941	7.746E+01	8.993	7.820E+01
9.047	8.163E+01	9.095	8.240E+01
9.089	8.161E+01	9.661	8.068E+01
9.925	7.921E+01	9.991	7.879E+01
10.056	9.208E+01	10.141	9.115E+01
10.236	8.965E+01	10.352	9.009E+01
10.556	8.942E+01	10.702	8.806E+01
10.912	8.608E+01	10.962	8.476E+01
11.074	8.335E+01	11.113	7.289E+01
11.194	6.640E+01	11.221	7.107E+01
11.347	7.521E+01	11.388	7.475E+01
11.569	6.629E+01	11.627	6.956E+01
11.723	7.419E+01	11.839	7.354E+01
12.093	6.410E+01	12.216	5.977E+01
12.391	5.345E+01	12.495	5.796E+01
12.643	6.385E+01	12.669	6.511E+01
12.899	6.511E+01	13.015	6.256E+01
13.245	5.759E+01	13.445	5.480E+01
13.675	5.044E+01	13.841	4.751E+01
14.255	4.413E+01	14.480	4.091E+01

Table I-3.6b (Continued)

λ	T	λ	T	λ	T
[illegible]	[illegible]	14.953	3.481E+01	13.232	3.285E+01
15.[illegible]	3.[illegible]	15.957	3.161E+01	15.997	8.026E+01
16.[illegible]	7.[illegible]	16.3u2	6.645E+01	16.448	5.998E+01
16.[illegible]	[illegible]	16.893	5.483E+01	17.016	5.554E+01
17.222	[illegible]	17.519	5.812E+01	17.821	5.828E+01
18.191	[illegible]	18.515	5.573E+01	18.634	5.464E+01
18.897	5.[illegible]	19.259	4.725E+01	19.562	4.332E+01
19.737	3.[illegible]	19.961	3.761E+01	20.239	3.565E+01
[illegible]	3.[illegible]	21.u36	3.225E+01	21.448	3.099E+01
21.823	2.[illegible]	22.129	2.883E+01	22.586	2.800E+01
23.[illegible]	2.877E+01	23.099	3.050E+01	23.296	3.920E+01
24.[illegible]	3.[illegible]	24.939	3.989E+01	24.143	4.364E+01
[illegible]	[illegible]	25.352	5.424E+01	25.675	5.181E+01
26.[illegible]	[illegible]	26.512	5.483E+01	27.022	5.070E+01
27.[illegible]	6.[illegible]	27.823	7.055E+01	28.247	7.604E+01
28.734	8.[illegible]	29.336	9.411E+01	29.539	9.748E+01
[illegible]	9.[illegible]	30.898	9.854E+01	31.236	9.728E+01
31.[illegible]	7.[illegible]				


TRANSMITTANCE OF MAGNESIUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
FIGURE I-3.68
MAGNESIUM OXIDE POWDER
T=300K
REPRESENTATIVE DATA


TRANSMITTANCE OF MAGNESIUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
FIGURE I-3.68
MAGNESIUM OXIDE POWDER
T=300K
REPRESENTATIVE DATA

I-3.7 Classical Oscillator Frequency and Observed Absorption Peaks of MgO

These data were compiled from Gourley (Ref. 3T-4), Piriou (Ref. 3T-13), Srivastava (Ref. 3T-15), and Saksena (Ref. 3R-15). Redundant measurements or calculations have not been removed.

λ (μ)	ν (cm^{-1})	Comments	Reference
27.36	365.5	T=77°K, med. strength	3T-13
27.03	370	2-phonon band	3T-15
25.26	395.88	principal lattice freq. (calc.)	3R-15
23.81	420	2-phonon band	3T-15
22.47	445	2-phonon band	3T-15
20.41	490	2-phonon band	3T-15
16.95	590	2-phonon band	3T-15
15.87	630	2-phonon band	3T-15
15.55	643	T=77°K	3T-13
15.22	657	IR active mode	3T-4
14.72	670	multiple phonon band	3T-15
14.35	697	IR active mode	3T-4
13.89	720	multiple phonon band	3T-15
13.74	728	IR active mode	3T-4
13.53	739	IR active mode	3T-4
13.51	740	IR active mode	3T-4
13.40	746	IR active mode	3T-4

$\lambda(\mu)$	$\nu(cm^{-1})$	Comments	Reference
13.16	760	multiple phonon band	3T-15
12.82	780	T=77°K, weak	3T-13
12.80	781	IR active mode	3T-4
12.76	784	T=300°K, weak	3T-13
12.69	788	IR active mode	3T-4
12.34	810	2 phonon band	3T-15
12.29	814	IR active mode	3T-4
12.06	821	IR active mode	3T-4
12.17	822	IR active mode	3T-4
12.08	828	T=77°K, weak	3T-13
12.08	828	IR active mode	3T-4
11.82	846	T=300°K, strong	3T-13
11.82	846	IR active mode	3T-4
11.72	853	T=77°K, strong	3T-13
11.63	860	2 phonon band	3T-15
11.63	860	IR active mode	3T-4
11.60	862	T=300°K, strong	3T-13
11.52	868	T=77°K, strong	3T-13
11.31	884	T=77°K, weak	3T-13
11.29	886	IR active mode	3T-4
11.24	890	2 phonon band	3T-15
11.22	891	IR active mode	3T-4
11.19	894	T=300°K, medium	3T-13
11.16	896	T=77°K, medium	3T-13
11.14	898	IR active mode	3T-4

λ (μ)	ν (cm^{-1})	Comments	Reference
10.33	923	IR active mode	3T-4
10.80	926	T=300°K, medium	3T-13
10.74	931	T=77°K, medium	3T-13
10.71	934	IR active mode	3T-4
10.60	943	IR active mode	3T-4
10.26	975	multiple phonon band	3T-15
10.18	982	T=300°K, strong	3T-13
10.15	985	IR active mode	3T-4
10.14	986	T=77°K, strong	3T-13
10.00	1000		
9.90	1010	T=300°K, weak	3T-13
9.84	1016	T=77°K, weak	3T-13
9.09 to 9.26	1080 to 1100	T=77°K, 300°K, medium	3T-13
8.97	1115	multiple phonon band	3T-15
8.88	1126	IR active mode	3T-4
8.87	1127	IR active mode	3T-4
8.00 to 8.33	1200 to 1250	T=77°K, 300°K, strong	3T-13
7.25	1380	multiple phonon band	3T-15
7.15	1400	T=77°K, 300°K, medium	3T-13
7.02	1425	multiple phonon band	3T-15
6.76	1480	multiple phonon band	3T-15
6.67	1500	multiple phonon band	3T-15
6.60	1515	multiple phonon band	3T-15
6.10	1640	multiple phonon band	3T-15
5.41	1850	multiple phonon band	3T-15

I-3.8 Conclusions: Areas Needing Further Research

a) Refractive Index – no measurements for powdered MgO at any temperature have been made.

b) Extinction Index – for single crystal MgO and polycrystalline MgO, the region from 55μ to 90μ has been inadequately surveyed. Data for powdered MgO at all temperatures and wavelengths are needed.

c) Spectral Emissivity – room temperature measurements for bulk MgO are needed, and also measurements for powdered MgO over the entire temperature and wavelength ranges.

d) Total Normal Emissivity – no data for powdered MgO have been found.

I-4 ZIRCONIUM DIOXIDE PROPERTIES

I-4.1 Refractive Index, n-Zirconium Dioxide


No data on the refractive index of zirconium dioxide were found.

I-4.2 Extinction Index, k-Zirconium Dioxide

The only value of k located in this literature search is that of Piriou (Ref. 4K-1). His data are for monoclinic ZrO_2 from 5μ to 7μ at $300^{\circ}K$, and are shown in Figure I-4.2 and tabulated in Table I-4.2

Table I-4.2 Zirconium Dioxide Extinction Index — Representative Data

λ	k	λ	k	λ	k	λ	k
5.503	2.853E-05	5.998	7.482E-05	6.496	2.465E-04	6.995	8.025E-04
7.359	8.229E-04	7.255	7.650E-04	7.366	9.250E-04	7.508	1.354E-03
7.741	2.200E-03	8.011	3.340E-03	8.345	4.614E-03	8.587	4.206E-03
8.996	6.174E-03	9.556	2.544E-02				


EXTINCTION INDEX OF ZIRCONIUM OXIDE
FIGURE I-4.2
ZIRCONIUM OXIDE
T=300K
REPRESENTATIVE DATA
EXTINCTION INDEX, K
1E-1
1E-2
1E-3
1E-4
1E-5
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

I-4.3 Spectral Emissivity, $\epsilon(\lambda)$- Zirconium Dioxide

Figures I-4.3a, b, c show the values of $\epsilon(\lambda)$ at T=1200, 1400, and 1600°K measured by Clark and Moore (Ref. 4SE-5) for cubic-stabilized zirconia. These data are in fair agreement with the other published values of $\epsilon(\lambda)$, which are presented in graphic and tabular form, except that the minimum shown at 2μ was not observed by Blau (Ref 4SE-2). Two possible reasons for this discrepancy are differences in spectrometer bandpass or crystal lattice structure. Clark and Moore (Ref. 4SE-5) described the effects of inadequately stabilized cubic ZrO_2 at 1600°K as being an increased emittance at short wavelengths with a corresponding long wavelength decrease. Figure I-4.3d shows the variation of $\epsilon(\lambda)$ with T for several wavelengths, and suggests a minimum near 1100°K at short wavelengths. The existing data are not sufficiently accurate and/or detailed to adequately determine this variation, however.

It should be noted that in general, emissivity data is dependent on such sample properties as porosity, density, and surface preparation, making application of such data to samples that differ from the original rather uncertain in accuracy. Wherever possible, emissivity data will describe in detail the sample studied.

Table I-4.3 Zirconium Dioxide Spectral Emissivity — Representative Data

a. T = 1200°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.193	[illegible]	.148	2.[illegible]	.129	2.[illegible]	.131
3.[illegible]	.237	[illegible]	.1[illegible]	[illegible]	.187	4.[illegible]	.266
[illegible]	.416	[illegible]	.5537	6.[illegible]	.623[illegible]	6.[illegible]	.713
[illegible]	.791	[illegible]	.8555	[illegible]	.892	[illegible]	.876
[illegible]	.913	[illegible]	.9333	10.[illegible]	.949	[illegible]	.957
12.[illegible]	.951	11.[illegible]	.9644	12.[illegible]	.970[illegible]	12.[illegible]	.974
13.[illegible]	.972	[illegible]	.975	14.[illegible]	.935	14.[illegible]	.893
[illegible]	.844						

b. T = 1400°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.247	[illegible]	.192	2.[illegible]	.172	2.[illegible]	.172
3.[illegible]	.277	[illegible]	.188	[illegible]	.222	4.[illegible]	.308
[illegible]	.[illegible]	[illegible]	.[illegible]	[illegible]	.555[illegible]	[illegible]	.744
[illegible]	.8[illegible]	[illegible]	.8872	[illegible]	.902[illegible]	[illegible]	.885
[illegible]	.942[illegible]	[illegible]	.9472	[illegible]	.954[illegible]	1[illegible]	.960[illegible]
[illegible]	.9[illegible]	11.[illegible]	.9668	12.[illegible]	.973	12.[illegible]	.977
13.[illegible]	.373	12.[illegible]	.962	14.[illegible]	.938	14.[illegible]	.902
1[illegible]	.852						

c. T = 1600°K

λ	ε	λ	ε	λ	ε	λ	ε
[illegible]	.237	[illegible]	.2[illegible]	2.[illegible]	.2[illegible]	2.[illegible]	.243
[illegible]	.3[illegible]	[illegible]	.8[illegible]	4.[illegible]	.262	[illegible]	.336
[illegible]	.[illegible]	[illegible]	.87[illegible]	6.[illegible]	.907[illegible]	[illegible]	.760[illegible]
[illegible]	.[illegible]	[illegible]	.9[illegible]	8.[illegible]	.96[illegible]	[illegible]	.882
3.[illegible]	.3[illegible]	[illegible]	.9[illegible]	10.[illegible]	.952	1[illegible]	.957
11.[illegible]	.[illegible]	[illegible]	.95[illegible]	12.[illegible]	.968[illegible]	12.[illegible]	.959
13.[illegible]	.367	[illegible]	.9[illegible]	14.[illegible]	.935	14.[illegible]	.90[illegible]
1[illegible]	.85[illegible]						




FIGURE I-4.3A
ZIRCONIUM OXIDE
T=1200K
REPRESENTATIVE DATA





FIGURE I-4.3B
ZIRCONIUM OXIDE
T=1400K
REPRESENTATIVE DATA


SPECTRAL EMISSIVITY OF ZIRCONIUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE I-4.3C
ZIRCONIUM OXIDE
TF1600K
REPRESENTATIVE DATA




Figure I-4.3d. Variation of $\epsilon(\lambda)$ With Temperature. Closed Circles are Clark (Ref. 4SE-5), Open Circles are Blau (Ref. 4SE-2), and Triangles are Backhund (Ref. 4SE-1).

I-4.4 Total Normal Emittance: $\epsilon(T)$—Zirconium Dioxide

Four sets of total normal emittance measurements for zirconia either pure or in calcia- or magnesia-stabilized forms have been found in the literature, and are in good agreement. The experimental error limit of $\pm$ 0.05 in $\epsilon(T)$ as reported by Hedge (Ref. 4TE-1) is probably representative of all the data. Figure I-4.4 shows all the experimental data points and a fitted third-order polynomial curve, which is tabulated in Table I-4.4.

$\epsilon(T)$ varies from approximately 0.8 at 50°K through an apparent minimum of about 0.4 between 1100 and 1600°K, to over 0.5 at 2500°K. No explanation of the minimum has been found in the literature.

All digitized data in the tables in Section III-4.4 were transcribed directly from the experimental points shown explicitly in the literature, not from fitted curves.

Table I-4.4a Representative Values of ε(T) of Zirconia to 2400°K, Obtained from a Third-Order Polynominal fit to all Experimentally Measured Points

T(°K)	ε(T)	T(°K)	ε(T)	T(°K)	ε(T)
200	0.0	1000	0.0	1800	0.0
210	0.0	1010	0.0	1810	0.0
220	0.0	1020	0.0	1820	0.0
230	0.0	1030	0.0	1830	0.0
240	0.0	1040	0.0	1840	0.0
250	0.0	1050	0.0	1850	0.0
260	0.0	1060	0.0	1860	0.0
270	0.0	1070	0.0	1870	0.0
280	0.0	1080	0.0	1880	0.0
290	0.0	1090	0.0	1890	0.0
300	0.0	1100	0.0	1900	0.0
310	0.0	1110	0.0	1910	0.0
320	0.0	1120	0.0	1920	0.0
330	0.0	1130	0.0	1930	0.0
340	0.0	1140	0.0	1940	0.0
350	0.0	1150	0.0	1950	0.0
360	0.0	1160	0.0	1960	0.0
370	0.0	1170	0.0	1970	0.0
380	0.0	1180	0.0	1980	0.0
390	0.0	1190	0.0	1990	0.0
400	0.0	1200	0.0	2000	0.0
410	0.0	1210	0.0	2010	0.0
420	0.0	1220	0.0	2020	0.0
430	0.0	1230	0.0	2030	0.0
440	0.0	1240	0.0	2040	0.0
450	0.0	1250	0.0	2050	0.0
460	0.0	1260	0.0	2060	0.0
470	0.0	1270	0.0	2070	0.0
480	0.0	1280	0.0	2080	0.0
490	0.0	1290	0.0	2090	0.0
500	0.0	1300	0.0	2100	0.0
510	0.0	1310	0.0	2110	0.0
520	0.0	1320	0.0	2120	0.0
530	0.0	1330	0.0	2130	0.0
540	0.0	1340	0.0	2140	0.0
550	0.0	1350	0.0	2150	0.0
560	0.0	1360	0.0	2160	0.0
570	0.0	1370	0.0	2170	0.0
580	0.0	1380	0.0	2180	0.0
590	0.0	1390	0.0	2190	0.0
600	0.0	1400	0.0	2200	0.0
610	0.0	1410	0.0	2210	0.0
620	0.0	1420	0.0	2220	0.0
630	0.0	1430	0.0	2230	0.0
640	0.0	1440	0.0	2240	0.0
650	0.0	1450	0.0	2250	0.0
660	0.0	1460	0.0	2260	0.0
670	0.0	1470	0.0	2270	0.0
680	0.0	1480	0.0	2280	0.0
690	0.0	1490	0.0	2290	0.0
700	0.0	1500	0.0	2300	0.0
710	0.0	1510	0.0	2310	0.0
720	0.0	1520	0.0	2320	0.0
730	0.0	1530	0.0	2330	0.0
740	0.0	1540	0.0	2340	0.0
750	0.0	1550	0.0	2350	0.0
760	0.0	1560	0.0	2360	0.0
770	0.0	1570	0.0	2370	0.0
780	0.0	1580	0.0	2380	0.0
790	0.0	1590	0.0	2390	0.0
800	0.0	1600	0.0	2400	0.0
810	0.0	1610	0.0		
820	0.0	1620	0.0		
830	0.0	1630	0.0		
840	0.0	1640	0.0		
850	0.0	1650	0.0		
860	0.0	1660	0.0		
870	0.0	1670	0.0		
880	0.0	1680	0.0		
890	0.0	1690	0.0		
900	0.0	1700	0.0		
910	0.0	1710	0.0		
920	0.0	1720	0.0		
930	0.0	1730	0.0		
940	0.0	1740	0.0		
950	0.0	1750	0.0		
960	0.0	1760	0.0		
970	0.0	1770	0.0		
980	0.0	1780	0.0		
990	0.0	1790	0.0		

Reproduced from best available copy.





Figure I-4.4 The Total Emissivity of Zirconia as a Function of Temperature -- Representative Data


I-4.5 Reflectance - Zirconium Dioxide

Figure I-4.5 shows the data of Clark (Ref. 4R-1) and Piriou (Ref. 4R-3) for monoclinic zirconia at 300°K. Reflectance spectra for the metastable cubic phase may be seen in Section III-4.5. No data from 2.5μ to 9μ were found in the literature, and no data for temperatures other than 300°K were obtained.

Table I-4 5 Zirconium Dioxide Reflectivity – Representative Data

λ	R	λ	R	λ	R
.268	1.193E+01	.29	1.263E+01	.311	1.453E+01
.332	1.709E+01	.34	2.088E+01	.364	2.329E+01
.379	2.704E+01	.406	3.536E+01	.421	4.319E+01
.43	4.042E+01	.456	5.527E+01	.473	6.217E+01
.482	6.875E+01	.533	7.470E+01	.564	7.980E+01
.611	8.299E+01	.646	8.347E+01	.686	8.732E+01
.744	8.839E+01	.816	8.930E+01	.896	9.018E+01
.901	9.102E+01	1.032	9.156E+01	1.086	9.123E+01
1.115	9.131E+01	1.148	9.226E+01	1.206	9.264E+01
1.288	9.277E+01	1.353	9.338E+01	1.418	9.334E+01
1.422	9.375E+01	1.483	9.321E+01	1.493	9.265E+01
1.527	9.139E+01	1.529	9.239E+01	1.542	9.308E+01
1.557	9.301E+01	1.666	9.367E+01	1.634	9.393E+01
1.691	9.429E+01	1.680	9.549E+01	1.703	9.579E+01
1.733	9.504E+01	1.787	9.584E+01	1.837	9.580E+01
1.894	9.597E+01	1.884	9.564E+01	1.911	9.552E+01
1.935	9.595E+01	1.963	9.670E+01	2.008	9.672E+01
2.020	9.670E+01	2.097	9.662E+01	9.102	5.754E+00
9.243	5.738E+00	9.363	5.541E+00	9.554	5.361E+00
9.774	5.148E+00	9.899	4.754E+00	10.072	4.459E+00
10.259	4.066E+00	10.499	3.410E+00	10.721	2.883E+00
10.937	2.311E+00	11.154	2.049E+00	11.323	1.689E+00
11.455	1.311E+00	11.647	8.197E-01	11.832	5.246E-01
11.933	2.459E-01	12.018	6.557E-02	12.097	2.131E-01
12.172	1.197E+00	12.272	2.131E+00	12.369	3.016E+00
12.421	3.238E+00	12.522	3.574E+00	12.592	3.918E+00
12.651	4.525E+00	12.713	5.541E+00	12.785	7.721E+00
12.875	1.121E+01	12.958	1.449E+01	13.026	1.730E+01
13.079	2.036E+01	13.124	2.236E+01	13.173	2.457E+01
13.262	2.755E+01	13.337	2.957E+01	13.412	3.164E+01
13.522	3.219E+01	13.711	3.380E+01	13.918	3.602E+01
14.133	3.841E+01	14.279	4.031E+01	14.362	4.166E+01
14.470	4.335E+01	14.542	4.531E+01	14.645	4.901E+01
14.755	5.241E+01	14.859	5.719E+01	14.912	5.993E+01
14.989	6.203E+01	15.064	6.446E+01	15.159	6.510E+01
15.324	6.609E+01	15.525	6.846E+01	15.742	6.959E+01
15.938	7.113E+01	16.260	7.279E+01	16.484	7.427E+01
16.508	7.469E+01	16.711	7.495E+01	16.895	7.481E+01
16.973	7.448E+01	17.096	7.328E+01	17.156	7.208E+01
17.223	7.015E+01	17.300	6.768E+01	17.380	6.505E+01
17.444	6.198E+01	17.529	6.000E+01	17.599	5.735E+01
17.661	5.436E+01	17.711	5.177E+01	17.746	4.838E+01
17.798	4.544E+01	17.805	4.192E+01	17.849	4.054E+01
17.932	3.962E+01	17.964	4.074E+01	18.011	4.219E+01
18.070	4.449E+01	18.137	4.853E+01	18.183	5.246E+01
18.249	5.632E+01	18.327	6.049E+01	18.380	6.453E+01


REFLECTIVITY OF ZIRCONIUM OXIDE
FIGURE 1-4.5
ZIRCONIUM OXIDE
T=300K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFLECTIVITY OF ZIRCONIUM OXIDE
FIGURE 1-4.5
ZIRCONIUM OXIDE
T=300K
REPRESENTATIVE DATA
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

I-4.6. Transmittance - Zirconium Dioxide

Unnormalized representative data for monoclinic zirconia transmittance are listed in Table I-4.6a and b, and shown in Figures I-4.6a and b. The data from 1μ to 9μ were measured by Piriou (Ref. 4T-6), and from 12μ to 36μ by Baun (Ref. 4T-1). The wavelengths of the absorption bands of ZrO_2 having cubic, tetragonal, strained monoclinic, and monoclinic structures are tabulated in Section I-4.8.

Table I-4.6 Zirconium Dioxide Transmittance-Representative Data


a.


λ	T	λ	T	λ	T	λ	T
1.315	7.968E+01	1.737	8.047E+01	2.378	8.104E+01	3.180	8.174E+01
3.473	9.220E+01	3.838	8.241E+01	4.162	8.230E+01	4.568	8.188E+01
5.041	8.150E+01	5.458	8.062E+01	5.720	7.967E+01	5.918	7.820E+01
5.019	7.743E+01	6.128	7.597E+01	6.196	7.485E+01	6.293	7.308E+01
6.377	7.070E+01	6.460	6.785E+01	6.559	6.480E+01	6.633	6.057E+01
6.721	5.671E+01	6.799	5.154E+01	6.865	4.757E+01	6.920	4.496E+01
6.979	4.315E+01	7.015	4.264E+01	7.056	4.236E+01	7.093	4.259E+01
7.125	4.369E+01	7.159	4.472E+01	7.190	4.513E+01	7.227	4.545E+01
7.255	4.494E+01	7.294	4.305E+01	7.325	4.159E+01	7.334	3.904E+01
7.365	3.574E+01	7.411	3.190E+01	7.456	2.893E+01	7.509	2.619E+01
7.575	2.336E+01	7.635	2.011E+01	7.697	1.702E+01	7.784	1.417E+01
7.892	1.082E+01	7.980	8.188E+00	8.051	6.227E+00	8.087	4.688E+00
8.157	3.759E+00	8.241	3.242E+00	8.341	2.937E+00	8.404	3.137E+00
8.477	3.501E+00	8.563	3.771E+00	8.641	3.242E+01	8.765	2.796E+00
8.878	1.950E+00	8.972	1.386E+00	9.065	6.579E-01		


Table I-4.6 (Continued)

b.

λ	R	λ	R	λ	R
12.616	5.288E+01	12.694	5.585E+01	12.778	5.295E+01
12.854	5.121E+01	12.932	5.035E+01	13.017	5.115E+01
13.074	5.227E+01	13.170	5.364E+01	13.283	5.560E+01
13.388	5.763E+01	13.454	6.013E+01	13.586	6.263E+01
13.689	6.531E+01	13.776	6.740E+01	13.879	6.942E+01
13.986	7.135E+01	14.184	7.387E+01	14.246	7.402E+01
14.353	7.367E+01	14.510	7.250E+01	14.668	7.101E+01
14.810	6.894E+01	14.957	6.638E+01	15.114	6.347E+01
15.283	6.075E+01	15.440	5.765E+01	15.601	5.478E+01
15.777	5.164E+01	15.969	4.769E+01	16.152	4.385E+01
16.370	3.957E+01	16.550	3.598E+01	16.727	3.283E+01
16.943	3.142E+01	17.109	3.212E+01	17.265	3.489E+01
17.443	3.756E+01	17.616	4.116E+01	17.814	4.551E+01
17.981	4.930E+01	18.155	5.252E+01	18.247	5.327E+01
18.455	5.393E+01	18.606	5.316E+01	18.801	4.904E+01
18.966	4.556E+01	19.283	3.085E+01	19.397	3.579E+01
19.558	3.232E+01	19.679	3.144E+01	19.871	3.027E+01
19.978	2.840E+01	20.081	2.639E+01	20.265	2.542E+01
20.464	2.494E+01	20.628	2.483E+01	20.939	2.544E+01
21.215	2.658E+01	21.481	2.820E+01	21.808	3.107E+01
22.115	3.374E+01	22.287	3.598E+01	22.442	3.721E+01
22.588	3.741E+01	22.715	3.623E+01	22.786	3.374E+01
22.942	3.229E+01	23.231	3.076E+01	23.529	2.968E+01
23.865	2.907E+01	24.284	2.972E+01	24.731	3.139E+01
25.069	3.374E+01	25.460	3.691E+01	25.757	3.987E+01
26.074	4.383E+01	26.480	4.830E+01	26.862	5.380E+01
27.281	5.725E+01	27.588	5.862E+01	27.920	5.908E+01
28.173	5.812E+01	28.334	5.305E+01	28.439	4.926E+01
28.697	4.846E+01	28.956	4.868E+01	29.151	4.914E+01
29.301	4.852E+01	29.456	4.777E+01	29.703	4.751E+01
30.044	4.769E+01	30.369	4.922E+01	30.926	5.230E+01
31.593	5.501E+01	32.332	5.765E+01	33.150	5.995E+01
34.028	6.162E+01	34.942	6.290E+01	36.193	6.430E+01


TRANSMITTANCE OF ZIRCONIUM OXIDE
FIG. 1-4.6A
ZIRCONIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ZIRCONIUM OXIDE
FIG. 1-4.6B
ZIRCONIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ZIRCONIUM OXIDE
FIG. I-4.68
ZIRCONIUM OXIDE
T=300 K
REPRESENTATIVE DATA
UNNORMALIZED TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

I-4.7 Observed Absorption Peaks of Zirconium Oxide

These data were compiled from Baun (Ref. 4T-1), Phillippi (Ref. 4T-5) and Piriou (Ref. 4T-6). Redundant data have not been removed.

W(μ)	F(cm^{-1})	Comments	Reference
7.0	1428.6	monoclinic	4T-6
8.1	1234.6	monoclinic	4T-6
12.66±0.16	790±10	monoclinic	4T-6
13.42	745	monoclinic	4T-1
13.51	740	strained monoclinic	4T-5
13.51	740	monoclinic	4T-5
14.29±0.20	700±10	monoclinic	4T-6
16.12	620	shoulder; monoclinic	4T-1
16.13	620	monoclinic	4T-5
17.24	580	strained monoclinic	4T-5
17.25±0.29	580±10	monoclinic	4T-6
17.39	575	tetragonal	4T-5
18.87	530	high intensity, broad; monoclinic	4T-1
19.42	515	monoclinic	4T-5
19.61	510	tetragonal	4T-5
19.61	510	strained monoclinic	4T-5
20.63±0.43	485±10	monoclinic	4T-6
20.83	480	broad minimum; cubic	4T-5
22.22	450	low intensity; monoclinic	4T-1
22.47	445	monoclinic	4T-5
22.49±0.50	445±10	monoclinic	4T-6
22.99	435	tetragonal	4T-5
23.53	425	strained monoclinic	4T-5
23.81	420	low intensity; monoclinic	4T-1
24.10	415	monoclinic	

Table I-4.7 (Continued)

W(μ)	F(cm^{-1})	Comments	Reference
24.41±0.59	410±10	monoclinic	4T-6
26.67	375	low intensity; monoclinic	4T-1
26.67	375	monoclinic	4T-5
26.68±0.71	375±10	monoclinic	4T-6
27.40	365	tetragonal	4T-5
27.78	360	shoulder; monoclinic	4T-1
27.78	360	strained monoclinic	4T-5
27.78	360	monoclinic	4T-5
37.04	270	monoclinic	4T-5
37.74	265	strained monoclinic	4T-5
37.88	264	monoclinic	4T-1
42.55	235	monoclinic	4T-5
43.48	230	strained monoclinic	4T-5
44.44	225	monoclinic	4T-1

I-4.8 Conclusions: Areas Needing Further Research

So little is known about zirconia that the research areas open for further work are best defined if that which has been measured is summarized.

a. k: Measured from 5μ to 9μ, 300°K for bulk monoclinic ZrO_2.

b. $\epsilon(\lambda)$: Measured well from 1μ to 15μ at 1200°K to 1600°K for bulk calcia stabilized zirconia.

c. $\epsilon(T)$: Well defined to 2386°K.

d. Reflectance: Bulk zirconia 0.2μ to 2.2μ and 9μ to 33μ. No data from 2.5μ to 9.0μ. All at 300°K.

e. Transmittance: Bulk monoclinic zirconia, 1μ to 9μ and powdered zirconia 11μ to 33μ. No 9μ to 11μ data of any kind for monoclinic zirconia. One measurement of 9μ to 11μ transmittance for cubic zirconia.

II-1. BIBLIOGRAPHY, ALUMINUM OXIDE

II-1.1 Refractive Index, n - Aluminum Oxide

1N-1 Häfele, H.G., "Das infrarotspecktrum des rubins," Z. fur Naturforsch. 18a, 331 (1963).

1N-2 Harris, L., and Piper, J., "Transmittance and Reflectance of Aluminum-Oxide Films in the Far Infrared," J. Opt. Soc. Am. 52, 223 (1962).

1N-2.5 Herzberger, M., and Salzberg, C., "Refractive Indices of Infrared Optical Materials and Color Correction of Infrared Lenses", J. Opt. Soc. Am. 52, 420 (1962).

1N-3 Loewenstein, E. V., Smith, D. R., Morgan, R. L., "Optical Constants of Far Infrared Materials, 2: Crystalline Solids," App. Opt. 12, 398 (1973).

1N-4 Malitson, I. H., Murphy, F. V., Rodney, W. S., "Refractive Index of Synthetic Sapphire," J. Opt. Soc. Am. 48, 72 (1958).

1N-5 Malitson, I. H., "Refraction and Dispersion of Synthetic Sapphire," J. Opt. Soc. Am. 52, 1377 (1962).

1N-6 Moses, A. J., "Refractive Index of Optical Materials in the Infrared Region," Hughes DS-166 (1970).

1N-7 Neuberger, M., "Optical Properties and Thermal Conductivity of Aluminum Oxide," Hughes Aircraft Co., Epic Report No. S-6, (1965).

1N-8 Olt, F. D., "Synthetic Sapphire, An Infrared Optical Material," Proc. IRIS 3, 141 (1958).

1N-9 Piriou, B., "Etude des bandes de rayons restants de la magnesie et du corindon. Influence de la temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

1N-10 Roberts, S., and Coon, D. D., "Far-Infrared Properties of Quartz and Sapphire," J. Opt. Soc. Am. 52, 1023 (1962).

1N-11 Russell, E. E., and Bell, E. E., "Optical Constants of Sapphire in the Far Infrared," J. Opt. Soc. Am. 57, 543 (1967).

1N-12 Streed, E. R., Cunnington, G. R., Lui, C. K., "Experimental Determination of the Infrared Spectral Optical Properties of Bulk and Powdered Aluminum Oxide," AFRPL-TR-73-3.

II-1.2 Extinction Index, k - Aluminum Oxide

1K-1 Gramm, N., Scott, G. E., Sibold, J. D., "Infrared Transmission Properties of High Density Alumina," Am. Ceram. Soc. Bull. 50, 962 (1971).

1K-2 Gryvnak, D. A., Burch, D. E., "Optical and Infrared Properties of Al_2O_3 at Elevated Temperatures," J. Opt. Soc. Am. 55, 625 (1965).

1K-3 Häfele, H.G., "Das infrarotspektrum des rubins," Z. fur Naturforsch. 18a, 331 (1963).

1K-4 Harris, L., and Piper, J., "Transmittance and Reflectance of Aluminum-Oxide Films in the Far Infrared," J. Opt. Soc. Am. 52, 223 (1962).

1K-5 Loewenstein, E. V., Smith, D. R., Morgan, R. L., "Optical Constants of Far Infrared Materials, 2: Crystalline Solids," Applied Optics 12, 398 (1973).

1K-6 Mergerian, D., "Optical Properties of Infrared-Transparent Solids at Elevated Temperatures," Proc. IRIS 4, 146 (1959).

1K-7 Moses, A. J., "Refractive Index of Optical Materials in the Infrared Region," Hughes DS-166 (1970).

1K-8 Mularz, E. J., Yuen, M. C. "An Experimental Investigation of Radiative Properties of Aluminum Oxide Particles," J. Q.S.R.T. 12, 1553 (1972).

1K-9 Neuberger, M., "Optical Properties and Thermal Conductivity of Aluminum Oxide," Hughes Aircraft Co., Epic Report No. S-6, (1965).

1K-10 Olt, R. D., "Synthetic Sapphire, an Infrared Optical Material," Proc. IRIS 3, 141 (1958).

1K-11 Oppenheim, U. P., Even, U., "Infrared Properties of Sapphire at Elevated Temperatures," J. Opt. Soc. Am. 52, 1078 (1962).

1K-12 Piriou, B., Cabannes, F., "Transmission infrarouge du corindon," C. R. Acad. Sci. Paris 264, 1110 (1967).

1K-13 Piriou, B., "Etude des bandes de rayons restants de la magnesie et du corindon. Influence de la temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

II-1.2 (Continued)

1K-14 Prikhod'ko, L. V., and Bagdasarov, Kh. S., "Infrared Absorption in Corundum at High Temperatures," Sov. Phys. 12, 2049 (1971).

1K-15 Russell, E. E., and Bell, E. E. "Optical Constants of Sapphire in the Far Infrared," J. Opt. Soc. Am. 57, 543 (1967).

1K-16 Streed, E. R., Cunnington, G. R., Lui, C. K., "Experimental Determination of the Infrared Spectral Optical Properties of Bulk and Powdered Aluminim Oxide," AFRPL-TR-73-3.

II-1.3 Spectral Emissivity, $\epsilon(\lambda)$ - Aluminum Oxide

1SE-1 Aronson, J. R., Emslie, A. G., Rooney, T. P., Coleman, I., Horlick, G., "Spectral Emittance and Reflectance of Powders," App. Opt. 8, 1639 (1969).

1SE-2 Aronson, J. R., Emslie, A. G., "The Influence of Physical Variables on Spectral Signatures of Natural Targets," AFCRL-70-0083.

1SE-3 Bergquam, J. B., Seban, R. A., "Spectral Radiation from Alumina Powder on a Metallic Substrate," J. Heat Trans. 94, 36 (1972).

1SE-4 Blau, H. H., Jr., Marsh, J. B., Martin, W. S., Jasperse, J. R., Chaffee, E., "Infrared Spectral Emittance Properties of Solid Materials," AFCRL-TR-60-416.

1SE-5 Blau, H. H., Jr., Jasperse, J. R., "Spectral Emittance of Refractory Materials," App. Opt. 3, 281 (1964).

1SE-6 Carlson, D. J., "Emittance of Condensed Oxides on Solid Propellant Combustion Products," Proc. 10th Symposium on Combustion, p. 1413, (1965).

1SE-7 Clark, H. E., and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Ceramic Oxides from 1200° to 1800°K," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

1SE-8 Clark, H. E., and Moore, D. G., "Rotating Cylinder Method for Measuring Normal Spectral Emittance of Ceramic Oxide Specimen from 1200° to 1600°K," J. Res. NBS 70A, 393 (1966).

1SE-9 Lyon, R. J. P., "Evaluation of Infrared Spectrophotometry for Compositional and Analysis of Lunar and Planetary Soils," Contract No. NASA CR-100 (1964).

1SE-10 McAlister, E. D., "High-Temperature Properties of Infrared Optical Materials," Proc. IRIS 4, 139 (1959).

1SE-11 Mergerian, D., "Optical Properties of Infrared-Transparent Solids at Elevated Temperatures," Proc. IRIS 4, 146 (1959).

1SE-12 Olt, R. D., "Synthetic Sapphire on Infrared Optical Material," Proc. IRIS 3, 141 (1958).

II-1.3 (Continued)

1SE-13 Richmond, J. C., "Effect of Surface Roughness on Emittance of Nonmetals," Thermophysics and Temp. Control of Spacecraft and Reentry Vehicles, Academic Press, New York (1966).

1SE-14 Schatz, E. A., Counts, C. R., III, Burks, T. L., "Improved Radiator Coatings, Part 1," ML-TDR-64-146.

1SE-15 Stierwalt, D. L., "Infrared Spectral Emittance Measurements of Optical Materials," App. Opt. 5, 1911 (1966).

1SE-16 Stierwalt, D. L., "Low Temperature Spectral Emittance Measurements" Thermophysics and Temp. Control of Spacecraft and Reentry Vehicles, Academic Press, New York (1966).

1SE-17 Streed, E. R., Cunnington, G. R., Lui, C. K., "Experimental Determination of the Infrared Spectral Optical Properties of Bulk and Powdered Aluminum Oxide," AFRPL-TR-73-3.

1SE-18 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

1SE-19 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

1SE-20 Worster, B. W., and Kadomiya, R. H., "Rocket Exhaust Aluminum Oxide Particle Properties," ARI-RR-30 (1973).

II-1.4 Total Normal Emissivity, ε(T) - Aluminum Oxide

1TE-1 Gannon, R. E., Linder, B., "Effect of Surface Roughness and Porosity on Emittance of Alumina," J. Am. Ceram. Soc. 47, 592 (1964).

1TE-2 Mergerian, D., "Optical Properties of Infrared-Transparent Solids at Elevated Temperatures," Proc. IRIS 4, 139 (1959).

1TE-3 Morizumi, S. J., Carpenter, H. J., "Thermal Radiation from the Exhaust Plume of an Aluminized Composite Propellant Rocket," J. Spacecraft 1, 501 (1964).

1TE-4 Olson, O. H., and Morris, J. C., "Determination of Emissivity and Reflectivity Data on Aircraft Structural Materials," WADC TR-56-222 Part II, Supplement I, ASTIA 202494 (1958).

1TE-5 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

1TE-6 Wittenberg, A. M., "Total Hemispherical Emissivity of Sapphire," J. Opt. Soc. Am. 55, 432 (1965).

1TE-7 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-1.5 Reflectance - Aluminum Oxide

1R-1 Aronson, J. R., and Emslie, A. G., "Spectral Reflectance and Emittance of Particulate Materials. 2. Application and Results," App. Opt. 12, 2573 (1973).

1R-2 Aronson, J. R., Emslie, A. G., Rooney, T. P., Coleman, I., Horlick, G., "Spectral Emittance and Reflectance of Powders," App. Opt. 8, 1639 (1969).

1R-3 Aronson, J. R., and McLinden, H. G., "Far-Infrared Spectra of Solids," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

1R-4 Barker, A. S., "Infrared Lattice Vibrations and Dielectric Dispersion in Corundum," Phys. Rev. 132, 1474 (1963).

1R-5 Brannon, R. E., Jr., and Goldstein, R. J., "Emittance of Oxide Layers on a Metal Substrate," J. Heat Transfer 92, 257 (1970).

1R-6 Clark, H. E., and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Ceramic Oxides from 1200° to 1800°K," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

1R-7 Gervais, F., Piriou, B., and Cabannes, F., "Etude du spectre de reflexion infrarouge du corindon avec une distribution anormale de phonons," C. R. Acad. Sci. B270, 1042 (1970).

1R-8 Harris, L., "Preparation and Infrared Properties of Aluminum Oxide Films," J. Opt. Soc. Am. 45, 27 (1955).

1R-9 Harris, L., and Piper, J., "Transmittance and Reflectance of Aluminum-Oxide Films in the Far Infrared," J. Opt. Soc. Am. 52, 223 (1962).

1R-10 Levy, R. M., "A New Infrared Technique for Characterizing Partially Amorphous Solids," J. Catalysis 9, 87 (1967).

1R-11 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: I, Spectra from 2 μ - 50 μ," App. Opt. 2, 591 (1963).

1R-12 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: III, Spectra from 2 μ - 50 μ," App. Opt. 4, 317 (1965).

II-1.5 (Continued)

1R-13 Neuberger, M., "Optical Properties and Thermal Conductivity of Aluminum Oxide," Hughes Aircraft Co., Epic Report No. S-6 (1965).

1R-14 Oppenheim, U. P., Even, U., "Infrared Properties of Sapphire at Elevated Temperatures," J. Opt. Soc. Am. 52, 1078 (1962).

1R-15 Piriou, B., "Etude des bandes de rayons restants de la magnesie et du corindon. Influence de la temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

1R-16 Plendl, J. N., and Gielisse, P. J., "Infrared Spectra of Inorganic Dielectric Solids," App. Opt. 3, 943 (1964).

1R-17 Salama, C. A. T., "RF Sputtered Aluminum Oxide Films on Silicon," J. Electrochem. Soc. 117, 913 (1970).

1R-18 Tipunin, Yu. V., Shalabutov, Yu. K., "Optical Properties of Corundum in the Infrared Spectral Region," Opt. Spectrosc. 31, 345 (1971).

II-1.6 Transmissivity - Aluminum Oxide

1T-1 Dorsey, G. A., Jr., "Far Infrared Absorption of Hydrous and Anhydrous Aluminas," Anal. Chem. 40, 971 (1968).

1T-2 Ferrieu, E., Pruniaux, B., 'Preliminary Investigations of Reactively Evaporated Aluminum Oxide Films on Silicon," J. Electrochem. Soc. 116, 1008 (1969).

1T-3 Gillespie, D. T., Olsen, A. L., Nichols, L. W., "Transmittance of Optical Materials at High Temperatures in the 1- to 12-Micron Range," U.S. Naval Ordnance Test Station, China Lake, Calif., NAVWEPS Report 8558 (1964).

1T-4 Grimm, N., Scott, G. E., Sibold, J. D., "Infrared Transmission Properties of High Density Alumina," Am. Ceram. Soc. Bull. 50, 962 (1971).

1T-5 Harris, L., "Preparation and Infrared Properties of Aluminum Oxide Films," J. Opt. Soc. Am. 45, 27 (1955).

1T-6 Harris, L., and Piper, J., "Transmittance and Reflectance of Aluminum-Oxide Films in the Far Infrared," J. Opt. Soc. Am. 52, 223 (1962).

1T-7 Kammori, O., Yamaguchi, N., and Sato, K., Bunseki Kagaku 16, 1050 (1967).

1T-8 Lee, D. W., Kingergy, W. D., "Radiation Energy Transfer and Thermal Conductivity of Ceramic Oxides," J. Am. Ceram. Soc. 43, 594 (1960).

1T-9 Loewenstein, E. V., "Optical Properties of Sapphire in the Far Infrared," J. Opt. Soc. Am. 51, 108 (1961).

1T-10 Marshall, R., Mitra, S. S., Gielisse, P. J., Plendl, J. N., Mansur, L. C., "Infrared Lattice Spectra of α - Al_2O_3 and Cr_2O_3," J. Chem. Phys. 43, 2893 (1965).

1T-11 McAlister, E. D., "High-Temperature Properties of Infrared Optical Materials," Proc. IRIS 4, 139 (1959).

1T-12 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: I, Spectra from 2 μ - 50 μ," App. Opt. 2, 591 (1963).

II-1.6 (Continued)

1T-13 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: III, Spectra from 2 μ - 50 μ," App. Opt. 4, 317 (1965).

1T-14 McCarthy, D. E., "Transmittance of Optical Materials from 0.17 μ - 3.0 μ," App. Opt. 6, 1896 (1967).

1T-15 Mitsuishi, A., Yoshinaga, H., Fujita, S., and Suemoto, Y., "Vibrational Spectra of Ruby and Haematite in the Infrared Region," Japanese J. of App. Phys. 1, (1962).

1T-16 Olt, R. D., "Synthetic Sapphire, An Infrared Optical Material," Proc. IRIS 3, 141 (1958).

1T-17 Oppenheim, U. P., Even, U., "Infrared Properties of Sapphire at Elevated Temperatures," J. Opt. Soc. Am. 52, 1078 (1962).

1T-18 O'Sullivan, J. P., Hockey, J. A., Wood, G. C., "Infra-Red Spectroscopic Study of Anodic Alumina Films," Trans. Farad. Soc. 65, 535 (1969).

1T-19 Piriou, B., Cabannes, F., "Spectroscopie Moleculaire," C. R. Acad. Sci. Paris 264, 1110 (1967).

1T-20 Roberts, S., and Coon, D. D., "Far-Infrared Properties of Quartz and Sapphire," J. Opt. Soc. Am. 52, 1023 (1962).

1T-21 Vratny, F., Dilling, M., Gugliotta, F., and Rao, C. N. R., "Infrared Spectra of Metallic Oxides, Phosphates and Chromates," J. Sci. Ind. Res. 20B, 590 (1961).

1T-22 White, W. B., "Application of Infrared Spectroscopy to Order-Disorder Problems in Simple Ionic Solids," Mat. Res. Bull. 2, 381 (1967).

II-1.7 Miscellaneous - Aluminum Oxide

1M-1 Adams, J. M., "A Determination of the Emissive Properties of a Cloud of Molten Alumina Particles," J. Q.S.R.T. 7, 273 (1967).

1M-2 Bakhir, A. P., Lavashenko, G. I., and Tamanovich, V. V., Zh. Prokladnoi Spektrosk 17, 25 (1972).

1M-3 Bakhir, A. P., Lavashenko, G. I. and Poliakova, N. G., Zh. Prokladnoi Spektrosk 18, 1047 (1973).

1M-4 Ballard, S. S., McCarthy, K. A., and Wolfe, W. L., "Optical Materials for Infrared Instrumentation - Supplement," IRIA State-of-the-Art Report 2389-11-S_1 (April 1961).

1M-5 Bauer, E., and Carlson, D. J., "Mie Scattering Calculations for Micron Sized Alumina and Magnesia Spheres," J. Q.S.R.T. 4, 363 (1964).

1M-6 Blau, H. H., Gray, E. L., "Reflection and Polarization Properties of Powder Materials," App. Opt. 6, 1899 (1967).

1M-7 Churchill, H., "Aluminum Behavior in Solid Propellant Combustion", AFRPL-TR-7413, May, 1974.

1M-8 Crabol, J., Caracteristiques Thermiques d'un Jet de Fusee Contenant des Particules d'Alumine, Off. Nat. Etud. Rech. Aerosp. 133, (1970).

1M-9 Godbee, H. W., and Ziegler, W. T., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850° C. I. Experimental," J. App. Phys. 37, 40 (1966).

1M-10 Godbee, H. W., and Ziegler, W. T., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850° C. II. Theoretical," J. App. Phys. 37, 56 (1966).

1M-11 Hass, G., and Ramsey, J. B., "Solar Absorptance and Thermal Emittance of Aluminum Coated with Surface Films of Evaporated Aluminum Oxide," Thermophysics and Temp. Control of Spacecraft and Reentry Vehicles, p. 47.

1M-12 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: II, Bibliography," App. Opt. 2, 596 (1963).

1M-13 Olechna, D. J., "Directional Dispersion of Extraordinary Optical Phonons in Uniaxial Crystals," J. Phys. Chem. Solids 31, 2755 (1970).

1M-14 Plass, G. N., "Mie Scattering and Absorption Cross Sections of Aluminum Oxide and Magnesium Oxide," SSD-TDR-62-127, (1963). Aeronutronic Div., Ford Motor Co., Newport Beach, Cal.

II-1.7 (Continued)

1M-15 Plass, G. N., "Mie Scattering and Absorption Cross Sections for Aluminum Oxide and Magnesium Oxide," App. Opt. 3, 867 (1964).

1M-16 Plass, G. N., "Temperature Dependence of the Mie Scattering and Absorption Cross Sections for Aluminum Oxide," App. Opt. 4, 1616 (1965).

1M-17 Sanders, C. F., Lenoir, J. M., "Radiative Transfer Through a Cloud of Absorbing-Scattering Particles," AIChE J. 18, 155 (1972).

1M-18 Schatz, E. A., "Reflectance of Compacted Powder Mixtures," J. Opt. Soc. Am. 57, 941 (1967).

1M-19 Vishevskii, I. I., and Skripak, V. N., "Radiative Heat Transfer in Polycrystalline Corundum," High Temp. 1, 403 (1969).

1M-20 Worster, B. W., "Particulate Infrared Radiation in Aluminized Solid-Fuel Rocket Plumes," J. Spacecraft 11, 260 (1974).

II-2. BIBLIOGRAPHY, CARBON

II-2.1 Refractive Index, n - Carbon

2N-1 Dalzell, W. H., Sarofim, A. F., "Optical Constants of Soot and Their Application to Heat-Flux Calculations," J. Heat Trans. 91, 100 (1969).

2N-2 Foster, P. J., Howarth, C. R., "Optical Constants of Carbons and Coals in the Infrared," Carbon 6, 719 (1968).

2N-3 Jones, A. R., and Schwar, M. J. R., "Light Scattering by Particles in Flames (A Review)," High Temp.-High Pressures 1, 369 (1969).

2N-4 Jungk, G., Lang, C. H., "Determination of Optical Constants: Amorphous Carbon," Phys. Stat. Sol. 50, 71 (1972).

2N-5 Krascella, N. L., "The Absorption and Scattering of Radiation by Small Solid Particles," J. Q.S.R.T. 5, 245 (1965).

2N-6 Lenham, A. P., Treherne, D. M., "The Optical Constants of Graphite," Observatory 86, 36 (1966).

2N-7 Levy-Mannheim, C., Mering, J., "Spectres Optiques de Lames Minces de Carbone. Effects de Traitments Thermiques," Carbon 10, 505 (1972).

2N-8 Lowes, T. M., and Newall, A. J., "The Emissivities of Flame Soot Dispersions," Comb. and Flame 16, 191 (1971).

2N-9 Twitty, J. T., Weinman, J. A., "Radiative Properties of Carbonaceous Aerosols," J. App. Meteor. 19, 725 (1971).

2N-10 Williams, M. W., Arakawa, E. T., "Optical Properties of Glassy Carbon from 0 to 82 eV," Appl. Phys. 43, 3460 (1972).

II-2.2 Extinction Index, k - Carbon

2K-1 Boynton, F., Ferriso, C., Ludwig, C. B., and Thomson, A., "Radiative Properties of Carbon Particles Produced by a Rocket Motor," AIAA Paper No. 66-133, AIAA 3rd Aerospace Sciences Meeting, January 1966.

2K-2 Dalzell, W. H., Sarofim, A. F., "Optical Constants of Soot and Their Application to Heat-Flux Calculations," J. Heat Trans. 91, 100 (1969).

2K-3 Foster, P. J., Howarth, C. R., "Optical Constants of Carbons and Coals in the Infrared," Carbon 6, 719 (1968).

2K-4 Hennig, G. R., "Optical Transmission of Graphite Compounds," J. Chem. Phys. 43, 1201 (1965).

2K-5 Jones, A. R., and Schwar, M. J. R., "Light Scattering by Particles in Flames (A Review)," High Temp.-High Pressures 1, 369 (1969).

2K-6 Jungk, G., Lang, C. H., "Determination of Optical Constants: Amorphous Carbon," Phys. Stat. Sol. 50, 71 (1972).

2K-7 Krascella, N. L., "The Absorption and Scattering of Radiation by Small Solid Particles," J. Q.S.R.T. 5, 245 (1965).

2K-8 Lenham, A. P., Treherne, D. M., "The Optical Constants of Graphite," Observatory 86, 36 (1966).

2K-9 Levy-Mannheim, C., Mering, J., "Spectres Optiques de Lames Minces de Carbone. Effects de Traitments Thermiques," Carbon 10, 505 (1972).

2K-10 Lowes, T. M., and Newall, A. J., "The Emissivities of Flame Soot Dispersions," Comb. and Flame 16, 191 (1971).

2K-11 Taft, E. A., and Philipp, H. R., "Optical Properties of Graphite," Phys. Rev. 138, 197 (1965).

2K-12 Twitty, J. T., Weinman, J. A., "Radiative Properties of Carbonaceous Aerosols," J. App. Meteor. 19, 725 (1971).

2K-13 Williams, M. W., Arakawa, E. T., "Optical Properties of Glassy Carbon from 0 to 82 eV," Appl. Phys. 43, 3460 (1972).

II-2.3 Spectral Emissivity, $\epsilon(\lambda)$ - Carbon

2SE-1 Abramov, A. S., Barykin, B. M., Romanov, A. I., Spiridonov, E. G., "Monochromatic Emissivity of Commercial Polycrystalline Graphites," High Temp. 9, 62 (1971).

2SE-2 Anacker, F., Mannkopff, R., "Das Emissionsvermogen von Kohlenstoff bei der Sublimationstemperatur," Z. für Physik 155, 16 (1959).

2SE-3 Autio, G. W., Scala, E., "The Normal Spectral Emissivity of Isotropic and Anisotropic Materials," Carbon 4, 13 (1966).

2SE-4 Beheshti, M., "Absorption and Scattering of Radiation by Solid Carbon Particles," AIAA J. 5, 809 (1967).

2SE-5 Blau, H. H., Jr., Chaffee, E., Jasperse, J. R., Martin, W. S., "High Temperature Thermal Radiation Properties of Solid Materials," AFCRC-TN-60-165, March 1960.

2SE-6 Boyle, W. S., Nozieres, P., "Band Structure and Infrared Absorption of Graphite," Phys. Rev. 111, 782 (1958).

2SE-7 Chang, J. H., and Sutton, G. W., "Spectral Emissivity Measurements of Ablating Phenolic Graphite," AVCO Everett Research Report 295, July 1968.

2SE-8 Dalzell, W. H., Sarofim, A. F., "Optical Constants of Soot and Their Application to Heat-Flux Calculations," J. Heat Trans. 91, 100 (1969).

2SE-9 "Study on the Spectral Emissivity of Carbon Particles Produced by a Rocket Motor," Report GD/C-DBE 66-006, General Dynamics, (1966).

2SE-10 Gmelin, L., "Gmelins Handbuch der Anorganischen Chemie," 8. aufl. Hrsg. Von der Deutschen chemischen geseilschaft, beard. von R. J. Meyer, unter berapender mitwirkung von Franz Peters. Leipzig-Berlin, Verlag Chemie g. m. b. h. s. (1924-1967).

2SE-11 Grenis, A. F., and Levitt, A. P., "The Spectral Emissivity and Total Normal Emissivity of Commercial Graphites at Elevated Temperatures," Proceedings of the Fifth Conference on Carbon, V. 2., MacMillan Co., New York (1963).

II-2.3 (Continued)

2SE-12 Jones, A. R., and Schwar, M. J. R., "Light Scattering by Particles in Flames (A Review)," High Temp.-High Pressure 1, 369 (1969).

2SE-13 Kibler, G. M., Lyon, T. F., Linevsky, M. J., and De Santis, V. J., "Refractory Materials Research," WADD TR-60-646, Part IV, Materials Lab., Wright-Patterson AFB, Ohio, Aug. 1964.

2SE-14 Liebert, C. H., and Hibbard, R. R., "Spectral Emittance of Soot," NASA TN-D-5647 (1970).

2SE-15 Plunkett, J. D., and Kingery, W. D., "The Spectral and Integrated Emissivity of Carbon and Graphite," Proceedings of the Fourth Conference on Carbon, Pergammon Press, New York, 1960.

2SE-16 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. I., MacMillan Co., New York (1957).

2SE-17 Wilson, R. G., and Spitzer, C. R., "Spectral and Integrated Emittance of Ablation Chars and Carbon," AIAA Journal 7, 2140 (1969).

2SE-18 Wilson, R. G., "Hemispherical Spectral Emittance of Ablation Chars, Carbon, and Zirconia (to 3700°K)." Symposium of Thermal Radiation of Solids, NASA SP-55 (1965).

2SE-19 Wilson, R. G., and Spitzer, C. R., "Visible and Near-Infrared Emittance of Ablation Chars and Carbon," AIAA J. 6, 665 (1968).

2SE-20 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

2SE-21 Yamada, H. Y., "High-Temperature Blackbody Radiation Source. Supplement I: Spectral Emissivity of Graphite," Report of BAMIRAC - prepared for the Advanced Research Projects Agency, August 1966.

II-2.4 Total Normal Emissivity, ε(T) - Carbon

2TE-1 Blau, H. H., Jr., Chaffee, E., Jasperse, J. R., Martin, W. S., "High Temperature Thermal Radiation Properties of Solid Materials," AFCRC-TN-60-165, March 1960.

2TE-2 Boynton, F., Ferriso, C., Ludwig, C. B., Thomson, A., "Radiative Properties of Carbon Particles Produced by a Rocket Motor," AIAA Paper No. 66-133, AIAA 3rd Aerospace Sciences Meeting January 1966.

2TE-3 Gmelin, L., "Gmelins Handbuch der Anorganischen Chemie," 8. aufl. Hrsg. Von der Deutschen chemischen gesellschaft, beard. von R. J. Meyer, unter berapender mitwirkung von Franz Peters. Leipzig-Berlin, Verlag Chemie g.m. b.h.s. (1924-1967).

2TE-4 Grenis, A. F., and Levitt, A. P., "The Spectral Emissivity and Total Normal Emissivity of Commercial Graphites at Elevated Temperatures," Proceedings of the Fifth Conference on Carbon, V.2., MacMillan Co., New York (1963).

2TE-5 Plunkett, J. D., and Kingery, W. D., "The Spectral and Integrated Emissivity of Carbon and Graphite," Proceedings of the Fourth Conference on Carbon, Pergammon Press, New York, (1960).

2TE-6 Rohsenow, W. M., Hartnett, J. P., Handbook of Heat Transfer, McGraw-Hill, New York, (1973).

2TE-7 Taylor, R. E., Kimbrough, W. D., "Thermophysical Properties of ATJS Graphite at High Temperatures," Carbon 8, 665 (1970).

2TE-8 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. I., MacMillian Co., New York (1967).

2TE-9 Wilson, R. G., "Hemispherical Spectral Emittance of Ablation Chars, Carbon, and Zirconia (to 3700 °K)," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

2TE-10 Wilson, R. G., and Spitzer, C. R., "Spectral and Integrated Emittance of Ablation Chars and Carbon," AIAA Journal 7, 2140 (1969).

2TE-11 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-2.5 Reflectance - Carbon

2R-1 Boyle, W. S., and Nozieres, P., "Band Structure and Infrared Absorption of Graphite," Phys. Rev. 111, 782 (1958).

2R-2 Foste', F. J., and Howarth, C. R., "Optical Constants of Carbons and Coals in the Infrared," Carbon 6, 719 (1968).

2R-3 Greenaway, D. L., and Harbeke, G., "Anisotropy of the Optical Constants and the Band Structure of Graphite," Phys. Rev. 178, 1340 (1969).

2R-4 Mattson, J. S., and Mark, H. B., "Infrared Internal Reflectance Spectroscopic Determination of Surface Functional Groups on Carbon," J. Coll. Int. Sci. 31, 131 (1969).

2R-5 Taft, E. A., and Philipp, H. R., "Optical Properties of Graphite," Phys. Rev. 138, 197 (1965).

2R-6 Williams, M. W., and Arakawa, E. T., "Optical Properties of Glassy Carbon from 0 to 83 eV," Appl. Phys. 43, 3460 (19[illegible]).

2R-7 Wilson, R. G., "Hemispherical Spectral Emittance of Ablation Chars, Carbon, and Zinconia (to 3700 °K)," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

II-2.6 Transmissivity - Carbon

2T-1 Friedel, R. A., and Carlson, G. L., "Infrared Spectra of Ground Graphite," J. Phys. Chem. 75, 1149 (1971).

2T-2 Friedel, R. A., and Hofer, L. J. E., "Spectral Characterization of Activated Carbon," J. Phys. Chem. 74, 2921 (1970).

2T-3 Friedel, R. A., and Carlson, G. L., "Difficult Carbonaceous Materials and Their Infrared and Raman Spectra. Reassignments for Coal Spectra," Fuel 51, 194 (1972).

2T-4 Levy-Mannheim, C., and Mering, J., "Spectres Optiques de Lames Minces de Carbone. Effects de Traitments Thermiques," Carbon 10, 505 (1972).

2T-5 Omori, K., "Infrared Absorption Spectra of Some Essential Minerals," Sci. Rept. Tohoku Univ. 7, 101 (no date).

2T-6 Yasinsky, J. B., and Ergun, S., "Transmittance of Single Crystals of Graphite in the Infrared Spectrum," Carbon 2, 355 (1965).

II-2.7 Miscellaneous - Carbon

2M-1 Bent, R., and Ladner, W. R., "The Ultra-violet Spectra of Coal-like Materials," Fuel 39, 479 (1960).

2M-2 Boynton, F. P., Ludwig, C. B., Thomson, A., "Spectral Emissivity of Carbon Particle Clouds in Rocket Exhausts," AIAA J. 6, 865 (1968).

2M-3 D'Alessio, A., Di Lorenzo, A., Beretta, F., Venitozzi, C., "Optical and Chemical Investigations on Fuel-Rich Methane-Oxygen Premixed Flames at Atmospheric Pressure," Fourteenth Symposium (International) on Combustion, The Combustion Institute, Pittsburgh, Penn., (1968).

2M-4 Ergun, S., McCartney, J. T., Walline, R. E., "Absorption of Ultra-violet and Visible Light by Ultra-thin Sections of Vitrinite from a High-volatile Bituminous Coal," Nature 187, 1014 (1960).

2M-5 Ergun, S., and McCartney, J. T., "Absorption by Graphite Single Crystals in the Ultraviolet and Visible Spectrum," Proceedings of the Fifth Conference on Carbon, V. 2., MacMillan Co., New York (1963).

2M-6 Ergun, S., "Determination of Longitudinal and Transverse Optical Constants of Absorbing Uniaxial Crystals - Optical Anisotropy of Graphite," Nature 213, 135 (1967).

2M-7 Friedel, R. A., and Queiser, J. A., "Ultra-violet-Visible Spectrum and the Aromaticity of Coal," Fuel 38, 369 (1960).

2M-8 Gilbert, L. A., "Refractive Indices and Absorption Coefficients of Coal in Bulk Measured in the Range 6000 to 2400Å by a Polarized Light Technique," Fuel 41, 351 (1962).

2M-9 Greenaway, D. L., and Harbeke, G., "Anisotropy of the Optical Constants and the Band Structure of Graphite," Phys. Rev. 178, 1340 (1969).

2M-10 Grigorovici, R., Devenyi, A., Gheorghiu, A., Belu, A., "Properties of Amorphous Carbon Films," J. Non-Cryst. Sol. 8, 793 (1972).

II-2.7 (Continued)

2M-11 Harris, L., "The Optical Properties of Metal Blacks and Carbon Blacks," The Eppley Foundation, Newport, R. I. (1967).

2M-12 Krascella, N. L., "The Absorption and Scattering of Radiation by Small Solid Particles," J. Q.S.R.T. 5, 245 (1965).

2M-13 Lieberman, M. L., "Effect of Gases on Particle Emission During the Heating of Graphite," Carbon 9, 345 (1971).

2M-14 McCartney, J. T., and Ergun, S., "Refractive Index and Thickness of Ultrathin Sections of Coals and Graphite by Interferometry," J. Opt. Soc. 52, 197 (1962).

2M-15 McCartney, J. T., Yasinsky, J. B., Ergun, S., "Optical Constants of Coals by Measurements in the UV and Visible Spectrum," Fuel 44, 349 (1965).

2M-16 Margerum, E. A., and Vand, A., "Light Scattering by Small Graphite Spheres," Mon. Not. Roy. Ast. Soc. 128, 431 (1964).

2M-17 Park, C., and Appleton, J. P., "Shock Tube Measurements of Soot Oxidation Rates at Combustion Temperatures and Pressures," source unknown.

2M-18 Sanders, C. F., and Lenoir, J. M., "Radiative Transfer Through a Cloud of Absorbing-Scattering Particles," AIChE J. 18, 155 (1972).

2M-19 Schurer, K., "The Spectral Emissivity of the Anode of a Carbon Arc," App. Opt. 7, 461 (1968).

2M-20 Stull, R. V., and Plass, G. N., "Emissivity of Dispersed Carbon Particles," J. Opt. Soc. Am. 50, 121 (1960).

2M-21 Taft, E. A., and Philipp, H. R., "Optical Properties of Graphite," Phys. Rev. 138, 197 (1965).

2M-22 Volz, F. E., "Infrared Optical Constants of Ammonium Sulfate, Sahara Dust, Volcanic Pumice, and Flyash," App. Opt. 12, 564 (1973).

2M-23 Waldman, J. L., and Happel, J., "Radiant Heat Transfer to Gas-Solids Mixtures," Chem. Eng. J. 1, 3 (1970).

II-2.7 (Continued)

2M-24 Wickramasinghe, N. C., "On the Optics of Small Graphite Spheres, I," Mon. Nat. Roy. Ast. Soc. 131, 263 (1966).

2M-25 Willis, C., "The Complex Refractive Index of Particles in a Flame," J. Phys. D: Appl. Phys. 3, 1944 (1970).

II-3. BIBLIOGRAPHY, MAGNESIUM OXIDE

II-3.1: Refractive Index, n – Magnesium Oxide

3N-1 Bradford, A. P., Hass, G., McFarland, M., "Optical Properties of Evaporated Magnesium Oxide Films in the 0.22-8-μ Wavelength Region," App. Opt. 11, 2242 (1972).

3N-2 Häfele, H. G., "Die Optischen Konstanten von Magnesium-oxyd im Infraroten," Ann. der Physik 7, 321 (1963).

3N-3 Hanna, R., "Infrared Properties of Magnesium Oxide," J. Am. Ceram. Soc. 48, 376 (1965).

3N-3.5 Herzberger, M. and Salzberg, C., "Refractive Indices of Infrared Optical Materials and Color Correction of Infrared Lenses", J. Opt. Soc. 52, 420 (1962).

3N-4 Jasperse, J. R., Kahan, A., Plendl, J. N., "Temperature Dependence of Infrared Dispersion in Ionic Crystals LiF and MgO," Phys. Rev. 146, 526 (1966).

3N-5 Mitskevich, V. V., "Infrared Absorption and Dispersion in LiF and MgO," Sov. Phys. - Sol. State 4, 2224 (1963).

3N-6 Moses, A. J., "Refractive Index of Optical Materials in the Infrared Region," Hughes DS-166 (1970).

3N-7 Neuberger, M., and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969).

3N-8 Piriou, B., "Etude des Bandes de Rayons Restants de la Magnesie et du Corindon. Influence de la Temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

3N-9 Rowntree, R. F., "Measurements of the Optical Constants of Magnesium Oxide and Calcium Tungstate in the Spectral Region Between 10 cm^{-1} and 100 cm^{-1} at 300°K and 90°K," AFCRL-63-454, Ohio State Univ. Sci. Report 4 (1963).

3N-10 Saksena, B. D., and Viswanathan, S., "Principal Lattice Frequency of MgO," Proc. Phys. Soc. 69, 129 (1955).

3N-11 Stephens, R. E., and Malitson, I. H., "Index of Refraction of Magnesium Oxide," J. Res. NBS 49, 249(1952).

3N-12 Wilmott, J. C., "The Infrared Spectrum of Magnesium Oxide," Proc. Phys. Soc. 63A, 389 (1950).

II-3.2: Extinction Index, k-Magnesium Oxide

3K-1 Andermann, G. and Duesler, E., "Improved Infrared Optical-Index Values for MgO," J. Opt. Soc. Am. 60, 53 (1970).

3K-2 Häfele, H. G., "Die Optischen Konstanten von Magnesium-oxyd im Infraroten," Ann. der Physik 7, 321 (1963).

3K-3 Hanna, R., and Crandall, W. B., "Ultraviolet, Visible, and Infrared Transmission in Magnesia," New York State Univ., Alfred College of Ceramics, AD 270255 (1962).

3K-4 Hanna, R., "Infrared Properties of Magnesium Oxide," J. Am. Ceram. Soc. 48, 376 (1965).

3K-5 Jasperse, J. R., Kahan, A., Plendl, J. N., "Temperature Dependence of Infrared Dispersion in Ionic Crystals LiF and MgO," Phys. Rev. 146, 526 (1966).

3K-6 Jasperse, J. R., Marram, E. P., Clark, O. M., "Temperature Dependence of the Infrared Spectra of Selected Dielectrics," AFCRL-65-252.

3K-7 Mitskevich, V. V., "Infrared Absorption and Dispersion in LiF and MgO," Sov. Phys. - Sol. State 4, 2224 (1963).

3K-8 Moses, A. J., "Refractive Index of Optical Materials in the Infrared Region," Hughes DS-166 (1970).

3K-9 Neuberger, M., and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969).

3K-10 Oppenheim, U. P., and Goldman, A., "Infrared Spectral Transmittance of MgO and BaF_2 Crystals Between 27° and 1000°C," J. Opt. Soc. of Am. 54, 127 (1964).

3K-11 Piriou, B., "Etude des Bandes de Rayons Restants de la Magnesie et du Corindon. Influence de la Temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

3K-12 Piriou, B., and Cabannes, F., "Absorption Infrarogue de la Magnesie," C. R. Acad. Sci. 264, 630 (1967).

3K-13 Plendl, J. N., and Gielisse, P. J., "Infrared Spectra of Inorganic Dielectric Solids," App. Opt. 3, 943 (1964).

II-3.2 (Continued)

3K-14 Price, W. C., and Wilkinson, G. R., "Molecular and Solid State Spectroscopy Report," U. S. Army Contract DA-91-591 EUC-1308 OI-4201-60 (R & D 120). Cited in Plendl (1K-13) and Rowntree (1K-15).

3K-15 Rowntree, R. F., "Measurements of the Optical Constants of Magnesium Oxide and Calcium Tungstate in the Spectral Region Between 10 cm^{-1} and 100 cm^{-1} at 300°K and 90°K," AFCRL-63-454, Ohio State Univ. Sci. Report 4 (1963).

3K-16 Wilmott, J. C., "The Infrared Spectrum of Magnesium Oxide," Proc. Phys. Soc. 63A, 389 (1950).

II-3.3: Spectral Emissivity, $\epsilon(\lambda)$ – MgO

3SE-1 Blau, H. H., Jr., Marsh, J. B., Martin, W. S., Jasperse, J. R., Chaffee, E., "Infrared Spectral Emittance Properties of Solid Materials," AFCRL-TR-60-416 (October 1960).

3SE-2 Blau, H. H., Jr., and Jasperse, J. R., "Spectral Emittance of Refractory Materials," App. Opt. 3, 281 (1964).

3SE-3 Clark, H. E. and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Ceramic Oxides from 1200° to 1800°K," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

3SE-4 Clark, H. E. and Moore, D. G., "A Rotating Cylinder Method for Measuring Normal Spectral Emittance of Ceramic Oxide Specimens from 1200° to 1600°K," J. Res. NBS 70A, 393-415 (1966).

3SE-5 McAlister, E. D., "High-Temperature Properties of Infrared Optical Materials," Proc. IRIS 4, 139 (1959).

3SE-6 Neuberger, M., and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969).

3SE-7 Olt, R. D., "Synthetic Sapphire, An Infra Optical Material," Proc. IRIS 3, 141 (1958).

3SE-8 Stierwalt, D. L., "Low Temperature Spectral Emittance Measurements," NOLC Report No. 667 (1966).

3SE-9 Stierwalt, D. L., "Infrared Spectral Emittance Measurements of Optical Materials," App. Opt. 5, 1911 (1966).

3SE-10 Stierwalt, D. L., "Low Temperature Spectral Emittance Measurements," Thermophysics and Temperature Control of Spacecraft and Reentry Vehicles, Academic Press, New York, (1966).

3SE-11 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V.4., MacMillan Co., New York (1967).

3SE-12 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-3.4: Total Normal Emissivity, $\epsilon(T)$ – MgO

3TE-1 Backhurst, I., J., Iron Steel Ind. 189, 124; cited in Touloukian (3TE-6).

3TE-2 Mrozowski, et al., State Univ. of N. Y. at Buffalo, N. Y., Carbon Res. Lab., WADC-TR-360, IV; cited in Touloukian (3TE-6)

3TE-3 Neuberger, M. and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969); citing Touloukian (3TE-6).

3TE-4 Olson, O. H., and Morris, J. C., "Determination of Emissivity and Reflectivity of Aircraft Structural Materials," WADC-TR-56-222, Part II, Supplement I, ASTIA 202494 (October 1958); cited in Wood (3TE8).

3TE-5 Straumanis, M. E., and Aka, E. Z., J. App. Phys. 23, 330 (1952); Cited in Touloukian (3TE-6).

3TE-6 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillian Co., New York (1967).

3TE-7 Tret'yarkov, Y. D., Troshkina, V. A., Khomyakov, K. G., Shur. Neorg. Khm. 4 (1), 5; cited in Touloukian (3TE-6).

3TE-8 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-3.5: Reflectance – Magnesium Oxide

3R-1 Andermann, G., and Duesler, E., "Improved Infrared Optical-Index Values for MgO," J. Opt. Soc. Am. 60, 53 (1970).

3R-2 Arlt, H., and Bolie H. - J., "Angle Dependent Reflectivity of Natural Surfaces, 1-12μ," AFCRL-68-0551, August 1968.

3R-3 Blevin, W. R., and Brown, W. J., "An Infra-red Reflectometer with a Spheroidal Mirror," J. Sci. Instrum. 42, 385 (1965).

3R-4 Clark, H. E., and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Ceramic Oxides from 1200° to 1800°K," Symposium on Thermal Radiation of Solids, NASA SP-55 (1965).

3R-5 De La Perrelle, E. T., Moss, T. S., Herbert, H., "The Measurements of Absorptivity and Reflectivity," Infrared Phys. 3, 35 (1963).

3R-6 Gervais, F., Cabannes, F., Piriou, B., "Spectre de reflexion infrarouge de la magnesie avec une distribution anormale de phonons," C. R. Acad. Sci. Paris 271, 707 (1970).

3R-7 Hanna, R., "Infrared Properties of Magnesium Oxide," J. Am. Ceram. Soc. 48, 376-380 (1965).

3R-8 Jasperse, J. R., Kahan, A., Plendl, J. N., "Temperature Dependence of Infrared Dispersion in Ionic Crystals LiF and MgO," Phys. Rev. 146, 526 (1966).

3R-9 Jasperse, J. R., Marram, E. P., Plendl, J. N., Mansur, L. C., Gielisse, P. J., "Temperature Dependence of the Infrared Spectra for LiF and MgO," Appl. Phys. Lett. 5, 24 (1964).

3R-10 Jasperse, J. R., Marram, E. P., Clark, O. M., "Temperature Dependence of the Infrared Spectra of Selected Dielectrics," AFCRL-65-252.

3R-11 McAloren, J. T., "A Reproducible Magnesium Oxide Standard for Reflectance Measurement from 0.3 to 2.6μ," Nature 195. 797 (1962).

3R-12 Neuberger, M., and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969).

II-3.5 (Continued)

3R-13 Piriou, B., "Etude des Bandes de Rayons Restants de la Magnesie et du Corindon. Influence de la Temperature," Rev. Hautes Temper. et Refract. 3, 109 (1966).

3R-14 Plendl, J. M., and Gielisse, P. J., "Infrared Spectra of Inorganic Dielectric Solids," App. Opt. 3, 943 (1964).

3R-15 Saksena, B. D., and Viswanathan, S., "Principal Lattice Frequency of MgO," Proc. Phys. Soc. 69, 129 (1955).

3R-16 Sanders, C. L., and Middleton, E. E. K., "The Absolute Spectral Diffuse Reflectance of Magnesium Oxide in the Near Infrared," J. Opt. Soc. Am. 43, 58 (1953).

3R-17 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

II-3.6: Transmittance – Magnesium Oxide

3T-1 Berthold, G., "Zur Ultrarotdurchassigkeit von BeO, BeS, MgO, MgS, and Li_2O," Z. für Physik 181, 333 (1964).

3T-2 Evans, J. V., and Whateley, T. L., "Infra-Red Study of Adsorption of Carbon Dioxide and Water on Magnesium Oxide," Trans. Farad. Soc. 63, 2769 (1967).

3T-3 Genzel, L., and Martin, T. P., "Infrared Absorption in Small Ionic Crystals," Phys. Stat. Sol. 51, 91 (1972).

3T-4 Gourley, J. T., and Runciman, W. A., "Multiphonon Infrared Absorption Spectra of MgO and CaO," J. Phys. C: Solid State Phys. 6, 583 (1973).

3T-5 Häfele, H. G., "Die Optischen Konstanten von Magnesium-oxide im Infraroten," Ann. der Physik 7, 321 (1963).

3T-6 Hanna, R., "Infrared Properties of Magnesium Oxide," J. Am. Ceram. Soc. 48, 376 (1965).

3T-7 Kammori, O., Yamaguchi, N., Sato, K., Bunseki Kagaki 16, 1050 (1967).

3T-7.5 Linsteadt, G., "Infrared Transmittance of Optical Materials at Low Temperatures", App. Opt. 3, 1453 (1964).

3T-8 Luxon, J. T., Montgomery, D. J., Summitt, R., "Effect of Particle Size and Shape on the Infrared Absorption of Magnesium Oxide Powders," Phys. Rev. 188, 1345 (1969).

3T-9 McAlister, E. D., "High-Temperature Properties of Infrared Optical Materials," Proc. IRIS 4, 139 (1959).

3T-10 Neuberger, M., and Carter, D. B., "Magnesium Oxide," Hughes DS-163 (1969).

3T-11 Olt, R. D., "Synthetic Sapphire, An Infrared Optical Material," Proc. IRIS 3, 141 (1958).

3T-12 Oppenheim, V. P., and Goldman, A., "Infrared Spectrum Transmittance of MgO and BaF_2 Crystals Between 27° and 1000°C," J. Opt. Soc. Am. 54, 27 (1964).

3T-13 Piriou, B., and Cabannes, F., "Absorption Infrarouge de la Magnesie," C. R. Acad. Sci. 264, 630 (1967).

3T-14 Ressler, G., and Möller, K. D., "Far Infrared Transmittance of Irtrans 1 to 5 in the 250 - 10 cm^{-1} Spectral Region", App. Opt. 5, 877 (1966).

II-3.6 (Continued)

3T-14 Raman, C. V., "The Vibrations of the MgO Crystal Structure and Its Infra-red Absorption Spectrum - Part I. The Results of Experimental Study," Proc. Ind. Acad. Sci. 54A, 205 (1961).

3T-15 Srivastava, S. P., "Multiphonon Absorption Bands in MgO," Chem. Phys. Letters 10, 387 (1971).

3T-16 Srivastava, S. P., and Singh, R. D., "Effect of Anharmonicity on the K ≈ O Modes of MgO and ZnS," Phys. Stat. Sol. 45, 99 (1971).

3T-17 Tresvyatskii, S. G., Yaremenko, Z. A., Lopato, L. M., "Optical Parameters of Synthetic Periclase Single Crystals," Soviet Physics-Crystallography 11, 407 (1966).

II-3.7: Miscellaneous – Magnesium Oxide

3M-1 Adler, J. G., "Observation of the Phonon Spectra of MgO by Inelastic Electron Tunneling in Metal-Insulator-Metal Junctions," Solid State Communications 7, 1635 (1969).

3M-2 Andermann, G., Wu, C. K., Duesler, E., "Kramers-Kronig Phase-Angle Partioning Method for Disclosing Systematic Errors in Infrared Reflectance Data," J. Opt. Soc. Am. 58, 1663 (1968).

3M-3 Bauer, E., and Carlson, D. J., "Mie Scattering Calculations for Micron Size Alumina and Magnesia Spheres," J. Q.S.R.T. 4, 363 (1964).

3M-4 Carlson, D. J., "Emittance of Condensed Oxides in Solid Propellant Combustion Products," Tenth Synposium (International) on Combustion, The Combustion Institute, Pittsburgh, Penn., (1965).

3M-5 Genzel, L., and Martin, T. P., "Lattice Dynamics of MgO Microcrystals," Phys. Stat. Sol. 51, 101 (1972).

3M-6 Godbee, H. W. and Ziegler, W., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850°C. I. Experimental," J. App. Phys. 37, 40 (1966).

3M-7 Godbee, H. W., and Ziegler, W., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850°C. II Theoretical," J. App. Phys. 37, 56 (1966).

3M-8 Hooper, M. A., and James, D. W., "Lattice Dynamics, Second-Order Vibrational Spectra and Fluorescence Spectra in Magnesium Oxide," Trans. Farad. Soc. 65, 2016 (1969).

3M-9 Kachare, A., Andermann, G., Brantley, L. R., "Realiability of Classical Dispersion Analysis of LiF and MgO Reflectance Data," J. Phys. Chem. Sol. 33, 467 (1972).

3M-10 Kagel, R. O., and Greenler, R. G., "Infrared Study of the Adsorption of Methanol and Ethanol on Magnesium Oxide," J. Chem. Phys. 49, 1638 (1968).

3M-11 McCarthy, D. E., "The Reflection and Transmission of Infrared Materials: IV, Bibliography," App. Opt. 4, 507 (1965).

3M-12 McCarthy, D. E., "Reflection and Transmission Measurements in the Far Infrared," App. Opt. 10, 2539 (1971).

II-3.7 (Continued)

3M-13 Plass, G. N., "Mie Scattering and Absorption Cross Sections of Aluminum Oxide and Magnesium Oxide," SSD-TDR-62-127, Aeronutronic Div., Ford Motor Co., VI, (1963).

3M-14 Plass, G. N., "Mie Scattering and Absorption Cross Sections for Aluminum Oxide and Magnesium Oxide," App. Opt. 3, 867 (1964).

3M-15 Plyler, E. D., Yates, D. J. B., Gebbie, H. A., "Radiant Energy from Sources in the Far Infrared," J. Opt. Soc. Am. 52, 859 (1962).

3M-16 Rupprecht, G., "Photon-Phonon Interaction in the Near Infrared," Phys. Rev. Lett. 12, 580 (1964).

3M-17 Sangster, M. J. L., Peckham, G., Saunderson, D. H., "Lattice Dynamics of Magnesium Oxide," J. Phys. Chem. 3, 1026 (1969).

3M-18 Sacadura, J. F. O., "Influence de la Rugosite Sur Le Rayonnement Thermique Emis Par les Surfaces Opaques: Essai de Modele," Int. Heat Mass Transfer 15, 1451 (1972).

3M-19 Sakhnovskii, M. Y., "The Optical Properties of Magnesium Oxide," Optics & Spektrosc. 18, 100 (1965).

3M-20 Seaney, R. J., "Optical Diffraction Effects in the Back-reflected Energy Distribution from an Aggregate of Small Irregular Particles," Nature 212 1447 (1966).

3M-21 Vratny, F., Dilling, M., Gugliotta, F., Rao, C. N. R., "Infrared Spectra of Metallic Oxides, Phosphates and Chromates," J. Sci. Ind. Res. 20B, 590 (1961).

3M-22 Zhorov, G. A., "Connection between Degree of Blackness of Total Normal Radiation and the Electric Resistance in Oxides," High Temp. 10, 597 (1972).

II-4. BIBLIOGRAPHY, ZIRCONIUM DIOXIDE

II-4.2 Extinction Index, k - Zirconium Dioxide

4K-1 Piriou, B. and Tsakiris, J., "Reflexion et Transmission dans l'infra Rouge de la Zircone Monoclinique," C. R. Acad. Sci. 261, 3079 (1965).

Preceding page blank

II-4.3 Spectral Emissivity, $\epsilon(\lambda)$ – Zirconium Dioxide

4SE-1 Backhund, H. G., Thermal Cond. Conf., National Physics Lab., Teddington, England. Cited by Touloukian, Ref. 4SE-7.

4SE-2 Blau, H. H., and Jasperse, J. R., "Spectral Emittance of Refractory Materials," App. Opt. 3, 281 (1964).

4SE-3 Blau, H. H., Marsh, J. B., Martin, W. S., Jasperse, J. R., Chaffee, E., "Infrared Spectral Emittance Properties of Solid Materials," AFCRL-TR-60-416.

4SE-4 Clark, H. E., and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Cermaic Oxides from 1200°K to 1800°K," NASA SP-55 (1965).

4SE-5 Clark, H. E., and Moore, D. G., "A Rotating Cylinder Method for Measuring Normal Spectral Emittance of Ceramic Oxide Specimens from 1200°K to 1600°K," J. Res. NBS 70A, 393 (1966).

4SE-6 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

4SE-7 Wilson, R. G., "Hemispherical Spectral Emittance of Ablation Chars, Carbon, and Zirconia (to 3700°K)," NASA SP-55 (1965).

4SE-8 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials: No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-4.4 Total Normal Emissivity, $\epsilon(T)$ – Zirconium Dioxide

4TE-1 Hedge, J. C., "Total Normal Emittance Measurements to 2200°C in Air," Thermophysics and Temperature Control of Spacecraft and Reentry Vehicles, Academic Press, New York (1966).

4TE-2 Jain, S. C., Shina, V., Reddy, B. K., "Thermal Conductivity of Metals at High Temperatures by the Jain and Krishnam Method: V. Zirconium," J. Phys. D: App. Phys. 3, 1359 (1970).

4TE-3 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

4TE-4 Wood, W. D., Deem, H. W., Lucks, C. F., Plenum Press Handbooks of High Temperature Materials : No. 3 : Thermal Radiative Properties, Plenum Press, New York (1964).

II-4.5 Reflectance – Zirconium Dioxide

4R-1 Clark, H. E., and Moore, D. G., "Method and Equipment for Measuring Thermal Emittance of Ceramic Oxides from 1200°K to 1800°K," NASA SP-55 (1965).

4R-2 Phillippi, C. M., and Mazdiyasni, K. S., "Infrared and Raman Spectra of Zirconia Polymorphs," J. Am. Ceram. Soc. 54, 254 (1971).

4R-3 Piriou, B., and Tsakiris, J., "Reflexion et Transmission dans l'infra Rouge de la Zircone Monoclinique," C. R. Acad. Sci. 261, 3079 (1965).

4R-4 Touloukian, Y. W., Thermophysical Properties of High Temperature Solid Materials, V. 4., MacMillan Co., New York (1967).

4R-5 Wilson, R. G., "Hemispherical Spectral Emittance of Ablation Chars, Carbon, and Zirconia (to 3700°K)," NASA SP-55 (1965).

II-4.6 Transmittance – Zirconium Dioxide

4T-1 Baun, W. L., and McDevitt, N. T., "The Use of Infrared Absorption Spectroscopy in Research on Hafnia and Zirconia," ASD-TDR-63-789, Sept. 1963.

4T-2 Kammori, O., Yamaguchi, N., Sato, K., Bunseki Kagsku 16, 1050 (1967).

4T-3 McDevitt, N. T., and Baun, W. L., "Infrared Absorption Spectroscopy in Zirconia Research," J. Am. Ceram. Soc. 47, 622 (1964).

4T-4 McDevitt, N. T., and Baun, W. L., "Infrared Absorption Study of Metal Oxides in the Low (700-240 cm^{-1}) Frequency Region," Spectrochimica Acta 20, 799 (1964).

4T-5 Phillippi, C. M., and Mazdiyasni, K. S., "Infrared and Raman Spectra of Zirconia Polymorphs," J. Am. Ceram. Soc. 54, 254 (1971)

4T-6 Piriou, B., and Tsakiris, J., "Reflexion et Transmission dans l'infra Rouge de la Zircone Monoclinique," C. R. Acad. Sci. 261, 3079 (1965).

II-4.7 Miscellaneous – Zirconium Dioxide

4M-1 Godbee, H. W., and Zeigler, W. T., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850° C. I. Experimental," J. App. Phys. 37, 40 (1966).

4M-2 Godbee, H. W., and Zeigler, W. T., "Thermal Conductivities of MgO, Al_2O_3, and ZrO_2 Powders to 850° C. II. Theoretical," J. App. Phys. 37, 56 (1966).

4M-3 Kan, H. K. A., Champetier, R. J., Erler, T. G., "A Study of Zirconium Oxide White Pigment for Space Environment," TR-0059(6250-20)-4. The Aerospace Corp., El Segundo, Ca. (1970).

4M-4 Lin, T., and Kan, H. K. A., "The Reflectance of a Light Diffuser with Non-Uniform Absorption," TR-0066(9250-04)-1, The Aerospace Corp., El Segundo, Ca. (1970).

4M-5 Schatz, E. A., "Reflectance of Compacted Powder Mixtures," J. Opt. Soc. 57, 941 (1967).

II-5 Bibliography, Author Cross Reference

Aronson, J.R.: 1SE-1, 1SE-2, 1R-1, 1R-2, 1R-3

Abramov, A.S.: 2SE-1

Adams, J.M.: 1M-1

Adler, J.G.: 3M-1

Anacker, F.: 2SE-2

Anderman, G.: 2SE-3, 3K-1, 3R-1, 3M-1, 3M-9

Appleton, J.P.: 2M-18

Arakawa, E.T.: 2N-10, 2K-13, 2R-6

Arlt, H.: 3R-2

Autio, G.W.: 2SE-3

Backhund, H.G.: 4SE-1

Backhurst, I: 3TE-1

Bagdasarov, Kh. S: 1K-14

Bakhir, A.P.: 1M-1, 1M-2

Ballard, S.S.: 1M-4

Barker, A.S.: 1R-4

Barykin, B.M.: 2SE-1

Bauer, E: 1M-5, 3M-3

Baun, W.L.: 4T-1, 4T-3, 4T-4

Behesti, M.: 2SE-4

Bell, E.E.: 1N-11, 1K-15

Belu, A.: 2M-11

Bent, R.: 2M-1

Beretta, F.: 2M-3

Bergquam, J.B.: 1SE-3

Berthold, G.: 3T-1

Blau, H.H.: 1SE-4, 1SE-5, 1M-6, 2SE-5, 2TE-1, 3SE-1, 3SE-2, 4SE-2, 4SE-3

Blevin, W.R.: 3R-3

Bolle, H.J.: 3R-2

Boyle, W.S.: 2SE-6, 2R-1

Boynton, F.: 2K-1, 2TE-2, 2M-2

Bradford, A.D.: 3N-1

II-5 (Continued)

Brannon, R.R.: 1R-5

Brantley, L.R.: 3M-9

Brown W.J.: 3R-3

Burch, D.E.: 1K-2

Burks, T.L.: 1SE-14

Cabannes, F.: 1K-12, 1R-7, 1T-19, 3K-12, 3R-6, 3T-13

Carlson, D.J.: 1SE-6, 1M-5, 3M-3, 3M-4

Carlson, G.L.: 2T-1, 2T-3

Carpenter, H.J.: 1TE-3

Carter, D.B.: 3N-7, 3K-9, 3SE-6, 3TE-4, 3R-12, 3T-10

Chaffee, E: 1SE-4, 2SE-5, 2TE-1, 3SE-1, 4SE-3

Champetier, R.J.: 4M-3

Chang, J.H.: 2SE-7

Clark, H.E.: 1SE-7, 1SE-8, 1R-6, 3SE-2, 2SE-4, 3R-4, 4SE-4, 4SE-5, 4R-1

Clark, O.M.: 3R-10

Coleman, I.: 1SE-1, 1R-2

Coon, D.D.: 1N-10, 1T-20

Counts, C.R.III: 1SE-14

Crabol, J: 1M-7

Crandall, W.B.: 3K-3

Cunnington, G.R.: 1N-12, 1K-16, 1SE-17

D'Allesio, A.: 2M-3

De La Perrelle, E.T.: 3R-5

Dalzell, W.H.: 2N-1, 2K-2, 2SE-8

Deem, H.W.: 1SE-19, 1TE-7, 2SE-20, 3SE-12, 2TE-11, 3TE-8, 4SE-8, 4TE-4

De Santis, V.J.: 2SE-13

Devenyi, A.: 2M-21

Dilling, M.: 1T-21, 3M-21

DiLorenzo, A.: 2M-3

Dorsey, G.A.: 1T-1

Duesler, E.: 3K-1, 3R-1, 3M-2

Emslie, A.G.: 1SE-1, 1SE-2, 1R-1, 1R-2

II-5 (Continued)

Ergun, S.: 2T-6, 2M-4, 2M-5, 2M-6, 2M-15, 2M-16
Erler, T.G.: 4M-3
Evans, J.V.: 3T-2
Even, U.: 1K-11, 1R-14, 1T-17
Ferrieu, E.: 1T-2
Ferriso, C.: 2K-1, 2TE-2
Friedel, R.A.: 2T-1, 2T-2, 2T-3, 2M-7
Foster, P.J.: 2N-2, 2K-3, 2R-2
Fuiita, S.: 1T-15
Gannon, R.E.: 1TE-7
Gebbie, H.A.: 3M-15
General Dynamics: 2SE-9
Genzel, L.: 3T-3, 3M-5
Gervais, F.: 1R-7, 3R-6
Gheorghiu, A.: 2M-11
Gielisse, P.J.: 1R-16, 1T-10, 3K-13, 3R-9, 3R-14
Gilbert, L.A.: 2M-8
Gillespie, D.T.: 1T-3
Gmelin, L.: 2SE-10, 2TE-3
Godbee, H.W.: 1M-8, 1M-9, 3M-6, 3M-7, 4M-1, 4M-2
Goldman, A.: 3K-10, 3T-12
Goldstein, R.J.: 1R-5
Gourley, J.T.: 3T-4
Graham, S.C.: 2M-9
Gray, E.L.: 1M-6
Grenier, A.F.: 2SE-11, 2TE-4
Grennler, R.G.: 3M-10
Greenaway, D.L.: 2R-3, 2M-10
Grigorovici, R.: 2M-11
Grimm, N.: 1K-1, 1T-4
Gryvnak, D.A.: 1K-2
Gugliotta, F.: 1T-21, 3M-21
Häfele, H.G.: 1N-1, 1K-3, 3N-2, 3K-2, 3T-5
Hanna, R.: 3N-3, 3K-3, 3K-4, 3T-6, 3R-7
Happel, J.: 2M-24

II-5 (Continued)

Harris, L.: 1N-2, 1K-4, 1R-8, 1R-9, 1T-5, 1T-6, 2M-12

Harbeke, G.: 2R-3, 2M-10

Hartnet, J.P.: 2TE-6

Hass, G.: 1M-10, 3N-1

Hedge, J.C.: 4TE-1

Hennig, G.R.: 2K-4

Hibbard, R.R.: 2SE-14

Hockey, J.A.: 1T-18

Hofer, L.J.E.: 2T-2

Homer, J.B.: 2M-9

Hooper, M.A.: 3M-8

Horlick, G.: 1SE-1, 1R-2

Howarth, C.R.: 2N-2, 2K-3, 2R-2

Jain, S.C.: 4TE-2

James, D.W.: 3M-8

Jasperse, J.R.: 1SE-4, 1SE-5, 2SE-5, 2TE-1, 3N-4, 3K-5, 3K-6, 3SE-1, 3SE-2, 3R-8, 3R-9, 3R-10

Jones, A.R.: 2N-3, 2K-5, 2SE-12

Jungk, G.: 2N-4, 2K-6

Kadomiya, R.H.: 1SE-20

Kahan, A.: 3N-4, 3K-5, 3R-8

Kan, H.K.A.: 4M-3, 4M-4

Kachare, A.: 3M-9

Kagel, R.O.: 3M-10

Kammori, O.: 1T-7, 3T-7, 4T-2

Khomyakov, K.G.: 3TE-7

Kibler, G.M.: 2SE-13

Kimbrough, W.D.: 2TE-7

Kingery, W.D.: 1T-8, 2SE-15, 2TE-5

Krascella, N.L.: 2N-5, 2K-7, 2M-13

Ludner, W.R.: 2M-1

Lang, C.H.: 2N-4, 2K-6

Lavashenko, G.I.: 1M-2, 1M-3

Lee, D.W.: 1T-8

Leiham, A.D.: 2N-6, 2K-8

II-5 (Continued)

Lenoir, J.M.: 1M-16, 2M-19

Levitt, A.P.: 2SE-11, 2TE-4

Levy, R.M.: 1R-10

Levy-Mannheim: 2N-7, 2K-9, 2T-4

Lieberman, M.L.: 2M-14

Liebert, C.H.: 2SE-14

Lin, T.: 3M-4

Linder, D.: 1TE-1

Linevsky, M.J.: 2SE-13

Loewenstein, E.V.: 1N-3, 1K-5, 1T-9

Lopato, L.M.: 3T-17

Lowes, T.M.: 2N-8, 2K-10

Lucks, C.F.: 1SE-19, 1TE-7, 2SE-20, 2TE-11, 3SE-12, 3TE-8, 4SE-8, 4TE-4

Ludwig, C.: 2K-1, 2TE-2, 2M-2

Lui, C.K.: 1N-12, 1K-16, 1SE-14

Luxon, J.T.: 3T-8

Lyon, R.J.P.: 1SE-9

Lyon, T.F.: 2SE-13

Malitson, I.H.: 1N-4, 1N-5, 3N-11

Mannkopff, R.: 2SE-2

Mansur, L.C.: 1T-10, 3R-9

Margerum, E.A.: 2M-17

Mark, H.B.: 2R-4

Marran, E.P.: 3K-6, 3R-9, 3R-10

Marsh, J.B.: 1SE-4, 3SE-1, 4SE-3

Marshall, R.: 1T-10

Martin, T.P.: 3T-3, 3M-5

Martin, W.S.: 1SE-4, 2SE-5, 2TE-1, 3SE-1, 4SE-3

Mattson, J.S.: 2R-4

Mazdiyasni, K.S.: 4R-2, 4T-5

McAlister, E.D.: 1SE-10, 1T-11, 3SE-5, 3T-9

McAloren, J.T.: 3R-11

McCarthy, D.E.: 1R-11, 1R-12, 1T-12, 1T-13, 1T-14, 1M-11, 3M-11, 3M-12

II-5 (Continued)

McCarthy, K.A.: 1M-4
McCartney, J.T.: 2M-4, 2M-5, 2M-15, 2M-16
McDevitt, N.T.: 4T-1, 4T-3, 4T-4
McFarland, M.: 3N-1
McLinden, H.G.: 1R-3
Mergerian, D.: 1K-6, 1SE-11, 1TE-2
Mering, J.: 2N-7, 2K-9, 2T-4
Middleton, E.E.K.: 3R-16
Mitra, S.S.: 1T-10
Mitskevich, V.V.: 3N-5, 3K-7
Mitsuishi, A.: 1T-15
Montgomery, D.J.: 3T-8
Moore, D.G.: 1SE-7, 1SE-8, 1R-6, 3SE-3, 3SE-4, 3R-4, 4SE-4, 4SE-5, 4R-1
Morgan, R.L.: 1N-3, 1K-5
Morizumi, S.J.: 1TE-3
Morris, J.C.: 1TE-4, 3TE-4
Moses, A.J.: 1N-6, 1K-7, 3N-6, 3K-8
Moss, T.S.: 3R-5
Mrowzowski: 3TE-2
Mularz, E.J.: 1K-8
Murphy, F.V.: 1N-4
Neuberger, M.: 1N-7, 1K-9, 1R-13, 3N-7 3K-9 3SE-6, 3TE-3 3R-12, 3T-10
Newall, A.J.: 2N-8, 2K-10
Nichols, L.W.: 1T-3
Nozieres, P.: 2SE-6, 2R-1
Olechna, D.J.: 1M-12
Olsen, A.L. 1T-3
Olson, O.H.: 1TE-4, 3TE-4
Olt, R.D.: 1N-8, 1K-10, 1T-16, 1T-18, 1SE-12, 3SE-7, 3T-11
Omori, K.: 2T-5
Oppenheim, U.P.: 1K-11, 1R-14, 1T-17, 3K-10, 3T-12
Park, C.: 2M-18
Peckham, G.: 3M-17
Philipp, H.R.: 2K-11, 2R-5, 2M-22

II-5 (Continued)

Phillippi, C. M.: 4R-2, 4T-5

Piper, J.: 1N-2, 1K-4, 1R-9, 1T-6

Piriou, B.: 1N-9, 1K-12, 1K-13, 1R-7, 1R-15, 1T-19, 3N-8, 3K-11, 3K-12, 3R-6, 3R-13, 4K-1, 4R-3, 4T-6

Plass, G.N.: 1M-13, 1M-14, 1M-15, 2M-21, 3M-13, 3M-14

Plendl, J.N.: 1R-16, 1T-10, 3N-4, 3K-5, 3K-13, 3R-8, 3R-9, 3R-14

Plunkett, J.D.: 2SE-15, 2TE-5

Plyler, E.D.: 3M-15

Poliakova, N.G.: 1M-3

Price, W.C.: 3K-14

Prikhod'ko, L.V.: 1K-14

Pruniaux, B.: 1T-2

Queiser, J.A.: 2M-7

Raman, C.V.: 3T-14

Ramsey, J.B.: 1M-10

Rao, C.N.R.: 1T-21, 3M-21

Reddy, B.K.: 4TE-2

Richmond, J.C.: 1SE-13

Roberts, S.: 1N-10, 1T-20

Rodney, W.S.: 1N-4

Rohensow, W.M.: 2TE-6

Romanov, H.I.: 2SE-1

Rooney, T.P.: 1SE-1, 1R-2

Rowntree, R.F.: 3N-9, 3K-15

Runciman, W.A.: 3T-4

Rupprecht, G.: 3M-16

Russell, E.E.: 1N-11, 1K-15

Sacadura, J.F.O.: 3M-18

Sakhnorskii, M.Y.: 3M-19

Saksena, B.D.: 3N-10, 3R-15

Salama, L.A.T.: 1R-17

Sangster, M.J.L.: 3M-17

Sanders, C.F.: 1M-16, 2M-19

Sanders, C.L.: 3R-16

Sarofim, A.F.: 2N-1, 2K-2, 2SE-8

II-5 (Continued)

Sato, K.: 1T-7, 3T-7, 4T-2
Saunderson, D.H.: 3M-17
Scala, E.: 2SE-3
Schatz, E.A.: 1M-17, 1SE-14, 4M-5
Schwar, M.J.R.: 2N-3, 2K-5, 2SE-12
Schurer, K.: 2M-20
Scott, G.E.: 1K-1, 1T-4
Seaney, R.J.: 3M-20
Seban, R.A.: 1SE-3
Shalabutov, Yu.K.: 1R-18
Shina, V.: 4TE-2
Sibold, J.D.: 1K-1, 1T-4
Singh, R.D.: 3T-16
Skripak, V.N.: 1M-18
Smith, D.R.: 1N-3, 1K-5
Spiridonov, E.G.: 2SE-1
Spitzer, C.R.: 2SE-17, 2SE-19, 2TE-10
Srivastava, S.P.: 3T-15, 3T-16
Stierwalt, D.L.: 1SE-15, 1SE-16, 3SE-8, 3SE-9, 3SE-10
Stephens, R.E.: 3N-11
Straumanis, M.E.: 3TE-5
Streed, E.R.: 1N-12, 1K-16, 1SE-17
Stull, R.V.: 2M-21
Suemoto, Y.: 1T-15
Summitt, R.: 3T-6
Sutton, G.W.: 2SE-7
Taft, E.A.: 2K-11, 2R-5, 2M-22
Tamanovich, V.V.: 1M-2
Taylor, R.E.: 2TE-7
Thomson, A.: 2K-1, 2TE-2, 2M-2
Tipunin, Yu.V.: 1R-18
Touloukian, Y.W.: 1SE-18, 1TE-5, 2SE-16, 2TE-8, 3SE-11, 3TE-6
3R-17, 4SE-6, 4TE-3, 4R-4
Tremorne, D.M.: 2N-6, 2E-8

II-5 (Continued)

Tret'yarkov, Y.D.: 3TE-7

Tresvyatskii, S.G.: 3T-17

Troshkina, V.A.: 3TE-7

Tsakiris, J.: 4K-1, 4R-3, 4T-6

Twitty, J.T.: 2N-9, 2K-12

Vishevskii, I.I.: 1M-18

Viswanathan, S.: 3N-10, 3R-15

Volz, F.E.: 2M-33

Vratney, F.: 1T-21, 3M-21

Waldman, J.L.: 2M-24

Walline, P.E.: 2M-4

Weinman, J.A.: 2N-9, 2K-12

Whateley, T.L.: 3T-2

White, W.B.: 1T-22

Wickramasinghe, N.C.: 2M-25

Wilkinson, G.R.: 3K-14

Williams, M.W.: 2N-10, 2K-13, 2R-6

Willis, C.: 2M-26

Wilmott, J.C.: 3N-12, 3K-16

Wilson, R.G.: 2SE-17, 2SE-18, 2SE-19, 2TE-9, 2TE-10, 2R-7, 4SE-7, 4R-5

Wittenberg, A.M.: 1TE-6

Wolfe, W.L.: 1M-4

Wood, G.C.: 1T-18

Wood, W.D.: 1SE-19, 1TE-7, 2SE-20, 2TE-11, 3SE-12, 3TE-8 4SE-8, 4TE-4

Worster, B.W.: 1SE-20, 1M-19

Wu, C.K.: 3M-2

Yamada, H.Y.: 2SE-21

II-5 (Continued)

Yamaguchi, N.: 1T-7, 3T-7, 4T-2
Yaremenko, Z.A.: 3T-17
Yasinsky, J.B.: 2T-6, 2M-16
Yates, D.J.B.: 3M-15
Yoshinaga, H.: 1T-15
Yuen, M.C.: 1K-8
Zhorov, G.A.: 3M-22
Ziegler, W.T.: 1M-8, 1M-9, 3M-6, 3M-7, 4M-1, 4M-2

III-1. ALUMINUM OXIDE DATA

III-1.1 Tabulated Refractive Index Data-Aluminum Oxide

Contents:

1N-2: Harris and Piper; films of 200 Å to 2800 Å thickness, T = 300°K (unspecified).

1N-3: Loewenstein; n_o and n_e at T = 1.5 and 300°K, 50μ to 300μ for sapphire.

1N-5: Malitson; n_o of sapphire at T = 297°K.

1N-9: Piriou; sapphire at T = 293°K, 1773°K.

1N-10: Roberts; sapphire, T = 300°K, $\lambda > 100\,\mu$.

1N-11: Russell; sapphire, T = 300°K, $\lambda > 60\,\mu$.


1N-12: Streed; sapphire at T = 300°K an 925°K, alumina powders at T = 300°K.


Harris and Piper (Ref. 1N-2)


The refractive index of aluminum oxide films of 200 to 2800 Å thickness was determined using a grating spectrograph to measure transmittance and reflectance. No spectrometer bandpass or experimental error estimate was given. Data were digitized from a line.

No representative curve for films was constructed.

λ	n	λ	n	λ	n	λ	n
15.103	1.777E+00	17.085	1.985E+00	19.025	2.093E+00	21.103	2.197E+00
22.939	2.698E+00	23.615	2.262E+00	25.839	2.389E+00	27.661	2.482E+00
27.978	2.250E+00	31.438	2.527E+00	33.283	2.394E+00	36.362	2.344E+00
36.731	2.799E+00	38.150	2.482E+00	41.251	2.417E+00	46.278	2.355E+00
53.360	2.194E+00	60.392	1.955E+00	66.458	1.757E+00	68.867	1.579E+00


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-2
ALUMINUM OXIDE FILM
T=273 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1N-2
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
.5
1.0
1.5
2.0
2.5
3.0
3.5
4.0
4.5
5.0
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-2
ALUMINUM OXIDE FILM
T=273 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1N-2
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
.5
1.0
1.5
2.0
2.5
3.0
3.5
4.0
4.5
5.0
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-2
ALUMINUM OXIDE FILM
T=273 K
HARRIS, J.OPT.SOC. 52, 223 (1962)
REF. 1N-2
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
.5
1.0
1.5
2.0
2.5
3.0
3.5
4.0
4.5
5.0

Loewenstein (Ref. 1N-3)

Long wavelength refractive index measurements were made on sapphire at T = 1.5°K and 300°K using a far infrared Michaelson interferometer. The sapphire purity was not given, but no differences n_o or n_e were observed between the sapphire and ruby containing 0.9 percent Cr, 0.05 percent each Fe and Ti, and less than 0.001 percent of other impurities. No spectral bandpass information was given. Uncertainty in n is given as ± 0.002. Data were taken from tables.


These tables were selected to construct the representative curve from 33μ to 55μ given in Section I, Figure I-1.1.


a. Ordinary Ray, T = 300°T


λ	n	λ	n	λ	n
333.333	3.069E+00	250.000	3.072E+00	200.000	3.076E+00
166.667	3.080E+00	142.857	3.085E+00	125.000	3.090E+00
111.111	3.097E+00	100.000	3.105E+00	90.909	3.114E+00
83.333	3.125E+00	76.923	3.136E+00	71.429	3.149E+00
66.667	3.164E+00	62.500	3.180E+00	58.824	3.198E+00
55.556	3.218E+00	52.632	3.241E+00		

b. Ordinary Ray, T = 1.5°K

λ	n	λ	n	λ	n
333.333	3.052E+00	250.000	3.055E+00	200.000	3.058E+00
166.667	3.062E+00	142.857	3.068E+00	125.000	3.073E+00
111.111	3.079E+00	100.000	3.087E+00	90.909	3.096E+00
83.333	3.106E+00	76.923	3.119E+00	71.429	3.132E+00
66.667	3.147E+00	62.500	3.167E+00	58.824	3.180E+00
55.556	3.198E+00	52.632	3.220E+00	50.000	3.240E+00
47.619	3.260E+00	45.455	3.287E+00	43.478	3.320E+00
41.667	3.350E+00	40.000	3.385E+00	38.462	3.428E+00
37.037	3.451E+00	35.714	3.522E+00	34.483	3.578E+00
33.333	3.636E+00				


REFRACTIVE INDEX OF ALUMINUM OXIDE
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
FIGURE 1N-3A
SAPPHIRE. ORDINARY RAY
T=300 K
LOEWENSTEIN. APP. OPT. 12, 398 (1973)
REF. 1N-3


REFRACTIVE INDEX OF ALUMINUM OXIDE
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
0.0
1.0
2.0
3.0
4.0
5.0
FIGURE 1N-38
SAPPHIRE. ORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12.398 (1973)
REF. 1N-3


REFRACTIVE INDEX OF ALUMINUM OXIDE
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
0.0
1.0
2.0
3.0
4.0
FIGURE 1N-38
SAPPHIRE. ORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12.398 (1973)
REF. 1N-3


Loewenstein (Ref. 1N-3)

c. Extraordinary Ray, T = 300°K

λ	n	λ	n	λ	n
333.333	3.415E+00	250.000	3.420E+00	200.000	3.428E+00
166.667	3.436E+00	142.857	3.445E+00	125.000	3.455E+00
111.111	3.470E+00	100.000	3.485E+00	90.909	3.502E+00
83.333	3.524E+00				

d. Extraordinary Ray, T = 1.5°K

λ	n	λ	n	λ	n
333.333	3.372E+00	250.000	3.377E+00	200.000	3.382E+00
166.667	3.388E+00	142.857	3.396E+00	125.000	3.408E+00
111.111	3.416E+00	100.000	3.432E+00	90.909	3.451E+00
83.333	3.470E+00	76.923	3.498E+00	71.429	3.511E+00
66.667	3.535E+00	62.500	3.555E+00	58.824	3.595E+00
55.556	3.630E+00	52.632	3.607E+00	50.000	3.708E+00
47.619	3.755E+00	45.455	3.805E+00	43.478	3.858E+00
41.667	3.928E+00	40.000	3.993E+00	38.462	4.075E+00
37.037	4.160E+00	35.714	4.245E+00	34.483	4.315E+00


REFRACTIVE INDEX OF ALUMINUM OXIDE
REFRACTIVE INDEX, N
5.0
4.5
4.0
3.5
3.0
2.5
2.0
1.5
1.0
.5
0.0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)
FIGURE 1N-3C
SAPPHIRE, EXTRAORDINARY RAY
T=300 K
LOEWENSTEIN, APP. OPT. 12, 398 (1973)
REF. 1N-3




FIGURE 1N-3D
SAPPHIRE. EXTRAORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12. 398 (1973)
REF. 1N-3




FIGURE 1N-3D
SAPPHIRE. EXTRAORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12. 398 (1973)
REF. 1N-3

Malitson (Ref. 1N-5)

n_{ord} was measured at 297°K for a synthetic sapphire prism from Linde Co.; n is reported accurate to the fifth decimal place, and fits the n_{calc} equation below to an accuracy of $n_{obs} - n_{calc} \leq 8 \times 10^{-5}$ from 0.265μ to 5.58 μ. These data were taken from a table.


$$n^2_{calc} - 1 = \sum_i \frac{A_i \lambda^2}{\lambda^2 - \lambda_i^2}$$

where

$\lambda_1 = 0.06144821$
$\lambda_2 = 0.1106997$
$\lambda_3 = 17.92656$
$A_1 = 1.023798$
$A_2 = 1.058264$
$A_3 = 5.280792$

These data were selected to construct the representative curve given in Section I, Figure I-1.1.

λ(μ)	n	λ	n	λ	n	λ	n
0.8944	1.75796	1.01398	1.75547	1.12866	1.75339	1.36728	1.74936
1.39506	1.74888	1.52952	1.74660	1.6932	1.74368	1.70913	1.74340
1.81307	1.74144	1.9701	1.73833	2.1526	1.73444	2.24929	1.73231
2.32542	1.73057	2.4374	1.72783	3.2439	1.70437	3.2668	1.70356
3.3026	1.70231	3.3303	1.70140	3.422	1.69818	3.5070	1.69504
3.7067	1.68746	4.2553	1.66371	4.954	1.62665	5.1456	1.61514
5.349	1.60202	5.419	1.59735	5.577	1.58638		


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-5
SAPPHIRE
T=300 K
MALITSON, J. OPT. SOC. 52, 1377 (1962)
REF. 1N-5
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
5.0
4.5
4.0
3.5
3.0
2.5
2.0
1.5
1.0
.5
0.0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


Piriou (Ref. 1N-9)


A grating spectrometer with an unspecified bandpass was used to measure the refractive index of sapphire (α - Al_2O_3) at T = 293°K and 1773°K. Tempe.atures were measured to ±1° using an optical pyrometer. No error analysis was given. Data were digitized from lines.

These data were selected to construct the representative curve given in Section I, Figure I-1.1.

a. T = 293°K

λ	n	λ	n	λ	n
33.190	3.761E+00	31.407	3.842E+00	30.204	3.905E+00
28.901	4.158E+00	27.805	4.530E+00	27.227	4.826E+00
26.730	5.274E+00	26.323	5.621E+00	26.276	5.007E+00
26.182	4.517E+00	25.969	3.373E+00	25.589	4.086E+00
25.193	4.681E+00	24.617	5.453E+00	24.227	6.077E+00
23.937	8.940E+00	23.779	7.545E+00	23.563	8.374E+00
23.466	8.919E+00	23.314	9.798E+00	23.216	1.042E+01
23.100	1.133E+01	23.049	1.187E+01	23.049	1.280E+01
23.017	1.421E+01	22.836	9.408E+00	22.731	6.870E+00
22.727	5.416E+00	22.647	3.813E+00	22.554	2.202E+00
22.472	1.315E+00	22.252	7.232E-01	21.647	1.183E-01
21.437	6.246E-02	21.246	1.611E-01	20.833	4.668E-01
20.717	8.777E-01	20.630	1.197E+00	20.422	1.828E+00
20.147	2.396E+00	19.782	3.044E+00	19.554	3.399E+00
19.174	3.988E+00	18.916	4.395E+00	18.581	5.066E+00
18.406	5.605E+00	18.221	6.510E+00	18.134	7.022E+00
18.012	7.862E+00	17.927	8.341E+00	17.840	9.263E+00
17.731	9.772E+00	17.702	1.068E+01	17.666	1.119E+01
17.621	1.195E+01	17.498	9.955E+00	17.480	6.672E+00
17.425	5.218E+00	17.359	4.020E+00	17.274	2.646E+00
17.211	1.686E+00	17.138	1.275E+00	16.941	6.377E-01
16.678	4.438E-01	16.329	3.324E-01	16.198	4.372E-01
16.007	6.476E-01	15.858	1.111E+00	15.7[illegible]	[illegible]
15.719	1.631E+00	15.569	4.504E-01	15.395	6.[illegible]
14.272	1.315E-02	12.964	1.315E-02	11.863	1.315E-02
11.223	1.644E-02	10.356	1.374E-01	10.552	5.293E-01
10.200	7.857E-01	9.906	9.106E-01	9.639	1.012E+00
9.317	1.039E+00	9.111	1.026E+00		



REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-9A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1N-9
REFRACTIVE INDEX. N
WAVELENGTH(MICRONS)



REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-9A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1N-9
REFRACTIVE INDEX. N
WAVELENGTH(MICRONS)

Piriou (Ref. 1N-9)

b. T = 1773°K

λ	n	λ	n	λ	n
33.290	3.9d0E+00	30.751	4.341E+00	28.875	4.732E+00
27.859	4.958E+00	26.965	4.576E+00	26.393	4.951E+00
25.859	5.332E+00	25.312	5.582E+00	25.033	5.672E+00
24.719	5.525E+00	24.508	5.197E+00	24.097	4.095E+00
23.801	3.348E+00	23.472	2.608E+00	23.177	1.928E+00
22.949	1.817E+00	22.640	1.741E+00	22.275	1.831E+00
21.693	2.283E+00	21.170	2.881E+00	20.633	3.542E+00
20.195	4.180E+00	19.764	4.747E+00	19.460	5.233E+00
19.222	5.367E+00	19.021	5.139E+00	18.887	4.963E+00
18.796	4.166E+00	18.506	3.392E+00	18.257	2.738E+00
17.957	2.114E+00	17.789	1.833E+00	17.544	1.464E+00
17.016	1.267E+00	16.784	1.154E+00	16.373	9.126E-01
16.173	7.599E-01	15.876	5.453E-01	15.302	5.215E-01
14.629	4.642E-01	13.959	4.324E-01	13.361	3.927E-01
12.783	3.784E-01	12.266	3.736E-01	12.050	3.736E-01
11.730	4.038E-01	11.337	5.103E-01	10.929	7.202E-01
10.651	8.474E-01	10.359	9.173E-01	10.036	9.936E-01
9.724	1.087E+00	9.430	1.159E+00		


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-98
SAPPHIRE
T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1N-9
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)



REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-98
SAPPHIRE
T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1N-9
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)

Roberts and Coon (Ref. IN-10)

n_o was measured for sapphire at $T \simeq 300^{\circ}K$ (unspecified room temperature) using a Czerny-Turner type grating monochromator with unspecified bandpass. The largest error was estimated to be ± 0.012, or ±0.1 percent. Data were digitized from a fitted straight line.

These data are in good agreement with the representative curve given in Section I.

λ	n	λ	n	λ	n	λ	n
113.000	3.092E+00	129.000	3.084E+00	158.000	3.076E+00	224.000	3.068E+00
302.000	3.056E+00						


REFRACTIVE INDEX OF ALUMINUM OXIDE
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
FIGURE 1N-10
SAPPHIRE
T=300 K
ROBERTS, J. OPT. SOC. 52, 1023 (1962)
REF. 1N-10

Russell (1N-11)

An asymmetric Fourier-transform method was used to measure n_o and n_e for sapphire. $T \cong 300^oK$ (unspecified room temperature). The total estimated probable error was ± 0.002 for 60 μ to 500 μ. These data were taken from a table.

These data were selected to construct the representative curve given in Section I, Figure I-1.1.

a. n_o

λ	n	λ	n	λ	n
4.950E+02	3.069E+00	3.968E+02	3.070E+00	3.311E+02	3.070E+00
2.833E+02	3.072E+00	2.481E+02	3.074E+00	2.203E+02	3.075E+00
1.984E+02	3.077E+00	1.805E+02	3.079E+00	1.653E+02	3.082E+00
1.527E+02	3.084E+00	1.416E+02	3.087E+00	1.323E+02	3.091E+00
1.241E+02	3.094E+00	1.167E+02	3.098E+00	1.103E+02	3.102E+00
1.044E+02	3.106E+00	9.921E+01	3.110E+00	9.452E+01	3.115E+00
9.017E+01	3.120E+00	8.628E+01	3.125E+00	8.271E+01	3.130E+00
7.937E+01	3.136E+00	7.634E+01	3.142E+00	7.348E+01	3.146E+00
7.087E+01	3.155E+00	6.845E+01	3.162E+00	6.614E+01	3.170E+00
6.402E+01	3.176E+00	6.200E+01	3.185E+00	6.013E+01	3.192E+00
5.838E+01	3.202E+00	5.669E+01	3.211E+00		

b. n_e

λ	n	λ	n	λ	n
4.950E+02	3.411E+00	2.833E+02	3.416E+00	1.984E+02	3.426E+00
1.527E+02	3.439E+00	1.241E+02	3.457E+00	1.044E+02	3.477E+00
9.017E+01	3.499E+00	7.937E+01	3.528E+00	7.087E+01	3.561E+00
6.402E+01	3.604E+00	5.968E+02	3.413E+00	2.481E+02	3.419E+00
4.805E+02	3.429E+00	1.416E+02	3.444E+00	1.167E+02	3.462E+00
3.921E+01	3.484E+00	8.628E+01	3.508E+00	7.634E+01	3.537E+00
6.845E+01	3.575E+00	3.311E+02	3.413E+00	2.203E+02	3.423E+00
1.653E+02	3.433E+00	1.323E+02	3.451E+00	1.103E+02	3.469E+00
9.452E+01	3.491E+00	8.271E+01	3.518E+00	7.348E+01	3.551E+00
6.614E+01	3.586E+00				




FIGURE 1N-11A
SAPPHIRE, ORDINARY RAY
T=300 K
RUSSELL, J. OPT. SOC. 57, 543 (1967)
REF. 1N-11




FIGURE 1N-11B
SAPPHIRE, EXTRAORDINARY RAY
T=300 K
RUSSELL, J. OPT. SOC. 57, 543 (1967)
REF. 1N-11

Streed (1N-12)

The refractive index of alumina particles of 1μ diameter and 99.95 percent purity and sapphire of 99.99 percent purity were measured using Kramers-Kronig analyses of polarized specular reflectance data obtained using a KBr prism spectrometer with a bandwidth of 0.016 μ to 0.15 μ. No error analysis was given. The data were taken from tables.


None of these data are in agreement with the representative curve given in Section I.


a. Alumina powder, first root of the Fresnel equation, T = 300°K.

λ	n	λ	n	λ	n	λ	n
2.000	31.300	2.500	22.950	3.000	5.360	3.500	7.620
4.000	10.810	5.000	9.660	6.000	5.670	7.000	2.590
8.000	1.560	9.000	0.000	10.000	0.000	10.500	0.000
11.000	0.000	12.000	1.970	13.000	2.010	14.000	1.980
15.000	2.080	16.000	2.080	17.000	2.440	18.000	2.310
19.000	2.370	20.000	1.340	21.000	1.870		

b. Alumina powder, second root of the Fresnel equation, T = 300°K.

λ	n	λ	n	λ	n	λ	n
2.000	.030	2.500	.040	3.000	.190	3.500	.130
4.000	.090	5.000	.100	6.000	.180	7.000	.370
8.000	.740	9.000	0.000	10.000	0.000	10.500	0.000
11.000	0.000	12.000	.520	13.000	.510	14.000	.530
15.000	.490	16.000	.530	17.000	.410	18.000	.440
19.000	.500	20.000	1.020	21.000	.600		


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12A
ALUMINA POWDER
T=300 K
STREED, AFRPL-TR-73-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0.0
3.5
7.0
10.5
14.0
17.5
21.0
24.5
28.0


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12B
ALUMINA POWDER
T=300 K
STREED, AFRPL-TR-73-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0.0
1.0
2.0
3.0
4.0


Streed (Ref. 1N-12)


c. Alumina flame sprayed powder, first root of the Fresnel equation, T = 300°K.

λ	n	λ	n	λ	n	λ	n
2.000	13.610	2.500	12.200	3.000	5.510	3.500	8.130
4.000	9.320	5.000	6.950	6.000	2.770	7.000	1.740
8.000	8.300	9.000	8.000	10.000	8.000	10.500	2.920
11.000	3.160	12.000	2.840	13.000	2.470	14.000	2.490
15.000	2.540	16.000	2.630	17.000	2.650	18.000	2.570
19.000	2.430	20.000	2.399	21.000	2.310		

d. Alumina flame sprayed powder, second root of the Fresnel equation, T = 300°K.

λ	n	λ	n	λ	n	λ	n
2.000	.070	2.500	.080	3.000	.180	3.500	.120
4.000	.120	5.000	.140	6.000	.360	7.000	.610
8.000	0.300	9.000	0.000	10.000	0.000	10.500	.340
11.000	.320	12.000	.350	13.000	.410	14.000	.400
15.000	.390	16.000	.380	17.000	.380	18.000	.390
19.000	.410	20.000	.420	21.000	.440		


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12C
ALUMINA FLAME SPRAYED POWDER
T=300 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12D
ALUMINA FLAME SPRAYED POWDER
T=300 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)


Streed (Ref. 1N-12)


e. Sapphire, first root of the Fresnel equation, T = 300°K

λ	n	λ	n	λ	n	λ	n
2.000	1.850	4.000	1.840	6.000	1.740	7.000	1.500
7.500	1.440	8.000	1.420	9.000	1.280	10.000	1.360
10.400	1.680	10.800	3.370	11.000	5.460	12.000	29.970
13.000	42.420	14.000	61.480	15.000	32.160	16.000	17.450
17.000	19.340	17.500	13.310	18.000	7.620	19.000	4.640
19.500	3.770	20.000	2.970	20.500	3.230	21.000	5.278
22.000	3.433						

f. Sapphire, second root of the Fresnel equation, T = 300°K.

λ	n	λ	n	λ	n	λ	n
2.000	5.400E-01	4.000	5.400E-01	6.000	5.700E-01	7.000	6.600E-01
7.500	6.300E-01	8.000	7.000E-01	9.000	7.800E-01	10.000	7.400E-01
10.400	2.600E-01	10.800	3.000E-01	11.000	1.800E-01	12.000	3.000E-02
13.000	5.000E-02	14.000	2.600E-02	15.000	3.000E-02	16.000	6.000E-02
17.000	9.000E-02	17.500	8.000E-02	18.000	1.300E-01	19.000	2.200E-01
19.500	6.700E-01	20.000	3.400E-01	20.500	3.100E-01	21.000	2.000E-02
22.000	3.000E-02						


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12E
SAPPHIRE
T=300 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12F
SAPPHIRE
T=300 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


Streed (Ref. 1N-12)


g. Sapphire, first root of the Fresnel equation, T = 925°K

λ	n	λ	n	λ	n	λ	n
2.000	1.850	4.000	1.840	6.000	1.740	7.000	1.500
7.500	1.480	8.000	1.460	9.000	1.280	10.000	1.250
10.400	1.560	10.800	2.520	11.000	3.540	12.000	19.930
13.000	47.980	14.000	76.420	15.000	62.500	16.000	20.170
17.000	28.970	17.500	16.120	18.000	8.910	19.000	6.210
19.500	4.600	20.000	3.910	20.500	2.820	21.000	5.780
22.000	47.980						

h. Sapphire second root of the Fresnel equation, T = 925°K

λ	n	λ	n	λ	n	λ	n
6.000	5.400E-01	4.000	5.400E-01	6.000	5.700E-01	7.000	6.600E-01
7.500	6.800E-01	8.000	6.800E-01	9.000	7.800E-01	10.000	7.900E-01
10.400	6.400E-01	10.800	4.000E-01	11.000	2.800E-01	12.000	5.000E-02
13.000	2.000E-02	14.000	1.000E-02	15.000	2.000E-02	16.000	5.000E-02
17.000	3.000E-02	17.500	6.000E-02	18.000	1.100E-01	19.000	1.600E-01
19.500	2.200E-01	20.000	2.600E-01	20.500	3.600E-01	21.000	1.700E-01
22.000	2.000E-02						


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12H
SAPPHIRE
T=925 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFRACTIVE INDEX OF ALUMINUM OXIDE
FIGURE 1N-12G
SAPPHIRE
T=925 K
STREED. AFRPL-TR-63-3
REF. 1N-12
REFRACTIVE INDEX, N
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

III-1 2 Tabulated Extinction Coefficient Data - Aluminum Oxide

Contents:

1K-1: Grimm; G.E. Lucalox, T = 300°K.

1K-2: Gryvnak; sapphire, T - 296 to 2293°K.

1K-4: Harris; aluminum oxide films 200 to 2800 Å thick.

1K-5: Loewenstein; sapphire, T = 1.5 and 300°K.

1K-6: Mergerian; sapphire, T = 373 to 1273°K.

1K-10: Olt; sapphire, T = 300°K.

1K-11: Oppenheim; sapphire, T = 293 to 1273°K.

1K-12: Piriou; sapphire, T = 77°K and 293°K.

1K-13: Piriou; sapphire, T = 293°K and 1773°K.

1K-15: Russell; sapphire, k_o and k_e, T = 300°K.


1K-16: Streed; sapphire at T = 300°K, alumina powder at T = 300, 1000, 1500, and 2000°K.

Grimm (Ref. 1K-1)

The in-line loss coefficient of General Electric Lucalox high density polycrystalline alumina with 0.2 percent MgO content, a density of 3.975 g/cm^3, and grain size of 27 $\pm$ 3μ was measured on a Perkin-Elmer 337 double beam spectrophotometer with an undisclosed bandpass. No error analysis or temperature was given. Data were digitized from a curve.

These data were selected to construct the representative curve presented in Section I, Figure I - 1.2.

λ	k	λ	k	λ	k
2.062	6.530E-07	2.244	6.661E-07	2.381	6.783E-07
2.5+0	6.904E-07	2.694	7.031E-07	2.885	7.268E-07
3.092	7.524E-07	3.280	7.810E-07	3.4+4	8.095E-07
3.554	8.360E-07	3.658	8.727E-07	3.830	9.471E-07
3.9+8	1.014E-06	4.089	1.110E-06	4.230	1.218E-06
4.350	1.337E-06	4.491	1.502E-06	4.613	1.682E-06
4.7+1	1.899E-06	4.853	2.148E-06	4.929	2.336E-06
5.015	2.559E-06	5.081	2.795E-06	5.133	3.102E-06
5.171	3.709E-06	5.212	4.583E-06	5.256	5.859E-06
5.299	7.850E-06	5.346	1.084E-05	5.384	1.374E-05
5.434	1.813E-05	5.478	2.338E-05		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-1
CE LUCALOX ALUMINA
T=300 K
GRIMM. AM. CERAM. SOC. BUL. 50, 962
(1971)
REF. 1K-1
EXTINCTION INDEX, K
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

Gryvnak (Ref. 1K-2)

The absorption coefficient of sapphire from 1 to 6 μ and T = 296 to 2293°K using a Perkin Elmer 112 spectrometer with an NaCl prism with an unspecified bandpass. For values of $k < 0.001$ mm^{-1} the estimated error may be as high as 30 percent. For $k > 0.001$ mm^{-1}, the estimated error is less than 15 percent. These data were digitized from continuous curves.

These data are in good agreement with the representative curve given in Section I-1.2.

a. T = 296°K


λ	k	λ	k	λ	k	λ	k
4.317	3.683E-07	4.239	1.820E-06	4.405	2.804E-06	4.586	4.463E-06
4.774	9.950E-06	5.008	1.140E-05	5.246	1.809E-05	5.469	2.713E-05
5.699	3.966E-05	5.266	5.349E-05	6.059	7.354E-05		


b. T = 673°K

λ	k	λ	k	λ	k	λ	k
3.697	1.332E-06	3.849	2.321E-06	4.001	3.035E-06	4.156	4.534E-06
4.314	6.930E-06	4.462	9.982E-06	4.653	1.507E-05	4.845	2.227E-05
5.024	3.113E-05	5.216	4.451E-05	5.402	6.262E-05	5.595	8.021E-05
5.556	9.518E-05						

c. T = 1073°K

λ	k	λ	k	λ	k	λ	k
3.923	1.112E-06	4.101	1.879E-06	4.271	2.948E-06	4.451	4.594E-06
4.626	9.988E-06	4.837	1.106E-05	5.034	1.662E-05	5.226	2.383E-05
5.397	3.292E-05	5.559	4.355E-05	5.743	6.128E-05		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2B
SAPPHIRE
T=673 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2A
SAPPHIRE
T=296 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Gryvnak (Ref. 1K-2)

d. T = 1473°K


λ	k	λ	k	λ	k	λ	k
.511	1.232E-07	.578	3.633E-08	.681	8.171E-08	.815	7.048E-08
.974	5.300E-08	1.176	5.133E-08	1.412	4.660E-08	1.946	4.677E-08
1.360	4.977E-08	2.096	2.204E-08	2.161	5.749E-08	2.403	7.079E-08	
2.021	9.989E-08	2.[illegible]	1.130E-07	2.914	1.551E-07	3.047	2.257E-07
3.209	4.004E-07	3.[illegible]	7.[illegible]E-07	3.518	1.399E-06	3.697	2.510E-06
3.851	4.337E-06	4.[illegible]	7.927E-06	4.309	1.321E-05	4.535	2.083E-05
4.[illegible]0	3.210E-05	[illegible]	4.618E-05	5.146	6.225E-05	5.282	7.817E-05


e. T = 1773°K


λ	k	λ	k	λ	k	λ	k
.[illegible]63	2.521E-07	.621	2.763E-07	.822	2.861E-07	1.042	2.877E-07
1.[illegible]23	2.[illegible]62E-07	1.[illegible]69	2.[illegible]72E-07	1.775	2.935E-07	2.073	3.110E-07
2.[illegible]38	3.[illegible]22E-07	2.[illegible]43	3.[illegible]44E-07	2.[illegible]04	3.[illegible]62E-07	2.[illegible]3	3.[illegible]58E-07
2.938	3.[illegible]90E-07	3.123	4.[illegible]33E-07	3.280	1.067E-06	3.[illegible]3	1.626E-06
3.608	2.[illegible]09E-06	3.783	4.251E-06	3.959	7.021E-06	4.[illegible]1	1.212E-05
4.[illegible]43	1.[illegible]88E-05	4.594	3.039E-05	4.789	4.419E-05	4.956	6.104E-05
5.113	8.[illegible]7E-05						


f. T = 1873°K

λ	k	λ	k	λ	k	λ	k
.506	5.173E-07	.702	5.765E-07	.952	6.220E-07	1.212	6.313E-07
1.529	6.322E-07	1.872	6.441E-07	2.[illegible]23	6.636E-07	2.397	7.100E-07
2.[illegible]05	7.[illegible]97E-07	2.700	8.167E-07	2.900	9.385E-07	3.[illegible]17	1.185E-06
3.291	1.539E-06	3.[illegible]82	2.353E-06	3.615	3.396E-06	3.761	5.314E-06
3.899	7.013E-06						


EXTINCTION INDEX OF ALUMINUM OXIDE
1E-3
1E-4
1E-5
1E-6
1E-7
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1K-2C
SAPPHIRE
T=1073 K
GRYUNAK. J. OPT. SOC. 55. 625 (1965)
REF. 1K-2


EXTINCTION INDEX OF ALUMINUM OXIDE
1E-4
1E-5
1E-6
1E-7
1E-8
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1K-2D
SAPPHIRE
T=1473 K
GRYUNAK. J. OPT. SOC. 55. 625 (1965)
REF. 1K-2


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2E
SAPPHIRE
T=1773 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
EXTINCTION INDEX, K
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2F
SAPPHIRE
T=1873 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
EXTINCTION INDEX, K
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


Gryvnak (Ref. 1K-2)


g. T = 1973°K

λ	k	λ	k	λ	k	λ	k
.538	7.706E-07	.786	8.974E-07	1.085	9.596E-07	1.336	9.846E-07
1.621	1.006E-06	1.947	1.042E-06	2.280	1.064E-06	2.605	1.15[illegible]-06
2.827	1.248E-06	3.054	1.454E-06	3.271	1.823E-06	3.450	2.593[illegible]-06
3.608	3.851E-06	3.789	5.997E-06	3.920	8.355E-06	4.040	1.109E-05

h. T= 2293°K

λ	k	λ	k	λ	k	λ	k
1.973	1.143E-06	2.206	1.229E-06	2.404	1.310E-06	2.584	1.417E-06
2.816	1.597E-06	3.032	1.837E-06	3.281	2.356E-06	3.451	3.085E-06
3.618	4.710E-06	3.809	7.897E-06	3.997	1.249E-05	4.214	2.078E-05
4.423	3.308E-05	4.663	5.447E-05	4.902	8.522E-05	5.120	1.231E-04
5.376	1.863E-04	5.597	2.614E-04	5.793	3.460E-04		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2G
SAPPHIRE
T=1973 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
1E-3
1E-4
1E-5
1E-6
1E-7
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20
22.5
25.
WAVELENGTH(MICRONS)



EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-2H
SAPPHIRE
T=2293 K
GRYUNAK, J. OPT. SOC. 55, 625 (1965)
REF. 1K-2
1E-3
1E-4
1E-5
1E-6
1E-7
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


Harris (Ref. 1K-4)


The extinction index of aluminum oxide films of 200 to 2800 Å thickness was determined using a grating spectrograph to measure transmittance. No spectrometer bandpass or experimental error estimate was given. Data were digitized from a line.

No representative curve for film was constructed.

λ	k	λ	k	λ	k	λ	k
15.148	1.350E+00	17.193	1.367E+00	19.063	1.260E+00	21.056	1.166E+00
23.662	1.129E+00	25.927	1.112E+00	27.810	1.050E+00	28.020	9.730E-01
31.474	8.053E-01	33.512	8.583E-01	36.679	7.412E-01	36.679	7.412E-01
38.169	6.501E-01	41.507	6.413E-01	53.415	5.265E-01	60.520	5.242E-01
66.532	4.712E-01						


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-4
ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1K-4
1E 2
1E 1
E 0
1E-1
EXTINCTION INDEX K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-4
ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1K-4
1E 2
1E 1
1E 0
1E-1
EXTINCTION INDEX K
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-4
ALUMINUM OXIDE FILM
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1K-4
EXTINCTION INDEX, K
WAVELENGTH MICRONS
1E 2
1E 1
1E 0
1E-1
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.

Loewenstein (Ref. 1K-5)

Long wavelength extinction index measurements were made on sapphire at T = 1.5°K and 300°K using a far infrared Michaelson interferometer. The sapphire purity was not given, but no differences in k_o or k_e were observed between the sapphire and ruby containing 0.9 percent Cr, 0.05 percent Fe and Ti, and less than 0.001 percent of other impurities. No spectral bandpass information was given. Uncertainty in k is ±10 percent for T = 300°K, and ±0.3 at 1.5°K. Data were taken from tables.


These data were selected to construct the representative curve of Section I, Figure I - 1.2.


a. Ordinary Ray, T = 300°K


λ	k	λ	k	λ	k
333.333	2.653E-03	250.000	2.387E-03	200.000	3.501E-03
166.667	4.377E-03	142.857	5.229E-03	125.000	5.769E-03
111.111	6.455E-03	100.000	6.923E-03	90.909	7.379E-03
83.333	7.958E-03	76.923	8.570E-03	71.429	9.095E-03
66.667	1.008E-02				

b. Ordinary Ray, T = 1.5°K

λ	k	λ	k	λ	k
333.333	2.653E-04	250.000	1.989E-04	200.000	1.592E-04
166.667	1.326E-04	142.857	1.137E-04	125.000	1.989E-04
111.111	1.768E-04	100.000	1.592E-04	90.909	1.447E-04
83.333	1.989E-04	76.923	1.836E-04	71.429	1.705E-04
66.667	2.122E-04	62.500	2.487E-04	58.824	2.341E-04
55.556	2.653E-04	52.632	2.932E-04	50.000	3.183E-04
47.619	3.410E-04	45.455	3.617E-04	43.478	4.152E-04


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-5A
SAPPHIRE. ORDINARY RAY
T=300 K
LOEWENSTEIN. APP. OPT. 12, 398 (1973)
REF. 1K-5
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX, K
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-5B
SAPPHIRE, ORDINARY RAY
T=1.5 K
LOEWENSTEIN, APP. OPT. 12,398 (1973)
REF. 1K-5
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX, K
0. 5. 10. 15. 20. 25. 30. 35. 40. 45. 50.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-5B
SAPPHIRE, ORDINARY RAY
T=1.5 K
LOEWENSTEIN, APP. OPT. 12,398 (1973)
REF. 1K-5
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX, K
0. 50. 100. 150. 200. 250. 300. 350. 400. 450. 500.
WAVELENGTH(MICRONS)


Loewenstein (Ref. 1K-5)


c. Extraordinary ray, T = 300°K


λ	k	λ	k	λ	k
333.333	5.040E-03	250.000	4.576E-03	200.000	5.093E-03
166.667	6.234E-03	142.857	7.617E-03	125.000	9.251E-03
111.111	1.149E-02	100.000	1.273E-02	90.909	1.375E-02
83.333	1.393E-02				

d. Extraordinary ray, T = 1.5°K

λ	k	λ	k	λ	k
333.333	2.653E-04	250.000	1.989E-04	200.000	1.592E-04
166.667	2.653E-04	142.857	2.274E-04	125.000	2.984E-04
111.111	3.537E-04	100.000	3.979E-04	90.909	5.064E-04
83.333	6.631E-04	76.923	7.958E-04	71.429	9.663E-04
66.667	1.167E-03	62.500	1.343E-03	58.824	1.498E-03
55.556	1.636E-03	52.632	1.675E-03	50.000	1.711E-03
47.619	1.705E-03	45.455	1.700E-03	43.478	1.661E-03
41.667	1.592E-03	40.000	1.528E-03	38.462	1.469E-03
37.037	1.415E-03	35.714	1.364E-03	34.483	1.399E-03


EXTINCTION INDEX OF ALUMINUM OXIDE
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX, K
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)
FIGURE 1K-5C
SAPPHIRE. EXTRAORDINARY RAY
T=300 K
LOEWENSTEIN. APP. OPT. 12.398 (1973)
REF. 1K-5


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-5D
SAPPHIRE. EXTRAORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12.398 (1973)
REF. 1K-5
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX. K
0. 5. 10. 15. 20. 25. 30. 35. 40. 45. 50.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-5D
SAPPHIRE. EXTRAORDINARY RAY
T=1.5 K
LOEWENSTEIN. APP. OPT. 12.398 (1973)
REF. 1K-5
1E 0
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX. K
0. 50. 100. 150. 200. 250. 300. 350. 400. 450. 500.
WAVELENGTH(MICRONS)

Mergerian (Ref. 1K-6)

The absorption coefficient of synthetic sapphire was measured using a Perkin-Elmer monochromator with an unspecified bandpass, at temperatures ranging from 373 to 1273°K. No error analysis was given. Data were digitized from specific points.


These data range from very much lower than the representative curve of Section I ($\lambda < 4\,\mu$) to good agreement (at 5 to 6 μ).


a. T = 373°K

λ	k	λ	k	λ	k	λ	k
1.009	3.257E-09	1.514	2.524E-09	2.477	2.209E-09	2.990	5.230E-09
4.033	2.838E-08	4.517	1.061E-07	5.004	3.911E-07	5.471	9.380E-07
5.985	2.292E-06						

b. T = 623°K

λ	k	λ	k	λ	k	λ	k
1.001	4.133E-09	1.475	2.313E-09	2.003	3.046E-09	2.485	3.898E-09
2.989	6.806E-09	3.521	3.100E-08	4.010	3.722E-08	4.505	1.128E-07
4.990	4.542E-07	5.466	1.067E-06	5.994	2.508E-06		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-6A
SAPPHIRE
T=373 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1K-6
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1.E-5
1.E-6
1.E-7
1.E-8
1.E-9
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-6B
SAPPHIRE
T=623 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1K-6
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1.E-5
1.E-6
1.E-7
1.E-8
1.E-9
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


Mergerian (Ref. 1K-6)


c. T = 1023°K

λ	k	λ	k	λ	k	λ	k
1.011	3.273E-09	1.488	4.260E-09	1.961	2.971E-09	2.494	3.692E-09
2.990	5.530E-09	3.498	1.129E-08	4.013	6.453E-08	4.513	2.161E-07
4.980	7.922E-07	5.473	1.895E-05	5.987	3.576E-06		

d. T = 1273°K

λ	k	λ	k	λ	k	λ	k
1.002	6.919E-09	1.493	9.909E-09	1.976	9.694E-09	2.501	7.910E-09
2.983	7.019E-09	3.494	1.422E-08	4.009	6.888E-08	4.493	2.614E-07
4.975	1.112E-06	5.457	2.724E-06	5.972	4.814E-06		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-6C
SAPPHIRE
T=1023 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1K-6
EXTINCTION INDEX, K
1E-5
1E-6
1E-7
1E-8
1E-9
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)



EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-6D
SAPPHIRE
T=1273 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1K-6
EXTINCTION INDEX, K
1E-5
1E-6
1E-7
1E-8
1E-9
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

Olt (Ref. 1K-10)

The absorption coefficient for clear Linde sapphire as measured by Beardsley is given. No error analyses or other experimental details are given. Digitized from a continuous curve.

These values are much lower than the representative curve of Section I - 1.2.

λ	k	λ	k	λ	k	λ	k
3.931	1.668E-06	4.014	3.119E-07	4.081	9.240E-08	4.161	3.317E-08
4.264	5.325E-08	4.355	7.629E-08	4.472	1.111E-07	4.601	1.611E-07
4.702	2.116E-07	4.838	2.951E-07	4.965	3.943E-07	5.105	5.335E-07
5.258	7.318E-07	5.416	1.007E-06	5.627	1.479E-06	5.840	2.150E-06
6.004	2.845E-06	6.160	3.726E-06	6.325	5.030E-06	6.435	6.289E-06
6.517	7.643E-06	6.609	9.629E-06				


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-10
SAPPHIRE
T=300 K
OPT. PROC. IRIS 3, 141 (1958)
REF. 1K-10
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E-5
1E-6
1E-7
1E-8
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Oppenheim (Ref. 1K-11)

A Perkin-Elmer 12G spectrometer with unspecified bandpass was used to measure the absorption coefficient of synthetic Meller Co. sapphire from 3μ to 6μ at temperatures ranging from 293 to 1273°K. The estimated accuracy of the data is 3 percent. The data were digitized from lines.


These values are slightly higher than the representative curve of Section I - 1.2.


a. T = 293°K

λ	k	λ	k	λ	k	λ	k
3.000	1.194E-08	3.940	5.487E-07	4.239	1.552E-06	4.332	2.620E-06
4.446	5.169E-06	4.591	1.078E-05	4.703	1.608E-05	4.862	2.553E-05
4.976	3.363E-05	5.069	4.078E-05	5.190	5.212E-05	5.297	6.352E-05
5.397	7.464E-05	5.482	8.590E-05	5.572	9.733E-05	5.649	1.088E-04
5.740	1.231E-04	5.810	1.353E-04	5.878	1.483E-04	5.953	1.634E-04
5.990	1.716E-04						

b. T = 773°K

λ	k	λ	k	λ	k	λ	k
3.000	9.549E-09	3.412	1.358E-07	3.819	5.045E-07	4.067	9.386E-07
4.158	1.343E-06	4.237	2.020E-06	4.319	2.997E-06	4.409	4.565E-06
4.496	6.544E-06	4.597	9.204E-06	4.679	1.203E-05	4.748	1.443E-05
4.828	1.801E-05	4.928	2.294E-05	4.994	2.693E-05	5.066	3.199E-05
5.134	3.729E-05	5.203	4.418E-05	5.269	5.078E-05	5.326	5.739E-05
5.385	6.514E-05	5.399	6.698E-05	5.414	7.092E-05		


EXTINCTION INDEX OF ALUMINUM OXIDE
1E-3
1E-4
1E-5
1E-6
1E-7
1E-8
1E-9
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1K-11A
SAPPHIRE
T=293 K
OPPENHEIM. J. OPT. SOC. 52, 1078(1962)
REF. 1K-11


EXTINCTION INDEX OF ALUMINUM OXIDE
1E-3
1E-4
1E-5
1E-6
1E-7
1E-8
1E-9
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1K-11B
SAPPHIRE
T=773 K
OPPENHEIM. J. OPT. SOC. 52, 1078(1962)
REF. 1K-11

Oppenheim (Ref. 1K-11)

c. T = 1073°K

λ	k	λ	k	λ	k	λ	k
3.001	3.209E-07	3.179	4.908E-07	3.402	8.365E-07	3.542	1.153E-06
3.690	1.462E-06	3.810	1.752E-06	3.904	2.172E-06	3.981	2.617E-06
4.072	3.704E-06	4.200	5.431E-06	4.267	7.701E-06	4.340	9.867E-06
4.428	1.296E-05	4.510	1.646E-05	4.596	2.080E-05	4.673	2.537E-05
4.736	2.960E-05	4.816	3.582E-05	4.889	4.280E-05	4.952	4.973E-05
5.012	5.739E-05	5.064	6.472E-05				

d. T = 1273°K

λ	k	λ	k	λ	k	λ	k
3.011	3.355E-06	3.241	4.787E-06	3.571	6.255E-06	3.766	7.630E-06
3.864	8.966E-06	3.977	1.271E-05	4.097	1.855E-05	4.206	2.599E-05
4.296	3.318E-05	4.369	4.002E-05	4.457	4.987E-05	4.539	6.032E-05
4.617	7.216E-05	4.691	8.493E-05	4.756	9.783E-05	4.818	1.114E-04
4.892	1.302E-04	4.949	1.463E-04	4.993	1.585E-04		




FIGURE 1K-11C
SAPPHIRE
T=1073 K
OPPENHEIM, J. OPT. SOC. 52, 1078(1962)
REF. 1K-11




FIGURE 1K-11D
SAPPHIRE
T=1273 K
OPPENHEIM, J. OPT. SOC. 52, 1078(1962)
REF. 1K-11

Piriou (Ref. 1K-12)


The absorption coefficient of sapphire from 4μ to 11μ was measured at temperatures of 77°K and 293°K. The experimental details were not given. Data were digitized from curves. These data were selected to construct the representative curve of Section I, Figure I - 1.2.


a. T = 77°K


λ	k	λ	k	λ	k
10.705	4.843E-02	10.614	3.933E-02	10.516	3.293E-02
10.434	2.824E-02	10.360	2.540E-02	10.329	2.491E-02
10.318	2.370E-02	10.267	2.354E-02	10.202	2.217E-02
10.132	2.041E-02	10.103	2.111E-02	10.070	2.158E-02
10.010	2.077E-02	9.948	2.020E-02	9.905	1.932E-02
9.855	1.899E-02	9.819	1.876E-02	9.794	1.840E-02
9.754	1.778E-02	9.674	1.753E-02	9.611	1.718E-02
9.538	1.664E-02	9.509	1.650E-02	9.474	1.704E-02
9.445	1.653E-02	9.415	1.705E-02	9.397	1.720E-02
9.361	1.691E-02	9.333	1.652E-02	9.303	1.579E-02
9.280	1.506E-02	9.242	1.473E-02	9.193	1.507E-02
9.144	1.532E-02	9.090	1.581E-02	9.047	1.608E-02
8.984	1.592E-02	8.931	1.513E-02	8.859	1.305E-02
8.781	1.241E-02	8.728	1.138E-02	8.683	1.073E-02
8.657	1.055E-02	8.616	1.073E-02	8.576	1.107E-02
8.551	1.362E-02	8.528	9.875E-03	8.523	9.445E-03
8.508	9.038E-03	8.470	8.792E-03	8.424	8.557E-03
8.393	8.147E-03	8.366	7.796E-03	8.347	7.485E-03
8.328	7.119E-03	8.291	6.915E-03	8.259	6.623E-03
8.234	6.280E-03	8.195	6.160E-03	8.167	6.184E-03
8.140	6.319E-03	8.095	6.772E-03	8.065	7.088E-03
8.027	7.209E-03	8.011	7.222E-03	7.983	7.022E-03
7.954	6.847E-03	7.927	6.683E-03	7.901	6.870E-03
7.874	7.104E-03	7.836	7.286E-03	7.799	7.279E-03
7.768	7.167E-03	7.737	6.764E-03	7.704	6.362E-03
7.691	6.150E-03	7.649	5.977E-03	7.622	6.084E-03
7.600	6.339E-03	7.578	6.630E-03	7.547	6.663E-03
7.517	6.426E-03	7.489	6.160E-03	7.467	5.721E-03
7.447	5.494E-03	7.427	5.393E-03	7.409	4.922E-03
7.364	4.582E-03	7.316	4.286E-03	7.290	4.167E-03
7.262	3.840E-03	7.224	3.589E-03	7.174	3.201E-03
7.133	2.930E-03	7.081	2.644E-03	7.044	2.525E-03
7.033	2.624E-03	7.028	2.796E-03	7.009	2.888E-03
6.981	2.820E-03	6.958	2.613E-03	6.932	2.417E-03
6.913	2.167E-03	6.893	1.965E-03	6.870	1.844E-03
6.836	1.728E-03				

b. $T = 293^{\circ}K$

λ	k	λ	k	λ	k
10.753	6.327E-02	10.603	4.808E-02	10.438	3.747E-02
10.272	3.071E-02	10.140	2.856E-02	10.052	2.827E-02
9.946	2.648E-02	9.681	2.276E-02	9.598	2.189E-02
9.447	2.154E-02	9.399	2.092E-02	9.339	1.967E-02
9.266	1.873E-02	9.212	1.892E-02	9.128	1.930E-02
9.096	1.961E-02	8.988	1.841E-02	8.920	1.721E-02
8.823	1.498E-02	8.743	1.372E-02	8.701	1.304E-02
8.657	1.354E-02	8.592	1.234E-02	8.522	1.152E-02
8.496	1.090E-02	8.452	1.075E-02	8.406	9.801E-03
8.347	9.214E-03	8.274	8.225E-03	8.232	8.003E-03
8.214	7.884E-03	8.125	9.273E-03	8.085	8.816E-03
8.059	9.115E-03	8.009	8.660E-03	7.937	8.523E-03
7.869	8.614E-03	7.834	8.878E-03	7.772	8.336E-03
7.729	7.714E-03	7.685	6.886E-03	7.658	6.979E-03
7.633	7.376E-03	7.595	7.787E-03	7.559	7.607E-03
7.526	7.283E-03	7.438	6.039E-03	7.337	5.119E-03
7.244	4.247E-03	7.127	3.538E-03	7.080	3.332E-03
7.050	3.481E-03	7.024	3.409E-03	6.970	3.068E-03
6.941	2.781E-03	6.885	2.236E-03	6.855	2.028E-03
6.798	1.896E-03	6.728	1.717E-03		
6.596	1.183E-03	6.437	9.153E-04	6.315	7.090E-04
6.220	5.515E-04	6.102	4.362E-04	6.097	3.545E-04
6.025	2.781E-04	5.923	2.169E-04	5.835	1.916E-04
5.671	1.356E-04	5.559	1.276E-04	5.448	9.956E-05
5.[illegible]	8.003E-05	5.263	6.176E-05	5.174	4.972E-05
5.[illegible]	3.989E-05	5.011	3.233E-05	4.924	2.552E-05
4.843	2.057E-05	4.765	1.626E-05		


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-12A
SAPPHIRE
T=77 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1K-12
1E 0
1E-1
1E-2
1E-3
EXTINCTION INDEX, K
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-12B
SAPPHIRE
T=293 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1K-12
EXTINCTION INDEX, K
1E-1
1E-2
1E-3
1E-4
1E-5
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-12B
SAPPHIRE
T=293 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1K-12
EXTINCTION INDEX, K
1E 0
1E-1
1E-2
1E-3
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


Piriou (Ref. 1K-13)


A grating spectrometer with an unspecified bandpass was used to measure the absorption index of sapphire at T = 293 and 1773°K. Temperatures were measured to ± 1 deg. using an optical pyrometer. No error analysis was given. Data were digitized from lines.

These data were selected to construct the representative curve of Section I, Figure I - 1.2.

a. T = 293°K

λ	k	λ	k	λ	k
33.213	1.578E-01	29.726	1.085E-01	28.179	3.287E-03
27.617	2.465E-01	26.716	4.274E-01	26.380	1.423E+00
26.150	2.790E+00	26.011	1.345E+00	25.818	8.514E-01
25.503	5.062E-01	25.185	2.959E-01	24.724	9.862E-02
24.431	1.052E-01	23.979	2.498E-01	23.578	8.443E-01
23.283	1.114E+00	23.143	1.742E+00	23.003	3.083E+00
22.832	1.437E+01	22.651	1.087E+01	22.530	9.603E+00
22.296	7.574E+00	22.060	5.638E+00	21.832	4.372E+00
21.736	3.810E+00	21.527	3.189E+00	21.335	2.400E+00
21.092	1.492E+00	20.866	9.876E-01	20.610	3.517E-01
20.302	1.512E-01	19.902	4.274E-02	19.403	1.052E-01
18.352	3.057E-01	18.474	5.339E-01	18.162	8.610E-01
17.969	1.345E+00	17.806	2.032E+00	17.722	3.439E+00
17.652	5.586E+00	17.549	9.802E+00	17.440	1.251E+01
17.357	1.073E+01	17.274	9.451E+00	17.049	7.306E+00
16.845	5.869E+00	16.730	5.360E+00	16.413	4.408E+00
16.062	3.281E+00	15.988	2.918E+00	15.851	3.208E+00
15.772	4.247E+00	15.712	4.955E+00	15.612	4.408E+00
15.551	4.870E+00	15.451	3.734E+00	15.305	3.402E+00
15.168	3.162E+00	14.961	2.968E+00	14.630	2.712E+00
14.352	2.482E+00	14.088	2.235E+00	13.639	2.015E+00
13.282	1.798E+00	12.874	1.591E+00	12.510	1.407E+00
12.170	1.170E+00	11.809	9.665E-01	11.541	7.265E-01
11.186	4.701E-01	10.922	2.170E-01		



EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-13A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1K-13
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
1E-3
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-13A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1K-13
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
1E-3
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Piriou (Ref. 1K-13)

b. $T = 1773^{\circ}K$

λ	k	λ	k	λ	k
.460	2.621E-07	.621	2.763E-07	.822	2.861E-07
1.042	2.877E-07	1.252	2.862E-07	1.560	2.872E-07
1.775	2.935E-07	2.073	3.118E-07	2.253	3.322E-07
2.348	3.444E-07	2.504	3.762E-07	2.736	4.558E-07
2.936	5.690E-07	3.123	7.488E-07	3.280	1.067E-06
3.435	1.626E-06	3.608	2.609E-06	3.783	4.251E-06
3.959	7.021E-06	4.171	1.212E-05	4.374	1.988E-05
4.594	3.039E-05	4.789	4.419E-05	4.956	6.104E-05
5.113	8.157E-05	9.791	1.320E-01	10.268	1.574E-01
10.804	2.114E-01	11.113	2.750E-01	11.403	4.324E-01
11.862	6.852E-01	12.391	9.650E-01	12.945	1.231E+00
13.540	1.512E+00	14.146	1.755E+00	14.557	1.965E+00
15.000	2.194E+00	15.442	2.456E+00	15.896	2.789E+00
16.231	3.076E+00	16.546	3.292E+00	16.867	3.537E+00
17.253	3.733E+00	17.360	3.848E+00	17.657	4.185E+00
17.916	4.522E+00	18.241	4.925E+00	18.428	5.036E+00
18.609	4.937E+00	18.751	4.610E+00	19.056	3.611E+00
19.393	2.591E+00	19.720	1.701E+00	19.879	1.375E+00
20.078	1.173E+00	20.374	9.793E-01	20.799	8.951E-01
20.977	9.094E-01	21.401	9.984E-01	21.712	1.196E+00
22.013	1.550E+00	22.169	1.811E+00	22.695	2.570E+00
23.145	3.304E+00	23.542	4.000E+00	23.794	4.258E+00
24.004	4.373E+00	24.249	4.227E+00	24.544	3.733E+00
24.958	2.906E+00	25.486	1.859E+00	25.719	1.645E+00
26.010	1.385E+00	26.334	1.250E+00	26.620	1.167E+00
26.850	1.178E+00	27.177	1.297E+00	27.427	1.372E+00
27.682	1.267E+00	28.003	1.025E+00	28.539	7.504E-01
29.446	5.390E-01	30.825	3.911E-01	33.210	2.560E-01


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-13B
SAPPHIRE
T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1K-13
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-1
1E-2
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-13B
SAPPHIRE
T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1K-13
EXTINCTION INDEX, K
WAVELENGTH(MICRONS)
1E 2
1E 1
1E 0
1E-2
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Russell (Ref. 1K-15)

An asymmetric Fourier-transform method was used to measure k_o and k_e for sapphire. T = 300°K (unspecified room temperature). Total estimated probable error was 50 percent for $\alpha < 1$ cm^{-1}, ±20 percent for $\alpha = 1.0$ cm^{-1} to 20.0 cm^{-1}, ±30 percent for $\alpha > 20.0$ cm^{-1}. Data were taken from a table.


These data are in good agreement with the representative curve of Section I - 1.2.


a. k_{ord}

λ	k	λ	k	λ	k
331.126	1.054E-03	220.264	2.980E-03	165.289	4.735E-03
132.275	5.158E-03	110.254	6.317E-03	94.518	7.446E-03
82.713	8.491E-03	73.475	9.180E-03	66.138	1.037E-02
60.132	1.254E-02				

b. k_{ext}

λ	k	λ	k	λ	k
331.126	1.318E-03	220.264	3.856E-03	165.289	5.261E-03
132.275	8.000E-03	110.254	1.114E-02	94.518	1.339E-02
82.713	1.530E-02	73.475	1.731E-02	66.138	1.889E-02


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-15A
SAPPHIRE. ORDINARY RAY
T=300K
RUSSELL. J. OPT. SOC. 57. 543(1967)
REF. 1K-15
1E-1
1E-2
1E-3
1E-4
EXTINCTION INDEX. K
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)


EXTINCTION INDEX OF ALUMINUM OXIDE
FIGURE 1K-15B
SAPPHIRE. EXTRAORDINARY RAY
T=300 K
RUSSELL. J. OPT. SOC. 57. 543 (1967)
REF. 1K-15
1E-1
1E-2
1E-3
EXTINCTION INDEX. K
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
WAVELENGTH(MICRONS)

Streed (Ref. 1K-16)

The extinction index of alumina particles 1 μ in diameter and 99.5 percent pure and of 99.95 percent pure sapphire was measured using transmittance and reflectance measurements for the sapphire, and emittance measurements for the powders. A KBr prism spectrometer with a bandwidth of 0.016 μ to 0.15 μ used. No error analysis was given. The data were taken from tables. These data do not agree with the representative curve of Section I - 1.2.

a. Al_2O_3 Extinction Index

Sapphire, T = 300°K

λ(μ)	k
2.0	2.6×10^{-6}
2.5	4.5×10^{-6}
3.0	5.6×10^{-6}
3.5	1.23×10^{-5}
4.0	1.37×10^{-4}
5.0	0.0043
6.0	0.011
7.0	0.021
8.0	0.031
9.0	0.038
10.0	0.049
17.0	0.058
18.0	0.061
19.0	0.075
20.0	0.064
21.0	0.0618
22.0	0.06162

Streed (Ref. 16-K)

b. Al_2O_3 Extinction Index

Powder, T = 300°K

λ(μ)	k
2.0	1.11×10^{-7}
2.5	5.0×10^{-7}
3.0	1.04×10^{-4}
3.5	6.1×10^{-5}
4.0	1.65×10^{-5}
5.0	3.26×10^{-5}
6.0	2.46×10^{-5}
7.0	0.015
8.0	0.391
9.0	4.055
10.0	5.87
10.5	2.034
11.0	0.792
12.0	0.179
13.0	0.172
14.0	0.199
15.0	0.157
16.0	0.168
17.0	0.067
18.0	0.098
19.0	0.199
20.0	0.612
21.0	0.356
22.0	0.103

Streed (Ref. 1K-16)

c. Flame Sprayed Powder, T = 300°K

λ (μ)	k
1.0	7.64×10^{-7}
1.5	1.60×10^{-6}
2.0	3.04×10^{-6}
2.5	6.27×10^{-4}
3.0	2.40×10^{-5}
3.5	5.10×10^{-5}
4.0	4.14×10^{-5}
4.5	6.22×10^{-5}
5.0	0.00012
5.5	0.00122
6.0	0.020
6.5	0.166
7.0	0.548
7.5	1.642
8.0	4.28
8.5	12.11
9.0	23.57
9.5	11.88
10.0	3.83
10.5	0.017
11.0	0.106
11.5	0.215
12.0	0.0196
13.0	0.0461
14.0	0.04
15.0	0.059
16.0	0.0471
17.0	0.0426
18.0	0.0398
19.0	0.0461
20.0	0.0662
21.0	0.0886
22.0	0.113

d. Flame Sprayed Powder, T = 1000°K

λ (μ)	k	λ (μ)	k
1.0	2.14×10^{-6}	17.5	0.02400
1.5	1.89×10^{-6}	18.0	0.02053
2.0	2.66×10^{-6}	18.5	0.02264
2.5	3.66×10^{-6}	19.0	0.02261
3.0	2.17×10^{-5}	19.5	0.03586
3.5	1.28×10^{-5}	20.0	0.01519
4.0	2.24×10^{-5}	20.5	0.04257
4.5	0.00012	21.0	0.04786
5.0	0.00056	21.5	0.03262
5.5	0.0034	22.0	0.03868
6.0	0.04127		
6.5	0.28554		
7.0	0.41254		
7.5	0.84663		
8.0	0.90307		
8.5	0.95951		
9.0	1.74334		
9.5	0.68399		
10.0	2.66349		
10.5	0.05261		
11.0	0.01221		
11.5	0.01053		
12.0	0.00865		
12.5	0.01177		
13.0	0.01660		
13.5	0.01990		
14.0	0.01788		
14.5	0.02666		
15.0	0.02413		
15.5	0.02187		
16.0	0.02043		
16.5	0.02503		
17.0	0.02023		

Streed (Ref. 1K-16)

e. Flame Sprayed, Powder, T = 1500°K

λ (μ)	k	λ (μ)	k
1.0	2.23×10^{-7}	16.5	0.00562
1.5	6.92×10^{-7}	17.0	0.00443
2.0	1.31×10^{-6}	17.5	0.00634
2.5	1.43×10^{-6}	18.0	0.00827
3.0	3.14×10^{-6}	18.5	0.02687
3.5	5.01×10^{-6}	19.0	0.04330
4.0	1.42×10^{-5}	19.5	0.11035
4.5	6.96×10^{-5}	20.0	0.14613
5.0	0.00053	20.5	0.11382
5.5	0.00302	21.0	0.12347
6.0	0.02125	21.5	0.08019
6.5	0.18710	22.0	0.02279
7.0	0.59809		
7.5	1.36920		
8.0	3.60427		
8.5	4.55257		
9.0	0.92292		
9.5	1.07239		
10.0	1.24704		
11.0	0.13552		
11.5	0.01877		
12.0	0.00544		
12.5	0.00459		
13.0	0.00279		
13.5	0.00620		
14.0	0.00533		
14.5	0.00588		
15.0	0.00436		
15.5	0.00450		
16.0	0.00343		

f. Flame Sprayed Powder, T = 2000°K

λ (μ)	k	λ (μ)	k
1.0	3.03×10^{-7}	16.5	0.00576
1.5	8.49×10^{-6}	17.0	0.00558
2.0	1.05×10^{-6}	17.5	0.00627
2.5	1.82×10^{-6}	18.0	0.00712
3.0	1.44×10^{-6}	18.5	0.01111
3.5	4.32×10^{-6}	19.0	0.02261
4.0	1.27×10^{-5}	19.5	0.02752
4.5	1.03×10^{-4}	20.0	0.06619
5.0	0.02435	20.5	0.05749
5.5	0.01042	21.0	0.05262
6.0	0.10709	21.5	0.05056
6.5	1.18664	22.0	0.02932
7.0	1.74375		
7.5	3.11248		
8.0	4.69408		
8.5	7.46471		
9.0	0.88074		
9.5	0.77691		
10.0	1.31256		
11.0	0.23054		
11.5	0.03387		
12.0	0.01243		
12.5	0.00686		
13.0	0.00678		
13.5	0.00760		
14.0	0.00739		
14.5	0.00710		
15.0	0.00681		
15.5	0.0003		
16.0	0.00437		

III-1.3 Tabulated Spectral Emissivity Data — Aluminum Oxide

Contents

1SE-2: Aronson; Alumina powder, 5-30 μ diameter, T = 298°K.

1SE-3: Bergquam; 0.3 μ diameter alumina powder, T = 1000°K.

1SE-4: Blau; bulk alumina at T = 873°K and 1303°K. Materials are Coors AD-85, Coors AD-99, and Norton TWA-2.

1SE-6: Carlson; liquid Al_2O_3 droplets T-2350°K to 2880°K.

1SE-8: Clark; 99.2 percent pure bulk alumina, T = 1200°K, 1400°K, 1600°K.

1SE-11: Mergerian; sapphire, T = 373°K, 648°K, 1013°K, 1213°K.

1SE-12: Richmond; alumina grit blasting effects.

1SE-14: Schatz; sintered alumina, T = 373°K, 885°K, 1003°K, 1148°K, 1273°K.

1SE-16: Stierwalt; sapphire, T = 4.2°K, 77°K, 200°K.

1SE-17: Streed; flame sprayed alumina particles of 0.06 μ, 1.0 μ, and 8.0 μ diameter, T = 300°K to 2000°K.

1SE-18: Touloukian; alumina: G.E. Lucalox, T = 813°K; Norton TWA-2, T = 873°K, 1323°K; Coors AD-99, T=873°K; Coos AD-995, T=814°K; and miscellaneous Coors and McDanel materials from 800°K - 1600°K plotted together.

Preceding page blank

Aronson (Ref. 1SE-2)

Microgrit "WCA" alumina precision lapping powders, 99 percent pure α-Al_2O_3, were studied. Particles have a platelet configuration with a diameter 5x the thickness. Particle size distributions are shown in Figure III-1.3.1, the average diameter in microns being approximately the WCA number. The sample temperature was determined by taking $\epsilon(\lambda) = 1$ at 1035 cm^{-1}, a Christiansen frequency. An interferometer with 15 cm^{-1} resolution was used with a standard blackbody and dry-ice cooled chamber. Sample surface temperatures were calculated to be 298°K, with the sample heating done by conduction from a tray held at 340.4 ±0.6°K. These data are not corrected for atmospheric absorption effects, and there is an apparent emittance peak at 660 cm^{-1} (15.2μ) due to CO_2, and peaks at the high frequency end and 575 cm^{-1} (17.4 μ) due to H_2O. No error analysis was given. Data are digitized from lines.

The 10 WCA, 300°K curve was taken to be representative (Figure I-1.3.2).

a. WCA = 5

λ	ε	λ	ε	λ	ε
22.236	8.646E-01	21.867	8.559E-01	21.508	8.727E-01
21.207	8.974E-01	21.091	9.087E-01	20.928	9.103E-01
20.668	8.990E-01	20.530	8.963E-01	20.292	8.967E-01
20.170	8.876E-01	19.937	8.809E-01	19.776	8.701E-01
19.627	8.522E-01	19.383	8.376E-01	19.151	8.392E-01
18.878	8.515E-01	18.702	8.623E-01	18.556	8.610E-01
18.394	8.795E-01	18.275	8.913E-01	18.135	8.939E-01
17.980	8.889E-01	17.827	8.664E-01	17.711	8.531E-01
17.631	8.500E-01	17.503	8.557E-01	17.372	8.582E-01
17.241	8.515E-01	17.096	8.339E-01	16.998	8.112E-01
16.896	8.036E-01	16.[illegible]	8.099E-01	16.648	8.443E-01
16.[illegible]	8.587E-01	16.2[illegible]	8.834E-01	16.165	8.976E-01
16.002	9.093E-01	15.	9.143E-01	15.846	9.064E-01
15.749	8.917E-01	15.[illegible]	8.819E-01	15.613	8.772E-01
15.512	8.858E-01	15.4[illegible]	9.072E-01	15.322	9.413E-01
15.270	9.542E-01	15.189	9.483E-01	15.076	9.270E-01
14.972	9.031E-01	14.[illegible]99	8.986E-01	14.765	9.066E-01
14.612	9.025E-01	14.561	8.894E-01	14.455	8.844E-01
14.372	8.822E-01	14.311	8.913E-01	14.211	9.014E-01
14.117	9.011E-01	14.020	8.964E-01	13.934	8.837E-01

Aronson (Ref. 1SE-2)

a. WCA = 5 (continued)

λ	ε	λ	ε	λ	ε
13.967	8.819E-01	13.795	8.919E-01	13.751	8.949E-01
13.708	9.018E-01	13.639	9.001E-01	13.560	8.960E-01
13.437	8.957E-01	13.349	8.970E-01	13.249	8.986E-01
13.130	8.977E-01	13.047	8.927E-01	12.964	9.012E-01
12.865	9.053E-01	12.775	9.132E-01	12.711	9.042E-01
12.617	8.995E-01	12.521	8.948E-01	12.452	9.030E-01
12.371	9.049E-01	12.307	8.973E-01	12.224	8.944E-01
12.194	8.958E-01	12.144	8.907E-01	12.084	8.984E-01
11.959	8.908E-01	11.889	8.793E-01	11.823	8.742E-01
11.765	8.705E-01	11.699	8.733E-01	11.621	8.654E-01
11.594	8.562E-01	11.524	8.600E-01	11.477	8.535E-01
11.425	8.551E-01	11.355	8.630E-01	11.254	8.655E-01
11.228	8.717E-01	11.151	8.686E-01	11.113	8.768E-01
11.056	8.825E-01	11.020	8.785E-01	10.952	8.926E-01
10.914	8.967E-01	10.899	9.041E-01	10.841	9.077E-01
10.801	9.115E-01	10.728	9.132E-01	10.689	9.211E-01
10.660	9.321E-01	10.613	9.399E-01	10.526	9.428E-01
10.441	9.429E-01	10.455	9.486E-01	10.399	9.519E-01
10.343	9.545E-01	10.313	9.639E-01	10.246	9.665E-01
10.199	9.647E-01	10.131	9.709E-01	10.089	9.792E-01
10.029	9.792E-01	9.982	9.839E-01	9.950	9.759E-01
9.876	9.750E-01	9.917	9.741E-01	9.750	9.725E-01
9.711	9.763E-01	9.644	9.738E-01	9.568	9.732E-01
9.479	9.735E-01	9.443	9.763E-01	9.403	9.721E-01
9.341	9.745E-01	9.274	9.773E-01	9.189	9.740E-01
9.116	9.582E-01	9.045	9.709E-01	8.970	9.693E-01
8.924	9.659E-01	8.887	9.606E-01	8.840	9.593E-01
8.823	9.551E-01	8.736	9.533E-01	8.662	9.464E-01
8.625	9.342E-01	8.611	9.241E-01	8.583	9.205E-01
8.564	9.251E-01	8.540	9.277E-01	8.512	9.349E-01
8.471	9.366E-01	8.449	9.369E-01	8.420	9.263E-01
8.404	9.205E-01	8.333	9.191E-01	8.313	9.121E-01
8.294	9.045E-01	8.252	8.986E-01	8.213	8.984E-01
8.197	8.948E-01	8.184	8.998E-01	8.156	8.960E-01
8.136	8.855E-01	8.118	8.686E-01	8.079	8.671E-01
8.062	8.755E-01	8.000	8.793E-01	7.983	8.739E-01
7.959	8.708E-01	7.969	8.601E-01	7.944	8.597E-01
7.929	8.620E-01				

Aronson (Ref. 1SE-2)

b. WCA = 9

λ	ε	λ	ε	λ	ε
7.338	7.441E-01	7.371	7.676E-01	7.398	7.451E-01
7.438	7.304E-01	7.482	7.587E-01	7.549	7.856E-01
7.643	7.817E-01	7.672	7.841E-01	7.709	7.913E-01
7.727	7.661E-01	7.756	7.876E-01	7.778	7.911E-01
7.825	7.859E-01	7.831	7.896E-01	7.856	7.985E-01
7.881	8.106E-01	7.914	8.081E-01	7.981	8.042E-01
8.014	8.153E-01	8.042	8.239E-01	8.068	8.326E-01
8.097	8.329E-01	8.116	8.291E-01	8.172	8.291E-01
8.201	8.395E-01	8.233	8.425E-01	8.261	8.387E-01
8.239	8.437E-01	8.315	8.540E-01	8.341	8.793E-01
8.369	8.839E-01	8.394	8.887E-01	8.437	8.869E-01
8.468	8.855E-01	8.516	8.941E-01	8.577	8.956E-01
8.604	8.966E-01	8.654	9.081E-01	8.672	9.182E-01
8.706	9.348E-01	8.775	9.357E-01	8.834	9.503E-01
8.908	9.041E-01	8.974	9.620E-01	9.043	9.715E-01
9.117	9.347E-01	9.201	9.796E-01	9.265	9.912E-01
9.[illegible]	9.364E-01	9.636	9.960E-01	9.919	9.959E-01
10.[illegible]	9.921E-01	10.203	9.867E-01	10.354	9.604E-01
10.454	9.492E-01	10.502	9.368E-01	10.590	9.321E-01
10.665	9.123E-01	10.709	9.115E-01	10.728	9.007E-01
10.787	8.975E-01	10.819	8.831E-01	10.877	8.891E-01
10.920	8.745E-01	10.965	8.696E-01	11.039	8.610E-01
11.114	8.541E-01	11.179	8.550E-01	11.226	8.570E-01
11.270	8.501E-01	11.359	8.487E-01	11.456	8.418E-01
11.479	8.339E-01	11.546	8.353E-01	11.625	8.353E-01
11.689	8.402E-01	11.737	8.408E-01	11.777	8.503E-01
11.882	8.573E-01	11.950	8.625E-01	12.012	8.739E-01
12.123	8.745E-01	12.169	8.822E-01	12.235	8.855E-01
12.[illegible]	8.904E-01	12.433	8.903E-01	12.497	8.847E-01
12.[illegible]	8.892E-01	12.664	8.879E-01	12.718	8.852E-01
12.785	8.896E-01	12.874	8.820E-01	12.979	8.817E-01
13.091	8.515E-01	13.164	8.849E-01	13.302	8.839E-01
13.528	8.729E-01	13.657	8.768E-01	13.725	8.771E-01
13.780	8.724E-01	13.904	8.647E-01	14.064	8.652E-01
14.[illegible]	8.[illegible]74E-01	14.374	8.531E-01	14.501	8.575E-01
14.[illegible]	8.[illegible]59E-01	14.683	8.534E-01	14.842	8.615E-01
14.994	8.624E-01	15.122	8.884E-01	15.235	8.971E-01
15.373	8.755E-01	15.452	8.531E-01	15.558	8.336E-01
15.653	8.304E-01	15.737	8.415E-01	15.774	8.580E-01
15.892	8.719E-01	15.964	8.322E-01	16.070	8.783E-01
16.135	8.684E-01	16.394	8.497E-01	16.584	8.059E-01
16.369	7.681E-01	16.801	7.374E-01	16.950	7.336E-01

b. WCA = 9 (continued)

λ	ε	λ	ε	λ	ε
17.018	7.512E-01	17.018	7.597E-01	17.220	8.059E-01
17.269	8.198E-01	17.452	8.218E-01	17.584	8.202E-01
17.705	8.326E-01	17.733	8.425E-01	17.852	8.524E-01
17.989	8.713E-01	18.026	8.783E-01	18.123	8.899E-01
18.282	8.960E-01	18.426	8.930E-01	18.599	8.886E-01
18.496	8.711E-01	18.996	8.684E-01	19.108	8.630E-01
19.355	8.934E-01	19.624	8.713E-01	19.896	8.681E-01
20.118	8.560E-01	20.326	8.382E-01	20.474	8.365E-01
20.241	8.681E-01	20.492	8.751E-01	20.709	8.896E-01
21.016	8.881E-01	21.255	8.955E-01	21.443	8.758E-01
21.894	8.521E-01	22.209	8.247E-01	22.525	8.076E-01
22.840	7.955E-01	23.056	8.003E-01	23.272	8.163E-01
23.446	8.444E-01	23.759	8.556E-01	24.018	8.756E-01
24.336	8.737E-01	24.756	8.681E-01	24.963	8.469E-01
25.270	8.281E-01	25.051	8.422E-01		





Figure III-1.3.1: Particle Size Distribution for WC Alumina Lapping Powders


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
.6
.5
.4
.3
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1SE-2A
ALUMINA POWDER. 5 WCA
T=298 K
ARONSON. AFCRL-70-0083
REF. 1SE-2




FIGURE 1SE-28
ALUMINA POWDER. 9 WCA
T=298 K
ARONSON. AFCRL-70-0083
REF. 1SE-2




FIGURE 1SE-28
ALUMINA POWDER. 9 WCA
T=298 K
ARONSON. AFCRL-70-0083
REF. 1SE-2

Aronson (Ref. 1SE-2)

c. WCA = 15

λ	ε	λ	ε	λ	ε
24.953	8.742E-01	24.508	8.724E-01	23.379	8.668E-01
23.717	8.638E-01	23.334	8.174E-01	23.334	8.082E-01
23.122	7.877E-01	22.855	7.511E-01	22.662	7.523E-01
22.417	7.875E-01	22.276	7.715E-01	21.913	7.787E-01
21.839	8.671E-01	21.431	8.566E-01	21.400	8.752E-01
21.106	8.677E-01	20.948	8.178E-01	20.589	8.653E-01
20.349	8.645E-01	20.042	8.407E-01	19.827	8.814E-01
19.606	8.746E-01	19.363	8.781E-01	19.086	8.998E-01
18.835	8.981E-01	18.333	8.817E-01	18.144	8.789E-01
17.988	8.556E-01	17.940	8.437E-01	17.723	8.068E-01
17.529	7.910E-01	17.493	7.742E-01	17.154	7.213E-01
17.127	7.151E-01	16.859	6.882E-01	16.888	6.848E-01
16.730	6.921E-01	16.667	7.181E-01	16.381	7.998E-01
16.565	8.149E-01	16.180	8.502E-01	16.111	8.535E-01
15.997	8.401E-01	15.883	8.222E-01	15.818	8.113E-01
15.737	8.080E-01	15.697	7.841E-01	15.653	7.794E-01
15.417	8.113E-01	15.286	8.457E-01	15.213	8.512E-01
15.137	8.405E-01	14.953	8.133E-01	14.772	8.133E-01
14.626	8.201E-01	14.582	8.116E-01	14.404	8.039E-01
14.347	8.020E-01	14.243	8.152E-01	14.146	8.237E-01
14.038	8.224E-01	13.950	8.230E-01	13.890	8.204E-01
13.823	8.257E-01	13.716	8.233E-01	13.595	8.266E-01
13.516	8.240E-01	13.440	8.296E-01	13.413	8.352E-01
13.288	8.464E-01	13.214	8.415E-01	13.177	8.435E-01
13.133	8.373E-01	13.050	8.375E-01	12.962	8.427E-01
12.899	8.453E-01	12.790	8.506E-01	12.690	8.530E-01
12.623	8.556E-01	12.512	8.526E-01	12.408	8.521E-01
12.432	8.548E-01	12.309	8.514E-01	12.290	8.550E-01
12.214	8.515E-01	11.975	8.218E-01	11.910	8.082E-01
11.816	8.614E-01	11.709	7.884E-01	11.623	7.814E-01
11.585	7.767E-01	11.481	7.951E-01	11.394	8.092E-01
11.312	8.144E-01	11.252	8.154E-01	11.220	8.204E-01
11.122	8.137E-01	11.070	8.279E-01	10.962	8.420E-01
10.922	8.489E-01	10.814	8.641E-01	10.776	8.727E-01
10.703	8.776E-01	10.578	8.894E-01	10.629	8.962E-01
10.572	9.128E-01	10.502	9.241E-01	10.353	9.537E-01
10.307	9.603E-01	10.262	9.746E-01	10.182	9.868E-01
10.145	9.892E-01	9.909	1.008E+00	9.770	1.010E 00

c. WCA = 15 (continued)

λ	ε	λ	ε	λ	ε
9.524	1.010E+00	9.531	1.009E+00	9.448	1.003E+00
9.346	9.991E-01	9.243	9.905E-01	9.210	9.832E-01
9.148	9.748E-01	9.100	9.735E-01	9.060	9.760E-01
9.019	9.696E-01	9.004	9.600E-01	8.977	9.583E-01
8.934	9.523E-01	8.918	9.545E-01	8.870	9.460E-01
8.823	9.422E-01	8.764	9.329E-01	8.704	9.276E-01
8.647	9.150E-01	8.594	8.953E-01	8.538	8.906E-01
8.495	8.911E-01	8.483	8.844E-01	8.363	8.718E-01
8.345	8.588E-01	8.302	8.412E-01	8.270	8.347E-01
8.239	8.282E-01	8.210	8.213E-01	8.156	8.215E-01
8.105	8.156E-01	8.064	8.156E-01	8.036	8.118E-01
8.009	8.083E-01				

Aronson (Ref. 1SE-2)

d. WCA = 20

λ	ε	λ	ε	λ	ε
7.332	7.366E-01	7.370	7.574E-01	7.426	7.529E-01
7.454	7.431E-01	7.490	7.621E-01	7.526	7.768E-01
7.576	7.614E-01	7.670	7.836E-01	7.701	7.867E-01
7.731	7.819E-01	7.810	7.985E-01	7.834	8.096E-01
7.930	8.008E-01	7.980	8.072E-01	8.024	8.187E-01
8.085	8.229E-01	8.139	8.297E-01	8.189	8.282E-01
8.212	8.430E-01	8.262	8.412E-01	8.313	8.612E-01
8.372	8.728E-01	8.426	8.810E-01	8.480	8.896E-01
8.531	8.948E-01	8.592	8.950E-01	8.626	9.103E-01
8.707	9.177E-01	8.778	9.236E-01	8.833	9.355E-01
8.936	9.411E-01	8.935	9.528E-01	9.020	9.643E-01
9.121	9.793E-01	9.220	9.780E-01	9.298	9.926E-01
9.531	9.924E-01	9.802	9.980E-01	10.068	9.903E-01
10.299	9.595E-01	10.390	9.337E-01	10.423	9.231E-01
10.505	9.070E-01	10.615	8.864E-01	10.694	8.659E-01
10.780	8.462E-01	10.883	8.334E-01	10.980	8.104E-01
11.028	8.008E-01	11.104	7.948E-01	11.153	7.864E-01
11.239	7.780E-01	11.366	7.790E-01	11.448	7.661E-01
11.492	7.496E-01	11.559	7.421E-01	11.604	7.309E-01
11.734	7.379E-01	11.870	7.555E-01	11.976	7.732E-01
12.049	7.795E-01	12.115	7.919E-01	12.173	7.933E-01

Aronson (Ref. 1SE-2)

d. WCA = 20 (continued)

λ	ε	λ	ε	λ	ε
12.237	8.069E-01	12.344	8.173E-01	12.462	8.109E-01
12.581	8.133E-01	12.706	8.111E-01	12.785	8.121E-01
12.892	8.037E-01	13.041	8.024E-01	13.065	7.950E-01
13.161	8.005E-01	13.311	8.035E-01	13.430	7.931E-01
13.593	7.829E-01	13.803	7.819E-01	13.857	7.723E-01
14.010	7.690E-01	14.103	7.705E-01	14.175	7.718E-01
14.354	7.483E-01	14.496	7.456E-01	14.594	7.512E-01
14.728	7.547E-01	14.831	7.441E-01	14.994	7.430E-01
15.082	7.516E-01	15.202	7.703E-01	15.299	7.730E-01
15.389	7.523E-01	15.533	7.086E-01	15.636	7.022E-01
15.694	7.146E-01	15.784	7.413E-01	15.882	7.735E-01
15.952	7.318E-01	16.096	8.097E-01	16.255	7.872E-01
16.397	7.423E-01	16.477	7.859E-01	16.573	6.837E-01
16.648	6.573E-01	16.828	6.392E-01	17.015	6.512E-01
17.171	6.819E-01	17.285	7.087E-01	17.437	7.344E-01
17.611	7.809E-01	17.731	7.748E-01	17.883	8.000E-01
18.023	8.331E-01	18.264	8.696E-01	18.575	8.788E-01
18.987	8.778E-01	19.297	8.645E-01	19.725	8.634E-01
19.917	8.711E-01	20.126	8.729E-01	20.334	8.575E-01
20.612	8.511E-01	20.739	8.696E-01	21.033	8.810E-01
21.259	8.657E-01	21.351	8.407E-01	21.431	8.118E-01
21.513	7.970E-01	21.616	7.819E-01	21.696	7.369E-01
21.824	7.171E-01	22.021	7.089E-01	22.419	7.034E-01
22.537	6.929E-01	22.683	6.935E-01	22.901	7.081E-01
23.038	7.369E-01	23.191	7.587E-01	23.304	7.908E-01
23.529	8.183E-01	23.907	8.323E-01	24.557	8.418E-01
24.942	8.413E-01	25.042	8.336E-01	25.362	8.316E-01
25.518	8.424E-01				

Aronson (Ref. 1SE-2)


e. WCA = 30


λ	ε	λ	ε	λ	ε
22.234	6.290E-01	22.143	6.407E-01	21.762	6.523E-01
21.487	7.115E-01	21.340	7.805E-01	21.156	8.254E-01
21.159	8.357E-01	20.956	8.749E-01	20.727	8.682E-01
20.607	8.460E-01	20.357	8.385E-01	20.202	8.392E-01
19.956	8.656E-01	19.790	8.805E-01	19.660	8.840E-01
19.476	8.798E-01	19.247	8.786E-01	18.985	8.817E-01

Aronson (Ref. 1SE-2)

e. WCA = 30 (continued)

λ	ε	λ	ε	λ	ε
18.689	8.783E-01	18.523	8.672E-01	18.347	8.525E-01
18.223	8.536E-01	18.111	8.380E-01	18.099	8.225E-01
17.896	7.941E-01	17.806	7.707E-01	17.725	7.402E-01
17.571	7.[illegible]	17.377	6.781E-01	16.948	5.734E-01
16.339	5.570E-01	16.743	5.746E-01	16.641	5.954E-01
16.612	6.130E-01	16.481	6.377E-01	16.320	7.031E-01
16.285	7.[illegible]	16.156	7.717E-01	16.069	7.785E-01
16.006	7.716E-01	15.837	7.007E-01	15.769	6.794E-01
15.752	6.643E-01	15.643	6.417E-01	15.593	6.395E-01
15.534	6.470E-01	15.411	6.787E-01	15.284	7.102E-01
15.271	7.157E-01	15.135	7.116E-01	14.993	7.010E-01
14.861	6.943E-01	14.659	6.973E-01	14.527	6.937E-01
14.446	6.970E-01	14.351	6.945E-01	14.238	7.058E-01
14.188	7.198E-01	14.086	7.242E-01	13.988	7.239E-01
13.883	7.231E-01	13.736	7.287E-01	13.637	7.393E-01
13.572	7.419E-01	13.471	7.405E-01	13.380	7.443E-01
13.323	7.342E-01	13.201	7.555E-01	13.117	7.533E-01
13.036	7.477E-01	12.897	7.517E-01	12.799	7.558E-01
12.739	7.540E-01	12.643	7.617E-01	12.567	7.591E-01
12.462	7.614E-01	12.388	7.659E-01	12.292	7.627E-01
12.265	7.556E-01	12.198	7.497E-01	12.126	7.334E-01
12.063	7.301E-01	11.994	7.228E-01	11.939	7.163E-01
11.870	7.069E-01	11.790	6.905E-01	11.701	6.837E-01
11.624	6.878E-01	11.562	6.884E-01	11.506	7.067E-01
11.437	7.220E-01	11.374	7.400E-01	11.262	7.487E-01
11.128	7.546E-01	11.068	7.626E-01	10.860	8.116E-01
10.686	8.479E-01	10.537	8.958E-01	10.466	9.069E-01
10.336	9.403E-01	10.157	9.688E-01	9.992	9.829E-01
9.885	9.898E-01	9.902	9.889E-01	9.724	9.844E-01
9.544	9.878E-01	9.403	9.854E-01	9.237	9.767E-01
9.133	9.558E-01	9.035	9.611E-01	8.95[illegible]	9.559E-01
8.945	9.546E-01	8.902	9.466E-01	8.845	9.430E-01
8.821	9.349E-01	8.714	9.318E-01	8.639	9.189E-01
8.593	9.029E-01	8.538	8.987E-01	8.452	9.007E-01
8.392	8.880E-01	8.356	8.836E-01	8.309	8.678E-01
8.248	8.548E-01	8.214	8.525E-01	8.194	8.443E-01
8.151	8.439E-01	8.109	8.402E-01	8.053	8.414E-01
8.017	8.386E-01	7.994	8.311E-01		


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-2C
ALUMINA POWDER. 15 WCA
T=298 K
ARONSON. AFCRL 70-0083
REF. 1SE-2
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
1.
.9
.8
.7
.6
.5
.4
.3
.2
.1
0.
FIGURE 1SE-2D
ALUMINA POWDER. 20 WCA
T=298 K
ARONSON. AFCRL-70-0083
REF. 1SE-2
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)




FIGURE 1SE-2D
ALUMINA POWDER. 20 WCA
T=298 K
ARONSON. AFCRL-70-0083
REF. 1SE-2




FIGURE 1SE-2E
ALUMINA POWDER, 30 WCA
T=298 K
ARONSON. AFCRL-70 0083
REF. 1SE-2

Bergquam (Ref. ISE-3)

Layers of 0.3μ diameter Linde Type A alumina powder with a thickness of 0.2, 0.100, and 0.125 inches on a platinum substrate were studied with no particle compaction (7 percent solid), light compaction (14 percent solid) and heavy compaction (24.5 percent solid) using a conventional monochromator and detector system. Samples were heated to approximately 1000°K, and measured with a thermocouple near the surface. No error analysis was given. Digitized from discrete points.


These data show values of $\epsilon(\lambda)$ very much lower than the representative curves of Section I-1.3.


a. Thickness = 0.025 in., no compaction

λ	ε	λ	ε	λ	ε	λ	ε
1.011	.101	2.011	.121	3.008	.146	4.012	.144
5.354	.154	6.323	.320	7.022	.527	8.033	.627
9.064	.566	9.809	.664				

b. Thickness = 0.125 in., no compaction

λ	ε	λ	ε	λ	ε	λ	ε
1.015	.048	2.016	.041	3.026	.053	4.055	.067
5.083	.119	6.346	.234	7.128	.340	8.043	.395
9.074	.409	9.943	.425				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-3A
ALUMINA POWDER. T=.025 IN.
T=1000 K
BERGQUAM. J. HEAT TRANS. 94. 36(1972)
REF. 1SE-3
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-3B
ALUMINA POWDER. T=.125 IN.
T=1000 K
BERGQUAM. J. HEAT TRANS. 94. 36(1972)
REF. 1SE-3
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Bergquam (Ref. 1SE-3)

c. Thickness = 0.125 in., light compaction


λ	ε	λ	ε	λ	ε	λ	ε
1.008	.045	1.994	.023	3.029	.045	4.045	.061
5.044	.113	6.153	.239	7.120	.352	8.007	.413
9.128	.433	9.875	.444				

d. Thickness = 0.10[illegible] in., heavy compaction

λ	ε	λ	ε	λ	ε	λ	ε
1.015	.282	1.987	.030	3.031	.108	4.063	.150
5.096	.296	6.031	.468	7.158	.483	7.978	.502
9.118	.527	9.902	.538				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE

FIGURE 1SE-3C
ALUMINA POWDER. T=.125 IN.
T=1000 K
BERGQUAM. J. HEAT TRANS. 94. 36(1972)
REF. 1SE-3



SPECTRAL EMISSIVITY OF ALUMINUM OXIDE

FIGURE 1SE-3D
ALUMINA POWDER. T=.100 IN.
T=1000 K
BERGQUAM. J. HEAT TRANS. 94. 36(1972)
REF. 1SE-3



Blau (Ref. 1SE-4)

Samples of varying degrees of purity were held in a silicon carbide heating element at 873°K and 1303°K. Temperatures were measured by thermocouple and optical pyrometer, with an absolute precision estimated to be ±1 percent. Emittances were measured using a prism spectrometer within specified resolutions and standard blackbody. Emittance errors are estimated to be ±4 percent absolute, ±2 percent relative. Essential features of $\epsilon(\lambda)$ for alumina from 85 to 99 percent pure are the same, and these data are representative of alumina. The data were digitized from discrete points.

a. Coors AD-85 Alumina (85 percent pure), T = 873°K

λ	ε	λ	ε	λ	ε	λ	ε
1.967	[illegible]	2.955	5.277E-01	3.988	5.497E-01	4.963	8.283E-01
5.[illegible]	[illegible]	[illegible]	[illegible]	7.939	9.808E-01	8.962	9.792E-01
9.931	[illegible]	10.[illegible]	[illegible]	11.992	8.216E-01	12.995	7.660E-01
[illegible]	[illegible]						


b. Coors AD-85 Alumina (85 percent pure), T = 1303°K.

λ	ε	λ	ε	λ	ε	λ	ε
.950	.428	1.955	.496	2.955	.555	3.984	.606
4.933	.367	5.943	.943	6.947	.962	7.924	.971
8.943	.982	9.973	.974	10.955	.949	11.965	.850
12.956	.804	13.973	.759				

c. Coors AD-99 Alumina (99 percent pure), T = 873°K.

λ	ε	λ	ε	λ	ε	λ	ε
1.971	.395	2.958	.447	3.969	.485	4.934	.737
5.938	.871	6.935	.935	7.931	.960	8.947	.973
9.961	.967	10.931	.874	11.961	.640	12.986	.633
13.969	.583						

Reproduced from best available copy.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-4A
AD-85 ALUMINA
T=873 K
BLAU, AFCRL-TR-60-416
REF. 1SE-4




FIGURE 1SE-4B
AD-85 ALUMINA
T=1303 K
BLAU. AFCRL-TR-60-416
REF. 1SE-4




FIGURE 1SE-4C
AD-99 ALUMINA
T=873 K
BLAU. AFCRL-TR-60-416
REF. 1SE-4

Blau (Ref. 1SE-4)

d. Coors AD-99 Alumina (99 percent pure), T = 1303°K.


λ	ε	λ	ε	λ	ε	λ	ε
1.974	.422	2.967	.453	3.967	.520	4.970	.795
5.376	.923	6.957	.972	7.975	.964	8.942	.983
9.961	.934	10.971	.924	11.964	.717	12.935	.673
14.011	.633						


e. Norton TWA-2, A402 Alumina (93.56 percent pure), T = 873°K.


λ	ε	λ	ε	λ	ε	λ	ε
1.953	.363	2.937	.446	3.926	.482	4.941	.726
5.942	.845	6.932	.906	7.939	.925	8.931	.937
9.946	.944	10.935	.842	11.972	.650	12.974	.630
14.954	.651						

f. Norton TWA-2, A402 Alumina (98.56 percent pure), T = 1303°K.

λ	ε	λ	ε	λ	ε	λ	ε
1.994	.431	2.937	.499	3.964	.576	4.997	.814
5.948	.941	6.982	.951	7.984	.966	8.995	.983
10.005	.983	11.005	.935	12.026	.734	12.999	.705
14.000	.672						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-4D
AD-99 ALUMINA
T=1303 K
BLAU. AFCRL-TR-60-416
REF. 1SE-4


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-4E
TWA-2 ALUMINA
T=873 K
BLAU. AFCRL-TR-60-416
REF. 1SE-4


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-4F
TWA-2 ALUMINA
T=1303
BLAU, AFCRL-TR-60-416
REF. 1SE-4

Carlson (Ref. 1SE-6)

These data represent $\epsilon(\lambda)$ for liquid Al_2O_3 droplets 1 to 10 μ in diameter in a rocket flame. A grating spectrometer with a tungsten comparitor source was used. These data indicate that a discontinuity at the alumina melting point occurs in $\epsilon(\lambda)$. No error analysis was given. Data were taken directly from a table.

a. $\lambda = 1.3\mu$


T	ϵ	T	ϵ	T	ϵ	T	ϵ
2800.000	.0042	2520.000	.0115	2760.000	.0027	2620.000	.0026
2790.000	.0034	2490.000	.0042	2700.000	.0009	2400.000	.0000
2740.000	.0034	2470.000	.0052	2730.000	.0051		


b. $\lambda = 1.7\mu$


T	ϵ	T	ϵ	T	ϵ	T	ϵ
2830.000	.0097	2530.000	.0115	2780.000	.0029	2620.000	.0012
2790.000	.0034	2490.000	.0114	2700.000	.0010	2400.000	.0000
2740.000	.0032	2470.000	.0057	2730.000	.0057		

c. $\lambda = 2.33\mu$

T	ϵ	T	ϵ	T	ϵ	T	ϵ
2830.000	.0051	2530.000	.0000	2760.000	.0139	2620.000	.0018
2790.000	.0026	2490.000	.0029	2700.000	.0065	2400.000	.0000
2740.000	.0022	2470.000	.0059	2730.000	.0074		


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-6A
LIQUID ALUMINA DROPLETS
1.3 MICRONS WAVELENGTH
CARLSON. 10TH SYMPOSIUM ON COMBUS
TION
REF. 1SE-6
SPECTRAL EMISSIVITY
1.
.9
.8
.7
.6
.5
.4
.3
.2
.1
0.
0.
300.
600.
900.
1200.
1500.
1800.
2100.
2400.
2700.
3000.
Temperature (Degrees Kelvin)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-6B
LIQUID ALUMINA DROPLETS
1.7 MICRONS WAVELENGTH
CARLSON. 10TH SYMPOSIUM ON COMBUS
TION
REF. 1SE-6
SPECTRAL EMISSIVITY
1.
.9
.8
.7
.6
.5
.4
.3
.2
.1
0.
0.
300.
600.
900.
1200.
1500.
1800.
2100.
2400.
2700.
3000.
TEMPERATURE(DEGREES KELVIN)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-6C
LIQUID ALUMINA DROPLETS
2.33 MICRONS WAVELENGTH
CARLSON. 10TH SYMPOSIUM ON COMBUS
TION
REF. 1SE-6
SPECTRAL EMISSIVITY
1.
.9
.8
.7
.6
.5
.4
.3
.2
.1
0.
0. 300. 600. 900. 1200. 1500. 1800. 2100. 2400. 2700. 3000.
TEMPERATURE(DEGREES KELVIN)

Clark (Ref. ISE-8)

Alumina specimens, 99.2 percent pure in a hollow cylindrical form with smooth, but not polished, surfaces were used. Measurements were made using a rotating furnace system and a double beam NaCl prism spectrometer with an unspecified bandpass. Thermocouples were used for temperature measurement. Maximum error limits in $\epsilon(\lambda)$ were + 0.012, -0.032 (at 2 μ). These data were taken directly from a table.


These data show $\epsilon(\lambda)$ higher than the representative curve given in Section I-1.3 for wavelengths longer than 12μ.


a. T = 1200°K

λ	ε	λ	ε	λ	ε	λ	ε
1.000	.060	1.500	.046	2.000	.042	2.500	.045
3.000	.058	3.500	.080	4.000	.141	4.500	.248
5.000	.389	5.500	.530	6.000	.653	6.500	.783
7.000	.892	7.500	.945	8.000	.966	8.500	.939
9.000	.965	9.500	.978	10.000	.984	10.500	.982
11.000	.958	11.500	.895	12.000	.836	12.500	.833
13.000	.833	13.500	.833	14.000	.828	14.500	.814
15.000	.799						

b. T = 1400°K

λ	ε	λ	ε	λ	ε	λ	ε
1.000	.073	1.500	.063	2.000	.061	2.500	.065
3.000	.075	3.500	.106	4.000	.169	4.500	.287
5.000	.431	5.500	.572	6.000	.696	6.500	.821
7.000	.910	7.500	.956	8.000	.975	8.500	.947
9.000	.973	9.500	.985	10.000	.989	10.500	.987
11.000	.972	11.500	.909	12.000	.860	12.500	.848
13.000	.849	13.500	.848	14.000	.841	14.500	.830
15.000	.813						



SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-8A
ALUMINA
T=1200 K
CLARK. J. RES. NBS 70A. 393 (1966)
REF. 1SE-8


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-8B
ALUMINA
T=1400 K
CLARK. J. RES. NBS 70A. 393 (1966)
REF. 1SE-8

Clark (Ref. 1SE-8)

c. $T = 1600^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
1.000	.397	1.500	.088	2.000	.085	2.500	.089
3.000	.397	3.500	.125	4.000	.177	4.500	.316
5.000	.459	5.500	.595	6.000	.711	6.500	.832
7.000	.912	7.500	.955	8.000	.973	8.500	.944
9.000	.967	9.500	.981	10.000	.986	10.500	.986
11.000	.971	11.500	.921	12.000	.873	12.500	.856
13.000	.852	13.500	.852	14.000	.846	14.500	.833
15.000	.813						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-8C
ALUMINA
T=1600 K
CLARK, J. RES. NBS 70A, 393 (1966)
REF. 1SE-8
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.

Mergerian (Ref. 1SE-11)

The spectral emissivity of a rotating Linde sapphire sample in a furnace containing a blackbody reference was measured using an NaCl double pass prism monochromator with a band-pass of approximately 0.25 μ. Precision was not specifically stated. These data were digitized from discrete points.


These data are in good agreement with the representative curves of Section I-1.3.


a. $T = 373^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
4.475	.178	4.979	.425	5.451	.657	5.9[illegible]	.798
6.443	.848	6.932	.857	7.430	.814	7.93[illegible]	.827
8.432	.846	8.957	.825	9.462	.827	9.953	.834
10.451	.796	10.959	.577	11.963	.189	12.491	.188
12.396	.159						

b. $T = 648^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
3.002	.004	3.496	.010	3.985	.059	4.486	.201
4.935	.437	5.468	.726	5.935	.817	6.446	.832
6.956	.837	7.440	.837	7.927	.849	8.443	.867
8.951	.866	9.458	.876	9.952	.876	10.445	.856
10.966	.677	11.481	.416	11.984	.261	12.494	.218
13.006	.199						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-11A
SAPPHIRE
T=373 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1SE-11


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-11B
SAPPHIRE
T=648 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1SE-11


Mergerian (Ref. 1SE-11)


c. $T = 1013^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
1.[illegible]02	.[illegible]	1.493	.000	2.001	.000	2.491	.000
3.[illegible]07	.[illegible]	3.993	.078	4.479	.278	4.964	.626
5.[illegible]60	.797	5.937	.835	6.938	.871	7.439	.873
7.933	.[illegible]74	8.447	.894	8.943	.901	9.437	.917
9.935	.927	10.457	.883	10.949	.821	11.447	.634
11.960	.[illegible]85	12.483	.317	12.981	.277		

d. $T = 1213^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
2.991	.[illegible]10	3.492	.628	4.003	.148	4.474	.408
[illegible].966	.[illegible]48	[illegible].439	.929	5.937	.866	6.438	.890
[illegible].939	.[illegible]39	[illegible].430	.908	7.944	.908	8.464	.927
[illegible].947	.918	9.[illegible]40	.948	9.938	.947	10.426	.938
10.961	.[illegible]50	11.449	.668	11.964	.458	12.469	.359
12.969	.[illegible]20						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-11D
SAPPHIRE
T=1213 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1SE-11


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-11C
SAPPHIRE
T=1013 K
MERGERIAN. PROC. IRIS 4. 146 (1959)
REF. 1SE-11

Richmond (Ref. 1SE-12)

$\epsilon(\lambda)$ for alumina was measured at an unspecified temperature using the NBS rotating cylinder method (Ref. 1SE-7, 1SE-8) to determine the degree to which $\epsilon(\lambda)$ is a function of surface roughness. It was found that no appreciable change in emissivity occurred below 14 μ after the smooth alumina was grit blasted. The peak at 3 μ is attributable to water. No erro analysis is given. The data points were digitized from a curve.

a. Before grit blasting.


λ	ϵ	λ	ϵ	λ	ϵ	λ	ϵ
1.021	.246	1.390	.226	1.849	.216	2.090	.216
2.482	.223	2.582	.237	2.677	.253	2.724	.303
2.750	.341	2.744	.388	2.744	.416	2.780	.422
[illegible]	.426	2.991	.424	2.966	.409	3.041	.381
[illegible]	[illegible]	3.200	.341	3.275	.334	3.325	.332
[illegible]	.333	3.4[illegible]	.357	3.054	.389	3.313	.432
3.940	.469	4.061	.507	4.136	.541	4.164	.562
4.187	.593	4.187	.595	4.221	.598	4.258	.596
4.320	.595	4.349	.600	4.376	.613	4.438	.660
4.563	.704	4.665	.747	4.695	.781	4.816	.814
4.925	.841	5.061	.868	5.200	.893	5.419	.921
5.654	.939	6.089	.961	6.339	.973	6.724	.984
7.169	.989	7.425	.991	7.747	.988	7.969	.979
8.133	.972	8.255	.966	8.321	.957	8.335	.949
8.451	.946	8.544	.947	8.741	.958	9.004	.970
9.275	.988	9.920	.986	9.736	.989	10.022	.989
10.291	.985	10.487	.976	10.701	.963	10.869	.947
11.026	.928	11.186	.904	11.336	.872	11.476	.845
11.651	.819	11.824	.796	11.964	.783	12.087	.779
12.215	.778	12.402	.782	12.615	.786	12.926	.796
13.171	.805	13.433	.811	13.590	.814	13.946	.812
14.287	.805	14.490	.795	14.761	.784	14.902	.778


Richmond (Ref. ISE-12)

b. After grit blasting.

λ	ε	λ	ε	λ	ε	λ	ε
1.015	.252	1.306	.230	1.608	.217	1.894	.211
2.123	.210	2.587	.211	2.581	.220	2.678	.238
2.730	.300	2.776	.341	2.825	.335	2.664	.390
2.917	.366	2.973	.372	3.120	.360	3.237	.349
3.414	.341	3.528	.346	3.624	.367	3.740	.390
3.704	.413	3.850	.438	3.993	.485	4.117	.532
4.171	.559	4.282	.565	4.282	.560	4.231	.551
4.332	.548	4.370	.559	4.393	.581	4.425	.607
4.464	.635	4.509	.663	4.561	.688	4.630	.716
4.765	.765	4.932	.814	5.093	.855	5.256	.885
5.428	.913	5.628	.928	5.867	.938	6.300	.954
6.936	.960	6.949	.970	7.098	.969	7.339	.972
7.746	.977	7.879	.979	7.944	.975	8.182	.953
8.343	.956	8.424	.965	8.519	.938	8.713	.949
8.997	.954	9.117	.966	9.439	.974	9.668	.978
9.924	.978	10.229	.977	10.397	.970	10.616	.960
10.795	.943	11.128	.922	11.304	.903	11.477	.880
11.630	.855	11.783	.832	12.058	.801	12.223	.785
12.437	.768	12.746	.749	12.867	.745	12.999	.745
13.223	.734	13.306	.733	13.529	.724	13.712	.715
13.934	.703	14.185	.693	14.462	.633	14.690	.674
14.929	.665						

Reproduced from best available copy.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-12A
ALUMINA
T= UNSPECIFIED
RICHMOND. THERMOPHYS. AND TEMPER.
CONTROL
REF. 1SE-12



SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-12B
ALUMINA
T= UNSPECIFIED
RICHMOND. THERMOPHYS. AND TEMPER.
CONTROL
REF. 1SE-12

Schatz (Ref. 1SE-14)

Spectral emissivity was measured for sintered Al_2O_3, 99 percent pure, from Linde Co. using a double beam spectrometer with unspecified bandpass and a standard blackbody. The sample was heated by conduction from a holder. The estimated accuracy is to within 5 percent for $\lambda > 2\ \mu$. Data are digitized from curves and in very good agreement with the representative curves given in Section I-1.3, except for a small peak at 13μ. T = 373°K, 885°K, 1003°K, 1148°K, and 1273°K.

a. T = 373°K

λ	ε	λ	ε	λ	ε	λ	ε
1.005	.182	1.984	.177	3.011	.174	3.315	.171
3.607	.174	3.817	.180	3.980	.184	4.126	.193
4.291	.216	4.415	.251	4.504	.275	4.636	.306
4.792	.345	4.943	.383	5.098	.422	5.246	.464
5.375	.503	5.472	.544	5.575	.588	5.677	.626
5.793	.567	5.937	.710	6.068	.748	6.234	.787
6.447	.822	6.623	.849	6.938	.869	7.317	.881
7.619	.889	7.916	.898	8.121	.890	8.373	.889
8.634	.894	8.847	.894	9.029	.900	9.252	.897
9.469	.903	9.727	.904	9.977	.902	10.223	.902
10.327	.901	10.430	.896	10.530	.882	10.635	.865
10.779	.835	10.839	.822	10.935	.779	11.030	.729
11.122	.684	11.225	.639	11.308	.595	11.410	.543
11.509	.512	11.584	.504	11.656	.502	11.751	.518
11.865	.534	11.982	.553	12.061	.567	12.225	.585
12.379	.596	12.520	.606	12.672	.610	12.852	.607
13.012	.609	13.243	.602	13.460	.596	13.645	.580
13.858	.557	14.098	.535	14.325	.512	14.565	.487
14.758	.452	14.995	.440				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-14A
SINTERED ALUMINA
T=373 K
SCHATZ, ML-TDR-64-146
REF. 1SE-14
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.


Schatz (Ref. 1SE-14)


b. T = 885°K

λ	ε	λ	ε	λ	ε	λ	ε
1.066	.104	1.993	.104	3.007	.104	3.513	.107
3.793	.108	3.921	.115	4.000	.130	4.094	.152
4.254	.201	4.444	.269	4.569	.305	4.739	.358
4.911	.414	5.070	.460	5.226	.507	5.412	.555
5.666	.503	5.766	.632	5.933	.671	6.101	.707
6.306	.743	6.538	.771	6.753	.797	7.014	.827
7.342	.837	7.595	.846	7.863	.850	8.358	.851
8.335	.863	9.138	.874	9.429	.873	9.698	.874
9.952	.879	10.144	.878	10.279	.880	10.477	.877
10.633	.866	10.763	.854	10.923	.823	11.098	.772
11.217	.729	11.389	.699	11.523	.623	11.654	.589
11.735	.576	11.972	.576	12.204	.577	12.348	.580
12.496	.573	12.628	.589	12.781	.599	12.993	.602
13.279	.600	13.591	.586	13.856	.581	14.087	.567
14.368	.567	14.676	.564	14.795	.564		

c. T = 1003°K

λ	ε	λ	ε	λ	ε	λ	ε
1.011	.102	2.001	.102	2.982	.102	3.518	.107
3.712	.115	3.883	.137	4.000	.164	4.101	.190
4.229	.233	4.371	.284	4.544	.343	4.705	.394
4.930	.450	5.136	.501	5.244	.544	5.431	.594
5.622	.644	5.764	.674	5.945	.706	6.174	.741
6.422	.775	6.668	.806	6.894	.822	7.156	.834
7.446	.843	7.779	.843	8.053	.851	8.347	.852
8.646	.868	8.916	.869	9.175	.875	9.421	.873
9.574	.872	9.875	.878	10.077	.881	10.293	.880
10.424	.879	10.615	.866	10.803	.847	10.947	.821
11.129	.797	11.276	.729	11.439	.680	11.636	.635
11.891	.612	12.263	.614	12.537	.615	12.781	.621
13.240	.624	13.244	.619	13.446	.615	13.634	.609
14.022	.603	14.149	.595	14.405	.587	14.578	.579
14.729	.573	14.881	.562	14.989	.554		


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-14B
SINTERED ALUMINA
T=885 K
SCHATZ. ML-TDR-64-146
REF. 1SE-14


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-14C
SINTERED ALUMINA
T=1003 K
SCHATZ. ML-TDR-64-146
REF. 1SE-14


Schatz (Ref. 1SE-14)


d. $T = 1148^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
1.304	.104	2.000	.104	2.998	.104	3.304	.108
3.540	.128	3.792	.146	3.981	.161	3.969	.191
4.100	.238	4.192	.282	4.355	.353	4.489	.407
4.625	.454	4.788	.500	4.985	.560	5.145	.609
5.294	.637	5.455	.677	5.638	.714	5.875	.757
6.099	.794	6.322	.822	6.548	.839	6.769	.853
7.333	.873	7.381	.892	7.662	.889	7.962	.891
8.233	.913	8.466	.905	8.716	.896	8.965	.896
9.264	.939	9.562	.912	9.911	.907	10.177	.906
10.363	.918	10.794	.885	10.998	.901	10.906	.879
11.367	.835	11.249	.753	11.429	.741	11.835	.692
11.955	.654	12.366	.656	12.576	.658	12.878	.661
13.079	.654	13.362	.639	13.589	.652	13.851	.651
14.031	.645	14.257	.602	14.470	.623	14.666	.615
14.321	.694	14.973					

e. $T = 1273^{\circ}K$

λ	ε	λ	ε	λ	ε	λ	ε
1.005	.104	1.995	.104	3.010	.107	3.436	.122
3.518	.149	3.785	.161	3.905	.188	4.021	.235
4.128	.282	4.348	.342	4.391	.403	4.522	.457
4.673	.509	4.961	.553	4.956	.594	5.100	.635
5.277	.679	5.455	.711	5.641	.748	5.629	.778
5.866	.798	5.960	.815	6.221	.832	6.441	.851
6.711	.873	6.959	.832	7.244	.894	7.533	.897
7.798	.898	8.002	.900	8.268	.906	8.559	.905
8.342	.911	8.152	.914	9.425	.914	9.716	.915
9.066	.913	10.155	.921	10.393	.922	10.455	.921
10.518	.916	10.747	.908	11.412	.880	11.023	.862
11.154	.837	11.276	.812	12.020	.776	11.527	.747
11.869	.720	11.848	.695	12.915	.684	12.249	.677
12.449	.574	12.669	.679	13.818	.678	13.146	.674
13.393	.672	13.902	.670	14.747	.667	14.029	.652
14.241	.651	14.518	.641		.627	14.973	.614


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-14D
SINTERED ALUMINA
T=1148 K
SCHATZ, ML-TDR-64-146
REF. 1SE-14


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1SE-14E
SINTERED ALUMINA
T=1273 K
SCHATZ, ML-TDR-64-146
REF. 1SE-14

Stierwalt (Ref. 1SE-16)

Sapphire, purity and crystal orientation unspecified, 0.79 mm thick, was studied using three single beam spectrometers to cover the entire spectral range of 4 μ to 125 μ using the standard blackbody comparison method. A temperature range of 4.2°K to 200°K was surveyed. An error analysis was not given. These data were digitized from curves.

These data were selected as representative spectral emittances in Section I-1.3 for sapphire above 12 μ, and are in good agreement with the representative data below 12μ (Figure I-1.3.1).

a. T = 4.2°K, 77°K, and 200°K, λ < 24.1 μ.

λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	[illegible]	[illegible]	4.377	7.125E-02
[illegible]	[illegible]	[illegible]	[illegible]	4.973	1.115E-01
[illegible]	[illegible]	[illegible]	[illegible]	5.523	1.910E-01
[illegible]	[illegible]	[illegible]	[illegible]	6.068	3.570E-01
[illegible]	[illegible]	[illegible]	[illegible]	6.444	6.175E-01
[illegible]	[illegible]	[illegible]	[illegible]	6.896	8.448E-01
[illegible]	[illegible]	[illegible]	[illegible]	7.300	9.271E-01
[illegible]	[illegible]	[illegible]	[illegible]	8.025	9.621E-01
[illegible]	[illegible]	[illegible]	[illegible]	9.254	9.744E-01
[illegible]	[illegible]	[illegible]	[illegible]	10.135	9.[illegible]5E-01
[illegible]	[illegible]	[illegible]	[illegible]	10.723	8.240E-01
[illegible]	[illegible]	[illegible]	[illegible]	11.142	5.947E-01
[illegible]	[illegible]	[illegible]	[illegible]	11.345	3.479E-01
[illegible]	[illegible]	[illegible]	[illegible]	11.674	2.844E-01
[illegible]	[illegible]	[illegible]	[illegible]	12.095	2.243E-01
[illegible]	[illegible]	[illegible]	[illegible]	12.709	1.935E-01
[illegible]	[illegible]	[illegible]	[illegible]	13.297	1.673E-01
[illegible]	[illegible]	[illegible]	[illegible]	13.843	1.268E-01
[illegible]	[illegible]	[illegible]	[illegible]	14.590	1.135E-01
[illegible]	[illegible]	[illegible]	[illegible]	15.238	1.675E-01
[illegible]	[illegible]	[illegible]	[illegible]	15.867	2.795E-01
[illegible]	[illegible]	[illegible]	[illegible]	16.386	2.072E-01
[illegible]	[illegible]	[illegible]	[illegible]	16.866	3.066E-01

a. T = 4.2°K, 77°K, and 200°K. $\lambda < 24.1\mu$. (continued)

λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	[illegible]	[illegible]	17.511	4.010E-01
[illegible]	[illegible]	[illegible]	[illegible]	18.144	5.650E-01
[illegible]	[illegible]	[illegible]	[illegible]	19.566	7.565E-01
[illegible]	[illegible]	[illegible]	[illegible]	20.157	5.594E-01
[illegible]	[illegible]	[illegible]	[illegible]	20.616	6.600E-01
[illegible]	[illegible]	[illegible]	[illegible]	20.803	2.035E-01
[illegible]	[illegible]	[illegible]	[illegible]	21.174	6.800E-02
[illegible]	[illegible]	[illegible]	[illegible]	22.270	9.425E-02
[illegible]	[illegible]	[illegible]	[illegible]	23.416	1.910E-01
[illegible]	[illegible]	[illegible]	[illegible]	24.007	2.949E-01

b. T = 4.2°K, $\lambda > 24\mu$.


λ	ε	λ	ε	λ	ε
[illegible]	[illegible]	[illegible]	[illegible]	24.701	3.555E-01
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	3.990E-01
[illegible]	[illegible]	[illegible]	[illegible]	26.229	4.851E-01
[illegible]	[illegible]	[illegible]	[illegible]	26.922	4.113E-01
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	1.955E-01
[illegible]	[illegible]	[illegible]	[illegible]	29.617	8.625E-02
[illegible]	[illegible]	[illegible]	[illegible]	34.460	4.975E-02
[illegible]	[illegible]	[illegible]	[illegible]	45.811	4.025E-02


c. $T = 77^{\circ}K$, $\lambda > 24\mu$.


λ	ϵ	λ	ϵ	λ	ϵ
24.480	3.906E-01	24.873	3.504E-01	25.336	3.604E-01
25.562	4.234E-01	25.866	4.635E-01	26.362	4.914E-01
26.803	5.003E-01	27.316	4.909E-01	27.855	4.577E-01
28.397	4.237E-01	29.086	3.695E-01	29.917	3.466E-01
30.725	3.084E-01	31.677	2.760E-01	32.169	2.593E-01
32.756	2.555E-01	33.264	2.583E-01	33.564	2.639E-01
33.846	2.683E-01	34.244	2.621E-01	34.667	2.432E-01
35.221	2.258E-01	35.763	2.113E-01	36.894	1.937E-01
38.370	1.820E-01	40.663	1.608E-01	43.530	1.383E-01
46.359	1.178E-01	50.994	9.375E-02	55.448	7.950E-02
60.953	6.525E-02	67.441	5.050E-02	75.021	3.950E-02
82.261	3.325E-02	91.586	2.550E-02	99.467	2.175E-02
109.882	2.175E-02	124.927	2.050E-02		


d. $T = 200^{\circ}K$, $\lambda > 24\mu$.


λ	ϵ	λ	ϵ	λ	ϵ
24.385	3.627E-01	24.955	3.323E-01	25.396	4.924E-01
25.653	5.257E-01	26.276	5.738E-01	27.316	6.135E-01
28.447	6.368E-01	30.426	6.630E-01	32.668	6.767E-01
34.959	6.812E-01	37.484	6.835E-01	40.496	6.835E-01
44.559	6.835E-01				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURES 1SE-16A AND -16B
SAPPHIRE
T=4.2 K FOR WAVELENGTHS GREATER
THAN 24.1 MICRONS
T=4.2 K TO 200 K FOR WAVELENGTHS
LESS THAN 24.1 MICRONS
STIERWALT. THERMOPHYS. AND TEMP
CONTROL
REF. 1SE-16
SPECTRAL EMISSIVITY
WAVE ENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURES 1SE-16A AND -16B
SAPPHIRE
T=4.2 K FOR WAVELENGTHS GREATER
THAN 24.1 MICRONS
T=4.2 K TO 200 K FOR WAVELENGTHS
LESS THAN 24.1 MICRONS
STIERWALT. THERMOPHYS. AND TEMP.
CONTROL
REF. 1SE-16
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-16C
SAPPHIRE
T=77 K
STIERWALT. THERMOPHYS. AND TEMP. CONTROL
REF. 1SE-16
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-16C
SAPPHIRE
T=77 K
STIERWALT. THERMOPHYS. AND TEMP. CONTROL
REF. 1SE-16
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
FIGURE 1SE-160
SAPPHIRE
T=200 K
STIERWALT, THERMOPHYS. AND TEMP.
CONTROL
REF. 1SE-16

Streed (1SE-17)

Flame sprayed alumina particles of 99.95 purity were heated in a graphite tube furnace and studied using a KBr prism spectrometer with a bandwidth of 0.016 μ to 0.15 μ. Temperatures were measured using thermocouples and an optical pyrometer; sample substrates were estimated to be within 45°K of the nominal temperature. Particles of 0.06, 1.0 and 8.0 μ diameter were studied over a temperature range of 300°K to 2000°K. The peak at 3 μ is water associated. No error analysis was given. Data are digitized from lines.

These data are similar to the representative alumina powder data presented in Section 1-1.3.2.

a. Particle size = .06 μ. T = 300°K.

λ	ε	λ	ε	λ	ε	λ	ε
1.705	.203	1.293	.223	1.504	.230	1.690	.247
1.857	.259	2.189	.268	2.272	.273	2.510	.294
2.581	.305	2.672	.332	2.780	.347	2.728	.373
2.742	.412	2.776	.491	2.816	.480	2.845	.514
2.889	.541	2.928	.567	3.000	.579	3.100	.571
3.192	.546	3.201	.513	3.280	.480	3.408	.451
3.568	.422	3.790	.411	3.960	.405	4.111	.411
4.357	.423	4.551	.451	4.743	.474	4.377	.499
5.019	.527	5.127	.559	5.240	.586	5.362	.628
5.448	.671	5.588	.712	5.741	.762	5.340	.829
6.042	.841	5.980	.881	6.090	.847	6.302	.909
6.525	.928	6.765	.942	7.155	.954	7.419	.952
7.795	.959	7.877	.971	8.341	.980	8.801	.980
9.159	.978	9.524	.978	9.753	.971	9.843	.971
9.954	.964	10.146	.956	10.149	.934	10.223	.909
10.261	.869	10.335	.826	10.374	.780	10.408	.741
10.481	.715	10.584	.696	10.745	.677	10.802	.672
11.159	.673	11.362	.681	11.661	.692	11.871	.706
12.122	.724						
13.366	.771	13.750	.771	14.213	.768	14.405	.767
14.567	.763	14.729	.770	15.215	.770	15.525	.768
15.784	.764	16.198	.756	16.581	.751	16.961	.745
17.382	.733	17.740	.731	18.214	.725	18.681	.725
19.282	.730	19.643	.736	20.194	.749	20.607	.757
21.175	.763	21.589	.772	21.919	.779		

Streed (Ref. ISE-17)

b. Particle size = 0.06 μ. T = 1000°K

λ	ε	λ	ε	λ	ε	λ	ε
1.[illegible]	.291	1.295	.292	1.377	.291	1.577	.295
1.773	.303	1.954	.312	2.076	.316	2.218	.324
2.382	.327	2.[illegible]	.336	2.650	.353	2.709	.369
2.867	.383	2.976	.388	3.036	.390	3.149	.381
3.269	.371	3.416	.359	3.487	.356	3.578	.361
3.720	.368	3.843	.379	3.978	.392	4.150	.407
4.301	.427	4.456	.449	4.589	.468	4.721	.490
4.842	.518	5.016	.552	5.161	.592	5.340	.642
5.493	.692	5.[illegible]	.739	5.731	.791	5.879	.825
[illegible].983	.851	6.111	.877	6.265	.908	6.428	.931
6.525	.941	6.765	.954	7.039	.961	7.163	.957
7.426	.956	7.656	.960	7.863	.968	8.121	.976
8.294	.980	8.527	.975	8.716	.970	8.903	.961
9.111	.955	9.292	.952	9.574	.953	9.771	.953
9.939	.958	10.384	.955	10.192	.944	10.272	.931
[illegible].389	.887	10.457	.885	10.576	.863	10.682	.842
[illegible].786	.823	10.861	.806	10.924	.789	11.007	.778
[illegible].143	.770	11.321	.763	11.510	.757	11.650	.750
11.812	.742	11.967	.738	12.094	.741	12.222	.746
13.428	.776	13.717	.774	14.208	.776	14.623	.779
15.082	.784	15.501	.792	16.016	.797	16.581	.802
17.119	.804	17.422	.806	17.754	.812	18.126	.810
18.467	.802	18.765	.794	19.172	.784	19.381	.782
19.917	.782	20.529	.782	21.170	.781	21.686	.779




FIGURE 1SE-17A
ALUMINA PARTICLES. .06 MICRON DIA.
T=300 K
STREED. AFRPL-TR-73-3
REF. 1SE-17




FIGURE 1SE-17B
ALUMINA PARTICLES. .06 MICRON DIA.
T=1000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17

Streed (Ref. 1SE-17)

c. Particle size = 0.06 μ. T = 1500°K

λ	ε	λ	ε	λ	ε	λ	ε
1.108	.189	1.467	.234	1.709	.215	1.923	.226
1.351	.248	2.523	.256	2.682	.260	2.956	.264
3.199	.273	3.431	.284	3.653	.302	3.975	.333
4.245	.375	4.470	.421	4.615	.455	4.810	.502
4.981	.552	5.158	.607	5.330	.655	5.500	.703
5.551	.754	5.816	.778	5.933	.802	6.054	.826
6.189	.852	6.328	.879	6.485	.902	6.651	.922
6.879	.936	7.160	.947	7.410	.951	7.599	.951
7.815	.959	8.097	.973	8.509	.971	8.741	.969
8.834	.956	9.093	.947	9.372	.943	9.628	.943
9.899	.945	10.186	.951	10.239	.956	10.428	.952
10.570	.943	10.704	.924	10.976	.877	11.220	.836
11.459	.785	11.687	.740	11.899	.783		
13.433	.634	13.897	.677	14.459	.670	14.942	.672
15.171	.663	15.725	.650	16.203	.642	16.479	.641
16.776	.646	17.250	.656	17.710	.676	18.158	.705
18.465	.729	18.630	.752	18.836	.780	19.140	.815
19.690	.742	20.194	.859	20.524	.849	20.822	.845
21.102	.832	21.361	.816	21.571	.794		

Streed (Ref. 1SE-17)

d. Particle size = 0.06 μ. T = 2000^{o}K

λ	ϵ	λ	ϵ	λ	ϵ	λ	ϵ
1.003	.164	1.507	.188	1.715	.198	2.132	.217
2.534	.222	2.804	.220	3.119	.217	3.402	.222
3.594	.234	3.334	.201	3.964	.288	4.183	.327
4.292	.362	4.454	.407	4.618	.462	4.743	.513
4.949	.580	5.146	.659	5.379	.739	5.660	.808
5.873	.854	6.034	.888	6.349	.938	6.542	.960
6.681	.963	6.308	.959	7.012	.958	7.185	.965
7.351	.971	7.558	.979	7.802	.977	7.969	.971
8.197	.973	8.278	.981	8.656	.975	8.856	.975
9.116	.955	9.377	.959	9.530	.928	9.647	.929
9.900	.937	10.004	.945	10.106	.949	10.377	.945
10.473	.928	10.586	.912	10.828	.892	11.067	.873
11.201	.855	11.329	.836	11.503	.808	11.599	.785
11.747	.761	11.897	.744	12.057	.730	12.197	.717
13.463	.698	14.252	.689	14.726	.683	15.279	.675
15.350	.661	16.340	.654	16.712	.651	17.285	.647
17.633	.653	18.171	.675	18.481	.695	18.793	.717
19.108	.751	19.367	.771	19.701	.797	20.073	.803
20.453	.797	20.848	.789	21.175	.778	21.565	.766
21.738	.763	21.924	.759				




FIGURE 1SE-17C
ALUMINA PARTICLES. .06 MICRON DIA.
T=1500 K
STREED. AFRPL-TR-73-3
REF. 1SE-17




FIGURE 1SE-17D
ALUMINA PARTICLES. .06 MICRON DIA.
T=2000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17

Streed (Ref. 1SE-17)


e. Particle size = 1.0μ. T = 300°K


λ	ε	λ	ε	λ	ε	λ	ε
1.179	.225	1.304	.235	1.594	.245	1.901	.251
2.214	.269	2.349	.268	2.449	.277	2.527	.290
2.587	.319	2.630	.345	2.666	.372	2.715	.402
2.764	.429	2.811	.452	2.882	.484	2.958	.514
3.061	.492	3.129	.469	3.189	.444	3.215	.429
3.266	.415	3.420	.388	3.624	.365	3.887	.351
4.162	.359	4.234	.355	4.559	.378	4.768	.405
4.938	.434	5.100	.400	5.212	.488	5.294	.529
5.352	.560	5.426	.602	5.497	.634	5.571	.669
5.554	.730	5.794	.748	5.937	.773	6.096	.808
6.283	.838	6.503	.866	6.777	.900	7.104	.928
7.447	.946	7.612	.960	8.147	.971	8.523	.982
8.928	.981	9.137	.981	9.456	.977	9.744	.967
9.336	.957	10.049	.934	10.142	.889	10.212	.862
10.271	.838	10.341	.802	10.427			
10.602	.747	10.726	.738	10.877	.735	11.104	.737
11.359	.745	11.600	.754	11.930	.759	12.070	.775
12.177	.782						
13.714	.814	14.207	.810	14.582	.811	15.188	.814
15.607	.814	16.221	.807	16.513	.800	17.101	.789
17.452	.789	17.745	.790	18.147	.793	18.537	.797
19.118	.805	19.299	.815	20.068	.824	20.356	.827
20.648	.829	21.461	.832	21.933	.835		

Streed (Ref. 1SE-17)

f. Particle size = 1.0 μ. T = 1000°K

λ	ε	λ	ε	λ	ε	λ	ε
1.[illegible]81	.245	1.[illegible]42	.249	1.414	.251	1.598	.249
1.446	.246	2.091	.241	2.292	.240	2.490	.250
2.598	.255	2.892	.293	2.774	.322	2.840	.335
2.952	.[illegible]46	3.169	.319	3.249	.335	3.412	.326
3.605	.314	3.759	.313	3.906	.310	4.029	.315
4.157	.327	4.313	.342	4.406	.363	4.509	.383
4.[illegible]81	.419	4.603	.445	4.798	.486	4.904	.524
5.[illegible]61	.561	5.116	.598	5.247	.636	5.363	.674
5.[illegible]15	.719	5.381	.764	5.911	.817	6.139	.857
6.[illegible]71	.890	6.547	.911	6.653	.921	6.789	.926
6.92[illegible]	.923	7.007	.921	7.161	.921	7.326	.924
7.4[illegible]0	.926	7.536	.930	7.747	.927	7.901	.924
8.[illegible]84	.921	8.273	.920	8.414	.923	8.564	.927
8.[illegible]31	.928	8.829	.928	9.087	.928	9.214	.924
9.[illegible]16	.926	9.[illegible]15	.926	9.744	.925	9.889	.920
10.034	.912	10.155	.899	10.302	.879	10.464	.845
10.[illegible]02	.811	10.763	.770	10.963	.739	11.188	.711
11.419	.69[illegible]	11.[illegible]50	.682	11.808	.679	11.980	.682
12.128	.68[illegible]	12.220	.694				
13.696	.728	14.043	.729	14.283	.732	14.473	.736
14.[illegible]94	.741	14.793	.742	15.[illegible]07	.739	15.442	.737
15.575	.728	15.888	.724	16.247	.721	16.641	.719
17.129	.721	17.359	.727	17.[illegible]01	.739	17.785	.746
17.[illegible]87	.750	18.238	.746	18.516	.739	18.799	.728
19.[illegible]72	.714	19.[illegible]40	.708	19.674	.701	19.[illegible]77	.698
20.13[illegible]	.703	20.319	.714	20.562	.728	20.817	.743
21.074	.750	21.240	.751	21.451	.748	21.719	.745
21.914	.742						


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-17E
ALUMINA PARTICLES. 1.0 MICRON DIA.
T=300 K
STREED. AFRPL-TR-73-3
REF. 1SE-17
WAVELENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
FIGURE 1SE-17F
ALUMINA PARTICLES. 1.0 MICRON DIA.
T=1000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17
WAVELENGTH(MICRONS)

Streed (Ref. ISE-17)


g. Particle size = 1.0 μ. T = 1500°K


λ	ε	λ	ε	λ	ε	λ	ε
1.[illegible]	.158	1.405	.159	1.710	.161	2.044	.163
[illegible]	.167	2.712	.174	3.015	.182	3.339	.194
[illegible]	.211	3.371	.237	4.028	.268	4.166	.299
[illegible]	.282	4.376	.360	4.467	.383	4.613	.429
[illegible]	.325	4.813	.511	4.885	.545	4.965	.574
[illegible]	.470	5.121	.627	5.199	.654	5.268	.679
[illegible]	.601	5.457	.733	5.550	.757	5.644	.786
[illegible]	.714	5.819	.841	6.092	.868	6.290	.893
[illegible]	.810	6.677	.939	6.804	.948	7.142	.954
6.[illegible]	.814	7.507	.958	7.683	.961	7.939	.972
7.[illegible]	.857	8.488	.972	8.058	.965	8.875	.955
7.[illegible]	.974	9.312	.944	9.475	.945	9.845	.947
8.[illegible]	.946	10.[illegible]	.963	10.326	.959	10.472	.953
9.[illegible]	.976	10.811	.918	10.903	.898	11.096	.870
9.[illegible]	.956	11.298	.822	11.397	.737	11.493	.773
10.[illegible]	.935	11.711	.722	11.856	.695	12.043	.668
11.[illegible]	.947						
11.[illegible]	.747	14.254	.617	14.758	.615	15.322	.606
12.184	.656	16.154	.561	16.628	.585	17.077	.595
13.[illegible]	.629	17.991	.635	18.238	.664	18.537	.693
15.[illegible]	.717	18.917	.737	19.091	.761	19.278	.786
17.[illegible]	.598	19.381	.828	20.359	.839	20.945	.839
18.[illegible]	.715	21.502	.735	21.743	.759	21.871	.732
19.[illegible]	.813						
21.[illegible]	.859						
21.[illegible]	.712						

Streed (Ref. 1SE-17)

h. Particle size = 1.0 μ. T = 2000°K

λ	ε	λ	ε	λ	ε	λ	ε
1.007	.135	1.469	.148	1.696	.154	2.070	.157
2.378	.159	2.779	.158	3.031	.161	3.229	.171
3.406	.180	3.805	.197	3.860	.231	3.987	.260
4.084	.295	4.191	.322	4.270	.358	4.337	.385
4.428	.430	4.502	.465	4.588	.502	4.668	.532
4.756	.575	4.853	.609	4.961	.648	5.053	.679
5.163	.714	5.278	.739	5.430	.774	5.543	.799
5.740	.836	5.867	.860	6.084	.894	6.223	.914
6.422	.933	6.656	.948	6.884	.960	7.103	.965
7.423	.964	7.655	.967	7.782	.974	7.969	.984
8.181	.976	8.422	.982	8.638	.977	8.953	.968
9.193	.959	9.341	.954	9.578	.955	9.872	.959
10.043	.969	10.164	.977	10.392	.977	10.575	.968
10.761	.953	10.831	.935	11.108	.903	11.238	.882
11.501	.838	11.663	.812	11.334	.775	12.051	.738
12.209	.707						
13.642	.676	13.947	.681	14.360	.677	14.913	.663
15.299	.650	15.848	.635	16.348	.620	16.835	.615
17.134	.629	17.535	.631	17.859	.649	18.091	.665
18.428	.638	18.717	.737	18.914	.756	19.163	.791
19.393	.812	19.722	.835	20.195	.846	20.434	.848
20.753	.846	21.205	.831	21.454	.812	21.649	.790
21.821	.773	21.922	.759				


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-17H
ALUMINA PARTICLES. 1.0 MICRON DIA.
T=2000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-17G
ALUMINA PARTICLES. 1.0 MICRON DIA.
T=1500 K
STREED. AFRPL-TR-73-3
REF. 1SE-17
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)

Streed (Ref. 1SE-17)


i. Particle size = 8.0 μ . T = 300°K

λ	ε	λ	ε	λ	ε	λ	ε
1.701	.194	1.258	.204	1.517	.212	1.794	.225
2.032	.236	2.297	.251	2.503	.259	2.557	.273
2.658	.309	2.886	.348	2.726	.382	2.790	.412
3.275	.448	3.005	.488	3.100	.474	3.218	.444
3.324	.414	3.419	.383	3.483	.363	3.544	.352
3.750	.342	3.976	.342	4.106	.347	4.373	.369
4.616	.397	4.398	.429	5.028	.459	5.210	.497
5.356	.537	5.479	.575	5.620	.622	5.746	.671
5.853	.714	5.952	.755	6.011	.784	6.080	.813
6.229	.846	6.396	.877	6.523	.895	6.663	.911
6.806	.923	7.004	.941	7.154	.950	7.471	.963
7.758	.970	8.313	.974	8.271	.978	8.545	.982
8.327	.982	8.971	.978	9.136	.977	9.427	.975
9.599	.972	9.918	.970	10.044	.948	10.164	.915
10.268	.890	10.412	.857	10.553	.829	10.711	.802
10.877	.781	11.026	.774	11.143	.775	11.410	.784
11.703	.796	11.997	.813	12.154	.825		
13.507	.855	14.248	.852	14.716	.849	15.220	.846
15.774	.843	16.268	.840	16.728	.836	17.203	.834
17.713	.834	18.249	.836	18.719	.839	19.219	.845
19.588	.857	20.220	.867	20.691	.874	21.276	.878
21.724	.891						

Streed (Ref. 1SE-17)

j. Particle size = 8.0 μ. T = 1000°K

λ	ε	λ	ε	λ	ε	λ	ε
1.903	.246	1.346	.246	1.730	.246	2.012	.[illegible]
2.217	.255	2.391	.266	2.586	.283	2.763	.304
2.442	.320	2.912	.340	2.991	.352	3.106	.350
3.241	.332	3.368	.313	3.464	.308	3.541	.306
3.526	.312	3.797	.326	3.935	.341	4.077	.359
4.292	.332	4.506	.434	4.689	.469	4.907	.523
5.071	.567	5.286	.622	5.515	.690	5.713	.753
5.921	.810	6.102	.850	6.191	.863	6.275	.872
6.363	.879	6.491	.883	6.815	.886	7.334	.890
7.931	.894	8.416	.899	8.638	.897	8.818	.897
8.951	.892	9.074	.861	9.190	.868	9.336	.851
9.443	.845	9.550	.845	9.732	.850	9.852	.858
10.004	.853	10.144	.866	10.275	.866	10.379	.863
10.483	.859	10.600	.844	10.702	.821	10.795	.779
10.864	.740	10.871	.719	10.923	.701	11.001	.690
11.143	.614	11.237	.681	11.506	.683	11.753	.684
11.999	.685						
13.769	.720	13.979	.718	14.165	.724	14.368	.735
14.660	.737	14.892	.734	15.047	.732	15.246	.727
15.462	.728	15.675	.734	15.944	.738	16.242	.738
16.523	.734	16.838	.729	17.098	.724	17.342	.726
17.522	.729	17.723	.733	17.989	.731	18.285	.728
18.536	.724	18.826	.721	19.104	.719	19.297	.726
19.487	.736	19.680	.750	19.914	.765	20.062	.774
20.255	.775	20.420	.773	20.631	.771	20.797	.768
20.978	.764	21.184	.764	21.336	.766	21.501	.768
21.680	.773	21.851	.778	21.986	.782		


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-17I
ALUMINA PARTICLES. 8 MICRONS DIA.
T=300 K
STREED. AFRPL-TR-73-3
REF. 1SE-17
SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
FIGURE 1SE-17J
ALUMINA PARTICLES. 8 MICRONS DIA.
T=1000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17

Streed (Ref. 1SE-17)

k. Particle size = 8.0 μ. T = 1500°K

λ	ε	λ	ε	λ	ε	λ	ε
1.001	.172	1.352	.169	1.640	.171	1.904	.177
2.170	.187	2.411	.204	2.568	.219	2.682	.230
2.818	.235	3.067	.236	3.164	.236	3.320	.243
3.516	.253	3.745	.269	3.967	.280	4.086	.297
4.234	.327	4.322	.352	4.437	.378	4.532	.396
4.618	.420	4.709	.443	4.787	.470	4.873	.496
4.950	.516	5.019	.543	5.112	.571	5.231	.599
5.333	.624	5.437	.649	5.536	.680	5.615	.706
5.702	.735	5.774	.760	5.868	.782	6.022	.821
6.144	.845	6.268	.868	6.411	.890	6.613	.913
6.946	.931	7.237	.938	7.545	.942	7.756	.953
8.159	.965	8.354	.966	8.603	.951	8.830	.943
9.020	.933	9.262	.933	9.536	.940	9.759	.941
9.898	.937	9.972	.933	10.157	.939	10.374	.941
10.534	.936	10.678	.919	10.788	.896	10.883	.877
11.031	.952	11.148	.827	11.229	.805	11.332	.782
11.467	.753	11.547	.725	11.657	.704	11.792	.683
11.953	.664	12.105	.649				
13.790	.665	13.941	.663	14.221	.656	14.397	.646
14.711	.639	15.198	.630	15.611	.622	15.992	.618
16.293	.620	16.671	.628	17.117	.640	17.393	.649
17.686	.663	18.242	.689	18.400	.707	18.670	.733
18.951	.756	19.222	.788	19.491	.806	19.766	.824
20.314	.835	20.770	.828	21.176	.811	21.444	.797
21.732	.791	21.916	.764				

Streed (Ref. 1SE-17)

1. Particle size = 8.0 μ. T = 2000°K

λ	ε	λ	ε	λ	ε	λ	ε
1.027	.192	1.254	.180	1.044	.193	1.902	.184
2.274	.158	2.557	.197	2.855	.207	3.124	.220
3.354	.235	3.563	.260	3.828	.281	4.016	.302
4.201	.325	4.314	.349	4.384	.368	4.525	.412
4.588	.448	4.692	.484	4.793	.526	4.900	.561
4.991	.591	5.098	.626	5.213	.664	5.334	.699
5.456	.735	5.576	.763	5.693	.796	5.837	.826
6.001	.853	6.167	.835	6.311	.902	6.473	.916
6.650	.929	6.896	.941	7.139	.947	7.369	.951
7.593	.961	7.888	.972	8.173	.972	8.371	.974
8.608	.973	8.779	.965	9.034	.948	9.192	.937
9.386	.929	9.626	.927	9.886	.929	10.188	.940
10.349	.941	10.498	.939	10.703	.924	10.823	.904
10.965	.878	11.108	.856	11.285	.826	11.422	.805
11.533	.774	11.772	.755	11.955	.727		
13.782	.634	14.226	.681	14.708	.675	15.201	.672
15.725	.654	16.126	.636	16.443	.637	16.827	.645
17.197	.656	17.745	.662	18.159	.665	18.471	.671
18.767	.689	19.128	.718	19.279	.737	19.524	.763
19.855	.801	20.236	.812	20.531	.807	20.835	.794
21.274	.781	21.669	.763	21.859	.756		




FIGURE 1SE-17K
ALUMINA PARTICLES. 8 MICRONS DIA.
T=1500 K
STREED. AFRPL-TR-73-3
REF. 1SE-17




FIGURE 1SE-17L
ALUMINA PARTICLES. 8 MICRONS DIA.
T=2000 K
STREED. AFRPL-TR-73-3
REF. 1SE-17

Touloukian (Ref. 1SE-18)

a. The spectral emissivity of General Electric Lucalox, a cold-pressed and sintered alumina with MgO added to control grain growth is presented for material of unspecified purity. The sample surface is machined, and the temperature is 813°K. Precision is ± 5 percent. These data show a much higher $\epsilon(\lambda)$ than the representative curve given in Section I, Figure I-1.3.1, and were digitized from discrete points.

λ	ε	λ	ε	λ	ε	λ	ε
1.001	.841	1.983	.953	2.975	.901	3.975	.903
4.48	.951						

b. Measurements of the spectral emissivity of Norton TWA, No. 2 alumina is presented. The alumina was machined ultrasonically and given a diamond wheel finish and had a purity of 98.56 percent. A precision of ± 4 percent is claimed. The temperature is 1323°K. These data are in good agreement with the representative curve given in Section I-1.3, and were digitized from discrete points.

λ	ε	λ	ε	λ	ε	λ	ε
1.985	.932	2.970	.900	3.955	.880	4.484	.833
4.966	.944	3.449	.742	8.683	.709	8.978	.680

c. Same as (b) above, but the temperature is 873°K.

λ	ε	λ	ε	λ	ε	λ	ε
1.947	.870	3.962	.839	4.495	.720	4.964	.840
5.465	.902	3.975	.920	5.950	.930	7.966	.941
8.212	.833	8.700	.627				




FIGURE 1SE-18A
LUCALOX ALUMINA
T=813 K
TOULOUKIAN. THERMOPHYS. PROPERTIES
REF. 1SE-18




FIGURE 1SE-18B
TWA-2 ALUMINA
T=1323 K
TOULOUKIAN. THERMOPHYS. PROPERTIES
REF. 1SE-18

Touloukian (Ref. 1SE-18)

d. Coors AD-99 alumina, 99 percent pure Al_2O_3, machined ultrasonically with a diamond wheel finish was studied using unspecified techniques. A precision of ± 4 percent is claimed. The temperature is 873°K. These data are in good agreement with the representative curve given in Section I-1.3, and were digitized from discrete points.

λ	ε	λ	ε	λ	ε	λ	ε
1.986	.370	2.981	.451	3.980	.481	4.496	.542
2.946	.881	5.464	.342	5.940	.963	6.825	.583
2.309	.980	5.224	.390	8.461	.650	8.664	.541
6.987	.599						

e. Coors AD-995 alumina, 99.5 percent pure Al_2O_3, machined surface was studied using unspecified techniques. A precision of ± 5 percent is claimed. The temperature is 814°K. These data show ε(λ) much lower at 3μ than the representative curve given in Section I, Figure I-1.3, and were digitized from discrete points.

λ	ε	λ	ε	λ	ε	λ	ε
1.002	.543	1.981	.271	3.005	.201	3.984	.310
4.201	.691						




FIGURE 1SE-18C
TWA-2 ALUMINA
T=873 K
TOULOUKIAN. THERMOPHYS. PROPERTIES
REF. 1SE-18






FIGURE 1SE-18D
COORS AD-99 ALUMINA
T=873 K
TOULOUKIAN. THERMOPHYS. PROPERTIES
REF. 1SE-18

Toulcukian (Ref. 1SE-18)

f. These are the remaining materials of Ref. 1SE-18, including Coors AD-99, Coors AD-96, Coors AD 96 + 1 $CoCO_3$, McDanel AP-30 (99 percent), McDanel AV30, vitrified alumina (96 percent), and McDanel AP-35 (isostatic)(99 percent). Precision is ±5 percent in general, and the temperature ranges from 800°K to 1600°K. These data were digitized from distinct points, and show good agreement with the representative curve for $\lambda < 3\,\mu$. For $\lambda > 3\,\mu$ there is a large variation within the data.

λ	ε	λ	ε	λ	ε	λ	ε
1.001	.599	1.001	.569	1.001	.536	1.001	.501
1.001	.478	1.001	.439	1.001	.412	1.001	.310
1.001	.221	1.001	.122	1.173	.300	1.299	.199
1.449	.162	1.806	.151	1.896	.130	1.986	.123
1.9[illegible]	.475	1.986	.418	1.986	.358	1.986	.288
1.98[illegible]	.250	1.986	.230	1.986	.129	1.986	.086
2.97[illegible]	.399	2.979	.440	2.979	.399	2.979	.330
2.97[illegible]	.267	2.979	.211	2.979	.142	2.979	.130
2.97[illegible]	.[illegible]	3.391	.153	3.970	.519	3.970	.499
3.97[illegible]	.463	3.970	.452	3.970	.420	3.970	.331
3.97[illegible]	.259	4.094	.209	4.228	.401	4.493	.799
4.44[illegible]	.[illegible]91	4.493	.779	4.493	.670	4.493	.626
4.49[illegible]	.598	4.493	.547	4.881	.802	4.958	.630
5.15[illegible]	.980	5.436	.980	5.436	.951	5.919	.877
5.30[illegible]	.394	5.919	.959	7.615	.962	7.821	.872
7.6[illegible]	.393	8.156	.929	8.196	.981	8.204	.837
8.24[illegible]	.863	8.357	.699	8.408	.829	8.459	.720
8.47[illegible]	.573	8.529	.531	8.569	.679	8.300	.500
8.89[illegible]	.799	8.894	.719	8.894	.647	8.894	.617
8.89[illegible]	.419	8.959	.459	9.09[illegible]	.437		


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-18E
COORS AD-995 ALUMINA
T=814 K
TOULOU' IAN. THERMOPHYS. PROPERTIES
REF. 1SE-18
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.5
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


SPECTRAL EMISSIVITY OF ALUMINUM OXIDE
FIGURE 1SE-18F
MISCELLANEOUS ALUMINAS
T=800 K TO 1600 K
TOULOUKIAN, THERMOPHYS. PROPERTIES
REF. 1SE-18
SPECTRAL EMISSIVITY
WAVELENGTH(MICRONS)
0.
.1
.2
.3
.4
.6
.7
.8
.9
1.
2.5
5.
7.5
10.
12.5
15.
20.
22.5
25.

Section III-1.4 Tabulated Total Emissivity Data - Aluminum Oxide

Contents:

ITE-1: Gannon; Norton Co. E111 alumina for T = 958°K to 1158°K; study of porosity and surface roughness effects.

ITE-2: Mergerian; Sapphire, T = 373°K to 1273°K.

ITE-3: Morizumi; rocket exhaust particles, T = 1389°K to 2222°K.

ITE-4: Olson; Norton RA-4213 and LA-603 Aluminas, T = 63°K tc 1800°K.

ITE-5: Touloukian; various aluminas, T = 63°K to 1800°K.

ITE-6: Wittenberg; sapphire, T = 200°K to 373°K.

Gannon (Ref. ITE-1)

The emittance of Norton Co. E111 alumina as a function of porosity and roughness was studied using a thermistor bolometer and a blackbody furnace. Samples were prepared by cold-pressing and sintering at 1973°K. Measurements were made between 958°K and 1158°K. No error analysis was given. Data were taken from a table.

The values measured for $\epsilon(T)$ are considerably lower than the representative curve given in Section I - 1.4.

Porosity (percent)	ϵ_n ($958^\circ K \leq T \leq 1158^\circ K$)
9.7	0.34
14.0	0.37
19.0	0.34
23.0	0.35
30.0	0.35

Surface Roughness	(Center Line Average)
< 20 μ inch	0.35
> 20 μ inch	0.36

Mergerian (Ref. 1TE-2)

Measurements of the total integrated (1 μ to 13 μ) emissivity of synthetic sapphire from T = 373°K to 1273°K were made using a Perkin-Elmer Model 99, NaCl monochromator and a blackbody furnace. No estimates of precision are given. These data are approximately 0.1 higher than Wittenberg's (Ref. 1TE-6) at 373°K, where they overlap. No representative curve was constructed for sapphire, and all measured total emissivities for sapphire are lower than the representative curve for alumina given in Section I - 1.4.

T	ε	T	ε	T	ε	T	ε
358.420	.460	643.358	.489	1012.585	.545	1269.627	.577

Morizumi (Ref TE-3)

The emissivity of rocket engine exhaust particles ranging from 0.79 μ to 3.95 μ in diameter was measured using narrow angle radiometers, black surfaced asymptotic calorimeters, and scanning spectrometers. It is concluded that ε(T) for small alumina particles is comparable to bulk alumina instead of sapphire. No error analysis was given. Data are digitized from distinct points. Sample temperature ranged from T = 1389°K to 2222°K. These data show emissivities slightly lower than the representative alumina curve given in Section I - 1.4.

a. Small rocket, expansion ratio 19:1 and exhaust diameter 12 in., measured by radiometer.

T	ε	T	ε	T	ε	T	ε
1984.312	.175	1985.397	.155	2058.609	.116	2152.558	.195
2152.558	.245						

b. Large rocket, expansion ratio 23.5:1 and exit diameter 26 in., measured by radiometer.

T	ε	T	ε	T	ε	T	ε
1677.041	.222	1677.041	.193	1762.335	.244	1884.234	.251
1937.430	.251						

c. Same rocket as b., measured by spectrometer.

T	ε
1881.238	.295

Olson (Ref. 1TE-4)

ε(T) was measured for Norton RA-4213 alumina and LA-603 alumina in air. Experimental details were not given. These data were digitized from curves.

These points were selected together with data from Ref. 1TE-5, to construct the representative curve given in Section I, Figure I - 1.4.

a. Norton RA-4213

T	ε	T	ε	T	ε	T	ε
224.685	.703	63.709	.770	81.217	.764	174.917	.749
397.213	.617	255.051	.790	318.678	.651	369.490	.665
547.561	.565	435.448	.671	523.554	.538	529.417	.558
764.531	.510	597.329	.583	743.734	.482	751.046	.523
1373.437	.395	775.742	.488	800.114	.408	1049.006	.407
1656.130	.313	1376.423	.335	1496.028	.381	1519.252	.290
		1714.156	.331	1781.353	.325		

b. Norton LA-603

T	ε	T	ε	T	ε	T	ε
390.336	.705	168.109	.773	203.287	.773	328.775	.741
524.368	.699	406.622	.700	432.353	.698	520.297	.658
699.365	.622	563.058	.624	563.058	.609	610.989	.625
1068.364	.516	761.444	.568	779.992	.635	783.541	.567
1470.481	.441	1304.783	.506	1312.716	.519	1364.147	.536
		1472.472	.459	1678.314	.426		

Touloukian (Ref. 1TE-5)

Various aluminas were studied, including Norton 603 and RA-4213. Measurements were made in air, argon, and vacuum. No error analysis was given. These data were digitized from specific points, and were selected together with data from Ref. 1T-4, to construct the representative curve given in Section I, Figure I - 1.4.

T	ε	T	ε	T	ε	T	ε
53.488	.725	67.001	.700	327.044	.779	359.245	.769
419.676	.768	427.646	.753	467.746	.763	496.638	.704
531.258	.783	598.007	.659	606.053	.741	645.145	.665
657.755	.712	662.547	.616	687.011	.700	693.317	.678
705.179	.670	767.213	.650	784.368	.536	787.390	.631
789.155	.695	791.173	.667	805.473	.649	831.095	.547
861.692	.616	864.677	.600	869.154	.573	885.323	.615
923.632	.614	946.259	.360	946.259	.349	950.498	.338
962.189	.630	968.159	.287	999.502	.482	1006.323	.531
1019.322	.565	1025.345	.510	1039.147	.569	1040.402	.386
1040.652	.482	1060.226	.635	1064.994	.570	1069.762	.408
1095.358	.253	1137.767	.510	1144.793	.356	1144.793	.349
1148.306	.338	1163.112	.467	1169.887	.248	1204.569	.525
1220.558	.420	1223.934	.249	1243.401	.483	1264.467	.337
1328.426	.509	1334.340	.519	1363.452	.545	1360.406	.445
1366.497	.263	1384.264	.393	1385.279	.329	1472.976	.941
1480.946	.449	1487.920	.462	1493.649	.376	1499.875	.277
1524.533	.285	1569.614	.277	1657.649	.433	1660.936	.307
1677.623	.283	1722.630	.330	1743.869	.450	1784.071	.322

Wittenberg (Ref. 1TE-6)

A calorimetric measurement was made of $\epsilon(T)$ for polished sapphire with the C-axis perpendicular and parallel to the surface normal. An error analysis indicates a relative accuracy of ±1.5 percent and an absolute accuracy of ±3.0 percent. These data were digitized from points. At 373°K, where these data overlap measurements made by Mergerian (Ref. 1TE-2), they show $\epsilon(T)$ being approximately 0.1 lower than Mergerian's. No representative curve for sapphire was constructed. All measured values for $\epsilon(T)$ of sapphire are lower than the representative curve for alumina given in Section I - 1.4.

a. C axis parallel to the sample surface

T	ε	T	ε	T	ε	T	ε
204.631	.496	205.346	.503	216.123	.503	226.484	.500
244.489	.504	254.248	.518	270.658	.523	295.645	.536
313.744	.543	325.967	.549	337.091	.555	354.801	.562
371.250	.565	373.969	.568				

b. C axis perpendicular to the sample surface

T	ε	T	ε	T	ε	T	ε
210.055	.474	212.551	.471	235.141	.479	240.452	.487
256.507	.496	269.393	.504	296.892	.524	320.456	.533
322.484	.534	322.822	.531	338.236	.541	370.893	.552
371.395	.550						

III-1.5 Tabulated Reflectivity Data - Aluminum Oxide

Contents:

1R-1: Aronson; corundum powders and spheres ranging in size from 0.3μ to 135μ diameter; the effects of surface abrasion on randomly oriented sapphire.

1R-3: Aronson; sapphire at long wavelengths, T = 10°K, 300°K.

1R-4: Barker; sapphire and ruby for ordinary and extraordinary ray orientations; the effect of surface etching and abrasion on the appearance of bands due to forbidden phonon modes.

1R-6: Clark; fine grained 99 + percent pure alumina.

1R-7: Gervais; sapphire heated to 960°K to 2070°K by a furnace and a 944 cm^{-1} laser.

1R-8: Harris; 50, 100, 200 volt Al_2O_3 films, T = 300°K.

1R-10: Levy; pelletized spinel alumina powder, T = 300°K.

1R-11: McCarthy; sapphire, 2 mm thick, T = 300°K.

1R-12: McCarthy; sapphire, 3 mm thick, T = 300°K.

1R-15: Piriou; sapphire, T = 293°K, 1773°K.

1R-17: Salama; RF sputtered Al_2O_3 film, T = 300°K.

1R-18: Tipunin; pure corundum, T = 300°K.


Preceding page blank


Aronson (Ref. 1R-1)

i) The reflectivity of corundum powders of irregular shape has been measured using a Michaelson interferometer. Powder size ranges from 0.3μ to 120μ in average diameter. No spectral bandpass or error analysis is given. The temperature is approximately 300°K. Data were digitized from lines. These data were used to construct the representative curve given in Section I, Figure I-1.5.3.

a. Particle size = 120μ diameter. Supplied by Norton Co.

λ	R	λ	R	λ	R
7.198	8.864E+00	7.354	8.074E+00	7.589	3.244E+00
7.835	1.777E+00	8.039	4.752E-01	8.216	8.264E-02
8.565	4.132E-02	8.827	2.273E-01	9.277	4.752E-01
9.612	2.479E-01	9.916	2.066E-02	10.137	5.992E-01
10.306	1.467E+00	10.462	4.504E+00	10.688	1.105E+01
10.858	1.615E+01	11.034	2.273E+01	11.216	2.925E+01
11.339	3.425E+01	11.456	3.880E+01	11.527	4.056E+01
11.627	4.139E+01	11.733	4.281E+01	11.861	4.315E+01
12.038	4.281E+01	12.217	4.232E+01	12.343	4.206E+01
12.573	4.228E+01	12.923	4.251E+01	13.314	4.383E+01
13.531	4.539E+01	14.090	4.719E+01	14.476	4.932E+01
14.898	5.182E+01	15.206	5.337E+01	15.322	5.409E+01
15.493	5.383E+01	15.570	5.299E+01	15.555	4.735E+01
15.734	4.246E+01	15.829	3.697E+01	15.876	3.546E+01
15.993	3.672E+01	16.101	4.371E+01	16.211	4.826E+01
16.209	5.200E+01	16.348	5.341E+01	16.458	5.431E+01
16.589	5.555E+01	16.760	5.463E+01	16.876	5.389E+01
17.013	5.194E+01	17.100	4.970E+01	17.192	4.695E+01
17.309	4.224E+01	17.419	3.554E+01	17.573	2.919E+01
17.848	2.452E+01	18.105	2.016E+01	18.377	1.528E+01
18.799	1.198E+01	19.188	9.628E+00	19.352	9.194E+00
19.531	1.006E+01	19.582	1.471E+01	19.667	1.851E+01
19.759	2.022E+01	19.940	2.138E+01	20.154	2.084E+01
20.347	1.635E+01	20.521	1.700E+01	20.741	1.637E+01
20.911	2.009E+01	20.982	2.731E+01	21.148	3.566E+01
21.150	4.135E+01	21.355	4.657E+01	21.544	5.074E+01
21.742	5.312E+01	21.938	5.407E+01	22.193	5.461E+01
22.437	5.422E+01	22.606	5.226E+01	22.714	4.733E+01
23.393	4.020E+01	23.664	3.318E+01	24.424	2.650E+01
25.000	2.124E+01	25.029	1.888E+01	25.756	2.014E+01
25.952	2.116E+01	26.319	2.084E+01	26.855	1.814E+01
27.248	1.655E+01	27.997	1.461E+01	28.415	1.372E+01
29.309	1.314E+01				



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1A
120 MICRON CORUNDUM POWDER
T=300 K
ARONSON. APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1A
120 MICRON CORUNDUM POWDER
T=300 K
ARONSON. APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (Ref. 1R-1)

b. Particle size = 50μ diameter. LWA powder from Microabrasives Corp.

λ	R
7.150	1.469E+01
7.542	6.548E+00
8.175	2.934E+00
8.995	1.033E-01
9.838	4.132E-02
10.353	2.252E+00
10.785	1.426E+01
11.237	3.129E+01
11.533	3.888E+01
11.939	3.835E+01
12.324	3.715E+01
13.351	4.124E+01
14.785	4.790E+01
15.388	5.674E+01
15.758	4.148E+01
16.190	3.695E+01
16.208	4.832E+01
16.942	5.297E+01
16.978	4.894E+01
17.337	3.947E+01
17.921	2.545E+01
18.289	1.467E+01
19.499	5.816E+00
19.808	1.421E+01
20.139	1.738E+01
20.754	1.223E+01
20.933	2.908E+01
21.394	4.639E+01
22.138	3.279E+01
23.344	4.118E+01
24.181	2.576E+01
25.372	1.632E+01
26.533	1.478E+01
27.521	1.143E+01
7.314	1.145E+01
7.772	5.496E+00
8.428	1.715E+00
8.906	6.198E-02
9.929	2.686E-01
10.463	4.483E+00
10.948	1.992E+01
11.403	3.401E+01
11.761	3.939E+01
12.214	3.727E+01
13.273	3.843E+01
14.239	4.369E+01
14.976	5.806E+01
15.543	4.952E+01
15.829	3.550E+01
16.037	4.628E+01
16.292	5.054E+01
16.743	5.214E+01
17.109	4.561E+01
17.422	3.228E+01
17.922	2.016E+01
18.749	9.773E+00
19.601	7.707E+00
19.880	1.588E+01
20.356	1.585E+01
20.789	1.436E+01
21.075	3.754E+01
21.582	5.022E+01
22.478	5.226E+01
23.435	3.481E+01
24.340	2.413E+01
25.736	1.506E+01
26.782	1.314E+01
28.448	1.093E+01
7.453	9.112E+00
8.314	3.864E+00
8.921	1.198E+00
9.164	3.719E-01
10.138	7.025E-01
10.546	9.587E+00
11.094	2.501E+01
11.523	3.725E+01
11.827	3.884E+01
12.673	3.705E+01
13.548	4.838E+01
14.535	4.655E+01
15.222	5.096E+01
15.372	4.533E+01
15.902	3.308E+01
16.114	4.423E+01
16.472	5.202E+01
16.897	5.058E+01
17.222	4.208E+01
17.486	3.051E+01
18.056	1.808E+01
19.092	7.686E+00
19.714	1.221E+01
20.024	1.800E+01
20.538	1.285E+01
21.929	2.014E+01
21.178	4.232E+01
21.804	5.208E+01
22.714	4.681E+01
23.896	2.364E+01
24.894	1.957E+01
26.263	1.665E+01
27.868	1.209E+01



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-18
60 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-18
60 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)

Aronson (Ref. 1R-1)

c. Particle size = 30 μm diameter. LWA powder from Microabrasives Corp.

λ	R	λ	R	λ	R
7.221	2.377E+01	7.332	2.071E+01	7.448	1.802E+01
7.350	1.521E+01	7.679	1.231E+01	7.817	1.074E+01
7.983	8.7[illegible]E+00	8.187	6.798E+00	8.392	4.690E+00
8.279	3.617E+00	8.731	1.694E+00	8.916	3.512E-01
9.134	5.959E-01	9.349	4.132E-01	9.584	1.033E-01
9.997	2.165E-01	10.243	1.136E+00	10.423	3.719E+00
10.545	6.632E+00	10.713	1.182E+01	10.829	1.539E+01
11.078	1.804E+01	11.133	2.165E+01	11.310	2.527E+01
11.421	2.711E+01	11.485	2.780E+01	11.570	2.754E+01
11.791	2.709E+01	11.892	2.652E+01	11.999	2.564E+01
12.222	2.609E+01	12.370	2.452E+01	12.547	2.454E+01
12.762	2.477E+01	12.895	2.511E+01	13.069	2.546E+01
13.201	2.662E+01	13.498	2.733E+01	13.696	2.892E+01
13.835	2.955E+01	14.[illegible]00	3.084E+01	14.300	3.143E+01
14.499	3.240E+01	14.371	3.299E+01	14.703	3.428E+01
14.891	3.635E+01	15.066	3.754E+01	15.192	3.821E+01
15.370	3.815E+01	15.527	3.792E+01	15.528	3.391E+01
15.650	3.218E+01	15.702	2.953E+01	15.724	2.749E+01
15.811	2.468E+01	15.896	2.219E+01	15.973	2.953E+01
16.191	3.365E+01	16.130	3.570E+01	16.229	3.764E+01
16.311	3.931E+01	16.469	4.044E+01	16.517	4.066E+01
16.734	4.63[illegible]E+01	16.911	3.921E+01	16.998	3.741E+01
17.150	3.54[illegible]E+01	17.115	3.324E+01	17.177	3.128E+01
17.291	2.7[illegible]5E+01	17.443	2.297E+01	17.620	1.[illegible]41E+01
17.851	1.459E+01	18.198	1.110E+01	18.591	8.719E+00
18.978	7.583E+00	19.394	6.860E+00	19.501	5.[illegible]17E+00
19.571	1.149E+01	19.800	1.370E+01	19.892	1.411E+01
20.[illegible]75	1.3[illegible]9E+01	20.256	1.256E+01	20.406	1.143E+01
20.[illegible]54	1.[illegible]2[illegible]E+01	20.546	9.5[illegible]4E+00	20.581	1.[illegible]64E+01
20.729	1.271E+01	20.911	1.920E+01	20.951	2.261E+01
21.079	2.589E+01	21.228	3.035E+01	21.433	3.460E+01
21.498	3.658E+01	21.766	3.837E+01	22.001	3.919E+01
22.307	3.906E+01	22.407	3.743E+01	22.526	3.275E+01
22.588	3.[illegible]90E+01	22.902	2.766E+01	23.008	2.599E+01
23.298	2.3[illegible]7E+01	23.430	2.169E+01	23.765	1.957E+01
24.[illegible]09	1.735E+01	24.412	1.508E+01	24.596	1.273E+01
25.140	1.[illegible]3[illegible]E+01	25.583	1.037E+01	25.891	1.145E+01
26.2[illegible]7	1.138E+01	26.[illegible]03	1.05[illegible]E+01	26.373	9.112E+00
27.[illegible]96	8.57[illegible]E+00	27.248	9.38[illegible]E+00	27.675	1.031E+01
28.339	1.159E+01	28.721	1.287E+01		



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1C
30 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1C
30 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (Ref. 1R-1)

d. Particle size = 10μ diameter. LWA powder from Microabrasives Corp.

λ	R	λ	R	λ	R
7.250	2.915E+01	7.414	2.515E+01	7.505	1.971E+01
7.833	1.579E+01	7.961	1.355E+01	8.090	1.147E+01
8.203	8.502E+00	8.347	6.488E+00	8.550	3.882E+00
8.738	2.604E+00	8.985	3.306E-01	9.174	3.306E-01
9.539	2.606E-02	9.752	3.306E-01	10.066	4.752E-01
10.284	1.322E+00	10.435	2.707E+00	10.591	3.884E+00
10.781	5.744E+00	11.117	8.700E+00	11.284	1.002E+01
11.416	9.733E+00	11.550	9.442E+00	11.792	8.326E+00
12.031	7.624E+00	12.327	7.335E+00	12.593	7.107E+00
12.917	7.417E+00	13.218	7.831E+00	13.540	8.574E+00
13.856	9.235E+00	14.227	1.014E+01	14.566	1.118E+01
14.935	1.219E+01	15.266	1.300E+01	15.479	1.289E+01
15.921	1.223E+01	15.826	1.054E+01	15.919	9.773E+00
16.055	1.175E+01	16.169	1.217E+01	16.247	1.281E+01
16.399	1.370E+01	16.483	1.417E+01	16.672	1.399E+01
16.862	1.395E+01	17.045	1.379E+01	17.246	1.207E+01
17.379	1.152E+01	17.558	9.481E+00	17.791	7.335E+00
18.033	8.715E+00	18.296	7.025E+00	18.515	7.831E+00
18.809	7.562E+00	19.188	7.107E+00	19.303	8.202E+00
19.879	8.099E+00	19.848	7.748E+00	20.024	6.983E+00
20.422	5.227E+00	20.617	4.339E+00	20.872	4.050E+00
21.125	4.876E+00	21.196	7.665E+00	21.591	9.731E+00
22.021	1.147E+01	22.302	1.246E+01	22.595	1.215E+01
23.136	9.711E+00	23.652	7.810E+00	24.294	6.467E+00
24.788	5.683E+00	25.550	3.988E+00	26.117	4.265E+00
26.888	5.896E+00	27.376	6.816E+00	28.204	7.748E+00
29.209	6.678E+00				



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1D
10 MICRON CORUNDUM POWDER
T=300 K
ARONSON. APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0
10
20
30
40
50
60
70
80
90
100



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1D
10 MICRON CORUNDUM POWDER
T=300 K
ARONSON. APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
40.
45.
50.
0
10
20
30
40
50
60
70
80
90
100

Aronson (Ref. 1R-1)

e. Particle size = 3.5μ diameter. LWA powder from Microabrasives Corp.

λ	R	λ	R	λ	R
7.226	2.692E+01	7.325	2.422E+01	7.443	2.143E+01
7.519	1.909E+01	7.624	1.657E+01	7.728	1.475E+01
7.838	1.329E+01	7.965	1.122E+01	8.094	8.536E+00
8.188	6.886E+00	8.317	4.752E+00	8.477	2.169E+00
8.585	1.198E+00	8.723	4.959E-01	8.842	1.653E-01
9.064	2.686E-01	9.434	2.686E-01	9.537	4.132E-02
9.923	2.893E-01	10.067	5.165E-01	10.266	1.260E+00
10.368	1.612E+00	10.528	1.850E+00	10.712	2.293E+00
10.835	3.144E+00	11.114	3.884E+00	11.283	4.421E+00
11.430	3.967E+00	11.693	3.704E+00	12.025	3.616E+00
12.350	3.305E+00	12.546	3.306E+00	12.930	3.533E+00
13.413	3.698E+00	13.915	4.132E+00	14.509	5.021E+00
15.004	5.644E+00	15.231	5.826E+00	15.534	5.517E+00
15.755	4.897E+00	15.973	4.938E+00	16.255	6.384E+00
16.473	6.818E+00	16.808	7.273E+00	17.059	7.190E+00
17.442	6.488E+00	17.651	5.682E+00	17.810	5.517E+00
18.013	6.302E+00	18.323	7.211E+00	18.598	7.521E+00
18.957	7.252E+00	19.292	7.128E+00	19.409	6.343E+00
19.551	5.289E+00	19.828	3.202E+00	20.093	2.107E+00
20.340	1.246E+00	20.759	1.219E+00	21.106	2.107E+00
21.383	3.140E+00	21.794	4.339E+00	22.138	4.979E+00
22.437	5.640E+00	22.839	5.764E+00	23.386	5.517E+00
23.769	5.310E+00	24.388	4.669E+00	24.788	4.050E+00
25.249	3.017E+00	25.622	2.231E+00	25.959	2.459E+00
26.275	4.008E+00	26.559	5.620E+00	26.965	6.302E+00
27.475	7.169E+00	28.100	7.273E+00	28.563	7.231E+00
29.414	6.488E+00	30.437	5.289E+00		



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1E
3.5 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1E
3.5 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (Ref. 1R-1)

f Particle size = 0.3μ diameter. Supplied by Adolf Meller Co.

λ	R	λ	R	λ	R
7.237	5.372E-01	7.350	4.545E-01	7.436	4.545E-01
7.570	4.132E-02	7.824	6.198E-02	8.194	6.198E-02
8.557	8.264E-02	8.759	8.254E-02	8.996	8.264E-02
9.232	1.653E-01	9.419	3.926E-01	9.676	8.678E-01
9.973	1.446E+00	10.225	2.231E+00	10.320	2.583E+00
10.538	2.521E+00	10.971	2.748E+00	11.326	3.058E+00
11.559	3.533E+00	12.118	3.223E+00	12.433	3.202E+00
12.719	2.672E+00	13.026	2.438E+00	13.355	2.624E+00
13.702	2.397E+00	14.074	2.314E+00	14.436	2.524E+00
14.372	2.624E+00	15.370	2.769E+00	15.794	2.707E+00
16.234	3.140E+00	16.664	3.926E+00	17.086	4.360E+00
17.321	4.388E+00	17.582	4.215E+00	17.794	3.843E+00
18.245	2.087E+00	18.494	1.694E+00	18.770	1.550E+00
18.933	1.157E+00	19.229	5.579E-01	19.570	8.264E-02
19.908	3.514E-01	20.248	3.512E-01	20.583	5.785E-01
20.955	1.198E+00	21.415	1.446E+00	22.001	2.789E+00
22.392	3.223E+00	22.743	3.285E+00	23.174	3.244E+00
23.575	3.137E+00	24.222	2.727E+00	24.629	2.293E+00
25.051	1.523E+00	25.523	7.438E-01	25.932	3.926E-01
27.138	2.273E-01	28.530	1.653E-01		


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1F
0.3 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1F
0.3 MICRON CORUNDUM POWDER
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


Aronson (Ref. 1R-1)

ii) The reflectivity of corundum beads of 35μ and 130μ diameter has been measured using a Michaelson interferometer. The beads have been melted to a spherical shape and annealed until the composition was entirely α - Al_2O_3. No spectral bandpass or error analysis is given. The temperature is approximately 300°K. Data were digitized from lines.

g. Bead diameter = 130μ.

λ	R	λ	R	λ	R
7.137	6.4+6E+00	7.364	4.839E+00	.568	2.892E+00
7.727	1.988E+00	7.913	1.265E+00	8.899	3.213E-01
9.353	2.008E-02	9.615	4.418E-01	9.696	1.225E+00
10.379	1.627E+00	10.270	2.470E+00	10.387	4.116E+00
10.918	6.908E+00	10.699	1.211E+01	10.835	1.695E+01
11.353	2.2+0E+01	11.154	3.011E+01	11.281	3.515E+01
11.356	3.907E+01	11.471	4.270E+01	11.535	4.505E+01
11.044	4.726E+01	11.700	4.859E+01	11.845	4.902E+01
11.936	4.655E+01	12.083	4.771E+01	12.184	4.726E+01
12.230	4.693E+01	12.211	4.751E+01	12.581	4.847E+01
12.930	4.972E+01	13.139	5.153E+01	13.340	5.350E+01
13.313	5.487E+01	13.691	5.573E+01	13.863	5.626E+01
14.088	5.695E+01	14.327	5.751E+01	14.529	5.859E+01
14.755	5.831E+01	15.021	6.124E+01	15.216	6.157E+01
15.343	6.112E+01	15.466	6.026E+01	15.552	5.822E+01
15.030	4.736E+01	15.705	4.080E+01	15.741	3.917E+01
15.853	3.611E+01	15.915	3.871E+01	15.941	4.501E+01
16.033	4.847E+01	16.023	5.299E+01	16.143	5.630E+01
16.242	5.885E+01	16.364	6.110E+01	16.204	6.244E+01
16.575	6.332E+01	16.787	6.312E+01	16.921	6.226E+01
17.019	5.988E+01	17.090	5.626E+01	17.174	5.076E+01
17.325	4.317E+01	17.476	3.656E+01	17.581	3.172E+01
17.740	2.721E+01	17.342	2.373E+01	18.182	2.012E+01
18.448	1.827E+01	18.749	1.335E+01	19.089	1.060E+01
19.323	9.395E+00	19.444	9.799E+00	19.519	1.269E+01
19.629	1.688E+01	19.895	1.747E+01	20.080	1.614E+01
20.235	1.425E+01	20.491	1.345E+01	20.547	1.446E+01
20.741	2.143E+01	20.866	2.306E+01	20.964	3.768E+01
20.741	4.105E+01	20.919	4.871E+01	21.153	5.628E+01
21.438	6.124E+01	21.581	6.352E+01	21.854	6.450E+01
22.103	6.430E+01	22.386	6.092E+01	22.497	5.369E+01
22.804	4.489E+01	23.297	3.641E+01	23.314	2.924E+01
24.333	2.435E+01	25.116	2.097E+01	25.345	1.876E+01
25.030	1.707E+01	25.855	1.845E+01	25.849	2.159E+01
26.933	2.209E+01	26.164	2.113E+01	26.454	1.855E+01
26.852	1.661E+01	27.590	1.560E+01	28.461	1.436E+01
29.268	1.343E+01	30.623	1.331E+01		



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1G
130 MICRON CORUNDUM BEADS
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1G
130 MICRON CORUNDUM BEADS
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (Ref. 1R-1)

h. Bead diameter = 35μ.

λ	R	λ	R	λ	R
7.134	1.343E+01	7.448	9.839E+00	7.698	7.651E+00
8.[illegible]	5.643E+[illegible]	8.286	4.473E+00	8.575	3.092E+00
8.938	1.747E+[illegible]	9.296	8.639E-01	9.549	4.217E-01
9.053	1.[illegible]E+[illegible]	9.576	1.627E+00	3.883	2.771E+00
9.381	3.[illegible]E+[illegible]	10.096	2.691E+00	10.212	2.309E+00
10.363	2.912E+[illegible]	10.444	9.352E+00	10.510	9.578E+00
10.723	1.257E+[illegible]	10.804	1.656E+01	10.909	1.837E+01
11.[illegible]	6.[illegible]E+[illegible]	11.441	3.380E+01	11.581	3.654E+01
11.[illegible]	3.776E+[illegible]	12.159	3.911E+01	12.409	3.978E+01
11.[illegible]	4.162E+[illegible]	13.[illegible]	4.196E+01	13.801	4.360E+01
12.[illegible]	4.[illegible]E+[illegible]	14.471	4.332E+01	14.977	4.886E+01
14.[illegible]	4.[illegible]E+[illegible]	15.257	4.916E+01	15.417	4.795E+01
[illegible]	4.932E+[illegible]	15.696	4.[illegible]E+01	15.774	3.388E+01
[illegible]	3.[illegible]E+[illegible]	15.933	3.[illegible]E+01	15.014	3.734E+01
[illegible]	3.[illegible]E+[illegible]	16.172	4.624E+01	16.293	4.838E+01
[illegible]	3.[illegible]E+[illegible]	16.[illegible]	5.106E+01	16.784	5.[illegible]84E+01
[illegible]	4.[illegible]E+[illegible]	17.[illegible]	4.759E+01	17.[illegible]	4.348E+01
[illegible]	4.[illegible]E+[illegible]	17.[illegible]	3.396E+01	17.464	3.168E+01
[illegible]	2.[illegible]E+[illegible]	17.722	2.348E+01	18.022	1.525E+01
[illegible]	2.638E+[illegible]	18.[illegible]	1.[illegible]E+01	18.[illegible]	9.[illegible]95E+00
[illegible]	1.[illegible]E+[illegible]	19.[illegible]	1.349E+01	19.783	1.484E+01
[illegible]	1.[illegible]E+[illegible]	20.[illegible]	1.[illegible]E+01	20.575	1.231E+01
[illegible]	1.[illegible]E+[illegible]	20.[illegible]	2.[illegible]E+01	20.501	2.306E+01
[illegible]	2.[illegible]E+[illegible]	20.923	3.355E+01	20.962	3.549E+01
[illegible]	2.[illegible]E+[illegible]	21.306	5.[illegible]E+01	21.759	5.[illegible]C2E+01
[illegible]	4.[illegible]E+[illegible]	22.[illegible]	3.869E+01	22.296	4.892E+01
[illegible]	2.[illegible]E+[illegible]	22.793	2.226E+01	23.168	3.[illegible]19E+01
[illegible]	1.[illegible]E+[illegible]	23.971	1.432E+01	24.256	2.[illegible]34E+01
[illegible]	1.[illegible]E+[illegible]	25.[illegible]	1.556E+01	25.784	1.568E+01
[illegible]	1.[illegible]E+[illegible]	26.164	1.[illegible]E+01	25.715	1.424E+01
[illegible]	1.[illegible]E+[illegible]	28.398	1.219E+01	29.864	1.203E+01


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1H
35 MICRON CORUNDUM BEADS
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1H
35 MICRON CORUNDUM BEADS
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (Ref. 1R-1)

iii) The changes in reflectivity of randomly oriented sapphire occuring from abrasion by 15μ diamond polishing compound shows the change in magnitude but not shape of the reflectance caused by surface asperities. No spectral bandpass or error analysis is given. The temperature is approximately 300°K. Data were digitized from lines.

i. Sapphire crystal, unabraded surface.


λ	R	λ	R	λ	R
7.200	1.381E+00	7.419	7.808E-01	7.556	5.405E-01
7.759	2.883E-01	7.943	1.852E-01	8.363	2.803E-01
8.746	8.068E-02	9.075	2.402E-01	9.481	6.006E-01
9.997	3.143E+00	10.111	4.855E+00	10.382	7.508E+00
10.338	1.097E+01	10.738	1.447E+01	10.850	1.778E+01
10.995	2.244E+01	11.033	2.646E+01	11.103	3.199E+01
11.153	3.038E+01	11.246	4.403E+01	11.330	5.095E+01
11.448	5.752E+01	11.506	6.294E+01	11.563	6.703E+01
11.679	7.139E+01	11.818	7.399E+01	11.985	7.661E+01
12.077	7.785E+01	12.271	7.872E+01	12.549	7.975E+01
12.799	8.113E+01	13.059	8.240E+01	13.339	8.398E+01
13.674	8.530E+01	13.903	8.618E+01	14.269	8.534E+01
14.587	8.291E+01	14.913	8.454E+01	15.215	8.177E+01
15.407	7.884E+01	15.655	7.522E+01	15.779	7.308E+01
15.891	7.251E+01	15.991	7.336E+01	16.039	7.327E+01
16.142	7.615E+01	16.242	7.649E+01	16.348	7.592E+01
16.497	7.460E+01	16.534	7.257E+01	16.544	7.092E+01
16.829	6.897E+01	17.044	6.652E+01	17.285	6.303E+01
17.609	5.968E+01	17.635	5.492E+01	17.848	4.954E+01
18.180	4.337E+01	18.258	3.821E+01	18.400	3.303E+01
18.531	2.874E+01	18.857	2.624E+01	19.068	2.388E+01
19.303	2.265E+01	19.422	2.336E+01	19.574	2.754E+01
19.870	3.179E+01	19.740	3.789E+01	19.810	4.194E+01
19.989	4.425E+01	20.084	4.518E+01	20.275	4.476E+01
20.[illegible]	4.373E+01	20.544	4.246E+01	20.545	4.212E+01
20.[illegible]	4.363E+01	20.773	4.041E+01	20.807	5.587E+01
20.[illegible]21	6.693E+01	20.890	6.600E+01	21.342	7.393E+01
21.334	7.927E+01	21.105	8.326E+01	21.220	8.313E+01
21.419	8.659E+01	21.562	8.634E+01	21.819	8.561E+01
21.907	8.361E+01	22.239	8.123E+01	22.615	7.767E+01
23.035	7.328E+01	23.481	6.854E+01	24.049	6.272E+01
24.526	5.715E+01	25.159	5.294E+01	25.586	4.938E+01
25.824	4.762E+01	26.153	4.917E+01	26.430	4.639E+01
26.831	4.325E+01	27.521	3.986E+01	27.972	3.807E+01
28.137	3.729E+01	28.579	3.730E+01	28.796	3.693E+01
29.073	3.492E+01	29.446	3.360E+01	30.053	3.179E+01
30.337	3.112E+01				



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-11
SAPPHIRE
T=300 K
ARONSON, APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-11
SAPPHIRE
T=300 K
ARONSON, APP. OPT. 12. 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Ar nson (Ref. 1R-1)

1. Sapphire crystal, surface abraded with 15μ diamond paste.

λ	R	λ	R	λ	R
9.703	1.341E+00	10.161	3.223E+00	18.468	5.425E+00
10.935	8.729E+00	10.782	1.189E+01	19.884	1.512E+01
10.959	1.912E+01	11.036	2.504E+01	11.079	2.776E+01
11.153	3.368E+01	11.217	3.781E+01	11.302	4.268E+01
11.339	4.554E+01	11.422	4.986E+01	11.472	5.234E+01
11.534	5.778E+01	11.697	5.958E+01	11.818	5.950E+01
11.922	5.899E+01	12.117	5.774E+01	12.285	5.655E+01
12.437	5.693E+01	12.657	5.736E+01	12.847	5.875E+01
13.161	6.104E+01	13.369	6.331E+01	13.553	6.534E+01
13.842	6.836E+01	14.181	7.147E+01	14.398	7.314E+01
14.741	7.583E+01	15.005	7.628E+01	15.189	7.541E+01
15.381	7.316E+01	15.540	7.078E+01	15.688	6.650E+01
15.756	6.532E+01	15.849	6.426E+01	15.944	6.530E+01
16.043	6.857E+01	15.997	7.088E+01	16.065	7.239E+01
16.158	7.314E+01	16.351	7.151E+01	16.565	6.989E+01
16.843	6.502E+01	16.972	6.298E+01	17.279	5.657E+01
17.548	5.114E+01	17.775	4.292E+01	18.041	3.616E+01
18.332	2.698E+01	18.849	2.179E+01	19.318	1.734E+01
19.411	1.924E+01	19.487	2.193E+01	19.509	2.986E+01
19.632	3.394E+01	19.787	3.606E+01	20.052	3.764E+01
20.278	3.473E+01	20.431	3.559E+01	20.549	3.461E+01
20.807	3.177E+01	20.734	4.146E+01	20.756	5.298E+01
20.847	6.300E+01	21.018	6.723E+01	21.207	7.245E+01
21.329	7.485E+01	21.594	7.872E+01	21.767	7.931E+01
21.977	7.872E+01	22.171	7.748E+01	22.458	7.488E+01
22.851	7.007E+01	23.427	6.351E+01	24.043	5.704E+01
24.681	5.214E+01	25.265	4.393E+01	25.663	4.145E+01
26.379	4.033E+01	26.824	3.953E+01	27.566	3.567E+01
27.926	3.376E+01	28.303	3.337E+01	28.532	3.476E+01
28.975	3.374E+01	29.189	3.114E+01	29.602	2.935E+01
30.159	2.809E+01				


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1J
SAPPHIRE (ABRADED)
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-1J
SAPPHIRE (ABRADED)
T=300 K
ARONSON, APP. OPT. 12, 2573 (1973)
REF. 1R-1
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Aronson (iR-3)

A Perkin-Elmer Model 201-C spectrophotometer was used to measure the far-infrared reflection spectrum of alumina (Z-cut sapphire). Experimental details and bandpass information were not given. The data were digitized from a curve.

The representative curve for sapphire reflectance was in part constructed from this curve and is given in Section I - 1.6.

a $T = 300^{\circ}K$; 0° orientation.

λ	R	λ	R	λ	R
243.+03	[illegible]	621.762	1.900E+01	346.821	1.967E+01
172.814	2.56[illegible]	195.759	2.307E+01	179.910	2.447E+01
140.331	3.[illegible]	170.213	2.646E+01	158.103	2.848E+01
116.[illegible]	[illegible]	143.369	3.111E+01	132.450	3.083E+01
101.811	3.[illegible]	109.583	3.173E+01	115.263	3.352E+01
87.15[illegible]	2.97[illegible]	95.525	3.262E+01	91.298	3.071E+01
74.[illegible]	[illegible]	79.819	3.367E+01	77.764	2.927E+01
[illegible]	2.03[illegible]	70.142	2.318E+01	68.473	2.172E+01
52.+81	2.363[illegible]	48.357	2.561E+01	44.411	2.790E+01
41.278	2.975[illegible]	39.392	2.966E+01	36.154	3.000E+01
33.78[illegible]	3.101[illegible]	31.786	3.340E+01	30.263	3.587E+01
28.8[illegible]	3.936E+01	27.959	4.308E+01	27.381	4.663E+01
26.[illegible]	5.[illegible]	26.604	5.210E+01	26.317	4.527E+01
25.[illegible]	4.[illegible]	25.706	4.294E+01	25.465	4.659E+01
24.[illegible]	5.[illegible]	24.105	5.434E+01	23.886	5.849E+01
23.[illegible]	6.[illegible]	23.686	7.210E+01	23.366	6.862E+01
23.161	7.218[illegible]	23.[illegible]42	6.856E+01	22.[illegible]72	7.409E+01
22.[illegible]	7.916[illegible]	22.599	8.316E+01	22.407	8.643E+01
22.[illegible]	9.[illegible]	22.101	9.243E+01	21.917	9.176E+01
21.[illegible]	9.[illegible]	21.432	8.897E+01	21.387	8.701E+01
21.226	8.521[illegible]	21.185	8.081E+01	21.174	7.650E+01
21.11[illegible]	7.213[illegible]	21.075	6.833E+01	21.049	6.413E+01
21.[illegible]	5.[illegible]	20.980	5.580E+01	20.947	5.149E+01
20.907	4.7[illegible]	20.864	3.934E+01	20.821	3.[illegible]99E+01
20.[illegible]	3.[illegible]	20.821	2.700E+01	20.821	2.272E+01
20.711	2.[illegible]	20.518	2.894E+01	20.308	3.295E+01
19.[illegible]	3.[illegible]	19.813	4.121E+01	19.730	4.395E+01
19.[illegible]	4.[illegible]	19.567	3.904E+01	19.413	3.621E+01
19.20[illegible]	3.896E+01	19.012	4.280E+01	18.813	4.666E+01
18.[illegible]	5.[illegible]	18.[illegible]54	5.361E+01	17.621	5.693E+01
17.[illegible]	6.[illegible]	17.134	6.255E+01	16.842	6.388E+01
16.[illegible]	5.292[illegible]	16.[illegible]58	6.119E+01	15.284	5.815E+01
16.[illegible]	5.[illegible]	15.968	5.432E+01	15.817	5.620E+01
15.[illegible]	6.[illegible]	15.[illegible]72	6.399E+01	15.318	6.777E+01
15.113	7.167[illegible]	14.908	7.560E+01	14.581	7.608E+01

Aronson (Ref. 1 R-3)

a. continued

λ	R	λ	R	λ	R
14.351	7.992E+01	13.971	7.530E+01	13.471	7.353E+01
12.941	7.042E+01	12.417	6.693E+01	11.954	6.369E+01
11.813	5.197E+01	11.682	5.798E+01	11.532	5.141E+01
11.378	4.495E+01	11.173	3.886E+01	11.022	3.196E+01
10.911	2.563E+01	10.810	1.856E+01	10.696	1.240E+01
10.287	7.832E+00	10.396	5.344E+00	10.151	3.389E+00
10.023	2.626E+00				

b. T =300°K; 90° orientation

λ	R	λ	R	λ	R
95.791	2.105E+01	91.172	1.966E+01	86.978	1.961E+01
84.063	2.197E+01	81.553	2.204E+01	78.430	1.908E+01
76.812	1.724E+01	75.504	1.475E+01	72.765	1.312E+01
68.736	1.197E+01	63.811	1.213E+01	59.805	1.559E+01
55.813	1.916E+01	53.342	2.075E+01	50.722	2.148E+01
47.833	2.305E+01	43.140	2.595E+01	39.920	2.778E+01
37.286	3.011E+01	35.081	3.241E+01	33.053	3.502E+01
31.305	3.755E+01	30.121	4.041E+01	29.184	4.440E+01
28.655	4.835E+01	28.042	5.233E+01	27.467	5.649E+01
26.957	6.018E+01	26.622	6.287E+01	26.425	6.067E+01
26.345	5.767E+01	26.097	5.997E+01	25.717	6.386E+01
25.181	6.731E+01	24.576	7.079E+01	23.959	7.469E+01
23.798	7.684E+01	23.621	8.102E+01	23.434	8.494E+01
23.338	8.901E+01	23.204	9.309E+01	22.857	9.453E+01
22.404	9.602E+01	22.108	9.620E+01	21.571	9.521E+01
21.298	9.411E+01	21.097	8.988E+01	20.871	8.567E+01
20.746	8.337E+01	20.385	8.144E+01	20.170	8.057E+01
20.023	7.874E+01	19.915	7.033E+01	19.851	6.248E+01
19.841	5.406E+01	19.797	4.571E+01	19.800	3.748E+01
19.774	2.933E+01	19.744	2.116E+01	19.730	1.307E+01
19.687	6.261E+00	19.448	8.813E+00	19.336	1.297E+01




FIGURE 1R-3A
SAPPHIRE, 0 DEG. ORIENTATION
T=300 K
ARONSON NASA SP-55
REF. 1R-3








FIGURE 1R-3B
SAPPHIRE, 90 DEG. ORIENTATION
T=300 K
ARONSON, NASA SP-55
REF. 1R-3


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-3A
SAPPHIRE. 0 DEG. ORIENTATION
T=300 K
ARONSON. NASA SP-55
REF. 1R-3
REFLECTIVITY
WAVELENGTH(MICRONS)
0. 50. 100. 150. 200. 250. 300. 350. 400. 450. 500.
0 10 20 30 40 50 60 70 80 90 100


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-3B
SAPPHIRE. 90 DEG. ORIENTATION
T=300 K
ARONSON. NASA SP-55
REF. 1R-3
REFLECTIVITY
WAVELENGTH(MICRONS)
0. 2.5 5. 7.5 10. 12.5 15. 17.5 20. 22.5 25.
0 10 20 30 40 50 60 70 80 90 100



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-3B
SAPPHIRE, 90 DEG. ORIENTATION
T=300 K
ARONSON, NASA SP-55
REF. 1R-3
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-3B
SAPPHIRE, 90 DEG. ORIENTATION
T=300 K
ARONSON, NASA SP-55
REF. 1R-3
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


Aronson (Ref. 1R-3)

c. $T \leq 10^{\circ}K$; 0° orientation.

λ	R	λ	R	λ	R
309.278	3.758E+01	213.144	3.976E+01	178.838	4.132E+01
152.866	4.302E+01	134.983	4.392E+01	119.522	4.575E+01
108.992	4.700E+01	100.418	4.636E+01	94.939	4.549E+01
90.363	4.490E+01	85.734	4.589E+01	83.705	4.624E+01
80.494	4.546E+01	78.305	4.351E+01	75.998	4.093E+01
74.349	3.859E+01	71.644	3.615E+01	68.209	3.478E+01
64.793	3.518E+01	60.273	3.650E+01	55.268	3.868E+01
50.613	3.998E+01	45.840	4.133E+01	42.345	4.341E+01
38.089	4.505E+01	35.904	4.647E+01	33.297	4.793E+01
31.216	4.938E+01	29.480	5.019E+01	28.290	5.062E+01
27.837	5.032E+01	27.480	4.930E+01	26.832	4.840E+01
26.483	5.062E+01	26.272	5.879E+01	26.041	5.262E+01
25.914	4.082E+01	25.772	3.181E+01	25.534	3.979E+01
25.449	4.660E+01	25.375	4.788E+01	24.979	4.998E+01
24.849	5.045E+01	24.323	5.032E+01	24.029	5.124E+01
23.868	5.391E+01	23.779	5.924E+01	23.644	6.047E+01
23.389	6.382E+01	23.125	6.722E+01	22.942	7.209E+01
22.812	7.920E+01	22.739	8.141E+01	22.465	8.423E+01
22.296	8.824E+01	22.129	9.224E+01	22.012	9.364E+01
21.767	9.462E+01	21.508	9.382E+01	21.271	9.214E+01
21.078	8.607E+01	20.936	6.630E+01	20.810	4.677E+01
20.732	3.006E+01	20.690	8.611E+00	20.605	1.790E+01
20.454	2.525E+01	20.170	3.011E+01	19.926	3.472E+01
19.773	3.341E+01	19.750	4.098E+01	19.697	5.064E+01
19.567	4.908E+01	19.461	4.558E+01	19.293	4.484E+01
19.101	4.550E+01	18.975	4.751E+01	18.887	4.904E+01
18.793	5.016E+01	18.501	5.188E+01	18.321	5.364E+01
18.229	5.498E+01	18.172	5.803E+01	18.136	6.287E+01
18.056	6.590E+01	17.854	6.787E+01	17.574	7.037E+01
17.398	7.180E+01	17.068	7.286E+01	16.926	7.353E+01
16.728	7.357E+01	16.585	7.709E+01	16.470	7.746E+01
16.331	7.685E+01	16.208	7.551E+01	16.136	7.252E+01
16.079	6.665E+01	16.020	6.115E+01	15.942	5.876E+01
15.887	6.161E+01	15.846	6.596E+01	15.798	7.063E+01
15.750	7.345E+01	15.611	7.653E+01	15.444	7.884E+01
15.278	8.160E+01	15.132	8.408E+01		


REFLECTIVITY OF ALUMINUM OXIDE
80
70
60
50
30
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)
FIGURE 1R-3C
SAPPHIRE. 0 DEG. ORIENTATION
ARONSON. NASA SP-55
REF. 1R-3


REFLECTIVITY OF ALUMINUM OXIDE
100
90
80
70
60
50
40
30
20
10
0
REFLECTIVITY
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
WAVELENGTH(MICRONS)
FIGURE 1R-3C
SAPPHIRE. 0 DEG. ORIENTATION
T=10 K
ARONSON. NASA SP-55
REF. 1R-3


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-3C
SAPPHIRE, 0 DEG. ORIENTATION
T=10 K
ARONSON, NASA SP-55
REF. 1R-3
REFLECTIVITY
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


Barker (Ref. 1R-4)


The reflectivity of sapphire and ruby were studied from 1 - 35μ using a prism spectrometer. It was determined that the presence of chromium in the ruby was indetectable in the infrared to 2.4×10^{20} ions/cm^3, but that crystal orientation was extremely important. Reflectivities for the ordinary ray (E ⊥ C axis) and the extraordinary ray (E ∥ C axis) are included, and the effect on forbidden phonon modes of etching several microns of surface from the crystal using molten boron oxide and lead oxide was studied. No error analysis or bandpass was given. The temperature is unspecified (room temperature). Data were digitized from points.

These data were selected in part to construct the representative curve for sapphire in Section I, Figure I - 1.6.

a. Ordinary ray reflectivity, Linde flame fusion white sapphire.

λ	R	λ	R	λ	R	λ	R
3.[illegible]	[illegible]	[illegible]	[illegible]	1.524	7.773E+00	2.487	7.627E+00
[illegible]	[illegible]	[illegible]	[illegible]	5.5000	5.548E+00	6.501	4.148E+00
[illegible]	[illegible]	[illegible]	[illegible]	9.0999	1.531E-01	9.511	3.785E-01
10.[illegible]	[illegible]	[illegible]	[illegible]	10.558	1.138E+00	10.640	7.482E+00
10.[illegible]	1.[illegible]	10.[illegible]	3.[illegible]	11.007	4.013E+01	11.057	5.034E+01
11.122	[illegible]	11.[illegible]	9.[illegible]	11.327	5.114E+01	11.345	6.503E+01
11.[illegible]	[illegible]	11.[illegible]	[illegible]	11.638	8.014E+01	11.973	8.511E+01
12.[illegible]	[illegible]	12.[illegible]	[illegible]	12.434	8.717E+01	12.681	8.911E+01
12.[illegible]	[illegible]	[illegible]	[illegible]	13.[illegible]	9.30[illegible]E+01	13.972	9.365E+01
[illegible]	[illegible]	[illegible]	[illegible]	14.[illegible]	9.[illegible]E+01	15.623	8.010E+01
15.[illegible]	[illegible]	15.[illegible]	[illegible]	15.979	6.512E+01	15.982	7.511E+01
16.[illegible]	[illegible]	16.121	[illegible]	16.133	8.717E+01	16.331	8.859E+01
16.[illegible]	[illegible]	16.[illegible]	[illegible]	17.249	8.315E+01	17.513	8.009E+01
18.[illegible]	[illegible]	19.[illegible]	[illegible]	19.[illegible]	5.[illegible]13E+01	18.257	5.026E+01
20.[illegible]	[illegible]	20.689	[illegible]	19.942	2.016E+01	20.375	1.031E+01
21.[illegible]	[illegible]	21.[illegible]	[illegible]	20.789	2.988E+01	20.925	7.007E+01
22.[illegible]	[illegible]	22.[illegible]	[illegible]	21.291	8.957E+01	21.776	9.206E+01
23.[illegible]	[illegible]	23.[illegible]	[illegible]	22.754	7.775E+01	22.949	5.997E+01
25.[illegible]	[illegible]	25.[illegible]	[illegible]	23.865	5.[illegible]09E+01	24.436	4.525E+01
26.[illegible]	[illegible]	26.[illegible]	[illegible]	25.[illegible]23	3.516E+01	25.693	3.053E+01
28.[illegible]	[illegible]	28.[illegible]	[illegible]	25.927	[illegible].154E+01	25.991	5.273E+01
32.[illegible]	[illegible]	33.[illegible]	[illegible]	26.901	[illegible].037E+01	27.989	3.756E+01
				30.942	[illegible].381E+01	31.344	3.309E+01
				34.532	3.178E+01		


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-4A
SAPPHIRE
T=300 K
BARKER. PHYS. REV. 132. 1474 (1963)
REF. 1R-4


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-4A
SAPPHIRE
T=300 K
BARKER. PHYS. REV. 132. 1474 (1963)
REF. 1R-4


Barker (Ref. 1R-4)


b. Extraordinary ray reflectivity, Linde fusion ruby, 1.8×10^{18} chromium ions/cm^3.

λ	R	λ	R	λ	R	λ	R
.890	7.418E+00	1.905	7.719E+00	2.957	7.191E+00	3.948	6.879E+00
5.006	5.901E+00	5.996	4.695E+00	7.054	3.518E+00	8.082	2.170E+00
9.077	9.362E-01	9.627	2.837E-01	10.044	4.397E-01	10.476	1.433E+00
10.894	4.336E+00	11.104	1.963E+01	11.234	3.511E+01	11.367	5.019E+01
11.502	9.396E+01	11.695	7.977E+01	12.074	8.134E+01	12.322	7.960E+01
12.559	8.247E+01	12.710	8.372E+01	13.119	8.468E+01	13.411	8.682E+01
13.963	8.811E+01	14.442	8.868E+01	14.942	8.675E+01	15.327	8.566E+01
15.853	8.420E+01	16.348	8.469E+01	16.501	7.958E+01	16.585	7.431E+01
17.015	7.255E+01	17.268	6.773E+01	17.388	5.987E+01	17.603	4.991E+01
18.015	3.491E+01	18.338	2.492E+01	18.756	1.489E+01	19.289	3.745E+00
19.411	3.096E+00	19.484	5.077E+00	19.609	4.235E+01	19.735	7.455E+01
19.867	8.222E+01	20.087	8.673E+01	20.466	8.898E+01	20.722	8.913E+01
20.917	9.177E+01	21.211	9.244E+01	21.552	9.327E+01	21.925	9.270E+01
22.956	8.999E+01	24.327	8.416E+01	25.117	7.952E+01	25.533	7.459E+01
26.026	6.724E+01	26.623	5.973E+01	27.279	5.450E+01	27.999	5.082E+01
29.042	4.655E+01	29.977	4.367E+01	30.983	4.198E+01	31.981	4.074E+01
32.979	3.940E+01	34.014	3.901E+01	35.015	3.840E+01		

c. Ordinary ray reflectivity, Meller sapphire, before etch.

λ	R	λ	R	λ	R	λ	R
15.221	8.318E+01	15.293	8.238E+01	15.394	8.088E+01	15.489	7.919E+01
15.595	7.720E+01	15.644	7.551E+01	15.711	7.349E+01	15.753	7.163E+01
15.860	6.972E+01	15.775	6.769E+01	15.781	6.589E+01	15.801	6.517E+01
15.852	6.822E+01	15.900	6.639E+01	15.940	6.708E+01	15.978	6.865E+01
16.009	6.954E+01	16.041	7.018E+01	16.157	7.037E+01	16.246	6.998E+01
16.393	6.854E+01	16.583	5.731E+01	16.738	6.556E+01	16.951	6.424E+01
17.122	6.440E+01	17.260	6.496E+01	17.446	6.487E+01	17.529	6.459E+01
17.591	6.577E+01	17.672	6.208E+01	17.725	6.030E+01	17.769	5.887E+01
17.853	5.794E+01	17.923	5.693E+01	17.877	5.531E+01	17.971	5.310E+01
18.033	5.113E+01	16.208	4.854E+01	20.959	6.286E+01	20.959	7.009E+01
20.973	7.353E+01	21.002	7.584E+01	21.094	7.779E+01	21.165	7.981E+01
21.265	8.184E+01	21.351	8.367E+01	21.417	8.456E+01	21.548	8.505E+01
21.655	8.566E+01	21.798	8.359E+01	21.977	8.181E+01	22.154	7.982E+01
22.382	7.791E+01	22.499	7.615E+01	22.671	7.421E+01	22.790	7.207E+01
22.885	7.000E+01	23.011	6.799E+01	23.107	6.588E+01	23.191	6.384E+01
23.249	6.192E+01	23.315	6.002E+01	23.389	5.715E+01		


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-4B
RUBY
T=300 K
BARKER. PHYS. REV. 132. 1474 (1963)
REF. 1R-4


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-4B
RUBY
T=300 K
BARKER. PHYS. REV. 132. 1474 (1963)
REF. 1R-4

Barker (Ref. 1R-4)

d. Ordinary ray reflectivity, Meller sapphire, after etch.

λ	R	λ	R	λ	R	λ	R
[illegible]	[illegible]	15.290	8.652E+01	15.444	8.448E+01	15.533	8.269E+01
15.584	8.074E+01	15.556	7.753E+01	15.716	7.342E+01	15.758	6.622E+01
15.773	5.907E+01	15.808	5.622E+01	15.835	5.409E+01	15.886	5.329E+01
15.937	5.762E+01	15.970	5.482E+01	15.978	5.909E+01	16.022	6.478E+01
16.071	7.022E+01	16.059	7.372E+01	16.101	7.799E+01	16.185	8.127E+01
16.266	8.322E+01	16.279	8.470E+01	16.484	8.557E+01	16.533	8.611E+01
16.906	8.534E+01	17.005	8.525E+01	17.164	8.559E+01	17.280	8.523E+01
17.375	8.396E+01	17.439	8.174E+01	17.495	7.869E+01	17.574	7.568E+01
17.638	7.215E+01	17.684	6.775E+01	17.736	6.411E+01	17.798	5.989E+01
17.851	5.625E+01	17.904	5.424E+01	17.938	5.321E+01	20.962	6.282E+01
20.990	7.066E+01	20.962	7.532E+01	21.002	7.853E+01	21.080	8.142E+01
21.173	8.375E+01	21.305	8.561E+01	21.462	8.742E+01	21.649	8.839E+01
21.812	8.947E+01	21.946	8.898E+01	22.129	8.874E+01	22.277	8.839E+01
22.421	8.763E+01	22.504	8.700E+01	22.577	8.577E+01	22.628	8.308E+01
22.669	8.938E+01	22.755	8.574E+01	22.821	8.104E+01	22.917	6.741E+01
22.995	6.409E+01	23.105	6.086E+01	23.199	5.817E+01	23.284	5.559E+01
23.377	5.407E+01						

e. Ordinary ray reflectivity, Meller sapphire, after etch and 15μ grit abrasion.

λ	R	λ	R	λ	R	λ	R
16.105	6.916E+01	16.244	6.611E+01	16.368	6.375E+01	16.505	6.064E+01
16.653	5.772E+01	16.801	5.506E+01	16.930	5.230E+01	17.053	4.928E+01
17.171	4.606E+01	17.302	4.364E+01	17.479	4.117E+01	17.784	3.925E+01
19.036	6.912E+01	20.939	6.923E+01	20.983	6.981E+01	21.054	7.222E+01
21.178	7.468E+01	21.311	7.660E+01	21.363	7.708E+01	21.529	7.749E+01
21.692	7.719E+01	21.983	7.549E+01	22.070	7.320E+01	22.181	7.095E+01
22.286	6.852E+01	22.377	6.596E+01	22.491	6.342E+01	22.617	6.115E+01
22.743	5.879E+01	22.875	5.652E+01	23.059	5.439E+01	23.293	5.247E+01

f. Ordinary ray reflectivity, Meller sapphire, after etch and 6μ grit abrasion.

λ	R	λ	R	λ	R	λ	R
16.169	6.894E+01	16.366	6.512E+01	16.552	6.274E+01	16.721	5.959E+01
16.937	6.620E+01	17.107	6.365E+01	17.280	6.517E+01	17.459	6.792E+01
17.597	6.897E+01	17.712	6.776E+01	17.861	6.464E+01	18.033	7.087E+01
21.015	7.209E+01	21.101	7.475E+01	21.196	7.804E+01	21.342	8.090E+01
21.459	8.132E+01	21.565	8.158E+01	21.727	8.121E+01	21.838	8.056E+01
22.028	7.757E+01	22.194	7.429E+01	22.416	7.066E+01	22.520	6.892E+01
22.705	6.734E+01	22.802	6.653E+01	22.926	6.532E+01	23.004	6.400E+01




FIGURE 1R-4C
SAPPHIRE
T=300 K
BARKER, PHYS. REV. 132, 1474 (1963)
REF. 1R-4




FIGURE 1R-4D
SAPPHIRE (ETCHED)
T=300 K
BARKER, PHYS. REV. 132, 1474 (1963)
REF. 1R-4




FIGURE 1R-4E
SAPPHIRE (ETCHED AND ABRADED)
T=300 K
BARKER, PHYS. REV. 132, 1474 (1963)
REF. 1R-4





FIGURE 1R-4F
SAPPHIRE (ETCHED AND ABRADED)
T=300 K
BARKER, PHYS. REV. 132, 1474 (1963)
REF. 1R-4

Clark (Ref. 1R-6)

A Cary 14M spectrophotometer was used to measure the reflectance of fine grained, 99 + percent pure alumina with a porosity of 36 percent. No error analysis or spectral bandpass is given. Data were digitized from a continuous line.

These data were selected in part to construct the representative curve in Section I, Figure I - 1.6.

λ	R	λ	R	λ	R	λ	R
.253	11.211	.271	15.816	.281	23.946	.292	31.436
.299	34.308	.304	40.652	.311	45.658	.313	49.009
.333	52.169	.343	54.139	.350	59.288	.356	63.228
.364	69.434	.375	73.245	.390	77.781	.409	80.941
.429	84.034	.439	83.647	.447	82.655	.455	81.832
.468	82.672	.483	85.276	.495	86.824	.510	87.933
.528	87.664	.556	86.824	.584	86.370	.612	85.950
.632	85.832	.651	86.403	.665	87.361	.675	89.815
.683	92.971	.691	96.910	.699	93.998	.753	91.409
.714	91.392	.740	92.462	.768	93.073	.786	93.192
.813	93.039	.844	92.988	.879	92.598	.910	92.309
.942	92.241	.971	92.615	.995	92.377	1.018	91.562
1.041	91.138	1.061	93.645	1.104	90.696	1.136	91.002
1.181	91.367	1.228	92.023	1.290	92.699	1.323	93.684
1.364	94.363	1.402	94.754	1.441	94.448	1.491	94.312
1.533	93.837	1.572	93.447	1.605	92.767	1.665	92.716
1.715	92.530	1.769	92.428	1.837	92.445	1.905	92.445
1.957	92.581	1.998	92.801	2.030	92.683	2.062	92.224
2.094	91.138						


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1R-6
ALUMINA
T=300 K
CLARK, NASA SP-55
REF. 1R-6

Gervais (Ref. 1R-7)

The reflection spectrum of sapphire (E ⊥ C) was studied from 9μ to 33μ over a temperature range of 960°K to 2070°K using a Perkin-Elmer 12C spectrometer with a 2 to 4 cm^{-1} bandpass. Samples were heated by furnace and by laser radiation at 944 cm^{-1}. The measurements have an estimated precision of 1 percent, and the largest temperature uncertainty is ± 50°K at 1550°K. Data were digitized from continuous lines.

Agreement of these data with the representative curve given in Section I - 1.6 is generally good.

a. T = 960°K ± 20°, laser heated.

λ	R	λ	R	λ	R
3.330E+01	2.963E+01	3.027E+01	3.210E+01	2.847E+01	3.467E+01
2.780E+01	3.589E+01	2.731E+01	3.965E+01	2.689E+01	4.208E+01
2.665E+01	4.056E+01	2.645E+01	3.774E+01	2.609E+01	3.526E+01
2.578E+01	3.613E+01	2.519E+01	3.893E+01	2.469E+01	4.225E+01
2.527E+01	4.628E+01	2.385E+01	5.134E+01	2.352E+01	5.760E+01
2.323E+01	6.554E+01	2.300E+01	7.188E+01	2.280E+01	7.429E+01
2.260E+01	7.500E+01	2.239E+01	7.347E+01	2.216E+01	7.043E+01
2.191E+01	6.545E+01	2.172E+01	6.082E+01	2.155E+01	5.391E+01
2.143E+01	4.382E+01	2.133E+01	2.642E+01	2.118E+01	1.311E+01
2.110E+01	1.078E+01	2.094E+01	1.041E+01	2.076E+01	1.208E+01
2.032E+01	1.861E+01	1.983E+01	2.589E+01	1.937E+01	3.294E+01
1.887E+01	3.957E+01	1.861E+01	4.387E+01	1.847E+01	4.787E+01
1.828E+01	5.482E+01	1.810E+01	6.204E+01	1.788E+01	6.880E+01
1.768E+01	7.379E+01	1.753E+01	7.598E+01	1.735E+01	7.696E+01
1.714E+01	7.737E+01	1.693E+01	7.696E+01	1.673E+01	7.570E+01
1.656E+01	7.373E+01	1.644E+01	7.193E+01	1.628E+01	7.018E+01
1.616E+01	7.279E+01	1.605E+01	7.663E+01	1.591E+01	8.155E+01
1.577E+01	8.418E+01	1.565E+01	8.544E+01	1.531E+01	8.597E+01
1.498E+01	8.594E+01	1.472E+01	8.576E+01	1.438E+01	8.523E+01
1.409E+01	8.449E+01	1.375E+01	8.332E+01	1.341E+01	8.186E+01
1.307E+01	7.983E+01	1.279E+01	7.761E+01	1.258E+01	7.538E+01
1.247E+01	7.450E+01	1.235E+01	7.348E+01	1.223E+01	7.195E+01
1.210E+01	6.990E+01	1.196E+01	6.611E+01	1.182E+01	6.154E+01
1.169E+01	5.637E+01	1.158E+01	5.165E+01	1.148E+01	4.674E+01
1.137E+01	4.081E+01	1.127E+01	3.429E+01	1.119E+01	2.792E+01
1.108E+01	1.990E+01	1.094E+01	1.245E+01	1.079E+01	7.434E+00
1.053E+01	4.648E+00	1.043E+01	2.194E+00	1.022E+01	8.357E-01
9.876E+00	3.398E-01	9.550E+00	4.178E-01	9.340E+00	6.964E-01
9.197E+00	9.401E-01				
1.035E+01	1.305E+00	1.032E+01	1.027E+00	1.023E+01	7.326E-01
1.011E+01	4.586E-01	1.002E+01	2.967E-01	9.882E+00	1.804E-01
9.782E+00	1.340E-01	9.690E+00	1.870E-01	9.543E+00	2.782E-01
9.428E+00	3.858E-01	9.324E+00	5.672E-01	9.226E+00	6.267E-01
9.167E+00	7.114E-01	9.107E+00	7.988E-01		




FIGURE 1R-7A
SAPPHIRE. LASER HEATED
T=960 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7






FIGURE 1R-7A
SAPPHIRE. LASER HEATED
T=960 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7

Gervais (Ref. 1P-7)

b. $T = 1145^{\circ}K \pm 40^{\circ}$, laser heated.

λ	R	λ	R	λ	R
3.319E+01	2.982E+01	3.196E+01	3.214E+01	2.904E+01	3.448E+01
2.80[illegible]E+01	3.670E+01	2.743E+01	3.873E+01	2.70[illegible]E+01	3.991E+01
2.672[illegible]E+01	3.786E+01	2.658[illegible]E+01	3.675E+01	2.610E+01	3.605E+01
2.562[illegible]E+01	3.760E+01	2.512[illegible]E+01	4.656E+01	2.467E+01	4.389E+01
2.434[illegible]E+01	4.723E+01	2.400[illegible]E+01	5.047E+01	2.385E+01	5.407E+01
2.368[illegible]E+01	5.722E+01	2.351[illegible]E+01	6.044E+01	2.333E+01	6.303E+01
2.316[illegible]E+01	6.725E+01	2.302[illegible]E+01	6.849E+01	2.290E+01	6.938E+01
2.269[illegible]E+01	6.954E+01	2.252[illegible]E+01	6.816E+01	2.242E+01	6.545E+01
2.226[illegible]E+01	6.192E+01	2.206[illegible]E+01	5.675E+01	2.191E+01	5.131E+01
2.180E+01	4.561E+01	2.166[illegible]E+01	3.972E+01	2.156E+01	3.299E+01
2.147[illegible]E+01	2.664E+01	2.142E+01	2.056E+01	2.132E+01	1.711E+01
2.123E+01	1.299E+01	2.107E+01	1.220E+01	2.091E+01	1.283E+01
2.074E+01	1.530E+01	2.045E+01	1.931E+01	2.019E+01	2.329E+01
1.996E+01	2.708E+01	1.971E+01	3.120E+01	1.946E+01	3.519E+01
1.922E+01	3.940E+01	1.901[illegible]+01	4.356E+01	1.878E+01	4.746E+01
1.854E+01	5.217E+01	1.834E+01	5.667E+01	1.819E+01	6.075E+01
1.804E+01	6.392E+01	1.790E+01	6.838E+01	1.770E+01	7.019E+01
1.751E+01	7.226E+01	1.728E+01	7.321E+01	1.712E+01	7.293E+01
1.693[illegible]E+01	7.140E+01	1.673[illegible]+01	6.962E+01	1.661[illegible]+01	6.737E+01
1.651E+01	6.687E+01	1.640[illegible]+01	6.761E+01	1.631E+01	7.195E+01
1.626[illegible]+01	7.497E+01	1.616[illegible]+01	7.851[illegible]+01	1.608E+01	8.076E+01
1.591E+01	8.248E+01	1.569E+01	8.343E+01	1.55[illegible]E+01	8.329E+01
1.5[illegible]E+01	8.277E+01	1.463E+01	8.198E+01	1.433[illegible]+01	8.116E+01
1.397[illegible]+01	7.976E+01	1.363[illegible]+01	7.773E+01	1.341[illegible]+01	7.560E+01
1.215[illegible]+01	6.430[illegible]+01	1.201[illegible]+01	6.122E+01	1.189E+01	5.770E+01
1.178[illegible]+01	5.364[illegible]+01	1.168[illegible]+01	4.923E+01	1.159[illegible]+01	4.508E+01
1.149[illegible]+01	4.[illegible]63E+01	1.140[illegible]+01	3.596E+01	1.131[illegible]+01	3.105E+01
1.125[illegible]+01	2.633E+01	1.110[illegible]+01	2.126E+01	1.109E+01	1.784E+01
1.10[illegible]E+01	1.200E+01	1.090[illegible]+01	8.565E+00	1.080E+01	6.006E+00
1.067[illegible]+01	3.639E+00	1.046[illegible]+01	1.741E+00	1.026E+01	2.611E-01
9.756E+00	3.134E-01	9.393[illegible]+00	3.482E-01	9.092E+00	9.749E-01
1.323E+01	1.472E+00	1.308E+01	1.451E+00	1.283E+01	1.437E+00
1.267[illegible]+01	1.42[illegible]E+00	1.251[illegible]+01	1.386E+00	1.231E+01	1.339E+00
1.[illegible]42[illegible]+01	1.26[illegible]E+00	1.[illegible]39E+01	1.075E+00	1.034E+01	8.328E-01
1.029[illegible]+01	7.432E-01	1.[illegible]23E+01	6.124E-01	1.017[illegible]+01	5.065E-01
1.011[illegible]+01	4.384E-01	1.007E+01	3.423E-01	1.00[illegible]E+01	2.608E-01
9.[illegible]40E+00	2.[illegible]40E-01	9.360[illegible]+00	1.877E-01	9.86[illegible]E+00	1.831E-01
9.736E+00	1.963E-01	9.666[illegible]+00	2.221E-01	9.586E+00	2.712E-01
9.54[illegible]E+00	3.[illegible]47E-01	9.438E+00	3.767E-01	9.366[illegible]+00	4.575E-01
9.[illegible]46[illegible]+00	6.[illegible]28E-01	9.190E+00	7.029E-01	9.14[illegible]E+00	7.766E-01
9.[illegible]17E+00	8.453E-01				


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-78
SAPPHIRE. LASER HEATED
T=1145 K
GERVAIS. COMPTES RENDUS 2708. 1042
(1972)
REF. 1R-7



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-78
SAPPHIRE. LASER HEATED
T=1145 K
GERVAIS. COMPTES RENDUS 2708. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)


Gervais (Ref. 1R-7)

c. T = 1420°K ± 30°, laser heated.

λ	R	λ	R	λ	R
[illegible]	3.139E+01	30.888	3.347E+01	29.120	3.631E+01
[illegible]	3.82[illegible]+01	27.942	3.872E+01	27.581	3.831E+01
[illegible]	3.7[illegible]3+01	26.744	3.760E+01	26.104	3.877E+01
[illegible]	4.07[illegible]+01	25.236	4.356E+01	24.992	4.572E+01
[illegible]	[illegible].90[illegible]+01	24.411	5.333E+01	24.155	5.643E+01
23.204	[illegible].68[illegible]+01	23.588	5.972E+01	23.582	6.033E+01
23.[illegible]42	5.946E+01	23.252	5.742E+01	23.119	5.546E+01
22.[illegible]46	5.291E+01	22.859	5.943E+01	22.713	4.487E+01
22.[illegible]46	3.639E+01	22.313	3.210E+01	22.142	2.758E+01
21.[illegible]80	2.335E+01	21.769	2.006E+01	21.622	1.827E+01
21.[illegible]68	1.696E+01	21.302	1.[illegible]E+01	21.157	1.698E+01
20.[illegible]91	1.[illegible]E+01	20.[illegible]8[illegible]	2.042E+01	20.507	2.345E+01
20.[illegible]00	2.[illegible]1E+01	20.[illegible]2[illegible]	2.970E+01	19.900	3.391E+01
19.722[illegible]	3.[illegible]18E+01	19.[illegible]29	4.[illegible]6E+01	19.320	4.435E+01
[illegible].1[illegible]	4.721E+01	[illegible].9[illegible]	4.933E+01	[illegible].[illegible]25	5.147E+01
[illegible].[illegible]00	[illegible].[illegible]E+01	18.[illegible]99	[illegible].[illegible]E+01	17.399	6.195E+01
17.[illegible]00	[illegible].[illegible]E+01	17.[illegible]99	[illegible].[illegible]E+01	16.929	6.644E+01
[illegible].[illegible]21	[illegible].[illegible]E+01	16.[illegible]96	[illegible].131E+01	16.[illegible]76	7.353E+01
[illegible].[illegible]33	[illegible].[illegible]E+01	[illegible].[illegible]3[illegible]	[illegible].[illegible]E+01	16.000	7.667E+01
[illegible].[illegible]43	7.[illegible]6E+01	[illegible].[illegible]41	[illegible].[illegible]E+01	15.214	7.[illegible]32E+01
[illegible].[illegible]46	7.[illegible]1E+01	[illegible].[illegible]15	[illegible].[illegible]E+01	14.380	7.128E+01
[illegible].[illegible]33	[illegible].[illegible]E+01	13.[illegible]0[illegible]	6.[illegible]6[illegible]1E+01	13.546	6.772E+01
12.[illegible]4[illegible]	[illegible].[illegible]E+01	12.[illegible]6[illegible]	[illegible].[illegible]21E+01	12.865	6.322E+01
[illegible].[illegible]88	[illegible].[illegible]E+01	12.[illegible]9[illegible]	[illegible].[illegible]36E+01	12.[illegible]2	5.[illegible]02E+01
[illegible].[illegible]66	[illegible].[illegible]E+01	12.[illegible]9[illegible]	[illegible].[illegible]10E+01	12.070	4.671E+01
[illegible].[illegible]66	[illegible].317E+01	11.[illegible]2[illegible]	3.[illegible]96E+01	11.737	3.565E+01
[illegible].[illegible]66	[illegible].117E+01	11.[illegible]6[illegible]	2.[illegible]6[illegible]E+01	11.[illegible]53	2.216E+01
[illegible].[illegible]66	1.[illegible]2[illegible]E+01	11.[illegible]5[illegible]	1.[illegible]19E+01	11.145	1.070E+01
[illegible].[illegible]14	[illegible].[illegible]E+01	[illegible].[illegible]87[illegible]	[illegible].972E+00	10.742	3.235E+00
[illegible].[illegible]00	2.[illegible]5E+00	10.[illegible]0[illegible]	1.[illegible]8[illegible]E+00	10.259	3.957E-01
[illegible].[illegible]00	1.721E-01	9.870	1.721E-01	9.603	1.721E-01
[illegible].[illegible]53	[illegible].3[illegible]E-01	9.313	9.979E-01		

Reproduced from best available copy.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7C
SAPPHIRE. LASER HEATED
T=1420 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7C
SAPPHIRE. LASER HEATED
T=1420 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)

Gervais (Ref. 1R-7)

d. $T = 1420^{\circ}K \pm 30^{\circ}$, furnace heated.

λ	R	λ	R	λ	R
30.877	3.907E+01	31.951	3.721E+01	30.877	3.907E+01
27.937	4.579E+01	[illegible]	[illegible]	27.937	4.579E+01
27.[illegible]49	4.390E+01	[illegible]	[illegible]	27.[illegible]49	4.390E+01
25.943	4.879E+01	[illegible]	[illegible]	25.943	4.879E+01
24.515	5.916E+01	[illegible]	[illegible]	24.515	5.916E+01
23.734	6.464E+01	[illegible]	[illegible]	23.734	6.464E+01
22.935	5.859E+01	[illegible]	[illegible]	22.935	5.859E+01
22.391	4.316E+01	[illegible]	[illegible]	22.391	4.316E+01
22.016	3.115E+01	[illegible]	[illegible]	22.016	3.115E+01
21.[illegible]68	2.497E+01	[illegible]	[illegible]	21.[illegible]68	2.497E+01
20.622	3.293E+01	[illegible]	[illegible]	20.622	3.293E+01
19.310	5.485E+01	[illegible]	[illegible]	19.310	5.485E+01
18.493	6.883E+01	[illegible]	[illegible]	18.493	6.883E+01
17.[illegible]13	7.415E+01	[illegible]	[illegible]	17.[illegible]13	7.415E+01
16.949	7.419E+01	[illegible]	[illegible]	16.949	7.419E+01
16.024	7.933E+01	[illegible]	[illegible]	16.024	7.933E+01
14.976	7.591E+01	15.[illegible]96	7.425E+01	14.976	7.591E+01
[illegible]	[illegible]	13.[illegible]83	[illegible]	13.625	6.804E+01
[illegible]	[illegible]	12.[illegible]49	[illegible]	12.[illegible]49	5.778E+01
[illegible]	[illegible]	12.297	[illegible]	12.153	4.782E+01
[illegible]	[illegible]	11.[illegible]37	[illegible]	11.693	3.070E+01
[illegible]	[illegible]	[illegible]	[illegible]	11.169	1.155E+01
[illegible]	[illegible]	10.[illegible]52	[illegible]	10.569	1.944E+00
9.[illegible]24	[illegible]	9.254	9.463E-01	9.763	5.162E-02
				9.104	1.256E+00



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7D
SAPPHIRE
T=1420 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7D
SAPPHIRE
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Gervais (Ref. 1R-7)

e. $T = 1550^{\circ}K \pm 50^{\circ}$, laser he d.

λ	R	λ	R	λ	R
3.329 +01	3.118 +01	3.086 +01	3.323E+01	2.889E+01	3.630E+01
2.802 +01	3.767 +01	2.773 +01	3.883E+01	2.741E+01	3.811E+01
2.714 +01	3.923 +01	2.688 +01	3.593E+01	2.638E+01	3.680E+01
2.57 +01	3.363E+01	2.529 +01	4.114E+01	2.492E+01	4.348E+01
2.488 +01	3.614 +01	2.447E+01	4.947E+01	2.415E+01	5.365E+01
2.398 +01	3.576 +01	2.383E+01	5.934E+01	2.364E+01	6.241E+01
2.348 +01	3.346 +01	2.329E+01	6.421E+01	2.310E+01	6.311E+01
2.298 +01	3.968 +01	2.272E+01	5.624E+01	2.247E+01	4.906E+01
2.228 +01	4.257 +01	2.210E+01	3.511E+01	2.190E+01	2.824E+01
2.170 +01	2.779 +01	2.160E+01	1.720E+01	2.151E+01	1.647E+01
2.125 +01	1.376 +01	2.104E+01	1.671E+01	2.077E+01	1.922E+01
2.031 +01	2.512 +01	1.992E+01	3.132E+01	1.956E+01	3.794E+01
1.922 +01	4.316 +01	1.892E+01	4.863E+01	1.873E+01	5.229E+01
1.858 +01	5.505 +01	1.837E+01	5.762E+01	1.817E+01	5.973E+01
1.793 +01	6.439 +01	1.770E+01	6.742E+01	1.747E+01	6.930E+01
1.737 +01	6.931 +01	1.713E+01	6.861E+01	1.700E+01	6.811E+01
1.685 +01	6.785 +01	1.670E+01	6.863E+01	1.636E+01	7.347E+01
1.619 +01	7.643 +01	1.596E+01	7.902E+01	1.570E+01	8.028E+01
1.549 +01	8.214 +01	1.553E+01	7.935E+01	1.471E+01	7.669E+01
1.416 +01	7.366 +01	1.368E+01	7.081E+01	1.387E+01	6.892E+01
1.305 +01	6.721E+01	1.285E+01	6.582E+01	1.287E+01	6.339E+01
1.248 +01	6.034 +01	1.219E+01	5.470E+01	1.196E+01	4.812E+01
1.176 +01	4.080 +01	1.157E+01	3.330E+01	1.139E+01	2.514E+01
1.124 +01	1.668 +01	1.112E+01	1.106E+01	1.099E+01	7.399E+00
1.086 +01	4.875 +00	1.075E+01	3.116E+00	1.064E+01	2.054E+00
1.048 +01	1.297 +00	1.046E+01	1.119E+00	1.043E+01	9.839E-01
1.039 +01	8.521 -01	1.033E+01	7.189E-01	1.027E+01	5.987E-01
1.018 +01	4.396 -01	1.013E+01	4.425E-01	1.009E+01	4.091E-01
1.004 +01	3.231 -01	9.997E+00	3.005E-01	9.925E+00	2.960E-01
9.884 +00	2.377 -01	9.835E+00	3.04 E-01	9.720E+00	3.388E-01
9.553 +00	4.386 -01	9.410 +00	5.632E-01	9.297E+00	6.943E-01
9.196 +00	8.241 -01	9.120 +00	9.320E-01		


SAPPHIRE
T=550 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. IR-7
WAVELENGTH(MICRONS)



FIGURE IR 2E
SAPPHIRE
T=1550 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. IR-7
REFLECTIVITY
WAVELENGTH(MICRONS)


Gervais (Ref. 1R-7)

f. T = 1775°K ± 20°, laser heated.

λ	R
29.301	3.625E+01
27.310	4.094E+01
26.333	3.792E+01
25.236	4.322E+01
24.313	5.264E+01
23.493	6.407E+01
22.887	6.569E+01
22.382	5.440E+01
21.922	3.073E+01
21.372	1.492E+01
20.535	2.249E+01
19.651	3.549E+01
18.909	4.767E+01
18.363	6.155E+01
17.470	7.096E+01
17.105	7.041E+01
16.494	7.403E+01
15.976	8.122E+01
15.272	8.157E+01
14.521	7.742E+01
13.838	7.329E+01
13.083	6.880E+01
12.466	6.466E+01
12.072	5.794E+01
11.783	4.693E+01
11.456	3.159E+01
11.117	1.377E+01
10.768	4.714E+00
10.250	7.071E-01

Reproduced from best available copy.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7F
SAPPHIRE. LASER HEATED
T=1775 K
GERVAIS. COMPTES RENDUS 2708. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7F
SAPPHIRE. LASER HEATED
T=1775 K
GERVAIS. COMPTES RENDUS 2708. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Gervais (Ref. 1R-7)

g T = 1775°K ± 20°, furnace heated.

λ	R	λ	R	λ	R
33.230	3.551E+01	30.939	1.780E+01	29.089	4.196E+01
28.[illegible]	[illegible]	[illegible]	[illegible]	27.284	4.545E+01
26.[illegible]	[illegible]	26.419	4.294E+01	25.934	4.419E+01
25.[illegible]	[illegible]	24.[illegible]	[illegible]	24.186	6.177E+01
23.[illegible]	[illegible]	23.[illegible]	[illegible]	23.470	7.259E+01
22.[illegible]	[illegible]	22.[illegible]	[illegible]	22.594	6.984E+01
22.[illegible]	[illegible]	22.[illegible]	[illegible]	22.050	5.471E+01
21.[illegible]	[illegible]	21.822[illegible]	[illegible]	21.676	3.173E+01
21.[illegible]	[illegible]	21.[illegible]	[illegible]	21.320	2.210E+01
21.[illegible]	[illegible]	20.[illegible]	[illegible]	20.274	3.506E+01
19.[illegible]	[illegible]	19.[illegible]	[illegible]	19.231	5.038E+01
18.[illegible]	[illegible]	18.[illegible]	[illegible]	18.349	7.191E+01
17.[illegible]	[illegible]	17.[illegible]	[illegible]	17.598	7.970E+01
17.[illegible]	[illegible]	17.[illegible]	[illegible]	17.087	7.634E+01
16.[illegible]	[illegible]	16.[illegible]	[illegible]	16.587	7.646E+01
15.[illegible]	[illegible]	15.[illegible]	[illegible]	15.981	8.381E+01
15.[illegible]	[illegible]	15.[illegible]	[illegible]	14.903	8.218E+01
14.[illegible]	[illegible]	13.[illegible]	[illegible]	13.091	7.646E+01
12.[illegible]	[illegible]	12.[illegible]	[illegible]	12.601	6.600E+01
12.[illegible]	[illegible]	12.076	5.539E+01	11.877	4.950E+01
11.[illegible]	[illegible]	11.[illegible]	3.391E+01	11.352	2.562E+01
11.[illegible]	[illegible]	11.[illegible]	1.234E+01	10.915	7.323E+00
10.[illegible]	[illegible]	10.[illegible]	2.699E+00	10.366	1.229E+00
10.[illegible]	[illegible]	9.[illegible]	2.189E-01	9.466	2.694E-01
9.313	[illegible]	9.090	1.051E+00		



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7G
SAPPHIRE
T=1775 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7G
SAPPHIRE
T=1775 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)

Gervais (Ref. 1R-7)

h. $T = 2070^{\circ}K \pm 20^{\circ}$, laser heated.

λ	R	λ	R	λ	R
3.322E+01	3.152E+01	3.065E+01	3.444E+01	2.965E+01	3.685E+01
2.808E+01	3.888E+01	2.769E+01	3.881E+01	2.693E+01	3.871E+01
2.616E+01	4.369E+01	2.548E+01	4.445E+01	2.472E+01	4.720E+01
2.442E+01	4.980E+01	2.417E+01	5.140E+01	2.397E+01	5.212E+01
2.369E+01	5.129E+01	2.339E+01	4.920E+01	2.312E+01	4.582E+01
2.295E+01	4.073E+01	2.275E+01	3.487E+01	2.244E+01	2.847E+01
2.204E+01	2.206E+01	2.174E+01	1.965E+01	2.146E+01	1.826E+01
2.106E+01	1.892E+01	2.089E+01	1.988E+01	2.056E+01	2.382E+01
2.024E+01	2.968E+01	1.996E+01	3.414E+01	1.966E+01	4.022E+01
1.933E+01	4.554E+01	1.916E+01	4.822E+01	1.879E+01	4.954E+01
1.815E+01	5.355E+01	1.770E+01	5.694E+01	1.728E+01	5.327E+01
1.709E+01	6.030E+01	1.664E+01	6.232E+01	1.665E+01	6.657E+01
1.652E+01	6.945E+01	1.637E+01	7.045E+01	1.614E+01	7.162E+01
1.586E+01	7.231E+01	1.557E+01	7.164E+01	1.503E+01	6.883E+01
1.454E+01	6.583E+01	1.410E+01	6.306E+01	1.366E+01	6.104E+01
1.322E+01	5.960E+01	1.285E+01	5.627E+01	1.251E+01	5.096E+01
1.228E+01	4.578E+01	1.210E+01	4.033E+01	1.184E+01	3.166E+01
1.168E+01	2.544E+01	1.150E+01	1.847E+01	1.133E+01	1.215E+01
1.115E+01	7.208E+00	1.093E+01	3.534E+00	1.070E+01	1.636E+00
1.057E+01	1.317E+00	1.055E+01	1.246E+00	1.054E+01	1.122E+00
1.050E+01	9.397E-01	1.045E+01	8.535E-01	1.041E+01	7.292E-01
1.036E+01	6.206E-01	1.027E+01	5.171E-01	1.015E+01	4.199E-01
1.005E+01	3.513E-01	9.946E+00	2.444E-01	9.831E+00	3.593E-01
9.649E+00	4.593E-01	9.515E+00	5.591E-01	9.399E+00	6.732E-01
9.296E+00	7.883E-01	9.207E+00	9.013E-01		


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7H
SAPPHIRE. LASER HEATED
T=2070 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-7H
SAPPHIRE. LASER HEATED
T=2070 K
GERVAIS. COMPTES RENDUS 270B. 1042
(1972)
REF. 1R-7
REFLECTIVITY
WAVELENGTH(MICRONS)

Harris (Re 1R-8)

The reflectance of 50, 100, and 200 volt aluminum oxide films from 14μ to 90μ was measured using a grating spectrometer. No estimates of error were given. Data were digitized from lines.

a. Thickness = 2800 Å (anodizing voltage of 200 volts).


λ	R	λ	R	λ	R	λ	R
[illegible]		[illegible]		18.501	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]


b. Thickness = 1370Å (100 volts)


λ	R	λ	R	λ	R	λ	R
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]


c. Thickness = 700 Å (50 volts)


λ	R	λ	R	λ	R	λ	R
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]
[illegible]		[illegible]		[illegible]	[illegible]	[illegible]	[illegible]



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-8A
ALUMINUM OXIDE FILM. T=2800A
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-8A
ALUMINUM OXIDE FILM. T=2800A
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-8A
ALUMINUM OXIDE FILM, T=2800A
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
10
20
30
40
50
60
70
80
90
100


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-8B
ALUMINUM OXIDE FILM, T=1370A
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
.5
1.0
1.5
2.0
2.5
3.0
3.5
4.0
4.5
5.0


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-8B
ALUMINUM OXIDE FILM. T=1370A
T=300 K
HARRIS. J.OPT.SOC. 52. 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
0.0
1.0
2.0
3.0
4.0
5.0


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-9B
ALUMINUM OXIDE FILM. T=1370A
T=300 K
HARRIS. J.OPT.SOC. 52. 223 (1962)
REF. 1R-8
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
0.0
1.0
2.0
3.0
4.0
5.0


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY(PERCENT)
WAVELENGTH(MICRONS)
FIGURE 1R-8C
ALUMINUM OXIDE FILM. T=700A
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1R-8


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY(PERCENT)
WAVELENGTH(MICRONS)
FIGURE 1R-8C
ALUMINUM OXIDE FILM. T=700A
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1R-8

Levy (Ref. 1R-10)


The relative reflectance of pelletized spinel alumina powder was measured on a Beckman IR-5 infrared spectrometer. The position and shape of the reflection maximum were found to be independent of pelletizing pressure or time and of the angle of incidence. No bandpass or error analysis data were given. Data points were digitized from a line.

These data are in generally good agreement with the representative curve given in Section I - 1.6. except for the peak shown at 11μ.

λ	R	λ	R	λ	R
[illegible]	[illegible]	10.301	3.727E+00	10.370	3.588E+00
[illegible]	[illegible]	10.390	[illegible]	10.402	7.568E+00
[illegible]	[illegible]	10.429	[illegible]	10.435	1.362E+01
[illegible]	[illegible]	10.447	[illegible]	10.453	1.917E+01
[illegible]	[illegible]	10.463	[illegible]	10.468	2.410E+01
[illegible]	[illegible]	10.484	[illegible]	10.490	3.094E+01
[illegible]	[illegible]	10.499	[illegible]	10.508	4.055E+01
[illegible]	[illegible]	10.523	[illegible]	10.539	5.559E+01
[illegible]	[illegible]	10.561	[illegible]	10.567	6.799E+01
[illegible]	[illegible]	10.583	[illegible]	10.599	8.095E+01
[illegible]	[illegible]	10.630	[illegible]	10.633	9.370E+01
[illegible]	[illegible]	10.650	[illegible]	10.664	9.995E+01
[illegible]	[illegible]	10.681	[illegible]	10.697	1.081E+02
[illegible]	[illegible]	10.714	[illegible]	10.720	1.126E+02
[illegible]	[illegible]	10.753	[illegible]	10.762	1.160E+02
[illegible]	[illegible]	10.797	[illegible]	10.800	1.176E+02
[illegible]	[illegible]	10.820	[illegible]	10.842	1.154E+02
[illegible]	[illegible]	10.885	[illegible]	10.893	1.118E+02
[illegible]	[illegible]	10.907	[illegible]	10.929	1.092E+02
[illegible]	[illegible]	10.946	[illegible]	10.955	1.078E+02
[illegible]	[illegible]	10.980	[illegible]	10.988	1.064E+02
[illegible]	[illegible]	11.012	[illegible]	11.033	1.025E+02
[illegible]	[illegible]	11.056	[illegible]	11.060	1.013E+02
[illegible]	[illegible]	11.079	[illegible]	11.087	1.004E+02
[illegible]	[illegible]	11.116	[illegible]	11.130	9.927E+01
[illegible]	[illegible]	11.147	[illegible]	11.158	9.836E+01
[illegible]	[illegible]	11.186	[illegible]	11.181	9.643E+01
[illegible]	[illegible]	11.203	[illegible]	11.217	9.537E+01
[illegible]	[illegible]	11.230	[illegible]	11.241	9.494E+01
[illegible]	[illegible]	11.274	[illegible]	11.282	9.484E+01
[illegible]	[illegible]	11.296	[illegible]	11.309	9.372E+01

Levy (Ref. 1R-10) Continued

λ	R	λ	R	λ	R
11.324	9.34[illegible]	11.339	9.35[illegible]	11.347	9.370E+01
11.328	9.[illegible]32E+01	11.372	9.378E+01	11.333	9.345E+01
11.333	9.32[illegible]	11.[illegible]	9.29[illegible]	11.411	9.321E+01
11.423	9.31[illegible]	11.429	9.27[illegible]	11.438	9.185E+01
11.468	9.2[illegible]	11.467	9.181E+01	11.473	9.140E+01
11.492	9.177E+01	11.495	9.121E+01	11.505	9.132E+01
11.511	9.1[illegible]	11.522	9.132E+01	11.536	9.101E+01
11.529	9.1[illegible]	11.573	9.111E+01	11.595	9.075E+01
11.58[illegible]	9.[illegible]1				



REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0.0
.5
1.0
1.5
2.0
2.5
3.0
3.5
4.0
4.5
5.0
FIGURE 1R-10
PELLETIZED SPINEL ALUMINA POWDER
T=300 K
LEVY, J. CATALYSIS 9, 87 (1967)
REF. 1R-10


McCarthy (Ref. 1R-11)

A Beckman 1R-5A spectrometer in the 2μ to 6μ region and a Beckman 1R-7 with Cs I optics in the 12.5μ to 50μ region were used to measure the reflectance of 2 mm thick synthetic sapphire. No bandpass or error information was given. The sample temperature is unspecified and may be assumed to be approximately 300°K. These data were digitized from a line.

These data are in generally good agreement with the representative curve given in Section I-1.6.

λ	R	λ	R	λ	R	λ	R
2.000	9.14[illegible]E+00	2.951	8.[illegible]E+00	3.[illegible]	4.[illegible]E+00	[illegible].898	9.139E+00
[illegible].332	[illegible].[illegible]E+00	[illegible].[illegible]	[illegible].[illegible]E+00	5.044	6.328E+00	[illegible].378	5.519E+00
[illegible].[illegible]	[illegible].381[illegible]E+00	6.[illegible]	[illegible].718[illegible]E+00	[illegible].387	[illegible].347E+00	[illegible].364	3.116E+00
9.[illegible]	1.914[illegible]E+00	9.[illegible]94	7.[illegible]E+01	9.895	1.231E+00	10.036	2.685E+00
10.[illegible]	[illegible].99[illegible]E+00	10.108	1.[illegible]E+01	10.225	1.753E+01	10.[illegible]	2.510E+01
10.[illegible]	[illegible].281E+01	11.043	3.900[illegible]E+01	11.485	4.555E+01	11.[illegible]01	4.329E+01
12.[illegible]	[illegible].[illegible]E+01	12.[illegible]	3.[illegible]E+01	12.466	3.243E+01	12.661	3.039E+01
13.[illegible]	[illegible].[illegible]E+01	13.11[illegible]	3.[illegible]E+01	13.32[illegible]	[illegible].070E+01	13.[illegible]03	[illegible].625E+01
13.[illegible]	[illegible].[illegible]E+01	13.[illegible]	[illegible].[illegible]E+01	13.9[illegible]	[illegible].[illegible]E+01	14.213	[illegible].533E+01
14.[illegible]	[illegible].[illegible]E+01	14.[illegible]	4.613[illegible]E+01	15.280	[illegible].312E+01	15.585	4.112E+01
15.[illegible]	[illegible].[illegible]E+01	15.126	[illegible].[illegible]E+01	16.[illegible]	[illegible].110E+01	16.902	[illegible].[illegible]E+01
17.[illegible]	[illegible].[illegible]E+01	17.[illegible]	5.[illegible]E+01	17.830	5.346E+01	18.[illegible]	5.552E+01
18.[illegible]	[illegible].[illegible]E+01	18.[illegible]	[illegible].[illegible]E+01	19.23[illegible]	[illegible].[illegible]E+01	19.6[illegible]	5.315E+01
20.[illegible]	[illegible].13[illegible]E+01	20.[illegible]	[illegible].[illegible]E+01	21.18[illegible]	[illegible].[illegible]E+01	21.9[illegible]	[illegible].188E+01
22.[illegible]	[illegible].[illegible]E+01	23.[illegible]	3.[illegible]E+01	24.772	3.281E+01	25.[illegible]	3.105E+01
28.[illegible]	2.931[illegible]E+01	28.[illegible]	2.[illegible]E+01	29.672	2.042E+01	31.[illegible]	2.495E+01
33.[illegible]	2.29[illegible]E+01	34.[illegible]	2.[illegible]E+01	35.914	2.150E+01	[illegible].[illegible]	2.135E+01
40.[illegible]	2.14[illegible]E+01	40.[illegible]	2.16[illegible]E+01	42.382	2.17[illegible]E+01	44.21[illegible]	2.216E+01
[illegible].127	2.19[illegible]E+01	[illegible].[illegible]	2.[illegible]E+01	46.912	2.377[illegible]E+01	[illegible].[illegible]	2.541E+01
43.[illegible]	2.79[illegible]E+01	[illegible].[illegible]	[illegible].[illegible]E+01	49.628	3.298[illegible]E+01	[illegible].941	3.[illegible]1E+01


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-11
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 2, 591 (1963)
REF. 1R-11
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-11
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 2, 591 (1963)
REF. 1R-11
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


McCarthy (Ref. 1R-12)

Beckman 1R-5A, 1R-7, and 1R-9 spectrometers were used with a fixed angle specular reflection attachment to measure the reflectance of 3.0 mm thick sapphire from 2μ to 50μ. All sample surfaces were flat to ten fringes or better. No attempt was made to measure back surface reflectance contributions. No bandpass or error information was given. The sample temperature is unspecified and may be assumed to be approximately 300°K. These data were digitized from a line.

These data are in generally good agreement with the representative curve given in Section I-1.6.

λ	R	λ	R	λ	R	λ	R
2.004	9.890E+00	4.332	9.830E+00	6.713	9.405E+00	8.451	7.152E+00
5.377	9.757E+00	7.361	9.255E+00	8.333	1.315E+00	8.929	9.390E-02
10.417	9.390E-02	10.611	8.438E+00	10.789	1.838E+01	10.915	2.806E+01
11.044	3.900E+01	11.189	9.933E+01	11.336	9.894E+01	11.478	6.949E+01
11.983	7.899E+01	11.783	8.186E+01	11.789	8.416E+01	11.983	8.588E+01
12.421	8.705E+01	12.887	8.389E+01	13.263	9.059E+01	13.551	9.180E+01
13.939	9.232E+01	14.121	9.223E+01	14.499	9.281E+01	14.798	9.134E+01
15.385	8.788E+01	15.393	8.563E+01	15.614	8.019E+01	15.963	8.223E+01
16.349	7.982E+01	16.892	6.353E+01	17.590	5.875E+01	18.153	4.905E+01
18.715	3.997E+01	19.197	2.961E+01	19.530	3.436E+01	19.731	4.092E+01
19.956	4.799E+01	20.[illegible]	4.[illegible]E+01	20.[illegible]	4.291E+01	20.562	4.414E+01
20.555	6.109E+01	[illegible]	6.[illegible]E+01	20.911	7.135E+01	21.[illegible]	7.896E+01
21.211	8.312E+01	[illegible]	[illegible]E+01	[illegible]	[illegible]E+01	21.693	8.763E+01
21.911	8.599E+01	[illegible]	[illegible]E+01	22.584	8.127E+01	22.761	7.850E+01
22.933	7.[illegible]E+01	[illegible]	7.[illegible]E+01	23.339	7.044E+01	23.636	6.80[illegible]E+01
23.919	6.[illegible]E+01	24.113	5.[illegible]E+01	24.330	5.849E+01	24.[illegible]	5.7[illegible]E+01
24.727	5.[illegible]E+01	[illegible]	[illegible]E+01	25.200	5.323E+01	[illegible]	[illegible]E+01
25.705	5.[illegible]E+01	[illegible]	[illegible]E+01	26.455	5.[illegible]E+01	26.639	5.356E+01
26.973	5.[illegible]E+01	27.238	5.[illegible]E+01	27.430	5.462E+01	27.562	5.353E+01
27.[illegible]	5.[illegible]E+01	28.149	5.[illegible]E+01	28.[illegible]	5.[illegible]E+01	28.[illegible]	5.[illegible]E+01
29.261	5.392E+01	30.[illegible]	5.[illegible]E+01	30.[illegible]	5.[illegible]E+01	32.992	5.[illegible]E+01
33.[illegible]	5.[illegible]E+01	34.[illegible]	5.[illegible]E+01	34.598	5.538E+01	40.936	5.543E+01
41.535	5.[illegible]E+01	-1.933	5.[illegible]E+01	44.250	5.410E+01	46.001	5.333E+01
48.132	5.[illegible]E+01	49.615	5.253E+01				


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-12
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 4, 317 (1965)
REF. 1R-12


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-12
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 4, 317 (1965)
REF. 1R-12


Piriou (Ref. IR-15)


A grating spectrometer with unspecified bandpass was used to measure the reflectivity of sapphire (α - Al_2O_3) at T = 293°K and 1773°K. Temperatures were measured by pyrometer to a precision of better than 2 percent. No error analysis was given. Data were digitized from curves.

These data are in generally good agreement with the representative curve given in Section I-1.6.

a. T = 293°K

λ	R	λ	R	λ	R
33.246	3.338E+01	30.924	3.490E+01	28.954	3.748E+01
32.527	4.067E+01	26.788	4.351E+01	26.462	4.661E+01
26.161	5.023E+01	26.044	5.377E+01	25.858	5.088E+01
25.798	4.189E+01	25.757	3.475E+01	25.635	3.229E+01
25.480	3.475E+01	25.310	3.773E+01	24.953	4.125E+01
24.605	4.528E+01	24.201	4.389E+01	23.848	5.268E+01
23.610	5.558E+01	23.385	5.955E+01	23.171	6.460E+01
23.044	6.871E+01	22.926	7.403E+01	22.843	7.996E+01
22.737	8.598E+01	22.676	8.943E+01	22.498	9.163E+01
22.313	9.318E+01	22.057	9.377E+01	21.891	9.397E+01
21.753	9.357E+01	21.525	9.273E+01	21.374	9.128E+01
21.242	8.944E+01	21.150	8.710E+01	21.101	8.563E+01
21.036	8.332E+01	20.990	7.707E+01	20.946	7.241E+01
20.909	6.615E+01	20.846	5.932E+01	20.808	5.168E+01
20.777	4.529E+01	20.763	3.680E+01	20.763	2.792E+01
20.749	1.909E+01	20.709	1.120E+01	20.667	8.110E+00
20.577	5.633E+00	20.483	8.755E+00	20.299	1.384E+01
20.165	1.779E+01	19.950	2.172E+01	19.748	2.618E+01
19.558	3.024E+01	19.226	3.558E+01	18.970	3.925E+01
18.687	4.390E+01	18.442	4.836E+01	18.226	5.395E+01
18.038	5.895E+01	17.846	6.421E+01	17.745	6.969E+01
17.562	7.460E+01	17.591	7.925E+01	17.550	8.502E+01
17.528	8.764E+01	17.422	8.761E+01	17.316	9.143E+01
17.139	9.257E+01	16.908	9.346E+01	16.737	9.371E+01
16.524	9.275E+01	16.370	9.134E+01	16.235	8.915E+01
16.136	8.654E+01	16.069	8.343E+01	16.035	8.011E+01
15.987	7.460E+01	15.969	6.979E+01	15.928	6.401E+01
15.843	5.610E+01	15.826	6.212E+01	15.766	7.091E+01
15.717	7.858E+01	15.689	8.556E+01	15.653	9.202E+01
15.566	9.394E+01	15.397	9.475E+01	15.180	9.518E+01
14.981	9.483E+01	14.630	9.462E+01	14.295	9.432E+01
13.892	9.374E+01	13.593	9.321E+01	13.298	9.184E+01
13.061	9.055E+01	12.762	8.900E+01	12.509	8.781E+01
12.313	8.642E+01	12.079	8.499E+01	11.865	8.280E+01
11.717	8.076E+01	11.604	7.848E+01	11.490	7.512E+01
11.395	7.185E+01	11.309	6.799E+01	11.216	6.394E+01


REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-15A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1R-15



REFLECTIVITY OF ALUMINUM OXIDE
REFLECTIVITY
WAVELENGTH(MICRONS)
FIGURE 1R-15A
SAPPHIRE
T=293 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1R-15


a. Continued

λ	R	λ	R	λ	R
11.175	6.117E+01	11.119	5.742E+01	11.084	5.306E+01
11.058	4.765E+01	11.032	4.379E+01	11.005	3.773E+01
10.967	3.257E+01	10.916	2.714E+01	10.871	2.144E+01
10.817	1.693E+01	10.778	1.363E+01	10.688	9.812E+00
10.591	7.086E+00	10.467	4.592E+00	10.294	2.114E+00
10.126	9.580E-01	9.983	3.964E-01	9.654	4.295E-01
9.378	8.259E-01	9.195	9.415E-01		

b. T = 1773°K

λ	R	λ	R	λ	R
33.209	3.647E+01	30.905	3.864E+01	29.505	4.093E+01
28.844	4.257E+01	28.045	4.539E+01	27.607	4.623E+01
27.333	4.648E+01	27.128	4.597E+01	27.089	4.481E+01
26.921	4.438E+01	26.704	4.483E+01	26.283	4.698E+01
25.497	5.164E+01	24.729	5.750E+01	24.376	6.165E+01
24.251	6.259E+01	23.870	6.424E+01	23.607	6.442E+01
23.399	6.391E+01	23.174	6.343E+01	23.111	6.241E+01
22.819	5.677E+01	22.605	5.033E+01	22.385	4.352E+01
22.176	3.769E+01	21.987	3.092E+01	21.904	2.785E+01
21.797	2.626E+01	21.623	2.536E+01	21.431	2.577E+01
21.224	2.638E+01	20.723	3.229E+01	20.213	3.870E+01
19.756	4.572E+01	19.372	5.246E+01	19.001	6.003E+01
18.717	6.485E+01	18.447	6.928E+01	18.359	7.033E+01
18.090	7.218E+01	17.931	7.344E+01	17.764	7.382E+01
17.645	7.377E+01	17.429	7.359E+01	17.172	7.316E+01
16.982	7.342E+01	16.693	7.460E+01	16.387	7.722E+01
16.131	7.841E+01	15.958	7.868E+01	15.715	7.788E+01
15.559	7.762E+01	15.226	7.638E+01	14.656	7.384E+01
14.095	7.098E+01	13.622	6.807E+01	13.165	6.508E+01
12.821	6.117E+01	12.565	5.819E+01	12.468	5.611E+01
12.392	5.492E+01	12.249	5.099E+01	12.085	4.529E+01
11.884	3.885E+01	11.745	3.327E+01	11.586	2.719E+01
11.426	2.030E+01	11.273	1.444E+01	11.082	8.044E+00
10.841	4.047E+00	10.625	2.296E+00	10.550	1.767E+00
10.281	5.781E-01	10.076	7.433E-01	9.868	5.286E-01
9.469	4.130E-01	9.151	4.460E-01		



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-15B
SAPPHIRE T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1R-15
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-15B
SAPPHIRE T=1773 K
PIRIOU. REV. HAUTES TEMPER. ET RE
FRACT. 3. 109 (1966)
REF. 1R-15
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Salama (Ref. 1R-17)

RF-sputtered aluminum oxide films on silicon, with densities ranging from 3.1 to 3.8 g/cm^3 and thickness $\leq$ 5000 Å, were studied. No experimental details on the measurement of the relative reflectance were given. These data were digitized from lines.

λ	R	λ	R	λ	R
6.557	2.973E+01	6.921	3.126E+01	7.163	3.275E+01
7.092	3.397E+01	7.688	3.557E+01	7.811	3.541E+01
7.913	3.579E+01	8.141	3.557E+01	8.392	3.712E+01
8.227	3.684E+01	8.748	3.737E+01	8.993	3.785E+01
9.259	3.852E+01	9.523	3.828E+01	9.727	3.847E+01
9.929	3.847E+01	10.246	3.970E+01	10.349	3.867E+01
10.572	3.927E+01	10.873	4.011E+01	11.234	4.274E+01
11.433	4.412E+01	11.839	4.630E+01	12.177	4.835E+01
12.332	5.112E+01	12.991	5.380E+01	13.359	5.590E+01
13.659	5.655E+01	13.966	5.850E+01	14.198	5.721E+01
14.775	5.753E+01	15.130	5.721E+01	15.455	5.698E+01
15.970	5.807E+01	16.677	5.717E+01	16.525	5.367E+01
17.059	5.273E+01	17.030	5.194E+01	18.323	5.080E+01
18.054	5.038E+01	18.854	4.927E+01	19.231	4.838E+01
19.554	4.757E+01	19.733	4.655E+01	20.258	4.591E+01
20.979	4.428E+01	21.273	4.373E+01	22.428	4.317E+01
23.173	4.181E+01	23.791	4.054E+01	24.341	4.005E+01
25.204	3.977E+01	25.886	3.928E+01	26.383	3.871E+01
27.333	3.831E+01	28.827	3.791E+01	29.834	3.738E+01
32.359	3.722E+01				


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-17
ALUMINUM OXIDE FILM
T=300 K
SALAMA. J. ELECTROCHEM. SOC. 117. 913
(1970)
REF. 1R-17
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-17
ALUMINUM OXIDE FILM
T=300 K
SALAMA. J. ELECTROCHEM. SOC. 117. 913
(1970)
REF. 1R-17
REFLECTIVITY
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Tipunin (Ref. 1R-18)

The reflectivity of pure corundum from 2μ to 25μ with the optic axis perpendicular to the crystal reflecting surface was studied. Experimental details and error estimates were not given. The data were ditigized from a line.

These data were selected in part to construct the reflectivity spectrum of corundum given in Section I, Figure I-1.6.

λ	R	λ	R	λ	R
24.602	4.138E+01	23.894	4.931E+01	23.373	5.653E+01
22.948	[illegible]378E+01	22.520	7.070E+01	22.091	7.762E+01
21.799	8.322E+01	21.560	8.838E+01	21.283	9.221E+01
21.067	9.095E+01	20.862	8.491E+01	20.673	8.062E+01
20.614	7.352E+01	20.614	6.202E+01	20.614	4.577E+01
20.614	2.991E+01	20.614	1.693E+01	20.543	1.377E+01
20.380	1.137E+01	20.214	1.287E+01	19.849	2.009E+01
19.456	2.751E+01	18.928	3.640E+01	18.454	4.363E+01
18.024	5.116E+01	17.587	5.999E+01	17.238	6.789E+01
16.831	7.512E+01	16.406	8.28JE+01	16.174	8.770E+01
15.984	8.934E+01	15.890	8.798E+01	15.821	8.279E+01
15.754	7.812E+01	15.693	7.557E+01	15.602	7.677E+01
15.458	8.073E+01	15.265	8.532E+01	15.046	8.938E+01
14.816	9.259E+01	14.627	9.443E+01	14.403	9.552E+01
14.092	9.583E+01	13.791	9.583E+01	13.376	9.582E+01
13.033	9.506E+01	12.715	9.426E+01	12.362	9.374E+01
11.955	9.305E+01	11.637	9.211E+01	11.410	9.103E+01
11.220	8.944E+01	11.130	8.798E+01	11.055	8.564E+01
10.991	8.142E+01	10.904	7.479E+01	10.831	6.558E+01
10.758	5.556E+01	10.668	4.512E+01	10.612	3.371E+01
10.538	2.401E+01	10.454	1.496E+01	10.347	8.571E+00
10.273	5.623E+00	10.172	3.117E+00	10.057	1.675E+00
9.941	1.159E+00	9.794	1.286E+00	9.441	2.377E+00
9.102	3.260E+00	8.758	4.065E+00	8.467	5.429E+00
8.173	6.208E+00	8.074	6.831E+00		


REFLECTIVITY OF ALUMINUM OXIDE
FIGURE 1R-18
CORUNDUM
T=300 K
TIPUNIN, OPT. SPECTROSC. 31, 845 (1971)
REF. 1R-18
REFLECTIVITY
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

III-1.6 Tabulated Transmittance Data-Aluminum Oxide

Contents:

1T-1: Dorsey; α, γ, and pseudo γ alumina powders, $T \tilde{=} 300^{\circ}K$.

1T-3: Gillespie; Linde sapphire, $T = 298^{\circ}K$ to $673^{\circ}K$.

1T-4: Grimm; synthetic sapphire and G.E. Lucalox, $T \tilde{=} 300^{\circ}K$.

1T-6: Harris; aluminum oxide films, $\lambda = 14\mu$ to 90μ.

1T-8: Lee; sapphire, $T = 297^{\circ}K$ to $1473^{\circ}K$.

1T-9: Loewenstein; sapphire, $T \sim 300^{\circ}K$.

1T-10: Marshall; sapphire, $T \sim 300^{\circ}K$.

1T-11: McAlister; sapphire, $T = 673^{\circ}K$, $873^{\circ}K$, $1073^{\circ}K$.

1T-12: McCarthy; sapphire, $T \tilde{=} 300^{\circ}K$.

1T-13: McCarthy; sapphire, $T \tilde{=} 300^{\circ}K$.

1T-15: Mitsuishi; powdered α - Al_2O_3, $T \tilde{=} 300^{\circ}K$.

1T-16: Olt; sapphire, $T = 773^{\circ}K$.

1T-17: Oppenheim; sapphire, $T = 293^{\circ}K$ to $1273^{\circ}K$.

1T-19: Piriou; sapphire, $T = 77^{\circ}K$ and $273^{\circ}K$.

1T-20: Roberts; sapphire, $T \tilde{=} 300^{\circ}K$.

1T-22: White; α - Al_2O_3 powder, $T \tilde{=} 300^{\circ}K$.


Dorsey (Ref. 1T-1)


Alpha, g: m na, and pseudogamma alumina powders were studied using a Beckman IR-7 and an IR-11 spectrophotometer. No error analysis was given. Powders were incorporated into KBr pellets or polyethylene sheets. Data were taken from curves.


These data were selected in part for the representative curve, Figure I - 1.6d of Section I - 1.6.

a. $\alpha - Al_2O_3$

λ	T	λ	T	λ	T
14.337	3.553E+01	14.517	3.609E+01	14.940	3.648E+01
15.209	3.560E+01	15.376	3.315E+01	15.585	3.009E+01
15.747	2.757E+01	15.873	2.676E+01	16.037	2.922E+01
16.105	3.280E+01	16.315	3.609E+01	16.503	3.280E+01
16.522	2.448E+01	16.522	2.073E+01	16.773	1.638E+01
16.995	1.547E+01	17.190	1.733E+01	17.430	2.778E+01
17.571	3.690E+01	17.837	4.532E+01	18.123	5.058E+01
18.361	5.658E+01	18.677	6.415E+01	18.899	7.222E+01
19.189	7.745E+01	19.476	7.450E+01	19.723	6.955E+01
20.033	6.411E+01	20.209	6.096E+01	20.440	6.391E+01
20.985	6.552E+01	21.464	6.342E+01	21.447	5.342E+01
21.523	4.584E+01	21.601	3.048E+01	21.990	2.255E+01
22.402	2.775E+01	22.712	3.567E+01	23.040	4.434E+01
23.416	5.272E+01	23.933	6.065E+01	24.931	7.204E+01
25.496	6.832E+01	25.678	6.352E+01	25.875	5.791E+01
26.362	6.356E+01	26.981	6.889E+01	27.967	7.555E+01
28.651	7.815E+01	29.874	7.860E+01	62.488	7.934E+01
110.282	8.031E+01	153.163	8.032E+01	212.658	8.029E+01
258.916	8.043E+01				


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1A
ALPHA ALUMINA POWDER
T=300 K
DORSEY. ANAL. CHEM. 40. 971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1A
ALPHA ALUMINA POWDER
T=300 K
DORSEY. ANAL. CHEM. 40. 971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1A
ALPHA ALUMINA POWDER
T=300 K
DORSEY, ANAL. CHEM. 40. 971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.


Dorsey (1T-1)


b. γ - Al_2O_3

λ	T	λ	T	λ	T
12.586	4.078E+01	12.854	3.949E+01	13.032	3.881E+01
13.238	3.855E+01	13.485	3.938E+01	13.948	4.068E+01
14.274	4.118E+01	14.558	4.240E+01	15.029	4.179E+01
15.315	4.057E+01	15.951	3.877E+01	16.297	3.751E+01
16.735	3.748E+01	17.022	3.644E+01	17.314	3.428E+01
17.553	3.284E+01	17.745	3.230E+01	18.130	3.478E+01
18.799	3.931E+01	19.507	4.430E+01	20.069	4.851E+01
20.650	5.210E+01	21.142	5.541E+01	21.587	5.663E+01
22.311	5.810E+01	23.195	6.008E+01	23.455	6.148E+01
23.993	6.315E+01	24.913	6.378E+01	25.289	6.249E+01
25.644	6.040E+01	26.408	6.011E+01	27.396	5.950E+01
28.435	6.076E+01	31.242	6.353E+01	35.102	6.694E+01
40.322	7.037E+01	47.569	7.323E+01	59.395	7.668E+01
74.045	7.844E+01	84.357	8.056E+01	100.995	8.261E+01
127.353	8.354E+01	140.144	8.415E+01	162.553	8.419E+01
202.118	8.412E+01	226.230	8.390E+01	255.377	8.354E+01
288.641	8.300E+01				

c. Pseudo-γ - Al_2O_3

λ	T	λ	T	λ	T
12.571	3.165E+01	12.760	3.055E+01	12.980	3.000E+01
13.261	3.013E+01	13.607	3.127E+01	14.088	3.200E+01
14.275	3.238E+01	14.911	3.165E+01	15.389	3.051E+01
15.748	2.886E+01	15.947	2.661E+01	16.221	2.406E+01
16.527	2.330E+01	16.827	2.292E+01	17.383	2.496E+01
17.982	2.655E+01	18.595	2.927E+01	19.633	3.324E+01
20.520	3.718E+01	21.445	4.135E+01	22.603	4.536E+01
23.294	4.781E+01	24.106	4.991E+01	24.790	4.953E+01
24.855	4.978E+01	25.382	4.867E+01	25.656	4.846E+01
26.397	4.953E+01	27.293	5.033E+01	27.987	5.216E+01
28.800	5.399E+01	30.007	5.450E+01	30.864	5.547E+01
32.651	5.744E+01	34.640	5.996E+01	37.909	6.300E+01
41.021	6.565E+01	45.327	6.807E+01	50.670	6.976E+01
56.282	7.153E+01	63.905	7.325E+01	71.925	7.421E+01
75.500	7.508E+01	82.332	7.625E+01	88.677	7.739E+01
97.104	7.763E+01	110.820	7.808E+01	127.889	7.794E+01
140.355	7.770E+01	161.808	7.742E+01	184.966	7.677E+01
222.965	7.715E+01	291.221	7.660E+01		


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1B
GAMMA ALUMINA POWDER
T=300 K
DORSEY, ANAL. CHEM. 40, 971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1B
GAMMA ALUMINA POWDER
T=300 K
DORSEY, ANAL. CHEM. 40, 971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.




FIGURE 1T-1B
GAMMA ALUMINA POWDER
T=300 K
DORSEY, ANAL. CHEM. 40, 971 (1968)
REF. 1T-1






FIGURE 1T-1C
PSEUDOGAMMA ALUMINA POWDER
T=300 K
DORSEY, ANAL. CHEM. 40, 971 (1968)
REF. 1T-1


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1C
PSEUDOGAMMA ALUMINA POWDER
T=300 K
DORSEY. ANAL. CHEM. 40.971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-1C
PSEUDOGAMMA ALUMINA POWDER
T=300 K
DORSEY. ANAL. CHEM. 40.971 (1968)
REF. 1T-1
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.

Gillespie (Ref. 1T-3)

The transmittance of Linde sapphire was measured over a temperature range of 298°K to 673°K, from 2μ to 8μ. A Perkin-Elmer 21 spectrophotometer with NaCl optics was used. No bandpass or error information was given. Data were digitized from curves.


These data agree generally with the representative curve given in Section I - 1.6.


a. T = 298°K

λ	T	λ	T	λ	T	λ	T
2.031	85.651	2.507	85.411	2.391	85.451	3.492	85.281
3.982	83.511	4.234	84.920	4.411	82.936	4.545	80.752
4.054	78.293	4.788	74.992	4.895	71.538	4.975	68.595
5.7	65.038	5.1	61.247	5.254	57.022	5.342	52.684
5.435	48.721	5.483	45.519	5.570	41.455	5.655	37.355
5.737	32.167	5.854	27.572	5.970	21.770	6.045	17.389
6.144	11.423	6.250	6.721	6.428	4.182	6.593	3.182
6.751	2.035	6.910	1.163	7.061	.806	7.266	.428
7.995	.092						

b. T = 373°K

λ	T	λ	T	λ	T	λ	T
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	3.496	85.230
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-3A
SAPPHIRE
T=298 K
GILLESPIE. NAVWEPS 8558 (1964)
REF. 1T-3
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-3B
SAPPHIRE
T=373 K
GILLESPIE. NAVWEPS 8558 (1964)
REF. 1T-3
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


Gillespie (Ref. 1T-3)


c. T = 473°K


d. T = 573°K

e. T = 673°K

Best Available Copy


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-3C
SAPPHIRE
T=473 K
GILLESPIE, NAVWEPS 8558 (1964)
REF. 1T-3
TRANSMITTANCE
WAVELENGTH(MICRONS)


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-3D
SAPPHIRE
T=573 K
GILLESPIE, NAVWEPS 8558 (1964)
REF. 1T-3
TRANSMITTANCE
WAVELENGTH(MICRONS)


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-3E
SAPPHIRE
T=673 K
GILLESPIE, NAVWEPS 8558 (1964)
REF. 1T-3
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


Grimm (Ref. 1T-4)

The transmittance of synthetic sapphire and General Electric Lucalox high density polycrystalline alumina with 0.2 percent MgO content, a density of 3.975 g/cm^3, and grain size of 27 $\pm$ 3μ was measured on a Perkin-Elmer 337 double beam spectrophotometer with an undisclosed bandpass. No error analysis or temperature was given. Data were digitized from a curve.

These data are in general agreement with the representative curve given in Section I - 1, 6.

a. Synthetic sapphire 6 mm thick, surface finish of < 5μ in.

λ	T	λ	T	λ	T	λ	T
3.[illegible]	73.349	3.000	73.221	3.095	73.328	3.352	73.397
3.598	73.424	3.917	73.403	4.134	73.339	4.299	73.221
[illegible]	72.891	4.585	72.251	4.685	71.766	4.780	71.215
[illegible]	[illegible].464	4.984	69.643	5.072	68.741	5.159	67.808
[illegible]	66.683	5.309	65.525	5.381	64.315	5.457	62.880
[illegible]	61.455	5.661	59.936	5.675	56.791	5.735	54.072
[illegible]	50.938	5.874	47.889	5.932	44.467	5.979	40.714
[illegible]	36.452	6.064	32.319	6.108	28.830	6.153	24.800
[illegible]	21.393	[illegible]	18.356	6.289	14.740	6.333	11.058
[illegible]	8.077	6.425	5.214	6.495	4.723	6.569	3.244
5.638	2.532						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-4A
SAPPHIRE, T=1.6 MM
T=300 K
GRIMM. CM. CERAM. SOC. BUL. 50, 962(1971)
REF. 1T-4
TRANSMITTANCE
100
90
80
70
60
50
40
30
20
10
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)


Grimm (Ref. 1T-4)


b. Lucalox alumina, 0.43 mm thick

λ	T	λ	T	λ	T	λ	T
3.000	6.884E+01	3.000	7.004E+01	3.000	7.106E+01	3.147	7.228E+01
3.331	7.341E+01	3.491	7.420E+01	3.676	7.549E+01	3.897	7.681E+01
4.053	7.751E+01	4.266	7.837E+01	4.464	7.905E+01	4.631	7.979E+01
4.840	7.981E+01	5.031	7.972E+01	5.193	7.912E+01	5.359	7.846E+01
5.506	7.729E+01	5.651	7.556E+01	5.781	7.382E+01	5.905	7.143E+01
6.009	6.876E+01	6.099	6.623E+01	6.180	6.256E+01	6.269	5.856E+01
6.345	5.401E+01	6.433	4.931E+01	6.491	4.426E+01	6.582	3.760E+01
6.666	3.217E+01	6.746	2.655E+01	6.826	2.207E+01	6.936	1.680E+01
7.063	1.148E+01	7.195	6.941E+00	7.321	3.890E+00	7.448	1.327E+00
7.479	1.373E-01						

c. Lucalox alumina, 1.5 mm thick

λ	T	λ	T	λ	T	λ	T
3.000	4.411E+01	3.000	4.608E+01	3.000	4.789E+01	3.000	4.996E+01
3.099	5.139E+01	3.256	5.223E+01	3.390	5.403E+01	3.522	5.550E+01
3.661	5.646E+01	3.811	5.805E+01	3.961	5.929E+01	4.096	6.034E+01
4.236	6.183E+01	4.374	6.286E+01	4.528	6.327E+01	4.660	6.322E+01
4.791	6.331E+01	4.932	6.324E+01	5.061	6.286E+01	5.200	6.163E+01
5.335	5.899E+01	5.450	5.634E+01	5.546	5.346E+01	5.640	5.002E+01
5.737	4.703E+01	5.841	4.304E+01	5.929	3.962E+01	5.997	3.609E+01
6.065	3.190E+01	6.127	2.747E+01	6.199	2.363E+01	6.270	1.942E+01
6.366	1.481E+01	6.411	1.124E+01	6.481	7.841E+00	6.556	4.699E+00
6.633	1.785E+00						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-4B
LULALOX ALUMINA. T= 0.43 MM
T=300 K
GRIMM. AM. CERAM. SOC. BUL. 50. 962(1971)
REF. 1T-4
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-4C
LUCALOX ALUMINA. T= 1.5 MM
T=300 K
GRIMM. AM. CERAM. SOC. BUL. 50. 962(1971)
REF. 1T-4
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Harris (Ref. 1T-6)

The transmittance of 50, 100, and 200 volt aluminum oxide films from 14μ to 90μ were measured using a grating spectrometer. No estimates of error were given. Data are digitized from lines.

The data for thin films are not comparable to the sapphire or bulk alumina data.

a. 50 volt film

λ	T	λ	T	λ	T	λ	T
9.403	8.757E+01	11.965	8.036E+01	14.090	8.944E+01	15.840	9.047E+01
10.201	9.116E+01	12.468	9.101E+01	22.007	9.221E+01	24.993	9.276E+01
20.945	9.319E+01	29.348	9.452E+01	30.826	9.498E+01	33.136	9.600E+01
32.369	9.763E+01	37.283	9.761E+01	39.018	9.790E+01	41.217	9.800E+01
43.211	9.832E+01	46.385	9.821E+01	49.213	9.861E+01	52.034	9.875E+01
56.014	9.879E+01	61.921	9.875E+01	69.018	9.890E+01	76.019	9.889E+01
84.303	9.856E+01	94.734	9.888E+01	95.364	9.901E+01	103.094	9.962E+01
118.135	9.917E+01	113.723	9.919E+01	118.372	9.918E+01		

b. 100 volt film

λ	T	λ	T	λ	T	λ	T
11.273	7.37 E+01	10.535	7.415E+01	12.505	7.491E+01	13.512	7.574E+01
14.501	7.852E+01	15.139	7.742E+01	15.824	7.858E+01	16.681	7.347E+01
17.923	8.025E+01	19.122	8.083E+01	20.696	8.133E+01	22.030	8.165E+01
23.153	8.197E+01	23.760	8.255E+01	24.584	8.332E+01	25.379	8.396E+01
26.049	8.448E+01	27.325	8.512E+01	26.536	8.561E+01	29.247	8.660E+01
30.066	8.714E+01	33.703	8.853E+01	31.763	8.995E+01	32.868	8.981E+01
34.103	9.001E+01	35.038	9.170E+01	36.942	9.257E+01	38.482	9.342E+01
39.206	9.429E+01	40.209	9.482E+01	40.985	9.537E+01	43.696	9.552E+01
40.233	9.577E+01	49.000	9.597E+01	53.045	9.615E+01	57.130	9.635E+01
61.233	9.693E+01	69.127	9.681E+01	58.538	9.700E+01	71.826	9.715E+01
74.909	9.739E+01	77.383	9.752E+01	81.632	9.754E+01	83.300	9.754E+01
86.495	9.752E+01	88.335	9.761E+01	90.734	9.774E+01	93.401	9.758E+01
90.201	9.733E+01						




FIGURE 1T-6A
50 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1T-6




FIGURE 1T-6A
50 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1T-6




FIGURE 1T-6A
50 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6






FIGURE 1T-6B
100 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.
0
10
20
30
40
50
60
70
80
90
100
FIGURE 1T-6B
100 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
0
10
20
30
40
50
60
70
80
90
100
FIGURE 1T-6B
100 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6

Harris (Ref. 1T-6)

c. 200 volt film

λ	T	λ	T	λ	T	λ	T
9.3[illegible]	[illegible]	[illegible]	[illegible]	12.762	[illegible]	14.004	6.158E+01
[illegible]	[illegible]	17.302	[illegible]	19.4[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	22.[illegible]	[illegible]	23.90[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	28.073	[illegible]	28.791	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	31.1[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	34.911	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]




FIGURE 1T-6C
200 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6





FIGURE 1T-6C
200 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS. J. OPT. SOC. 52. 223 (1962)
REF. 1T-6


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
FIGURE 1T-6C
200 VOLT ALUMINUM OXIDE FILM
T=300 K
HARRIS, J. OPT. SOC. 52, 223 (1962)
REF. 1T-6

Lee (Ref. 1T-8)

Sapphire samples 2 mm thick were examined using a Beckman IR-3 spectrophotometer having an unspecified bandpass, over a temperature range of 297°K to 1473°K. No error analysis was given. Data were digitized from curves.


These data are in general agreement with the representative curve given in Section I - 1.6.


a. T = 297°K

λ	T	λ	T	λ	T	λ	T
2.000	9.921E+01	2.155	9.921E+01	2.329	9.921E+01	2.494	9.921E+01
2.674	9.921E+01	2.867	9.921E+01	3.103	9.899E+01	3.441	9.872E+01
3.718	9.814E+01	3.950	9.731E+01	4.215	9.613E+01	4.421	9.431E+01
4.626	9.169E+01	4.754	8.904E+01	4.850	8.689E+01	4.934	8.420E+01
5.026	8.101E+01	5.119	7.748E+01	5.196	7.401E+01	5.271	7.012E+01
5.326	6.686E+01	5.365	6.406E+01	5.386	6.213E+01		

b. T = 573°K

λ	T	λ	T	λ	T	λ	T
2.000	9.921E+01	2.179	9.921E+01	2.364	9.921E+01	2.512	9.921E+01
2.701	9.921E+01	2.852	9.920E+01	3.100	9.900E+01	3.422	9.867E+01
3.698	9.803E+01	3.859	9.728E+01	3.981	9.630E+01	4.104	9.508E+01
4.253	9.309E+01	4.400	9.044E+01	4.514	8.789E+01	4.639	8.415E+01
4.768	7.973E+01	4.892	7.424E+01	4.981	6.909E+01	5.067	6.240E+01
5.145	5.516E+01	5.237	4.655E+01	5.298	4.072E+01	5.358	3.551E+01
5.411	2.974E+01						


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0
10
20
30
40
50
60
70
80
90
100
FIGURE 1T-8A
SAPPHIRE
T=297 K
LEE. J. AM. CERAM. SOC. 43, 594 (1960)
REF. 1T-8


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
0
10
20
30
40
50
60
70
80
90
100
FIGURE 1T-8B
SAPPHIRE
T=573 K
LEE. J. AM. CERAM. SOC. 43, 594 (1960)
REF. 1T-8


Lee (Ref. 1T-8)


c. $T = 873^{\circ}K$

λ	T	λ	T	λ	T	λ	T
2.000	9.909E+01	2.190	9.909E+01	2.347	9.909E+01	2.511	9.909E+01
2.708	9.909E+01	2.864	9.909E+01	3.041	9.909E+01	3.166	9.876E+01
3.308	9.829E+01	3.458	9.722E+01	3.646	9.524E+01	3.802	9.343E+01
3.920	9.128E+01	4.072	8.838E+01	4.238	8.417E+01	4.371	8.049E+01
4.518	7.519E+01	4.627	7.095E+01	4.731	6.530E+01	4.834	5.798E+01
4.921	5.030E+01	5.000	4.414E+01	5.091	3.760E+01	5.170	3.220E+01
5.255	2.757E+01	5.331	2.281E+01	5.394	1.950E+01		

d. $T = 1473^{\circ}K$

λ	T	λ	T	λ	T	λ	T
2.000	9.616E+01	2.096	9.741E+01	2.203	9.872E+01	2.280	9.924E+01
2.453	9.924E+01	2.620	9.924E+01	2.763	9.910E+01	2.891	9.906E+01
2.970	9.876E+01	3.077	9.805E+01	3.296	9.659E+01	3.482	9.470E+01
3.656	9.221E+01	3.833	8.930E+01	4.050	8.487E+01	4.217	8.084E+01
4.346	7.677E+01	4.466	7.139E+01	4.573	6.566E+01	4.693	5.923E+01
4.782	5.267E+01	4.862	4.660E+01	4.940	3.791E+01	5.027	3.007E+01
5.107	2.339E+01	5.191	1.724E+01	5.275	1.208E+01	5.347	8.743E+00


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1T-8C
SAPPHIRE
T=873 K
LEE. J. AM. CERAM. SOC. 43. 594 (1960)
REF. 1T-8


TRANSMITTANCE OF ALUMINUM OXIDE
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
FIGURE 1T-8D
SAPPHIRE
T=1473 K
LEE. J. AM. CERAM. SOC. 43. 594 (1960)
REF. 1T-8

Loewenstein (Ref. 1T-9)

The transmissivity of synthetic sapphire was measured in the far infrared using an interferometer. No experimental details or error analyses were given. The data were digitized from points.


These data are in good general agreement with the representative curve given in Section I - 1.6.


a. Optic axis unoriented

λ	T	λ	T	λ	T
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	[illegible]
1.318E+02	[illegible]	[illegible]	[illegible]	1.283E+02	3.351E+01

b. Optic axis parallel to face of sapphire sample

λ	T	λ	T	λ	T
9.729E+02	5.207E+01	8.270E+02	5.065E+01	7.126E+02	4.535E+01
6.223E+02	4.449E+01	5.569E+02	4.806E+01	5.023E+02	4.767E+01
[illegible]	5.700E+01	4.162E+02	5.700E+01	3.847E+02	5.617E+01
[illegible]	5.705E+01	3.337E+02	5.490E+01	3.117E+02	5.150E+01
[illegible]	5.771E+01	2.790E+02	5.005E+01	2.639E+02	[illegible]
2.501E+02	5.312E+01	2.382E+02	4.961E+01	2.270E+02	4.553E+01
[illegible]	4.460E+01	2.082E+02	[illegible]	1.997E+02	[illegible]
[illegible]	4.149E+01	1.855E+02	3.870E+01	1.785E+02	4.325E+01
[illegible]	3.699E+01	1.666E+02	3.537E+01	1.611E+02	3.801E+01
[illegible]	3.439E+01	1.514E+02	3.369E+01	1.472E+02	3.533E+01
[illegible]	3.202E+01	1.387E+02	3.253E+01	1.351E+02	3.460E+01
1.318E+02	2.973E+01	1.284E+02	2.621E+01		3.299E+01


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-9A
SAPPHIRE. UNORIENTED OPTIC AXIS
T=300 K
LOEWENSTEIN. J. OPT. SOC. 51. 108(1961)
REF. 1T-9
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
10
20
30
40
50
60
70
80
90
100



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-9B
SAPPHIRE. OPTIC AXIS PARALLEL TO
SAMPLE FACE
T=300 K
LOEWENSTEIN. J. OPT. SOC. 51. 108(1961)
REF. 1T-9
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
10
20
30
40
50
60
70
80
90

Marshall (Ref. 1T-10)

The transmissivity of sapphire from 6μ to 10μ was measured using unspecified methods. Sample thickness was approximately 150μ. No error analysis was given. Data were digitized from curves.

These data are in good general agreement with the representative curve given in Section I - 1.6.

λ	T	λ	T	λ	T
9.086	1.570E+00	8.962	1.981E+00	8.885	2.558E+00
8.849	3.405E+00	8.807	4.893E+00	8.777	5.693E+00
8.738	6.130E+00	8.688	9.485E+00	8.652	6.840E+00
8.624	7.673E+00	8.597	9.439E+00	8.554	1.119E+01
8.500	1.296E+01	8.445	1.479E+01	8.400	1.660E+01
8.344	1.843E+01	8.304	1.944E+01	8.276	1.959E+01
8.250	2.004E+01	8.228	2.084E+01	8.206	2.219E+01
8.182	2.299E+01	8.155	2.321E+01	8.135	2.285E+01
8.095	2.127E+01	8.053	1.981E+01	8.006	1.851E+01
7.959	1.791E+01	7.911	1.743E+01	7.874	1.748E+01
7.830	1.780E+01	7.790	1.837E+01	7.762	1.913E+01
7.737	2.046E+01	7.717	2.138E+01	7.693	2.204E+01
7.669	2.216E+01	7.638	2.197E+01	7.597	2.165E+01
7.567	2.155E+01	7.544	2.189E+01	7.513	2.295E+01
7.434	2.422E+01	7.444	2.675E+01	7.417	2.895E+01
7.391	3.113E+01	7.362	3.314E+01	7.339	3.455E+01
7.308	3.559E+01	7.275	3.642E+01	7.241	3.776E+01
7.214	3.901E+01	7.190	4.098E+01	7.174	4.295E+01
7.158	4.406E+01	7.137	4.502E+01	7.110	4.618E+01
7.085	4.706E+01	7.051	4.775E+01	7.010	4.842E+01
6.972	4.920E+01	6.938	5.032E+01	6.913	5.176E+01
6.889	5.438E+01	6.871	5.731E+01	6.855	6.014E+01
6.820	6.293E+01	6.791	6.411E+01	6.761	6.465E+01
6.729	6.500E+01	6.700	6.538E+01	6.684	6.593E+01
6.669	6.721E+01	6.642	7.019E+01	6.621	7.234E+01
6.592	7.410E+01	6.560	7.554E+01	6.528	7.657E+01
6.498	7.719E+01	6.470	7.733E+01	6.445	7.717E+01
6.417	7.697E+01	6.364	7.697E+01	6.366	7.702E+01
6.343	7.762E+01	6.322	7.841E+01	6.295	7.948E+01
6.272	8.000E+01	6.249	8.000E+01		


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-10
SAPPHIRE
T=300 K
MARSHALL, J. CHEM. PHYS. 43, 2893(1965)
REF. 1T-10
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

McAlister (Ref. 1T-11)

The transmittance of sapphire from 1μ to 6μ at temperatures of 673°K, 873°K, and 1073°K was measured using a Perkin-Elmer 112 spectrometer with NaCl optics. The precision of the transmittance data is estimated to be ± 1 percent. Data were digitized from curves.


These data are in good general agreement with the representative curve given in Section I - 1.6.


a) T = 673°K

λ	T	λ	T	λ	T	λ	T
1.713	8.965E+01	1.919	9.024E+01	2.052	9.079E+01	2.172	9.067E+01
2.319	9.077E+01	2.465	9.113E+01	2.613	9.145E+01	2.795	9.130E+01
2.959	9.105E+01	3.119	9.074E+01	3.281	9.031E+01	3.410	8.984E+01
3.552	8.870E+01	3.682	8.711E+01	3.783	8.610E+01	3.882	8.356E+01
3.979	8.114E+01	4.056	7.886E+01	4.126	7.589E+01	4.211	7.336E+01
4.291	6.944E+01	4.347	6.530E+01	4.418	6.156E+01	4.468	5.767E+01
4.546	5.341E+01	4.612	4.913E+01	4.664	4.630E+01	4.708	4.262E+01
4.748	3.911E+01	4.777	3.729E+01	4.832	3.486E+01	4.879	3.229E+01
4.936	2.935E+01	4.986	2.641E+01	5.050	2.338E+01	5.110	2.026E+01
5.181	1.739E+01	5.250	1.451E+01	5.319	1.222E+01	5.371	1.034E+01
5.406	8.616E+00	5.487	6.722E+00	5.562	4.815E+00	5.643	2.868E+00
5.708	1.907E+00						

b) T = 873°K

λ	T	λ	T	λ	T	λ	T
3.158	8.695E+01	3.261	8.513E+01	3.358	8.337E+01	3.437	8.172E+01
3.521	7.926E+01	3.581	7.660E+01	3.651	7.438E+01	3.726	7.120E+01
3.799	6.826E+01	3.862	6.547E+01	3.932	6.269E+01	3.991	5.971E+01
4.059	5.631E+01	4.130	5.299E+01	4.189	5.041E+01	4.245	4.692E+01
4.293	4.400E+01	4.359	4.132E+01	4.416	3.810E+01	4.499	3.419E+01
4.573	3.064E+01	4.645	2.741E+01	4.694	2.497E+01	4.744	2.185E+01
4.793	1.973E+01	4.855	1.569E+01	4.916	1.331E+01	4.981	1.131E+01
5.025	8.999E+00	5.095	7.103E+00	5.187	4.946E+00	5.288	3.381E+00



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-11A
SAPPHIRE. T=4 MM
T=673K
MCALISTER. PROC. IRIS 4. 139(1959)
REF. 1T-11
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-11B
SAPPHIRE. T=4 MM
T=873K
MCALISTER. PROC. IRIS 4. 139(1959)
REF. 1T-11
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

McAlister (Ref. 1T-11)

c) T = 1073°K

λ	T	λ	T	λ	T	λ	T
1.695	5.891E+01	1.852	8.933E+01	1.957	8.938E+01	2.044	8.888E+01
2.242	8.907E+01	2.435	8.933E+01	2.634	8.904E+01	2.814	8.919E+01
2.967	8.912E+01	3.061	8.885E+01	3.196	8.804E+01	3.302	8.730E+01
3.457	8.545E+01	3.516	8.344E+01	3.597	8.143E+01	3.578	7.916E+01
3.713	7.693E+01	3.824	7.452E+01	3.897	7.161E+01	3.968	6.826E+01
4.134	6.505E+01	4.104	6.176E+01	4.175	5.852E+01	4.230	5.589E+01
4.264	5.363E+01	4.318	5.091E+01	4.365	4.895E+01	4.422	4.571E+01
4.496	4.146E+01	4.569	3.816E+01	4.647	3.364E+01	4.709	3.014E+01
4.735	2.713E+01	4.823	2.377E+01	4.893	2.036E+01	4.965	1.739E+01
5.028	1.498E+01	5.071	1.277E+01	5.114	1.105E+01	5.161	8.998E+00
5.228	7.472E+00	5.303	6.025E+00	5.384	4.223E+01	5.443	3.091E+00
5.498	2.315E+00	5.571	1.026E+00				



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-11C
SAPPHIRE. T=4 MM
T=1073K
MCALISTER. PROC. IRIS 4. 13 959
REF. 1T-11
TRANSMITTANCE
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

McCarthy (Ref. 1T-12)

A Beckman 1R-5A spectrometer in the 2μ to 6μ region and a Beckman 1R-7 with Cs I optics in the 12.5μ to 50μ region were used to measure the transmittance of 2 mm thick synthetic sapphire. No bandpass or error information was given. The sample temperature is unspecified and may be assumed to be approximately 300°K. These data were digitized from a curve.

These data are in good agreement with the representative curve given in Section I - 1.6. except for the strong 2.5μ to 4.0μ band attributable to water.

λ	T	λ	T	λ	T	λ	T
[illegible]	[illegible]	2.362	[illegible]	2.503	8.456E+01	2.535	8.086E+01
[illegible]	[illegible]	[illegible]	[illegible]	2.563	5.349E+01	2.619	5.126E+01
[illegible]	[illegible]	[illegible]	[illegible]	2.772	2.736E+01	2.873	3.949E+01
[illegible]	[illegible]	[illegible]	[illegible]	3.424	7.436E+01	[illegible]	8.434E+01
[illegible]	[illegible]	[illegible]	[illegible]	4.031	3.714E+01	4.213	8.670E+01
[illegible]	[illegible]	[illegible]	[illegible]	5.193	5.765E+01	5.326	6.237E+01
[illegible]	[illegible]	[illegible]	[illegible]	5.503	3.054E+01	5.822	2.426E+01
[illegible]	[illegible]	[illegible]	[illegible]	6.218	5.430E+00	6.305	3.457E+00
[illegible]	[illegible]	[illegible]	[illegible]	6.839	4.006E-01		



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-12
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 2, 591 (1963)
REF. 1T-12
TRANSMITTANCE
100
90
80
70
60
50
40
30
20
10
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.
WAVELENGTH(MICRONS)

McCarthy (Ref. 1T-13)

Beckman 1R5-A, 1R-7, and 1R-9 spectrometers were used to measure the transmittance of 3.0 mm thick synthetic sapphire from 2μ to 50μ. All sample surfaces were flat to ten fringes or better. No bandpass or error information was given. The sample temperature is unspecified and may be assumed to be approximately 300°K. These data were digitized from a curve.

These data are in good general agreement with the representative curve given in Section I - 1.6.

λ	T	λ	T	λ	T	λ	T
2.000	8.35[illegible]E+01	3.704	8.844E+01	4.304	8.823E+01	4.567	8.669E+01
[illegible]	8.272E+01	[illegible]	[illegible]	5.290	6.522E+01	[illegible]	[illegible]
[illegible]	4.514E+01	5.882	[illegible]	6.149	2.259E+01	6.325	1.160E+01
[illegible]	[illegible]	6.553	3.912E+00	6.945	1.831E+00	[illegible]	7.825E-01
[illegible]	3.130E-01						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-13
SAPPHIRE
T=300 K
MCCARTHY, APP. OPT. 4. 317 (1965)
REF. 1T-13
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Mitsuishi (Ref. 1T-15)

Powdered α - Al_2O_3 suspended in a KBr disk and in a polyethylene sheet was studied from 17μ to 40μ using Hitachi EPI-2 Infrared Spectrometer with unspecified bandpass. No error analysis was given. Data were digitized from curves.

These data were selected in part to construct the representative curve given in Section I - 1.6.

a) Powdered Alpha Alumina in a KBr disc

λ	T	λ	T	λ	T	λ	T
17.981	5.081E+01	18.342	5.587E+01	18.645	6.144E+01	18.879	6.672E+01
19.209	7.193E+01	19.428	7.606E+01	19.561	7.877E+01	19.767	8.064E+01
19.861	8.009E+01	19.972	7.566E+01	20.087	7.186E+01	20.191	6.682E+01
20.282	6.335E+01	20.388	5.951E+01	20.484	5.845E+01	20.615	5.917E+01
20.655	6.015E+01	20.723	6.078E+01	20.838	6.008E+01	20.914	5.867E+01
20.964	5.593E+01	21.059	5.233E+01	21.121	4.994E+01	21.224	4.845E+01
21.353	4.854E+01	21.546	4.943E+01	21.624	5.008E+01	21.805	5.040E+01
21.888	5.009E+01	22.090	4.778E+01	22.255	4.422E+01	22.394	4.169E+01
22.491	4.059E+01	22.635	4.009E+01	22.832	4.112E+01	23.103	4.379E+01
23.392	4.737E+01	23.735	5.049E+01	23.954	5.269E+01	24.398	5.426E+01
24.652	5.466E+01	24.931	5.487E+01	25.131	5.587E+01	25.375	5.777E+01
25.565	6.032E+01	25.649	6.083E+01	25.792	6.009E+01	25.845	5.807E+01
25.944	5.590E+01	26.039	5.475E+01	26.142	5.581E+01	26.242	5.741E+01
26.415	5.922E+01	26.604	6.015E+01	26.979	6.182E+01	27.718	6.383E+01
28.462	6.551E+01	29.100	6.676E+01	29.850	6.831E+01	30.768	7.047E+01
31.595	7.242E+01	32.548	7.419E+01	33.505	7.540E+01	35.001	7.710E+01
35.993	7.850E+01	37.308	7.987E+01	38.447	8.068E+01	39.466	8.140E+01




FIGURE 1T-15A
POWDERED ALPHA ALUMINA IN KBR DISC
T=300 K
MITSUISHI. JAP. J. APP. PHYS. 1. 1(1962)
REF. 1T-15






FIGURE 1T-15B
POWDERED ALPHA ALUMINA IN KBR DISC
T=300 K
MITSUISHI. JAP. J. APP. PHYS. 1. 1(1962)
REF. 1T-15

Mitsuishi (Ref. 1T-15)

b. Powdered Alpha Alumina on Polyethylene

λ	T	λ	T	λ	T	λ	T
17.778	1.108E+01	18.269	1.695E+01	18.523	2.180E+01	18.797	2.873E+01
19.055	3.642E+01	19.225	4.322E+01	19.374	4.841E+01	19.472	5.403E+01
19.558	5.519E+01	19.674	5.439E+01	19.788	4.663E+01	19.934	3.767E+01
20.042	2.792E+01	20.160	2.108E+01	20.332	1.924E+01	20.480	1.970E+01
20.587	2.102E+01	20.748	2.025E+01	20.946	1.549E+01	20.997	1.186E+01
21.119	9.527E+00	21.183	8.523E+00	21.356	8.239E+00	21.594	8.655E+00
21.842	8.920E+00	22.032	8.258E+00	22.170	7.311E+00	22.278	5.511E+00
22.448	4.716E+00	22.581	4.451E+00	22.816	5.625E+00	23.179	8.542E+00
23.579	1.104E+01	24.012	1.362E+01	24.448	1.623E+01	24.806	1.877E+01
25.122	2.155E+01	25.367	2.504E+01	25.565	2.640E+01	25.743	2.595E+01
25.636	2.369E+01	25.904	2.153E+01	25.926	2.015E+01	26.048	1.883E+01
26.224	2.087E+01	26.443	2.337E+01	26.719	2.598E+01	27.035	2.869E+01
27.560	3.140E+01	28.285	3.477E+01	29.069	3.773E+01	29.922	4.035E+01
30.932	4.438E+01	32.062	4.778E+01	33.169	5.076E+01	34.382	5.388E+01
35.538	5.652E+01	36.836	5.860E+01	37.967	6.044E+01	38.857	6.229E+01
39.979	6.362E+01						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-15B
POWDERED ALPHA ALUMINA ON POLY ETHYLENE
T=300 K
MITSUISHI, JAP. J. APP. PHYS. 1, 1(1962)
REF. 1T-15
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-15B
POWDERED ALPHA ALUMINA ON POLY ETHYLENE
T=300 K
MITSUISHI, JAP. J. APP. PHYS. 1, 1(1962)
REF. 1T-15
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
5.
10.
15.
20.
25.
30.
35.
40.
45.
50.

Olt (Ref. 1T-[illegible])

The transmittance of 0.125 in thick sapphire is reported from 1μ to 6μ. Experimental details are unspecified. The sample temperature is 773°K. The data were digitized from a curve.

These data are in good general agreement with the representative curve given in Section I - 1.6.

λ	T	λ	T	λ	T	λ	T
1.000	8.012E+01	1.108	8.075E+01	1.351	8.220E+01	1.521	8.213E+01
1.655	8.210E+01	1.789	8.224E+01	1.917	8.281E+01	2.093	8.408E+01
2.172	8.457E+01	2.289	8.486E+01	2.367	8.464E+01	2.420	8.424E+01
2.492	8.347E+01	2.466	8.154E+01	2.477	8.017E+01	2.501	7.969E+01
2.537	7.971E+01	2.592	8.005E+01	2.715	8.134E+01	2.829	8.239E+01
2.903	8.324E+01	2.964	8.376E+01	3.024	8.400E+01	3.070	8.389E+01
3.119	8.362E+01	3.173	8.303E+01	3.239	8.229E+01	3.290	8.199E+01
3.327	8.188E+01	3.368	8.224E+01	3.404	8.285E+01	3.459	8.353E+01
3.432	8.407E+01	3.527	8.439E+01	3.542	8.446E+01	3.586	8.404E+01
3.626	8.351E+01	3.667	8.288E+01	3.724	8.232E+01	3.762	8.208E+01
3.811	8.191E+01	3.861	8.213E+01	3.925	8.239E+01	3.946	8.286E+01
3.989	8.313E+01	4.020	8.293E+01	4.055	8.242E+01	4.070	8.151E+01
4.099	7.974E+01	4.124	7.593E+01	4.142	7.392E+01	4.149	7.108E+01
4.170	7.020E+01	4.198	7.073E+01	4.225	7.192E+01	4.251	7.318E+01
4.267	7.388E+01	4.293	7.444E+01	4.325	7.474E+01	4.365	7.443E+01
4.403	7.352E+01	4.459	7.191E+01	4.525	6.950E+01	4.589	6.737E+01
4.643	6.501E+01	4.698	6.215E+01	4.751	5.899E+01	4.811	5.541E+01
4.855	5.179E+01	4.904	4.823E+01	4.969	4.376E+01	5.023	4.018E+01
5.108	3.512E+01	5.197	3.221E+01	5.282	2.967E+01	5.347	2.600E+01
5.402	2.320E+01	5.450	2.018E+01	5.500	1.706E+01	5.547	1.356E+01
5.537	1.050E+01	5.621	8.350E+00	5.688	6.073E+00	5.743	4.322E+00


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-16
SAPPHIRE
T=273 K
OLT, PROC IRIS 3, 141 (1958)
REF: 1T-16
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Oppenheim (Ref. 1T-17)

A Perkin-Elmer 12G spectrometer with unspecified bandpass was used to measure the transmittance of synthetic Meller Co. sapphire from 1μ to 6μ at temperatures ranging from 293°K to 1273°K. The estimated accuracy of the data is 3 percent. The data were digitized from individual points.

These data were selected in part to construct the representative curve given in Section I, Figure I-1.6a.

a. T = 293°K

λ	T	λ	T	λ	T	λ	T
1.629	8.300E+01	1.397	8.466E+01	2.338	8.516E+01	3.213	8.538E+01
4.189	8.389E+01	4.374	7.871E+01	4.593	6.784E+01	4.792	5.579E+01
4.998	4.238E+01	5.409	2.151E+01	5.619	1.257E+01		

b.

λ	T	λ	T	λ	T	λ	T
1.629	8.301E+01	1.401	8.467E+01	2.341	8.516E+01	3.497	8.401E+01
4.191	7.503E+01	4.380	6.666E+01	4.595	5.052E+01	4.797	3.782E+01
4.992	2.227E+01	5.393	5.873E+00	5.613	2.482E+00		




FIGURE 1T-17A
SAPPHIRE
T=293 K
OPPENHEIM. J. OPT. SOC. 52. 1078(1962)
REF. 1T-17




FIGURE 1T-17B
SAPPHIRE
T=773 K
OPPENHEIM. J. OPT. SOC. 52. 1078(1962)
REF. 1T-17


Oppenheim (Ref. 1T-17)


c. T = 1073°K

λ	T	λ	T	λ	T	λ	T
1.023	7.959E+01	1.399	8.156E+01	2.323	8.246E+01	3.491	7.788E+01
4.2[illegible]	[illegible]	4.387	4.231E+01	4.598	2.512E+01	4.799	1.561E+01
5.014	5.673E+00	5.461	1.036E+00	5.612	5.282E-01		

d. T = 1273°K

λ	T	λ	T	λ	T	λ	T
1.027	7.541E-01	1.394	7.656E-01	2.327	7.797E-01	3.478	7.261E-01
4.189	4.729E-01	4.391	3.054E-01	4.603	1.854E-01	4.796	1.035E-01
5.003	3.988E-02						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-17C
SAPPHIRE
T=1073 K
OPPENHEIM. J. OPT. SOL. 52. 1078(1962)
REF. 1T-17
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-17D
SAPPHIRE
T=1273 K
OPPENHEIM. J. OPT. SOC. 52. 1078(1962)
REF. 1T-17
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Piriou (Ref 1T-19)

The infrared transmission of sapphire from 3μ to 11μ was measured at temperatures of 77°K and 273°K for sample thicknesses of 0.062 mm to 1.01 mm. The experimental details were not given. Data were digitized from curves.


These data were selected in part to construct the representative curve given in Section I, Figure I - 1.6b.


a. Thickness = 1.01 mm, T = 293°K, diamond polished, then heated for 5 hrs at 1800°K

λ	T	λ	T	λ	T	λ	T
4.579	8.598E+01	4.774	8.487E+01	4.918	8.279E+01	5.048	8.098E+01
5.149	7.959E+01	5.237	7.784E+01	5.329	7.564E+01	5.403	7.249E+01
5.477	7.003E+01	5.556	6.738E+01	5.646	6.444E+01	5.756	6.121E+01
5.845	5.856E+01	5.921	5.576E+01	5.985	5.195E+01	6.034	4.828E+01
6.079	4.522E+01	6.124	4.038E+01	6.175	3.523E+01	6.233	3.005E+01
6.301	2.355E+01	6.362	1.828E+01	6.448	1.462E+01	6.525	1.231E+01
6.604	8.985E+00	6.653	6.473E+00	6.753	4.210E+00	6.884	2.479E+00
6.959	1.514E+00	7.007	1.331E+00	7.108	6.489E-01	7.216	4.493E-01

b. Thickness = 0.265 mm, T = 293°K, diamond polished, then heated for 5 hrs at 1800°K

λ	T	λ	T	λ	T	λ	T
4.527	8.773E+01	4.803	8.713E+01	5.013	8.681E+01	5.226	8.611E+01
5.358	8.492E+01	5.450	8.372E+01	5.552	8.207E+01	5.630	8.060E+01
5.702	8.005E+01	5.819	7.959E+01	5.922	7.888E+01	6.005	7.716E+01
6.089	7.396E+01	6.147	7.074E+01	6.210	6.746E+01	6.268	6.430E+01
6.308	6.087E+01	6.340	5.850E+01	6.402	5.573E+01	6.484	5.346E+01
6.539	5.159E+01	6.596	4.821E+01	6.633	4.426E+01	6.668	4.156E+01
6.714	3.898E+01	6.785	3.661E+01	6.832	3.314E+01	6.874	2.978E+01
6.932	2.266E+01	6.982	1.965E+01	7.016	1.795E+01	7.077	1.871E+01
7.118	1.752E+01	7.188	1.449E+01	7.265	1.149E+01	7.363	8.436E+00
7.454	6.290E+00	7.550	4.143E+00	7.604	4.692E+00	7.635	5.008E+00
7.694	4.250E+00	7.793	3.378E+00	7.900	2.662E+00	8.023	2.712E+00
8.084	3.328E+00	8.137	4.010E+00	8.203	4.110E+00	8.272	3.677E+00
8.367	2.779E+00	8.487	1.947E+00	8.580	1.314E+00	8.690	7.820E-01
8.794	5.324E-01						



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-19A
SAPPHIRE. T=1.01 MM
T=293 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1T-19
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-19B
SAPPHIRE. T=.265 MM
T=293 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1T-19
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Piriou (Ref. 1T-19)

c. Thickness = 0.167 mm, T = 300°K, chemically etched surface


λ	T	λ	T	λ	T	λ	T
3.506	8.773E+01	3.875	8.796E+01	4.215	8.840E+01	4.432	8.898E+01
4.779	8.943E+01	4.985	8.983E+01	5.168	8.993E+01	5.322	8.975E+01
5.480	8.905E+01	5.616	8.806E+01	5.772	8.730E+01	5.922	8.628E+01
6.017	8.394E+01	6.116	8.045E+01	6.226	7.634E+01	6.318	7.185E+01
6.398	6.839E+01	6.481	6.620E+01	6.557	6.484E+01	6.596	6.264E+01
6.636	5.923E+01	6.663	5.678E+01	6.700	5.521E+01	6.745	5.392E+01
6.809	4.992E+01	6.850	4.609E+01	6.888	4.206E+01	6.932	3.906E+01
6.968	3.546E+01	7.004	3.322E+01	7.031	3.385E+01	7.061	3.467E+01
7.109	3.250E+01	7.177	2.947E+01	7.238	2.599E+01	7.297	2.261E+01
7.361	1.982E+01	7.429	1.713E+01	7.485	1.416E+01	7.534	1.201E+01
7.572	1.179E+01	7.621	1.277E+01	7.655	1.322E+01	7.714	1.218E+01
7.706	1.038E+01	7.829	9.384E+00	7.867	9.052E+00	7.908	9.800E+00
7.943	1.054E+01	8.002	1.030E+01	8.061	1.007E+01	8.091	1.102E+01
8.116	1.219E+01	8.167	1.267E+01	8.231	1.254E+01	8.295	1.132E+01
8.345	9.933E+00	8.436	8.519E+00	8.517	6.938E+00	8.573	5.458E+00
8.624	4.503E+00	8.698	4.542E+00	8.765	3.677E+00	8.852	2.612E+00
8.949	1.647E+00	9.056	9.651E-01	9.191	6.822E-01	9.282	1.997E-01


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-19C
SAPPHIRE. T=.167 MM
T=300 K
PIRIOU. COMPTES RENDUS 264. 1110
(1967)
REF. 1T-19
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Piriou (Ref. 1T-19)

d. Thickness = 0.062 mm, T = 77°K, chemically etched surface


λ	T	λ	T	λ	T	λ	T
5.943	8.599E+01	6.102	8.513E+01	6.190	8.250E+01	6.239	8.109E+01
6.310	7.997E+01	6.391	7.941E+01	6.505	7.896E+01	6.566	7.814E+01
6.625	7.612E+01	6.693	7.441E+01	6.778	7.262E+01	6.815	7.147E+01
6.880	6.765E+01	6.923	6.548E+01	6.959	6.350E+01	6.989	6.281E+01
7.049	6.343E+01	7.081	6.213E+01	7.135	5.988E+01	7.203	5.684E+01
7.265	5.436E+01	7.321	5.210E+01	7.380	4.988E+01	7.450	4.846E+01
7.478	4.688E+01	7.507	4.489E+01	7.535	4.376E+01	7.571	4.345E+01
7.596	4.433E+01	7.622	4.569E+01	7.651	4.648E+01	7.690	4.549E+01
7.724	4.345E+01	7.746	4.221E+01	7.769	4.124E+01	7.804	4.060E+01
7.834	4.038E+01	7.871	4.070E+01	7.913	4.129E+01	7.946	4.141E+01
7.989	4.114E+01	8.019	4.070E+01	8.054	4.056E+01	8.075	4.134E+01
8.086	4.244E+01	8.106	4.376E+01	8.120	4.471E+01	8.152	4.509E+01
8.182	4.521E+01	8.221	4.461E+01	8.268	4.365E+01	8.296	4.227E+01
8.336	4.136E+01	8.357	3.988E+01	8.384	3.842E+01	8.415	3.745E+01
8.448	3.666E+01	8.488	3.610E+01	8.514	3.523E+01	8.540	3.359E+01
8.558	3.248E+01	8.580	3.135E+01	8.604	3.092E+01	8.635	3.109E+01
8.671	3.138E+01	8.701	3.059E+01	8.730	2.932E+01	8.772	2.727E+01
8.815	2.520E+01	8.864	2.338E+01	8.910	2.179E+01	8.963	2.038E+01
8.999	1.970E+01	9.044	1.913E+01	9.107	1.962E+01	9.151	2.014E+01
9.206	2.046E+01	9.251	2.068E+01	9.282	2.029E+01	9.324	1.916E+01
9.3[illegible]	1.810E+01	9.408	1.739E+01	9.482	1.701E+01	9.579	1.703E+01
9.[illegible]	1.672E+01	9.[illegible]70	1.583E+01	9.749	1.523E+01	9.839	1.442E+01
9.915	1.330E+01	9.979	1.216E+01	10.028	1.173E+01	10.073	1.140E+01
10.136	1.157E+01	10.195	1.096E+01	10.261	1.002E+01	10.335	8.636E+00
10.397	7.504E+00	10.491	5.389E+00	10.541	4.859E+00	10.593	3.877E+00
10.668	2.779E+00	10.738	1.780E+00	10.795	1.082E+00	10.828	3.827E-01


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-19D
SAPPHIRE, T=.062 MM
T=77 K
PIRIOU, COMPTES RENDUS 264, 1110
(1967)
REF. 1T-19
TRANSMITTANCE
WAVELENGTH(MICRONS)
100
90
80
70
60
50
40
30
20
10
0
0.
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Piriou (Ref. 1T-19)

e. Thickness = 0.062 mm, T = 300°K, chemically etched surface

λ	T	λ	T	λ	T	λ	T
6.805	7.700E+01	6.866	7.424E+01	6.901	7.129E+01	6.923	6.973E+01
6.953	6.916E+01	6.993	6.864E+01	7.011	6.924E+01	7.020	7.038E+01
7.042	7.135E+01	7.069	7.051E+01	7.101	6.908E+01	7.131	6.706E+01
7.161	6.543E+01	7.213	6.323E+01	7.281	6.029E+01	7.338	5.873E+01
7.387	5.716E+01	7.423	5.558E+01	7.448	5.306E+01	7.474	5.053E+01
7.492	4.869E+01	7.525	4.798E+01	7.550	4.833E+01	7.575	4.998E+01
7.598	5.142E+01	7.620	5.224E+01	7.652	5.077E+01	7.688	4.968E+01
7.720	4.813E+01	7.746	4.695E+01	7.778	4.627E+01	7.814	4.726E+01
7.869	4.836E+01	7.906	4.902E+01	7.934	4.861E+01	7.960	4.786E+01
7.991	4.746E+01	8.015	4.723E+01	8.047	4.778E+01	8.054	4.932E+01
8.067	5.067E+01	8.081	5.242E+01	8.103	5.357E+01	8.134	5.409E+01
8.181	5.394E+01	8.207	5.319E+01	8.231	5.137E+01	8.253	5.040E+01
8.282	5.037E+01	8.308	4.831E+01	8.326	4.658E+01	8.349	4.569E+01
8.371	4.501E+01	8.432	4.423E+01	8.477	4.240E+01	8.514	3.979E+01
8.534	3.814E+01	8.562	3.707E+01	8.585	3.715E+01	8.596	3.775E+01
8.647	3.829E+01	8.674	3.780E+01	8.704	3.595E+01	8.738	3.441E+01
8.769	3.278E+01	8.805	3.089E+01	8.843	2.954E+01	8.888	2.735E+01
8.931	2.548E+01	8.995	2.514E+01	9.032	2.567E+01	9.090	2.679E+01
9.161	2.773E+01	9.237	2.862E+01	9.258	2.771E+01	9.292	2.570E+01
9.323	2.457E+01	9.349	2.423E+01	9.383	2.474E+01	9.419	2.461E+01
9.453	2.488E+01	9.456	2.561E+01	9.470	2.635E+01	9.502	2.609E+01
9.545	2.573E+01	9.598	2.507E+01	9.641	2.442E+01	9.716	2.439E+01
9.745	2.440E+01	9.777	2.329E+01	9.819	2.218E+01	9.867	2.177E+01
9.912	2.137E+01	9.950	2.073E+01	9.990	1.993E+01	10.039	1.957E+01
10.080	1.964E+01	10.106	2.014E+01	10.150	2.014E+01	10.186	1.896E+01
10.216	1.795E+01	10.270	1.703E+01	10.320	1.634E+01	10.353	1.493E+01
10.407	1.365E+01	10.458	1.183E+01	10.506	9.767E+00	10.575	7.238E+00
10.637	5.208E+00	10.701	3.611E+00	10.738	2.396E+00	10.765	2.130E+00
10.805	1.448E+00						


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-19E
SAPPHIRE, T=.062 MM
T=300 K
PIRIOU, COMPTES RENDUS 264, 1110
(1967)
REF. T-19
TRANSMITTANCE
WAVELENGTH(MICRONS)
0
10
20
30
40
50
60
70
80
90
100
2.5
5.
7.5
10.
12.5
15.
17.5
20.
22.5
25.

Roberts (Ref. 1T-20)

The transmittance of sapphire 0.986 mm thick at T $\simeq$ 300°K (unspecified room temperature) was measured using a Czerny-Turner type grating monochromator with unspecified bandpass. Transmittance precision was unstated, but probably better than 1 percent. Data were digitized from specific points.


These data are in agreement with the representative curve of Section I - 1.6.


a. Ordinary ray

λ	T	λ	T	λ	T
[illegible]	[illegible]	2221.334	5.+50E+01	2243.580	5.170E+01
[illegible]	[illegible]	785.313	[illegible]	453.819	4.381E+01
[illegible]	[illegible]	244.191	+.[illegible]39[illegible]+01	195.810	3.661E+01
[illegible]	[illegible]	145.747	3.2[illegible]+01	123.599	2.446E+01
[illegible]	[illegible]	107.691	2.[illegible]+01	99.818	2.266E+01
[illegible]	[illegible]	89.860	1.811[illegible]+01	8+.503	1.598E+01
[illegible]	[illegible]	78.268	1.344[illegible]+01	72.853	1.227E+01
[illegible]	[illegible]	69.496	8.880[illegible]+00	6+.431	8.288E+00
[illegible]	[illegible]	57.869	5.132[illegible]+00	5+.353	4.299E+00
[illegible]	[illegible]	47.448	1.175E+00		

b. Extraordinary ray

λ	T	λ	T	λ	T
[illegible]	[illegible]	2630.958	4.943E+01	2420.+34	4.810E+01
[illegible]	[illegible]	1919.747	4.159E+01	617.347	3.852E+01
[illegible]	[illegible]	253.483	3.387E+01	202.332	2.779E+01
[illegible]	[illegible]	117.427	1.430[illegible]+01	107.188	1.241E+01
[illegible]	[illegible]	93.116	6.9+0[illegible]+00	89.019	6.166E+00
[illegible]	[illegible]	81.041	4.390[illegible]+00	77.597	3.862E+00
[illegible]	[illegible]	72.152	3.[illegible]51E+00	65.447	2.486E+00
[illegible]	[illegible]	60.361	1.084E+00	57.864	5.920E-01


TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-20A
SAPPHIRE. ORDINARY RAY
T=300 K
ROBERTS. J. OPT. SOC. 52. 1023 (1962)
REF. 1T-20
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
10
20
30
40
50
60
70
80
90
100



TRANSMITTANCE OF ALUMINUM OXIDE
FIGURE 1T-20B
SAPPHIRE. EXTRAORDINARY RAY
T=300 K
ROBERTS. J. OPT. SOC. 52. 1023 (1962)
REF. 1T-20
TRANSMITTANCE
WAVELENGTH(MICRONS)
0.
50.
100.
150.
200.
250.
300.
350.
400.
450.
500.
10
20
30
40
50
60
70
80
90
100

White (Ref. 1T-22)

The transmissivity of α - Al_2O_3 powder of unspecified size was measured between 12μ to 23μ on a Perkin-Elmer 21 spectrophotometer equipped with KBr optics. Samples were mounted in KBr pressed pellets. No error analysis was given. Data were digitized from curves.

These data were selected in part to construct the representative curve given in Section I, Figure I - 1.6c.

λ	T	λ	T	λ	T	λ	T
12.000	7.256E+01	12.019	6.680E+01	12.183	6.225E+01	12.307	5.985E+01
12.341	5.889E+01	12.450	5.492E+01	12.556	5.251E+01	12.761	4.989E+01
12.984	4.757E+01	13.247	4.520E+01	13.536	4.329E+01	13.835	4.171E+01
14.155	4.026E+01	14.355	3.984E+01	14.556	4.018E+01	14.733	4.041E+01
14.955	4.017E+01	15.463	3.965E+01	16.035	3.902E+01	16.560	3.848E+01
16.767	3.822E+01	17.024	3.752E+01	17.243	3.683E+01	17.483	3.646E+01
17.677	3.647E+01	17.884	3.689E+01	18.106	3.793E+01	18.253	3.951E+01
18.430	4.373E+01	18.545	4.758E+01	18.654	5.194E+01	18.792	5.667E+01
18.963	6.346E+01	19.126	6.919E+01	19.308	7.684E+01	19.463	8.403E+01
19.546	8.981E+01	19.619	9.288E+01	19.672	9.478E+01	19.724	9.724E+01
19.762	9.813E+01	19.829	9.872E+01	19.959	9.921E+01	20.078	9.853E+01
20.201	9.654E+01	20.368	9.311E+01	20.486	8.988E+01	20.621	8.728E+01
20.742	8.582E+01	20.859	8.474E+01	20.911	8.397E+01	20.984	8.252E+01
21.090	7.904E+01	21.190	7.644E+01	21.291	7.296E+01	21.394	7.036E+01
21.472	6.743E+01	21.567	6.478E+01	21.716	6.150E+01	21.864	5.898E+01
22.033	5.670E+01	22.266	5.412E+01	22.482	5.271E+01	22.631	5.229E+01
22.795	5.213E+01	22.968	5.231E+01	23.142	5.316E+01	23.265	5.446E+01
23.439	5.582E+01	23.590	5.902E+01	23.728	6.162E+01	23.821	6.393E+01
23.891	6.551E+01						



Best Available Copy