

(12)

FC

Observations on Approximate and Exact Treatments of Fracture Statistics for Polyaxial Stress States

ADA019572

S. B. BATDORF
Laboratory Operations ✓
The Aerospace Corporation
El Segundo, Calif. 90245

4 December 1975

Final Report

APPROVED FOR PUBLIC RELEASE:
DISTRIBUTION UNLIMITED

Prepared for
OFFICE OF NAVAL RESEARCH
Washington, D. C. 20390
and

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH
Arlington, Va. 22209

SPACE AND MISSILE SYSTEMS ORGANIZATION
AIR FORCE SYSTEMS COMMAND
Los Angeles Air Force Station
P.O. Box 92960, Worldway Postal Center
Los Angeles, Calif. 90009


D D C
RECEIVED
JAN 22 1976
RECEIVED

1473

DISCLAIMER NOTICE

THIS DOCUMENT IS BEST QUALITY PRACTICABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.


Approved



G. W. King
Vice President and General Manager
Laboratory Operations

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

FOR THE COMMANDER



Ronald C. Lawson
2nd Lt, United States Air Force
Office of Research Applications
Deputy for Technology

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

(19) REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER SAMS0-TR-75-289	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) OBSERVATIONS ON APPROXIMATE AND EXACT TREATMENTS OF FRACTURE STATISTICS FOR POLYAXIAL STRESS STATES		5. TYPE OF REPORT & PERIOD COVERED Final
7. AUTHOR(s) Samuel B. Batdorf		6. PERFORMING ORG. REPORT NUMBER TR-0076(9990)-2
9. PERFORMING ORGANIZATION NAME AND ADDRESS The Aerospace Corporation El Segundo, Calif. 90245		8. CONTRACT OR GRANT NUMBER(s) F04701-75-C-0076
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Washington, D. C. 20390		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 12 17p.
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) Space and Missile Systems Organization Air Force Systems Command Los Angeles, Calif. 90009		12. REPORT DATE 4 December 1975
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		13. NUMBER OF PAGES 14
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		15. SECURITY CLASS. (of this report) Unclassified
18. SUPPLEMENTARY NOTES		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Fracture Statistics Failure Statistics Failure Theory Brittle Fracture		DISPATCH SYMBOLS Dist. ... A
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) An approximate technique sometimes used for estimating the probability of failure of brittle materials under polyaxial loading conditions is to assume that the effect of each principal stress is independent of the presence of the others. It is shown that this assumption is generally unconservative, and that the errors can be large. An exact treatment is given in terms of Weibull theory for materials that obey Weibull's two-parameter formulation, and a simple conservative approximation is suggested for such materials.		

CONTENTS

OBSERVATIONS ON APPROXIMATE AND EXACT TREATMENTS OF FRACTURE STATISTICS FOR POLY-AXIAL STRESS STATES	3
REFERENCES	15

FIGURES

1. Ratio of \ln of Probability of Survival in Equibiaxial Tension to that in Uniaxial Tension [equal to $P_f(\sigma, \sigma)/P_f(\sigma, 0)$ when $P_f \ll 1$]	7
2. Comparison of Theoretical Survival Prediction with Barnett-Freudenthal (BF) Approximation	10
3. Ratio of Theoretical Prediction to Barnett-Freudenthal (BF) Approximation	12

OBSERVATIONS ON APPROXIMATE AND EXACT
TREATMENTS OF FRACTURE STATISTICS
FOR POLYAXIAL STRESS STATES

In his original treatment of the statistics of fracture, Weibull [1] introduced a two-parameter functional form for the relationship between simple tension and probability of fracture. He also showed how to compute the corresponding statistics of failure for bending, torsion, and other stress states that involve only uniaxial tensile stresses. These applications have become well known and are widely used [2-4].

In problems that involve biaxial or triaxial tensile stresses, the situation is more complicated. Weibull gave, without formal proof, a procedure for treating such problems and showed how to apply it in several simple cases. Some investigators have expressed doubts concerning the rigor of Weibull's treatment of polyaxial stress states [5,6], and there are indications that these doubts were later shared by Weibull himself [7,8]. Since, in addition, rather tedious calculations are required for each polyaxial stress state, in practical structures that involve continuously varying stress states, there is a natural tendency to use approximations. One simple approximation, which constitutes, in fact, the only technique suggested for handling polyaxial stress statistics in a recent treatise on fracture [9], is to assume that

$$P_s (\sigma_1, \sigma_2, \sigma_3) = P_s (\sigma_1) P_s (\sigma_2) P_s (\sigma_3) \quad (1)$$

where P_s is the probability of survival, and $\sigma_1, \sigma_2, \sigma_3$ are the principal stresses. This method was mentioned earlier by Barnett et al. [5]. For brevity, it is referred to here as the Barnett-Freudenthal (BF) approximation.

One objective of the present investigation is to investigate the limitations of this approach and thus assist potential users in understanding the general nature and approximate magnitude of the errors involved. Another objective

is to point out an alternative approximation that is preferable in some applications. For the sake of simplicity and brevity, interest is focused primarily on biaxial tension applied to isotropic materials whose fracture statistics in simple tension can be described with satisfactory accuracy by Weibull's two-parameter formulation:

$$P_f = 1 - \exp [-k\sigma^m] \quad (2)$$

or

$$\ln P_s = \ln (1 - P_f) = -k\sigma^m \quad (3)$$

where P_f is the probability of fracture. An exact treatment of the Weibull theory solution is also given.

The BF approximation would be strictly correct if all the cracks were oriented with their planes normal to any one of the principal stresses. However, this is rarely the case and certainly does not occur in isotropic materials. Generally, there will be some cracks inclined to the principal axes that will be fractured by combined stresses even though capable of surviving any of the principal stresses applied individually. This phenomenon tends to make eq. (1) unconservative. However, there are also cases in which a given crack would be fractured by more than one of the principal stresses even acting alone, and this tends to make the assumption of noninteraction, i. e., eq. (1), conservative. We show how these opposite trends interact, and that, generally, the unconservative tendency dominates.

In the case of equibiaxial tension, eq. (1) reduces to

$$P_s (\sigma, \sigma) = [P_s (\sigma, 0)]^2 \quad (4)$$

or

$$\frac{\ln P_s(\sigma, \sigma)}{\ln P_s(\sigma, \sigma)} = 2 \quad (5)$$

Equation (5) implies that, for the small values of P_f of primary interest

$$\frac{\ln P_s(\sigma, \sigma)}{\ln P_s(\sigma, \sigma)} = \frac{\ln [1 - P_f(\sigma, \sigma)]}{\ln [1 - P_f(\sigma, \sigma)]} \cong \frac{P_f(\sigma, \sigma)}{P_f(\sigma, \sigma)} = 2 \quad (6)$$

i. e., the probability of failure in equibiaxial tension is twice that for uniaxial tension.

As noted earlier, one would expect, from general principles, that this would sometimes be an underestimate of the probability of equibiaxial fracture. In order to determine when and how much, we must turn to theory. For this purpose, we select a recent reformation of weakest link theory in which the flaws are identified as cracks [10], and the polyaxial stress statistics are derived in a straightforward manner from the basic assumptions. It was noted earlier [8] that, according to this theory, when the probability of fracture in simple tension obeys eq. (2), the probability for equibiaxial tension becomes

$$P_f(\sigma, \sigma) = 1 - \exp \left[-(2m+1)mk\sigma^m \frac{\Gamma(m)\Gamma(1.5)}{\Gamma(m+1.5)} \right] \quad (7)$$

For integral values of m , eq. (7) becomes

$$P_f(\sigma, \sigma) = 1 - \exp \left[- \frac{k(m)! \sigma^m}{(m-0.5)(m-1.5) \dots 0.5} \right] \quad (8)$$

Combining eqs. (2) and (8), we obtain

$$\frac{\ln P_s(\sigma, \sigma)}{\ln P_s(\sigma, 0)} = \frac{m!}{(m - 0.5)(m - 1.5) \dots 0.5} \quad (9)$$

In Fig. 1, this result is compared with the previous one given in eq. (5), and we conclude that the BF approximation leads to the correct result for equibiaxial tension when $m = 1$. However, for $m = 5$ and 10 , it underestimates small equibiaxial failure probabilities by factors of approximately 2 and 3, respectively. Note that eq. (9), can be approximated surprisingly well by the very simple equation

$$\frac{\ln P_s(\sigma, \sigma)}{\ln P_s(\sigma, 0)} \cong 2(m)^{0.45} \quad (10)$$

From Fig. 1, it is clear that the BF approximation is conservative for $m < 1$. However, values of m in the range of $0 < m \leq 1$ are abnormal. With the use of eq. (2), it is readily shown that the slope of the $P_f(\sigma)$ curve is zero at $\sigma = 0$ when $m > 1$, in agreement with observation. For $m = 1$, the slope is finite; for $m < 1$, it is infinite; such behavior is rarely, if ever, encountered in nature. Thus, we conclude that, for practical purposes, eq. (1) can be considered unconservative.

We now consider the way the size of the error in eq. (1) varies with stress ratio, again focusing attention on the biaxial case. It was pointed out earlier [8] that, for materials that obey eq. (2), the Weibull theory and that of Batdorf and Crose [10] give the same results. In the general case of triaxial tension characterized by principal stresses σ_1, σ_2 and σ_3 , where $\sigma_1 \geq \sigma_2 \geq \sigma_3 \geq 0$, both theories imply that the probability of fracture takes the form




Figure 1. Ratio of \ln of Probability of Survival in Equibiaxial Tension to that in Uniaxial Tension [equal to $P_f(\sigma, \sigma) / P_f(\sigma, 0)$ when $P_f \ll 1$]

$$P_f = 1 - \exp -k \int_0^{2\pi} d\phi \int_0^\pi (\sigma_1 \cos^2 \phi \sin^2 \theta + \sigma_2 \sin^2 \phi \sin^2 \theta + \sigma_3 \cos^2 \theta)^m \sin \theta d\theta \quad (11)$$

where θ and ϕ are the polar and azimuthal angles, respectively. As noted by Shur [11], the integral in eq. (11) yields

$$\int_0^{2\pi} d\phi \int_0^\pi ()^m \sin \theta d\theta = 4\pi \sigma_1^m \frac{(m!)^2}{(2m+1)!} \sum_{i,j,k}^m \frac{(2i)! (2j)! (2k)!}{(i! j! k!)^2} s^j t^k \quad (12)$$

where i, j, k are any positive integers that satisfy the inequalities $0 < i, j, k < m$ and $i + j + k = m$, and where

$$s = \sigma_2 / \sigma_1 \quad (13a)$$

$$t = \sigma_3 / \sigma_1 \quad (13b)$$

For the biaxial case, $\sigma_3 = t = 0$, and the probability of survival becomes

$$P_s = \exp \left[- \frac{4\pi k}{2m+1} \sigma_1^m F(m, s) \right] \quad (14)$$

where

$$F(m, s) = \frac{(m!)^2}{(2m)!} \sum_{i=0}^m \frac{(2i)! [2(m-i)]!}{[i!(m-i)!]^2} \quad (15)$$

Thus, in the general biaxial case,

$$\frac{\ln P_s(\sigma_1, \sigma_2)}{\ln P_s(\sigma_1, 0)} = \frac{F(m, s)}{F(m, 0)} = F(m, s) \quad (16)$$

where m is any positive integer, and $0 \leq s = \frac{\sigma_2}{\sigma_1} \leq 1$.

The BF approximation gives, for the biaxial case,

$$\frac{\ln P_s(\sigma_1, \sigma_2)}{\ln P_s(\sigma_1, 0)} = \frac{\ln P_s(\sigma_1, s)}{\ln P_s(\sigma_1, 0)} = 1 + s^m \quad (17)$$

Curves that represent eqs. (16) and (17) are shown in Fig. 2. It is evident that, for values of m of practical interest, the BF approximation consistently underestimates the fracture contribution of the second stress, and that the error is largest, in absolute terms, at least, for the equibiaxial case, $s = 1$.

Another way to compare theory with the BF approximation is to take the ratios of eqs. (16) and (17). Thus,

$$\frac{\ln(P_s)_{Th}}{\ln(P_s)_{BF}} = \frac{F(m, s)}{1 + s^m} \quad (18)$$

This result is shown in Fig. 3. It is evident that the ratio increases monotonically from $s = 0$ to $s = 1$. Moreover, in the range $2 < m \lesssim 10$, the ratio is reasonably constant near $s = 1$.

The first of these observations suggests a simple method for obtaining an upper bound to the failure probability, or a lower bound to the survival




Figure 2. Comparison of Theoretical Survival Prediction with Barnett-Freudenthal (BF) Approximation

probability of a biaxially stressed structure; viz., it implies that, in every element of the structure,

$$\frac{\ln (P_s)_{Th}}{\ln (P_s)_{BF}} = \frac{F(m, s)}{1 + s^m} \leq \frac{F(m, 1)}{2} \cong m^{0.45} \quad (19)$$

Since eq. (19) holds for every element individually, it must hold for the structure as a whole.

Thus, we conclude that

$$- \ln (P_s)_{BF} \leq - \ln (P_s)_{Th} \leq - m^{0.45} \ln (P_s)_{BF} \quad (20)$$

For small values of P_f , this implies that

$$(P_f)_{BF} \leq (P_f)_{Th} < m^{0.45} (P_f)_{BF} \quad (21)$$

Because the curves of Fig. 3 are fairly flat near $s = 1$, in the case of structures whose loading is nearly equibiaxial, the second inequality in eqs. (20) and (21) approaches equality. In the case of circular disks with uniform lateral or concentric ring loading, for instance, the (small) probabilities of failure should, according to the theories discussed here, be quite close to $m^{0.45}$ times the result given by the BF approximation, which yields a simple closed-form solution.

As mentioned earlier, the preceding analysis is based on the assumption that the uniaxial tensile fracture statistics of the material under consideration can be described with adequate accuracy by Weibull's two-parameter equation. When the material is better represented by his three-parameter equation, the analysis becomes more complicated and is beyond the scope of the present paper. However, the general observation that eq. (1) is unconservative still applies, and it is to be expected




Figure 3. Ratio of Theoretical Prediction to Barnett-Freudenthal (BF) Approximation

that the size of the error might be substantial, particularly when the Weibull parameter m is large. Finally, it should be pointed out that, for materials that obey eq. (2), an accurate Weibull-type treatment of structural problems that involve biaxial or triaxial stresses is not difficult when a computing machine is used in conjunction with finite elements provided that closed-form solutions to the integral in eq. (11) are used. These solutions are given in eqs. (12), (14), and (15).

REFERENCES

- [1] W. Weibull, Ingeniors Vetenshaps Akadamein, Handlingar, 151 (1939).
- [2] W. H. Duckworth et al., Mechanical Property Tests on Ceramic Bodies, WADC Technical Report 52-67 (March 1952).
- [3] E. Y. Robinson, Estimating Weibull Parameters for Composite Materials, Proceedings of Colloquium on Structural Reliability, Carnigie-Mellon Univ. Press (1972).
- [4] N. A. Weil and I. M. Daniel, Analyses of Fracture Probabilities in Nonuniformly Stressed Brittle Materials, Journal of the American Ceramic Society, 47:6 (1964).
- [5] R. L. Barnett et al., Fracture of Brittle Materials Under Transient Mechanical and Thermal Loading, AFFDL-TR-66-220 (March 1967).
- [6] W. H. Dukes, Handbook of Brittle Material Design Technology, AGARDograph No. 152 (December 1970).
- [7] W. Weibull, A Survey of Statistical Effects in the Field of Material Failure, Applied Mechanics Surveys, Spartan Books (1966).
- [8] S. B. Batdorf, Weibull Statistics for Polyaxial Stress States, Journal of the American Ceramic Society, 57 (1974).
- [9] A. M. Freudenthal, Statistical Approach to Brittle Fracture, Fracture, Vol 2, H. Liebowitz, ed., Academic Press, New York (1968).
- [10] S. B. Batdorf and J. G. Crose, A Statistical Theory for the Fracture of Brittle Structures Subjected to Nonuniform Polyaxial Stresses, Journal of Applied Mechanics, 41 (1974) 459.
- [11] D. M. Shur, Statistical Criterion of the Danger of Material Fracture in a Complex Stress State, Mashinovedenie, 1 (1971) 51.

LABORATORY OPERATIONS

The Laboratory Operations of The Aerospace Corporation is conducting experimental and theoretical investigations necessary for the evaluation and application of scientific advances to new military concepts and systems. Versatility and flexibility have been developed to a high degree by the laboratory personnel in dealing with the many problems encountered in the nation's rapidly developing space and missile systems. Expertise in the latest scientific developments is vital to the accomplishment of tasks related to these problems. The laboratories that contribute to this research are:

Aerophysics Laboratory: Launch and reentry aerodynamics, heat transfer, reentry physics, chemical kinetics, structural mechanics, flight dynamics, atmospheric pollution, and high-power gas lasers.

Chemistry and Physics Laboratory: Atmospheric reactions and atmospheric optics, chemical reactions in polluted atmospheres, chemical reactions of excited species in rocket plumes, chemical thermodynamics, plasma and laser-induced reactions, laser chemistry, propulsion chemistry, space vacuum and radiation effects on materials, lubrication and surface phenomena, photo-sensitive materials and sensors, high precision laser ranging, and the application of physics and chemistry to problems of law enforcement and biomedicine.

Electronics Research Laboratory: Electromagnetic theory, devices, and propagation phenomena, including plasma electromagnetics; quantum electronics, lasers, and electro-optics; communication sciences, applied electronics, semi-conducting, superconducting, and crystal device physics, optical and acoustical imaging; atmospheric pollution; millimeter wave and far-infrared technology.

Materials Sciences Laboratory: Development of new materials; metal matrix composites and new forms of carbon; test and evaluation of graphite and ceramics in reentry; spacecraft materials and electronic components in nuclear weapons environment; application of fracture mechanics to stress corrosion and fatigue-induced fractures in structural metals.

Space Physics Laboratory: Atmospheric and ionospheric physics, radiation from the atmosphere, density and composition of the atmosphere, aurorae and airglow; magnetospheric physics, cosmic rays, generation and propagation of plasma waves in the magnetosphere; solar physics, studies of solar magnetic fields; space astronomy, x-ray astronomy; the effects of nuclear explosions, magnetic storms, and solar activity on the earth's atmosphere, ionosphere, and magnetosphere; the effects of optical, electromagnetic, and particulate radiations in space on space systems.

THE AEROSPACE CORPORATION
El Segundo, California