

AD-A025 894

RIA-76-U343

6-13

TECHNICAL
LIBRARY

AD A 025 894



ATTEMPTED SYNTHESIS OF PYRIDINE CONTAINING BIS-ALPHA-DIKETONES VIA THE BENZOIN CONDENSATION

ROBERT J. CHERILL and STANLEY E. WENTWORTH
POLYMER AND CHEMISTRY DIVISION

April 1976

Approved for public release; distribution unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER AMMRC TR 76-13		2. GOVT ACCESSION NO.	
4. TITLE (and Subtitle) ATTEMPTED SYNTHESIS OF PYRIDINE CONTAINING BIS- ALPHA-DIKETONES VIA THE BENZOIN CONDENSATION		3. RECIPIENT'S CATALOG NUMBER	
7. AUTHOR(s) Robert J. Cherill and Stanley E. Wentworth		5. TYPE OF REPORT & PERIOD COVERED Final Report	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DRXMR-RA		6. PERFORMING ORG. REPORT NUMBER	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Materiel Development and Readiness Command, Alexandria, Virginia 22333		8. CONTRACT OR GRANT NUMBER(s)	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS D/A Project:1T162105AH84 AMCMS Code:612105.11.H8400 Agency Accession:DA OF4696	
		12. REPORT DATE April 1976	
		13. NUMBER OF PAGES 8	
		15. SECURITY CLASS. (of this report) Unclassified	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Synthesis (chemical) High-temperature polymers Polyquinoxalines Pyridines			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)			

(SEE REVERSE SIDE)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Block No. 20

ABSTRACT


Although polyphenylquinoxalines are exceptional high-temperature-resistant resins, they are prohibitively expensive due largely to the high cost of the bis- α -diketones from which they are prepared. The benzoin condensation of each of the three isomeric pyridine monocarboxaldehydes with terephthalaldehyde followed by oxidation has been investigated as an alternate route to these monomers. Although all such attempts were unsuccessful, an insight into the complexities of mixed benzoin condensations is presented.

UNCLASSIFIED


SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

INTRODUCTION


Although the polyphenylquinoxalines are among the best of the currently available high-temperature-resistant resins, they suffer the disadvantage of extremely high cost. This is due largely to the high cost of their aromatic bis- α -diketone monomers (e.g., I) which are prepared from expensive starting materials via a multistep synthesis.¹ Thus, a significant reduction in the cost of this monomer would have a similar effect on the polymer.





Although the benzoin condensation followed by oxidation has long been used for the preparation of aromatic α -diketones, extension of this route to the preparation of aromatic bis- α -diketones has been unsuccessful* (Eq.1).



Apparently, competing side reactions such as oligomerization of terephthalaldehyde (III) and self condensation of benzaldehyde (II) prevent the desired mixed benzoin condensation from taking place. A recent report by Jones et al.,² however, has shown that the route can work when furan-2-carboxaldehyde (IV) is substituted for benzaldehyde.



This result suggested the possibility of one or more of the isomeric pyridine monocarboxaldehydes (Va, b, and c) behaving in a similar manner.



Since the thermal stability of the pyridyl group is comparable to that of the phenyl, the properties of polyquinoxaline(s) incorporating a pyridine-containing monomer should be essentially the same as the phenyl-containing analog. Thus, a successful preparation of pyridine containing bis- α -diketones using the inexpensive benzoin condensation route would provide a significantly less costly polyquinoxaline. Our efforts to develop such a route are described.

*PACIOREK, K. L., KARLE, D. W., and KRATZER, R. H. *Synthesis of Isomeric Bisbenzils*. Ultrasystems, Inc., Contract N00017-73-C-4325, Final Report, August 1974. This report, which appeared while the present work was in progress, describes a successful application of the benzoin condensation to the synthesis of aromatic bis- α -diketones.

1. WRASIDLO, W. J., and AUGL, J. M. *Synthesis and Evaluation of New Phenylated Polyquinoxalines*. Naval Ordnance Laboratory, NOL TR 69-120, October 1969.
2. JONES, R. J., VAUGHAN, R. W., O'RELL, M. K., and SHEPPARD, C. H. *Development of Autoclavable Addition-Type Polyimides*. TRW Systems Group, Contract NAS3-15834, Final Report, NASA CR-121251, February 1974.

EXPERIMENTAL

Materials

The 2-, 3-, and 4-pyridinecarboxaldehydes (Aldrich) were vacuum distilled, stored under nitrogen, and refrigerated. Terephthaldehyde (Aldrich) was washed with NaHCO_3 , and recrystallized from 50% EtOH/ H_2O . Dibenzo-18-crown-6 was prepared according to the literature, mp 163 to 165 C (Reference 3, 164 C). Hexamethylphosphoramide, N,N-dimethylformamide and acetonitrile were redistilled and dried (molecular sieves). All other compounds were used as received. Melting points (uncorrected) were taken on a Fisher-Johns melting point apparatus and infrared spectra were recorded on a Perkin-Elmer Model 137 Spectrophotometer.

CONDENSATION

Aqueous

An ethanolic solution of the desired amounts of terephthaldehyde and the particular pyridine carboxaldehyde was placed in a round bottom flask fitted with a magnetic stirrer and a reflux condenser capped with an addition funnel. To this was added dropwise with stirring a saturated solution of the required amount of KCN in ethanol/water (1:1,v:v). The reaction time and temperature were varied according to the experiment, depending upon the reactivity of the pyridinecarboxaldehyde. After the time indicated (Table 1), the mixture was cooled (if above ambient) and poured with stirring into a 5-fold excess of water. The resulting solids were removed by filtration, water washed, and finally air dried. In some cases recrystallization from ethanol or chloroform was attempted.

Nonaqueous

Crown Ether Method

An acetonitrile solution of terephthaldehyde and 2-pyridinecarboxaldehyde was placed in a three-neck round bottom flask fitted with a mechanical stirrer, a reflux condenser, and an addition funnel. To this was added dropwise with stirring an acetonitrile solution of the required quantity of dibenzo-18-crown-6/KCN complex. After one hour the precipitate, if present, was removed by filtration, dried, and recrystallized from ethanol. In those cases where no solid was present, the solution was taken to dryness with a rotary evaporator. The resulting solids were triturated with water in order to break down the KCN/crown ether complex. This crude product was subjected to oxidation (see below).

N,N-Dimethylformamide Method

An N,N-dimethylformamide solution of terephthaldehyde and 2-pyridinecarboxaldehyde was placed in a three-neck round bottom flask equipped with a mechanical stirrer, a reflux condenser, and an addition funnel. To this was added dropwise with stirring a saturated solution of the required amount of KCN in N,N-dimethylformamide. After stirring for 24 hours, the reaction mixture was poured with

3. PEDERSEN, C. J. *Cyclic Ethers and Their Complexes with Metal Salts*. Journal of the American Chemical Society, v. 89, 1967, p. 7017-36.

stirring into a 5-fold excess of water. The resulting solids were removed by filtration, water washed, and vacuum dried. This crude product was subjected to oxidation.

Table 1. CONDENSATIONS

Exp.	Pyridine Aldehyde	Mole Ratio (a) (b)		Solvent System	Reaction Conditions		Oxidation	Comments
					Time (hr)	Temp.		
1	4	2:1	1:1	EtOH/H ₂ O	0.5	reflux		Very poor yield crude product, no identifiable bis-benzoin
2	4	2:1	4:1	EtOH/H ₂ O	2.0	reflux	Table 2 Exp. 1	Crude yield higher, recrystallized fraction oxidized
3	2	2:1	4:1	EtOH/H ₂ O	2.0	reflux		α -pyridoin only product identified
4	2	2:1	4:1	EtOH/H ₂ O	0.25	ambient		Red and yellow materials isolated, neither bis-benzoin
5	2	2:1	3:1	EtOH/H ₂ O	0.25	0 C		No bis-benzoin isolated
6	2	2:1	1:1	MeCN Crown ether	1.0	ambient		No bis-benzoin isolated
7	2	2:1	1:10	MeCN Crown ether	1.0	ambient	Table 2 Exp. 2	Crude product subject to oxidation
8	2	2:1	1:1	DMF	24.0	ambient	Table 2 Exp. 3	Crude product subject to oxidation
9	3	2:1	4:1	EtOH/H ₂ O	24.0	ambient		Product mp 187 to 190 C, poor elemental analysis for bis-benzoin*†
10	3	2:1	4:1	EtOH/H ₂ O	24.0	70 C		Same product as in Exp. 9
11	3	4:1	3:1	EtOH/H ₂ O	24.0	ambient	Table 2 Exps. 4, 5&6	Product mp 154 to 155 C, elemental analysis*† fails to confirm bis-benzoin

*Calcd. for C₂₀H₁₆N₂O₄: C, 69.0; H, 4.6; N, 8.0; O, 18.4

†Found: N, 6.3

‡Found: C, 65.8; H, 5.3; N, 8.6

(a) Pyridine Aldehyde/Terephthaldehyde

(b) KCN/Terephthaldehyde

OXIDATIONS

Copper Sulfate-Pyridine Method

In a round bottom flask equipped with a magnetic stirrer and a condenser was placed a solution of the required amount of $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ in 70:30 pyridine:water (v:v) and the presumed bis-benzoin (see above). After reaction (see Conditions, Table 2), the mixture was poured with stirring into a 5-fold excess of water. The resulting precipitate was removed by filtration, water washed, and dried. In those cases where recrystallization was attempted, ethanol was used.

Copper Sulfate-Hexamethylphosphoramide Method⁴

To a magnetically stirred solution of the required amount of $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ in hexamethylphosphoramide in a round bottom flask was added the presumed bis-benzoin in one portion. The resulting mixture was stirred for the desired period (see Table 2) while oxygen was slowly bubbled through in order to maintain the copper in the 2^+ oxidation state. The resulting bright green mixture was poured with stirring into a 5-fold excess of water. The resulting solids were removed by filtration, water washed, and dried. Attempted recrystallization from several solvents failed to yield the desired bis- α -diketone.

Table 2. OXIDATIONS

Exp.	Substrate Table 1 Exp.	Oxidant Solvent	Reaction Conditions		Comments
			Time (hr)	Temp.	
1	2	CuSO_4 /pyridine*	5.0	reflux	Green material isolated. No isolation of bis- α -diketone.
2	7	CuSO_4 /pyridine*	5.0	reflux	Yellow material isolated. Unpurified by chromatography or recrystallization.
3	8	CuSO_4 /pyridine*	24.0	ambient	Isolation of α -pyridil and other unidentified material.
4	11	CuSO_4 /HMPA*	24.0	ambient	Green material isolated. No isolation of bis- α -diketone,
5	11	10% HNO_3 /AcOH	1.0	100 C	Recovery of starting material only.
6	11	50% HNO_3 /AcOH	1.0	100 C	Isolation of presumed carboxylic acids.

*The concentration of CuSO_4 in this experiment was in a four-mole excess based on presumed pure bis-benzoin.

4. MACAIONE, D. P., and WENTWORTH, S. E. *An Improved Method for the Synthesis of Benzils from Benzoin*s. *Synthesis*, 1974, p. 716.

Nitric Acid Method

The presumed bis-benzoin was dissolved in an acetic-acid/nitric-acid mixture (see Table 2) in a round bottom flask fitted with a magnetic stirrer and a reflux condenser. After stirring for one hour under reflux, the reaction mixture was cooled and diluted with one third its volume of water. The resulting solids were isolated by filtration, water washed, and air dried.

DISCUSSION

4-Pyridinecarboxaldehyde

The condensation of 4-pyridinecarboxaldehyde with terephthalaldehyde in aqueous ethanol, the usual solvent for the benzoin condensation (Table 1, Exp. 1) yielded products in such small quantity that purification and identification were impossible. An increase in the concentration of KCN according to the procedure of Jones et al.² (Table 1, Exp. 2) led to an increased yield which still resisted purification. A possible source of this difficulty is the number of isomeric forms, both positional and stereo, in which the bis-benzoin can exist. However, since all of these isomers can be oxidized to the same desired bis- α -diketone, a portion of this impure material was subjected to oxidation with copper sulfate in pyridine (Table 2, Exp. 1). Unfortunately, this procedure yielded only a green unrecrystallizable copper-containing material which was presumed to be complex. At this point it was decided to proceed to the 2-pyridinecarboxaldehyde system.

2-Pyridinecarboxaldehyde

Attempted condensation of 2-pyridinecarboxaldehyde and terephthalaldehyde using the procedure of Jones et al.² (Table 1, Exp. 3) gave α -pyridoin as the only isolable product. It was noted that the initially burgundy colored reaction mixture took on an orange color typical of α -pyridoin as the reaction progressed. It was speculated that the burgundy color might be due to the desired bis-benzoin which, on heating in the presence of KCN, reverted to the thermodynamically more stable α -pyridoin. Accordingly, this reaction was attempted at ambient and subambient temperatures (Table 1, Exps. 4 and 5) for a shorter time. Unfortunately, although the red color was retained in both cases, neither attempt yielded the desired bis-benzoin. The infrared spectrum of the water washed and dried products indicated the presence of both hydroxyl and nitrile groups from which we infer the presence of a cyanohydrin, the conjugate base of which has been suggested as an intermediate in the benzoin condensation.⁵ We next sought to enhance the catalytic activity of the cyanide ion through complexation of its potassium counter-ion with dibenzo-18-crown-6 (a cyclic or so-called crown ether) (Table 1, Exps. 6 and 7). In neither case was a bis-benzoin isolated. The crude product from Exp. 7 was subjected to oxidation with copper sulfate/pyridine (Table 2, Exp. 2). This reaction failed to yield the desired bis- α -diketone. In the hope that a simple nonaqueous solvent might facilitate this condensation, it was run in N,N-dimethylformamide (Table 1, Exp. 8). Subsequent oxidation of the crude product (Table 2, Exp. 3) yielded only α -pyridil.

5. IDE, W. S., and BUCK, J. S. *The Synthesis of Benzoin*. Organic Reactions, v. 4, 1948, p. 273-4.

3-Pyridinecarboxaldehyde

When the procedure of Jones et al.² was applied to the condensation of 3-pyridinecarboxaldehyde and terephthalaldehyde (Table 1, Exp. 9), a product was obtained whose infrared spectrum and melting point was consistent with that of a bis-benzoin. Elemental analysis, however, failed to confirm the desired structure. Repeat of this reaction at elevated temperature (Table 1, Exp. 10) yielded the same product. When the reaction was run with a 2-fold excess of 3-pyridinecarboxaldehyde (Table 1, Exp. 11), a lower melting product was obtained whose infrared spectrum again supported a bis-benzoin structure. Although the elemental analysis was closer to that required for the desired bis-benzoin, it still failed to confirm that structure. Oxidation of this material under a variety of conditions (Table 2, Exps. 4, 5, and 6) failed to yield the desired bis- α -diketone.

CONCLUSIONS

As can be seen from an inspection of Table 1, an appropriate set of conditions for the benzoin condensation of pyridinecarboxaldehydes with terephthalaldehyde has not been discovered. Although the method developed by Paciorek et al. might be effective with this system, their success with benzaldehyde in this reaction clearly eliminates economics as a rationale for further investigation of heterocyclic bis- α -diketones.

ACKNOWLEDGMENT

The authors gratefully acknowledge the many helpful discussions with Mr. Domenic P. Macaione during the course of this work.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20301
12	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Metals and Ceramics Information Center, Battelle Memorial Institute, 505 King Avenue, Columbus, Ohio 43201
	Chief of Research and Development, Department of the Army, Washington, D. C. 20310
2	ATTN: Physical and Engineering Sciences Division
	Commander, Army Research Office, P. O. Box 12211, Research Triangle Park, North Carolina 27709
1	ATTN: Information Processing Office
	Commander, U. S. Army Materiel Development and Readiness Command, 5001 Eisenhower Avenue, Alexandria, Virginia 22333
1	ATTN: DRCDE-TC
	Commander, U. S. Army Electronics Command, Fort Monmouth, New Jersey 07703
1	ATTN: AMSEL-GG-DD
1	AMSEL-GG-DM
	Commander, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
1	ATTN: Technical Library
1	AMSMI-RSM, Mr. E. J. Wheelahan
	Commander, U. S. Army Armament Command, Rock Island, Illinois 61201
2	ATTN: Technical Library
	Commander, U. S. Army Natick Laboratories, Natick, Massachusetts 01760
1	ATTN: Technical Library
	Commander, Edgewood Arsenal, Maryland 21010
1	ATTN: Mr. F. E. Thompson, Dir. of Eng. & Ind. Serv., Chem-Mun Br
	Commander, Frankford Arsenal, Philadelphia, Pennsylvania 19137
1	ATTN: SMUFA-L300, Mr. J. Corrie
	Commander, Harry Diamond Laboratories, 2800 Powder Mill Road, Adelphi, Maryland 20783
1	ATTN: Technical Information Office

No. of
Copies

To

Commander, Picatinny Arsenal, Dover, New Jersey 07801

1 ATTN: SMUPA-RT-S

1 SARPA-FR-M-D, PLASTEC, A. M. Anzalone

Commander, Redstone Scientific Information Center, U. S. Army Missile
Command, Redstone Arsenal, Alabama 35809

4 ATTN: AMSMI-RBLD, Document Section

Commander, U. S. Army Foreign Science and Technology Center,
220 7th Street, N. E., Charlottesville, Virginia 22901

1 ATTN: AMXST-SD3

Commander, U. S. Army Environmental Hygiene Agency, Edgewood Arsenal,
Maryland 21010

1 ATTN: Chief, Library Branch

Naval Research Laboratory, Washington, D. C. 20375

1 ATTN: Dr. J. M. Krafft - Code 8430

Chief of Naval Research, Arlington, Virginia 22217

1 ATTN: Code 471

Commander, Naval Surface Weapons Center, Silver Spring, Maryland 20910

1 ATTN: Dr. J. M. Augl

Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433

2 ATTN: AFML (MXE), E. Morrissey

1 AFML (LC)

1 AFML (LMD), D. M. Forney

1 AFML (MBC), Mr. Stanley Schulman

National Aeronautics and Space Administration, Washington, D. C. 20546

1 ATTN: Mr. B. G. Achhammer

1 Mr. G. C. Deutsch - Code RR-1

National Aeronautics and Space Administration, Marshall Space Flight
Center, Huntsville, Alabama 35812

1 ATTN: R-P&VE-M, R. J. Schwinghamer

1 S&E-ME-MM, Mr. W. A. Wilson, Building 4720

National Aeronautics and Space Administration, Lewis Research Center,
21000 Brook Park Road, Mail Stop 49-1, Cleveland, Ohio 44135

1 ATTN: W. B. Alston

National Aeronautics and Space Administration, Langley Research Center,
Hampton, Virginia 23365

1 ATTN: Mr. P. M. Hergenrother

No. of
Copies

To

1	Materials Sciences Corporation, Blue Bell Campus, Merion Towle Building, Blue Bell, Pennsylvania 19422
1	The Charles Stark Draper Laboratory, 68 Albany Street, Cambridge, Massachusetts 02139
	Lockheed-Georgia Company, Marietta, Georgia 30060
1	ATTN: Advanced Composites Information Center, Dept. 72-14 - Zone 402
1	Dr. R. J. Jones, TRW Defense and Space Systems Group, Bldg. 01, One Space Park, Redondo Beach, California 90278
1	Dr. N. Bilow, Hughes Aircraft Company, Culver City, California 90230
1	Dr. C. Hughes, AVCO/Lowell, 2 Industrial Avenue, Lowell, Massachusetts 01851
	Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172
2	ATTN: DRXMR-PL
1	DRXMR-AG
2	Authors

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
ATTEMPTED SYNTHESIS OF PYRIDINE CONTAINING
BIS- α -DIKETONES VIA THE BENZOIN CONDENSATION
Robert J. Cherill and Stanley E. Wentworth

Technical Report AMMRC TR 76-13, April 1976, 8 pp-
tables, D/A Project 1T162105AH84,
AMCMS Code 612105.11.H8400

Although polyphenylquinoxalines are exceptional high-temperature-resistant resins, they are prohibitively expensive due largely to the high cost of the bis- α -diketones from which they are prepared. The benzoin condensation of each of the three isomeric pyridine monocarboxaldehydes with terephthaldehyde followed by oxidation has been investigated as an alternate route to these monomers. Although all such attempts were unsuccessful, an insight into the complexities of mixed benzoin condensations is presented.

AD _____
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Synthesis (chemical)
Polyquinoxalines
Pyridines


Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
ATTEMPTED SYNTHESIS OF PYRIDINE CONTAINING
BIS- α -DIKETONES VIA THE BENZOIN CONDENSATION
Robert J. Cherill and Stanley E. Wentworth

Technical Report AMMRC TR 76-13, April 1976, 8 pp-
tables, D/A Project 1T162105AH84,
AMCMS Code 612105.11.H8400

Although polyphenylquinoxalines are exceptional high-temperature-resistant resins, they are prohibitively expensive due largely to the high cost of the bis- α -diketones from which they are prepared. The benzoin condensation of each of the three isomeric pyridine monocarboxaldehydes with terephthaldehyde followed by oxidation has been investigated as an alternate route to these monomers. Although all such attempts were unsuccessful, an insight into the complexities of mixed benzoin condensations is presented.

AD _____
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words

Synthesis (chemical)
Polyquinoxalines
Pyridines



DEPARTMENT OF THE ARMY
ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD 314

OFFICIAL BUSINESS

THIRD CLASS MAIL

Commander
U. S. Army Armament Command
ATTN: Technical Library
Rock Island, Illinois 61201