

ADA 038837

AMMRC TR 77-4

12

AD

MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE OF A MARAGING STEEL AND METASTABLE BETA TITANIUM ALLOY UNDER TORSIONAL LOADING

PETER T. LUM and RICHARD CHAIT
ENGINEERING STANDARDIZATION DIVISION

February 1977

Approved for public release; distribution unlimited.



DDC FILE COPY

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AMRC-TR-77-4	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE OF A MARAGING STEEL AND METASTABLE BETA TITANIUM ALLOY UNDER TORSIONAL LOADING.	5. TYPE OF REPORT & PERIOD COVERED Final Report	6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Peter T. Lum and Richard Chait	8. CONTRACT OR GRANT NUMBER(s)	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DXXMR-E	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT D/A Project AT162105AH84 AMCMS Code: 612105-11-H8400 Agency Accession: DA OF4691	
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Materiel Development and Readiness Command, Alexandria, Virginia 22333	12. REPORT DATE February 1977	13. NUMBER OF PAGES 9
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 12/12p.	15. SECURITY CLASS. (of this report) Unclassified	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		ABSTRACT BY DTIC DATE RECD DDC DATE RECD UNCLASSIFIED CONFIDENTIAL
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Titanium alloys Low-cycle fatigue Maraging steel Monotonic response Torsional response		DTIC CONFIDENTIAL, UNCLASSIFIED, SECRET DATE AUTH. AND/or SPECIAL
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		

(SEE REVERSE SIDE)

403 105

LB

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Block No. 20

ABSTRACT

This study deals with the torsional response of Ti-8823 and 18Ni (200) maraging steel. The effect of different heat treatments and the subsequent change in microstructure are investigated. In the case of the Ti-8823, a comparison was made between the solution-treated-and-aged condition, and the direct-aged condition. It was found that the finer precipitate morphology in the DA material offered a greater resistance to torsional fatigue. For the 18Ni (200) maraging steel, an increase of aging time from 3 to 98 hours led to a substantial increase in the amount of reverted austenite, which in turn led to a significant improvement in torsional fatigue behavior. The results are analyzed in terms of the Manson-Coffin equation.

UNCLASSIFIED

INTRODUCTION

Much of the designer's information is based on a material's response to tensile deformation. However, when service requirements are clearly nonuniaxial, it behooves the designer to obtain information which more closely approximates service loading conditions. Designing components to carry torsional loads such as with torsion bars is an example. Torsional loading has been accompanied by nonuniform deformation which is unlike that observed under tensile loading.¹⁻³ For example, the 18Ni maraging steel family exhibits an excellent combination of toughness, strength, and ductility. Here, strength and ductility refer to behavior under tensile loading. However, under torsional loading 18Ni maraging steels compared to other high strength steels shows a marked decrease in strain to fracture.³ This report examines aspects of the torsional deformation of 18Ni (200) maraging steel which may improve its performance under monotonic as well as strain-controlled torsional fatigue loading.

Strength values in the range provided by the 18Ni (200) maraging steel are also possible with metastable beta titanium alloys. However, there appears to be little data in the literature regarding behavior of these titanium alloys under either monotonic or cyclic torsional loading. Therefore, the present effort also concerns itself with the metastable beta titanium alloy Ti-8Mo-8V-2Fe-3Al, henceforth termed Ti-8823.

MATERIALS AND TEST PROCEDURE

The chemical composition for the 18Ni (200) and Ti-8823 alloys are shown in Table 1. The heat treatments that were utilized are detailed in Table 2. The Ti-8823 was given either the generally recommended solution treatment and age (STA) heat treatment or direct age (DA) after hot work. The heat treatment for 18Ni (200) steel includes a treatment that provides substantial amounts of reverted austenite. This treatment was used by Pampillo and Paxton⁴ to improve the tensile properties. The amount of reverted austenite present in the material after this heat treatment was determined by X-ray diffraction analysis to be approximately 37 percent.

Solid cylindrical specimens approximately 0.200 inch in diameter were tested in a 2000 in.-lb Instron torsion machine. Monotonic torque-twist curves were obtained from each heat-treated condition. In addition, strain-controlled low-cycle fatigue tests were conducted in torsion to obtain the plastic shear strain range ($\Delta\gamma_p$) versus number of cycles to failure (N_f) curves. A cyclic strain hardening exponent n' was obtained from a least-squares fit of the log-log plot of the shear stress versus shear strain utilizing stress values obtained from steady-state hysteresis loops at different $\Delta\gamma_p$ levels.

1. POLAKOWSKI, N. H., and MOSTOVOY, S. *Transient and Destructive Instability in Torsion*. Trans. ASM, v. 54, 1961, p. 567.
2. SPRETNAK, J. W. *Plastic Instability in Some Ultra-High Strength Steels*. Trans. Japan Institute of Metals, v. 9, 1968, p. 305.
3. CHIAI, R. *Flow and Fracture of High Strength Steels in Torsion*. J. Test and Evaluation, v. 1, 1973, p. 435.
4. PAMPILLO, C. A., and PAXTON, H. W. *The Effect of Reverted Austenite on the Mechanical Properties and Toughness of 12Ni and 18Ni(200) Maraging Steels*. Met. Trans., v. 3, 1972, p. 2895.

Table 1. CHEMICAL COMPOSITION (WEIGHT PERCENT)

Alloy	Ni	Co	Mo	Ti	Al	Mn	Si	P	S	C
18Ni (200) Steel	12.3	8.5	3.22	0.22	0.08	0.04	0.04	0.005	0.008	0.008
	Al	V	Mo	Fe	Sn	Cu	C	O	H	N
Ti-8823	3.08	8.08	7.80	2.07	-	-	0.035	0.133	0.006	0.010

Table 2. HEAT TREATMENT OF MARAGING STEEL AND TITANIUM ALLOY

Alloy	Austenitizing or Solutionizing Treatment	Aging Treatment	Comment
18Ni (200)	1500 F(1 hr)	900 F(3 hr)	Customary heat treatment
	1500 F(1 hr)	962 F(98 hr)	Reverted austenite heat treatment
Ti-8823	1475 F(1-1/2 hr)	1000 F(8hr)	STA heat treatment
	-	950 F(8 hr)	DA heat treatment

RESULTS AND DISCUSSION

Torsional Stress-Strain Curve (Monotonic)

The monotonic shear stress-shear strain curves for 18Ni (200) and Ti-8823 alloys are shown in Figures 1 and 2. From these curves, strain hardening differences were determined since it has been shown that one of the factors influencing torsional ductility is the strain hardening behavior. In their work with 2024 aluminum Fields and Backofen⁵ have shown that a low strain hardening rate is a contributing factor to the occurrence of nonuniform torsion deformation. The 18Ni (200) steel given the customary heat treatment displays a definite tendency toward localized deformation upon monotonic loading as shown in Figure 3. As expected, the presence of the localized deformation reduces the strain to fracture. Using a power-law relationship $\tau = K\gamma^n$ between the shear stress τ and shear strain γ , the strain hardening exponent n of 18Ni (200) steel given the customary heat treatment is approximately 0.05. The 18Ni (200) steel given the reverted austenite heat treatment exhibits a stress-strain curve where $n = 0.07$. In line with this trend is the fact that the material given the reverted austenite heat treatment exhibited a greater value of strain to fracture without a decrease in strength.

The same trend is seen with the Ti-8823 material. For the material given the DA heat treatment, $n = 0.11$, while the STA heat treatment leads to $n = 0.05$. Therefore, it is not unexpected that the strain to fracture for the DA material is greater than for the STA material at about the same shear strength level.

It was mentioned that the enhancement of torsional ductility in the 18Ni (200) steel was due to the presence of reverted austenite and its effect on the material's capacity to strain harden. Microstructural differences also exist for Ti-8823. As shown in Figure 4, material given the age treatment directly after hot working shows a fine, uniformly distributed network of alpha particles,

5. FIELDS, D. S., and BACKOFEN, W. A. Determination of Strain Hardening Characteristics by Torsion Testing. Proc. ASTM, v. 57, 1957, p. 1259.




Figure 1. Monotonic shear stress-shear strain curves for 18Ni (200) maraging steel.




Figure 2. Monotonic shear stress-shear strain curves for Ti-8Mo-8V-2Fe-3Al.




Figure 3. Localized torsional deformation of 18Ni (200) maraging steel as a result of monotonic loading. Mag. 4X.



Direct Aged



Solution Treated and Aged

Figure 4. Effect of heat treatment on microstructure of Ti-8823 alloy. Mag. 12,000X

whereas material given the STA heat treatment possesses alpha precipitates which are coarse compared to DA material. This is due to the effect of the intermediate solutionizing treatment.⁶ It is interesting to note that DA microstructure also results in better fracture toughness, yield strength, tensile strength, and tensile ductility than the STA material.⁶

Torsional Low-Cycle Fatigue Behavior - $\Delta\gamma_p$ Versus N_f Curves

Factors that influence the monotonic torsional stress-strain curves would also be expected to have a pronounced effect on the low-cycle fatigue behavior. The torsional low-cycle fatigue test results are shown in Figures 5 and 6 where $\Delta\gamma_p$ (plastic strain range) is plotted as a function of N_f (cycle to failure) for both Ti-8823 and 18Ni (200) steel. For Ti-8823, there is a marked difference between the DA and STA materials. For a given strain range, the DA material exhibits a higher N_f . The same is true for the 18Ni (200) steel given the reverted austenite heat treatment.

Visual observations made during the cycling of the 18Ni (200) steel show the higher resistance to torsional deformation of the material given the reverted austenite heat treatment. Localized deformation bands shown in Figure 3 provide sites for surface cracks of the type shown in Figure 7a during deformation of the material given the customary heat treatment. While material given the reverted austenite heat treatment does have some cracks as shown in Figure 7b, they are less numerous than those shown in Figure 7a for regularly heat-treated material, despite the order of magnitude difference in $\Delta\gamma_p$.

6. CHAIT, R., and DeSISTO, T. S. *An Evaluation of Some High Strength Titanium Alloys Processed in Heavy Section*. Army Materials and Mechanics Research Center, AMMRC PIR 75-3, September 1975.




Figure 5. Low-cycle fatigue curves for Ti-8823.




Figure 6. Low-cycle fatigue curves for 18Ni (2LW) maraging steel.




Figure 7. The effect of heat treatment on crack formation of 18Ni (200) maraging steel after torsional fatigue.

Analysis of Low-Cycle Fatigue Behavior

Efforts to characterize the low-cycle fatigue behavior are well known.⁷ It was found that tensile low-cycle fatigue behavior can be described by

$$N_f^{1/2} \Delta \epsilon_p = \text{constant} \quad (1)$$

where $\Delta \epsilon_p$ is the plastic strain range.

A more general form of the equation was obtained by Feltner and Morrow.⁸

$$N_f^c \Delta \epsilon_p = \text{constant} \quad (2)$$

Here, the damage energy is considered to result primarily from plastic work and is assumed to be constant. Assuming an exponential relationship between plastic stress and plastic strain, one arrives at

$$c = -(1/1+n) \quad (3)$$

7. TAVERNELLI, J. I., and COLLINS, L. I., Jr. *A Compilation and Interpretation of Cyclic Strain Fatigue Tests on Metals*. Trans. ASM v. 51, 1959, p. 438.

8. FELTNER, C. L., and MORROW, J. D. *Microplastic Strain Hysteresis Energy as a Criterion for Fatigue Fracture*. Journal of Basic Engineering, March 1961, p. 15.

where n is the strain hardening exponent. Halford and Morrow⁹ took the plastic zone size into account and obtained

$$c = -(1/1+5n) \quad (4)$$

Equation 4 was also utilized to analyze the torsional low-cycle fatigue behavior of several alloys, both ferrous and nonferrous.⁹ Using strain hardening exponent values obtained from monotonic torsion tests, satisfactory agreement was obtained between the measured and actual slope of the $\Delta\gamma_p$ versus N_f curves. It was noted that perhaps one should use the strain hardening exponent representative of cyclic behavior (n') rather than monotonic behavior.¹⁰ In the present study both n and n' were utilized in conjunction with Equation 4 to calculate the slope of $\Delta\gamma_p$ versus N_f curves and compare it with the value obtained from the actual slope. From the comparison shown in Table 3, it is seen that utilizing n' values results in better agreement.

Table 3. COMPARISON OF ACTUAL AND CALCULATED SLOPES OF $\Delta\gamma_p$ VERSUS N_f CURVES

Materials	Heat Treatment	n	n'	Measured Slope	Calculated Slope	
					$-(1/1+5n)$	$-(1/1+5n')$
Ti-8823	STA	0.05	0.123	-0.48	-0.80	-0.62
	DA	0.11	0.11	-0.26	-0.64	-0.65
18Ni (200)	Reverted Austenite	0.07	0.13	-0.47	-0.74	-0.60
	Regular	0.05	0.13	-0.55	-0.93	-0.61

NOTE: n and n' are the values of the strain hardening exponents obtained from monotonic and cyclic tests, respectively.

CONCLUSION

This study has examined the torsional response of two high strength alloys, an 18Ni (200) maraging steel and a Ti-8Mc-8V-2Fe-3Al alloy. Both monotonic and low-cycle fatigue behavior were examined. The following conclusions were made.

1. Compared to 18Ni (200) steel given the customary heat treatment, increasing the amount of reverted austenite improves resistance to torsional deformation under monotonic as well as low-cycle fatigue loading.
2. Direct aging after hot working provides Ti-8823 with better resistance to torsional deformation (both monotonic and low-cycle fatigue) than does the more common solution-treat-and-age heat treatment.
3. These improvements are thought to be associated in part to increased strain hardening capacity.
4. The low-cycle fatigue behavior can be analyzed using the representation of Halford and Morrow. Good agreement was obtained between calculated (using cyclic strain hardening values) and measured values of the slope of the $\Delta\gamma_p$ versus N_f curves.

9. HALFORD, G. R., and MORROW, J. D. *Low Cycle Fatigue in Torsion*. Proc. ASTM, v. 62, 1962, p. 695.

10. VAN SWAN, L. F., PELLOUX, R. M., and GRANT, N. J. *Fatigue Behavior of Maraging Steel 300*. Metallurgical Transactions A, v. 6A, January 1975, p. 45.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20301
12	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, Ohio 43201
	Chief of Research and Development, Department of the Army, Washington, D. C. 20310
2	ATTN: Physical and Engineering Sciences Division Commander, Army Research Office, P. O. Box 12211, Research Triangle Park, North Carolina 27709
1	ATTN: Information Processing Office Commander, U. S. Army Materiel Development and Readiness Command, 5001 Eisenhower Avenue, Alexandria, Virginia 22333
1	ATTN: DRCLDC, Mr. R. Zentner Commander, U. S. Army Electronics Command, Fort Monmouth, New Jersey 07703
1	ATTN: DRSEL-GG-DD
1	DRSEL-GG-DM
	Commander, U. S. Army Missile Command, Redstone Arsenal, Alabama 35803
1	ATTN: Technical Library
1	DRSMI-RSM, Mr. E. J. Wheelahan
	Commander, U. S. Army Armament Command, Rock Island, Illinois 61201
2	ATTN: Technical Library Commander, U. S. Army Satellite Communications Agency, Fort Monmouth, New Jersey 07703
1	ATTN: Technical Document Center Commander, U. S. Army Tank-Automotive Research and Development Command, Warren, Michigan 48090
2	ATTN: DRDTA, Research Library Branch Commander, White Sands Missile Range, New Mexico 88002
1	ATTN: STEWS-WS-VT
	Commander, Aberdeen Proving Ground, Maryland 21005
1	ATTN: STEAP-TL, Bldg. 305
	Commander, Frankford Arsenal, Philadelphia, Pennsylvania 19137
1	ATTN: Library, H1300, B1. 51-2
1	SARFA-L300, Mr. J. Corrie
	Commander, Picatinny Arsenal, Dover, New Jersey 07801
1	ATTN: SARPA-RT-S
	Commander, Redstone Scientific Information Center, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
4	ATTN: DRSMI-RBLD, Document Section

No. of Copies	To
	Commander, Watervliet Arsenal, Watervliet, New York 12189
1	ATTN: SARWV-RDT, Technical Information Services Office
	Commander, U. S. Army Foreign Science and Technology Center, 220 7th Street, N. E., Charlottesville, Virginia 22901
1	ATTN: DRXST-SD2
	Director, Eustis Directorate, U. S. Army Air Mobility Research and Development Laboratory, Fort Eustis, Virginia 23604
1	ATTN: Mr. J. Robinson, SAVDL-EU-SS
	Librarian, U. S. Army Aviation School Library, Fort Rucker, Alabama 36360
1	ATTN: Building 5907
	Naval Research Laboratory, Washington, D. C. 20375
1	ATTN: Dr. J. M. Krafft - Code 8430
2	Dr. G. R. Yoder - Code 6382
	Chief of Naval Research, Arlington, Virginia 22217
1	ATTN: Code 471
	Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433
2	ATTN: AFML/MXE/E. Morrissey
1	AFML/LC
1	AFML/LLP/D. M. Forney, Jr.
1	AFML/MBC/Mr. Stanley Schulman
	National Aeronautics and Space Administration, Washington, D. C. 20546
1	ATTN: Mr. B. G. Achhammer
1	Mr. G. C. Deutsch - Code RR-1
	National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, Alabama 35812
1	ATTN: R-PGVE-M, R. J. Schwinghamer
1	S&E-ME-M, Mr. W. A. Wilson, Building 4720
1	Ship Research Committee, Maritime Transportation Research Board, National Research Council, 2101 Constitution Ave., N. W., Washington, D. C. 20418
	Wyman-Gordon Company, Worcester, Massachusetts 01601
1	ATTN: Technical Library
	General Dynamics, Convair Aerospace Division, P. O. Box 748, Fort Worth, Texas 76101
1	ATTN: Mfg. Engineering Technical Library
1	Mechanical Properties Data Center, Belfour Stulen Inc., 13917 W. Bay Shore Drive, Traverse City, Michigan 49684
	Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts
2	ATTN: DRXMR-PL
1	DRXMR-AG
2	Authors

Army Materials and Mechanics Research Center,
Worcester, Massachusetts 02122
MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE
OF A MARAGING STEEL AND METASTABLE BETA
TITANIUM ALLOY UNDER TORSIONAL LOADING -
Peter T. Lum and Richard Chait

Technical Report AMRC TR 77-4, February 1977, 9 pp -
illus-tables, D/A Project 11162105A484,
AMCS Code 612105.11.168400

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION
key Words
Titanium alloys
Maraging steel
Torsional response

This study deals with the torsional response of Ti-6222 and 18Ni (200) maraging steel. The effect of different heat treatments and the subsequent change in microstructure are investigated. In the case of the Ti-6222, a comparison was made between the solution-treated-and-aged condition, and the direct-used condition. It was found that the finer precipitate morphology in the DA material offered a greater resistance to torsional fatigue. For the 18Ni maraging steel, an increase of aging time from 3 to 96 hours led to a substantial increase in the amount of reverted austenite which in turn led to a significant improvement in torsional fatigue behavior. The results are analyzed in terms of the Manson-Coffin equation.

Army Materials and Mechanics Research Center,
Worcester, Massachusetts 02122
MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE
OF A MARAGING STEEL AND METASTABLE BETA
TITANIUM ALLOY UNDER TORSIONAL LOADING -
Peter T. Lum and Richard Chait

Technical Report AMRC TR 77-4, February 1977, 9 pp -
illus-tables, D/A Project 11162105A484,
AMCS Code 612105.11.168400

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION
key Words
Titanium alloys
Maraging steel
Torsional response

This study deals with the torsional response of Ti-6222 and 18Ni (200) maraging steel. The effect of different heat treatments and the subsequent change in microstructure are investigated. In the case of the Ti-6222, a comparison was made between the solution-treated-and-aged condition, and the direct-used condition. It was found that the finer precipitate morphology in the DA material offered a greater resistance to torsional fatigue. For the 18Ni maraging steel, an increase of aging time from 3 to 96 hours led to a substantial increase in the amount of reverted austenite which in turn led to a significant improvement in torsional fatigue behavior. The results are analyzed in terms of the Manson-Coffin equation.

Army Materials and Mechanics Research Center,
Worcester, Massachusetts 02122
MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE
OF A MARAGING STEEL AND METASTABLE BETA
TITANIUM ALLOY UNDER TORSIONAL LOADING -
Peter T. Lum and Richard Chait

Technical Report AMRC TR 77-4, February 1977, 9 pp -
illus-tables, D/A Project 11162105A484,
AMCS Code 612105.11.168400

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION
key Words
Titanium alloys
Maraging steel
Torsional response

This study deals with the torsional response of Ti-6222 and 18Ni (200) maraging steel. The effect of different heat treatments and the subsequent change in microstructure are investigated. In the case of the Ti-6222, a comparison was made between the solution-treated-and-aged condition, and the direct-used condition. It was found that the finer precipitate morphology in the DA material offered a greater resistance to torsional fatigue. For the 18Ni maraging steel, an increase of aging time from 3 to 96 hours led to a substantial increase in the amount of reverted austenite which in turn led to a significant improvement in torsional fatigue behavior. The results are analyzed in terms of the Manson-Coffin equation.

Army Materials and Mechanics Research Center,
Worcester, Massachusetts 02122
MONOTONIC AND LOW-CYCLE FATIGUE RESPONSE
OF A MARAGING STEEL AND METASTABLE BETA
TITANIUM ALLOY UNDER TORSIONAL LOADING -
Peter T. Lum and Richard Chait

Technical Report AMRC TR 77-4, February 1977, 9 pp -
illus-tables, D/A Project 11162105A484,
AMCS Code 612105.11.168400

AD UNCLASSIFIED
UNLIMITED DISTRIBUTION
key Words
Titanium alloys
Maraging steel
Torsional response

This study deals with the torsional response of Ti-6222 and 18Ni (200) maraging steel. The effect of different heat treatments and the subsequent change in microstructure are investigated. In the case of the Ti-6222, a comparison was made between the solution-treated-and-aged condition, and the direct-used condition. It was found that the finer precipitate morphology in the DA material offered a greater resistance to torsional fatigue. For the 18Ni maraging steel, an increase of aging time from 3 to 96 hours led to a substantial increase in the amount of reverted austenite which in turn led to a significant improvement in torsional fatigue behavior. The results are analyzed in terms of the Manson-Coffin equation.