

AD-A039 687

BRANDEIS UNIV WALTHAM MASS DEPT OF CHEMISTRY

F/G 7/2

THE POLYMERIZATION OF NIBR<sub>2</sub>(P(CH<sub>2</sub>CH<sub>2</sub>CN)<sub>3</sub>)<sub>2</sub>: A 'TRIPLY-SPECIFIC'--ETC(U)

APR 77 K CHENG, B M FOXMAN

N00014-76-C-0822

UNCLASSIFIED

TR-1


NL

1 of 1  
AD  
A039687



END

DATE  
FILMED  
6-77



NATIONAL BUREAU OF STANDARDS  
MICROCOPY RESOLUTION TEST CHART

12  
NW

OFFICE OF NAVAL RESEARCH

Contract No. N00014-76-C-0822

Task No. NR 356-619

TECHNICAL REPORT No. 1

The Polymerization of  $\text{NiBr}_2[\text{P}(\text{CH}_2\text{CH}_2\text{CN})_3]_2$ :

A "Triply-Specific" Solid State Reaction

Kent Cheng and Bruce M. Foxman

Department of Chemistry

Brandeis University

Waltham, Massachusetts 02154

DDC  
MAY 17 1977  
RESOLVED

Prepared for Publication

in the

Journal of the American Chemical Society

April, 1977

Reproduction in whole or in part is permitted  
for any purpose of the United States Government

Approved for public release; distribution unlimited

ADA 039687

AD No. \_\_\_\_\_  
DDC FILE COPY

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 1 ✓	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER (14) TR-1
4. TITLE (and Subtitle) The Polymerization of $\text{NiBr}_2[\text{P}(\text{CH}_2\text{CH}_2\text{CN})_3]_2$ : A "Triply-Specific" Solid-State Reaction	5. TYPE OF REPORT & PERIOD COVERED (9) Interim report	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Kent Cheng and Bruce M. Foxman	8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0822 new	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry, Brandeis University, ✓ Waltham, MA 02154	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR356-619	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, Virginia 22217	12. REPORT DATE April 1977	13. NUMBER OF PAGES 11 (2) 13 p
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release, distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES  Submitted to the Journal of the American Chemical Society  400 983		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)  Nickel Halophosphines, Solid State Polymerization, Coordination Polymers		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  See page 11.		

Contribution from the  
Department of Chemistry,  
Brandeis University  
Waltham, Massachusetts 02154

The Polymerization of  $\text{NiBr}_2[\text{P}(\text{CH}_2\text{CH}_2\text{CN})_3]_2$ :

A "Triply-Specific" Solid State Reaction

by

Kent Cheng and Bruce M. Foxman\*

ACCESSION for		
NTIS	White Section	<input checked="" type="checkbox"/>
DOC	Buff Section	<input type="checkbox"/>
UNANNOUNCED		<input type="checkbox"/>
JUSTIFICATION.....		
BY.....		
DISTRIBUTION/AVAILABILITY CODES		
Dist.	AVAIL. end/or	SPECIAL
A		

Sir:

The reactivity of coordination complexes in the solid state has been little explored.<sup>1</sup> Because of the rather stringent directional requirements, the most interesting solid-state reactions of coordination complexes are undoubtedly polymerization processes.<sup>2</sup> Studies of the potentially topochemical polyreactions of monomeric coordination complexes, by analogy with other inorganic and organic systems<sup>3</sup> can thus lead to an understanding of synthetic, dimensional and symmetry-based criteria for the solid-state preparation of crystalline coordination polymers. Square-planar, red monomeric complexes of the type  $\text{NiX}_2\text{CEP}_2$  ( $\text{X} = \text{Cl}, \text{Br}$ ;  $\text{CEP} = \text{P}(\text{CH}_2\text{CH}_2\text{CN})_3$ ) are obtained as kinetic products at room temperature, and have been shown to undergo polymerization reactions in solution or in the solid state<sup>4</sup> to yield highly crystalline, blue, octahedral coordination polymers. For  $\text{NiBr}_2\text{CEP}_2$ ,<sup>4a</sup> we have examined the polymerization in solution and in single crystals:

red  $\text{NiBr}_2\text{CEP}_2$     1. RT, days (soln.) or months (xtal)  
                           2.  $80^\circ$ , 30 min (either)  $\xrightarrow{\hspace{1.5cm}}$   
                           3.  $130^\circ$ , instantaneous (xtal)

blue  $(\text{NiBr}_2\text{CEP}_2)_x \xrightarrow[\text{T} > 130^\circ (\text{xtal})]{\Delta} \text{Partial Decomposition}$

Further, we find that the reaction is characterized by (a) product specificity, (b) stereospecificity, leading to formation of linear polymer, (c) "crystallographic specificity" and (d) highly anisotropic "front motion" through individual single crystals.

When either an acetone solution or moist individual single crystals of monomer are allowed to polymerize at various temperatures, the blue polymeric product is always contaminated with a green material, which has defied characterization.<sup>5</sup> However, when dry individual single crystals are allowed to polymerize at temperatures below  $\sim 130^\circ$ , only the blue polymeric product is formed. Thus, this reaction is readily product-specific only in the solid state. While the rate of polymerization is slower ( $\sim \frac{1}{6}$ ) in the solid state at room temperature and below the rates are about equal at  $80^\circ$  C, and the solid state transformation is faster above the latter temperature.

In order to determine the probable geometrical course of the reaction, we have carried out complete three-dimensional X-ray structure analyses on single crystals of monomer and polymer grown from solution:

Monomer, Orthorhombic, Pbca	→	Polymer, Monoclinic, B <sub>2</sub> <sub>1</sub> /c <sup>6</sup>
a = 13.169, b = 22.004, c = 8.487 Å		a = 13.907, b = 21.055, c = 8.496 Å;
V = 2459.3 Å <sup>3</sup>		β = 97.46° ; V = 2466.7 Å <sup>3</sup>

In both the monomer and polymer phases, Ni atoms occupy the centers of symmetry  $(0,0,0)$ ,  $(\frac{1}{2}, 0, \frac{1}{2})$ ,  $(0, \frac{1}{2}, \frac{1}{2})$ ,  $(\frac{1}{2}, \frac{1}{2}, 0)$ . The crystal structure of the product phase shows that only Ni complexes at  $(0,0,0)$  and  $(\frac{1}{2}, 0, \frac{1}{2})$  have reacted to form part of a repeating polymer chain, while Ni complexes at  $(\frac{1}{2}, \frac{1}{2}, 0)$  and  $(1, \frac{1}{2}, \frac{1}{2})$  have reacted to form a

second polymer chain. This is a significant observation: since it can be shown that the solid-state reaction pathway is likely to be identical to that suggested by this "before and after" view (vide infra), we conclude that polymerization occurs only in specific ac planes in the crystal. Such a "layer-by-layer" reaction precludes cross-linking of polymer chains and may be expected to lead to the formation of rigorously linear polymer, as well as highly oriented crystalline product.

At temperatures  $> 20^\circ$  the crystals do not show well-defined front motion as the reaction proceeds, hence we have confined our initial studies of reacting crystals to temperatures near  $-5^\circ$ . Crystals of the monomer are well-defined, wine-red, nearly opaque prisms, elongated along  $[001]$ , with well-defined  $\{010\}$ ,  $\{100\}$ ,  $(111)$ ,  $(\bar{1}\bar{1}\bar{1})$ ,  $(\bar{1}\bar{1}\bar{1})$ , and  $(11\bar{1})$  faces. Reaction always begins on a single  $(100)$  face or on a pair of  $(100)$  faces; the reaction proceeds (over a 6-month period), with the first significant observation being a thin blue coloration of the entire  $(100)$  face. A very distinct blue reaction front then moves across the crystal, virtually parallel to the  $(100)$  face. X-ray diffraction studies of partially reacted crystals (5%-60% complete) show that the reaction is topotactic,<sup>7</sup> and, further, that  $(a_{\text{reactant}}^*, a_{\text{product}}^*)$  and  $(b_{\text{reactant}}^*, b_{\text{product}}^*)$  are aligned. The  $c$  axis in the monoclinic product lies  $\sim 7.5^\circ$  away from the  $c^*$  axis of the reactant phase (note that in the transformation from orthorhombic to monoclinic,

$\beta$  changes from  $90^\circ$  to  $97.5^\circ$ ). However, for crystals where the solid-state reaction begins on a single (100) face, only one new  $c^*$  axis is observed, i.e. twinning about  $[001]_{\text{reactant}}$  does not occur to a detectable extent. Thus, the first product which appears on a crystal face appears to determine, in a crystallographically specific manner, unit cell orientation in the product. We note that this strictly linear polymerization process appears to be different from other carefully-studied examples,<sup>3</sup> (including the polymerization of  $\text{NiCl}_2\text{CEP}_2$ ),<sup>8</sup> in which the polymer appears first in a solid solution with monomer, and crystallization/orientation of product may be effected via annealing.

The relationship between pairs of reactant and product molecules, chosen so as to be representative of the overall polymerization reaction, is presented in the Figure, which demonstrates the spatial similarities between reactant and product. The reaction mechanism qualitatively involves polymerization in crystal ac planes, followed by repacking of the polymer along the b direction; further, it may be shown that motion of the centroids of the individual complexes during reaction defines the product a axis (and  $\beta$  angle of  $97.5^\circ$ ). The direction of slowest front motion (i.e. along the a direction) is consistent with the observation that only the a axis of the reactant crystal must reorient to form the product pseudomorph.

Acknowledgements. This work was supported in part by the Office of Naval Research, and in part by the National Science Foundation, through instrumentation grant No. CHE 76-05582.


References

1. J. B. Newkirk, Acta Metal., 4, 316 (1956); M. R. Snow and R. F. Boomsma, Acta Cryst., B28, 1908 (1972) are examples of more detailed studies.
2. A few examples may be found in B. P. Block, "Coordination Polymers," in Inorganic Polymers, F. G. A. Stone and W. A. G. Graham, ed., Academic Press, New York, N.Y., 1962, pp. 447-531.
3. (a) M. J. Cohen, A. F. Garito, A. J. Heeger, A. G. MacDiarmid, C. M. Mikulski, M. S. Saran and J. Kleppinger, J. Amer. Chem. Soc., 98, 3844 (1976); (b) R. H. Baughman, R. R. Chance and M. J. Cohen, J. Chem. Phys., 64, 1869 (1976); (c) R. H. Baughman, J. Polym. Sci., Polym. Phys. Ed., 12, 1511 (1974) and references therein; (d) M. D. Cohen and B. S. Green, Chem. Brit., 9, 490 (1973); (e) I. C. Paul and D. Y. Curtin, Accounts Chem. Res., 6, 217 (1973); G. Adler, Trans. Amer. Cryst. Assn., 7, 55 (1971).
4. (a) R. A. Walton and R. Whyman, J. Chem. Soc. [A], 1394 (1968); (b) M. G. B. Drew, D. F. Lewis and R. A. Walton, J. Chem. Soc., Chem. Commun., 326 (1969): we have been informed by Dr. Drew that the coordinates for this structure were inadvertently destroyed.
5. The material is probably  $\text{NiBr}_2\text{CEP}$  (ref. 4a); it crystallizes in a trilled orthorhombic unit cell, and our structure analysis is as yet incomplete.



6. Coordinates:  $\pm (x, y, z)$ ;  $\pm (x, \frac{1}{2}-y, \frac{1}{2}+z)$ ;  $\pm (\frac{1}{2}+x, y, \frac{1}{2}+z)$ ;  $\pm (\frac{1}{2}+x, \frac{1}{2}-y, z)$ .
7. L. S. D. Glasser, F. P. Glasser, and H. F. W. Taylor, Quart Rev. (London), 16, 343 (1962). For our own working definition of topotaxy, we further require that the diffraction patterns of reactant and product lattices be observable on X-ray diffraction photographs at all times during the reaction.
8. K. Cheng and B. M. Foxman, unpublished observations.

Figure Caption

Figure 1. Pairs of reactant and product molecules viewed normal to the ab plane of the respective unit cells. Reaction front motion is slowest in the a direction.



- N
- C
- P
- Ni
- Br



Abstract

The solid-state reaction of square-planar  $\text{NiBr}_2[\text{P}(\text{CH}_2\text{CH}_2\text{CN})_3]_2$  has been shown to lead to highly oriented crystals of octahedral polymer. Reaction of the monomer in the solid-state at  $-5^\circ$  leads to product which is characterized by (a) freedom from the usual contaminants arising from reaction in solution; (b) stereospecificity, leading to formation of strictly linear polymer; and (c) topotaxy, in which ( $a^*$  reactant,  $a^*$  product), ( $b^*$  reactant,  $b^*$  product) are aligned for the orthorhombic reactant and monoclinic product phases; further, no twinning is observable in the product. There is a negligible volume change involved in the polymerization ( $\sim 0.3\%$ ). Individual single crystals react at  $-5^\circ$  with a well-defined front passing across the crystal, virtually parallel to a (100) face. This is consistent with the observation that only the a axis of the reactant crystal must reorient to form the product pseudomorph.

APPROXIMATELY

||

TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. of Copies</u>		<u>No. of Copies</u>
Office of Naval Research Arlington, VA 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, VA 22314	12
Office of Naval Research Arlington, VA 22217 Attn: Code 100IP	6	U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709 Attn: CRD-AA-IP	
ONR Branch Office 536 S. Clark Street Chicago, IL 60605 Attn: Dr. George Sandoz	1	Commander Naval Undersea Research & Development Center San Diego, California 92132 Attn: Technical Library, Code 133	1
ONR Branch Office 1030 East Green Street Pasadena, CA 91106 Attn: Dr. R. J. Marcus	1	Naval Weapons Center China Lake, CA 93555 Attn: Head, Chemistry Division	1
ONR Branch Office 715 Broadway New York, NY 10003 Attn: Scientific Dept.	1	Naval Civil Engineering Laboratory Port Hueneme, CA 93041 Attn: Mr. W. S. Haynes	1
ONR Branch Office 760 Market Street, Rm. 447 San Francisco, CA 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, CA 93940	
ONR Branch Office 495 Summer Street Boston, MA 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps Washington, D.C. 20380 Attn: Code RD-1	1
Director, Naval Research Laboratory Washington, D.C. 20390 Attn: Library, Code 2029 (ONRL) Technical Info. Div. Code 6100, 6170	6 1 1		
The Asst. Secretary of the Navy (R&D) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1		
Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser)	1		

TECHNICAL REPORT DISTRIBUTION LIST

	<u>No. of Copies</u>		<u>No. of Copies</u>
Dr. W. N. Lipscomb Department of Chemistry Harvard University Cambridge, MA 02138	1	Dr. A. Cowley University of Texas Department of Chemistry Austin, TX 78712	1
Dr. R. M. Grimes Department of Chemistry University of Virginia Charlottesville, VA 22903	1	Dr. W. Hatfield Department of Chemistry University of North Carolina Chapel Hill, NC 27514	1
Dr. M. Tsutsui Department of Chemistry Texas A&M University College Station, TX 77843	1	Dr. D. Seyferth Department of Chemistry Massachusetts Institute of Technology Cambridge, MA 02139	1
Dr. M. F. Hawthorne Department of Chemistry University of California Los Angeles, CA 90024	1	Dr. M. H. Chisholm Department of Chemistry Princeton University Princeton, NJ 08540	1
Dr. D. B. Brown Department of Chemistry University of Vermont Burlington, VT 05401	1	Dr. B. Foxman Department of Chemistry Brandeis University Waltham, MA 02154	1
Dr. Alan Siedle National Bureau of Standards Department of Commerce Chemistry Section Washington, D.C. 20375	1		
Dr. W. B. Fox Naval Research Laboratory Chemistry Division Code 6130 Washington, D.C. 20375	1		
Dr. R. J. Lagow University of Texas Department of Chemistry Austin, TX 78712	1		