

AD-A040 430

GRUMMAN AEROSPACE CORP BETHPAGE N Y RESEARCH DEPT
FAST NEUTRON INDUCED ACTIVITY OF ELEMENTS RELEVANT TO FUSION RE--ETC(U)
APR 77 E A KAMYKOWSKI


F/G 18/11

UNCLASSIFIED


RM-631

NL

| OF |
AD
A040430



END
DATE
FILMED
7-77



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

RM-631

FAST NEUTRON INDUCED ACTIVITY
OF ELEMENTS RELEVANT TO FUSION
REACTOR STRUCTURAL DESIGN

April 1977

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER RM-631	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Fast Neutron Induced Activity of Elements Relevant to Fusion Reactor Structural Design		5. TYPE OF REPORT & PERIOD COVERED Memorandum
7. AUTHOR(s) E. Kamykowski		6. PERFORMING ORG. REPORT NUMBER RM-631
9. PERFORMING ORGANIZATION NAME AND ADDRESS Grumman Aerospace Corporation Bethpage, New York 11714		8. CONTRACT OR GRANT NUMBER(s) N/A
11. CONTROLLING OFFICE NAME AND ADDRESS N/A		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS N/A
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) N/A		12. REPORT DATE April 1977
		13. NUMBER OF PAGES 58
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) N/A		
18. SUPPLEMENTARY NOTES N/A		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The designer of nuclear fusion devices must consider the problem of induced activation of system components resulting from irradiation by the generated neutron flux. Requirements for maintenance and repair, as well as for storage of exposed equipment, can be directly affected by the levels of activity induced and by the radioactive decay characteristics of the constituent elements. Since the activation cross sections and decay proper-		

DD FORM 1473
1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Properties of these elements have been tabulated, the induced activity of different structural materials can be computed and analyzed.

We describe a computer program developed to catalog isotopic activities obtained for 19 elements following seven day and one year exposures to an intense flux of 14 MeV neutrons. These elements comprise the most prominent components of reactor-related structural materials. The results are presented as decay curves for each element, including the contributions from each isotope. This compilation makes possible a graphic analysis of the activation and decay properties for each element listed and permits comparison of anticipated levels of total activity for different elements. In addition, activation of representative alloys is simulated by combination of constituent element activities. Examples of this application are present in plots of radioactive decay curves generated for Inconel, Nitronic 33, and 304 steel.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Grumman Research Department Memorandum RM-631

14

13

FAST NEUTRON INDUCED ACTIVITY OF ELEMENTS
RELEVANT TO FUSION REACTOR STRUCTURAL DESIGN.

6

by

9 Memorandum rept.

10

E. A. Kamykowski

Nuclear and Astrophysics

11

April 1977

12 62 p.

DDC
RECEIVED
JUN 18 1977
RECEIVED

AS A

Approved by:

Richard A. Scheuing
Richard A. Scheuing
Director of Research

406 165

DISTRIBUTION STATEMENT A
Approved for public release;
Distribution Unlimited

ACKNOWLEDGMENTS

The author wishes to acknowledge the many fruitful discussions with E. Schneid that helped shape the final content of this work.

I also wish to thank A. Favale for the interesting applications he has proposed for this program, and M. D'Agostino and M. Stauber for their direction during its development.

APPROVED BY	
DATE	NON EXIST <input checked="" type="checkbox"/>
BY	BY NAME <input type="checkbox"/>
REVISIONS	<input type="checkbox"/>
REVISIONS	<input type="checkbox"/>
CLASSIFICATION/AVAILABILITY CODES	
AUTH. DIV./SPECIAL	
A 23	978

ABSTRACT

The designer of nuclear fusion devices must consider the problem of induced activation of system components resulting from irradiation by the generated neutron flux. Requirements for maintenance and repair, as well as for storage of exposed equipment, can be directly affected by the levels of activity induced and by the radioactive decay characteristics of the constituent elements. Since the activation cross sections and decay properties of these elements have been tabulated, the induced activity of different structural materials can be computed and analyzed.

We describe a computer program developed to catalog isotopic activities obtained for 19 elements following seven day and one year exposures to an intense flux of 14 MeV neutrons. These elements comprise the most prominent components of reactor-related structural materials. The results are presented as decay curves for each element, including the contributions from each isotope. This compilation makes possible a graphic analysis of the activation and decay properties for each element listed and permits comparison of anticipated levels of total activity for different elements. In addition, activation of representative alloys is simulated by combination of constituent element activities. Examples of this application are present in plots of radioactive decay curves generated for Inconel, Nitronic 33, and 304 steel.

TABLE OF CONTENTS

<u>Item</u>	<u>Page</u>
Introduction	1
Description of Program	1
Conclusion	9
Appendices:	
A. Listing of Program ACTALLOY	13
B. Decay Curves - Seven Day Activation	16
C. Decay Curves - One Year Activation	36

PRECEDING PAGE BLANK NOT FILMED

LIST OF ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1	Radioactive Decay of 304 Steel and Constituents Following 1000 Sec Irradiation by 10^{13} n/(cm ² -sec) Flux of 14 MeV Neutrons	11
2	Comparison of Radioactive Decay Curves for Inconel, Nitronic 33, and Fe-Ni Alloy (A-286) Following 1000 Sec Irradiation by 10^{13} n/(cm ² -sec) Flux of 14 MeV Neutrons	12


LIST OF TABLES

<u>Table</u>		<u>Page</u>
1	List of Reactions	4
2	Conversion to Standard Time Units	8

PRECEDING PAGE, BLANK, NOT FILMED

INTRODUCTION

The designer of future fusion reactors must give serious consideration to the activation properties of structural materials exposed to a substantial fast neutron flux. The principal fusion reaction



envisioned for power reactors, produces neutrons of approximately 14 MeV. While scattering of the high energy neutrons to lower energies is expected, a large fraction of neutrons impinging on the critical "first wall" structures will be within the 14 MeV range.

In order to categorize the fundamental activation and radioactive decay characteristics of possible structural materials, a computer code has been generated which simulates exposure of pertinent elements and alloys to a high flux of 14 MeV neutrons and traces the decay of the induced activity. Plots of specific activity versus time are compiled and describe the characteristic decay properties of the radioactive products that can be generated in a fusion reactor.

This memorandum has been prepared to provide a reference that can be used as a guide in the selection of materials for fusion reactor first wall structures. Since elements can be examined separately by the computer program, the activation problems associated with alloying constituents can be easily identified.

DESCRIPTION OF PROGRAM

PARAMETERS

We have simulated the continuous irradiation of 19 different elements by a 10^{15} n/(cm²-sec) flux of 14 MeV neutrons for durations of seven days and one year. The flux level and irradiation

periods correspond to possible operating conditions for a fusion power reactor. The short period is selected to simulate the activity to be expected at maintenance periods during test operations while the long irradiation time is used to obtain the radioactivity levels anticipated after long term power generation.

The principal neutron-induced reactions, the 14 MeV cross sections, and the associated half lives for each of the related isotopes are presented in Table 1. Reactions are included which have cross sections greater than 0.03 mb and have product half lives between one minute and 10^6 years. Fractional abundances entered for each correspond to the naturally occurring weight ratios.

PROGRAM OPERATION

The program incorporates the options of analyzing an alloy composed of the listed elements or of selecting one or all of these elements for calculation. If one element is selected, the routine enters a request for the symbol of the element of interest and proceeds to search for the data array containing the parameters of the pertinent isotopes. If calculation of an alloy is required the number of elements and their respective symbols and weight fractions must be entered.

The calculation describing the isotopic induced activity contributing to the activation of an alloy is expressed as follows

$$A = \frac{W_a f N_o \rho}{A_o} (\sigma \phi) [1 - \exp(-0.693 t_1 / T_{\frac{1}{2}})] [\exp(-0.693 t_2 / T_{\frac{1}{2}})]$$

where

A = induced activity (dis/sec - cm^3)

ρ = density (gm/cm^3)

N_o = Avogadro number (6.02×10^{23})

W_a = weight fraction of element in alloy
 f = fractional abundance (natural)
 A_o = atomic weight
 $\sigma(\text{mb})$ = cross section (units of millibarns)
 ϕ = flux [entered as 10^{15} n/(cm²-sec) in the program]
 $T_{\frac{1}{2}}$ = half life (hrs)
 t_1 = irradiation period
 t_2 = decay period

Disintegrations per sec/cm³ are converted to Curies/cm³ (1 Curie = 3.7×10^{10} dis/sec). To permit logarithmic representation a zero check is made, and if encountered, sets $A = 10^{-77}$.

At the end of the computation a disk file is automatically created for data storage (identified by elemental symbol or alloy name). A file for an element consists of a set of records containing the calculated activity of each reaction listed for it and one final record describing the total response for that element. A file created for an alloy consists of a record for each constituent element and a final record containing the data for the total response of the alloy.

Different irradiation time, alternate units of decay time representation, and additional elements may be easily introduced. Subsequent running of the program replaces the original file content with those data calculated with the new parameters. A listing of the program is presented in Appendix A.

TABLE 1 LIST OF REACTIONS

Reaction	No.	$T_{1/2}$ (hrs)	$\sigma(14-15 \text{ MeV})$ (mb)	Frac Abun
$^{24}\text{Mg}(n,p)^{24}\text{Na}$	1	15.0	175	0.787
$^{27}\text{Al}(n,2n)^{26}\text{Al}$	1	6.5×10^9	4.5	1
$^{27}\text{Al}(n,p)^{27}\text{Mg}$	2	0.158	83	1
$^{27}\text{Al}(n,\alpha)^{24}\text{Na}$	3	15.0	115	1
$^{28}\text{Si}(n,p)^{28}\text{Al}$	1	0.039	200	0.922
$^{29}\text{Si}(n,p)^{29}\text{Al}$	2	0.110	225	0.047
$^{31}\text{P}(n,2n)^{30}\text{P}$	1	0.042	10	1
$^{31}\text{P}(n,p)^{31}\text{Si}$	2	2.62	110	1
$^{31}\text{P}(n,\alpha)^{28}\text{Al}$	3	0.039	115	1
$^{32}\text{S}(n,p)^{32}\text{P}$	1	343.2	225	0.95
$^{34}\text{S}(n,\alpha)^{31}\text{Si}$	2	2.62	130	0.0422
$^{36}\text{S}(n,2n)^{35}\text{S}$	3	2112	20	0.00014
$^{39}\text{K}(n,2n)^{38}\text{K}$	1	0.129	3.5	0.931
$^{39}\text{K}(n,p)^{39}\text{Ar}$	2	2.4×10^6	360	0.931
$^{39}\text{K}(n,\alpha)^{36}\text{Cl}$	3	2.7×10^9	108	0.931
$^{41}\text{K}(n,2n)^{40}\text{K}$	4	1.1×10^{13}	450	0.0688
$^{41}\text{K}(n,p)^{41}\text{Ar}$	5	1.83	78	0.0688
$^{41}\text{K}(n,\alpha)^{38}\text{Cl}$	6	0.622	28	0.0688
$^{46}\text{Ti}(n,2n)^{45}\text{Ti}$	1	3.09	33	0.0793
$^{46}\text{Ti}(n,p)^{46}\text{Sc}$	2	2016	285	0.0793
$^{47}\text{Ti}(n,p)^{47}\text{Sc}$	3	81.6	120	0.0728
$^{47}\text{Ti}(n,pn)^{46}\text{Sc}$	4	2016	50	0.0728
$^{48}\text{Ti}(n,p)^{48}\text{Sc}$	5	44	62	0.7394
$^{48}\text{Ti}(n,\alpha)^{45}\text{Ca}$	6	3960	47	0.7394
$^{48}\text{Ti}(n,pn)^{47}\text{Sc}$	7	81.6	12.4	0.7394
$^{49}\text{Ti}(n,p)^{49}\text{Sc}$	8	0.958	33	0.0551
$^{49}\text{Ti}(n,pn)^{48}\text{Sc}$	9	44	15	0.0551
$^{50}\text{Ti}(n,p)^{50}\text{Sc}$	10	0.030	22	0.0534
$^{50}\text{Ti}(n,\alpha)^{47}\text{Ca}$	11	112.8	8.6	0.0534
$^{50}\text{V}(n,2n)^{49}\text{V}$	1	7920	575	0.0024
$^{50}\text{V}(n,\alpha)^{47}\text{Sc}$	2	81.6	35	0.0024
$^{51}\text{V}(n,2n)^{50}\text{V}$	3	5.3×10^{19}	750	0.9976
$^{51}\text{V}(n,p)^{51}\text{Ti}$	4	0.097	35	0.9976
$^{51}\text{V}(n,\alpha)^{48}\text{Sc}$	5	44	25	0.9976
$^{51}\text{V}(n,\alpha n)^{47}\text{Sc}$	6	81.6	4.5	0.9976
$^{50}\text{Cr}(n,2n)^{49}\text{Cr}$	1	0.70	22	0.0431
$^{50}\text{Cr}(n,pn)^{49}\text{V}$	2	7920	200	0.0431
$^{52}\text{Cr}(n,2n)^{51}\text{Cr}$	3	667.2	350	0.8376
$^{52}\text{Cr}(n,p)^{52}\text{V}$	4	0.063 4	112	0.8376

TABLE 1 (CONT) LIST OF REACTIONS

Reaction	No.	$T_{1/2}$ (hrs)	$\sigma(14-15 \text{ MeV})$ (mb)	Frac Abun
$^{53}\text{Cr}(n,p)^{53}\text{V}$	5	0.033	40	0.0955
$^{54}\text{Cr}(n,\alpha)^{51}\text{Ti}$	6	0.097	16	0.0238
$^{55}\text{Mn}(n,2n)^{54}\text{Mn}$	1	7272	950	1
$^{55}\text{Mn}(n,p)^{55}\text{Cr}$	2	0.058	87	1
$^{55}\text{Mn}(n,\alpha)^{52}\text{V}$	3	0.063	34	1
$^{54}\text{Fe}(n,2n)^{53}\text{Fe}$	1	0.142	15.5	0.0582
$^{54}\text{Fe}(n,p)^{54}\text{Mn}$	2	7272	360	0.0582
$^{54}\text{Fe}(n,\alpha)^{51}\text{Cr}$	3	667.2	95	0.0582
$^{54}\text{Fe}(n,pn)^{53}\text{Mn}$	4	1.75×10^{10}	175	0.0582
$^{56}\text{Fe}(n,2n)^{55}\text{Fe}$	5	23652	400	0.9166
$^{56}\text{Fe}(n,p)^{56}\text{Mn}$	6	2.58	108	0.9166
$^{57}\text{Fe}(n,p)^{57}\text{Mn}$	7	0.028	95	0.0219
$^{57}\text{Fe}(n,pn)^{56}\text{Mn}$	8	2.58	13	0.0219
$^{58}\text{Fe}(n,\alpha)^{55}\text{Cr}$	9	0.058	14	0.0033
$^{58}\text{Fe}(n,p)^{58}\text{Mn}$	10	0.018	20	0.0033
$^{59}\text{Co}(n,2n)^{58}\text{Co}$	1	1704	265	1
$^{59}\text{Co}(n,2n)^{*}^{58m}\text{Co}$	2	9.0	400	1
$^{59}\text{Co}(n,p)^{59}\text{Fe}$	3	1080	80	1
$^{59}\text{Co}(n,\alpha)^{56}\text{Mn}$	4	2.58	28	1
$^{58}\text{Ni}(n,2n)^{57}\text{Ni}$	1	36	33	0.6780
$^{58}\text{Ni}(n,p)^{58}\text{Co}$	2	1704	400	0.6788
$^{58}\text{Ni}(n,p)^{*}^{58m}\text{Co}$	3	9.0	360	0.6788
$^{58}\text{Ni}(n,\alpha)^{57}\text{Co}$	4	6528	550	0.6788
$^{58}\text{Ni}(n,\alpha)^{55}\text{Fe}$	5	23652	150	0.6788
$^{58}\text{Ni}(n,pn)^{57}\text{Co}$	6	6408	550	0.6788
$^{60}\text{Ni}(n,2n)^{59}\text{Ni}$	7	7.0×10^8	300	0.2623
$^{60}\text{Ni}(n,p)^{60}\text{Co}$	8	46078	120	0.2623
$^{60}\text{Ni}(n,p)^{*}^{60m}\text{Co}$	9	0.175	12	0.2623
$^{61}\text{Ni}(n,p)^{61}\text{Co}$	10	1.65	96	0.0119
$^{61}\text{Ni}(n,pn)^{60}\text{Co}$	11	46078	3.7	0.0119
$^{61}\text{Ni}(n,pn)^{*}^{60m}\text{Co}$	12	0.175	3.7	0.0119
$^{62}\text{Ni}(n,p)^{62}\text{Co}$	13	0.232	22	0.0366
$^{62}\text{Ni}(n,p)^{*}^{62m}\text{Co}$	14	0.027	22	0.0366
$^{62}\text{Ni}(n,\alpha)^{59}\text{Fe}$	15	1080	20	0.0366
$^{62}\text{Ni}(n,pn)^{61}\text{Co}$	16	1.65	4.3	0.0366
$^{64}\text{Ni}(n,2n)^{63}\text{Ni}$	17	8.1×10^5	1030	0.0108
$^{64}\text{Ni}(n,p)^{64}\text{Co}$	18	0.130	3	0.0108

TABLE 1 (CONT) LIST OF REACTIONS

Reaction	No.	T _{1/2} (hrs)	$\sigma(14-15 \text{ MeV})$ (mb)	Frac Abun
$^{64}\text{Ni}(n,p)^{*}^{64\text{m}}\text{Co}$	19	0.033	3	0.0108
$^{64}\text{Ni}(n,\alpha)^{61}\text{Fe}$	20	0.10	1.5	0.0108
$^{63}\text{Cu}(n,2n)^{62}\text{Cu}$	1	0.165	550	0.6909
$^{63}\text{Cu}(n,p)^{63}\text{Ni}$	2	8.1×10^5	119	0.6909
$^{63}\text{Cu}(n,\alpha)^{60}\text{Co}$	3	4.6×10^4	35	0.6909
$^{63}\text{Cu}(n,\alpha)^{*}^{60\text{m}}\text{Co}$	4	0.175	23	0.6909
$^{63}\text{Cu}(n,\text{He}^3)^{61}\text{Co}$	5	1.65	2	0.6909
$^{65}\text{Cu}(n,2n)^{64}\text{Cu}$	6	12.9	950	0.6909
$^{65}\text{Cu}(n,p)^{65}\text{Ni}$	7	2.56	21	0.3091
$^{65}\text{Cu}(n,\alpha)^{62}\text{Co}$	8	0.232	12.5	0.3091
$^{65}\text{Cu}(n,\alpha)^{*}^{62\text{m}}\text{Co}$	9	0.027	1.9	0.3091
$^{65}\text{Cu}(n,\alpha n)^{61}\text{Co}$	10	1.65	2.8	0.3091
$^{64}\text{Zn}(n,2n)^{63}\text{Zn}$	1	0.63	175	0.4889
$^{64}\text{Zn}(n,p)^{64}\text{Cu}$	2	12.9	180	0.4889
$^{66}\text{Zn}(n,2n)^{65}\text{Zn}$	3	5880	600	0.2781
$^{66}\text{Zn}(n,p)^{66}\text{Cu}$	4	0.085	77	0.2781
$^{66}\text{Zn}(n,\alpha)^{63}\text{Ni}$	5	8.1×10^5	50	0.2781
$^{67}\text{Zn}(n,p)^{67}\text{Cu}$	6	61	56	0.0411
$^{67}\text{Zn}(n,pn)^{66}\text{Cu}$	7	0.085	20	0.0411
$^{68}\text{Zn}(n,\alpha)^{65}\text{Ni}$	8	2.56	18	0.1857
$^{68}\text{Zn}(n,pn)^{67}\text{Cu}$	9	59	2.5	0.1857
$^{70}\text{Zn}(n,2n)^{69}\text{Zn}$	10	0.92	310	0.0062
$^{70}\text{Zn}(n,2n)^{*}^{69\text{m}}\text{Zn}$	11	14	920	0.0062
$^{70}\text{Zn}(n,\alpha)^{67}\text{Ni}$	12	0.014	11	0.0062
$^{92}\text{Mo}(n,2n)^{91}\text{Mo}$	1	0.258	160	0.1584
$^{92}\text{Mo}(n,2n)^{*}^{91\text{m}}\text{Mo}$	2	0.018	16	0.1584
$^{92}\text{Mo}(n,p)^{92}\text{Nb}$	3	242.4	65	0.1584
$^{92}\text{Mo}(n,\alpha)^{89}\text{Zn}$	4	78.4	19	0.1584
$^{92}\text{Mo}(n,\alpha)^{*}^{89\text{m}}\text{Zn}$	5	0.07	6.5	0.1584
$^{92}\text{Mo}(n,pn)^{*}^{91\text{m}}\text{Nb}$	6	1488	44	0.1584
$^{94}\text{Mo}(n,2n)^{93}\text{Mo}$	7	8.8×10^6	570	0.0904
$^{94}\text{Mo}(n,2n)^{*}^{93\text{m}}\text{Mo}$	8	6.9	570	0.0904
$^{94}\text{Mo}(n,p)^{94}\text{Nb}$	9	1.75×10^8	6	0.0904
$^{94}\text{Mo}(n,p)^{*}^{94\text{m}}\text{Nb}$	10	0.105	6	0.0904
$^{95}\text{Mo}(n,p)^{95}\text{Nb}$	11	840	26	0.1572
$^{95}\text{Mo}(n,p)^{*}^{95\text{m}}\text{Nb}$	12	90	26	0.1572
$^{95}\text{Mo}(n,pn)^{94}\text{Nb}$	13	1.75×10^8	6.5	0.1572

TABLE 1 (CONT) LIST OF REACTIONS

Reaction	No.	T ₁ (hrs)	$\sigma(14-15 \text{ MeV})$ (mb)	Frac Abun
$^{95}\text{Mo}(n, pn^*)^{94m}\text{Nb}$	14	0.105	6.5	0.1572
$^{96}\text{Mo}(n, p)^{96}\text{Nb}$	15	23	27	0.1653
$^{96}\text{Mo}(n, \alpha)^{93}\text{Zn}$	16	1.3×10^{10}	13.5	0.1653
$^{96}\text{Mo}(n, pn)^{95}\text{Nb}$	17	840	5	0.1653
$^{96}\text{Mo}(n, pn^*)^{95m}\text{Nb}$	18	90	1.8	0.1653
$^{97}\text{Mo}(n, p)^{97}\text{Nb}$	19	1.2	78	0.0946
$^{97}\text{Mo}(n, p^*)^{97m}\text{Nb}$	20	0.017	7.7	0.0946
$^{97}\text{Mo}(n, pn)^{96}\text{Nb}$	21	23	2.4	0.0946
$^{98}\text{Mo}(n, p)^{98}\text{Nb}$	22	0.858	14	0.2378
$^{98}\text{Mo}(n, pn)^{97}\text{Nb}$	23	1.2	0.8	0.2378
$^{98}\text{Mo}(n, pn^*)^{97m}\text{Nb}$	24	0.017	0.25	0.2378
$^{100}\text{Mo}(n, 2n)^{99}\text{Mo}$	25	67	2250	0.0963
$^{100}\text{Mo}(n, \alpha)^{97}\text{Zn}$	26	17	13.5	0.0963
$^{107}\text{Ag}(n, 2n)^{106}\text{Ag}$	1	0.4	700	0.5182
$^{107}\text{Ag}(n, 2n^*)^{106m}\text{Ag}$	2	201.6	530	0.5182
$^{107}\text{Ag}(n, \alpha n^*)^{103m}\text{Rh}$	3	0.95	2	0.5182
$^{109}\text{Ag}(n, 2n)^{108}\text{Ag}$	4	0.04	950	0.4818
$^{109}\text{Ag}(n, 2n^*)^{108m}\text{Ag}$	5	43800	28	0.4818
$^{109}\text{Ag}(n, p)^{109}\text{Pd}$	6	13.5	7.2	0.4818
$^{109}\text{Ag}(n, p^*)^{109}\text{Pd}$	7	0.078	7.2	0.4818
$^{109}\text{Ag}(n, \alpha^*)^{106m}\text{Rh}$	8	2.167	25	0.4818
$^{109}\text{Ag}(n, \alpha n)^{105}\text{Rh}$	9	35.9	0.55	0.4818
$^{93}\text{Nb}(n, 2n^*)^{92m}\text{Nb}$	1	242.4	430	1
$^{93}\text{Nb}(n, p)^{93}\text{Zn}$	2	$1.3\text{E}10$	44	1
$^{93}\text{Nb}(n, \alpha)^{90}\text{Y}$	3	64.2	9.5	1
$^{93}\text{Nb}(n, \alpha^*)^{90m}\text{Y}$	4	3.2	5.5	1
$^{93}\text{Nb}(n, n^*)^{93m}\text{Nb}$	5	32412	330	1
$^{180}\text{Ta}(n, 2n)^{179}\text{Ta}$	1	14400	2250	0.000123
$^{180}\text{Ta}(n, n^*)^{180m}\text{Ta}$	2	8.1	1000	0.000123
$^{181}\text{Ta}(n, 2n^*)^{180m}\text{Ta}$	3	8.1	1100	0.99988
$^{181}\text{Ta}(n, 3n)^{179}\text{Ta}$	4	14400	2	0.99988
$^{181}\text{Ta}(n, p)^{181}\text{HF}$	5	1020	2.6	0.99988
$^{181}\text{Ta}(n, \alpha)^{178}\text{Lu}$	6	0.5	1.2	0.99988
$^{181}\text{Ta}(n, \alpha^*)^{178m}\text{Lu}$	7	0.33	0.03	0.99988
$^{13}\text{C}(n, \alpha)^{10}\text{Be}$	1	$2.4\text{E}10$	130	0.0111
$^{10}\text{B}(n, t)^8\text{Be}$	1	$1.08\text{E}5$	100	0.196
$^{11}\text{B}(n, t)^9\text{Be}$	2	$1.08\text{E}5$	17.2	0.804

USE OF CURVES

The plots of radioactive decay for the seven day and one year operations are given in Appendices B and C, respectively. The data in this report are presented in a log-log display, with the abscissa in units of years from 10^{-6} to 10^3 and the ordinate in Curies/cm^3 , specific activity, encompassing values from 10^{-3} to 10^4 . The use of many orders of magnitude for both axes permits the compact display of the total responses as well as the distinct contribution of individual reaction to this activity for different decay times.

The actual data points plotted correspond to abscissa values $E+n$ and $\sqrt{10} E+n$ where $E+n$ is 10^{+n} ($-6 \leq n \leq 3$). The lines connecting these points are meant to guide the eye and to display the over-all trend of the decay curve. A listing relating 10^{+n} years to more conventional time units (i.e., 10^{-6} years = 31.6 sec) is presented in Table 2.

TABLE 2 CONVERSION TO STANDARD TIME UNITS

<u>Years</u>	<u>Convenient Time Units</u>
1E3	1000 yrs
1E2	100 yrs
1E1	10 yrs
1E0	1 yr
1E-1	36.5 days
1E-2	3.65 days
1E-3	8.76 hrs
1E-4	52.6 min
1E-5	5.26 min
1E-6	31.6 sec

For the sake of brevity, the data plotted here are derived from an arbitrarily chosen set of parameters: 10^{15} n/(cm²-sec), 14 MeV neutrons, seven day and one year irradiations, natural abundances. The value of specific activity, however, may be easily adjusted to reflect a different flux level or an assumed weight fraction by application of the appropriate multiplication factor. For example, the activity obtained with the stipulated flux of 10^{15} n/(cm²-sec) may be varied to reflect that expected at 10^{14} by multiplying by 1/10. By the use of appropriate factors, the plotted data can easily be generalized to provide information about a variety of physical conditions without resorting to the generation of individual plots for each parameter change.

An example of the application of the program option for analysis of alloys is presented in Figs. 1 and 2. The first figure displays the total activity obtained for 304 steel following irradiation by a 10^{13} n/(cm²-sec) flux of 14 MeV neutrons for a 1000 sec period. The weight percent of the constituent elements in the alloy and their respective activity contributions are indicated in this figure. Figure 2 demonstrates another study in which the activation characteristics of different alloys are to be compared. The activation conditions for this comparison are the same as those used to generate the curves in Fig. 1. For the sake of clarity, the constituent contributions for each alloy are not plotted.

CONCLUSION

The set of curves tabulated in this report permits a compact graphic compilation of activation and radioactive decay characteristics for 19 elements of importance in fusion reactor structural

design. In addition, the program incorporates the option to examine alloys composed of the listed elements. Requirements for evaluation of activation effects based upon more detailed flux and spectral distributions can be accommodated as they arise. In this regard, the present report serves not only as a useful reference but also as a basis for future simulation.

304 STEEL




Fig. 1 Radioactive Decay of 304 Steel and Constituents Following 1000 Sec Irradiation by 10^{13} n/(cm²-sec) Flux of 14 MeV Neutrons

ALLOY COMPARISON




Fig. 2 Comparison of Radioactive Decay Curves for Inconel, Nitronic 33, and Fe-Ni Alloy (A286), Following 1000 Sec Irradiation by 10^{13} n/(cm²-sec) Flux of 14 MeV Neutrons

APPENDIX A
LISTING OF PROGRAM ACTALLOY

```

630 PRINT #1,1000*((-13+K)/2),BE1,KJ
640 NEXT K
650 PRINT #1,END
660 IF Y8=V THEN 830
670 IF N8=N THEN 830
680 FOR K=1 TO 25
690 PRINT #2,1000*((-13+K)/2),BE1,KJ
700 DEL,KJ=BE1,KJ
710 NEXT K
720 PRINT #2,END
730 READ #2,REC(2)*1
740 IF JCR THEN 220
750 MAT F=CON
760 MAT H=F#E
770 FOR K=1 TO 25
780 PRINT #2,1000*((-13+K)/2),HE1,KJ
790 NEXT K
800 PRINT #2,END
810 PRINT #8,HE1,1J
820 STOP
830 PRINT #8,BE1,1J
840 IF Y8=V THEN 270
850 STOP

```

```

ACTALLOY
10 REM COMPUTE SPECIFIC ACTIVITY
20 REM ELEMENTS NB,TA,C,B
30 REM ELEMENTS MG,AL,SI,P,S,K,TI,U,CR,MN,FE,CO,NI,CU,ZN,AG,MO
40 FILES X,X
50 DIM GRC(2),MRE(2),Y8E(1),MRE(1),S8C(8)
60 REM UGT, FRAC IS SET TO 1 IN NEXT LINE
70 U1=1
80 DIM ACS(3),LICS(3),DCS(3),RE1,5(3),BE1,25J,TIC(25)
90 DIM U(20),ETS(3),FC1,5(3),HE1,25J
100 REM FLUX =10-13 N/CM^2/SEC
110 F1=1E13
120 N0=6 02E23
130 INPUT "DO ALL ELEMENTS ? (YES OR NO) ",Y8
140 IF Y8=V THEN 260
150 INPUT "DOING AN ALLOY? ",N8
160 IF N8=N THEN 250
170 J=0
180 INPUT "ALLOY NAME (FILE) AND # OF ELEMENTS ",S8,M
190 REDIM ECM,25J,FL1,MJ
200 CREATE Q1,S8,M+1,106
210 ASSIGN S8,2,R0
220 J=J+1
230 INPUT "ELEMENT SYMBOL AND UGT FRAC. IN ALLOY ",M8,U1
240 GOTO 260
250 INPUT "ENTER SYMBOL OF REQUIRED ELEMENT ",M8
260 RESTORE
270 IF TYP(0)=3 THEN 850
280 IF TYP(0)=2 THEN 310
290 READ D1
300 GOTO 270
310 READ GS,M,R1,A1
320 IF Y8=V THEN 350
330 IF M=GS THEN 350
340 GOTO 270
350 CREATE Q1,GS,M+1,106
360 ASSIGN GS,1,R0
370 REDIM DCN,25J,ACN(1),LDC(1),M3
380 REM MRS, U=1, DAYS U=24, URS, U=168, MO.(39), U=720, YRS(365), U=8760
390 U=8760
400 REM T = DURATION OF OPERATION (HRS.)
410 T=1000/3600
420 FOR I=1 TO M
430 READ M1,S1,F2
440 L(1)=.693/M1
450 AC1=((R1N0XU1F2)/A1)YS1F1S(1E-27)S(1-EXP(-L(1)T))
460 C=0
470 FOR K=1 TO 25
480 TIC(3)=V(1000*((-13+K)/2))
490 REM HILICURIES/CC
500 C=AC1DEXP(-L(1)T(1DC))
510 C=C/(3 7E7)
520 IF C>0 THEN 540
530 C=1E-77
540 PRINT #1,1000*((-13+K)/2),C
550 DEL,KJ=C
560 NEXT K
570 PRINT #1,END
580 READ #1,REC(1)*1
590 NEXT I
600 MAT R=CON
610 MAT B=R#D
620 FOR K=1 TO 25

```

ACTALDY
 860 REN SYMBOL 8 OF REACTIONS. (CM/CC). AT UGT
 870 DATA 1.1 74.24 312
 880 REN T1/2(MRS). MBARNIS.FR ABUM
 890 DATA 15.175 787
 900 DATA 1.3 2 702.26 9815
 910 DATA 6.4859 5.1 158.83.1.15.115.1
 920 DATA 51.2.2.33.28 836
 930 DATA 039.200 922.11.225 047
 940 DATA 1.3 2 7.123 895
 950 DATA 042.10.1.2 62.110.1. 039.115.1
 960 DATA 5.3.2.07.32 064
 970 DATA 343.2.225.95.2 62.130. 0422.2112.20. 00014
 980 DATA 1.6 89.39 102
 990 DATA 129.3 5.931.2 36E5.360 931.2 27E9.108. 931
 1000 DATA 1.1E13.450. 0688.1 83.78. 0688. 622.28. 0688
 1010 DATA 11.4 5.47 9
 1020 DATA 3 09.33. 0793.2016.285. 0793.81 6.120. 0728
 1030 DATA 2016.50. 0728.44 62 7394.3960.47. 7394
 1040 DATA 81 6.12 4 7394 958.33. 0551.44.15. 0551
 1050 DATA 03.22. 0534.112 8.8 6. 0534
 1060 DATA 1.6 15.96.50 942
 1070 DATA 7920.575 0024 81 6.35. 0024.5 3E19.750. 9976
 1080 DATA 097.35 9975.44.25. 9975.81 6.4.5. 9976
 1090 DATA 0.6 7.2 51 936
 1100 DATA 7.22. 0432.7920.200. 0431.607 2.350. 8376
 1110 DATA 063.112. 8376. 033.40. 0355. 097.16. 0238
 1120 DATA 1.3 7 2.54 933
 1130 DATA 7272.550.1 053 87.1. 063.34.1
 1140 DATA 1.0 7 86.55 847.1
 1150 DATA 142.15 5. 0532. 7272.360 0532.047 2.95. 0532
 1160 DATA 1.75E19.1 75. 0532. 23552.400. 9160.2 58.108. 9165
 1170 DATA 028.95. 0219 2.58.13. 0219. 058.14. 0033. 018.20. 0033
 1180 DATA 4.0 3 58 933
 1190 DATA 1704.265.1 9.400.1.1080.80.1.2.58.28.1
 1200 DATA 1.1 58.8 9.58 71
 1210 DATA 36.33 6788.1704.400. 6788.9.360. 6788
 1220 DATA 628.550. 6788.23652.150. 6788.6408.550. 6788
 1230 DATA 758.300 2623.46078.120. 2623.175.12. 2623
 1240 DATA 1.65.55. 0119.46078.3 7. 0119.175.3 7. 0119
 1250 DATA 032.82. 0366. 027.22. 0366.100.20. 0366
 1260 DATA 1 65.4 3. 0366.806000.1030. 0108. 13.3. 0108
 1270 DATA 033.3 0108 1 1 5. 0108
 1280 DATA 0.10 8 92.63 546
 1290 DATA 165.550 6909.806000.119. 6909.46000.35. 6909
 1300 DATA 175.23. 6909.1 65.2 6909.12 9.950. 6909
 1310 DATA 2 56.21 3091 232.12 5. 3091. 027.1 9. 3091.1 65.2 8. 3091
 1320 DATA 71.12 7 14 65 37
 1330 DATA 63.175 4889.12 9.180. 4889.5880.600. 2781
 1340 DATA 085.77 2781.806000.50. 2781.61 56. 0411
 1350 DATA 085.20 0411 2 56 18. 1857.59 2 5. 1857
 1360 DATA 03 310 0062 14 920 0062 014 11 0062
 1370 DATA 10 9 10 5 107 868
 1380 DATA 4 700 5182 201 6 530 5182 95 2 5182
 1390 DATA 04 950 4818 423 0 28 4818 13 5 7 2 4818
 1400 DATA 078 7 2 4818 2167 25 4818 35 9 55 4818
 1410 DATA 10 26 10 2 95 94
 1420 DATA 258 160 1584 018 16 1584 242 4 65 1584
 1430 DATA 78 4 19 15 1 07 6 5 1524 1488 44 1584
 1440 DATA 8 7CE6 570 0904 6 9 570 0904 1 75E8 6 0904
 1450 DATA 10 5 0904 843 25 1572 90 26 1572
 1460 DATA 1 7 6 5 1572 05 6 5 1572 23 27 1653
 1470 DATA 1 31E10 13 5 1653 840 5 1653 90 1 8 1653

1480 DATA 1 2.78 0946 017 7 7 0946 23 2 4 0946
 1490 DATA 858 14 2378 1 2 8 2378 017 25 2378
 1500 DATA 67 2250 0963 17 13 5 0963
 1510 DATA NB 5 8 57 92 906
 1520 DATA 242 4 430 1 1 3E10 44 1 64 2 9 5 1
 1530 DATA 3 2 5 5 1 32412 330 1
 1540 DATA TA 7 16 6 180 948
 1550 DATA 14400 2250 000123 9 1 1000 000123 8 1 1100 00003
 1560 DATA 14400 2 99988 1020 2 6 99988
 1570 DATA 5 1 2 99988 33 03 99988
 1580 DATA C 1 2 1 12 012
 1590 DATA 2 4E10 130 0111
 1600 DATA B 2 2 35 10 811
 1610 DATA 108000 100 196 108000 17 2 304
 1620 END

APPENDIX B

DECAY CURVES - SEVEN DAY ACTIVATION

This appendix contains the radioactive decay curves (Figs. B-1 through B-19) generated by the computer code ACTALOY for 19 elements: Mg, Al, Si, P, S, K, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Zn, Ag, Mo, Nb, and Ta.

The data simulates the activity derived from a seven day continuous irradiation by a 10^{15} n/(cm²-sec) flux of 14 MeV neutrons.

The number adjacent to a curve refers to the reaction listed for the element in Table 1. The solid curve labeled "Total" represents the expected activity for an element obtained from the sum of its individually numbered isotope reactions.




Fig. B-1 Radioactive Decay Curves for Mg




Fig. B-2 Radioactive Decay Curves for Al




Fig. B-3 Radioactive Decay Curves for Si

PHOSPHORUS




Fig. B-4 Radioactive Decay Curves for P




Fig. B-5 Radioactive Decay Curves for S




Fig. B-6 Radioactive Decay Curves for K




Fig. B-7 Radioactive Decay Curves for Ti




Fig. B-8 Radioactive Decay Curves for V





Fig. B-9 Radioactive Decay Curves for Cr

MANGANESE



YEARS AFTER SHUTDOWN

Fig. B-10 Radioactive Decay Curves for Mn




Fig. B-11 Radioactive Decay Curves for Fe




Fig. B-12 Radioactive Decay Curves for Co




Fig. B-13 Radioactive Decay Curves for Ni




Fig. B-14 Radioactive Decay Curves for Cu




Fig. B-15 Radioactive Decay Curves for Zn




Fig. B-16 Radioactive Decay Curves for Ag

MOLYBDENUM




Fig. B-17 Radioactive Decay Curves for Mo




Fig. B-18 Radioactive Decay Curves for Nb




Fig. B-19 Radioactive Decay Curves for Ta

APPENDIX C

DECAY CURVES - ONE YEAR ACTIVATION

This appendix contains the radioactive decay curves (Figs. C-1 through C-19) generated by the computer code ACTALOY for 19 elements: Mg, Al, Si, P, S, K, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Zn, Ag, Mo, Nb, and Ta.

The data simulates the activity derived from a one year continuous irradiation by a 10^{15} n/(cm²-sec) flux of 14 MeV neutrons.

The number adjacent to a curve refers to the reaction listed for the element in Table 1. The solid curve labeled "Total" represents the expected activity for an element obtained from the sum of its individually numbered isotope reactions.




Fig. C-1 Radioactive Decay Curves for Mg




Fig. C-2 Radioactive Decay Curves for Al




Fig. C-3 Radioactive Decay Curves for Si

2-15-55




Fig. C-4 Radioactive Decay Curves for P




Fig. C-5 Radioactive Decay Curves for S




Fig. C-6 Radioactive Decay Curves for K




Fig. C-7 Radioactive Decay Curves for T1




Fig. C-8 Radioactive Decay Curves for V




Fig. C-9 Radioactive Decay Curves for Cr




Fig. C-10 Radioactive Decay Curves for Mn




Fig. C-11 Radioactive Decay Curves for Fe




Fig. C-12 Radioactive Decay Curves for Co




Fig. C-13 Radioactive Decay Curves for Ni




Fig. C-14 Radioactive Decay Curves for Cu




Fig. C-15 Radioactive Decay Curves for Zn




Fig. C-16 Radioactive Decay Curves for Ag

MEGARENVUJ




Fig. C-17 Radioactive Decay Curves for Mo




Fig. C-18 Radioactive Decay Curves for Nb




Fig. C-19 Radioactive Decay Curves for Ta