

AD-A041 867

EIC CORP NEWTON MASS

F/G 10/3

LITHIUM - INORGANIC ELECTROLYTE BATTERIES. (U)

JUN 77 J R DRISCOLL, G L HOLLECK, P G GUDRAIS DAAB07-74-C-0030

UNCLASSIFIED

C-401

ECOM-74-0030-13

NL

ADA041 867



END

DATE
FILMED

8-77





J
12
P.S.

ADA 041867

Research and Development Technical Report

ECOM-74-0030-13

LITHIUM-INORGANIC ELECTROLYTE BATTERIES

J. R. Driscoll
G. L. Holleck
P. G. Gudrais
S. B. Brummer

EIC Corporation
Newton, MA 02158



JUNE 1977

Thirteenth Progress Report for Period 01 January 1977 - 31 March 1977

DISTRIBUTION STATEMENT

Approved for Public Release;
Distribution Unlimited

DDC FILE COPY

Prepared for

ECOM

US ARMY ELECTRONICS COMMAND FORT MONMOUTH, NEW JERSEY 07703

NOTICES

Disclaimers

The findings of this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official government endorsement or approval of commercial products or services referenced herein.

Disposition

Destroy this report when it is no longer needed. Do not return to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

19 REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM	
1. REPORT NUMBER ECOM-74-0030-13	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER (9) progress	
4. TITLE (and Subtitle) LITHIUM - INORGANIC ELECTROLYTE BATTERIES.		5. TYPE OF REPORT & PERIOD COVERED Quarterly Report no. 13 01 Jan 1977 - 31 Mar 1977	
7. AUTHOR(s) Joseph R./Driscoll, Gerhard L./Holleck, Peter G./Gudrais, S. Barry/Brummer		6. PERFORMING ORG. REPORT NUMBER (14) C-401	
9. PERFORMING ORGANIZATION NAME AND ADDRESS EIC Corporation 55 Chapel Street, Newton, MA 02158		8. CONTRACT OR GRANT NUMBER(s) (15) DAAB07-74-C-0030	
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Electronics Command Attn: DRSEL-TL-PR Fort Monmouth, New Jersey 07703		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS (16) 1T1 61102 A34A 02435	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) (12) 36p.		12. REPORT DATE (11) JUN 1977	
		13. NUMBER OF PAGES 31	
		15. SECURITY CLASS. (of this report) UNCLASSIFIED	
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; distribution unlimited.			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Cells Utilizing Solvent Reduction, Inorganic Electrolytes, Lithium Anodes, Thionyl Chloride, Storage Effects, Temperature Effects, Lithium Alloys, Calcium Anodes, Calcium Plate Lithium Anodes.			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The major area of investigation during this report period has been the voltage delay and depression in Li/SOCl ₂ cells after storage at 71°C. These are due to films on the Li anode surface which arise from reaction with the electrolyte. The effects of test-cell design and variation in storage procedures have been assessed. Calcium deposited onto the anode			

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

408 525

1B

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

20. Abstract (Cont.)

decreases the voltage delay. The efficiency of Ca deposition onto Li metal was investigated. An infrared spectrophotometric survey of the $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte system was initiated.

Our Li/SOCl_2 test cell design was reviewed. The cells were modified in three areas. Quartz substituted for Teflon as the cell-body material. A larger anode was used (4 cm^2 vs. 1 cm^2) and the Ni Exmet current collector was removed. These changes provided substantial improvement. No voltage delay was observed in 6 cells stored 256 hours. There was still voltage depression.

The question of atmospheric exchange with the storage cells was explored. Argon-filled Al containers were used to store the cells. There was evidence of improvement in the Li/SOCl_2 cells with regard to voltage delay up to 300 hours of storage.

A new method of preparing the electrolyte salt was tested. It is synthesized and purified in the metal at 180°C . The purification was done by electrolysis. Storage tests indicate it is approximately equivalent to electrolyte prestored with Li.

Infrared spectrophotometry was used to survey the $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte system. Eastman 246 SOCl_2 contains $<200 \text{ ppm}$ HCl and SO_2 . After distillation, more SO_2 , and SO_2Cl_2 , are detected. Water reacts with SOCl_2 to produce SO_2 and HCl in direct proportion to the amount added. Solutions of the electrolyte contain HCl , SO_2 and hydroxy aluminum compounds. Storage of the electrolyte with Li removes HCl and hydroxy compounds but introduces low levels of other products. Water reacts with the electrolyte solution to produce SO_2 and HCl , and also hydroxy aluminum components.

↑
END

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

TABLE OF CONTENTS

<u>Section</u>	<u>Page</u>
I. INTRODUCTION.	1
II. ELECTROCHEMICAL EFFECTS OF SYSTEM PURITY.	3
A. Cell Design and Storage Revisions	3
B. Double Sealed vs. Single Sealed H-Cells	4
C. Quartz Plate vs. Teflon Disc Cells.	5
III. INFRARED SPECTROMETRY	15
A. Experimental.	15
B. Results	15
IV. CALCIUM DEPOSITION FROM SOLUTIONS IN SOCl_2	23
V. SUMMARY AND FUTURE WORK	29
VI. REFERENCES.	31

ACCESSION for	
RTIS	White Section ☒
DDC	Built Section ☐
UNANNOUNCED	☐
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

LIST OF FIGURES

<u>Figure</u>		<u>Page</u>
Fig. 1	Initial polarization of Li/SOCl ₂ cells with 480Ω (~1 cm ²). These were stored 288 hr at 71°C in the HAL cell configuration.	6
Fig. 2	Initial polarization of Li/SOCl ₂ cells with 480 (~1 cm ²). These were stored 360 hr in the HAL configuration	7
Fig. 3	Initial polarization of fresh Li/SOCl ₂ cells (4 cm ² anodes). Quartz plates were substituted for the Teflon discs . . .	9
Fig. 4	Initial polarization of Li/SOCl ₂ cells stored 256 hr at 71°C in the HAL configuration. The anodes were 4 cm ²	10
Fig. 5	Initial polarization of Li/SOCl ₂ cells stored 278 hr at 71°C in the HAL configuration. The anodes were 4 cm ² . The cells were discharged at 1 A/cm ² for 2 sec prior to storage . . .	11
Fig. 6	Initial polarization of Li/SOCl ₂ cells stored 281 hr at 71°C in the HAL configuration. The anodes were 4 cm ² . The electrolyte salt was prepared and purified as a melt.	12
Fig. 7	Infrared spectrum of Eastman 246 undistilled SOCl ₂ . Pathlength 0.10 mm, AgCl windows.	16
Fig. 8	Absorbance of the SO ₂ and HCl infrared bands as a function of added water in SOCl ₂ at 25°C. AgCl window cells, 0.10 mm pathlength were used.	18
Fig. 9	Infrared spectrum of freshly prepared 1.5M LiAlCl ₄ /SOCl ₂ electrolyte before storage with Li. Pathlength 0.10 mm, AgCl windows.	20
Fig. 10	Infrared spectrum of 1.5M LiAlCl ₄ /SOCl ₂ electrolyte after storage at 71°C with Teflon discs used in T-cells. Pathlength 0.10 mm, AgCl windows.	21
Fig. 11	Polarization of a 2.25 cm ² Ni electrode in 1M Ca(SbCl ₆) ₂ /SOCl ₂ at 25°C at the specified current densities.	24
Fig. 12	Polarization at a 2.25 cm ² Li electrode in 1M Ca(SbCl ₆) ₂ at 25°C with 0.9 mA/cm ²	26

I. INTRODUCTION

In recent years there has been considerable research and development on ambient-temperature, high energy density Li cells. A particularly promising system is based on thionyl chloride, SOCl_2 (1,2). Here, SOCl_2 serves both as solvent and depolarizer for the cell. D cells have delivered 100 Whr/lb and 40 W/lb at the 2.5 hr rate and, as usual, have delivered higher energy densities at lower discharge rates (3).

The purpose of the present program is to study the feasibility of an all-inorganic electrolyte Li primary battery operable and storable over the temperature range of -40°F to $+160^\circ\text{F}$. The desired energy density is 150 watt-hours per pound of total battery weight and the desired power density is 50 watts per pound.

This report contains the results of the thirteenth quarter work on this program. During this quarter the emphasis of the program has been on an investigation of the problem of cell passivation during storage at 71°C (160°F). Our studies (4), and others (3,5), show that the cause of the Li passivation is the formation of a nonconductive film on the Li anode during storage, especially at elevated temperatures. Our research efforts have been directed at studying film formation, and modifying the film to improve cell performance. As a result of our investigation at least two promising leads have been developed for the alleviation of the passivation problem.

A remarkable improvement was obtained with cell preparation techniques designed to eliminate Li-reactive impurities (6). Li/ SOCl_2 cells were prepared in a very clean argon atmosphere with electrolyte, separators and in some cases cathodes which had been previously stored with Li at 71°C in SOCl_2 . The improvement with regard to voltage delay was substantial in comparison to cells prepared without these procedures. Cells stored up to 200 hours had no voltage delay and only slight voltage depression. Beyond 250 hours storage, however, these cells begin to suffer voltage delays. During this quarter we have continued to explore the mechanism which cause this degradation in performance. Electrolyte prepared and purified by a new method has been tested. A new test cell design has been used and new storage procedures have been implemented.

The second promising method of eliminating voltage delay has utilized Ca as an alloying element at the Li anode surface (7). Calcium is added to the system by saturating the electrolyte with CaCl_2 . The cells are stored with this electrolyte. Under these conditions, Ca most likely deposits onto the Li surface by exchange, since the Ca open circuit

potential vs. Li^+/Li in this solution is +0.8V. During the present quarter we have explored methods of producing a more defined surface state by deposition from Ca^{+2} solutions.

In order to explore the SOCl_2 electrolyte system more completely with regard to purity and reaction products, a survey by infrared spectrophotometry was initiated. The effects of water and Li prestorage have been studied.

II. ELECTROCHEMICAL EFFECTS OF SYSTEM PURITY

In seeking to alleviate the voltage delay in Li/SOCl₂ cells after storage at 71°C, we have established procedures designed to reduce or remove the effects of Li reactive species before cell assembly. The effect of such species has been clearly demonstrated by Marincic and Lombardi (8). Their work showed that 200 ppm of Fe in the SOCl₂ electrolyte will severely passivate the Li anode within 24 hours, even at room temperature. Clearly, Fe need not be the only species of concern. In order to increase the system purity, cells have been assembled in a very clean argon atmosphere, electrolyte has been prestored with Li at 71°C, and separators and, in some cases cathodes, have been prestored with Li in SOCl₂ at 71°C. The effect of these has been to substantially improve cell performance (i.e., eliminate voltage delay) up to 200 hours. Beyond about 250 hours, however, cell performance degrades sharply.

Some data developed during the last quarter suggested that the degradation at ~250 hours may not be intrinsic to the cell but rather relate to artifacts of the test procedure. For example, tests indicated that the containers used to hold the actual Li/SOCl₂ cells during storage have measurable exchange with the atmosphere at about 300 hours. These results have prompted a revision in the cell design and storage procedures. These are discussed below. A new method of preparing and purifying the electrolyte salt has also been tested.

A. Cell Design and Storage Revisions

Concern over exchange between the atmosphere and the storage cell during long term storage tests has prompted a change in the storage procedures. At the same time, Li/SOCl₂ cell design was reviewed. Based on this, modifications were made to enhance chemical inertness and stability during long term tests.

The original Li/SOCl₂ design, the so-called T-cell, is described in detail in the ninth quarterly report. Briefly it comprises two Teflon discs which sandwich the electrode package. The electrode package consisted of a flat Li anode and carbon black cathode with a glass fiber separator. Two additional glass fiber separators are used at the external faces of the anode and cathode to prevent contact with the Teflon and to act as electrolyte reservoirs. The Teflon discs were compressed onto the electrode package by threaded Teflon rods and nuts. The anodes were 1 cm² (one side), formed by pressing 15 mil Li foil onto both sides of a Ni Exmet grid to which a Ni lead wire was welded.

The revised cell design incorporates three major changes: Quartz plates (0.125" thick) are substituted for the Teflon discs; the area of the anode has been increased from 1 cm² to 4 cm² (one side) and the Ni Exmet grid and lead wires have been eliminated. The 15 mil Li foil anode is cut with a tab to provide the electrical connection.

The quartz plates are more attractive as cell materials because of the reduced probability of contamination. It was thought that the more porous Teflon material may possibly contain leachable substances which are residual from its manufacture or cleaning. As a test of this possibility, several of the Teflon discs used for the T-cells were stored with electrolyte at 71°C. The solution darkened to a brown color within 3 hours of reaching temperature. Gas chromatographic analysis showed no new major components, but the SO₂ content did increase by at least a factor of 2. These are initial results and more extensive analysis is currently underway. Whether the darkening is indicative of the presence of substances harmful or beneficial to Li anode storage properties is unknown. Nonetheless, they represent a random factor in the tests which is best eliminated at present and left for future evaluation.

The possible effects of the increased anode size, and elimination of the Ni grid are discussed below.

The groups of the individual Li/SOCl₂ cells are normally placed in Teflon O-ring-sealed glass containers for storage. These glass containers are fabricated from commercial O-ring joints (Ace Glass Co.) and clamped shut with Al rings. In order to substantially reduce any exchange between the interior of these cells and the atmosphere, they are now placed in sealed containers fabricated from Al. These containers were formed from Al tubing. One end was sealed by welding onto a plate. The container is sealed for storage with an O-ring seal, using another plate. The cover plate has a pressure gauge for monitoring the system integrity. When sealed, empty cells are heated at 71°C, the indicated pressures are 2-2.5 psig. This corresponds to the value anticipated based on the ideal gas law (~2.3 psig). The variation is probably due to imprecision in the gauges (0-30 psig) at their low pressure end. These containers have shown no pressure loss after 3 weeks at 71°C.

B. Double Sealed vs. Single Sealed H-Cells

The importance of possible atmospheric exchange in the degradation of cell performance has been assessed by comparison of the voltage delay between T-cells stored in the normal H-cell and T-cells stored in the H-cells inside the Al containers. Two of the double sealed assemblies were prepared. One contained 4 T-cells, the other 6 T-cells. They were prepared under the highest purity conditions. Once the T-cells were prepared and placed in the H-cell, and the H-cell sealed and placed in

the Al container, the Al cell was flushed with dry argon and sealed. The sealed combination was then placed in the 71°C oven for storage. This combination cell is designated an HAL cell.

The two HAL cells were stored 288 hours (HAL 1) and 360 hours (HAL 2). The individual T-cells were tested for voltage delay at room temperature. The tests were, as before, constant load with the cell voltage and Li anode potential vs. a Li reference electrode monitored on a rapid time base.

The results are shown in Figures 1 and 2. The resistive load chosen draws ~ 6 mA/cm² from a fresh cell, which corresponds to the $\sim 3A$ rate from a practical D-cell with a 400 cm² electrode area. All nine of the T-cells tested had severe voltage delays. One of the T-cells in HAL 1 had shorted. The behavior of the T-cells was consistent within the individual HAL cell. The observed behavior is similar to that of T-cells stored similar times in only the H-cells. This suggests that for the T-cells, at least, atmosphere contamination is not the major source of the voltage delay problem at the 250-350 hour mark.

C. Quartz Plate vs. Teflon Disc Cells

Initial testing of the quartz plate Li/SOCl₂ test cells has shown them to be superior to the Teflon disc cells (T-cells) with regard to voltage delay characteristics after 71°C storage. The quartz plate cells were assembled and described above. They were stored at 71°C in the HAL cell configuration. Three HAL cells (HAL 3, 4 and 5) were assembled, each containing 6 Li/SOCl₂ quartz-plate cells. HAL 3 was designed to assess the differences between the quartz plate cell and the T-cell. HAL 4 was designed to assess the effect of briefly anodizing the Li anode before storage. A 2 sec current pulse of 1A/cm² (4A) was used. The third HAL cell (HAL) contained quartz plate cells with electrolyte prepared from LiAlCl₄ synthesized and purified by a new method (9).

For this purpose, the LiAlCl₄ was synthesized as the melt and purified by electrolysis: 1.5 mol of LiCl (Fisher L-121) and 1.5 mol AlCl₃ (Fluka, puriss) were melted together in a Pyrex container. The temperature was maintained at $180 \pm 5^\circ\text{C}$. The product was dark brown. The melt was purified by anodizing a piece of pure Al (Ventron m5N ingot) against an Al wire cathode. The anodization was continued for 2 weeks at 4.4 mA/cm² (40 mA). There was gassing at both electrodes when they were initially inserted into the melt. When the current was applied, gassing was observed only at the cathode. The gassing is due to hydrogen ion reduction. The gassing ceased after 3-3.5 hours. At the end of the electrolysis, the melt was water-white. The cooled melt was powdered with a mortar and pestle. The 1.5M LiAlCl₄/SOCl₂ electrolyte was prepared by dissolving the salt in SOCl₂ kept at -10 to -20°C. An empirical test of purity suggests that this electrolyte is a significant




Fig. 1: Initial polarization of Li/SOCl₂ cells with 480Ω (≈1 cm²). These were stored 288 hr at 71°C in the HAL cell configuration.




Fig. 2: Initial polarization of Li/SOCl₂ cells with 480Ω (1 cm²). These were stored 360 hr in the HAL configuration.

improvement over that used earlier. The test comprised storage of the electrolyte with Li at 71°C. After 10 days, the Li still retained its bright metallic surface although the solution color had changed to bright yellow. The normal electrolyte stored this way, e.g., as part of its purification procedure, causes the Li surface to darken when stored an equivalent length of time.

HAL 3 was stored 256 hours, HAL 4 278 hours and HAL 5 281 hours. The Li/SOCl₂ cells were tested for voltage delay with constant load. Three cells in each were tested with 94Ω and three with 153Ω. These draw 9.0 mA/cm² and 5.6 mA/cm² respectively from fresh cells, as shown in Figure 3.

The test results indicate that after 250 hours storage the quartz plate cells are a significant improvement over the T-cells. Figure 4 shows the initial cell discharge voltage curves for the 6 Li/SOCl₂ cells of HAL 3. None of the cells show any voltage delay (<2V), although there is voltage depression. The cells discharged through the 153Ω resistor are between 0.7 and 1.1V lower in voltage than the fresh cells. The cells discharged through 94Ω are 1.2 to 1.4V lower in voltage.

Pulsed, high current discharge of the quartz plate cells of HAL 4 before storage did not improve their storage capability. Figure 5 shows the voltage curves for the initial discharge. The performance, in fact, is inferior to the HAL 3 cells. All of the cells show a voltage delay. Their performance, however, is still superior to the T-cell design stored a similar length of time. There are two major differences in the preparation of the HAL 4 and HAL 3 cells. The HAL 4 cells were anodized prior to storage and they were stored for 22 additional hours. At the present time, it is not clear which is the major contributor to the poorer performance of the HAL 4 relative to the HAL 3 cells. Limited evidence, however, suggests that time is the more important. This conclusion is based on the HAL 5 cell data (Figure 6). The basis of comparison with the HAL 3 and 4 cells is the average cell voltage at 60 sec after the application of the resistive load. It is a somewhat arbitrary choice, but we feel it reflects overall cell performance, since in these tests, the cell voltages remain relatively stable from the 30 sec mark out to at least 120 sec. At 60 sec, the average cell voltages for the HAL 3, 4 and 5 quartz plate cells discharged with the 153Ω load are 2.53V, 1.87V and 2.04V respectively. The average cell voltages obtained with the 94Ω load mirror these values, with the HAL 3, 4 and 5 cells having average cell voltages of 2.13V, 1.51V and 1.60V. It is clear that the two HAL cells (4 and 5) stored 22 hours and 25 hours longer are inferior. Further, there is no significant difference between the HAL 4 and 5, which suggests that the brief anodization has not adversely affected the electrodes. Thus we feel that the additional time at 71°C is the major source of the degradation in electrode performance.




Fig. 3: Initial polarization of fresh Li/SOCl₂ cells (4 cm² anodes). Quartz plates were substituted for the Teflon discs.




Fig. 4: Initial polarization of Li/SOCl₂ cells stored 256 hr at 71°C in the HAL configuration. The anodes were 4 cm².




Fig. 5: Initial polarization of Li/SOCl₂ cells stored 278 hr at 71°C in the HAL configuration. The anodes were 4 cm². The cells were discharged at 1 A/cm² for 2 sec prior to storage.




Fig. 6: Initial polarization of Li/SOCl₂ cells stored 281 hr at 71°C in the HAL configuration. The anodes were 4 cm². The electrolyte salt was prepared and purified as a melt.

There is one caveat to the argument. The HAL 5 cells were prepared with a different electrolyte. This was electrolyte prepared from LiAlCl_4 synthesized and purified in the melt. We feel, however, that this electrolyte is not significantly different from the normal electrolyte prestored with Li, since storage tests with Li at 71°C for 10 days have shown no discoloration or corrosion of the Li. This is the same behavior we observe with prestored electrolyte.

The quartz plate cells are better in overall performance than the T-cells. The reason or reasons for the improvement must lie in one or more of the three areas of major difference between the two types of cell. We explained above the anticipated advantages with the substitution of quartz for Teflon. Basically it is a concern that the Teflon may be a source of contaminants.

The use of larger anodes, the second difference, can have two possible advantages. A greater probability of finding areas of faulty film epitaxy. This will be important if after storage the discharge is very localized, as we have observed (10). Another advantage of larger anodes is that they should be much freer from possible edge effects. The third area of change, elimination of the Ni Exmet current collector, may also have two advantages. If the electrolyte penetrates between the grid and the Li, it is possible that an insulating film will build up, causing poor electrical contact between the Ni grid and the Li. It may also be that SOCl_2 reduction on the exposed Ni will help depolarize the corrosion of the anode, although it is by no means clear how this would result in a voltage delay.

In summary, atmospheric exchange is not a significant problem in the H-cell storage container up to ~300 hours. Quartz plate Li/ SOCl_2 test cells perform better than Teflon disc cells (T-cells) after storage at 71°C . This is an important finding, although the specific cause or causes of the improvement have not yet been established. Brief anodization of the Li in the complete cell before storage does not improve its storage capability. A new electrolyte salt preparation and purification procedure have been used. The results suggest it is at least as good as the normal electrolyte.

Further work will concentrate on identifying the source or sources for the improvement on the quartz cells. Experiments will isolate each of the three major areas to determine its contribution to the improvement in performance. In order to establish the effect of the substitution of quartz for Teflon, electrode packages identical to the T-cell design will be assembled and used with the quartz plate design. These will have 1 cm^2 anode area and have Ni Exmet current collectors. In order to investigate the effect of the Ni Exmet, electrode packages of 1 cm^2 without Ni Exmet and 4 cm^2 with Ni Exmet will be tested. The performance of these will be

compared to data already available for 1 cm² anodes with Exmet and 4 cm² anodes without Exmet. In order to assess the effect of anode area on cell performance, a series of cells with increasing anode area will be tested. Two cell designs will be used, multiplate prismatic and spiral wound. These may have anode areas in excess of 120 cm².

Once the sources of the improvement are determined, cells will be designed around these to maximize the benefits. We also feel that there is a need for a more time-efficient test procedure for storage cells. We will attempt to establish such a procedure. The fundamental concept is to reduce the amount of storage time by testing a cell under conditions more adverse than would normally be used. For example, cells could be cooled to -30°C for testing and current densities in excess of 7 mA/cm² could be used. The ultimate validity of this type of testing must be established, but if it is successful it would substantially increase the data yield.

III. INFRARED SPECTROMETRY

An investigation of SOCl_2 -based electrolyte systems by infrared spectrophotometry has been initiated. The ultimate aim is to provide a more complete understanding of the chemistry. Particularly important areas to be explored are the electrolyte purity, discharge reaction products and solution decomposition products. We report here on the results of a survey of SOCl_2 and 1.5M $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte. Part of this initial work is to assess the areas where infrared spectrophotometry will be most valuable.

A. Experimental

All spectra were recorded on a Beckman Acculab 5 dual beam spectrophotometer. The instrument covers the range from 4000 cm^{-1} to 375 cm^{-1} . Several commercial cells were tested. All of the spectra reported here were obtained with Beckman TAC cells. These have AgCl windows and can be sealed permanently. Two path lengths were used, 0.025 mm and 0.10 mm. The IR cells were filled and sealed in an argon filled glove box.

B. Results

• SOCl_2

The spectrum of undistilled Eastman 246 SOCl_2 is shown in Figure 7. The major feature is a strong absorption at 1225 cm^{-1} , with a weaker band at 2420 cm^{-1} . There are still weaker bands at 920 cm^{-1} and 765 cm^{-1} . This spectrum agrees substantially with published spectra for SOCl_2 (11,12). The Aldrich Library spectrum (11) shows only the 1225 cm^{-1} band. Since that spectrum is of the pure liquid, and the 1225 cm^{-1} is on scale, a capillary cell was most probably used. This would reduce the weaker bands below the limits of detection. The data of Martz and Lagemann (12) are more complete. The main band at 1225 cm^{-1} is assigned to the S-O stretching. The band at 2420 cm^{-1} is the first overtone. The weaker bands below 1000 cm^{-1} are summation bands of the lower energy S-Cl stretch, molecular deformation and torsion.

The spectrum of distilled SOCl_2 shows two additional bands, at 1340 and 1410 cm^{-1} . Eastman 246 SOCl_2 was distilled at atmospheric pressure under argon from Li chips. The middle fraction, boiling between 75.5 – 77°C (uncorr.), was used. The 1340 cm^{-1} band is most probably due to SO_2 (12,13). This band was reported by Martz and Lagemann and, as reported below, the band appears with a reaction product of H_2O and SOCl_2 . We have obtained the spectra of SO_2Cl_2 , which agrees substantially with published spectra. SO_2Cl_2 has two prominent bands at 1410 cm^{-1} and

WAVELENGTH IN MICRONS




Fig. 7: Infrared spectrum of Eastman 246 undistilled SOCl_2 . Pathlength 0.10 mm, AgCl windows.


1200 cm^{-1} , assigned to the asymmetric and symmetric S-O stretching (12). The 1200 cm^{-1} band would be obscured by the 1225 cm^{-1} band of SOCl_2 . These results indicate that distillation of SOCl_2 under the conditions specified above introduces some decomposition products.

- SOCl_2 with added S, HCl and H_2O

Solutions of S, HCl and H_2O in SOCl_2 were studied in order to establish the nature of spectra and to determine if the IR is suitable to quantify the species generated during cell discharge. A 1M S solution was prepared using undistilled SOCl_2 . The S dissolved slowly at room temperature, requiring three days to dissolve completely. The solution was bright yellow. The IR spectrum was identical to SOCl_2 . The presence of S causes no detectable decomposition of SOCl_2 .

A solution of HCl-saturated SOCl_2 was prepared with anhydrous HCl gas and undistilled SOCl_2 . We have estimated the solubility of HCl to be about 0.5M. There was some experimental difficulty in obtaining the spectra. The temperature of the cells increased sufficiently to cause the cells to split. The spectrum showed only one additional band at 2780 cm^{-1} , which is most probably the HCl stretching frequency (14).

The effect of H_2O on the IR spectra of SOCl_2 has been reported by French *et al.* (15). They report that the addition of H_2O produces a band at 2800 cm^{-1} , which is ascribed to hydrogen band H-O stretching in HOSOC1 . They worked with relatively long path length cells 0.5-10 cm and water concentrations less than 100 ppm. Our measurements have begun with larger water concentrations (300-3000 ppm) and shorter path length cells (0.1 mm). The addition of water does cause a peak to appear at 2780 cm^{-1} and it also causes a peak at 1340 cm^{-1} . The absorbance of both increases with increasing water addition. The increase is linear for the 2780 cm^{-1} band and apparently linear for the 1340 cm^{-1} band (Figure 8). We believe the bands are due to HCl (2780 cm^{-1}) and SO_2 (1340 cm^{-1}) resulting from the reaction



The 2780 cm^{-1} band resulting from the addition of water is identical to the band we observe for HCl-saturated SOCl_2 . The presence of SO_2 after H_2O addition suggests that the HOSOC1 species postulated by French *et al.* cannot be present in high concentrations, if it exists at all. When they added AlCl_3 to the solution of H_2O in SOCl_2 , the 2780 cm^{-1} band began to disappear, which they attributed to the reaction



We feel that the disappearance of the 2780 cm^{-1} band is due to the reaction of HCl with AlCl_3 according to




Fig. 8: Absorbance of the SO₂ and HCl infrared bands as a function of added water in SOCl₂ at 25°C. AgCl window cells, 0.10 mm pathlength were used.



This reaction seems probable, due to the high stability of AlCl_4^- in SOCl_2 . For example, AlCl_3 will dissolve LiCl in SOCl_2 . Lithium chloride has a heat of formation of 97 kcal/mol but HCl has a heat of formation of only 22 kcal/mol. Thus it seems unlikely that HCl would be stable in the presence of AlCl_3 . Further measurements are underway to resolve this question.

• 1.5M LiAlCl_4 , SOCl_2

The spectrum of freshly prepared 1.5M LiAlCl_4 , SOCl_2 is shown in Figure 9. The electrolyte was prepared from undistilled Eastman 246 SOCl_2 and LiAlCl_4 prepared and purified in the melt, as described above. Spectra of electrolyte prepared by dissolving LiCl in a solution of $\text{AlCl}_3/\text{SOCl}_2$ have the same features.

Comparison of this spectrum with that of SOCl_2 reveals three major changes. There is a broad band of centered at 3350 cm^{-1} ; there is a shoulder on the lower wave number side of the SOCl_2 overtone band centered at about 2350 cm^{-1} ; there is a new band at 1330 cm^{-1} . There is also a slight indication of HCl at 2780 cm^{-1} . The 1330 cm^{-1} band is due to SO_2 which, along with the HCl , probably results from the reaction with H_2O contained in the salt. The SO_2 concentration is about 0.07M, as estimated from Figure 8. The band at 3350 cm^{-1} is probably due to H-O stretching on aluminum hydroxy compounds (15,16).

These species are relatively stable in SOCl_2 . In tests with electrolyte to which water was added, the intensity of this band remained unaltered after 7 days at room temperature. It is quite clear that added H_2O reacts preferentially with the AlCl_4^- rather than with SOCl_2 because a precipitate formed which did not redissolve even after 7 days.

Storage of the electrolyte at 71°C with Li causes the 3350 cm^{-1} band to disappear. This indicates that these hydroxy compounds will react with Li . The HCl band at 2780 cm^{-1} is also removed, but the SO_2 band at 1330 cm^{-1} increases. Quantitative measurements are presently underway. The stored electrolyte shows a weak band at 1070 cm^{-1} , not evident in SOCl_2 or unstored electrolyte. This band has not yet been identified. It is not SCl_2 whose spectrum is featureless above 600 cm^{-1} . The S-Cl stretching bands overlap with the S-Cl bands of SOCl_2 . No other changes in spectrum are evident.

Figure 10 shows the spectrum of electrolyte stored with Teflon. This electrolyte had previously been stored with Li to remove the hydroxy and HCl components. Several features have been introduced by the Teflon. The HCl band at 2780 cm^{-1} , a shoulder on the SO_2 peak at 1330 cm^{-1} , an absorbance at 1110 cm^{-1} and a shoulder at 1075 cm^{-1} . These have not yet




Fig. 9: Infrared spectrum of freshly prepared 1.5M $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte before storage with Li. Pathlength 0.10 mm, AgCl windows.




Fig. 10: Infrared spectrum of 1.5M $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte after storage at 71°C with Teflon discs used in T-cells. Pathlength 0.10 mm, AgCl windows.

been identified. Their position, however, is in the region of S-O stretching and most likely are due to reaction products from materials leached from the Teflon. Exact identification of these components is probably not necessary, but it is an indication of the improvements in purity that can be obtained by changing to the quartz plate cell design.

The initial survey of the SOCl_2 electrolyte system with infrared spectrophotometry has provided valuable insights. It is a useful method for analysis of such species as SO_2 , HCl , hydroxy compounds, SO_2Cl_2 . It is not an adequate technique for SCl_2 because SCl_2 does not have absorbance band unobscured by SOCl_2 . Neither is it suitable for S solutions. The reaction of H_2O with SOCl_2 produces SO_2 and HCl . The reaction of H_2O with electrolyte, however, generates hydroxy compounds, probably of aluminum, which are reactive to Li. Storage of electrolyte with Li removes these hydroxy compounds, and apparently the HCl , but generates a new and at the moment unidentified component. We will attempt to identify this component as well as continue to survey likely contaminants of the SOCl_2 electrolyte system.

IV. CALCIUM DEPOSITION FROM SOLUTIONS IN SOCl₂

Calcium has proven to be an effective alloying element for Li anodes for the reduction in the severity of the voltage delay after storage at 71°C (7). Cells stored 800 hours have shown no voltage delay. The Ca was introduced by saturating the electrolyte with CaCl₂. Although CaCl₂ shows very limited solubility, it provides sufficient Ca²⁺ to diffuse to the Li anode and to deposit by exchange. This method of preparing cells has shown promise, as indicated above, but also has been subject to inconsistencies. During this quarter we have approached this problem by investigating methods of depositing Ca coatings before cell assembly.

In order to deposit Ca onto Li, a more soluble Ca salt would be beneficial. Ca(SbCl₆)₂ is soluble in SOCl₂ up to at least 1M. The solution is prepared by addition of a 5% excess of anhydrous CaCl₂ to a solution 2M SbCl₅ in SOCl₂. The dissolution reaction is very exothermic. Conductivity measurements show this Ca(II) solution to be about as conductive as 1.5M LiAlCl₄, but we believe that the solution contains little free Ca²⁺. Chemical and electrochemical evidence suggests that the Ca(II) is present as a complex, perhaps as Ca(SbCl₆)⁺: For example, previous tests show that Ca(AlCl₄)₂ has very limited solubility in SOCl₂ and a solution of AlCl₃ will not dissolve CaCl₂. However, the addition of a 1.5M LiAlCl₄/SOCl₂ solution to 1M Ca(SbCl₆)₂/SOCl₂ produces no precipitate even at a 1:1 volume ratio. This indicates that the Ca(II) must be stabilized by the SbCl₆⁻.

Further evidence is afforded by attempts to electroplate Ca onto Ni and Li substrates. In these tests, the 2.25 cm² working electrodes were immersed in 1M Ca(SbCl₆)₂/SOCl₂ with a Ca counter electrode. The tests were run galvanostatically. If the free Ca²⁺ concentration were 1M, a transition time of ~10⁵ sec should be observed at a cathodic current density of 1 mA/cm². In the case of Ni, a fresh electrode shows an open circuit potential of +3.6V vs. Li⁺/Li. This potential is determined by the SOCl₂-reduction reaction. For current densities less than ~0.7 mA/cm², the potential remains above +3.0V vs. Li. With current densities greater than ~0.8 mA/cm², a potential of -0.2 to -0.3V vs. Li is rapidly established. After ~1 coul/cm² of charge has been passed, the Ni electrode potential becomes more negative, exceeding -5.0V vs. Li (Figure 11). At this time, the electrode is covered with a black film which is air sensitive. When the electrode is removed to the air, the film rapidly becomes white, then transparent. Qualitative analysis has shown the presence of both Ca and Sb.




Fig. 11: Polarization of a 2.25 cm^2 Ni electrode in $1\text{M Ca}(\text{SbCl}_6)_2/\text{SOCl}_2$ at 25°C at the specified current densities.

The possible presence of a LiCl film from the concurrent reduction of SOCl_2 should not seriously interfere with the plating process in these tests. For example, we have found that Li may be plated onto Ni at current densities greater than 10 mA/cm^2 at potentials a few tens of millivolts cathodic of the Li open circuit potential.

With Li working electrodes, the fresh Li had an open circuit potential of $\pm 20 \text{ mV}$ vs. Li^+/Li . At cathodic current densities of 0.5 to 1.2 mA/cm^2 , a Li electrode rapidly polarized to -0.2 to -0.3 V vs. Li. After about 10 coul/cm^2 of charge had been passed, the electrode polarized sharply to greater than -5.0 V vs. Li (Figure 12). This electrode was also coated with a black film. Analysis of this film is currently in progress.

These data for the Ni and Li electrodes suggest that the free Ca^{2+} concentration in the $1 \text{ M Ca(SbCl}_6)_2/\text{SOCl}_2$ solution is not 1 M , but rather that the majority of the Ca^{2+} is in the form of a complex. The data further suggest that it is a very strong complex, since pure Ca is not plated from solution at potentials ~ 1 volt negative of the Ca open circuit potential ($\sim +0.8 \text{ V}$ vs. Li). Rather a mixture of Ca and Sb are found on the electrode. Analyses are currently underway to determine the Ca to Sb ratio. If the ratio is stoichiometric, it would suggest that a single species is being reduced and perhaps the data will yield an estimate of the nature of that species. For example, if the mole ratio of Ca to Sb were $1:1$, the solution species might then be $\text{Ca(SbCl}_6)^+$. All of the above results suggest a very interesting chemistry for the $\text{Ca(SbCl}_6)_2/\text{SOCl}_2$ system. It may be appropriate to investigate this chemistry further using the methods of complex chemistry. For example, ligand-exchange titrations or precipitation reactions may prove useful. Whether it is possible to electrodeposit only Ca onto Li from $1 \text{ M Ca(SbCl}_6)_2/\text{SOCl}_2$ is unknown at present. Further testing at cathodic current densities less than 0.5 mA/cm^2 will be carried out.

We have established that Ca does deposit by exchange onto Li from $\text{Ca(SbCl}_6)_2$ solution. In these experiments, pieces of Li foil (6 cm^2 , two sides) were immersed in 0.1 M , 0.3 M and $1.0 \text{ M Ca(SbCl}_6)_2/\text{SOCl}_2$ for varying lengths of time. The Li pieces were removed, thoroughly rinsed with SOCl_2 , and analyzed for their Ca content by atomic absorption. The analytical results are presented in Table 1. The Ca depletion in the solutions was small. For example, the sample stored for 88 hours in $0.1 \text{ M Ca(SbCl}_6)_2$ removed only 6% of the Ca present. These deposits contain only trace amounts of Sb, possibly from entrainment of electrolyte.

These data show the accumulation of Ca to be relatively slow and relatively insensitive to $\text{Ca(SbCl}_6)_2$ concentration. Both of these suggest that the deposition is not controlled by solution processes. Of possible solution processes, diffusion is the most likely to be limiting.




Fig. 12: Polarization of a 2.25 cm^2 Li electrode in $1\text{M Ca}(\text{SbCl}_6)_2$ at 25°C with 0.9 mA/cm^2 .

Table 1

Ca Deposition on Li Metal from $\text{Ca}(\text{SbCl}_6)_2/\text{SOCl}_2$
at 25°C coul/cm²

Time (hr) Conc	1	3	19	88(A)	88(B)
0.1M	0.052	0.088	0.398	0.969	1.81
0.3M	0.065	0.163	0.458	2.25	1.99
1.0M	0.093	-	0.404	-	-

Yet calculations show that diffusion would permit deposition rate orders of magnitude greater than those observed. For example, assuming $D = 5 \times 10^{-6}$ cm²/s, then with $t = 1$ hr, $C = 10^{-4}$ mol/cm³, the charge deposited would be 4.6 coul/cm² vs. the 0.052 coul/cm² measured. This view is further substantiated by the relative insensitivity of the deposition rate to solution concentration of $\text{Ca}(\text{SbCl}_6)_2$.

Since we can deposit Ca onto Li by chemical exchange, our next step will be to prepare Li(Ca) anodes by this technique for storage testing. Chemical analyses of the $\text{Ca}(\text{SbCl}_6)_2$ solutions will be carried out to ascertain impurity levels. We feel this is necessary to determine if purification of these solutions is necessary to remove species known to be detrimental (e.g., Fe and Cu).

V. SUMMARY AND FUTURE WORK

During the past quarter, work has continued on the voltage delay problem suffered by Li/SOCl₂ cells during storage at 71°C. We have reviewed our test cell design and storage procedures. Test cells assembled with quartz plates have shown improved performance compared with our Teflon test cells. The quartz plate cells have larger anode areas and do not have Ni Exmet anode current collectors. The specific source of the improvement has not been identified. The substitution of the quartz for Teflon certainly removes a source of contamination. IR spectrophotometry had been used to ascertain that Teflon introduces HCl and at least one other component into 1.5M LiAlCl₄/SOCl₂ electrolyte during storage at 71°C. The larger anode can provide a larger number of defect sites on the surface which are capable of being activated during discharge and/or reduce edge effects. The removal of the Ni Exmet precludes the possibility of poor electrical contact during testing.

Atmospheric exchange between our storage cells and air does not appear to be a problem up to ~300 hours storage.

A new salt preparation method was used. The salt is prepared as the melt at 180°C and purified by electrolysis. Electrolyte prepared with this LiAlCl₄ gave cell performance closely equivalent to that of our normal electrolyte, which is prestored with Li.

In an effort to further elucidate the chemistry of the LiAlCl₄/SOCl₂ system, a study by infrared spectrophotometry was initiated. This study has several aims: We wish to survey the system to identify and quantify possible impurities. We further wish to study the discharge reaction products, especially possible minor products. Undistilled Eastman 246 SOCl₂ has shown no extraneous absorption bands. This limits the HCl and SO₂ concentrations to less than ≤200 ppm. Distillation introduces SO₂ and SO₂Cl₂ into the solvent. Preparation of the electrolyte introduces small amounts of SO₂ and HCl, probably from reaction with H₂O contained in the salt. The salt also introduces hydroxy aluminum compounds, which are relatively stable in SOCl₂. Storage with Li at 71°C removes the hydroxy aluminum compounds and the HCl. The storage also introduces an as yet unidentified component.

Water reacts with SOCl₂ to produce HCl and SO₂ in proportion to the water added. Water reacts with electrolyte to produce some HCl and SO₂ but primarily hydroxy aluminum compounds.

HCl and SO₂Cl₂ have identifiable absorbances in the IR, which SOCl₂ solutions of S and SCl₂ do not.

Calcium plating studies from $\text{Ca}(\text{SbCl}_6)_2/\text{SOCl}_2$ solution have indicated that chemical exchange between a Li surface and the solution will deposit Ca. These studies suggest that the free Ca^{2+} is stabilized, for example, as the $\text{Ca}(\text{SbCl}_6)^+$ species.

During the next quarter, we will continue to explore the problem of voltage delay. The improvement in performance observed in the quartz plate cells will be fully explored in order to establish the precise cause or causes. Lithium (Ca) anodes will be prepared by exchange from $\text{Ca}(\text{SbCl}_6)_2$ solution and will be tested in complete cells after storage at 71°C . The infrared spectrophotometric survey of the SOCl_2 system will be continued.

VI. REFERENCES

1. W. K. Behl, J. A. Christopoulos, M. Ramirez and S. Gilman, J. Electrochem. Soc., 120, 1619 (1973).
2. J. J. Auborn, K. W. French, S. I. Lieberman, V. K. Shah and A. Heller, J. Electrochem. Soc., 120, 1613 (1973).
3. A. N. Dey, Quarterly Report, ECOM-74-0109-2, November 1974.
4. G. L. Holleck, M. J. Turchan and D. R. Cogley, Fourth Quarterly Report, ECOM-74-0030-4, January 1975.
5. N. Marincic and A. Lombardi, Quarterly Report, ECOM-74-0108-4, May 1975.
6. J. R. Driscoll, G. L. Holleck, D. E. Toland and S. B. Brummer, Tenth Quarterly Report, ECOM-74-0030-10, June 1976.
7. J. R. Driscoll, G. L. Holleck, D. E. Toland and S. B. Brummer, Eleventh Quarterly Report, ECOM-74-0030-11, October 1976.
8. N. Marincic and A. Lombardi, Quarterly Report, ECOM-74-0108-5, August 1975.
9. L. G. Boxall, H. L. Jones and R. A. Osteryoung, J. Electrochem. Soc., 121(2), 212 (1974).
10. G. L. Holleck, M. J. Turchan and D. E. Toland, Fifth Quarterly Report, ECOM-74-0030-5, April 1975.
11. J. Pouchert, The Aldrich Library of Infrared Spectra, 2nd ed. (Milwaukee, Wisconsin: Aldrich Chemical Co., Inc., 1975).
12. D. E. Martz and R. T. Lagemann, J. Chem. Phys., 22, 1193 (1954).
13. D. F. Burow, "Liquid Sulfur Dioxide" in The Chemistry of Nonaqueous Solvents, ed. J. J. Lagowski (New York: Academic Press, 1970).
14. R. T. Edwards and W. West, J. Chem. Phys., 5, 14 (1937).
15. K. French, P. Cukor, C. Persiani and J. Auborn, J. Electrochem. Soc., 121, 1645 (1974).
16. J. R. Dyer, Applications of Absorption Spectroscopy of Organic Compounds (New Jersey: Prentice Hall, 1965).

Distribution List

Defense Documentation Center (12)
Attn: DDC-TCA
Cameron Station - Bldg. 5
Alexandria, Virginia 22314

Commander (1)
Harry Diamond Laboratories
Attn: Library
2800 Powder Mill Road
Adelphi, Md. 20783

Commander (1)
Naval Electronics Lab Center
Attn: Library
San Diego, California 92152

Commander (1)
US Army Research Office
Attn: DRXRO-IP
P.O. Box 12211
Research Triangle Park, N.C. 27709

Commander (1)
US Naval Surface Weapons Center
White Oak Laboratory
Attn: Library, Code WX-21
Silver Spring, Maryland 20910

Commander (1)
USA Mobility Equipment R&D Command
Attn: DRXFB-R
Fort Belvoir, Virginia 22060

Commandant, Marine Corps (2)
Headquarters, US Marine Corps
Attn: Code LMC
Washington, D.C. 20380

Commander, US Army Security Agency (1)
Attn: IARDA-IT
Arlington Hall Station
Arlington, Virginia 22212

Rome Air Development Center (1)
Attn: Documents Library (TILD)
Griffiss AFB, N.Y. 13441

NASA Scientific & Technical (1)
Information Facility
Baltimore/Washington Intl. Airport
P.O. Box 8757
Maryland 21240

Headquarters (1)
ESD(DRI)
L. G. Hanscom Field
Bedford, Massachusetts 01731

Commander
US Army Electronics Command
Fort Monmouth, New Jersey 07703
Attn: DRSEL-TL-DT (1)
Attn: DRSEL-TL-P (1)
Attn: DRSEL-MS-TI (2)
Attn: DRSEL-GG-TD (1)
Attn: USMC-LNO (1)
Attn: DRSEL-GG-AR (5)
Attn: DRSEL-TL-DD (1)

Headquarters (1)
DAMA-ARP/Dr. F. D. Verderame
Washington, D.C. 20310

Distribution List Continued

Mr. Don Mortel (1)
Director, Aerospace Power Division
Attn: AFAPL/PO
Wright-Patterson AFB, Ohio 45433

Mr. E. Cohn (1)
NASA Headquarters
Code RPP
Washington, D.C. 20546

Institute for Defense Analyses (1)
Attn: Mr. Robert Hamilton
P.O. Box 55
Libertytown, Md. 21762

Commander (1)
US Army Materiel Development
and Readiness Command
Attn: DRCRD-TC
5001 Eisenhower Avenue
Alexandria, Virginia 22333

The Electric Storage Battery Co. (1)
Carl F. Norburg Research Center
19 W. College Avenue
Yardley, Pa. 19067
Attn: Dr. A. Salkind

Commander (1)
US Army Mobility Equipment R&D Center
Attn: DRXFB-EE
Fort Belvoir, Virginia 22060

Commander (1)
Harry Diamond Laboratories
Attn: DRXDO-RDD (Mr. A. Benderly)
2800 Powder Mill Road
Adelphi, Md. 20783

Commander (1)
Picatinny Arsenal
Attn: SARPA-FR-S-P
Dover, New Jersey 07801

Mr. Joe McCartney (1)
Naval Undersea Center
Code 608
San Diego, California 92132

Power Information Center (1)
University City Science Institute
3624 Science Center
Philadelphia, Pennsylvania 19104

Office of Assistant Director (1)
(Engineering Technology), ODDR&E
Room 3D-1089, Attn: Mr. R. W. Ziem
Pentagon
Washington, D.C. 20301

Mr. Richard E. Oderwald (1)
Department of the Navy
Headquarters, US Marine Corps
Code LMC 4
Washington, D.C. 20380

NASA Lewis Research Center (1)
Mail Stop 309-1
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: Dr. Stuart Fordyce

Transportation Systems Center (1)
Kendall Square
Cambridge, Massachusetts 02142
Attn: Dr. Norman Rosenberg

P. R. Mallory & Co., Inc. (1)
Northwest Industrial Park
Burlington, Massachusetts 01803
Attn: Dr. Per Bro

GTE Laboratories, Inc. (1)
40 Sylvan Road
Waltham, Massachusetts 02154
Attn: Library

Distribution List Continued

Foote Mineral Company Route 100 Exton, Pa. 19341 Attn: Dr. H. Grady	(1)	General Motors Corp. Research Laboratories General Motors Technical Center 12 Mile and Mounds Roads Warren, Michigan 48090 Attn: Dr. J. L. Hartman	(1)
Honeywell Inc. 104 Rock Road Horsham, Pa. 19044 Attn: C. Richard Walk	(1)	Union Carbide Corporation Parma Research Center P.O. Box 6116 Cleveland, Ohio 44101 Attn: Tech Library	(1)
Sanders Associates, Inc. Sonobuoy Division 95 Canal Street Nashua, New Hampshire 03060 Attn: Mr. David Dwyer	(1)	P. R. Mallory & Co., Inc. S. Broadway Tarrytown, New York 10591 Attn: J. Dalfonso	(1)
Eagle Picher Industries P.O. Box 47 Joplin, Missouri 64801 Attn: Mr. E. Broglio	(1)	North American Rockwell Corp. Atomics International Division Box 309 Canoga Park, California 91304 Attn: Dr. L. Heredy	(1)
Yardney Electric Company 82 Mechanic Street Pawcatuck, Ct. 02891 Attn: Mr. William E. Ryder	(1)	General Electric Research and Development Center P.O. Box 8 Schenectady, New York 12301 Attn: Dr. Stefan Mitoff	(1)
Exxon Research and Engineering Co. Corporate Research Laboratory Linden, New Jersey 07036 Attn: Dr. R. Hamlen	(1)	Frank Murphy/SB331 Naval Underwater Systems Center Newport Laboratory Newport, Rhode Island 02840	(1)
Argonne National Laboratories 9700 South Cass Avenue Argonne, Illinois 60439 Attn: Dr. E. C. Gay	(1)	Dr. D. Pouli Portfolio Manager Hooker Chemicals & Plastics Corp. M.P.O. Box 8 Niagra Falls, New York 14302	(1)
GTE Sylvania, Inc. 77 A Street Needham Heights, Mass. 02194 Attn: Mr. Richard Pabst	(1)	University of California Department of Science & Research Santa Barbara, California 93100 Attn: Dr. J. Kennedy	(1)
Dr. Leonard Nanis G207 S.R.I. Menlo Park, California 94025	(1)		

Distribution List Continued

Dr. Hugh Barger (1)
P.O. Box 2232
Davidson, N.C. 28036

Gulton Industries, Inc. (1)
Metuchen, New Jersey 08840
Attn: Mr. S. Charlip

Electrochimica (1)
2485 Charleston Road
Mountain View, California 94040

Energy Storage & Conversion Dept. (1)
T.R.W. Systems
One Space Park
Redondo Beach, California 90278
Attn: Dr. H. P. Silverman

Sanders Associates Inc. (1)
24 Simon Street
Mail Stop NSI-2208
Nashua, New Hampshire 03060
Attn: J. Marshall

Power Conversion, Inc. (1)
70 MacQuesten Parkway
Mount Vernon, New York 10550
Attn: Stuart Chodosh